

資料 I-7 Iguidi地区、Taddart地区鉍石分析結果一覽表

No	Iguidi Sector			Iguidi Sector				Taddart Sector			
	Sample No.	Cu %	Ag g/t	No	Sample No.	Cu %	Ag g/t	No	Sample No.	Cu %	Ag g/t
1	P1	0.04	3.6	41	P41	2.48	0.5	1	a171	3.15	1.7
2	P2	2.70	4.0	42	P42	0.44	<0.3	2	a172	1.74	5.0
3	P3	1.60	5.2	43	P43	1.17	<0.3	3	a173	4.28	15.5
4	P4	1.24	3.6	44	P44	1.15	<0.3	4	a174	<0.01	2.3
5	P5	1.16	2.8	45	P45	0.69	<0.3	5	a178	7.00	114.0
6	P6	1.20	3.6	46	P46	0.92	<0.3	6	a179	4.81	26.0
7	P7	1.24	4.4	47	P47	0.44	0.5	7	a180	<0.01	1.0
8	P8	0.80	4.4	48	P48	2.51	1.3	8	a181	0.94	26.0
9	P9	1.20	5.2	49	P49	1.54	<0.3	9	a182	8.20	119.0
10	P10	1.12	4.0	50	P50	1.26	<0.3	10	a183	2.97	34.0
11	P11	2.20	4.8	51	P51	0.50	<0.3	11	a184	4.28	13.0
12	P12	0.62	2.8	52	P52	0.37	<0.3	12	a185	6.52	8.0
13	P13	1.00	2.8	53	P53	0.72	0.5	13	W31	2.36	13.0
14	P14	0.41	2.8	54	P54	1.08	<0.3	14	W32	0.20	2.3
15	P15	0.84	3.2	55	P55	0.81	<0.3	15	W33	0.71	2.5
16	P16	0.46	<0.3					16	W36	0.07	47.0
17	P17	0.23	<0.3					17	W37	1.83	21.3
18	P18	0.21	<0.3					18	W38	1.64	28.0
19	P19	1.48	<0.3					19	W39	2.30	42.0
20	P20	0.87	<0.3					20	W40	3.93	136.0
21	P21	0.74	<0.3					21	K60	0.13	0.8
22	P22	1.48	0.5					22	K61	0.01	0.3
23	P23	0.59	<0.3					23	K62	4.66	20.5
24	P24	0.39	<0.3					24	K63	0.43	0.5
25	P25	0.71	<0.3					25	K64	4.81	11.3
26	P26	1.00	0.3					26	K65	3.39	22.0
27	P27	0.09	<0.3					27	K66	2.97	9.8
28	P28	1.89	0.3					28	K67	1.74	2.3
29	P29	1.41	<0.3					29	K68	1.54	8.0
30	P30	2.70	1.9					30	K69	1.54	9.3
31	P31	0.44	<0.3					31	K70	<0.01	<0.3
32	P32	1.13	0.3					32	K71	<0.01	<0.3
33	P33	0.74	<0.3					33	K72	<0.01	20.3
34	P34	0.77	<0.3					34	K73	0.44	1.3
35	P35	2.04	<0.3					35	K74	1.64	13.0
36	P36	1.17	<0.3					36	K75	2.66	16.0
37	P37	4.18	0.3					37	K76	1.15	1.3
38	P38	0.98	<0.3					38	K77	2.00	3.3
39	P39	1.26	0.3					39	K78	4.00	42.5
40	P40	1.30	<0.3					40	K79	1.26	1.9

資料 I — 8 Agadir地区地化学探査試料化学分析結果一覽表

(1)

No.	Sample No.	Grade (ppm)			No.	Sample No.	Grade (ppm)		
		Cu	Mo	W			Cu	Mo	W
1	1- 0	25	<10	<5	50	5- 7	10	<10	<5
2	1- 1	40	<10	<5	51	5- 8	15	<10	<5
3	1- 2	15	<10	<5	52	5- 9	85	<10	<5
4	1- 3	15	<10	<5	53	5-10	15	<10	<5
5	1- 4	15	<10	<5	54	6- 1	10	<10	<5
6	1- 5	20	<10	<5	55	6- 2	25	<10	<5
7	1- 6	15	<10	<5	56	6- 3	45	<10	<5
8	1- 7	15	<10	<5	57	6- 4	<5	<10	<5
9	1- 8	15	<10	<5	58	6- 5	30	<10	<5
10	1- 9	45	<10	<5	59	6- 6	30	<10	<5
11	1-10	55	<10	<5	60	6- 7	30	<10	<5
12	2- 0	<5	<10	<5	61	6- 8	100	<10	<5
13	2- 1	10	<10	<5	62	6- 9	25	<10	<5
14	2- 2	10	<10	<5	63	6-10	35	<10	<5
15	2- 3	10	<10	<5	64	7- 1	10	<10	20
16	2- 4	25	<10	<5	65	7- 2	30	<10	<5
17	2- 5	90	<10	<5	66	7- 3	20	<10	<5
18	2- 6	10	<10	<5	67	7- 4	<5	<10	<5
19	2- 7	10	<10	<5	68	7- 5	10	<10	<5
20	2- 8	15	<10	<5	69	7- 6	45	<10	<5
21	2- 9	70	<10	<5	70	7- 7	<5	<10	<5
22	2-10	20	<10	<5	71	7- 8	10	<10	<5
23	3- 0	25	<10	<5	72	7- 9	<5	<10	<5
24	3- 1	120	<10	<5	73	7-10	30	<10	<5
25	3- 2	35	<10	<5	74	8- 1	15	<10	<5
26	3- 3	10	<10	<5	75	8- 2	10	<10	<5
27	3- 4	10	<10	<5	76	8- 3	4400	<10	700
28	3- 5	40	<10	<5	77	8- 4	10	<10	<5
29	3- 6	25	<10	<5	78	8- 5	15	<10	<5
30	3- 7	95	<10	<5	79	8- 6	15	<10	<5
31	3- 8	30	<10	<5	80	8- 7	50	<10	<5
32	3- 9	15	<10	<5	81	8- 8	15	<10	<5
33	3-10	<5	<10	<5	82	8- 9	35	<10	<5
34	4- 1	40	<10	<5	83	8-10	20	<10	<5
35	4- 2	15	<10	<5	84	9- 1	30	<10	<5
36	4- 3	95	<10	<5	85	9- 2	20	<10	<5
37	4- 4	20	<10	<5	86	9- 3	15	<10	<5
38	4- 5	10	<10	<5	87	9- 4	55	<10	<5
39	4- 6	30	<10	<5	88	9- 5	220	<10	16
40	4- 7	10	<10	<5	89	9- 6	210	<10	<5
41	4- 8	85	<10	<5	90	9- 7	75	<10	<5
42	4- 9	10	<10	<5	91	9- 8	25	<10	16
43	4-10	15	<10	<5	92	9- 9	25	<10	<5
44	5- 1	15	<10	<5	93	9-10	15	<10	<5
45	5- 2	10	<10	<5	94	10- 1	15	<10	<5
46	5- 3	<5	<10	<5	95	10- 2	35	<10	<5
47	5- 4	<5	<10	<5	96	10- 3	25	<10	40
48	5- 5	10	<10	<5	97	10- 4	25	<10	55
49	5- 6	75	<10	<5	98	10- 5	10	<10	<5

(2)

No.	Sample No.	Grade (ppm)			No.	Sample No.	Grade (ppm)		
		Cu	Mo	W			Cu	Mo	W
99	10- 6	<5	<10	<5	151	15- 8	10	<10	<5
100	10- 7	345	<10	<5	152	15- 9	<5	<10	<5
101	10- 8	20	<10	<5	153	15-10	<5	<10	<5
102	10- 9	10	<10	<5	154	16- 1	10	<10	<5
103	10-10	10	<10	<5	155	16- 2	15	<10	<5
104	11- 1	20	<10	<5	156	16- 3	15	<10	<5
105	11- 2	15	<10	<5	157	16- 4	10	<10	<5
106	11- 3	265	<10	<5	158	16- 5	15	<10	<5
107	11- 4	15	<10	<5	159	16- 6	10	<10	<5
108	11- 5	10	<10	<5	160	16- 7	<5	<10	<5
109	11- 6	10	<10	<5	161	16- 8	25	<10	<5
110	11- 7	15	<10	<5	162	16- 9	10	<10	<5
111	11- 8	25	<10	<5	163	16-10	15	<10	<5
112	11- 9	30	<10	100	164	17- 1	10	<10	<5
113	11-10	30	<10	<5	165	17- 2	25	<10	<5
114	12- 1	10	<10	12	166	17- 3	115	<10	1400
115	12- 2	15	<10	<5	167	17- 4	<5	<10	<5
116	12- 3	125	<10	<5	168	17- 5	25	<10	<5
117	12- 4	25	<10	<5	169	17- 6	170	<10	<5
118	12- 5	10	<10	<5	170	17- 7	15	<10	<5
119	12- 6	10	<10	40	171	18- 1	<5	<10	<5
120	12- 7	55	20	140	172	18- 2	<5	<10	<5
121	12- 8	<5	<10	<5	173	18- 3	15	<10	<5
122	12- 9	10	<10	<5	174	18- 4	10	<10	<5
123	12-10	<5	<10	<5	175	18- 5	20	<10	<5
124	13- 1	<5	<10	<5	176	17- 6	15	<10	<5
125	13- 2	15	<10	<5	177	18- 7	180	<10	<5
126	13- 3	45	<10	<5	178	18- 8	25	<10	<5
127	13- 4	85	<10	<5	179	18- 9	20	<10	<5
128	13- 5	18	<10	<5	180	18-10	10	<10	<5
129	13- 6	<5	<10	16	181	19- 1	35	<10	32
130	13- 7	15	<10	12	182	19- 2	190	<10	20
131	13- 8	45	<10	<5	183	19- 3	20	<10	<5
132	13- 9	190	<10	8	184	19- 4	105	<10	<5
133	13-10	80	<10	<5	185	19- 5	560	<10	<5
134	14- 1	<5	<10	<5	186	19- 6	20	<10	<5
135	14- 2	<5	<10	<5	187	19- 7	95	<10	<5
136	14- 3	10	<10	<5	188	19- 8	15	<10	<5
137	14- 4	<5	<10	<5	189	19- 9	15	<10	<5
138	14- 5	<5	<10	<5	190	19-10	20	<10	<5
139	14- 6	10	<10	<5	191	20- 1	55	<10	36
140	14- 7	205	<10	<5	192	20- 2	30	<10	<5
141	14- 8	30	<10	<5	193	20- 3	15	<10	34
142	14- 9	30	<10	<5	194	20- 4	75	<10	20
143	14-10	10	<10	<5	195	20- 5	55	<10	<5
144	15- 1	2650	30	400	196	20- 6	15	<10	<5
145	15- 2	<5	<10	<5	197	20- 7	55	<10	24
146	15- 3	15	<10	<5	198	20- 8	15	<10	<5
147	15- 4	25	<10	<5	199	20- 9	40	<10	<5
148	15- 5	50	<10	<5	200	20-10	65	<10	<5
149	15- 6	15	<10	<5	201	21- 1	30	<10	<5
150	15- 7	<5	<10	<5	202	21- 2	<5	<10	<5

No.	Sample No.	Grade (ppm)			No.	Sample No.	Grade (ppm)		
		Cu	Mo	W			Cu	Mo	W
203	21- 3	<5	<10	<5	254	26- 1	10	<10	<5
204	21- 4	<5	<10	<5	255	26- 2	30	<10	<5
205	21- 5	<5	<10	<5	256	26- 3	<5	<10	30
206	21- 6	<5	<10	<5	257	26- 4	410	30	88
207	21- 7	<5	<10	<5	258	26- 5	<5	<10	8
208	21- 8	385	<10	<5	259	26- 6	25	<10	<5
209	21- 9	15	<10	<5	260	26- 7	<5	<10	8
210	21-10	30	<10	<5	261	26- 8	155	<10	<5
211	22- 1	15	<10	<5	262	26- 9	<5	<10	<5
212	22- 2	15	<10	18	263	26-10	<5	<10	<5
213	22- 3	<5	<10	8	264	27- 0	175	<10	<5
214	22- 4	45	<10	<5	265	27- 1	60	410	<5
215	22- 5	40	<10	<5	266	27- 2	2250	50	<5
216	22- 6	40	<10	<5	267	27- 3	<5	<10	<5
217	22- 7	15	<10	<5	268	27- 4	<5	<10	20
218	22- 8	35	<10	<5	269	27- 5	210	<10	<5
219	22- 9	15	<10	<5	270	27- 6	55	<10	<5
220	22-10	65	<10	<5	271	27- 7	465	<10	<5
221	23- 1	<5	<10	<5	272	27- 8	105	<10	<5
222	23- 2	225	<10	<5	273	27- 9	100	<10	<5
223	23- 3	<5	<10	<5	274	27-10	<5	<10	8
224	23- 4	<5	<10	<5	275	28- 1	<5	<10	<5
225	23- 5	10	<10	<5	276	28- 2	285	<10	<5
226	23- 6	<5	<10	10	277	28- 3	<5	<10	<5
227	23- 7	<5	<10	8	278	28- 4	600	<10	<5
228	23- 8	1200	<10	<5	279	28- 5	70	<10	<5
229	23- 9	<5	<10	<5	280	28- 6	55	<10	<5
230	23-10	<5	<10	<5	281	28- 7	65	<10	8
231	24- 0	<5	<10	<5	282	28- 8	45	<10	20
232	24- 1	<5	<10	<5	283	28- 9	<5	<10	<5
233	24- 2	<5	<10	<5	284	28-10	75	<10	<5
234	24- 3	<5	<10	<5	285	29- 1	<5	<10	<5
235	24- 4	10	<10	<5	286	29- 2	35	<10	18
236	24- 5	<5	<10	<5	287	29- 3	15	<10	<5
237	24- 6	<5	<10	<5	288	29- 4	<5	<10	<5
238	24- 7	<5	<10	8	289	29- 5	40	<10	<5
239	24- 8	<5	<10	<5	290	29- 6	50	<10	<5
240	24- 9	<5	<10	<5	291	29- 7	190	<10	<5
241	24-10	10	<10	22	292	29- 8	10	<10	<5
242	25- 0	<5	<10	<5	293	29- 9	30	<10	<5
243	25- 1	15	<10	<5	294	29-10	10	<10	<5
244	25- 2	<5	<10	<5	295	30- 1	10	<10	<5
245	25- 3	45	<10	<5	296	30- 2	55	<10	<5
246	25- 4	85	<10	<5	297	30- 3	55	<10	<5
247	25- 5	<5	<10	<5	298	30- 4	50	<10	<5
248	25- 6	<5	<10	10	299	30- 5	225	<10	<5
249	25- 7	<5	<10	<5	300	30- 6	470	<10	<5
250	25- 8	<5	<10	<5	301	30- 7	15	<10	<5
251	25- 9	<5	<10	<5	302	30- 8	85	<10	<5
252	25-10	10	<10	<5	303	30- 9	60	<10	<5
253	26- 0	30	<10	<5	304	30-10	10	<10	<5



資料 I — 9 Iguidi地区地化学探査試料化学分析結果一覽表

(1)

No.	Sample No.	Cu ppm	Ag ppm	No.	Sample No.	Cu ppm	Ag ppm
1	H1-1	6400	<0.4	48	H17-1	51	<0.4
2	H1-2	13400	<0.4	49	H17-2	20	<0.4
3	H1-3	6400	<0.4	50	H17-3	10	<0.4
4	H2-1	1900	<0.4	51	H18-1	28	<0.4
5	H2-2	2700	<0.4	52	H18-2	63	<0.4
6	H3-1	390	0.4	53	H18-3	23	<0.4
7	H3-2	3750	<0.4	54	H19-1	22	<0.4
8	H4-1	300	<0.4	55	H19-2	27	<0.4
9	H4-2	1040	<0.4	56	H19-3	140	<0.4
10	H4-3	480	<0.4	57	H20-1	23	<0.4
11	H5-1	80	<0.4	58	H20-2	31	<0.4
12	H5-2	300	<0.4	59	H20-3	15	<0.4
13	H5-3	26	<0.4	60	H21-1	20	<0.4
14	H5-4	60	<0.4	61	H21-2	46	<0.4
15	H6-1	260	<0.4	62	H21-3	88	<0.4
16	H6-2	2800	<0.4	63	H22-1	114	0.8
17	H6-3	2250	<0.4	64	H22-2	86	<0.4
18	H6-4	2350	1.0	65	H22-3	60	<0.4
19	H7-1	33	<0.4	66	H23-1	54	0.4
20	H7-2	1650	<0.4	67	H24-1	500	<0.4
21	H7-3	2050	<0.4	68	H24-2	700	<0.4
22	H7-4	1600	<0.4	69	H24-3	240	<0.4
23	H8-1	100	<0.4	70	H25-1	124	<0.4
24	H8-2	81	<0.4	71	H25-2	54	<0.4
25	H8-3	700	1.4	72	H25-3	180	<0.4
26	H8-4	2700	0.8	73	H26-1	112	<0.4
27	H9-1	30	2.8	74	H26-2	98	<0.4
28	H9-2	230	1.2	75	H26-3	54	<0.4
29	H9-3	290	<0.4	76	H27-1	30	<0.4
30	H9-4	120	<0.4	77	H27-2	78	<0.4
31	H10-1	34	<0.4	78	H27-3	106	<0.4
32	H10-2	740	<0.4	79	H28-1	82	<0.4
33	H10-3	1600	<0.4	80	H28-2	44	<0.4
34	H11-1	250	<0.4	81	H28-3	84	<0.4
35	H11-2	59000	<0.4	82	H29-1	162	<0.4
36	H12-1	33	<0.4	83	H29-2	62	<0.4
37	H12-2	51	<0.4	84	H29-3	86	<0.4
38	H13-1	53	<0.4	85	H30-1	68	<0.4
39	H13-2	80	0.4	86	H30-2	16	<0.4
40	H14-1	31	<0.4	87	H30-3	98	<0.4
41	H14-2	25	<0.4	88	H31-1	90	<0.4
42	H15-1	29	<0.4	89	H31-2	180	<0.4
43	H15-2	40	<0.4	90	H31-3	66	<0.4
44	H15-3	44	<0.4	91	H32-1	42	<0.4
45	H16-1	15	<0.4	92	H32-2	44	<0.4
46	H16-2	20	<0.4	93	H32-3	150	<0.4
47	H16-3	14	<0.4	94	H33-1	58	2.0

(2)

No.	Sample No.	Cu ppm	Ag ppm	No.	Sample No.	Cu ppm	Ag ppm
95	H33-2	88	2.4	142	K16-1	1320	0.4
96	H33-3	24	3.6	143	K16-2	380	0.8
97	K1-1	4400	1.2	144	K16-3	3300	0.8
98	K1-2	11600	4.8	145	K17-1	300	1.2
99	K1-3	10400	1.2	146	K17-2	196	0.8
100	K2-1	6600	1.2	147	K17-3	2400	0.8
101	K2-2	4300	1.6	148	K18-1	106	1.2
102	K2-3	15600	3.2	149	K18-2	38	0.4
103	K3-1	1220	<0.4	150	K18-3	132	0.4
104	K3-2	6600	<0.4	151	K19-1	1780	0.4
105	K3-3	660	<0.4	152	K19-2	3200	0.8
106	K4-1	360	<0.4	153	K19-3	620	0.4
107	K4-2	28	0.8	154	K20-1	2360	0.4
108	K4-3	58	0.4	155	K20-2	1440	0.8
109	K5-1	860	0.4	156	K20-3	80	0.8
110	K5-2	960	0.4	157	K21-1	260	0.8
111	K5-3	16400	0.4	158	K21-2	80	<0.4
112	K6-1	102	0.4	159	K21-3	420	<0.4
113	K6-2	44	0.4	160	K22-1	2240	<0.4
114	K6-3	2400	0.4	161	K22-2	480	1.2
115	K7-1	260	0.4	162	K22-3	960	<0.4
116	K7-2	1180	0.4	163	K23-1	9600	<0.4
117	K7-3	780	0.4	164	K23-2	1700	<0.4
118	K8-1	560	0.4	165	K23-3	80	0.8
119	K8-2	70	0.4	166	K23-4	134	0.4
120	K8-3	1500	0.4	167	K23-5	380	0.4
121	K9-1	640	0.4	168	K23-6	8600	0.4
122	K9-2	340	0.4	169	K24-1	900	0.8
123	K9-3	440	0.4	170	K24-2	132	<0.4
124	K10-1	1200	0.4	171	K24-3	260	<0.4
125	K10-2	21000	0.4	172	K25-1	6800	<0.4
126	K10-3	82000	1.2	173	K25-2	1320	0.4
127	K11-1	6800	1.2	174	K25-3	860	0.4
128	K11-2	900	0.8	175	K26-1	1580	0.8
129	K11-3	1080	<0.4	176	K26-2	1680	0.4
130	K12-1	1760	0.4	177	K26-3	620	0.4
131	K12-2	280	0.4	178	K27-1	160	0.4
132	K12-3	960	0.4	179	K27-2	240	0.8
133	K13-1	6000	0.4	180	K27-3	196	0.4
134	K13-2	1660	2.0	181	K28-1	540	<0.4
135	K13-3	2500	0.8	182	K28-2	360	<0.4
136	K14-1	3800	<0.4	183	K28-3	380	0.8
137	K14-2	340	1.2	184	K29-1	2160	0.4
138	K14-3	900	0.8	185	K29-2	600	4.8
139	K15-1	1160	0.4	186	K29-3	500	<0.4
140	K15-2	48	0.8	187	K30-1	900	1.2
141	K15-3	820	1.2	188	K30-2	420	0.4

(3)

No.	Sample No.	Cu ppm	Ag ppm	No.	Sample No.	Cu ppm	Ag ppm
189	K30-3	116	0.8				
190	K31-1	1380	0.8				
191	K31-2	960	0.4				
192	K31-3	1880	0.8				
193	K32-1	1360	0.8				
194	K32-2	600	0.4				
195	K32-3	3300	0.8				
196	K33-1	5100	0.4				
197	K33-2	2600	0.4				
198	K33-3	17000	0.8				
199	K34-1	440	1.2				
200	K34-2	4800	<0.4				
201	K34-3	2700	<0.4				
202	K35-1	150	<0.4				
203	K35-2	200	0.4				
204	K35-3	1500	<0.4				
205	K36-1	470	<0.4				
206	K36-2	140	1.0				
207	K36-3	89	0.6				
208	K37-1	76	0.4				
209	K37-2	39	<0.4				
210	K37-3	28	0.4				
211	K38-1	20500	0.4				
212	K38-2	14000	0.8				
213	K38-3	7000	1.0				
214	K39-1	11200	0.6				
215	K39-2	10400	0.4				
216	K39-3	25000	0.4				
217	K40-1	28000	0.6				
218	K40-2	1040	0.4				
219	K40-3	34000	0.4				
220	K41-1	370	0.4				
221	K41-2	210	0.4				
222	K41-3	4000	0.4				
223	K42-1	270	<0.4				
224	K42-2	230	<0.4				
225	K42-3	680	<0.4				
226	K43-1	330	<0.4				
227	K43-2	90	<0.4				





資料 I — 10 Taddart地区地化学探査試料化学分析結果一覽表

(1)

No.	Sample No.	Cu ppm	Ag ppm	No.	Sample No.	Cu ppm	Ag ppm
1	E-01	99	0.1	51	E-60	5500	0.3
2	E-02	176	0.1	52	E-61	250	0.1
3	E-03	29400	23.0	53	F-01	18	0.1
4	E-04	227	0.2	54	F-02	7	0.1
5	E-05	8390	9.6	55	F-03	3000	0.1
6	E-06	350	0.2	56	F-04	100	0.1
7	E-07	3130	3.1	57	F-05	398	0.9
8	E-08	7330	8.2	58	F-06	8000	4.8
9	E-09	770	0.5	59	F-07	65	0.1
10	E-10	1760	0.1	60	F-08	29000	62.0
11	E-11	3000	0.1	61	F-09	75	0.1
12	E-12	845	0.1	62	F-10	37	0.1
13	E-13	2120	2.1	63	F-11	130	0.5
14	E-14	135	0.1	64	F-12	30	0.1
15	E-18	20	0.1	65	F-13	360	0.1
16	E-21	71	0.1	66	F-14	50	0.1
17	E-22	1070	30.0	67	F-15	610	0.4
18	E-27	2080	0.6	68	F-16	48	0.1
19	E-28	20	0.1	69	F-17	24	0.1
20	E-29	23	0.1	70	F-18	53	0.1
21	E-30	1390	2.2	71	F-19	4850	3.9
22	E-31	39	0.1	72	F-20	50	0.2
23	E-32	31	0.1	73	F-21	200	0.1
24	E-33	165	0.1	74	F-22	214	0.1
25	E-34	100	0.1	75	F-23	32	0.1
26	E-35	330	0.1	76	F-24	20	0.1
27	E-36	75	0.1	77	F-25	13700	5.8
28	E-37	125	0.1	78	F-26	1280	3.2
29	E-38	7640	1.1	79	F-27	500	0.1
30	E-39	40700	11.1	80	F-28	358	0.2
31	E-40	29000	9.1	81	F-29	115	0.1
32	E-41	63	0.1	82	F-30	29	0.1
33	E-42	515	0.1	83	F-31	18	0.1
34	F-43	191	0.1	84	F-32	12	0.1
35	E-44	26	0.1	85	F-33	17	0.1
36	E-45	135	0.1	86	F-34	9200	3.9
37	E-46	3170	1.8	87	F-35	53	0.1
38	E-47	126	0.1	88	F-36	11100	0.1
39	E-48	15700	14.2	89	F-37	1430	0.6
40	E-49	1780	1.2	90	F-38	3000	1.1
41	E-50	3930	4.2	91	F-39	18	0.1
42	E-51	125	0.1	92	F-40	3500	0.1
43	E-52	15500	13.8	93	F-41	455	0.1
44	E-53	51	0.1	94	F-42	18	0.1
45	E-54	16	0.1	95	F-43	37	0.1
46	E-55	6700	6.1	96	F-44	30	0.1
47	E-56	790	3.2	97	F-45	44	0.1
48	E-57	20400	20.0	98	F-46	100	0.1
49	E-58	6500	1.2	99	F-47	10	0.1
50	E-59	500	0.1	100	F-48	78	0.1

(2)

No.	Sample No.	Cu ppm	Ag ppm				
101	F-49	39	0.1				
102	F-50	500	0.1				
103	F-51	54	0.1				
104	F-52	115	0.1				
105	F-53	19	0.1				
106	F-54	230	0.1				
107	F-55	22	0.1				
108	F-56	19	0.1				
109	F-57	800	0.2				
110	F-58	23	0.4				
111	F-59	162	0.1				
112	F-60	30	0.2				
113	F-61	10	0.1				
114	F-62	60	0.1				
115	F-63	85	0.1				
116	F-64	1200	24.0				
117	F-65	17700	6.7				
118	F-66	100	0.1				
119	F-67	150	0.5				
120	F-68	130	0.1				
121	F-69	2600	1.9				
122	F-70	50	0.1				
123	F-71	168	0.1				
124	F-72	880	0.6				
125	F-73	1450	0.9				
126	F-74	30	0.1				
127	G-01	220	0.6				
128	G-03	2500	0.1				
129	G-07	540	0.1				
130	G-14	500	0.1				
131	G-17	78	0.2				
132	G-20	230	0.2				
133	G-21	14200	22.0				
134	G-23	4500	3.8				
135	G-24	1930	0.8				
136	G-25	50	0.3				
137	G-26	332	0.1				
138	G-28	28	0.1				
139	G-30	6800	2.9				
140	G-31	160	0.2				
141	G-32	28	0.1				
142	G-36	1700	3.8				
143	G-38	128	0.2				
144	G-43	10	0.1				
145	G-45	33	0.1				
146	G-48	39	0.1				
147	G-50	64	0.1				
148	G-66	440	0.6				







JICA