

Taylor, S.R., 1964. Abundance of chemical elements in the continental crust: a new table. *Geochim. Cosmochim. Acta*, 28, 1273-1285.

Tischendorf, G., 1977. Geochemical and petrographic characteristics of silic magmatic rocks associated with rare element mineralization. *G.S. of Czechoslovakia*, 2, 41-96.

White, A.J.R., 1979. Mantle source type granite. *G.S.A., Abstr.*, 11, 539.

White, A.J.R. and Chappell, B.W., 1977. Ultrametamorphism and granitoid genesis. *Tectonophy.*, 43, 7-22.

# APPENDICES



付表2 鉍石研磨薄片鑑定結果一覽表

(1)

試料番号	採取位置	錫石	モナズ石	有機イットリウム鉍	ポリクレース	銳錐石	ジルコン	チタン鉄鉍	チタン石	ザクロ石	電気石	石英	カリ長石	斜長石	摘要
1	AAK-01 A-1 area, AA5111	◎	◇					◎		○	◇	○	◇	◇	
2	AAK-05 A-1 area, AA3413	◇	◇	?			◇	◎			○	◎	◇		
3	AAM-06 A-1 area, AAC904	◇	◇		◇		○	◎	◇		◇	○	◇	◇	
4	AAM-07 A-1 area, AA1206	◇	◇		◇		○	◎	◇		○	○	◇	◇	円磨度良
5	AAM-09 A-1 area, AA1812		◇		○		○	◎	◇		○	◇	◇	◇	
6	ABM-03 A-2 area, AB2702	◇	○		◇		○	◎		◇		◇	◇	◇	
7	ABT-02 A-2 area, AB2511	○	○		○		◎	○				◇	◇	◇	非常に細粒
8	ABT-04 A-2 area, AB3414	◇	○		○		◎	○			◇	◇	◇	◇	細粒・円磨度良
9	BAT-03 B-1 area, BA0606	◇	○				○	○			◇	◇	◇	◇	
10	BBM-01 B-2 area, BB0705	◇	○				◇	◎				○	○	○	
11	BCP-03 B-3 area, BC0810	◎	◇				○	○				◇	◇	◇	
12	BDI-07 B-4 area, BD0107	◇	○				○	◎				○	○	○	
13	BDI-09 B-4 area, BD0412	◎					○	◎				◇			
14	CAI-12 C area, CA0315	○	○				◎	◇			◇	◇	◇	◇	細粒・円磨度良

◎：多量， ○：中量， ◇：少量

付表2 鉍石研磨薄片鑑定結果一覧表

(2)

試料番号	採取位置	錫石	モナズ石	有機イットリウム鉍	ポリクレータ	鋭錐石	ジルコロン	チタン鉄鉍	チタン石	ザクロ石	電気石英	石英	カリ長石	斜長石	摘要
15	DAI-02 D-1 area, DA2302		◎				◎	◎				◇	◇	◇	
16	DAM-02 D-1 area, DA1113	◇	◎				○	○			◇	◇	◇		
17	DAM-03 D-1 area, DA1712	◇	◎				◎	◇			◇	◇	◇		
18	DBI-03 D-2 area, DB1001	◇	◇				◇	◎				○	◇		
19	DBI-04 D-2 area, DB1009		○				◎	○			○	○	◇		
20	DBI-06 D-2 area, DB0807		○				◇	◎			○	◇	◇		
21	DBM-05 D-2 area, DB0503		○				○	◎			○	◇	◇		
22	DBP-08 D-2 area, DB0601		◎					◎			◎	○	○	◇	

◎：多量， ○：中量， ◇：少量

付表3 X線解析試験結果一覧表

試料番号	採取位置	石	斜	カ	白	カ	イ	黄	摘 要
		英	長	リ	雲	オ	ラ	鉄	
		石	石	長	母	リ	イ	鉱	
1	X-01	A-2 area, AB0409-AB0508	○	・	・	・			
2	X-02	A-2 area, AB0507	◎	・	・	・			
3	X-03	A-2 area, AB0508	◎	・	・	・	○		
4	X-04	A-2 area, AB0409	◎	・	・	・		・	
5	X-05	A-2 area, AB1215	◎	・	・	・		・	
6	X-06	A-2 area, AB2910	◎		・	・			
7	X-07	A-2 area, AB2211	◎			・	○		
8	X-08	B-1 area, BA1501	◎			・	○		
9	X-09	C area, CA0713	◎			・	○		
10	X-10	D-1 area, DA1909	◎				○		
11	X-11	C area, CA1119	◎			・	○		

◎： 多量，      ○： 中量，      ・： 少量

附表4 土壤地化学試料分析値一覽表

(1)

NO	SP.No. unit	Sn	W	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1	AA0601	20	8	5	42	300	0.7	130	91	16.0	2.4	120	16.0	67	14.9	11.0	<20	7.97	1.08
2	AA0602	28	8	5	38	240	0.5	100	61	13.0	1.7	110	14.0	50	10.0	8.3	<20	6.77	0.89
3	AA0603	8	<4	2	19	120	0.5	35	21	4.1	0.6	51	5.5	20	1.5	3.0	<20	3.32	0.50
4	AA0604	<5	<4	<1	17	65	0.3	20	15	3.5	<0.5	30	3.7	22	3.8	2.8	<20	3.24	0.49
5	AA0605	11	5	2	20	110	0.6	40	23	4.9	<0.5	44	5.1	18	3.9	4.4	<20	3.70	0.57
6	AA0606	<5	<4	2	19	150	1.0	42	26	5.3	0.8	34	2.6	21	5.1	4.4	<20	3.98	0.52
7	AA0701	26	11	5	38	270	0.9	140	82	19.0	2.2	120	16.0	66	16.0	13.0	20	6.81	0.94
8	AA0702	26	8	4	42	280	0.7	130	72	17.0	2.2	120	17.0	60	15.2	12.0	20	8.20	1.11
9	AA0703	<5	<4	2	19	94	0.6	33	20	4.1	0.6	41	5.4	19	3.1	3.3	<20	3.20	0.45
10	AA0704	6	<4	1	21	71	0.4	29	15	3.4	0.6	35	5.6	21	4.7	2.9	<20	3.32	0.43
11	AA0705	6	<4	2	24	170	0.7	63	39	7.0	0.9	56	9.2	34	6.2	5.5	<20	4.69	0.64
12	AA0706	8	<4	3	28	160	0.5	60	34	8.0	1.3	66	8.0	36	7.7	6.7	<20	5.80	0.75
13	AA0804	19	10	1	12	32	0.4	16	7	1.7	<0.5	14	2.4	14	2.8	2.1	<20	2.46	0.38
14	AA0805	<5	<4	2	18	120	0.7	39	23	5.1	0.7	35	4.0	24	3.4	3.3	<20	3.67	0.55
15	AA0806	18	<4	5	37	280	0.7	130	74	17.0	2.0	120	13.0	64	15.2	11.0	<20	8.12	1.07
16	AA0807	22	<4	4	37	250	0.6	110	53	14.0	1.8	110	14.0	56	13.2	11.0	<20	7.64	1.03
17	AA0808	28	<4	4	41	280	0.6	120	65	15.0	2.0	110	15.0	65	14.0	12.0	<20	7.23	1.04
18	AA0809	26	<4	6	41	290	0.7	140	85	18.0	3.0	110	17.0	77	16.3	13.0	<20	9.00	1.26
19	AA0810	35	9	4	42	280	0.9	130	78	17.0	2.7	120	17.0	65	14.6	13.0	<20	9.01	1.14
20	AA0901	15	<4	4	46	260	0.6	130	74	15.0	1.9	140	8.7	38	12.7	7.3	25	4.72	0.58
21	AA0902	19	<4	5	53	410	0.5	190	118	28.0	2.4	170	13.0	50	12.9	10.0	<20	6.38	0.74
22	AA0903	16	<4	4	46	370	0.6	170	108	21.0	2.3	160	14.0	59	15.2	13.0	25	6.70	0.87
23	AA0904	38	<4	4	47	330	0.6	140	73	17.0	2.2	130	13.0	70	14.4	10.0	27	6.03	0.76
24	AA0905	<5	<4	4	43	310	0.4	160	95	19.0	2.0	130	10.0	114	19.8	13.0	25	7.22	0.98
25	AA0906	<5	11	3	56	290	0.6	140	85	17.0	2.8	120	11.0	96	17.8	13.0	23	6.88	0.88
26	AA0907	130	8	4	29	270	0.7	120	62	15.0	2.3	110	15.0	63	13.0	11.0	27	7.83	1.06
27	AA0908	27	8	4	40	290	0.5	130	74	16.0	2.6	130	16.0	66	15.0	11.0	26	7.12	0.93
28	AA0909	27	8	4	40	280	0.6	130	68	17.0	2.6	120	16.0	61	15.4	12.0	22	8.43	1.14
29	AA1001	<5	9	1	49	360	0.9	190	120	23.0	2.0	150	12.0	96	16.2	12.0	26	7.01	0.92
30	AA1002	16	<4	4	44	330	0.8	170	99	20.0	2.5	130	12.0	56	15.1	10.0	25	5.53	0.69
31	AA1003	12	<4	3	44	430	0.8	210	130	26.0	3.2	170	13.0	69	22.9	14.0	25	7.00	0.96
32	AA1004	17	6	4	44	390	0.9	210	110	25.0	2.9	170	17.0	65	19.8	12.0	33	7.23	0.93
33	AA1005	13	6	4	46	400	0.4	200	120	23.0	2.0	180	18.0	58	16.7	11.0	<20	6.21	0.79
34	AA1006	23	<4	4	47	460	1.1	240	130	28.0	2.9	200	22.0	59	20.1	12.0	25	6.92	0.91
35	AA1007	15	<4	4	34	330	0.9	180	110	23.0	3.3	150	17.0	71	13.2	15.0	<20	8.75	1.19
36	AA1101	18	<4	4	42	280	0.8	130	74	16.0	2.1	120	11.0	49	11.1	10.0	<20	5.68	0.71
37	AA1102	10	<4	4	39	310	1.0	160	98	19.0	1.8	130	9.5	52	13.2	8.9	<20	5.74	0.72
38	AA1103	21	<4	3	29	210	0.8	120	70	15.0	1.7	88	9.3	52	9.1	11.0	<20	6.11	0.69
39	AA1104	9	<4	3	33	210	0.9	180	61	13.0	2.2	87	9.3	49	9.5	8.0	<20	5.61	0.74
40	AA1105	12	<4	4	44	390	0.4	210	130	26.0	2.6	180	16.0	63	17.6	12.0	<20	7.18	0.86
41	AA1106	17	<4	4	39	410	1.0	180	100	22.0	3.5	160	20.0	61	15.8	13.0	<20	8.69	1.15
42	AA1201	24	9	3	29	200	1.1	110	63	14.0	1.7	75	11.0	54	9.1	8.8	<20	5.72	0.83
43	AA1202	12	<4	3	32	210	0.7	110	65	14.0	1.8	92	10.0	46	9.6	11.0	<20	5.99	0.83
44	AA1203	23	7	4	45	310	0.6	150	85	18.0	2.1	130	13.0	58	13.0	9.9	<20	6.24	0.72
45	AA1204	25	<4	3	32	210	1.2	120	70	16.0	1.5	88	8.0	58	12.8	11.0	<20	7.15	0.95
46	AA1205	28	<4	3	43	290	1.3	160	100	22.0	2.8	130	15.0	62	10.7	13.0	<20	7.28	0.86
47	AA1206	21	9	4	37	240	0.6	110	58	13.0	1.3	100	14.0	47	6.5	8.4	<20	5.18	0.63
48	AA1301	19	9	3	40	210	0.8	91	49	12.0	2.0	82	14.0	58	9.5	10.0	<20	6.45	0.87
49	AA1302	12	8	4	43	180	0.3	89	55	11.0	1.1	95	12.0	42	9.8	6.7	<20	4.77	0.59
50	AA1303	11	<4	3	40	190	0.9	89	59	12.0	1.4	86	15.0	56	10.1	10.0	24	5.53	0.76
51	AA1304	21	<4	3	39	190	0.7	99	58	13.0	1.9	81	17.0	70	8.4	11.0	<20	6.46	0.82
52	AA1305	12	<4	3	35	210	1.0	110	67	15.0	1.8	86	15.0	59	10.9	11.0	<20	7.01	0.93
53	AA1306	7	<4	4	33	310	1.2	170	100	21.0	2.4	130	19.0	50	14.0	11.0	<20	9.89	1.11
54	AA1401	11	8	3	39	170	0.7	84	49	12.0	2.0	83	9.3	46	10.4	10.0	<20	5.98	0.75
55	AA1402	15	9	4	38	200	0.8	99	62	14.0	1.4	88	14.0	65	13.2	12.0	<20	7.94	1.00
56	AA1403	11	11	3	34	190	1.0	100	59	14.0	2.1	82	15.0	63	13.0	11.0	<20	7.18	0.93
57	AA1404	18	<4	3	40	200	0.7	90	61	12.0	2.0	80	15.0	56	9.6	10.0	<20	6.29	0.86
58	AA1501	32	7	7	51	200	1.3	110	64	16.0	2.1	110	12.0	57	11.0	13.0	28	7.59	0.92
59	AA1502	25	8	6	52	200	0.5	100	60	14.0	1.9	110	11.0	54	10.5	13.0	<20	9.42	1.30
60	AA1503	29	8	5	45	130	0.6	57	25	6.7	1.3	140	20.0	59	5.4	10.0	<20	8.26	1.02
61	AA1504	14	7	3	32	210	0.8	110	67	15.0	2.3	85	22.0	62	10.2	11.0	<20	7.93	1.11
62	AA1505	13	<4	3	37	290	1.1	160	95	22.0	3.5	120	19.0	88	18.3	15.0	<20	8.67	1.11
63	AA1601	33	12	7	54	290	0.7	120	74	16.0	3.1	120	19.0	111	15.5	16.0	<20	10.60	1.51
64	AA1602	34	9	7	51	310	0.8	160	96	21.0	4.0	140	29.0	112	19.9	21.0	<20	13.70	1.77
65	AA1603	31	12	6	49	290	0.8	150	87	20.0	3.6	130	25.0	114	17.5	20.0	25	13.40	1.67
66	AA1604	37	<4	8	51	270	0.9	140	80	19.0	3.5	120	24.0	138	17.3	14.0	<20	11.10	1.43
67	AA1605	9	8	4	32	200	1.1	100	63	14.0	1.8	82	11.0	55	9.8	9.5	<20	6.89	1.08
68	AA1606	<5	<4	1	24	140	1.1	67	37	9.2	0.9	46	5.1	46	7.1	7.4	<20	5.05	0.67
69	AA1701	26	11	6	52	250	0.8	120	74	17.0	3.3	110	12.0	99	14.0	14.0	25	8.87	1.19
70	AA1702	33	10	5	49	220	1.1	98	72	17.0	2.4	93	16.0	86	14.8	13.0	<20	8.06	1.18
71	AA1703	34	9	6	52	230	1.4	120	79	22.0	3.1	96	15.0	96	16.3	16.0	<20	9.80	1.33
72	AA1704	36	10	5	51	250	1.0	120	94	22.0	3.0	100	16.0	104	15.8	16.0	30	10.30	1.39
73	AA1705	36	10	5	52	280	1.1	110	65	18.0	2.5	110	19.0						

附表4 土壤地化学試料分析値一覽表

(2)

NO	SP.No.	Sn	H	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
94	AA1910	25	10	5	49	230	0.9	95	62	16.0	2.5	83	13.0	82	11.8	13.0	<20	9.00	1.23
95	AA1911	20	9	6	49	240	1.0	100	75	17.0	1.7	88	17.0	87	15.3	14.0	<20	9.40	1.21
96	AA1912	40	<4	6	62	270	0.0	130	64	19.0	2.6	110	22.0	84	16.4	17.0	<20	10.50	1.35
97	AA1913	20	<4	5	39	320	0.0	160	120	24.0	3.0	130	17.0	116	13.8	14.0	23	0.53	1.23
98	AA1914	7	<4	3	34	290	0.6	150	100	21.0	2.7	110	17.0	70	14.7	15.0	<20	10.80	1.40
99	AA2001	24	<4	2	27	72	0.2	20	<5	2.5	1.1	39	9.3	20	1.4	3.2	<20	3.43	0.44
100	AA2002	8	9	1	24	80	0.4	21	9	2.8	0.9	34	8.7	24	2.5	4.3	<20	3.52	0.55
101	AA2003	21	12	4	35	170	0.7	77	52	11.0	1.7	71	11.0	60	10.1	9.1	<20	7.35	1.02
102	AA2004	24	8	5	42	230	0.9	110	38	16.0	2.0	93	11.0	84	13.9	16.0	<20	10.40	1.47
103	AA2005	33	10	5	50	250	0.7	110	67	17.0	3.7	110	12.0	174	14.3	20.0	<20	13.10	1.75
104	AA2006	13	8	3	32	220	0.6	100	57	16.0	2.1	77	13.0	100	10.3	14.0	<20	11.10	1.49
105	AA2007	21	10	3	43	220	0.3	100	36	15.0	3.0	85	14.0	81	14.1	12.0	<20	9.74	1.33
106	AA2008	27	9	4	54	180	0.4	90	49	12.0	1.1	85	10.0	80	14.0	12.0	<20	8.62	1.19
107	AA2009	12	5	2	37	210	1.0	120	71	18.0	1.4	85	14.0	82	13.7	12.0	<20	7.75	0.99
108	AA2010	26	8	4	52	220	0.8	100	62	16.0	1.8	81	12.0	102	13.7	17.0	<20	9.29	1.13
109	AA2011	35	8	5	51	250	1.2	110	64	16.0	1.7	90	13.0	83	14.1	14.0	<20	8.54	1.09
110	AA2012	29	10	7	46	280	0.4	110	76	16.0	1.7	97	16.0	82	13.7	13.0	<20	8.49	1.10
111	AA2013	<5	5	<1	28	220	0.7	100	60	15.0	1.0	70	11.0	53	14.1	12.0	<20	7.27	0.93
112	AA2014	<5	<4	<1	22	160	1.4	74	30	11.0	0.7	49	6.9	47	8.0	10.0	<20	5.86	0.80
113	AA2101	16	6	<1	34	170	0.7	56	39	9.0	1.1	52	8.6	43	5.8	6.5	<20	5.51	0.73
114	AA2102	15	8	4	33	120	0.3	46	31	6.4	1.1	51	8.8	63	5.8	7.5	<20	5.31	0.62
115	AA2103	22	8	2	31	110	0.3	48	39	6.7	1.2	43	6.9	43	7.3	8.4	<20	6.06	0.96
116	AA2104	30	10	5	46	140	0.3	64	38	9.3	1.1	81	7.1	58	8.7	9.8	<20	7.95	1.15
117	AA2105	31	14	7	45	140	0.3	62	28	9.0	1.1	83	9.5	54	7.6	9.1	<20	7.57	0.95
118	AA2106	22	8	<1	37	210	1.2	96	54	13.0	1.3	68	12.0	77	11.6	12.0	<20	7.67	1.00
119	AA2107	25	6	5	44	220	1.0	110	43	15.0	2.5	85	12.0	72	14.4	14.0	<20	8.07	1.14
120	AA2108	32	8	5	49	220	0.8	96	50	14.0	1.1	90	14.0	85	9.9	12.0	<20	8.67	1.14
121	AA2109	27	8	7	47	240	1.1	95	56	14.0	1.7	84	12.0	78	13.9	11.0	<20	8.52	1.05
122	AA2110	20	16	4	36	120	0.2	48	26	5.8	0.9	57	8.6	31	3.1	5.9	<20	4.28	0.56
123	AA2111	16	6	<1	37	200	1.5	130	76	20.0	1.8	97	13.0	69	15.3	14.0	<20	9.46	1.28
124	AA2112	<5	<4	<1	15	110	2.3	70	49	11.0	1.1	26	2.8	39	8.6	7.6	<20	5.52	0.83
125	AA2201	7	5	<1	31	100	0.2	22	16	2.8	0.7	39	7.1	22	2.5	3.0	<20	3.11	0.44
126	AA2202	16	7	4	35	180	0.3	97	65	13.0	1.0	63	11.0	74	14.5	14.0	<20	9.04	1.30
127	AA2203	16	11	<1	29	55	0.8	22	9	2.6	0.5	35	6.9	10	4.5	2.5	<20	2.86	0.39
128	AA2204	17	12	<1	37	100	<0.2	43	10	6.3	1.3	51	5.6	38	9.7	6.8	<20	5.87	0.82
129	AA2205	21	10	<1	43	160	0.6	68	51	10.0	2.9	70	7.4	96	8.5	12.0	<20	9.28	1.18
130	AA2206	24	9	4	44	220	0.9	100	59	15.0	1.8	85	8.1	92	12.9	11.0	<20	9.84	1.14
131	AA2207	14	8	<1	35	190	0.9	79	52	11.0	1.3	66	8.6	55	9.6	9.2	<20	6.20	0.86
132	AA2208	10	5	<1	34	250	1.0	120	58	18.0	3.3	90	14.0	74	15.7	12.0	<20	9.13	1.21
133	AA2209	42	9	4	53	270	0.8	120	65	18.0	1.8	100	16.0	89	16.5	16.0	<20	9.31	1.27
134	AA2210	<5	<4	<1	18	150	1.7	68	50	10.0	1.1	27	3.6	42	7.7	5.3	<20	4.68	0.62
135	AA2301	26	10	<1	42	250	1.1	110	94	18.0	2.0	87	15.0	172	16.1	15.0	<20	10.70	1.36
136	AA2302	26	10	<1	42	230	0.8	88	47	14.0	1.0	83	13.0	69	11.3	13.0	<20	9.20	1.14
137	AA2303	15	8	<1	35	120	0.5	52	37	8.0	1.7	68	9.6	58	6.5	9.4	<20	8.08	1.07
138	AA2304	27	11	5	43	150	0.5	73	27	11.0	2.5	78	11.0	66	7.4	9.4	<20	8.52	1.15
139	AA2305	13	9	<1	34	150	0.8	65	42	8.9	1.2	59	8.4	57	7.3	8.3	<20	6.34	0.81
140	AA2306	16	6	3	37	130	0.8	59	34	8.6	2.6	57	7.3	43	6.0	7.1	<20	5.23	0.78
141	AA2307	6	4	<1	34	150	1.1	70	45	10.0	1.3	58	7.5	49	7.0	7.7	<20	5.66	0.69
142	AA2308	13	5	2	35	170	0.8	74	39	11.0	1.1	61	7.4	49	8.8	7.3	<20	5.89	0.72
143	AA2309	12	5	4	35	190	1.0	74	40	10.0	1.1	67	8.0	43	8.4	6.0	<20	5.32	0.76
144	AA2310	<5	4	<1	20	110	1.0	45	34	7.3	0.8	30	4.2	53	5.6	5.4	<20	4.02	0.68
145	AA2401	<5	11	3	23	180	1.3	53	27	7.3	0.9	28	3.0	39	5.3	5.1	<20	4.54	0.65
146	AA2402	14	13	<1	22	190	1.9	58	41	9.4	1.0	32	4.8	59	5.4	6.2	<20	4.59	0.59
147	AA2403	33	10	7	46	250	0.5	100	40	17.0	2.1	99	19.0	176	17.5	17.0	<20	10.30	1.47
148	AA2404	20	6	3	35	190	1.2	80	64	12.0	1.1	63	10.0	52	9.6	8.6	<20	5.38	0.74
149	AA2405	15	7	4	35	140	0.7	66	48	9.0	1.3	64	7.3	45	7.5	8.2	<20	5.18	0.81
150	AA2406	11	6	<1	35	180	0.6	68	43	9.3	1.1	65	8.8	100	8.1	8.0	<20	5.52	0.67
151	AA2407	10	5	<1	40	210	0.9	95	61	14.0	1.3	80	11.0	144	12.5	8.8	<20	6.40	0.90
152	AA2501	9	23	<1	21	100	0.2	19	17	2.5	0.6	29	3.2	38	1.6	2.9	<20	2.55	0.42
153	AA2502	6	10	<1	22	97	0.4	18	14	2.6	0.7	27	3.5	41	1.5	2.6	<20	2.84	0.48
154	AA2503	14	<8	2	23	89	0.5	18	7	1.9	<0.5	28	3.8	30	1.5	2.5	<20	2.77	0.39
155	AA2504	19	31	<1	26	72	0.4	17	10	2.0	0.7	25	3.0	19	1.3	2.5	<20	2.68	0.40
156	AA2505	22	36	3	30	83	0.4	10	20	1.9	0.6	31	4.0	33	3.4	4.2	<20	3.15	0.45
157	AA2506	15	32	<1	27	81	0.4	26	14	3.3	0.8	40	4.8	36	1.8	2.5	<20	4.29	0.63
158	AA2507	20	11	<1	25	43	0.9	18	<5	1.9	0.6	34	3.8	54	5.6	5.9	<20	3.29	0.40
159	AA2508	33	8	<1	43	120	0.9	40	28	5.2	0.7	34	6.1	156	12.8	14.0	<20	3.45	0.48
160	AA2509	14	11	4	33	210	1.2	100	55	16.0	1.8	86	20.0	105	8.5	8.0	<20	9.13	1.18
161	AA2510	15	5	<1	36	190	0.8	75	37	11.0	1.1	62	9.1	56	7.1	7.8	<20	5.57	0.79
162	AA2601	44	6	5	55	180	1.1	87	51	12.0	1.2	71	9.2	107	21.2	19.0	<20	6.36	0.87
163	AA2602	50	10	10	56	340	1.1	150	72	23.0	3.1	120	10.8	77	16.2	15.0	25	12.60	1.63
164	AA2603	10	13	8	28	330	0.4	150	80	22.0	4.9	130	22.0	22	5.1	2.8	25	10.40	1.32
165	AA2604	7	29	<1	23	76	0.4	29	12	3.6	0.7	35	4.2	18	2.2	2.2	<20	3.46	0.52
166	AA2605	9	25	2	23	100	0.7	32	20	2.6	1.6	28	3.2	10	2.9	2.2	<20	2.8	



付表4 土壤地化学試料分析値一覧表

(3)

NO	SP.No.	Sn	H	Ta	Nb	Ce	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Tu
	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
188	AA2803	45	8	6	58	280	0.9	350	56	20.0	3.9	120	16.0	170	20.0	19.0	25	11.10	1.48
189	AA2804	57	9	9	57	260	<0.2	110	50	15.0	1.7	98	15.0	80	15.5	13.0	26	8.89	0.95
190	AA2805	<5	7	<1	19	120	0.6	42	23	4.5	0.6	23	3.0	51	5.6	5.5	<20	3.88	0.47
191	AA2806	12	16	3	29	72	<0.2	28	19	3.4	0.6	37	4.6	25	3.5	3.9	<20	3.02	0.43
192	AA2807	7	10	<1	24	34	0.5	15	14	1.7	<0.5	29	2.0	22	2.8	3.5	<20	2.87	0.47
193	AA2808	14	17	<1	26	53	0.4	20	16	2.4	<0.5	29	3.0	22	4.7	2.4	<20	3.22	0.51
194	AA2809	29	33	2	12	69	<0.2	30	<5	3.2	<0.5	26	3.7	38	4.6	2.2	<20	2.26	0.42
195	AA2810	21	7	<1	39	230	1.1	130	81	18.0	3.0	95	15.0	75	16.6	12.0	<20	8.06	1.03
196	AA2811	16	0	4	31	210	0.9	100	68	13.0	1.4	81	12.0	131	13.2	12.0	<20	5.13	0.27
197	AA2812	22	6	3	39	200	0.5	100	40	14.0	1.0	84	12.0	151	14.0	11.0	<20	6.93	0.97
198	AA2813	<5	6	3	28	130	0.7	63	35	7.9	1.1	45	5.9	57	7.1	6.9	<20	5.58	0.81
199	AA2814	51	11	7	53	240	0.7	130	33	16.0	2.3	100	16.0	197	16.7	14.0	26	9.36	1.27
200	AA2901	67	10	8	56	270	1.0	150	59	20.0	4.6	120	17.0	162	22.1	18.0	21	9.24	1.21
201	AA2902	49	11	6	51	330	0.4	100	79	25.0	4.9	130	32.0	210	23.2	19.0	<20	17.10	2.29
202	AA2903	61	11	9	57	260	0.5	140	77	18.0	3.5	110	23.0	91	17.6	16.0	<20	8.88	1.11
203	AA2904	63	9	11	62	250	0.9	140	63	19.0	1.3	118	16.0	84	19.2	15.0	<20	7.67	1.03
204	AA2905	54	7	10	51	310	0.9	160	95	20.0	4.9	120	20.0	251	21.7	20.0	30	11.40	1.60
205	AA2906	55	15	11	54	400	0.4	180	88	24.0	2.5	160	25.0	106	12.0	12.0	35	11.90	1.61
206	AA2907	49	9	9	52	260	0.6	150	78	20.0	2.0	110	18.0	239	16.1	16.0	<20	3.98	1.36
207	AA2908	45	9	8	52	220	0.7	110	66	14.0	1.5	95	14.0	77	13.4	14.0	<20	7.72	1.16
208	AA2909	23	15	4	37	120	0.6	62	36	8.2	2.0	52	7.3	54	8.9	9.0	<20	5.57	0.72
209	AA2910	27	11	5	42	180	0.6	85	50	12.0	1.7	71	11.0	74	13.2	13.0	<20	8.05	1.06
210	AA2911	15	8	3	37	150	0.8	83	39	10.0	1.8	64	8.0	66	9.8	10.0	<20	5.17	0.96
211	AA2912	9	<4	4	29	190	0.7	93	74	13.0	2.1	70	13.0	63	10.2	10.0	<20	6.29	0.93
212	AA2913	13	6	<1	33	190	1.1	95	40	12.0	1.3	70	11.0	59	13.0	7.9	<20	6.31	0.82
213	AA2914	<5	5	2	21	160	1.2	60	33	6.4	0.5	34	4.9	50	4.6	6.2	<20	4.10	0.56
214	AA2915	<5	6	<1	20	79	0.7	28	10	2.6	0.5	21	2.0	19	5.5	3.1	<20	2.55	0.46
215	AA3001	44	7	6	51	180	0.6	80	38	10.0	1.2	75	10.0	133	8.8	10.0	<20	5.61	0.73
216	AA3002	24	9	3	27	77	0.4	40	25	5.2	0.7	39	5.4	39	2.1	5.2	<20	3.65	0.45
217	AA3003	53	6	6	51	170	0.4	85	39	11.0	1.0	76	11.0	167	12.9	11.0	<20	5.28	0.70
218	AA3004	40	11	8	47	360	1.0	200	110	28.0	5.6	150	29.0	258	27.3	24.0	21	14.38	1.93
219	AA3005	40	10	9	35	350	0.8	200	120	27.0	4.3	150	19.0	133	23.4	23.0	<20	15.60	2.85
220	AA3006	35	9	6	49	180	0.7	89	47	11.0	2.1	85	11.0	58	10.5	11.0	<20	7.01	0.86
221	AA3007	18	8	4	39	170	0.3	89	44	11.0	1.3	73	8.7	62	11.1	10.0	<20	6.66	0.90
222	AA3008	44	9	7	53	270	0.9	130	80	18.0	3.3	110	14.0	213	16.6	17.0	<20	10.20	1.32
223	AA3009	31	7	1	49	220	0.7	110	58	15.0	1.4	93	12.0	71	14.2	14.0	<20	7.39	1.05
224	AA3010	5	4	1	27	210	0.9	120	64	15.0	2.0	84	13.0	78	14.4	13.0	<20	8.23	1.10
225	AA3101	68	8	11	65	180	0.5	98	45	13.0	2.7	100	8.4	101	10.5	11.0	<20	7.65	1.03
226	AA3102	39	10	7	42	150	0.5	66	33	9.8	1.2	79	7.4	47	8.6	8.3	<20	6.07	0.80
227	AA3103	29	7	5	39	71	0.3	35	14	4.6	0.8	47	4.3	26	5.4	5.5	<20	4.00	0.49
228	AA3104	5	<4	2	24	44	0.4	20	14	2.5	0.6	32	4.1	27	2.9	3.2	<20	3.80	0.49
229	AA3105	<5	5	1	15	39	0.3	15	10	1.8	0.5	27	3.0	11	1.6	2.3	<20	2.53	0.40
230	AA3106	12	29	2	18	38	0.4	17	<5	1.7	<0.5	22	2.9	11	1.5	2.5	<20	2.01	0.29
231	AA3107	12	10	3	30	58	0.4	25	18	3.1	1.1	38	4.3	44	3.8	3.0	<20	3.18	0.40
232	AA3108	18	9	3	35	93	0.4	43	38	5.5	0.8	51	6.9	64	7.1	6.5	<20	4.11	0.54
233	AA3109	41	9	4	49	180	1.3	110	75	14.0	2.2	72	9.6	77	16.0	14.0	<20	6.22	0.81
234	AA3110	50	8	5	51	250	0.8	140	85	18.0	2.4	110	16.0	120	20.0	19.0	<20	8.10	1.14
235	AA3111	14	6	4	14	210	0.4	100	63	12.0	2.5	95	14.0	67	16.6	11.0	<20	6.66	0.94
236	AA3201	11	5	3	25	120	1.0	59	39	7.1	1.1	33	6.1	40	7.5	7.0	<20	3.84	0.50
237	AA3202	<5	<4	<1	19	99	1.1	56	43	6.8	0.9	25	2.9	31	6.6	5.7	<20	3.34	0.47
238	AA3203	<5	<4	1	17	49	0.3	13	8	1.5	0.5	21	2.6	20	1.5	1.4	<20	1.76	0.26
239	AA3204	<5	<4	<1	20	31	0.3	11	7	1.3	<0.5	22	2.5	16	1.5	2.0	<20	2.10	0.34
240	AA3205	13	28	2	17	56	0.4	29	19	2.9	<0.5	21	2.9	28	1.7	3.5	<20	1.98	0.28
241	AA3206	11	5	2	23	46	0.3	18	12	2.4	<0.5	20	3.0	26	5.3	7.9	<20	2.25	0.28
242	AA3207	26	8	4	34	91	0.5	43	31	5.3	0.7	50	6.8	44	7.9	4.6	<20	3.53	0.46
243	AA3208	19	5	3	42	140	0.6	59	38	7.3	0.7	53	7.0	48	10.1	6.5	<20	3.76	0.47
244	AA3209	16	5	3	38	130	0.4	60	41	7.6	0.7	57	7.6	48	8.1	8.9	<20	3.99	0.55
245	AA3301	14	13	1	16	94	1.5	54	38	7.2	0.7	19	2.3	42	7.6	7.8	<20	3.27	0.39
246	AA3302	5	10	<1	19	110	1.9	87	66	11.0	1.1	19	2.2	60	10.8	6.4	<20	4.97	0.69
247	AA3303	<5	9	<1	17	33	0.3	11	<5	1.3	<0.5	15	2.0	11	3.7	9.2	<20	1.52	0.22
248	AA3304	5	7	<1	21	36	0.4	15	<5	1.9	<0.5	19	2.3	13	3.9	1.6	<20	1.96	0.31
249	AA3305	<5	5	1	26	42	0.3	21	16	2.5	<0.5	24	3.4	39	2.5	4.4	<20	2.27	0.31
250	AA3306	16	5	3	33	92	0.4	48	25	5.8	0.7	44	5.7	40	4.2	5.1	<20	3.94	0.46
251	AA3307	16	5	3	34	110	0.5	54	29	6.5	0.7	52	8.1	69	7.9	6.4	<20	3.97	0.53
252	AA3308	5	<4	3	34	100	0.5	56	26	6.5	0.8	48	5.4	43	6.0	6.7	<20	3.95	0.50
253	AA3309	19	5	4	39	160	0.8	80	55	10.0	1.0	65	8.6	76	11.6	10.0	<20	4.86	0.65
254	AA3310	36	8	6	51	280	0.8	160	100	20.0	3.3	120	15.0	128	27.6	29.0	<20	12.10	1.51
255	AA3401	56	6	6	52	200	0.5	110	71	13.0	2.0	86	16.0	143	14.1	10.0	<20	3.96	0.63
256	AA3402	56	6	7	53	240	0.5	130	80	16.0	2.6	100	23.0	80	16.5	12.0	<20	5.76	0.84
257	AA3403	50	8	6	52	260	0.7	120	80	15.0	2.4	100	14.0	75	15.6	12.0	23	5.72	0.83
258	AA3404	38	7	5	43	150	0.7	73	45	9.1	1.8	69	11.0	45	8.9	7.3	<20	4.79	0.54
259	AA3405	34	6	4	34	120	0.8	59	37	7.7	1.2	52	7.7	43	10.0	7.9	<20	4.81	0.52
260	AA3406	<5	5	1	17	51	0.4	13	12	1.5	<0.5	22	3.2	16	1.3	2.1	<20	2.16	0.28

附表4 土壤地化学試料分析値一覽表

(4)

NO	SP.No.	Sn	N	To	Nb	Ce	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
282	AA3514	19	5	3	39	220	0.8	110	82	15.0	2.5	89	14.0	84	16.0	15.0	<20	7.63	0.97
283	AA3601	70	10	13	74	310	1.0	160	110	20.0	3.4	130	21.0	91	18.9	14.0	25	7.65	0.90
284	AA3602	89	10	11	68	300	0.8	140	100	19.0	2.6	120	15.0	171	15.7	14.0	27	7.47	0.88
285	AA3603	18	8	3	23	66	0.4	35	22	3.0	<0.5	30	3.1	55	1.7	3.5	<20	2.18	0.30
286	AA3604	19	7	4	30	50	0.5	26	11	2.0	<0.5	43	5.5	24	2.6	5.7	<20	2.90	0.40
287	AA3605	31	7	4	36	77	0.3	31	17	3.8	0.8	48	7.5	32	2.6	7.5	<20	3.91	0.49
288	AA3606	41	8	5	54	138	0.4	65	49	8.1	0.8	79	8.2	50	7.3	8.7	<20	4.47	0.57
289	AA3607	<5	6	2	22	130	0.5	29	22	3.5	<0.5	29	3.7	26	3.9	4.2	<20	3.36	0.48
290	AA3608	<5	<4	2	20	83	0.4	21	14	2.5	<0.5	26	3.5	23	3.1	3.4	<20	3.24	0.44
291	AA3609	<5	5	1	21	130	0.7	27	21	3.6	<0.5	26	3.0	37	5.5	4.1	<20	3.24	0.51
292	AA3610	<5	6	2	20	87	0.5	22	14	2.7	0.8	25	3.0	25	2.0	4.0	<20	3.05	0.48
293	AA3611	<5	4	2	20	140	0.4	22	16	3.3	<0.5	25	2.7	29	3.4	3.4	<20	3.05	0.46
294	AA3612	<5	<4	1	18	120	0.8	30	15	4.4	<0.5	29	2.7	30	6.2	4.9	<20	3.71	0.51
295	AA3613	54	8	7	54	260	0.7	140	70	18.0	3.0	110	15.0	79	15.8	13.0	<20	7.29	1.07
296	AA3614	13	6	1	34	190	1.0	87	35	11.0	2.4	71	11.0	47	9.5	8.7	<20	6.43	0.79
297	AA3615	30	7	4	44	180	0.7	88	43	12.0	1.4	94	11.0	62	8.7	9.5	<20	6.17	0.93
298	AA3616	12	6	3	29	170	1.2	87	47	12.0	1.9	60	15.0	61	11.0	10.0	<20	5.66	0.78
299	AA3617	17	6	4	38	240	1.1	120	70	16.0	2.4	96	12.0	74	14.3	13.0	<20	8.59	1.08
300	AA3701	58	7	7	61	160	0.4	70	36	9.6	1.0	89	7.3	52	8.8	9.0	<20	4.78	0.73
301	AA3702	73	10	14	75	280	0.8	150	71	19.0	2.5	130	14.0	80	19.9	17.0	<20	8.23	1.06
302	AA3703	71	8	15	75	320	0.4	160	90	20.0	1.7	130	18.0	92	18.7	16.0	<20	8.50	1.04
303	AA3704	44	16	1	28	51	0.4	20	13	2.4	0.5	29	3.6	19	1.4	2.5	<20	2.63	0.42
304	AA3705	18	12	3	30	46	0.3	23	12	2.5	<0.5	30	5.1	25	3.3	3.4	<20	2.95	0.45
305	AA3706	32	6	4	39	87	0.4	36	24	4.7	1.0	47	6.3	39	5.1	3.0	<20	4.20	0.56
306	AA3707	<5	<4	1	22	43	0.6	19	7	2.6	0.6	20	2.9	22	4.2	8.2	<20	3.16	0.44
307	AA3708	<5	<4	1	19	49	0.3	9	6	1.8	<0.5	22	3.0	15	2.3	4.5	<20	2.07	0.32
308	AA3709	<5	<4	1	19	54	0.2	10	7	1.2	<0.5	23	2.5	14	2.2	4.0	<20	2.65	0.40
309	AA3710	<5	6	1	21	55	0.5	12	7	1.5	<0.5	26	3.0	23	1.2	3.9	<20	3.16	0.52
310	AA3711	<5	<4	2	20	74	0.7	23	10	3.4	<0.5	24	3.6	27	2.9	5.5	<20	3.16	0.52
311	AA3712	<5	4	2	24	110	0.8	44	25	6.2	1.3	32	5.3	31	4.2	6.8	<20	3.00	0.53
312	AA3713	43	7	7	52	230	0.8	120	60	16.0	2.3	98	15.0	82	14.5	17.0	<20	6.27	0.93
313	AA3714	24	6	4	43	200	0.5	100	43	13.0	2.2	81	11.0	76	15.2	18.0	<20	7.44	0.94
314	AA3715	20	8	4	41	220	0.9	110	46	14.0	1.7	88	11.0	66	12.3	14.0	<20	7.67	1.05
315	AA3716	12	5	3	31	180	1.0	99	55	13.0	1.9	67	15.0	62	13.2	13.0	<20	6.73	0.91
316	AA3717	8	6	1	29	130	0.6	65	32	9.0	0.8	48	6.6	50	7.1	7.8	<20	4.11	0.64
317	AA3801	68	9	6	52	120	0.4	53	23	7.2	0.9	64	7.0	41	6.0	9.4	<20	4.52	0.60
318	AA3802	61	8	7	56	130	0.3	57	49	7.5	1.5	72	7.1	47	10.2	9.6	<20	4.20	0.65
319	AA3803	63	9	10	67	250	0.8	120	68	16.0	2.5	110	12.0	81	15.1	17.0	<20	7.36	0.96
320	AA3804	68	8	11	65	270	0.7	130	60	17.0	1.4	110	15.0	85	14.8	17.0	22	7.03	0.94
321	AA3805	48	23	3	27	100	0.5	52	32	6.6	0.9	39	6.5	30	5.3	7.0	<20	3.49	0.54
322	AA3806	51	12	7	53	180	0.8	97	48	12.0	1.5	90	18.0	53	8.4	9.5	<20	5.00	0.71
323	AA3807	12	<4	1	15	28	0.3	12	8	1.2	<0.5	15	2.5	13	1.5	2.3	<20	2.12	0.31
324	AA3808	10	<4	1	15	73	0.5	16	7	2.1	<0.5	17	2.7	14	4.6	2.8	<20	2.38	0.36
325	AA3809	31	<4	1	15	27	0.3	9	<5	1.1	<0.5	17	1.6	16	5.2	2.1	<20	2.31	0.34
326	AA3810	23	<4	2	18	35	0.3	11	9	1.5	<0.5	18	2.1	16	4.8	3.1	<20	2.52	0.40
327	AA3811	10	5	1	22	57	0.6	18	11	2.6	<0.5	26	3.8	21	3.2	3.8	<20	2.92	0.47
328	AA3812	27	<4	4	40	160	0.8	85	48	11.0	1.7	71	11.0	59	12.8	12.0	<20	6.90	0.85
329	AA3813	17	7	5	42	240	0.8	120	84	18.0	1.8	97	16.0	76	18.9	17.0	20	9.24	1.15
330	AA3814	7	5	2	<2	170	1.0	96	62	13.0	1.5	64	12.0	62	13.1	13.0	<20	6.39	0.89
331	AA3901	105	30	3	29	45	0.4	23	8	2.4	<0.5	38	3.7	17	4.7	3.6	<20	2.16	0.30
332	AA3902	78	11	5	44	120	0.5	55	26	7.6	<0.5	56	7.5	37	9.2	9.0	<20	3.85	0.53
333	AA3903	64	8	9	64	210	0.5	110	65	14.0	2.1	93	11.0	74	13.8	14.0	<20	6.28	0.81
334	AA3904	69	7	10	67	220	0.6	110	60	14.0	2.7	100	11.0	61	14.2	13.0	<20	5.68	0.71
335	AA3905	52	<4	10	63	250	0.4	120	69	16.0	2.5	110	11.0	71	17.6	16.0	21	7.51	0.91
336	AA3906	5	4	1	16	32	0.4	12	6	1.6	<0.5	15	2.5	12	3.2	3.3	<20	2.19	0.32
337	AA3907	<5	7	1	16	36	0.4	11	7	1.4	<0.5	15	2.0	17	2.3	2.4	<20	1.99	0.32
338	AA3908	14	6	1	15	47	0.2	9	8	1.0	<0.5	17	1.7	10	2.2	2.2	<20	1.74	0.27
339	AA3909	29	5	1	20	61	0.3	9	6	1.1	<0.5	23	2.4	15	2.4	3.4	<20	2.03	0.34
340	AA3910	14	8	1	22	73	0.4	21	12	3.0	0.6	28	4.3	19	4.1	4.2	<20	3.14	0.50
341	AA3911	16	7	4	34	220	0.9	120	70	16.0	2.7	93	12.0	67	13.6	15.0	<20	8.07	1.16
342	AA3912	22	6	4	41	190	0.6	98	44	13.0	1.7	83	11.0	65	10.2	14.0	<20	7.61	0.98
343	AA3913	21	7	4	38	180	0.7	84	44	11.0	2.0	72	9.3	61	10.3	13.0	<20	6.36	0.79
344	AA3914	<5	<4	2	18	48	0.4	25	18	3.1	0.7	22	3.1	29	2.5	5.2	<20	3.30	0.44
345	AA4001	60	7	9	61	170	0.5	92	55	12.0	0.7	82	14.0	49	10.8	9.4	<20	3.95	0.50
346	AA4002	20	16	3	27	80	0.6	35	16	4.5	0.5	33	6.1	21	4.5	4.8	<20	2.87	0.40
347	AA4003	17	17	1	14	81	0.3	10	7	1.3	<0.5	16	1.6	8	2.5	1.3	<20	1.68	0.27
348	AA4004	5	24	2	16	140	0.5	18	13	2.7	<0.5	18	2.5	10	1.6	2.2	<20	1.72	0.31
349	AA4005	<5	<4	1	12	13	0.3	4	<5	0.4	<0.5	9.7	1.7	6	2.7	1.2	<20	1.40	0.22
350	AA4006	<5	7	1	20	42	0.4	11	7	1.7	0.6	20	2.8	11	2.9	3.3	<20	2.01	0.35
351	AA4007	14	6	3	30	110	0.9	54	31	7.2	1.1	49	7.4	45	5.7	7.4	<20	4.95	0.67
352	AA4008	22	6	4	41	270	0.6	130	64	10.0	2.0	100	15.0	91	17.6	25.0	23	12.00	1.59
353	AA4009	25	<4	5	41	200	0.9	99	56	13.0	2.0	83	13.0	70	8.3	12.0	<20	7.81	0.99
354	AA4010	24	7	5	38	170	0.8	84	53	11.0	2.0	73	8.7	63	9.9	12.0	<20	7.04	0.91
355	AA4011	61	10	7	54	190	0.6												

付表4 土壤地化学試料分析値一覧表

(5)

376 AA4301	28	14	4	30	72	0.2	32	20	4.0	1.1	47	5.2	33	3.9	7.4	<20	5.32	0.81
377 AA4302	26	12	4	33	89	0.3	35	31	4.5	1.0	52	5.9	38	4.8	6.5	<20	4.84	0.67
378 AA4303	18	17	3	27	93	0.6	41	23	4.4	0.7	49	9.7	25	3.9	5.3	<20	3.50	0.51
379 AA4304	30	8	5	41	250	0.7	120	73	14.0	2.8	110	17.0	71	13.5	15.0	<20	7.61	1.15
380 AA4305	32	8	6	40	260	1.0	130	94	16.0	2.5	110	18.0	71	13.0	14.0	<20	7.32	1.11
381 AA4306	26	8	3	34	220	0.7	110	70	14.0	2.3	99	15.0	64	14.6	14.0	<20	7.33	1.21
382 AA4401	11	11	2	23	67	0.4	28	18	3.5	0.7	36	4.8	26	5.5	5.4	<20	3.37	0.47
383 AA4402	5	15	3	23	61	0.2	28	20	3.5	0.7	36	5.4	25	3.7	4.8	<20	3.49	0.52
384 AA4403	12	8	4	28	150	0.4	75	51	9.1	1.5	68	7.0	53	10.7	12.0	<20	6.74	1.03
385 AA4404	12	7	4	32	130	0.6	62	47	7.2	1.0	65	9.2	41	6.8	8.4	<20	4.87	0.76
386 AA4405	25	9	4	35	210	0.7	96	72	12.0	2.2	85	11.0	55	13.9	14.0	<20	7.40	1.10
387 AA4406	29	10	5	39	220	0.9	110	89	14.0	1.6	96	14.0	64	12.3	15.0	<20	7.03	1.21
388 AA5001	87	12	8	52	280	0.8	110	80	12.0	1.9	96	21.0	49	10.3	9.5	<20	4.58	0.75
389 AA5002	45	22	5	36	140	0.8	67	49	8.6	1.4	64	9.8	36	8.6	8.0	<20	5.07	0.76
390 AA5003	58	21	2	17	85	0.5	14	6	1.8	<0.5	19	3.3	13	1.3	2.5	<20	2.20	0.28
391 AA5004	112	13	2	22	37	<0.2	17	18	2.2	<0.5	24	3.3	13	2.3	2.6	<20	2.53	0.35
392 AA5005	39	14	2	23	20	0.3	10	5	1.1	<0.5	23	3.0	12	1.5	1.8	<20	2.08	0.26
393 AA5006	76	12	2	18	26	0.3	18	6	1.6	<0.5	16	2.6	11	3.1	1.8	<20	1.94	0.27
394 AA5007	51	14	1	21	43	0.5	24	13	2.3	<0.5	19	2.9	15	1.7	3.2	<20	2.33	0.35
395 AA5008	76	14	3	29	74	0.5	35	12	4.6	<0.5	31	5.1	24	3.7	5.0	<20	3.17	0.47
396 AA5009	94	7	8	57	190	0.6	96	53	13.0	0.9	85	13.0	58	10.0	12.0	<20	4.73	0.69
397 AA5010	90	9	9	56	200	0.3	100	51	14.0	1.3	94	15.0	54	10.4	11.0	<20	5.08	0.70
398 AA5011	62	9	8	37	140	0.2	69	38	9.9	1.5	61	7.5	42	9.2	9.4	<20	5.03	0.65
399 AA5101	50	29	3	30	61	0.3	26	11	3.5	1.7	40	5.2	24	5.5	4.2	<20	3.52	0.51
400 AA5102	54	11	3	34	71	0.5	34	19	4.8	1.1	46	4.9	31	4.7	7.6	<20	5.10	0.69
401 AA5103	47	10	3	33	67	0.4	29	13	4.0	0.7	40	4.4	25	5.5	6.0	<20	3.09	0.49
402 AA5104	44	11	3	34	77	0.5	32	12	4.5	0.7	41	6.1	28	4.0	5.8	<20	3.62	0.51
403 AA5105	72	9	7	52	190	0.6	90	51	13.0	1.5	79	10.0	56	10.6	11.0	<20	5.44	0.63
404 AA5106	71	15	3	30	65	0.6	26	10	3.5	0.7	32	4.9	21	3.0	4.8	<20	3.45	0.47
405 AA5107	127	25	3	27	45	0.4	19	7	1.9	0.7	25	3.1	19	2.4	3.3	<20	3.17	0.46
406 AA5108	57	12	2	22	36	0.4	13	5	1.5	0.5	24	2.8	17	3.9	2.7	<20	2.40	0.37
407 AA5109	27	7	3	35	130	0.8	60	35	8.7	1.1	53	7.0	50	8.4	9.2	<20	5.34	0.73
408 AA5110	16	6	4	36	150	0.7	71	45	10.0	1.4	63	9.7	49	10.9	10.0	<20	5.33	0.73
409 AA5111	88	10	8	53	130	0.3	66	29	9.1	1.3	66	21.0	41	6.3	9.0	<20	3.46	0.56
410 AA5112	61	7	3	24	56	0.4	31	14	2.9	0.6	24	3.5	21	3.1	4.0	<20	2.09	0.40
411 AA5113	37	6	1	22	48	0.3	24	8	1.9	0.7	28	4.4	15	3.1	3.0	<20	2.74	0.38
412 AA5201	19	5	2	36	140	0.3	62	42	9.0	1.6	59	8.3	48	8.5	10.0	<20	5.29	0.76
413 AA5202	23	7	4	36	160	0.6	63	39	9.5	1.3	58	8.2	48	8.9	10.0	<20	5.34	0.73
414 AA5203	21	7	3	36	110	0.4	49	26	7.1	1.0	50	7.8	41	6.6	8.0	<20	4.57	0.61
415 AA5204	28	9	3	36	130	0.6	58	39	8.3	1.0	54	8.3	41	5.8	9.0	<20	4.31	0.44
416 AA5205	77	13	3	29	57	0.3	25	15	3.4	0.7	31	4.2	24	4.8	4.8	<20	2.57	0.23
417 AA5206	78	15	3	31	61	0.3	25	16	3.3	1.0	32	4.2	24	2.6	6.2	<20	3.32	0.30
418 AA5207	116	18	3	31	59	0.5	27	13	3.3	1.1	35	4.1	27	3.6	5.2	<20	3.57	0.37
419 AA5208	16	5	2	32	140	0.6	66	44	9.5	1.1	56	7.3	48	9.4	9.2	<20	5.02	0.66
420 AA5209	24	<4	3	33	160	0.4	68	41	9.8	1.7	58	8.1	50	7.6	10.0	<20	4.71	0.28
421 AA5210	45	9	3	37	140	0.7	68	46	9.2	1.2	60	14.0	44	7.9	8.4	<20	3.85	0.28
422 AA5211	14	5	3	22	34	0.3	23	15	1.7	<0.5	21	2.0	11	2.1	2.4	<20	1.67	0.21
423 AA5212	41	11	2	25	28	0.3	24	15	1.8	<0.5	23	1.9	18	1.5	3.4	<20	2.56	0.30
424 AA5301	13	7	3	39	150	0.6	66	38	9.6	1.3	57	9.6	50	7.0	10.0	<20	5.25	0.76
425 AA5302	30	8	5	39	160	<0.2	69	50	10.0	0.9	66	13.0	48	7.4	10.0	<20	4.29	0.55
426 AA5303	28	9	6	41	150	<0.2	69	51	10.0	1.9	62	9.1	52	8.6	10.0	<20	4.63	0.59
427 AA5304	27	6	3	36	140	0.3	61	29	8.0	0.9	59	11.0	48	8.2	11.0	<20	4.62	0.60
428 AA5305	26	4	5	35	170	0.2	63	51	12.0	1.1	61	8.6	61	11.0	13.0	<20	5.26	0.75
429 AA5306	27	7	4	40	150	0.2	66	40	9.8	1.3	63	10.0	49	6.9	10.0	<20	4.53	0.50
430 AA5307	29	5	5	40	170	0.8	71	48	11.0	1.7	61	11.0	52	10.4	10.0	<20	4.42	0.59
431 AA5308	23	7	5	39	150	0.6	71	39	11.0	1.5	60	9.3	50	11.0	11.0	<20	5.41	0.75
432 AA5309	24	<4	2	32	140	0.6	58	46	8.3	1.0	54	8.2	40	8.2	9.8	<20	4.42	0.75
433 AA5310	18	4	3	28	140	0.3	59	39	8.7	1.5	54	6.2	49	7.8	7.5	<20	4.58	0.70
434 AA5311	31	6	5	33	160	0.7	77	54	11.0	1.7	62	10.0	57	9.7	11.0	<20	4.92	0.69
435 AA5312	163	52	3	26	120	0.3	62	31	7.3	<0.5	40	6.7	25	5.7	5.8	<20	2.89	0.44
436 AA5313	17	10	2	19	32	0.4	14	5	1.7	<0.5	20	2.5	18	1.3	2.5	<20	2.17	0.25
437 AA5401	<5	<4	1	14	88	0.9	19	7	3.0	<0.5	16	2.0	22	4.4	4.5	<20	2.44	0.27
438 AA5402	<5	<4	1	14	66	0.6	23	19	3.3	<0.5	19	1.6	20	3.1	3.9	<20	2.14	0.26
439 AA5403	13	<4	2	18	39	0.7	15	5	2.2	<0.5	24	2.7	19	2.0	3.5	<20	2.06	0.31
440 AA5404	42	7	5	39	160	1.1	80	57	12.0	1.8	66	15.0	56	11.6	12.0	<20	4.30	0.55
441 AA5405	31	6	4	35	160	0.3	66	54	10.0	1.1	59	8.6	49	8.0	10.0	<20	4.73	0.64
442 AA5406	31	<4	6	36	190	0.9	82	33	12.0	2.3	69	12.0	54	9.6	9.4	<20	5.70	0.71
443 AA5407	31	<4	4	40	180	0.9	71	57	11.0	2.0	70	11.0	50	8.8	10.0	<20	5.29	0.70
444 AA5408	18	<4	4	29	150	0.8	62	40	9.2	1.6	53	8.5	45	8.0	7.8	<20	4.92	0.60
445 AA5409	7	8	1	23	120	0.8	47	42	6.4	1.9	32	5.1	35	7.1	6.9	<20	2.89	0.35
446 AA5410	11	7	1	26	94	0.7	41	28	5.9	1.4	32	4.1	34	4.7	6.5	<20	3.60	0.45
447 AA5411	7	8	3	23	84	0.7	36	24	5.2	0.9	25	2.6	30	4.6	6.5	<20	3.14	0.53
448 AA5501	29	<4	<1	37	190	0.6	77	61	12.0	2.2	63	9.4	55	9.7	11.0	<20	5.35	0.79
449 AA5502	30	<4	4	40	170	0.9	71	52	11.0	1.2	64	11.0	52	8.1	10.0	<20	4.52	0.76
450 AA5503	19	5	4	34	140	0.3	52	29	7.7	1.2	48	8.0	39	5.7	6.9	<20	4.26	0.74
451 AA5504	<5	<4	2	25	82	0.7	19	15	3.1	0.7	21	2.0	25	2.7	4.7	<20	2.74	0.32
452 AA5505	<5	<4	2	10	70	0.6	15	15	2.8	0.7	18	2.3	19	2.4	4.0	<20	2.82	0.40
453 AA5506	<5	<4	2	21	90	0.7	16	15	2.8	0.7	23	3.8	24	2.5	4.9	<20	2.82	0.40
454 AA5507	<5	<4																

付表 4 土壤地化学試料分析値一覽表

(6)

NO	SP.No. unit	Sn ppm	W ppm	Ta ppm	Nb ppm	Co ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
472	AB0203	<5	<4	1	14	92	1.1	45	31	5.0	<0.5	18	3.1	25	4.2	4.3	<20	2.99	0.47
473	AB0204	40	8	5	32	110	0.5	22	10	4.3	1.7	98	9.6	64	3.2	3.5	<20	11.50	1.56
474	AB0205	24	11	7	40	92	0.8	32	22	5.9	1.7	60	11.0	99	7.2	7.5	<20	17.40	2.30
475	AB0206	18	15	7	35	170	0.7	43	18	6.0	1.7	79	11.0	87	7.3	7.7	<20	15.80	2.13
476	AB0207	35	8	8	43	120	0.3	18	9	4.1	1.6	75	8.7	91	4.6	4.2	<20	15.80	2.19
477	AB0208	37	11	11	48	140	0.7	36	25	7.9	2.7	78	9.7	135	8.2	9.0	<20	25.70	3.28
478	AB0209	49	9	11	49	95	0.6	24	12	4.5	1.6	65	9.5	135	7.6	7.3	<20	23.20	3.14
479	AB0301	<5	<4	1	16	99	1.2	45	25	5.2	<0.5	19	2.1	24	5.0	4.5	<20	3.20	0.53
480	AB0302	<5	<4	1	14	65	0.7	26	17	3.4	<0.5	17	1.9	24	0.5	3.0	<20	3.32	0.50
481	AB0303	<5	<4	1	14	130	1.2	66	37	6.6	<0.5	19	2.3	26	4.5	4.7	<20	3.77	0.48
482	AB0304	26	8	4	29	130	0.4	21	12	5.0	1.0	78	6.7	57	4.4	4.5	<20	10.40	1.36
483	AB0305	36	12	8	42	70	0.3	8	5	2.2	1.4	83	7.7	72	3.8	3.9	<20	13.80	1.90
484	AB0306	42	10	8	41	70	0.3	3	6	1.7	1.1	100	5.8	63	4.4	4.7	<20	11.20	1.66
485	AB0307	37	8	11	47	91	<0.3	7	11	2.6	2.0	90	9.0	82	4.8	5.5	<20	17.93	2.40
486	AB0308	45	9	10	45	110	0.6	22	15	4.8	1.2	79	11.0	94	6.9	7.0	<20	17.40	2.43
487	AB0309	33	<4	8	40	110	0.9	45	23	9.4	2.9	78	14.0	122	9.3	10.0	<20	22.40	3.07
488	AB0401	<5	<4	1	15	55	0.9	24	11	3.0	<0.5	21	2.4	25	1.5	2.5	<20	3.51	0.49
489	AB0402	<5	<4	2	14	79	0.9	28	22	3.8	<0.5	21	2.6	25	3.8	4.2	<20	3.76	0.55
490	AB0403	20	7	6	31	110	0.7	23	22	5.3	1.3	74	5.8	66	6.9	7.9	<20	11.10	1.50
491	AB0404	20	12	9	36	120	0.8	16	15	4.8	1.7	73	8.1	78	5.9	5.9	<20	15.40	2.14
492	AB0405	26	<4	5	36	120	1.5	140	90	29.0	8.0	59	12.0	307	36.2	33.0	<20	45.20	5.76
493	AB0406	46	11	9	44	84	0.6	6	10	1.6	1.2	86	7.9	58	1.8	2.7	<20	11.50	1.67
494	AB0407	31	14	6	41	130	0.3	18	15	4.0	1.0	89	7.3	71	6.1	6.5	<20	13.40	1.85
495	AB0408	45	9	9	42	85	0.6	19	11	5.3	2.3	70	8.8	118	9.0	10.0	<20	19.90	2.70
496	AB0409	44	12	12	60	66	0.8	18	6	4.4	2.6	66	13.0	165	10.0	10.0	<20	32.30	4.37
497	AB0410	53	9	11	57	88	0.5	26	18	5.4	1.8	71	9.3	139	9.6	10.0	<20	26.50	3.51
498	AB0501	<5	<4	2	16	87	1.1	42	33	5.9	0.8	23	4.7	37	2.9	2.7	<20	4.67	0.64
499	AB0502	20	7	4	26	130	1.2	69	44	11.0	1.7	66	11.0	92	9.9	11.0	<20	12.50	1.72
500	AB0503	48	6	10	37	110	1.1	130	66	18.0	4.7	51	12.0	218	22.5	20.0	<20	35.10	4.71
501	AB0504	43	8	5	31	170	1.7	120	81	28.0	5.3	85	17.0	197	26.7	24.0	<20	32.30	4.27
502	AB0505	36	7	8	40	140	0.3	19	8	4.1	1.7	93	7.5	84	2.7	2.9	<20	14.90	2.00
503	AB0506	32	10	7	43	130	0.7	27	13	6.2	2.9	78	8.3	113	11.5	11.0	<20	18.10	2.56
504	AB0507	24	11	9	43	45	0.3	13	14	3.6	2.0	32	8.2	117	6.2	6.7	<20	21.60	2.98
505	AB0508	48	13	12	64	66	0.3	8	9	2.8	2.2	57	11.0	136	4.9	5.0	<20	25.60	3.64
506	AB0509	48	11	13	64	44	0.4	6	7	2.8	2.3	69	10.0	126	9.0	8.0	<20	27.10	3.67
507	AB0510	34	13	12	60	58	0.5	15	7	3.7	2.4	74	13.0	129	8.2	7.9	<20	28.70	3.92
508	AB0511	<5	<4	1	18	80	0.5	9	10	1.7	<0.5	25	2.8	20	2.0	3.4	<20	3.42	0.51
509	AB0512	<5	<4	1	17	67	0.3	8	9	1.5	<0.5	19	2.2	15	1.5	2.7	<20	3.15	0.39
510	AB0513	<5	<4	2	14	94	0.3	7	10	1.3	<0.5	23	1.9	17	1.1	2.6	<20	2.94	0.45
511	AB0514	154	<4	1	20	140	1.2	45	36	6.2	<0.5	28	3.1	24	4.8	5.0	<20	4.39	0.67
512	AB0515	<5	<4	1	17	110	0.9	27	17	3.8	<0.5	25	4.0	26	3.6	4.7	<20	3.59	0.59
513	AB0516	<5	<4	2	22	110	1.3	48	34	6.5	<0.5	26	2.6	32	7.4	8.0	<20	4.35	0.65
514	AB0501	36	8	7	31	170	0.8	65	33	11.0	2.6	84	11.0	118	11.0	10.0	<20	17.20	2.37
515	AB0602	38	7	7	30	140	1.0	71	47	12.0	3.0	78	13.0	100	13.3	12.0	<20	16.20	2.20
516	AB0603	19	7	5	25	110	0.9	44	32	7.7	1.1	41	5.8	63	5.3	5.5	<20	9.42	1.34
517	AB0604	49	11	7	38	140	0.7	49	21	9.6	2.9	85	11.0	126	14.9	14.0	<20	19.20	2.58
518	AB0605	28	11	7	45	140	0.6	24	14	5.5	2.6	82	10.0	116	8.9	9.2	<20	18.60	2.56
519	AB0606	33	8	6	35	100	0.3	35	7	4.7	1.5	100	6.6	98	5.5	5.7	<20	13.90	1.96
520	AB0607	38	9	9	45	120	0.4	28	9	4.7	1.8	80	8.6	114	8.9	9.3	<20	19.20	2.54
521	AB0608	44	10	9	44	100	0.6	26	10	7.1	2.1	73	9.8	113	7.6	8.2	<20	20.50	2.81
522	AB0609	51	11	9	42	110	0.6	19	15	4.9	1.8	69	9.0	110	7.1	8.0	<20	21.20	2.88
523	AB0610	32	8	10	41	130	0.5	40	21	6.4	2.2	83	8.5	98	7.6	7.9	<20	16.80	2.24
524	AB0611	37	10	9	53	94	0.9	28	24	7.3	2.8	68	15.0	139	9.3	10.0	<20	21.40	2.80
525	AB0612	<5	4	1	16	110	0.5	11	10	1.9	<0.5	28	3.8	21	1.9	2.7	<20	3.44	0.45
526	AB0613	<5	6	2	16	82	0.5	8	3	1.5	<0.5	24	3.6	18	1.6	2.6	<20	3.06	0.40
527	AB0614	<5	<4	2	17	120	0.9	16	14	2.9	<0.5	31	3.0	16	1.9	3.2	<20	3.32	0.39
528	AB0615	<5	5	2	18	140	1.1	38	40	5.7	<0.5	24	3.7	23	5.1	3.8	<20	3.39	0.45
529	AB0616	7	<4	3	24	120	1.1	44	33	5.6	<0.5	33	6.6	34	4.4	5.8	<20	4.39	0.60
530	AB0617	15	<4	3	24	86	0.7	22	18	3.3	1.1	35	8.1	27	4.0	4.6	<20	3.85	0.50
531	AB0701	24	7	7	37	100	0.8	40	33	8.2	2.1	55	11.0	107	12.0	15.0	<20	17.50	2.15
532	AB0702	23	9	5	29	120	1.1	52	37	8.9	1.6	77	12.0	85	7.4	11.0	<20	12.00	1.45
533	AB0703	27	8	5	32	120	0.6	42	29	7.2	2.0	74	12.0	95	6.3	12.0	<20	14.30	1.95
534	AB0704	31	9	6	38	110	0.5	21	14	5.8	2.9	63	9.9	107	9.4	17.0	<20	16.50	1.99
535	AB0705	38	14	8	50	170	1.3	72	65	16.0	3.6	99	15.0	131	18.3	22.0	<20	17.80	2.20
536	AB0706	38	10	7	39	170	1.5	120	85	23.0	5.4	67	17.0	211	27.8	36.0	<20	31.00	4.25
537	AB0707	35	10	8	39	110	1.0	38	29	9.2	2.9	85	13.0	110	15.4	15.0	<20	17.50	1.95
538	AB0708	35	10	8	44	95	0.9	29	27	9.1	2.8	71	15.0	135	13.1	19.0	<20	21.50	2.92
539	AB0709	39	8	9	47	100	0.8	44	38	13.0	4.5	68	20.0	190	19.3	27.0	<20	28.50	3.45
540	AB0710	28	11	7	41	140	0.9	45	27	5.9	1.5	57	16.0	65	7.3	9.2	<20	9.80	1.46
541	AB0711	<5	4	1	15	81	0.5	10	10	1.7	<0.5	22	3.4	19	1.4	2.7	<20	2.71	0.32
542	AB0712	<5	<4	1	18	120	0.8	18	18	3.1	<0.5	28	2.3	21	1.6	3.7	<20	3.46	0.45
543	AB0713	<5	<4	2	18	63	0.8	14	13	2.4	<0.5	20	3.4	21	4.3	3.5	<20	3.52	0.48
544	AB0714	<5	4	3	21	67	1.0	34	24	4.8	<0.5	19	7.1	30	4.4	5.4	<20	3.65	0.47
545	AB0715	12	<4	5	38	88	0.9	44	30	6.2	1.2	30	6.7						

付表4 土壤地化学試料分析値一覽表

(7)

NO	SP.No. unit	Sn ppm	W ppm	Ta ppm	Nb ppm	Ce ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
566	AD0020	41	7	8	42	110	0.6	43	40	10.0	3.1	64	11.0	139	15.6	20.0	<20	21.00	2.78
567	AD0021	40	10	6	41	130	0.6	27	22	6.4	2.5	79	9.9	120	7.4	17.0	<20	17.30	2.34
568	AD0022	39	7	8	41	110	0.7	33	33	8.2	2.0	69	9.2	125	11.1	18.0	<20	18.40	2.55
569	AD0023	12	9	5	37	86	0.7	37	28	4.9	1.2	40	6.9	60	4.9	8.1	<20	8.42	1.21
570	AD0024	16	8	6	38	100	0.7	35	25	5.0	1.3	40	6.7	60	6.1	8.5	<20	9.21	1.31
571	AD0025	25	9	5	32	160	1.3	72	55	11.0	2.0	74	14.0	87	13.0	14.0	<20	11.90	1.55
572	AD0026	32	6	6	31	100	1.1	49	43	7.9	1.0	39	11.0	55	8.0	8.1	<20	7.79	1.09
573	AD0027	34	<4	6	30	130	1.3	59	49	8.1	1.4	33	15.0	39	6.1	7.4	<20	5.27	0.71
574	AD0028	15	4	4	32	140	0.9	59	30	8.6	2.0	55	9.5	70	11.0	10.0	<20	7.30	0.98
575	AD0029	16	7	6	35	160	1.0	72	58	9.8	1.0	85	7.9	80	6.6	11.0	<20	9.53	1.31
576	AD0030	20	<4	5	32	300	1.9	120	97	20.0	3.0	99	17.0	126	20.0	20.0	<20	11.90	2.14
577	AD0031	23	<4	6	34	170	1.3	77	59	13.0	3.0	84	11.0	109	15.9	16.0	<20	16.60	2.24
578	AD0032	20	7	6	37	160	1.3	78	56	12.0	2.6	65	13.0	100	14.5	14.0	<20	14.60	2.01
579	AD0033	16	7	6	38	160	0.9	65	45	8.8	2.3	50	16.0	91	13.0	13.0	<20	13.80	1.87
580	AD0034	41	7	6	36	150	1.3	74	59	13.0	3.2	71	11.0	107	14.5	14.0	<20	15.00	1.99
581	AD0035	25	8	6	39	150	0.9	60	46	8.5	1.7	61	8.3	67	8.9	13.0	<20	12.60	1.69
582	AD0036	27	9	6	37	150	1.0	62	50	11.0	2.6	70	7.6	98	12.6	15.0	<20	15.60	2.07
583	AD0037	42	8	8	41	130	0.9	52	40	8.0	2.2	65	7.4	91	6.1	13.0	<20	14.70	1.99
584	AD0038	46	11	7	39	140	1.0	66	48	10.0	2.4	65	11.0	106	9.0	13.0	<20	15.40	2.12
585	AD0039	26	9	5	27	230	1.7	81	64	12.0	0.7	81	10.0	57	7.5	10.0	<20	6.94	0.95
586	AD0020	22	<4	3	25	230	1.4	72	52	9.6	0.6	80	8.2	46	8.9	8.8	<20	4.05	0.63
587	AD0021	24	11	4	32	120	1.3	59	44	8.4	1.6	61	9.3	63	6.8	8.9	<20	7.56	1.08
588	AD0022	32	10	4	25	170	1.5	77	53	11.0	2.9	61	8.4	77	9.5	11.0	<20	8.62	1.14
589	AD0023	46	9	6	30	160	1.6	85	57	13.0	2.5	57	15.0	84	13.0	14.0	<20	9.54	1.31
590	AD1002	<5	4	1	18	43	<0.2	5	8	0.9	<0.5	21	2.0	15	0.9	2.1	<20	3.20	0.43
591	AD1003	<5	<4	2	18	150	0.6	11	30	1.9	<0.5	27	3.7	20	2.1	3.6	<20	3.39	0.45
592	AD1004	13	8	4	37	91	0.8	39	13	4.9	<0.5	40	8.1	59	4.4	7.7	<20	9.56	1.39
593	AD1005	13	7	8	39	110	0.7	38	23	5.7	1.1	42	7.8	71	6.6	8.8	<20	10.70	1.55
594	AD1006	21	8	5	36	130	1.0	51	33	7.8	1.3	49	11.0	86	12.8	11.0	<20	12.30	1.72
595	AD1007	34	<4	7	38	100	1.3	53	28	7.2	<0.5	27	11.0	45	8.0	7.7	<20	5.73	0.73
596	AD1008	24	6	7	41	120	0.9	33	17	4.8	<0.5	35	11.0	36	5.1	5.4	<20	4.94	0.65
597	AD1009	25	<4	4	25	130	1.1	53	27	8.2	<0.5	42	10.0	50	5.5	8.4	<20	6.11	0.93
598	AD1010	13	7	6	39	100	1.0	64	29	9.2	2.0	73	11.0	85	10.1	13.0	<20	12.20	1.67
599	AD1011	11	<4	6	48	170	1.0	72	42	12.0	3.1	65	9.7	114	13.6	15.0	<20	16.40	2.18
600	AD1012	27	<4	5	39	130	0.9	56	26	9.4	2.2	69	7.7	117	13.3	15.0	<20	16.50	2.30
601	AD1013	31	<4	8	42	120	0.6	34	14	6.4	1.7	71	6.0	110	13.0	15.0	<20	16.60	2.24
602	AD1014	25	7	6	30	150	1.0	74	44	11.0	2.4	80	9.3	78	9.8	11.0	<20	11.40	1.54
603	AD1015	31	9	8	38	130	0.9	48	26	11.0	2.5	84	12.0	130	12.5	17.0	<20	21.20	2.79
604	AD1016	15	6	4	35	100	0.9	57	30	7.8	1.0	91	7.9	68	9.7	8.2	<20	9.80	1.31
605	AD1017	17	10	7	52	120	0.7	43	22	5.5	1.3	62	8.7	73	6.0	9.3	<20	11.20	1.57
606	AD1018	27	7	7	36	93	0.9	42	11	6.1	1.4	39	13.0	74	7.9	10.0	<20	11.70	1.55
607	AD1019	27	8	4	32	150	1.2	64	39	11.0	1.8	65	7.8	60	7.9	9.7	<20	8.37	1.11
608	AD1020	22	5	2	29	170	1.7	85	46	13.0	2.3	73	9.3	71	12.7	10.0	<20	9.22	1.20
609	AD1021	25	11	6	29	200	2.3	140	78	18.0	3.5	67	17.0	77	15.3	12.0	<20	33.80	4.15
610	AD1022	21	7	4	31	170	1.0	58	40	8.0	0.7	60	7.2	50	7.3	6.9	<20	6.32	0.97
611	AD1023	22	8	4	34	150	1.4	77	47	10.0	1.2	67	9.8	70	10.9	10.0	<20	8.25	1.11
612	AD1024	26	10	6	34	160	1.2	72	34	10.0	1.8	55	9.8	59	9.2	8.0	<20	7.08	1.01
613	AD1102	<5	<4	1	15	70	0.2	9	8	1.5	<0.5	25	3.8	20	0.9	3.0	<20	2.94	0.46
614	AD1103	<5	<4	2	22	65	0.4	17	10	2.6	<0.5	29	4.1	26	4.0	4.0	<20	4.36	0.63
615	AD1104	31	11	6	38	160	1.7	96	61	16.0	3.7	74	14.0	107	14.1	16.0	<20	16.10	2.21
616	AD1105	28	9	8	37	140	1.8	97	73	17.0	3.8	78	14.0	102	18.9	16.0	<20	15.10	2.04
617	AD1106	28	<4	5	30	150	1.6	85	48	13.0	2.2	61	16.0	92	13.9	13.0	<20	12.30	1.75
618	AD1107	47	<4	4	28	120	1.5	52	35	8.8	0.9	34	13.0	43	8.6	8.0	<20	7.05	0.94
619	AD1108	21	<4	4	25	120	1.0	57	25	7.4	1.7	36	7.4	49	8.9	8.0	<20	6.11	0.84
620	AD1109	15	<4	3	25	120	1.0	58	32	6.3	1.7	50	6.0	52	9.2	7.0	<20	6.82	0.89
621	AD1110	20	9	6	37	200	1.1	72	39	9.7	2.2	83	9.9	84	12.3	12.0	<20	12.20	1.73
622	AD1111	16	8	9	57	150	0.9	75	44	11.0	2.5	55	7.0	137	14.6	18.0	<20	21.60	2.83
623	AD1112	20	<4	7	39	99	0.7	36	21	6.6	3.3	58	5.7	145	10.9	10.0	<20	23.50	3.15
624	AD1113	27	<4	5	29	160	1.0	64	50	12.0	2.4	92	8.8	75	13.2	13.0	<20	11.30	1.46
625	AD1114	20	8	5	35	160	1.1	68	33	9.2	2.0	92	8.9	74	9.8	10.0	<20	10.30	1.49
626	AD1115	28	6	5	32	170	3.1	120	83	24.0	5.0	94	14.0	142	27.8	25.0	<20	17.60	2.29
627	AD1116	26	10	5	37	160	1.1	58	30	8.8	1.2	63	7.8	78	10.6	11.0	<20	11.10	1.38
628	AD1117	14	8	4	32	210	0.9	45	28	6.5	2.1	73	7.8	70	6.0	9.0	<20	11.10	1.46
629	AD1118	11	10	4	27	200	2.0	110	73	18.0	3.4	66	22.0	97	10.8	15.0	<20	13.10	1.80
630	AD1119	20	9	4	31	120	1.0	41	12	6.4	1.9	73	7.7	61	7.3	8.5	<20	8.99	1.21
631	AD1120	25	7	4	34	170	1.0	59	35	8.9	1.3	71	7.3	98	8.0	12.0	<20	12.30	1.65
632	AD1121	25	8	4	25	130	2.1	88	63	15.0	1.0	64	11.0	80	12.8	11.0	<20	8.06	1.11
633	AD1122	25	15	5	33	160	1.8	80	52	12.0	1.0	66	9.6	67	11.0	11.0	<20	9.18	1.15
634	AD1123	22	10	3	25	190	1.1	50	16	6.9	1.5	71	14.0	53	7.9	8.0	<20	6.26	0.80
635	AD1124	16	9	5	31	180	3.1	110	85	20.0	2.7	63	11.8	94	21.1	14.0	<20	9.81	1.22
636	AD1201	14	11	7	37	220	1.6	130	67	18.0	3.6	78	19.0	126	16.2	23.0	<20	27.10	3.45
637	AD1202	19	8	6	36	170	1.1	64	41	8.7	1.3	67	13.0	70	10.7	10.0	<20	11.90	1.58
638	AD1203	9	<4	2	28	110	0.6	24	17	3.4	<0.5	28	3.7	26	2.2	4.4	<20	3.90	0.55
639	AD1204	16	7	4	39	130	1.1	62	33	8.									

附表4 土壤地化学試料分析值一覽表

(8)

NO	SP.No. unit	Sn ppm	H ppm	Ta ppm	Nb ppm	Co ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
660	AB1304	30	5	3	37	65	0.6	30	22	5.0	1.0	28	5.6	07	0.6	11.0	<20	0.01	1.11
661	AB1305	<5	<4	2	22	110	0.9	32	23	4.6	0.9	29	5.1	30	3.7	5.0	<20	4.89	0.65
662	AB1306	<5	<4	1	22	130	0.8	23	14	3.8	0.7	32	3.5	27	2.1	4.0	<20	4.23	0.56
663	AB1307	<5	<4	2	22	83	0.6	12	18	2.1	<0.5	30	3.5	20	5.1	3.0	<20	3.57	0.54
664	AB1308	22	<4	5	33	93	0.6	32	13	4.4	0.7	28	7.9	38	3.5	5.0	<20	5.71	0.74
665	AB1309	24	<4	5	42	97	0.5	35	21	4.0	0.7	30	6.2	43	5.3	6.3	<20	5.67	0.74
666	AB1310	9	8	5	40	190	0.9	71	34	8.6	2.3	72	6.8	71	7.1	10.0	<20	10.50	1.49
667	AB1311	19	6	6	40	150	1.0	56	34	7.3	1.6	81	7.2	89	7.5	10.0	<20	13.70	1.83
668	AB1312	18	<4	5	39	260	0.8	65	29	8.6	2.2	86	9.1	95	9.2	12.0	<20	14.80	2.09
669	AB1313	20	<4	7	39	190	1.1	75	41	10.0	2.9	78	6.5	95	9.8	13.0	<20	15.20	1.99
670	AB1314	32	<4	6	36	160	0.7	60	30	7.5	2.1	75	6.7	86	8.4	12.0	<20	13.20	1.62
671	AB1315	31	<4	5	32	160	1.2	77	45	11.0	2.7	80	10.0	88	9.9	12.0	<20	12.80	1.62
672	AB1316	42	<4	7	38	140	0.8	59	25	8.3	1.3	65	18.0	85	9.0	8.0	<20	12.20	1.69
673	AB1317	30	<4	5	33	200	1.4	130	84	17.0	2.5	100	18.0	93	14.6	14.0	<20	12.80	1.70
674	AB1318	17	7	4	29	190	0.8	57	33	7.5	1.3	82	7.6	64	10.6	8.7	<20	9.08	1.17
675	AB1319	25	10	4	31	180	0.8	41	25	5.9	0.9	86	8.4	46	6.7	6.3	<20	6.12	0.81
676	AB1320	24	11	4	29	180	1.1	61	40	10.0	1.4	68	9.5	63	9.8	9.0	<20	8.39	1.07
677	AB1321	16	8	4	31	170	1.1	44	24	6.7	1.4	66	3.4	53	7.1	7.6	<20	7.72	1.04
678	AB1322	19	10	6	36	160	0.8	42	20	5.8	1.4	68	6.2	70	4.7	9.0	<20	10.10	1.44
679	AB1323	22	9	4	31	190	1.6	99	53	12.0	1.0	75	11.0	65	11.6	8.7	<20	8.46	1.06
680	AB1324	23	9	5	32	170	0.7	40	18	5.5	1.0	71	6.4	63	6.5	8.0	<20	8.53	1.16
681	AB1325	27	6	4	29	190	1.3	77	52	11.0	1.0	69	9.7	56	9.7	11.0	<20	8.59	1.11
682	AB1326	27	14	4	27	190	1.2	71	41	9.5	1.4	72	8.6	53	8.9	9.0	<20	5.29	0.70
683	AB1403	<5	7	1	21	110	0.7	22	15	3.0	0.7	29	4.0	25	4.3	4.2	<20	4.71	0.63
684	AB1404	26	<4	6	33	190	1.7	96	74	19.0	3.6	53	12.0	130	19.6	19.0	<20	23.10	3.10
685	AB1405	25	7	7	32	170	1.6	75	56	15.0	2.7	53	11.0	114	16.8	17.0	<20	18.70	2.52
686	AB1406	8	<4	3	27	70	0.8	30	17	4.1	0.7	24	4.1	34	4.8	4.2	<20	4.91	0.70
687	AB1407	<6	7	3	26	85	0.6	15	10	2.5	<0.5	20	3.0	24	2.4	3.5	<20	4.39	0.60
688	AB1408	<5	<4	1	19	120	0.6	12	10	2.2	<0.5	26	3.4	20	3.7	3.5	<20	3.22	0.46
689	AB1409	8	<4	3	24	180	0.8	35	21	4.5	<0.5	26	4.5	31	3.6	4.7	<20	4.33	0.50
690	AB1410	12	<4	2	23	120	0.9	43	29	6.1	1.0	28	6.3	55	7.3	6.9	<20	5.22	0.69
691	AB1411	24	13	5	39	140	1.0	59	43	8.7	1.5	75	7.3	84	7.9	11.0	<20	10.70	1.44
692	AB1412	19	9	6	45	160	0.9	70	50	10.0	1.9	76	6.7	96	9.4	13.0	<20	14.50	1.90
693	AB1413	26	<4	7	47	160	0.8	62	46	9.6	1.9	74	7.6	101	11.5	16.0	<20	15.60	2.10
694	AB1414	29	<4	6	41	130	0.8	61	30	9.8	1.5	58	7.3	94	10.0	12.0	<20	14.70	1.90
695	AB1415	28	<4	6	37	160	0.9	56	35	9.9	1.9	75	7.4	98	13.1	15.0	<20	14.60	1.97
696	AB1416	30	6	6	42	160	1.8	100	72	21.0	4.5	94	12.0	162	20.5	25.0	<20	21.60	2.83
697	AB1417	36	6	5	37	200	1.1	67	38	12.0	2.3	79	7.6	107	12.2	16.0	<20	15.40	1.96
698	AB1418	41	14	7	39	260	2.4	150	110	27.0	3.6	110	23.0	134	25.8	20.0	<20	18.00	2.46
699	AB1419	27	8	5	34	180	0.7	56	36	7.6	1.5	77	7.3	74	7.5	10.0	<20	10.70	1.48
700	AB1420	25	11	5	31	170	1.0	45	33	8.2	1.9	65	6.2	67	5.1	8.4	<20	9.42	1.27
701	AB1421	26	10	4	31	180	1.1	41	29	8.1	1.7	66	9.5	54	9.6	9.4	<20	7.61	1.06
702	AB1422	26	9	3	27	220	2.7	130	90	22.0	1.1	67	7.3	80	17.4	13.0	<20	8.04	1.02
703	AB1423	36	11	4	29	190	0.9	37	19	5.1	1.2	61	6.5	47	4.5	6.2	<20	5.86	0.78
704	AB1424	23	10	4	32	180	0.7	39	21	5.9	1.1	63	6.9	57	6.5	7.8	<20	7.63	1.04
705	AB1425	21	9	3	26	210	1.0	53	35	8.5	2.0	69	8.8	49	5.8	6.5	<20	6.60	0.80
706	AB1426	27	6	5	31	180	0.9	45	24	5.7	1.4	47	10.0	68	8.4	8.0	<20	8.58	1.12
707	AB1427	22	11	3	32	190	1.1	48	30	7.6	1.4	54	7.7	64	7.1	8.7	<20	8.16	1.06
708	AB1501	<5	<4	1	21	89	0.9	30	20	4.3	0.9	26	3.5	27	4.9	5.0	<20	4.52	0.58
709	AB1502	27	8	5	33	110	1.0	64	30	7.8	1.9	37	8.3	91	11.2	12.0	<20	13.60	1.82
710	AB1503	26	7	5	36	130	1.3	59	46	12.0	2.1	47	9.8	87	11.8	13.0	<20	13.40	1.76
711	AB1504	<5	9	1	17	93	0.6	16	14	2.4	<0.5	23	4.0	21	1.2	3.2	<20	2.70	0.52
712	AB1505	<5	<4	1	19	99	0.4	14	10	2.2	0.8	25	3.2	24	2.2	3.4	<20	3.21	0.53
713	AB1506	<5	<4	2	22	100	0.7	21	19	3.3	<0.5	27	2.4	25	3.3	3.7	<20	3.54	0.54
714	AB1507	<5	9	1	21	110	0.9	23	22	3.6	<0.5	24	3.3	24	2.6	3.2	<20	3.48	0.53
715	AB1508	<5	8	1	16	140	1.1	40	32	5.8	<0.5	32	5.6	29	5.7	5.0	<20	3.84	0.61
716	AB1509	30	4	3	26	97	1.0	45	28	8.0	1.5	29	7.7	50	5.7	7.9	<20	5.90	0.75
717	AB1510	42	10	6	33	170	1.1	56	43	9.3	2.3	64	7.7	78	10.9	12.0	<20	10.30	1.47
718	AB1511	30	<4	7	43	140	1.2	52	42	9.0	2.7	60	9.1	108	10.6	14.0	<20	18.40	2.39
719	AB1512	26	<4	4	31	190	1.2	75	58	12.0	1.7	70	10.0	82	11.4	12.0	<20	11.90	1.57
720	AB1513	9	<4	3	24	140	1.1	64	45	10.0	1.6	45	6.6	76	9.2	12.0	<20	8.81	1.18
721	AB1514	25	10	8	41	130	1.0	50	38	9.2	2.5	54	7.1	112	10.1	17.0	<20	17.60	2.37
722	AB1515	39	<4	5	33	170	0.8	51	35	9.5	2.7	79	5.6	91	7.9	13.0	<20	14.00	1.84
723	AB1516	23	9	6	38	140	0.9	49	34	9.1	2.5	62	7.9	96	9.8	12.0	<20	14.20	1.89
724	AB1517	32	7	6	37	160	0.6	50	28	9.2	2.0	73	7.0	91	9.1	12.0	<20	13.10	1.74
725	AB1518	34	<4	5	42	170	0.5	46	25	7.8	1.5	68	7.5	92	8.3	14.0	<20	12.80	1.60
726	AB1519	14	11	6	30	170	0.9	47	26	8.5	1.6	68	6.3	89	12.1	15.0	<20	12.60	1.66
727	AB1520	27	<4	4	29	200	1.4	57	36	10.0	1.1	69	9.7	63	12.0	9.1	<20	7.87	1.06
728	AB1521	29	<4	4	28	200	0.7	48	25	7.0	1.3	70	5.8	70	9.2	10.0	<20	10.60	1.42
729	AB1522	26	<4	3	22	220	1.4	77	56	13.0	0.9	89	9.9	62	12.2	11.0	<20	7.89	1.06
730	AB1523	26	11	5	30	160	1.0	89	64	17.0	1.3	60	8.4	81	12.5	11.0	<20	10.20	1.30
731	AB1524	31	10	3	25	230	1.4	70	48	9.4	0.9	66	5.8	53	6.8	6.5	<20	5.86	0.82
732	AB1525	21	8	4	29	190	<0.2	39	21	5.2	0.7	62	5.9	51	4.1	3.7	<20	6.90	0.90
733	AB1601	20	5	3	19	110	1.4	54	38	8.0	1.4	28	6.1	44	6.0				

付表4 土壤化学試料分析値一覽表

(9)

NO	SP.No. unit	Sn ppm	H ppm	Ta ppm	Nb ppm	Ce ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
754	AB1622	23	<4	3	16	240	0.6	93	36	6.2	0.9	81	8.2	47	6.9	5.2	20	5.01	0.68
755	AB1623	25	7	4	30	180	1.0	67	35	6.9	1.0	72	8.1	71	3.3	9.4	<20	9.23	1.14
756	AB1624	10	10	4	26	180	1.5	78	56	11.0	1.7	67	16.0	64	9.7	9.5	<20	7.76	0.99
757	AB1625	22	12	3	29	230	1.0	81	30	7.6	1.0	77	9.4	54	5.9	6.2	<20	5.98	0.83
758	AB1626	18	<4	4	23	180	1.3	85	62	10.0	2.1	72	9.7	76	9.3	10.0	<20	8.13	1.09
759	AB1627	25	11	4	30	200	1.5	90	62	12.0	2.1	69	8.4	66	11.1	10.0	<20	6.93	0.91
760	AB1628	28	11	4	29	190	1.2	62	40	7.6	1.3	66	8.8	55	6.3	7.0	<20	5.93	0.81
761	AB1629	25	<4	6	32	170	0.7	59	29	5.3	1.0	64	6.4	48	8.5	6.0	<20	5.86	0.83
762	AB1630	21	8	4	36	120	0.6	47	19	4.7	0.9	68	6.5	53	4.3	6.5	<20	5.51	0.76
763	AB1701	<5	<4	3	24	72	0.7	33	25	4.1	0.6	25	4.7	34	4.7	4.5	<20	4.89	0.71
764	AB1702	22	9	7	40	140	1.4	81	57	12.0	3.1	54	12.0	126	17.6	17.0	<20	17.00	2.34
765	AB1703	30	<4	6	35	130	1.2	66	58	10.0	2.1	65	11.0	92	12.3	12.0	<20	11.10	1.51
766	AB1704	<5	6	1	18	41	0.6	17	11	2.3	<0.5	19	3.8	24	3.4	3.5	<20	3.03	0.44
767	AB1705	<5	5	1	17	75	0.6	17	17	2.8	<0.5	26	3.8	23	2.4	3.3	<20	3.21	0.47
768	AB1706	8	7	2	20	110	0.6	17	10	2.5	0.6	29	5.1	21	2.5	3.1	<20	3.44	0.50
769	AB1707	35	10	7	35	160	1.3	76	61	11.0	2.0	61	13.0	95	13.1	11.0	<20	12.10	1.64
770	AB1708	<5	7	1	20	140	1.1	59	43	7.1	1.1	30	12.0	37	6.2	6.1	<20	4.48	0.57
771	AB1709	41	4	4	29	91	0.8	52	35	6.4	1.2	28	9.1	47	7.1	7.8	<20	5.26	0.68
772	AB1710	39	8	6	65	150	1.1	72	44	9.0	1.3	45	6.4	131	9.8	12.0	<20	10.20	1.34
773	AB1711	70	<4	8	79	130	0.9	63	43	9.7	2.6	69	8.0	200	13.1	16.0	<20	18.00	2.40
774	AB1712	51	<4	5	61	170	0.9	61	33	8.9	2.4	75	7.6	167	10.7	16.0	<20	14.00	1.91
775	AB1713	44	9	6	37	220	1.6	98	73	15.0	2.9	76	13.0	122	16.0	16.0	<20	13.10	1.81
776	AB1714	57	<4	4	34	260	2.3	170	140	28.0	2.9	97	9.5	129	20.5	20.0	<20	12.70	1.76
777	AB1715	<5	7	7	92	93	0.8	45	29	7.1	1.5	42	6.2	161	9.8	13.0	<20	11.70	1.61
778	AB1716	180	10	5	26	160	1.0	61	44	9.3	2.2	61	7.4	110	11.3	12.0	<20	12.90	1.64
779	AB1717	<5	<4	5	43	120	0.7	42	29	7.3	1.7	53	7.2	134	9.2	11.0	<20	11.00	1.38
780	AB1718	31	5	5	40	120	0.5	33	19	4.9	2.3	43	5.4	123	7.2	13.0	<20	12.50	1.64
781	AB1719	180	7	6	68	130	0.6	31	17	4.8	1.2	64	8.6	113	6.9	10.0	<20	11.00	1.52
782	AB1720	68	6	4	66	180	1.3	70	45	9.4	1.9	64	11.0	85	9.8	10.0	<20	7.50	0.99
783	AB1721	199	7	3	<2	160	0.8	47	31	5.5	0.7	57	9.1	108	6.8	5.8	<20	4.96	0.66
784	AB1722	15	26	13	111	530	5.3	360	240	49.8	7.5	210	38.0	46	16.0	13.0	<20	26.80	3.58
785	AB1723	501	10	4	<2	190	0.7	43	21	5.8	1.3	71	6.7	260	5.5	6.3	<20	6.95	1.05
786	AB1724	5	5	3	51	120	0.7	55	33	7.4	1.3	78	7.2	<2	10.3	8.7	<20	5.79	0.78
787	AB1725	<5	6	4	88	160	1.1	65	46	9.7	1.7	57	6.8	220	9.0	8.2	<20	5.05	0.70
788	AB1726	55	10	5	125	140	1.0	50	33	5.8	1.3	55	9.2	59	6.5	6.5	<20	7.73	1.02
789	AB1801	65	7	4	34	120	0.8	54	38	7.2	1.2	40	8.5	121	5.3	6.9	<20	6.13	0.84
790	AB1802	<5	7	5	111	120	0.9	66	48	11.0	2.7	55	9.6	256	12.8	12.8	<20	9.33	1.28
791	AB1803	145	<4	4	114	110	1.0	60	41	9.0	1.8	55	8.4	655	9.8	11.0	<20	8.79	1.13
792	AB1804	41	5	2	31	140	0.9	29	25	4.4	1.2	23	4.9	71	3.2	4.6	<20	3.63	0.48
793	AB1805	287	<4	1	38	66	0.6	20	14	2.6	0.7	22	3.3	79	2.9	3.3	<20	3.07	0.40
794	AB1806	37	<4	2	27	84	0.9	43	26	5.2	<0.5	25	4.8	25	3.6	5.3	<20	4.04	0.55
795	AB1807	<5	7	2	18	100	0.9	32	26	4.2	<0.5	27	3.1	43	2.8	4.3	<20	3.50	0.52
796	AB1808	79	10	1	30	85	1.1	59	37	6.3	<0.5	31	4.0	44	5.6	6.2	<20	4.03	0.58
797	AB1809	<5	<4	2	18	99	0.6	22	12	3.0	<0.5	29	5.9	28	2.5	4.4	<20	3.42	0.47
798	AB1810	29	<4	3	25	60	0.5	18	11	2.5	<0.5	28	5.3	33	5.0	4.9	<20	2.75	0.39
799	AB1811	17	<4	2	23	110	0.8	54	27	6.9	0.9	73	4.9	52	8.1	8.3	<20	5.31	0.72
800	AB1812	30	<4	5	37	140	1.0	72	53	11.0	2.4	78	7.2	105	13.4	14.0	<20	11.30	1.54
801	AB1813	35	<4	6	36	140	1.0	76	50	11.0	2.5	88	7.9	195	12.6	16.0	<20	12.10	1.61
802	AB1814	42	10	6	36	180	0.9	64	41	10.0	2.7	79	8.5	127	12.9	15.0	<20	16.50	2.19
803	AB1815	35	8	5	34	170	1.0	56	42	9.4	2.2	75	11.0	94	10.9	13.0	<20	11.70	1.59
804	AB1816	53	6	4	32	170	1.4	84	65	13.0	2.5	77	10.0	101	14.9	21.0	<20	13.30	1.79
805	AB1817	53	6	7	35	150	1.3	95	63	14.0	2.6	61	10.0	107	18.7	21.0	<20	12.60	1.63
806	AB1818	183	7	6	17	130	0.9	58	36	7.0	1.7	50	5.6	166	6.3	13.0	<20	11.10	1.54
807	AB1819	48	<4	5	32	160	1.1	68	52	11.0	2.4	67	8.8	91	12.4	11.0	<20	10.80	1.44
808	AB1820	50	8	6	28	170	1.2	77	57	12.0	2.1	62	11.0	95	11.6	13.0	<20	13.30	1.75
809	AB1821	32	<4	3	26	190	1.6	87	74	17.0	2.4	86	9.2	89	16.3	13.0	<20	9.66	1.26
810	AB1822	19	<4	3	24	140	1.2	62	46	9.3	1.8	63	9.5	80	10.1	12.0	<20	8.01	1.05
811	AB1823	21	8	3	36	160	1.4	67	48	10.0	1.7	62	9.3	77	10.8	11.0	<20	8.11	1.08
812	AB1824	27	10	4	30	180	1.6	78	53	12.0	1.6	77	6.4	66	10.5	9.8	<20	6.54	0.10
813	AB1825	33	8	4	38	190	2.1	130	86	19.0	2.3	78	8.7	98	15.4	15.0	<20	10.80	1.46
814	AB1826	20	12	4	29	200	1.2	73	48	10.0	1.3	86	9.3	45	9.3	8.0	<20	6.54	0.87
815	AB1827	21	<4	5	29	160	1.3	72	43	11.0	1.3	68	10.0	61	10.3	11.0	<20	7.38	1.00
816	AB1901	<5	6	2	17	69	0.5	16	16	2.4	0.7	22	3.2	22	3.2	4.4	<20	3.91	0.59
817	AB1902	<5	8	1	17	180	0.8	22	18	3.5	0.5	27	3.5	30	4.6	4.2	<20	3.72	0.55
818	AB1903	<5	9	2	18	120	0.7	19	13	2.9	1.3	31	4.4	28	3.5	4.1	<20	3.88	0.54
819	AB1904	<5	8	2	14	120	1.1	57	36	6.5	0.7	29	8.3	31	7.8	5.2	<20	4.08	0.53
820	AB1905	34	<4	4	21	100	0.9	30	22	4.6	0.7	48	6.4	31	4.2	5.6	<20	4.22	0.54
821	AB1906	18	6	5	34	120	1.0	67	37	7.7	1.7	43	9.1	66	7.2	9.5	<20	8.47	1.14
822	AB1907	18	8	7	54	140	1.1	69	43	9.4	2.2	44	9.0	95	10.3	14.0	<20	15.20	1.97
823	AB1908	21	8	10	70	140	1.2	65	46	10.0	2.5	50	11.0	153	11.8	20.0	<20	23.80	3.04
824	AB1909	23	<4	8	59	150	0.9	51	28	8.7	2.8	51	8.2	158	14.7	19.0	<20	23.10	2.97
825	AB1910	44	7	6	39	140	1.2	70	47	11.0	2.4	58	9.6	114	13.2	17.0	<20	17.40	2.33
826	AB1911	42	<4	6	38	140	1.0	56	32	8.0	1.7	73	6.7	82	8.9	12.0	<20	12.20	1.71
827	AB1912	38	8	6	37	160	0.9	56	32	7.8	1.7								

附表4 土壤地化学試料分析値一覽表

(10)

NO	SP.No. unit	Sn ppm	W ppm	Ta ppm	Nb ppm	Co ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
848	AB2010	56	12	7	48	150	0.9	58	46	8.3	2.3	88	8.3	135	9.2	20.9	<20	19.90	2.97
849	AB2011	55	8	6	44	140	0.8	46	36	6.1	2.4	68	7.8	88	9.6	14.5	<20	13.00	1.88
850	AB2012	36	10	7	51	96	0.8	43	28	6.0	2.1	42	13.0	137	7.6	21.6	<20	21.10	2.90
851	AB2013	57	9	6	38	110	0.8	43	36	6.3	1.5	56	7.9	97	9.6	14.6	<20	11.70	1.90
852	AB2014	58	9	6	44	120	0.8	46	28	5.7	1.0	51	7.5	98	9.0	13.8	<20	12.50	1.84
853	AB2015	50	4	6	35	100	0.7	31	26	4.8	1.6	52	5.3	73	5.9	10.3	<20	9.55	1.47
854	AB2016	51	9	5	38	120	0.7	34	30	5.5	1.8	56	9.3	77	5.5	11.8	<20	11.10	1.72
855	AB2017	43	<4	6	38	140	0.8	56	39	7.9	2.0	64	7.3	96	7.4	13.6	<20	12.90	1.86
856	AB2018	42	5	5	32	170	1.1	71	51	8.8	0.7	73	11.0	72	8.8	11.8	<20	7.75	1.15
857	AB2019	36	6	5	39	96	0.7	32	19	3.5	1.1	53	7.1	64	8.7	10.7	<20	8.54	1.37
858	AB2020	37	9	5	31	160	1.0	64	40	6.3	0.7	67	9.2	54	6.6	8.7	<20	5.82	0.94
859	AB2021	36	10	4	36	130	0.9	52	28	5.6	1.3	52	7.1	52	6.4	8.1	<20	11.10	1.91
860	AB2021	12	8	3	21	78	0.6	36	23	3.8	0.8	28	4.6	34	6.3	5.2	<20	3.63	0.61
861	AB2102	27	6	4	30	180	1.0	66	58	8.3	1.9	90	8.1	77	2.6	11.8	<20	8.04	1.30
862	AB2103	33	10	5	31	180	1.0	58	44	7.3	2.3	92	9.6	79	7.4	11.6	<20	8.33	1.34
863	AB2104	43	7	6	30	180	1.1	95	62	11.0	2.3	82	9.5	118	7.7	18.3	<20	13.00	2.00
864	AB2105	37	13	6	50	120	0.7	53	35	6.5	2.0	68	9.5	101	11.2	16.2	<20	14.30	2.15
865	AB2106	48	<4	5	44	140	0.6	52	33	6.4	1.8	83	6.9	99	7.8	13.4	<20	12.10	1.95
866	AB2107	54	8	7	42	160	0.6	59	46	7.4	1.6	83	7.7	91	7.0	12.8	<20	11.70	1.82
867	AB2108	55	7	7	42	130	0.7	47	38	6.6	2.0	76	8.2	114	8.3	16.3	<20	17.10	2.56
868	AB2109	57	8	6	40	140	0.7	58	30	7.2	2.1	79	7.7	109	8.0	14.8	<20	14.40	2.11
869	AB2110	44	9	7	50	120	0.6	50	40	6.0	1.8	78	9.6	101	7.6	15.3	<20	14.80	2.25
870	AB2111	56	10	6	42	120	0.7	38	23	4.8	2.3	67	7.7	94	7.9	13.7	<20	13.20	2.00
871	AB2112	43	10	6	41	120	0.6	37	29	5.0	1.6	66	7.1	100	9.5	14.6	<20	12.70	2.00
872	AB2113	47	8	6	41	120	0.4	27	14	3.8	1.7	62	6.2	99	5.1	13.1	<20	11.90	1.92
873	AB2114	50	10	6	41	120	0.5	32	21	4.3	1.6	64	7.7	93	6.1	13.4	<20	12.30	1.89
874	AB2115	52	9	6	32	150	0.6	38	33	4.5	1.4	61	6.4	70	4.3	10.6	<20	10.10	1.56
875	AB2116	55	<4	5	31	130	0.8	46	40	6.4	1.5	51	9.7	78	6.7	11.3	<20	9.78	1.57
876	AB2117	39	11	6	36	180	0.8	47	28	5.8	1.2	59	11.0	72	5.8	11.2	<20	8.86	1.43
877	AB2118	34	9	5	42	110	0.7	33	21	4.2	1.0	41	9.2	72	4.4	11.1	<20	10.00	1.53
878	AB2119	41	8	4	35	160	0.7	39	26	4.5	1.0	67	5.5	66	5.9	9.3	<20	6.66	1.19
879	AB2120	24	6	4	35	89	0.7	49	38	4.7	1.2	36	5.7	51	5.4	7.1	<20	4.70	0.74
880	AB2121	21	9	4	39	120	0.8	59	40	6.7	1.1	33	5.9	56	11.0	8.7	<20	6.11	0.94
881	AB2122	45	<4	6	38	180	1.2	100	91	11.0	2.0	108	15.0	85	2.3	15.1	<20	10.20	1.56
882	AB2201	8	<4	3	22	76	0.7	26	19	3.8	<0.5	27	4.2	31	5.3	4.2	<20	3.38	0.61
883	AB2202	21	5	3	25	96	0.7	47	28	5.1	0.9	37	5.1	46	8.5	7.4	<20	4.73	0.74
884	AB2203	28	9	4	42	140	1.0	58	44	7.7	1.6	73	8.0	81	6.8	12.4	<20	7.76	1.31
885	AB2204	38	11	4	31	140	0.7	52	35	6.9	1.6	88	7.9	82	10.5	12.5	<20	8.33	1.34
886	AB2205	31	<4	5	48	140	0.9	59	46	7.9	1.9	83	9.1	95	8.3	14.7	<20	13.10	2.04
887	AB2206	42	8	6	37	110	0.6	41	33	6.1	1.5	45	8.5	105	11.6	15.0	<20	15.00	2.17
888	AB2207	58	<4	6	38	140	0.8	57	41	9.3	2.0	61	7.4	115	6.1	16.5	<20	13.80	2.21
889	AB2208	65	<4	6	36	130	0.4	35	25	4.4	1.4	65	6.0	108	9.2	13.7	<20	11.80	1.92
890	AB2209	59	<4	5	38	110	0.4	36	29	5.2	1.5	65	6.8	118	8.3	15.7	<20	13.40	1.92
891	AB2210	50	<4	7	43	140	0.4	38	21	4.7	1.5	73	6.8	91	6.5	13.9	<20	12.70	2.01
892	AB2211	51	13	5	41	180	0.5	44	32	5.1	1.3	78	10.8	82	5.1	12.0	<20	10.60	1.59
893	AB2212	54	<4	5	41	150	0.5	38	27	4.8	1.4	78	8.2	88	6.1	13.3	<20	12.60	1.81
894	AB2213	37	12	5	38	100	0.5	40	26	4.6	1.4	61	7.3	71	4.7	10.3	<20	8.71	1.35
895	AB2214	38	10	4	37	130	0.7	50	35	6.2	1.4	72	6.3	72	3.8	10.5	<20	7.43	1.25
896	AB2215	48	7	5	48	93	0.7	36	31	4.5	1.2	49	6.2	69	6.9	10.3	<20	3.02	1.32
897	AB2216	44	11	5	39	94	0.6	35	23	4.2	1.4	51	7.6	72	8.3	10.4	<20	8.66	1.45
898	AB2217	36	10	5	33	168	1.1	84	55	8.1	1.2	71	12.0	81	7.1	11.7	<20	8.45	1.31
899	AB2218	37	9	5	37	120	0.8	50	38	6.4	1.2	58	10.0	66	4.5	9.7	<20	8.23	1.25
900	AB2219	26	7	4	36	53	0.5	30	21	3.3	0.7	21	4.5	44	6.1	6.0	<20	4.79	0.73
901	AB2220	30	<4	5	41	110	0.8	59	35	6.6	1.1	49	7.7	69	5.5	9.7	<20	6.82	1.09
902	AB2221	33	<4	4	37	140	0.7	62	45	6.6	1.0	72	13.0	61	6.0	9.2	<20	6.30	1.22
903	AB2301	30	10	5	34	130	0.9	50	33	6.1	1.0	59	8.9	69	6.3	12.5	<20	10.10	1.59
904	AB2302	31	12	6	37	110	0.8	52	27	6.0	1.0	89	9.6	82	8.1	12.8	<20	10.30	1.52
905	AB2303	59	<4	5	38	130	0.8	51	38	7.8	2.0	67	7.8	118	10.0	16.2	<20	14.30	2.21
906	AB2304	61	<4	6	38	130	0.6	49	31	6.6	1.9	66	7.6	110	10.1	16.1	<20	14.70	2.16
907	AB2305	48	<4	5	27	110	0.8	56	48	9.3	2.4	54	7.5	126	8.8	18.0	<20	16.90	2.50
908	AB2306	67	6	7	48	130	0.6	37	28	6.3	2.4	60	7.7	117	7.0	16.1	<20	18.40	2.69
909	AB2307	45	<4	9	51	76	0.5	18	24	3.7	1.9	44	6.8	142	7.2	18.7	<20	28.80	3.13
910	AB2308	60	8	7	47	91	0.4	21	17	4.2	2.0	56	7.2	142	8.4	18.9	<20	21.10	3.86
911	AB2309	42	6	6	38	110	0.5	30	25	5.4	2.4	59	7.5	134	9.3	18.4	<20	19.00	2.78
912	AB2310	57	9	7	36	190	0.6	41	36	6.4	2.0	70	8.9	112	8.4	16.9	<20	16.90	2.50
913	AB2311	48	10	7	49	150	0.5	40	37	6.4	1.9	81	9.2	118	9.3	18.4	<20	18.60	2.78
914	AB2312	40	15	5	48	170	0.6	50	37	6.6	1.6	81	8.1	87	8.2	15.2	<20	12.30	1.84
915	AB2313	48	11	6	41	170	0.7	63	47	7.4	1.5	83	8.9	69	5.3	11.5	<20	8.18	1.33
916	AB2314	31	8	5	40	180	0.5	38	25	4.1	1.1	51	8.1	61	10.8	8.2	<20	8.29	1.24
917	AB2315	37	<4	4	30	170	1.3	76	62	10.0	1.0	77	12.0	81	7.3	12.1	<20	8.87	1.29
918	AB2316	39	11	5	43	110	0.9	50	31	5.7	1.4	42	8.0	74	4.2	9.4	<20	9.26	1.34
919	AB2317	33	6	4	33	96	0.7	41	31	4.8	0.8	49	4.6	54	8.6	11.0	<20	6.87	0.91
920	AB2318	29	<4	4	48	120	0.8	58	47	7.1	1.4	68	5.8	71	4.3	10.3	<20	7.51	1.17
921	AB2319	34	9	4	42	170	0.7	57	41	6.6	1.4	81	9.3	61	6.0	8.1	<20	7.36	1.19



附表4 土壤地化学試料分析値一覽表

(11)

NO	SP. No.	Sn	W	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
942	AB2414	34	4	4	31	99	0.8	46	33	6.1	0.9	51	5.8	51	4.3	8.0	<20	5.26	0.86
943	AB2415	33	<4	4	27	93	0.9	43	32	5.7	0.6	53	3.9	48	4.9	7.5	<20	4.94	0.73
944	AB2416	18	<4	2	21	49	0.8	25	13	3.8	<0.5	22	2.8	37	2.7	5.3	<20	4.34	0.43
945	AB2417	17	<4	3	27	67	0.6	39	32	5.8	1.3	25	2.6	53	4.2	7.4	<20	5.39	0.78
946	AB2418	20	<4	5	44	160	1.2	66	36	10.9	1.8	60	6.5	84	6.8	13.4	<20	10.50	1.51
947	AB2419	34	10	4	41	210	1.0	65	57	9.3	1.5	77	9.4	82	8.5	10.0	<20	10.70	1.40
948	AB2420	8	6	2	19	74	0.5	11	12	2.3	<0.5	20	2.2	26	2.5	4.3	<20	3.19	0.44
949	AB2421	10	<4	<1	23	47	0.7	23	20	3.6	<0.5	19	2.3	35	2.3	4.8	<20	4.02	0.55
950	AB2422	18	<4	2	25	84	0.7	31	21	4.9	<0.5	30	4.6	34	2.2	5.7	<20	4.81	0.69
951	AB2423	30	7	2	28	120	0.6	48	43	7.3	0.7	39	7.1	50	6.6	8.0	<20	6.00	0.90
952	AB2424	59	<4	5	24	130	0.9	62	43	9.6	2.1	44	7.9	58	9.2	7.9	<20	8.26	1.11
953	AB2425	28	<4	3	24	100	1.0	51	23	7.7	0.7	33	5.6	50	7.5	6.4	<20	5.48	0.80
954	AB2501	11	<4	2	23	100	0.9	47	28	6.5	0.7	24	3.9	45	6.7	6.1	<20	4.86	0.68
955	AB2502	29	9	3	28	150	1.2	75	53	11.0	1.4	82	8.7	81	7.6	12.0	<20	8.66	1.24
956	AB2503	37	14	4	36	190	1.1	65	44	11.0	1.3	100	8.1	90	9.9	13.7	<20	11.70	1.68
957	AB2504	40	<4	5	44	150	0.7	48	29	7.8	2.3	73	6.0	106	8.2	14.9	<20	13.10	1.96
958	AB2505	49	<4	6	43	150	0.6	30	19	5.5	1.5	75	6.9	71	5.6	11.9	<20	10.00	1.56
959	AB2506	59	<4	6	39	120	<0.2	24	26	5.7	1.2	61	6.5	104	7.6	14.8	<20	13.90	2.02
960	AB2507	38	7	8	53	62	0.8	28	22	5.8	2.8	40	11.0	147	7.4	20.7	<20	22.70	3.12
961	AB2508	40	7	5	38	120	0.4	18	12	4.2	2.4	47	4.3	128	8.5	18.0	<20	15.70	2.20
962	AB2509	51	<4	6	44	93	0.6	23	14	5.1	2.8	39	5.6	144	7.2	10.8	<20	21.10	2.81
963	AB2510	47	9	6	51	89	0.7	38	30	6.1	1.5	57	6.9	112	6.4	15.6	<20	15.20	1.37
964	AB2511	49	12	6	40	200	0.7	70	57	9.5	1.0	60	9.3	70	8.0	10.8	<20	8.00	1.12
965	AB2512	36	6	5	38	100	1.0	42	29	5.5	1.0	55	6.7	61	4.5	8.3	<20	7.10	0.98
966	AB2513	37	9	5	41	96	0.8	43	32	5.8	1.4	53	8.1	64	5.2	9.2	<20	8.00	1.04
967	AB2514	35	<4	6	44	100	0.8	47	30	6.9	1.1	37	7.5	66	5.6	9.4	<20	8.53	1.23
968	AB2515	27	<4	4	33	97	0.9	45	30	6.2	0.7	35	4.6	53	5.1	6.9	<20	6.40	0.99
969	AB2516	45	<4	2	31	99	0.8	50	38	7.5	0.7	32	3.6	58	5.9	7.7	<20	6.47	0.85
970	AB2517	29	<4	3	36	150	1.2	65	41	9.7	0.9	71	6.8	65	7.3	9.9	<20	7.86	1.07
971	AB2518	26	<4	5	41	170	1.1	70	49	10.0	0.9	62	8.2	81	8.3	12.5	<20	8.90	1.35
972	AB2519	29	<4	5	44	200	1.2	76	41	11.0	1.0	54	6.9	86	9.3	12.3	<20	9.88	1.49
973	AB2520	14	<4	<1	18	87	0.9	18	20	2.7	1.4	20	2.8	27	2.8	4.1	<20	2.39	0.43
974	AB2521	21	<4	2	24	62	0.6	27	17	4.1	1.4	25	5.0	35	3.8	5.1	<20	4.45	0.62
975	AB2522	22	6	3	27	93	0.7	43	29	6.8	0.6	36	5.8	43	5.1	7.3	<20	5.36	0.82
976	AB2523	24	<4	3	23	96	0.9	47	34	7.2	1.6	32	6.7	52	5.8	8.1	<20	6.03	0.96
977	AB2524	17	<4	3	21	140	1.4	55	51	9.2	0.6	27	3.9	43	7.7	8.0	<20	5.10	0.77
978	AB2525	9	6	<1	21	100	0.6	22	22	3.3	<0.5	16	3.4	28	5.8	4.3	<20	2.54	0.35
979	AB2526	15	<4	1	19	96	0.7	32	21	4.4	1.9	22	3.8	31	4.7	4.7	<20	3.03	0.48
980	AB2601	13	<4	2	19	110	1.0	43	38	5.9	<0.5	24	3.4	34	4.6	5.6	<20	3.82	0.56
981	AB2602	23	<4	4	28	100	0.7	46	25	6.6	0.6	38	6.8	44	5.8	6.7	<20	5.39	0.71
982	AB2603	23	<4	2	26	98	0.9	46	27	6.8	0.6	38	5.3	47	5.2	7.3	<20	5.24	0.80
983	AB2604	43	<4	4	23	100	0.9	51	30	7.9	1.2	33	6.5	44	8.5	7.6	<20	6.00	0.90
984	AB2605	13	6	<1	19	120	0.7	28	21	4.4	1.3	21	3.0	27	4.7	4.5	<20	3.50	0.50
985	AB2606	11	<4	1	20	110	0.7	25	21	4.4	<0.5	26	3.5	29	3.4	3.5	<20	3.67	0.42
986	AB2607	13	<4	2	17	110	1.0	39	30	5.7	<0.5	22	4.0	28	3.3	4.4	<20	2.77	0.47
987	AB2608	16	6	2	19	130	0.8	35	31	5.8	<0.5	23	2.8	29	5.8	4.7	<20	3.00	0.49
988	AB2609	6	6	4	30	160	1.3	68	49	9.0	1.0	73	7.0	69	7.4	4.9	<20	8.37	1.17
989	AB2610	27	12	5	39	170	1.1	74	60	11.0	1.2	69	7.5	90	11.9	10.4	<20	10.90	1.66
990	AB2611	39	12	7	47	170	0.9	51	30	7.6	1.6	77	9.7	68	8.5	12.7	<20	11.10	1.63
991	AB2612	34	<4	6	41	140	0.8	51	32	7.0	1.3	81	8.0	95	8.1	12.3	<20	12.10	1.81
992	AB2613	47	5	7	54	120	0.4	44	24	6.9	2.3	71	7.2	104	6.2	13.9	<20	14.30	1.81
993	AB2614	61	<4	10	63	130	1.0	40	32	7.1	2.6	57	9.0	146	8.3	15.1	<20	22.50	3.28
994	AB2615	52	<4	5	46	67	0.6	20	14	4.1	1.7	54	4.9	109	6.3	21.1	<20	15.10	2.07
995	AB2616	49	<4	9	61	120	0.7	38	28	7.3	2.9	50	10.0	161	10.4	13.1	<20	21.80	3.09
996	AB2617	31	10	9	60	130	1.0	49	39	7.7	2.1	48	9.8	138	10.4	21.8	<20	18.20	2.69
997	AB2618	29	10	7	61	120	0.8	43	34	7.0	<0.5	48	8.4	116	10.1	14.0	<20	16.50	2.19
998	AB2619	35	10	6	44	120	0.9	39	29	6.2	1.9	46	9.6	89	6.9	10.8	<20	12.20	1.56
999	AB2620	37	6	6	39	130	<0.2	63	48	10.0	2.5	54	16.0	82	10.3	11.6	<20	10.50	1.49
1000	AB2621	24	<4	3	50	140	1.2	59	37	9.1	1.1	52	7.9	88	10.7	12.4	<20	18.10	1.39
1001	AB2622	46	<4	5	35	170	0.8	62	44	8.9	1.4	89	8.1	83	10.9	12.9	<20	11.70	1.66
1002	AB2623	44	<4	5	34	160	0.7	42	33	6.1	1.4	89	9.1	60	8.2	9.2	<20	6.91	1.01
1003	AB2624	40	12	4	36	150	0.6	34	11	4.3	<0.5	96	7.3	47	3.9	7.1	<20	6.77	0.98
1004	AB2625	29	<4	3	33	130	0.4	33	22	4.2	<0.5	83	7.5	40	2.5	6.2	<20	6.16	0.87
1005	AB2626	34	<4	4	42	180	1.1	90	54	12.0	2.5	78	16.0	84	12.5	12.9	<20	11.00	1.47
1006	AB2627	38	<4	6	35	230	0.7	64	40	8.4	<0.5	99	14.0	43	7.9	5.9	<20	6.73	0.77
1007	AB2701	30	<4	4	27	110	0.8	58	39	8.4	1.7	44	6.4	40	7.4	8.0	<20	6.69	0.94
1008	AB2702	41	<4	5	24	150	0.9	76	51	11.0	<0.5	60	10.0	64	8.4	14.2	<20	10.90	1.52
1009	AB2703	29	<4	3	27	120	0.9	51	24	7.2	<0.5	39	6.9	55	6.3	8.1	<20	6.64	0.92
1010	AB2704	20	<4	1	21	100	<0.2	39	25	4.9	<0.5	26	3.6	35	5.0	5.3	<20	4.24	0.59
1011	AB2705	16	<4	<1	19	91	1.0	35	28	4.6	<0.5	22	2.8	26	4.3	4.3	<20	3.65	0.54
1012	AB2706	17	4	2	29	120	0.9	53	28	6.5	<0.5	64	5.7	57	6.9	7.6	<20	6.66	0.91
1013	AB2707	18	<4	3	29	170	1.0	60	38	8.1	<0.5	118	7.6	71	8.2	9.4	<20	8.31	0.96
1014	AB2708	38	<4	4	20	160	0.9	65	31	8.0	<0.5	95	11.0	71	8.0	10.6	<20	8.78	1.11
1015	AB																		

付表4 土壤地化学試料分析値一覽表

(12)

NO	SP.No.	Sn	H	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
unit		ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1036	AB2803	20	8	4	33	130	1.0	65	49	8.6	1.1	52	7.4	64	7.8	10.5			0.89
1037	AB2804	29	<4	5	42	170	1.2	85	60	12.0	1.6	92	7.8	81	10.5	13.3	<20	9.40	1.34
1038	AB2805	30	7	4	41	160	1.0	75	50	11.0	1.6	86	6.8	85	9.5	13.8	<20	9.56	1.34
1039	AB2806	27	<4	4	40	160	0.9	57	38	9.2	1.9	91	7.6	84	7.6	13.6	<20	10.00	1.44
1040	AB2807	36	11	6	45	170	1.0	61	41	9.7	2.4	96	8.3	96	7.8	14.8	<20	12.70	1.69
1041	AB2808	28	9	5	37	140	0.8	60	40	9.1	1.7	73	6.1	85	9.2	13.4	<20	10.50	1.57
1042	AB2809	19	<4	4	39	110	0.7	40	27	6.3	1.3	71	4.8	73	7.8	11.6	<20	9.96	1.43
1043	AB2810	48	<4	6	42	110	0.6	41	29	5.9	1.4	68	11.0	78	7.5	11.7	<20	9.79	1.39
1044	AB2811	49	<4	6	55	110	<0.2	43	30	6.6	1.6	72	7.1	114	8.4	17.3	<20	15.70	2.22
1045	AB2812	51	5	6	45	95	0.7	34	17	6.0	2.1	56	5.9	104	7.8	15.3	<20	15.20	2.08
1046	AB2813	41	<4	7	50	80	0.7	32	17	5.0	1.8	50	7.8	105	8.0	16.8	<20	15.40	2.15
1047	AB2814	43	10	5	40	93	0.6	34	17	4.3	1.2	61	6.5	77	5.7	11.2	<20	10.00	1.45
1048	AB2815	41	9	4	37	92	0.7	33	16	4.0	1.2	55	5.5	64	3.8	9.6	<20	9.85	1.29
1049	AB2816	12	<4	2	20	80	0.9	34	29	5.1	0.7	22	5.1	36	3.4	6.1	<20	4.77	0.71
1050	AB2817	8	<4	1	15	87	1.0	37	26	5.7	0.9	21	5.3	35	4.6	6.1	<20	4.15	0.65
1051	AB2818	7	<4	1	17	87	0.8	30	18	4.1	0.9	24	3.5	28	2.9	4.5	<20	3.09	0.47
1052	AB2819	10	<4	2	21	91	0.9	34	22	5.6	0.9	24	6.2	31	2.2	5.3	<20	4.93	0.55
1053	AB2820	7	7	2	19	97	0.7	39	19	4.6	0.7	27	4.9	29	2.9	4.0	<20	3.71	0.53
1054	AB2821	13	<4	2	21	73	0.9	30	23	4.3	0.5	20	4.5	31	6.5	4.5	<20	3.46	0.57
1055	AB2822	17	7	2	24	90	0.8	38	22	5.2	0.8	31	6.3	40	5.4	6.0	<20	4.90	0.73
1056	AB2823	17	7	2	22	93	1.0	37	24	5.6	0.8	31	7.5	38	5.6	5.9	<20	4.20	0.69
1057	AB2824	9	<4	2	20	100	0.9	44	32	6.4	1.3	30	9.3	46	6.2	6.7	<20	5.43	0.83
1058	AB2825	20	<4	3	25	120	1.0	42	28	7.3	0.7	46	10.0	43	5.4	7.0	<20	6.09	0.84
1059	AB2826	27	<4	3	33	140	0.7	52	37	7.2	0.7	59	8.9	44	5.9	7.0	<20	5.84	0.84
1060	AB2901	23	<4	3	25	96	0.7	44	36	6.4	1.5	31	6.3	51	6.2	6.7	<20	5.79	0.81
1061	AB2902	24	<4	3	27	130	0.9	53	35	7.6	1.0	40	7.2	53	5.7	8.3	<20	6.57	0.95
1062	AB2903	30	<4	4	33	150	0.9	65	47	8.7	0.9	70	7.8	69	6.5	12.0	27	0.09	1.19
1063	AB2904	30	10	4	43	120	1.0	60	41	7.1	1.4	72	7.9	75	9.9	11.1	<20	8.47	1.19
1064	AB2905	30	8	4	42	84	0.7	32	27	4.8	1.5	70	6.7	75	5.3	11.7	<20	9.02	1.29
1065	AB2906	31	16	7	62	120	1.2	60	34	8.2	2.3	60	15.0	114	9.2	16.8	<20	14.80	1.97
1066	AB2907	33	7	5	39	150	0.7	63	37	8.2	1.8	82	5.3	84	9.4	14.1	<20	11.20	1.47
1067	AB2908	42	7	7	47	120	0.7	47	29	6.8	2.0	96	7.1	94	8.3	14.0	<20	13.40	1.76
1068	AB2909	37	9	7	50	81	0.5	38	27	5.5	2.0	81	6.6	100	7.2	15.9	<20	13.90	1.97
1069	AB2910	34	10	5	47	81	0.6	31	24	4.6	1.8	71	6.5	85	6.7	13.0	<20	12.20	1.67
1070	AB2911	30	12	7	57	98	0.8	41	25	6.1	2.0	53	11.0	116	8.3	16.6	<20	16.00	2.29
1071	AB2912	50	9	7	46	59	0.8	36	11	3.7	1.7	58	8.2	81	3.6	11.5	<20	11.10	1.53
1072	AB2913	51	11	6	49	63	0.7	39	19	4.2	1.6	68	5.7	86	7.3	10.9	<20	12.10	1.70
1073	AB2914	46	9	4	36	82	0.7	45	22	4.8	1.5	66	5.7	65	5.4	10.1	<20	8.36	1.17
1074	AB2915	45	7	4	29	200	1.1	73	45	9.4	1.8	82	7.6	73	7.9	11.9	<20	8.57	1.22
1075	AB2916	15	7	2	20	110	0.8	31	22	3.7	0.6	35	5.6	20	5.1	5.5	<20	3.78	0.54
1076	AB2917	10	7	3	20	66	0.7	31	21	3.6	0.5	23	5.7	31	2.9	4.4	<20	3.83	0.53
1077	AB2918	12	7	2	21	70	0.7	30	22	3.8	0.9	25	6.3	34	2.5	4.5	<20	3.85	0.55
1078	AB3001	35	5	3	25	120	1.2	57	40	7.6	0.7	33	7.4	50	9.2	7.8	<20	5.74	0.76
1079	AB3002	42	5	3	27	120	0.9	55	35	7.4	1.3	41	7.2	40	6.6	8.9	<20	6.18	0.86
1080	AB3003	41	7	3	30	110	0.9	52	39	7.0	1.4	46	9.3	50	7.9	8.9	<20	5.96	0.82
1081	AB3004	41	7	4	39	120	0.6	36	27	5.2	1.0	66	7.4	60	6.9	9.2	<20	7.29	1.03
1082	AB3005	44	6	4	37	100	0.9	30	27	5.9	1.2	98	5.5	65	6.4	11.5	<20	8.12	1.10
1083	AB3006	44	5	3	33	73	0.7	27	22	3.9	0.9	100	5.7	58	5.6	9.2	<20	7.44	1.02
1084	AB3007	39	10	5	43	120	1.0	60	40	7.8	1.6	54	7.1	84	6.5	12.3	<20	10.70	1.45
1085	AB3008	61	7	5	44	120	0.6	52	40	7.1	2.0	86	5.5	86	9.1	14.6	<20	12.00	1.65
1086	AB3009	59	8	5	43	91	0.6	41	25	6.2	1.7	68	6.5	91	7.4	14.0	<20	13.40	1.86
1087	AB3010	71	8	6	43	57	0.6	25	11	3.7	1.3	62	5.7	79	4.8	12.2	<20	10.20	1.58
1088	AB3011	66	10	7	47	71	0.7	30	22	4.3	1.8	55	9.7	92	3.6	14.3	<20	13.00	1.78
1089	AB3012	67	9	5	42	74	0.7	31	20	4.2	1.3	56	7.9	61	6.2	10.5	<20	9.09	1.30
1090	AB3013	53	11	6	39	65	0.5	25	13	3.2	1.2	50	4.8	59	3.4	8.7	<20	8.57	1.23
1091	AB3014	60	7	5	35	98	0.8	46	20	5.4	1.4	71	7.9	77	5.8	11.9	<20	10.50	1.50
1092	AB3015	37	9	3	37	66	0.6	36	15	4.4	1.3	37	6.2	67	7.9	10.0	<20	8.05	1.09
1093	AB3016	28	6	2	19	93	0.9	33	25	4.4	1.0	28	8.3	32	2.7	5.3	<20	4.66	0.62
1094	AB3017	39	6	3	26	95	0.5	26	14	3.4	1.0	60	6.7	33	5.6	5.6	<20	4.40	0.62
1095	AB3018	36	<4	3	23	93	1.0	49	32	6.3	1.3	31	6.3	40	5.9	8.2	<20	4.76	0.72
1096	AB3019	36	7	3	24	120	1.1	62	45	7.8	1.8	42	7.4	50	7.5	9.0	<20	6.47	0.85
1097	AB3020	25	<4	3	27	140	0.9	52	31	6.8	1.6	47	8.3	46	7.4	7.1	<20	5.77	0.83
1098	AB3021	31	6	3	30	100	0.7	51	36	6.7	1.0	39	7.2	52	6.5	8.3	<20	5.98	0.80
1099	AB3022	40	6	3	33	93	0.7	42	25	5.9	1.0	53	8.2	50	7.3	9.3	<20	6.95	0.91
1100	AB3023	52	<4	5	38	140	0.9	60	48	7.6	2.1	93	6.8	71	7.3	11.4	<20	9.10	1.31
1101	AB3024	30	6	5	39	96	0.7	45	28	6.0	1.6	82	3.7	71	5.6	11.4	<20	8.81	1.29
1102	AB3025	57	7	6	43	100	0.7	40	30	5.9	1.7	84	6.2	82	6.6	12.0	<20	12.20	1.71
1103	AB3026	61	9	7	44	83	0.7	40	27	5.7	1.7	68	7.2	90	9.3	13.2	<20	13.20	1.73
1104	AB3027	79	10	6	39	42	<0.2	20	10	2.6	1.6	69	5.7	52	6.1	8.0	<20	9.06	1.21
1105	AB3028	66	9	6	43	68	<0.2	31	10	4.0	1.2	59	7.3	67	4.6	9.6	<20	9.61	1.35
1106	AB3029	82	10	6	41	39	<0.2	22	15	2.6	1.4	62	5.6	70	6.0	9.9	<20	10.50	1.45
1107	AB3030	80	8	5	36	54	0.3	16	7	1.9	0.7	63	3.7	39	5.6	6.1	<20	5.01	0.71
1108	AB3031	76	<4	6	37	77	0.3	14	10	1.9	0.7	75	5.1	56	4.4	7.1	<20	7.09	1.03
1109	AB3032	56	7	5	36	150	0.4	13	20	2.2	1.5	74	6.3						

附表4 土壤地化学試料分析値一覽表

(13)

NO	SP.No.	Sn	W	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	By	Pr	Yb	Lu
unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1130	AB3218	33	<4	1	18	96	1.0	44	36	5.6	0.7	34	4.8	35	5.0	6.8	<20	4.29	0.65
1131	AB3219	38	<4	5	41	130	0.5	43	36	5.3	0.7	65	8.6	48	6.9	8.6	<20	6.87	0.91
1132	AB3220	40	6	4	39	130	0.6	41	34	5.2	0.9	69	8.1	50	4.8	7.4	<20	6.45	0.93
1133	AB3221	48	6	3	33	140	0.5	34	28	4.6	0.9	76	9.2	38	6.9	21.5	<20	4.76	0.65
1134	AB3222	38	7	4	35	120	0.6	36	26	4.7	0.9	66	9.8	39	5.4	7.0	<20	4.99	0.70
1135	AB3223	35	<4	3	28	100	0.6	32	23	4.1	0.9	55	6.9	34	4.4	6.6	<20	4.47	0.62
1136	AB3224	34	<4	4	33	76	0.6	39	25	4.8	1.2	39	9.4	48	6.2	7.3	<20	7.07	1.84
1137	AB3301	30	<4	2	20	120	1.0	46	37	6.0	0.9	36	5.7	39	6.5	5.9	<20	4.98	0.70
1138	AB3302	38	<4	3	18	110	1.0	44	26	5.9	0.7	31	4.5	37	3.8	8.4	<20	4.49	0.60
1139	AB3303	30	<4	2	18	91	0.7	33	28	4.3	0.7	28	4.0	30	4.2	5.6	<20	3.71	0.52
1140	AB3304	35	<4	3	20	120	0.7	38	29	5.0	0.7	43	8.1	38	5.3	6.4	<20	4.95	0.76
1141	AB3305	31	7	3	25	130	1.2	57	48	7.8	1.1	34	7.4	47	7.6	9.1	<20	5.68	0.74
1142	AB3306	31	<4	3	23	110	1.0	48	35	6.5	1.0	32	8.2	43	6.2	7.3	<20	5.76	0.80
1143	AB3307	97	<4	7	31	200	1.0	100	60	13.0	3.3	81	15.0	90	17.1	23.6	<20	15.30	2.12
1144	AB3308	37	<4	2	26	120	0.9	46	32	6.1	1.0	37	7.4	44	7.0	6.8	<20	5.31	0.77
1145	AB3309	39	8	2	22	98	0.8	40	28	5.3	1.4	30	6.1	41	4.8	6.6	<20	4.70	0.67
1146	AB3310	29	9	2	24	64	0.7	32	22	4.0	0.7	28	6.4	36	3.5	5.5	<20	4.75	0.61
1147	AB3311	26	7	3	23	80	0.8	32	24	3.9	0.7	29	8.1	35	4.7	5.4	<20	4.32	0.59
1148	AB3312	32	7	2	23	67	0.7	32	22	3.9	0.9	28	7.3	34	4.3	5.3	<20	4.27	0.67
1149	AB3313	31	7	3	21	71	0.7	31	21	4.1	0.9	29	6.5	34	4.4	5.3	<20	4.72	0.63
1150	AB3314	38	<4	2	23	72	0.8	32	22	4.1	0.9	29	6.6	36	3.7	4.8	<20	4.42	0.64
1151	AB3315	22	<4	2	19	100	1.1	44	36	5.8	0.9	28	5.5	40	4.3	6.2	<20	4.69	0.60
1152	AB3316	29	<4	3	23	86	0.8	39	28	5.4	1.2	30	11.0	45	4.8	6.4	<20	5.95	0.84
1153	AB3317	28	<4	3	20	88	0.8	41	30	5.4	1.0	30	8.9	42	4.7	5.9	<20	6.15	0.89
1154	AB3318	33	<4	2	18	93	0.8	43	27	5.5	0.9	29	11.0	39	4.4	5.8	<20	5.76	0.82
1155	AB3319	22	9	2	18	110	1.0	43	34	5.6	0.9	32	6.0	34	4.9	5.7	<20	4.55	0.61
1156	AB3320	29	8	3	23	77	0.9	36	19	4.0	1.1	35	7.0	34	4.4	5.1	<20	4.05	0.51
1157	AB3321	25	7	2	22	51	0.6	24	16	2.8	0.6	24	4.3	29	2.6	3.4	<20	3.37	0.47
1158	AB3322	27	<4	2	21	85	0.7	37	23	4.7	0.7	26	6.0	32	4.4	5.4	<20	4.17	0.64
1159	AB3323	33	5	3	29	68	0.4	25	20	3.2	0.9	35	6.2	44	3.7	6.7	<20	5.25	0.90
1160	AB3401	35	5	3	25	79	0.6	37	28	4.4	0.8	36	6.4	39	5.8	7.0	<20	4.37	0.85
1161	AB3402	26	7	2	19	99	0.8	35	26	4.6	0.7	33	3.6	36	4.9	6.9	<20	3.91	0.66
1162	AB3403	33	8	3	24	98	0.8	37	35	4.7	0.7	33	5.8	40	6.0	7.0	<20	4.63	0.71
1163	AB3404	27	7	3	24	78	0.7	34	28	4.3	0.7	26	5.5	37	6.5	7.3	<20	4.57	0.71
1164	AB3405	35	7	<1	20	88	0.7	37	30	4.9	0.7	31	4.5	37	5.9	6.5	<20	3.90	0.66
1165	AB3406	40	8	3	29	140	1.1	70	46	8.4	1.2	71	9.2	68	10.2	12.6	<20	7.57	1.24
1166	AB3407	40	7	3	24	92	0.8	40	27	5.5	0.6	33	8.0	44	6.4	8.4	<20	5.68	0.89
1167	AB3408	34	7	2	23	93	0.8	44	38	5.7	0.7	29	7.5	47	6.6	7.6	<20	4.84	0.75
1168	AB3409	27	6	2	19	97	0.8	36	28	4.5	0.7	33	4.9	36	7.0	6.8	<20	4.11	0.69
1169	AB3410	24	7	2	19	78	0.7	28	27	3.5	0.7	24	5.5	32	5.3	4.4	<20	3.60	0.55
1170	AB3411	34	6	2	22	76	0.8	33	31	4.5	0.8	29	8.1	43	4.5	6.2	<20	4.42	0.77
1171	AB3412	29	<4	3	22	83	0.8	38	27	4.8	0.8	28	6.5	45	5.6	7.2	<20	5.20	0.87
1172	AB3413	26	9	3	21	72	0.8	34	31	4.4	0.8	24	7.7	44	5.6	6.7	<20	4.73	0.72
1173	AB3414	29	<4	2	22	69	0.7	33	21	4.1	0.8	26	6.4	38	3.6	6.2	<20	4.86	0.74
1174	AB3415	25	5	<1	21	100	0.8	36	30	4.5	1.0	30	5.5	34	6.1	6.1	<20	4.07	0.67
1175	AB3416	29	7	3	20	86	0.6	38	35	5.0	1.0	30	8.9	44	6.3	6.5	<20	5.39	0.94
1176	AB3417	25	7	2	22	70	0.6	25	21	3.1	0.7	26	4.9	32	2.9	4.8	<20	3.38	0.61
1177	AB3418	24	6	2	22	79	0.8	37	34	4.6	0.7	25	8.2	42	4.3	5.6	<20	4.21	0.64
1178	AB3419	29	6	2	22	47	0.5	21	23	2.6	0.5	18	4.9	31	2.2	3.5	<20	3.41	0.59
1179	AB3420	26	7	2	21	64	0.6	29	17	3.5	0.7	25	5.5	34	4.4	5.5	<20	4.17	0.67
1180	AB3421	32	5	3	21	58	0.5	29	21	3.5	0.5	31	8.2	32	4.7	5.1	<20	3.72	0.58
1181	AB3422	30	<4	2	24	53	0.5	25	11	3.8	0.5	29	5.4	36	4.6	5.6	<20	3.95	0.65
1182	AB3423	14	<4	3	29	45	0.5	22	12	2.6	0.7	29	6.0	41	3.6	5.6	<20	4.33	0.78
1183	AB3501	51	7	5	37	140	0.8	47	38	6.4	1.4	78	7.6	76	8.5	13.2	<20	9.68	1.62
1184	AB3502	50	<4	6	44	74	0.6	30	23	4.5	1.3	44	6.7	79	6.5	11.7	<20	10.50	1.59
1185	AB3503	31	8	3	25	52	0.4	25	14	2.9	0.7	38	6.0	39	3.9	5.4	<20	4.28	0.72
1186	AB3504	35	7	3	28	61	0.6	32	19	3.5	0.8	30	6.9	40	5.0	7.4	<20	5.05	0.87
1187	AB3505	34	9	3	34	55	0.6	28	22	3.3	0.9	27	6.6	49	3.7	6.4	<20	6.47	0.98
1188	AB3506	32	8	3	25	56	0.6	23	16	3.0	0.8	31	5.4	32	4.5	5.9	<20	4.36	0.73
1189	AB3507	28	<4	2	21	98	0.8	37	28	5.3	0.7	31	6.1	39	4.6	6.2	<20	4.59	0.79
1190	AB3508	32	7	3	24	76	0.7	33	28	4.4	0.9	28	5.2	47	3.2	7.3	<20	5.74	0.98
1191	AB3509	17	10	4	33	60	0.6	31	13	4.1	1.2	33	6.0	57	6.1	8.8	<20	8.39	1.22
1192	AB3510	60	9	5	41	70	0.6	35	11	3.9	1.7	55	5.6	62	5.3	8.4	<20	9.82	1.21
1193	AB3511	88	6	7	45	100	0.8	41	32	6.5	2.9	60	5.8	105	8.7	17.3	<20	16.70	2.31
1194	AB3512	71	9	8	37	150	0.5	25	18	3.6	1.1	64	4.4	66	3.8	8.9	<20	9.67	1.26
1195	AB3601	62	7	6	38	57	0.4	20	10	3.2	1.7	61	4.4	68	5.1	9.2	<20	10.20	1.37
1196	AB3602	59	5	6	38	56	<0.2	24	14	3.8	1.7	62	4.0	72	6.1	10.8	<20	11.90	1.61
1197	AB3603	68	5	4	37	77	0.6	34	26	4.8	1.5	80	4.3	74	2.3	10.8	<20	10.50	1.47
1198	AB3604	62	10	7	39	100	<0.2	41	26	5.3	1.7	76	5.8	65	7.4	10.6	<20	12.10	1.64
1199	AB3605	57	9	7	42	79	0.6	38	21	4.9	1.7	65	5.5	72	5.3	10.3	<20	11.00	1.54
1200	AB3606	62	10	7	46	100	0.9	36	24	5.2	1.8	61	6.3	81	5.3	12.7	<20	13.30	1.78
1201	AB3607	50	12	6	46	100	0.9	52	25	5.8	1.4	48	9.6	74	4.7	11.0	<20	11.10	1.50
1202	AB3608	66	10	6	39	51	0.5	34	12	3.5	1.6	63	6.2	69	5.6	9.6	<20	11.20	1.45
1203	AB3609	73	11	7	37	78	<0.2	40	18	3.8	2.2	64	6.6	63	4.7	10.8	<20	1	

付表4 土壤地化学試料分析値一覽表

(14)

NO	SP.No.	Sn	H	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1224	BA0310	28	8	7	49	210	1.3	86	50	13.0	1.7	95	19.0	90	11.7	14.9	28	11.80	1.68
1225	BA0311	28	9	7	44	200	1.7	88	45	12.0	1.2	87	17.0	89	10.2	13.0	<20	10.50	1.51
1226	BA0312	24	9	8	43	190	1.3	85	58	14.0	1.9	95	18.0	89	13.5	16.4	<20	12.30	1.72
1227	BA0313	28	8	6	43	210	1.3	82	51	12.0	1.3	88	17.0	92	9.6	12.2	<20	11.30	1.49
1228	BA0314	28	7	7	67	190	1.7	86	42	14.0	1.3	85	14.0	89	13.5	13.6	<20	11.20	1.44
1229	BA0401	10	5	3	32	160	0.9	80	46	11.0	1.2	50	15.0	67	8.9	10.9	<20	9.10	1.24
1230	BA0402	<5	5	3	30	38	0.3	22	<5	2.6	0.7	42	6.0	28	2.9	2.8	<20	4.83	0.66
1231	BA0403	<5	5	3	28	70	0.7	28	12	3.5	<0.5	28	6.0	39	3.2	4.5	<20	3.93	0.55
1232	BA0404	8	7	5	44	130	0.7	49	25	6.4	0.7	40	8.0	78	3.7	7.1	<20	5.99	0.87
1233	BA0406	<5	6	<1	17	130	<0.2	9	5	1.3	<0.5	24	4.1	11	0.8	1.7	<20	2.45	0.35
1234	BA0407	12	7	5	39	87	<0.2	48	25	5.4	0.8	61	5.6	65	5.4	6.6	<20	5.21	0.86
1235	BA0408	11	6	5	37	72	0.6	36	22	4.6	0.8	44	6.2	7	4.8	6.4	<20	6.06	0.94
1236	BA0501	<5	<4	<1	21	63	0.9	26	10	3.4	0.8	29	4.4	36	4.0	4.8	<20	4.28	0.61
1237	BA0502	10	7	5	37	170	0.8	61	36	9.0	2.0	75	15.0	66	11.1	10.4	<20	7.63	1.10
1238	BA0503	<5	<4	3	19	93	1.8	41	27	5.7	1.1	25	6.6	34	5.1	6.4	<20	5.09	0.69
1239	BA0504	<5	<4	<1	18	93	1.2	38	17	5.2	0.7	20	1.4	44	5.9	4.4	<20	3.33	0.48
1240	BA0505	<5	5	1	18	100	0.8	19	12	3.0	0.7	27	4.4	39	4.0	4.0	<20	4.39	0.68
1241	BA0601	<5	<4	<1	47	28	<0.2	14	<5	1.7	0.5	25	3.0	35	2.3	4.3	<20	4.04	0.57
1242	BA0602	<5	<4	<1	18	36	0.6	13	<5	1.9	0.5	25	2.9	36	2.5	3.9	<20	4.26	0.59
1243	BA0603	<5	<4	<1	22	46	0.5	19	<5	2.3	<0.5	23	3.5	32	3.1	4.6	<20	3.53	0.52
1244	BA0604	<5	5	2	29	110	1.4	57	34	8.1	1.1	37	12.0	60	7.2	8.7	<20	7.54	1.07
1245	BA0606	7	<4	4	36	180	0.9	86	50	12.0	2.0	62	14.0	74	10.4	12.3	<20	10.70	1.51
1246	BA0606	6	5	4	35	180	1.1	87	49	12.0	2.2	59	12.0	126	9.1	11.6	<20	10.70	1.43
1247	BA0701	<5	<4	<1	20	42	0.6	16	8	1.9	0.7	26	3.1	32	3.7	4.3	<20	4.54	0.59
1248	BA0702	<5	4	<1	20	48	0.8	23	12	3.1	0.6	21	2.3	23	3.5	5.0	<20	3.61	0.54
1249	BA0703	<5	<4	<1	20	69	0.8	40	19	4.4	0.5	21	3.5	36	5.3	5.2	<20	4.17	0.62
1250	BA0704	<5	5	2	22	70	<0.2	25	10	3.0	0.5	35	2.7	35	1.6	3.9	<20	4.09	0.59
1251	BA0705	5	7	<1	28	95	0.9	42	20	5.1	0.7	49	6.6	22	3.4	5.7	<20	5.02	0.71
1252	BA0706	<5	6	3	26	110	1.0	51	28	6.2	0.7	38	7.7	9	9.0	7.2	<20	5.36	0.85
1253	BA0707	<5	5	3	32	150	0.9	71	39	9.9	1.1	55	14.0	70	8.2	11.6	<20	9.09	1.18
1254	BA0708	37	<4	3	154	140	1.1	75	63	10.0	1.2	54	17.0	498	9.0	11.5	<20	8.90	1.29
1255	BA0709	<5	<4	<1	23	73	0.6	25	12	2.4	0.9	22	2.7	19	3.6	4.9	<20	3.45	0.51
1256	BA0901	<5	<4	<1	19	44	0.8	26	16	2.9	<0.5	15	2.1	27	1.1	4.5	<20	3.79	0.49
1257	BA0902	31	10	7	53	150	1.2	72	41	11.0	1.5	68	12.0	111	12.4	13.9	<20	11.20	1.45
1258	BA0903	6	6	1	27	73	<0.2	31	17	4.0	0.7	37	5.6	34	4.8	5.5	<20	4.37	0.61
1259	BA0904	<5	<4	2	19	60	0.6	17	11	2.2	<0.5	23	3.5	24	1.9	2.5	<20	2.47	0.35
1260	BA0905	<5	<4	<1	18	21	<0.2	7	7	0.8	<0.5	21	2.1	<2	0.8	2.1	<20	1.85	0.26
1261	BA0906	<5	9	2	25	24	0.4	11	6	1.6	<0.5	27	3.6	28	2.6	3.2	<20	3.37	0.52
1262	BA0907	<5	6	3	42	69	0.9	40	19	5.1	0.7	39	5.9	36	3.5	6.6	<20	5.01	0.88
1263	BA0908	<5	<4	5	32	240	3.8	138	81	21.0	3.5	43	28.0	163	20.5	26.4	<20	16.30	2.82
1264	BA0909	16	8	3	39	110	0.8	52	20	8.3	1.0	58	11.0	47	5.3	7.7	<20	6.28	0.90
1265	BA0910	<5	4	4	28	61	0.2	25	7	2.3	0.5	38	4.0	17	3.7	2.7	<20	2.97	0.51
1266	BA0911	<5	<4	<1	22	95	0.5	24	13	1.7	<0.5	30	3.0	14	4.1	1.8	<20	2.23	0.40
1267	BA1001	15	6	5	38	93	0.9	45	26	6.3	0.7	42	8.5	48	4.1	7.8	<20	6.71	0.93
1268	BA1002	24	8	6	48	150	0.9	72	39	11.0	2.3	59	11.0	94	11.1	13.3	<20	10.60	1.54
1269	BA1003	<5	<4	3	24	32	<0.2	17	<5	2.3	<0.5	26	3.2	20	3.2	3.8	<20	3.10	0.45
1270	BA1004	<5	<4	2	24	20	<0.2	11	<5	1.5	<0.5	25	3.6	15	2.2	3.3	<20	3.37	0.50
1271	BA1005	6	6	2	31	42	<0.2	20	13	2.6	<0.5	36	4.3	27	1.6	4.2	<20	4.28	0.59
1272	BA1006	<5	5	2	24	53	0.5	20	16	2.7	<0.5	27	4.7	19	2.9	4.1	<20	3.57	0.51
1273	BA1007	5	6	6	36	110	<0.2	49	23	8.0	1.0	59	10.0	44	5.9	6.5	<20	6.27	0.87
1274	BA1008	10	5	4	<2	87	0.6	45	27	5.3	1.3	49	8.0	37	4.0	6.4	<20	5.34	0.85
1275	BA1009	<5	<4	5	48	88	<0.2	47	23	5.3	0.7	39	6.2	34	5.3	5.3	<20	5.18	0.83
1276	BA1010	<5	5	<1	23	69	<0.2	20	11	1.5	<0.5	28	3.0	12	0.7	2.6	<20	2.12	0.38
1277	BA1011	<5	<4	<1	26	93	0.3	30	9	2.0	<0.5	34	4.1	16	4.2	2.3	<20	2.33	0.40
1278	BA1011	<5	<4	2	26	64	1.0	38	20	5.1	0.7	29	5.1	48	6.9	7.0	<20	4.82	0.63
1279	BA1012	10	<4	6	41	140	1.3	80	44	12.0	1.9	43	14.0	97	12.2	13.5	<20	11.50	1.59
1280	BA1013	7	<4	4	34	100	0.9	43	31	6.4	1.7	37	8.5	48	7.9	8.2	<20	6.90	0.97
1281	BA1014	25	10	8	58	150	1.3	83	40	12.0	2.2	56	12.0	104	10.5	15.7	<20	12.70	1.78
1282	BA1015	10	7	5	41	130	1.0	58	36	7.7	2.2	61	13.0	48	8.4	8.1	<20	6.31	1.02
1283	BA1016	12	4	6	30	110	<0.2	58	26	7.0	0.9	46	6.1	48	8.6	9.1	<20	6.32	0.83
1284	BA1017	17	5	7	60	120	0.7	60	45	6.8	0.9	49	7.9	61	7.3	7.3	<20	6.25	1.00
1285	BA1018	16	<4	6	46	99	<0.2	48	35	5.2	0.9	65	9.4	46	7.4	9.1	<20	5.14	0.86
1286	BA1019	14	4	9	68	110	0.7	58	39	6.8	0.7	48	7.5	60	7.8	8.7	<20	6.51	1.13
1287	BA1110	13	4	7	69	100	0.7	56	37	6.2	1.3	43	6.2	71	5.8	14.0	<20	6.70	1.09
1288	BA1201	15	8	5	42	140	1.2	72	59	9.5	2.0	48	15.0	103	11.9	12.3	<20	9.52	1.40
1289	BA1202	12	8	4	49	110	0.9	57	47	6.9	1.0	41	10.0	73	8.0	8.0	<20	7.33	1.16
1290	BA1203	28	7	5	40	100	0.6	46	30	5.4	1.0	47	9.4	51	5.9	4.0	<20	6.10	0.94
1291	BA1204	14	<4	3	38	54	0.6	23	12	2.7	<0.5	29	5.8	30	1.6	2.3	<20	3.85	0.60
1292	BA1205	9	<4	2	23	29	0.3	11	5	1.3	<0.5	26	5.4	13	2.1	3.9	<20	2.29	0.47
1293	BA1206	20	5	3	30	51	0.5	19	13	2.2	0.9	38	7.5	22	1.6	3.9	<20	3.33	0.55
1294	BA1207	15	<4	2	24	56	0.5	24	21	2.8	<0.5	23	5.5	24	0.8	15.2	<20	2.97	0.45
1295	BA1301	43	7	6	44	130	1.0	68	57	9.1	1.6	58	14.0	88	11.2	7.2	<20	10.20	1.49
1296	BA1302	23	5	3	36	76	0.5	35	24	4.2	0.7	36	8.1	39	4.3	7.0			

付表4 土壤地化学試料分析値一覽表

(15)

NO	SP.No.	Sn	W	Ta	Nb	Ce	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1318	B00205	<5	8	1	39	93	1.0	47	38	6.2	<0.5	38	9.2	55	6.2	7.5	<20	8.51	0.90
1319	B00206	15	11	1	66	140	1.1	50	43	7.6	<0.5	66	14.0	54	6.6	9.6	<20	7.88	1.03
1320	B00207	18	12	1	42	80	0.9	37	20	5.1	1.4	55	12.0	91	4.3	9.6	<20	8.62	1.09
1321	B00301	<5	<4	1	17	97	1.0	31	20	3.7	<0.5	24	4.0	27	2.1	4.4	<20	3.69	0.57
1322	B00302	<5	5	1	20	47	<0.2	22	17	2.6	1.0	26	4.9	29	3.1	4.8	<20	3.93	0.58
1323	B00303	<5	4	1	19	74	<0.2	31	16	2.3	<0.5	23	3.1	26	3.0	4.2	<20	3.66	0.46
1324	B00304	<5	<4	1	17	110	1.1	33	23	4.0	<0.5	23	4.3	72	4.1	4.4	<20	3.86	0.47
1325	B00305	11	8	1	39	120	1.3	59	39	8.7	0.2	48	13.0	74	8.1	11.3	<20	10.40	1.42
1326	B00306	<5	9	1	24	39	0.7	17	13	2.4	1.1	31	4.4	28	1.7	5.0	<20	4.13	0.57
1327	B00307	<5	10	1	41	47	0.7	22	13	2.0	1.0	36	6.4	47	1.6	6.1	<20	6.05	0.76
1328	B00401	11	14	1	33	90	1.1	43	29	5.9	1.3	41	11.0	51	0.1	9.6	<20	7.53	0.93
1329	B00402	<5	<4	1	10	38	0.6	15	10	1.6	0.6	24	3.1	20	2.9	3.6	<20	3.37	0.47
1330	B00403	<5	4	1	23	39	0.8	23	15	2.5	0.7	25	5.2	31	3.5	4.6	<20	4.37	0.59
1331	B00404	12	8	1	44	120	1.3	65	38	9.3	2.3	43	13.0	85	8.1	11.6	<20	11.30	1.44
1332	B00405	<5	7	1	21	61	0.7	29	12	2.7	<0.5	20	3.6	30	3.4	3.3	<20	2.66	0.38
1333	B00501	<5	<4	1	16	44	0.7	10	10	2.2	0.5	21	3.9	31	3.2	3.6	<20	3.25	0.40
1334	B00502	<5	<4	1	18	31	<0.2	14	10	1.5	0.6	25	3.2	58	0.8	3.9	<20	3.55	0.43
1335	B00503	<5	6	1	15	60	<0.2	21	15	2.1	<0.5	25	2.4	28	0.9	3.6	<20	3.37	0.43
1336	B00504	<5	5	1	<2	57	<0.2	21	15	2.4	<0.5	27	4.5	6	1.5	3.0	<20	3.76	0.47
1337	B00601	<5	7	1	21	140	0.8	29	30	3.5	<0.5	30	5.0	31	2.7	4.8	<20	4.26	0.59
1338	B00602	<5	5	1	21	38	0.8	20	18	2.4	0.6	29	4.3	46	2.3	4.5	<20	4.63	0.59
1339	B00603	<5	5	1	17	25	0.6	14	7	1.7	<0.5	25	5.1	18	4.4	3.6	<20	3.80	0.41
1340	B00604	<5	6	1	18	31	0.6	10	9	2.0	<0.5	29	3.9	21	2.4	3.6	<20	3.79	0.49
1341	B00605	<5	11	1	27	74	1.2	30	19	4.2	1.0	44	8.9	37	3.1	5.6	<20	6.01	0.74
1342	B00606	9	6	1	20	110	1.0	62	44	9.0	1.0	42	12.0	51	0.3	13.6	<20	12.30	1.55
1343	B00607	6	10	1	24	74	0.9	24	15	3.4	0.9	36	8.1	75	2.5	4.8	<20	5.68	0.92
1344	B00701	14	12	1	37	110	<0.2	41	21	5.9	1.0	62	13.0	46	3.4	8.7	<20	7.98	1.05
1345	B00702	<5	8	1	23	43	0.9	27	18	3.2	0.9	36	5.6	31	3.7	4.6	<20	4.98	0.63
1346	B00703	<5	6	1	27	41	0.9	24	17	3.1	0.8	41	7.2	42	2.1	5.0	<20	5.52	0.73
1347	B00704	<5	8	1	24	58	0.8	31	20	4.2	0.8	39	5.2	39	2.5	6.0	<20	5.88	0.73
1348	B00705	14	10	5	38	150	1.2	74	48	11.0	1.7	60	11.0	42	9.4	12.3	<20	11.90	1.61
1349	B00706	9	9	3	32	160	0.8	33	14	4.9	1.0	47	7.6	32	0.8	6.2	<20	7.57	1.06
1350	B00707	<5	<4	2	24	96	0.7	10	10	1.9	1.1	34	2.9	<2	1.1	4.2	<20	5.20	0.54
1351	B00708	<5	<4	2	26	110	0.7	15	10	2.4	1.0	41	3.6	2	1.5	4.4	<20	5.49	0.75
1352	B00801	<5	<4	3	27	120	1.1	64	28	7.2	0.9	39	8.7	61	9.9	10.6	<20	7.03	0.95
1353	B00802	13	14	5	34	160	1.1	56	22	7.5	1.3	54	11.0	123	6.6	5.3	<20	9.18	1.22
1354	B00803	14	12	4	37	150	1.0	80	50	12.0	1.5	58	19.0	175	12.9	9.2	<20	12.70	1.78
1355	B00804	17	12	6	31	160	1.2	85	52	12.0	2.3	66	21.0	<2	15.6	8.8	<20	15.90	2.21
1356	B00805	<5	8	2	17	120	0.7	20	9	2.8	0.9	45	6.1	7	3.5	5.3	<20	5.66	0.87
1357	B00806	<5	<4	2	22	160	0.4	9	9	1.7	0.9	46	3.8	<2	0.8	4.1	<20	5.41	0.77
1358	B00807	<5	<4	1	24	89	<0.2	0	5	1.3	0.7	48	4.2	27	1.1	4.5	<20	5.27	0.74
1359	B00808	<5	<4	2	22	53	0.7	31	9	2.9	0.7	33	4.6	<2	3.6	4.7	<20	5.00	0.75
1360	B00902	12	9	5	38	230	0.9	62	39	9.3	1.4	80	11.0	<2	9.9	12.0	<20	10.40	1.45
1361	B00903	15	<4	7	32	230	1.1	120	78	16.8	3.7	96	26.0	93	16.9	17.2	<20	19.20	2.52
1362	B00904	<5	7	3	18	120	1.4	46	27	5.8	1.2	55	7.0	<2	3.6	6.1	<20	6.11	0.87
1363	B00905	<5	<4	2	29	43	<0.2	22	16	2.8	0.5	40	4.0	<1	4.6	3.9	<20	3.77	0.61
1364	B01001	7	13	4	<2	62	0.6	22	19	3.1	0.9	42	6.1	28	5.3	6.8	<20	6.35	0.98
1365	B01002	9	17	6	65	85	0.8	35	17	5.0	1.4	57	8.5	130	2.9	6.9	<20	10.50	1.53
1366	B01003	23	12	6	40	80	0.6	35	17	5.2	1.5	67	7.9	12	5.4	9.6	<20	11.10	1.58
1367	B01004	22	8	6	55	82	<0.2	29	18	4.3	1.4	69	11.0	71	6.1	10.5	<20	11.00	1.56
1368	B01005	25	7	6	53	73	<0.2	38	27	5.5	1.4	63	13.0	133	8.4	11.7	<20	11.70	1.53
1369	B01101	14	14	4	39	74	0.8	29	19	4.1	1.0	47	10.0	<2	4.7	8.0	<20	7.06	0.93
1370	B01102	9	14	4	39	78	0.6	32	16	4.5	1.2	42	8.7	129	5.6	6.7	<20	7.26	0.94
1371	B01103	17	17	5	44	84	0.8	37	24	5.1	1.2	48	10.0	65	6.6	8.1	<20	7.49	1.06
1372	B01104	17	15	5	48	91	0.7	38	29	5.5	1.2	47	11.0	179	6.9	9.7	<20	8.26	1.09
1373	B01105	15	13	5	47	100	0.7	37	24	5.2	1.0	51	11.0	152	6.3	6.9	<20	7.77	1.11
1374	B01106	20	14	4	44	100	0.8	38	30	5.3	1.4	50	12.0	179	8.0	8.1	<20	8.83	1.07
1375	B01107	15	14	6	59	140	1.3	70	47	11.0	2.8	57	19.0	124	13.3	18.0	<20	16.40	2.15
1376	B01108	19	12	4	42	130	1.0	43	38	6.6	2.0	63	15.0	<2	8.1	9.6	<20	8.05	0.91
1377	B01109	23	19	6	49	77	0.8	39	25	5.4	1.5	56	10.0	<2	6.4	9.0	<20	9.10	1.19
1378	B01110	22	11	6	53	90	0.4	43	26	5.8	1.4	66	13.0	97	9.0	11.5	<20	11.10	1.49
1379	B01111	20	8	6	52	98	0.6	40	34	6.3	1.2	86	15.0	68	5.1	9.6	<20	9.71	1.30
1380	B01112	31	8	5	45	150	0.7	39	34	6.2	1.0	84	17.0	66	5.9	10.8	<20	9.11	1.24
1381	B01113	30	9	6	24	130	0.3	22	16	2.9	0.6	73	8.9	89	<0.5	4.2	<20	3.97	0.50
1382	B01114	31	9	5	45	49	0.2	22	10	2.6	0.5	61	8.5	73	1.1	3.9	<20	3.55	0.43
1383	B01115	38	14	5	42	86	0.5	18	13	2.2	0.9	67	6.8	<2	2.2	3.9	<20	3.28	0.47
1384	B01201	<5	10	3	35	48	0.3	17	13	2.6	0.9	35	7.1	43	3.7	5.2	<20	5.65	0.79
1385	B01202	16	13	5	39	110	0.9	37	24	5.6	1.0	53	13.0	83	4.5	8.4	<20	7.35	1.00
1386	B01203	24	14	5	44	100	0.8	47	31	7.0	1.4	60	16.0	57	6.9	10.8	<20	9.59	1.24
1387	B01204	22	13	5	43	120	1.0	48	39	7.4	1.8	61	19.0	175	7.8	14.7	<20	12.10	1.49
1388	B01205	23	12	4	42	99	0.8	59	30	7.6	1.3	54	18.0	93	10.0	13.2	<20	10.90	1.34
1389	B01206	22	12	4	39	110	1.1	62	40	9.5	2.1	55	21.0	91	7.9	14.5	<20	13.00	1.67
1390	B01207	23	15	5	41	120	1.0	58	44	9.0	2.1	59	22.0	53	11.1	13.6	<20	12.10	1.47
13																			

付表4 土壤地化学試料分析値一覽表

(16)

NO	SP.No. unit	Sn ppm	H ppm	Ta ppm	Nb ppm	Co ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
1412	BB1304	23	6	4	41	130	0.9	49	32	7.2	1.4	72	14.0	<2	6.2	10.4	<20	9.65	1.29
1413	BB1305	18	10	6	46	95	0.6	37	24	4.9	1.4	62	11.0	56	5.0	0.7	<20	7.94	0.97
1414	BB1306	32	7	6	40	88	0.5	36	23	3.0	1.2	84	11.0	41	5.3	6.7	<20	6.32	0.80
1415	BB1307	19	10	5	41	91	0.9	48	32	7.2	1.6	48	15.0	83	9.7	12.4	<20	10.40	1.32
1416	BB1308	21	11	6	41	56	0.6	35	27	4.3	0.7	38	14.0	46	4.4	5.4	<20	4.34	0.58
1417	BB1309	25	15	4	40	110	0.8	42	26	5.8	<0.5	53	13.0	43	8.6	6.6	<20	4.61	0.62
1418	BB1310	24	14	5	41	110	0.9	40	21	5.5	1.2	57	15.0	56	6.8	7.7	<20	7.22	1.00
1419	BB1311	28	22	5	41	130	1.0	55	39	7.0	1.7	61	16.0	58	6.5	10.5	<20	7.48	1.01
1420	BB1312	23	17	5	41	90	0.7	43	34	6.6	<0.5	69	16.0	54	7.3	9.9	<20	8.32	1.06
1421	BB1313	22	14	6	41	89	1.1	44	29	6.6	1.5	48	16.0	72	6.6	11.4	<20	9.27	1.24
1422	BC0101	26	4	<1	23	38	0.7	15	10	1.9	0.5	25	3.3	26	1.0	4.2	<20	3.72	0.53
1423	BC0102	25	4	2	24	45	0.6	17	12	2.2	<0.5	27	4.3	27	2.6	4.8	<20	3.64	0.50
1424	BC0103	27	6	3	26	44	0.9	31	20	3.5	0.5	42	9.2	34	5.3	5.2	<20	4.96	0.64
1425	BC0104	26	4	2	22	42	0.8	32	18	3.3	<0.5	31	7.0	28	4.6	4.3	<20	3.86	0.57
1426	BC0105	35	7	2	20	33	0.5	15	12	1.9	<0.5	31	6.3	18	2.8	2.6	<20	3.25	0.42
1427	BC0106	49	7	3	29	41	<0.2	16	9	2.1	0.5	43	7.1	23	0.9	3.6	<20	4.18	0.56
1428	BC0107	42	9	4	37	61	0.7	25	17	3.2	0.8	57	13.0	41	4.4	5.9	<20	6.41	0.84
1429	BC0108	57	9	5	43	82	1.5	53	29	6.5	1.2	75	26.0	68	7.5	9.3	<20	9.57	1.24
1430	BC0109	42	10	4	36	62	0.7	23	21	3.2	1.6	52	11.0	44	3.4	6.1	<20	6.31	0.84
1431	BC0110	34	10	4	33	50	0.7	22	15	2.8	0.7	51	8.8	33	3.4	4.6	<20	5.00	0.76
1432	BC0111	22	8	3	36	40	0.7	18	12	2.1	0.6	46	8.6	25	0.6	3.5	<20	4.20	0.53
1433	BC0112	34	10	3	31	43	0.5	19	13	2.3	0.5	40	7.3	25	1.2	4.0	<20	4.91	0.56
1434	BC0113	48	<4	5	39	49	0.6	29	18	3.4	0.7	42	14.0	34	5.7	5.1	<20	6.46	0.87
1435	BC0201	24	<4	2	18	37	0.7	11	9	1.4	0.5	23	4.4	31	2.9	4.4	<20	4.25	0.60
1436	BC0202	24	5	1	23	53	0.6	15	17	2.0	0.7	29	3.9	33	4.5	4.4	<20	5.17	0.55
1437	BC0203	59	12	6	41	73	0.7	35	26	5.1	1.2	57	16.0	62	7.0	8.5	<20	6.42	1.08
1438	BC0204	22	6	2	25	57	0.6	19	13	2.6	0.7	30	5.1	34	4.4	4.9	<20	4.99	0.65
1439	BC0205	26	8	3	30	42	0.6	22	12	2.6	1.4	30	6.7	38	4.5	5.1	<20	5.73	0.79
1440	BC0206	36	9	4	33	54	0.7	26	11	3.1	1.2	44	11.0	42	2.6	6.1	<20	6.60	0.94
1441	BC0207	35	6	5	29	110	0.7	29	17	3.8	1.1	45	11.0	37	2.9	6.3	<20	5.64	0.81
1442	BC0208	50	12	5	34	100	1.1	46	38	7.6	1.6	63	29.0	88	11.2	13.7	<20	11.70	1.55
1443	BC0209	46	12	6	40	100	1.5	54	33	7.4	1.4	74	28.0	74	8.1	11.6	<20	11.70	1.58
1444	BC0210	51	13	6	38	97	0.8	44	35	6.8	1.7	65	23.0	72	8.3	11.4	<20	11.40	1.48
1445	BC0211	52	23	7	36	120	0.7	69	46	8.9	2.3	82	26.0	69	10.3	10.4	<20	10.30	1.44
1446	BC0212	57	12	7	38	100	0.9	31	23	5.5	1.4	65	17.0	61	6.3	9.7	<20	10.20	1.33
1447	BC0213	45	11	5	40	96	0.7	32	33	5.2	1.0	60	17.0	58	4.3	8.4	<20	10.10	1.32
1448	BC0214	21	5	2	27	49	0.7	14	17	2.1	1.1	30	4.3	36	2.5	5.5	<20	4.78	0.65
1449	BC0215	48	7	5	41	68	0.9	36	20	4.9	1.5	48	19.0	53	4.1	7.1	<20	7.35	0.89
1450	BC0216	45	13	5	39	86	0.9	32	18	4.6	1.2	54	14.0	54	7.0	7.9	<20	8.23	1.00
1451	BC0217	39	13	5	38	80	0.6	32	26	4.4	1.2	50	12.0	47	4.6	6.2	<20	7.29	0.93
1452	BC0218	44	15	6	40	110	1.0	44	28	6.2	1.3	65	13.0	53	4.6	7.7	<20	8.85	1.13
1453	BC0219	44	17	4	38	85	0.7	41	25	5.7	1.0	60	13.0	46	4.7	8.2	<20	7.78	1.02
1454	BC0220	49	20	5	39	130	0.8	48	29	6.6	1.5	67	14.0	54	6.2	9.2	<20	8.19	1.10
1455	BC0221	57	14	6	44	75	1.0	49	37	7.5	1.2	65	19.0	89	9.0	12.4	<20	12.40	1.55
1456	BC0301	26	<4	2	21	78	0.9	32	17	3.2	0.7	29	3.2	32	3.3	5.7	<20	4.47	0.60
1457	BC0302	25	8	2	22	88	0.8	23	12	2.6	0.7	30	4.2	32	4.5	5.2	<20	4.52	0.67
1458	BC0303	24	<4	2	21	96	1.2	49	36	6.0	0.7	26	5.0	34	5.2	6.3	<20	5.15	0.70
1459	BC0304	26	<4	2	19	110	1.0	25	16	3.4	0.7	29	3.6	33	1.5	5.7	<20	4.52	0.62
1460	BC0305	51	14	5	38	100	0.9	36	23	5.9	1.5	66	23.0	67	5.7	10.8	<20	10.40	1.37
1461	BC0306	52	16	5	39	120	1.0	55	43	8.9	1.5	80	29.0	88	9.6	14.7	<20	12.10	1.54
1462	BC0307	44	12	6	38	110	1.1	49	36	7.7	1.5	68	27.0	73	7.1	12.1	<20	11.90	1.62
1463	BC0308	43	11	6	29	130	1.3	68	49	10.0	2.3	56	29.0	98	13.1	13.5	<20	13.90	1.95
1464	BC0309	49	11	6	39	120	0.9	37	28	6.6	1.3	70	19.0	62	5.7	10.1	21	9.38	1.33
1465	BC0310	64	9	6	40	90	0.6	32	26	4.0	1.2	57	12.0	50	3.9	7.0	<20	7.29	1.06
1466	BC0311	41	7	4	38	71	0.7	31	20	3.9	1.4	47	8.6	35	4.6	5.4	<20	5.40	0.78
1467	BC0312	28	5	4	36	40	0.4	25	8	2.6	0.7	32	6.1	25	3.9	4.4	<20	4.56	0.69
1468	BC0313	24	<4	<1	26	52	0.5	21	14	2.1	0.6	25	4.9	17	0.4	2.0	<20	3.17	0.46
1469	BC0314	24	<4	2	23	63	0.5	23	9	1.9	<0.5	24	4.1	14	1.1	2.8	<20	2.24	0.42
1470	BC0315	32	<4	3	32	51	0.5	22	14	2.3	0.6	34	5.8	23	1.6	3.3	<20	4.11	0.60
1471	BC0316	38	12	5	33	110	1.1	50	43	7.7	1.5	53	22.0	71	9.5	10.8	<20	12.10	1.72
1472	BC0317	60	10	7	40	120	0.8	40	32	6.3	1.9	67	19.0	65	6.4	9.9	<20	10.40	1.45
1473	BC0318	53	17	5	38	120	0.9	63	46	8.6	1.4	73	22.0	80	8.2	12.0	<20	10.40	1.43
1474	BC0319	59	20	6	33	240	1.1	130	92	16.0	2.7	100	27.0	91	15.3	15.1	<20	12.90	1.78
1475	BC0320	49	20	4	34	140	0.6	49	40	6.6	1.2	71	14.0	46	6.3	7.8	<20	6.77	0.97
1476	BC0321	38	11	3	28	52	0.5	41	26	5.1	0.7	48	10.0	36	4.0	5.9	<20	5.65	0.77
1477	BC0322	26	10	<1	21	12	0.6	28	11	2.4	0.5	30	5.3	16	1.9	3.3	<20	3.13	0.44
1478	BC0323	27	14	<1	20	19	0.4	10	7	1.4	<0.5	28	5.5	12	0.5	1.6	<20	2.34	0.37
1479	BC0401	40	9	3	34	36	0.6	23	13	3.2	0.7	42	9.2	36	6.8	4.9	<20	5.25	0.68
1480	BC0402	56	10	7	39	120	0.7	38	33	6.5	1.3	63	18.0	71	7.0	10.8	<20	9.95	1.57
1481	BC0403	42	11	7	30	110	1.4	56	42	8.7	2.3	48	5.0	103	9.1	14.6	<20	16.20	2.82
1482	BC0404	37	11	5	34	95	0.6	37	19	4.9	0.9	52	8.6	39	1.8	6.3	<20	6.06	0.91
1483	BC0405	35	6	2	24	87	0.4	18	9	1.4	<0.5	33	4.5	9	1.9	1.7	<20	2.42	0.34
1484	BC0406	27	8	3	23	100	0.3	26	11	1.9	<0.5	32	4.0	9	3.5	1.6	<20	2.12	0.35
1485	BC0501	29	<4	2	32	44	0.4	25	7	2.0	<0.5	34	5.1	15	2.2	2.6	<20	3.15	0.50

付表4 土壤地化学試料分析値一覽表

(17)

NO	SP.No.	Sn	H	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1506	BC0614	56	31	5	43	120	0.9	26	24	3.6	1.2	96	17.0	19	1.4	4.7	<20	4.94	0.69
1507	BC0615	53	41	2	40	160	1.1	31	34	4.7	0.7	98	25.0	32	4.6	5.5	<20	4.93	0.68
1508	BC0701	42	6	<1	32	170	3.5	110	120	18.0	2.3	26	3.8	39	11.9	12.6	<20	9.25	1.04
1509	BC0702	20	12	6	18	120	1.1	45	31	7.0	2.1	83	16.8	49	7.1	10.7	<20	12.10	1.75
1510	BC0703	49	9	4	39	140	0.7	29	16	4.1	1.2	49	9.8	78	4.2	6.5	<20	7.04	1.08
1511	BC0704	46	8	5	36	67	0.6	28	14	3.3	0.7	49	7.1	33	2.7	4.5	<20	5.32	0.68
1512	BC0705	41	8	5	37	42	0.4	17	9	2.1	0.7	39	5.7	27	4.5	4.6	<20	5.31	0.68
1513	BC0706	31	6	3	28	26	0.4	12	13	1.4	0.5	34	5.7	24	2.5	3.3	<20	3.61	0.50
1514	BC0707	28	5	3	28	20	0.5	103	15	1.3	<0.5	36	4.5	22	0.3	2.8	<20	3.35	0.47
1515	BC0708	37	7	4	34	38	0.4	16	17	2.0	0.5	46	5.1	26	1.1	4.4	<20	4.35	0.59
1516	BC0709	32	7	3	36	36	0.5	19	18	2.1	0.9	37	5.5	28	2.9	4.4	<20	4.63	0.61
1517	BC0710	39	10	4	36	49	0.6	24	14	2.8	0.7	68	6.0	31	1.5	4.7	<20	4.60	0.65
1518	BC0711	52	8	5	40	49	0.4	15	9	1.7	<0.5	110	11.0	20	0.7	3.6	<20	3.61	0.49
1519	BC0712	59	11	5	42	110	0.3	19	15	1.6	<0.5	120	14.0	18	1.3	3.6	<20	3.39	0.39
1520	BC0713	59	17	6	43	110	0.7	14	16	1.4	<0.5	120	16.0	22	1.0	3.6	<20	3.44	0.49
1521	BC0801	56	7	7	38	110	0.9	41	28	7.2	2.3	59	17.0	89	8.9	12.4	<20	13.20	1.68
1522	BC0802	47	12	6	24	170	1.0	40	23	6.0	1.0	63	11.0	50	4.4	8.1	<20	8.86	1.08
1523	BC0803	49	9	5	28	150	0.9	30	17	4.7	1.0	52	9.6	45	4.4	6.3	<20	6.70	0.96
1524	BC0804	40	8	5	38	120	0.9	25	17	3.7	0.9	48	7.6	36	2.7	5.4	<20	5.51	0.86
1525	BC0805	40	9	4	37	100	0.6	22	13	3.3	0.6	43	7.2	34	1.7	5.5	<20	5.53	0.81
1526	BC0806	45	10	6	39	120	0.7	27	23	3.7	1.0	54	10.0	48	5.8	6.9	<20	7.19	1.08
1527	BC0807	43	8	4	36	50	0.6	20	17	2.7	0.6	46	6.8	33	4.1	5.3	<20	4.80	0.73
1528	BC0808	36	7	3	33	44	0.6	21	13	2.4	0.6	39	6.6	30	3.1	3.7	<20	4.07	0.66
1529	BC0809	41	8	5	45	55	0.7	24	20	2.9	0.7	66	7.9	38	4.6	5.4	<20	5.54	0.75
1530	BC0910	49	10	5	38	81	0.6	24	21	3.1	0.7	100	13.0	35	1.3	5.1	<20	5.05	0.72
1531	BC0911	51	17	7	50	120	0.8	61	42	7.3	1.5	70	20.0	74	6.2	9.7	<20	10.30	1.47
1532	BC0912	50	13	5	40	89	0.3	27	21	3.3	0.7	95	14.0	36	3.7	5.2	<20	5.36	0.80
1533	BC0901	40	9	4	32	87	0.6	26	19	3.8	0.9	47	10.0	44	5.0	6.6	<20	6.39	0.93
1534	BC0902	35	9	4	25	80	0.8	37	19	4.5	0.7	32	13.0	48	4.3	7.7	<20	7.15	1.08
1535	BC0903	47	10	5	37	100	0.6	26	19	3.9	1.2	51	8.4	49	2.5	6.1	<20	6.83	1.02
1536	BC0904	39	7	4	16	83	0.5	20	16	3.0	0.9	41	6.1	35	2.3	5.9	<20	5.49	0.80
1537	BC0905	46	7	4	12	110	0.6	28	24	4.0	0.8	58	13.0	43	3.7	6.7	<20	6.94	0.99
1538	BC0906	66	13	5	15	130	1.1	80	66	12.0	2.0	87	23.0	86	12.6	15.4	<20	14.40	2.03
1539	BC0907	19	<4	2	23	70	0.8	45	31	5.9	0.7	42	10.0	47	5.7	7.7	<20	5.86	0.76
1540	BC0908	37	7	3	32	85	0.9	42	38	4.4	1.4	48	7.7	42	4.9	5.6	<20	5.67	0.80
1541	BC0909	46	8	5	41	74	0.6	24	16	3.2	0.8	57	11.0	43	3.9	6.4	<20	6.64	0.97
1542	BC0910	47	11	5	38	55	0.6	22	16	2.6	0.8	60	9.3	36	6.3	5.5	<20	6.09	0.90
1543	BC0911	46	10	5	39	97	0.3	19	14	2.5	0.7	61	9.8	37	2.1	4.6	<20	5.76	0.76
1544	BC0912	44	6	4	40	78	0.5	19	14	2.6	0.7	58	10.8	39	2.5	5.4	<20	5.84	0.87
1545	BC0913	44	8	4	40	43	0.5	18	10	2.2	1.2	54	9.4	38	0.8	5.2	<20	6.13	0.97
1546	BC0914	43	9	6	40	69	0.4	17	7	2.0	0.6	75	11.0	30	3.7	3.8	<20	4.34	0.67
1547	BC1001	19	<4	<1	16	53	0.4	12	9	1.4	0.5	15	2.7	19	2.2	3.0	<20	2.31	0.30
1548	BC1002	41	10	4	34	69	0.6	30	19	4.0	1.1	42	12.0	48	6.6	6.8	<20	7.42	1.08
1549	BC1003	45	10	8	45	100	0.7	23	16	4.2	1.1	68	15.0	61	3.6	8.9	<20	9.68	1.31
1550	BC1004	51	8	7	39	130	0.8	38	30	5.0	1.3	63	16.0	71	4.3	10.5	<20	10.40	1.43
1551	BC1005	43	7	7	40	96	0.9	32	24	5.8	2.0	65	20.0	85	9.5	12.9	<20	13.40	1.72
1552	BC1006	63	8	8	43	100	0.7	28	31	5.1	1.5	62	13.0	71	5.9	10.0	<20	10.80	1.47
1553	BC1007	63	8	8	40	110	0.6	38	24	5.7	1.7	59	15.0	63	8.9	12.1	<20	13.60	1.88
1554	BC1008	52	<4	6	45	170	0.8	18	16	2.2	0.6	120	14.0	27	4.9	4.9	<20	4.69	0.69
1555	BC1009	52	<4	5	44	160	0.6	25	12	2.3	0.7	120	11.8	27	2.5	3.7	<20	4.57	0.68
1556	BC1010	51	8	5	45	130	0.3	30	10	2.4	0.7	110	13.0	26	4.9	4.5	<20	4.46	0.65
1557	BC1011	50	6	6	43	110	0.3	26	20	3.0	0.7	97	18.0	33	6.5	4.6	<20	5.35	0.63
1558	BC1012	60	9	8	46	100	0.7	38	38	7.3	1.8	64	19.0	91	8.0	13.3	<20	14.40	1.98
1559	BC1013	55	8	5	41	49	0.3	12	9	1.5	<0.5	110	15.0	22	2.2	3.5	<20	3.87	0.63
1560	BC1101	39	10	5	31	90	1.2	46	35	6.3	1.2	37	14.0	62	5.3	9.3	<20	9.33	1.38
1561	BC1102	57	13	7	42	130	1.6	68	65	17.0	3.9	71	35.0	156	19.7	28.0	<20	20.10	2.38
1562	BC1103	49	9	5	45	73	0.6	23	13	2.8	0.7	68	11.0	33	1.3	4.8	<20	5.54	0.89
1563	BC1104	32	7	5	41	110	0.6	28	18	3.2	0.9	65	8.8	31	5.8	4.2	<20	5.10	0.70
1564	BC1105	44	6	5	39	110	0.5	21	17	2.4	0.5	93	8.4	25	5.5	3.7	<20	3.74	0.52
1565	BD0101	42	10	4	31	120	1.1	54	41	7.4	0.9	41	11.0	59	11.9	10.9	<20	7.44	0.99
1566	BD0102	46	11	4	34	120	1.0	48	34	6.7	1.6	40	12.0	59	7.9	9.4	<20	8.34	1.06
1567	BD0103	45	11	4	33	110	0.9	49	30	6.3	0.9	45	11.0	60	7.6	6.8	<20	7.56	1.03
1568	BD0104	48	12	4	31	130	1.2	64	43	9.0	1.7	47	14.0	74	10.0	12.0	<20	9.90	1.35
1569	BD0105	38	11	3	27	110	0.9	58	45	7.6	1.8	35	8.8	71	10.4	11.8	<20	8.53	1.38
1570	BD0106	47	9	3	33	120	1.0	58	38	7.8	1.4	50	16.0	66	8.9	11.6	<20	8.04	1.10
1571	BD0107	37	8	4	20	100	1.0	53	39	7.1	1.3	35	12.0	63	8.9	10.6	<20	8.58	1.06
1572	BD0108	47	10	4	33	130	1.0	58	43	8.3	1.8	51	13.0	70	10.0	11.9	<20	9.52	1.19
1573	BD0109	44	37	5	40	110	1.0	57	41	7.7	1.7	51	12.8	72	7.4	10.7	<20	9.25	1.12
1574	BD0201	29	7	<1	20	130	1.3	64	45	6.0	0.7	32	7.2	46	8.0	8.0	<20	5.41	0.73
1575	BD0202	34	9	<1	23	100	0.8	53	41	7.0	1.6	32	9.3	61	9.6	9.7	<20	8.12	1.08
1576	BD0203	44	11	3	29	90	0.9	45	33	5.7	1.1	38	7.6	53	6.1	8.6	<20	6.20	0.85
1577	BD0204	32	7	<1	23	50	0.7	23	14	2.9	0.7	23	4.5	36	2.6	5.8	<20	4.09	0.56
1578	BD0205	38	7	1	19	41	0.6	20	15	2.4	0.5	24	2.3	33	5.8	5.2	<20	3.62	0.53
1579	BD0206	51	9	5	24	110	0.9	55	28										

付表4 土壤地化学試料分析値一覽表

(18)

NO	SP.No. unit	Sn ppm	W ppm	Ta ppm	Nb ppm	Co ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
1600	BD0315	47	12	5	35	100	0.8	45	38	5.8	1.0	51	13.0	65	11.1	9.6	<20	7.33	1.10
1601	BD0316	49	11	4	37	100	0.7	45	33	5.6	1.2	46	10.0	65	8.3	9.6	<20	7.85	1.24
1602	BD0317	51	10	3	36	110	1.2	61	39	6.9	1.3	46	10.0	84	9.8	12.3	<20	7.31	1.16
1603	BD0318	50	13	4	31	120	0.8	50	40	7.2	1.4	48	13.0	72	11.0	10.6	<20	8.24	1.39
1604	BD0319	57	12	5	37	10	0.9	51	43	6.9	1.6	51	13.0	73	10.3	12.6	<20	7.36	1.21
1605	BD0320	34	6	4	26	99	0.8	52	35	6.5	1.3	34	12.0	64	4.9	11.5	<20	8.09	1.28
1606	BD0321	43	9	3	29	110	0.8	54	39	6.0	1.3	42	13.0	69	11.4	10.7	<20	8.11	1.33
1607	BD0322	42	10	3	26	110	1.0	57	39	7.2	1.3	40	13.0	68	12.9	10.1	<20	7.50	1.17
1608	BD0401	37	8	3	27	93	0.9	48	41	6.1	1.5	33	9.4	65	7.9	11.0	<20	7.82	1.05
1609	BD0402	44	12	4	41	66	0.7	38	37	4.4	1.2	48	11.0	53	8.3	8.9	<20	5.54	0.95
1610	BD0403	50	11	3	35	87	0.7	38	33	4.8	1.2	48	9.8	57	9.1	9.1	<20	6.04	0.95
1611	BD0404	39	13	3	32	66	0.8	37	24	4.1	1.3	38	6.3	51	3.5	8.2	<20	5.53	0.98
1612	BD0405	47	10	3	30	93	0.8	49	51	5.9	1.4	40	12.0	63	10.4	10.3	<20	5.77	0.86
1613	BD0406	36	10	3	29	120	0.8	56	30	7.5	1.5	47	12.0	74	11.9	12.5	<20	8.67	1.44
1614	BD0407	40	9	3	29	110	0.8	53	44	6.9	1.1	42	12.0	66	7.6	10.7	<20	8.10	1.12
1615	BD0408	50	10	3	33	110	0.8	51	33	6.5	1.2	45	12.0	67	10.9	10.9	<20	7.40	1.13
1616	BD0409	46	9	4	34	90	0.7	48	37	6.0	1.4	35	10.0	76	9.2	11.6	<20	7.54	1.21
1617	BD0410	53	6	3	25	72	0.7	37	25	4.2	1.2	27	7.2	52	6.1	8.2	<20	5.56	0.83
1618	BD0411	62	<4	1	21	88	0.6	43	20	3.3	<0.5	25	4.2	38	3.3	4.7	<20	3.49	0.58
1619	BD0412	51	5	<1	22	130	0.5	63	37	5.2	0.7	30	4.4	36	5.3	5.8	<20	4.52	0.70
1620	BD0413	53	8	3	30	61	0.6	30	25	3.5	0.9	30	5.7	53	4.8	6.8	<20	5.05	0.55
1621	BD0414	41	8	4	35	83	0.7	34	26	4.4	1.0	36	7.9	54	5.3	8.2	<20	7.10	1.11
1622	BD0415	51	11	4	35	110	0.5	48	30	5.6	1.0	46	9.6	61	7.2	9.4	<20	6.75	1.11
1623	BD0416	50	12	5	37	65	0.7	44	36	5.6	0.9	46	12.0	62	9.7	9.4	<20	7.45	1.11
1624	BD0417	45	10	4	29	110	0.9	54	41	6.9	1.2	47	12.0	67	8.1	10.6	<20	8.37	1.32
1625	BD0418	45	11	4	33	110	0.9	53	41	7.2	1.4	47	15.0	70	8.3	12.0	<20	8.23	1.36
1626	BD0501	20	9	1	19	97	0.6	22	10	2.9	1.0	23	1.9	26	3.3	5.1	<20	3.21	0.56
1627	BD0502	22	7	1	17	93	0.7	31	26	3.9	<0.5	20	1.6	28	3.6	4.5	<20	2.86	0.53
1628	BD0503	20	9	<1	18	67	0.7	27	21	3.0	<0.5	17	1.8	27	3.7	4.4	<20	2.96	0.45
1629	BD0504	22	7	<1	20	36	0.5	17	15	2.0	<0.5	20	2.3	28	3.3	4.1	<20	2.78	0.47
1630	BD0505	22	6	1	19	50	0.6	16	12	2.3	<0.5	21	2.2	28	5.1	4.3	<20	2.76	0.49
1631	BD0506	25	<4	1	18	48	0.6	23	13	2.6	<0.5	19	2.0	26	2.6	3.9	<20	2.78	0.46
1632	BD0601	20	8	<1	19	95	0.6	16	18	2.3	<0.5	26	3.2	27	2.2	5.1	<20	3.33	0.54
1633	BD0602	20	9	2	19	72	0.6	16	13	2.1	0.6	24	2.9	27	4.1	4.2	<20	3.10	0.51
1634	BD0603	25	6	<1	19	46	0.4	12	11	1.7	<0.5	23	2.8	29	3.8	4.4	<20	3.06	0.53
1635	BD0604	19	6	2	19	58	0.7	19	17	2.4	<0.5	18	2.6	29	4.1	5.1	<20	3.01	0.52
1636	BD0605	22	5	1	15	92	0.7	26	20	3.1	<0.5	18	2.5	27	4.5	5.2	<20	2.82	0.49
1637	BD0606	23	4	<1	15	46	0.6	18	11	2.0	<0.5	15	2.5	27	4.0	4.1	<20	2.90	0.45
1638	BD0607	20	4	<1	16	50	0.6	19	14	2.3	0.6	18	2.0	26	3.3	3.9	<20	2.90	0.46
1639	BD0608	19	5	<1	17	69	0.7	25	19	3.0	<0.5	15	1.7	26	0.9	4.1	<20	2.63	0.44
1640	BD0609	21	7	1	18	61	0.6	21	18	2.7	0.6	19	1.6	25	1.5	4.1	<20	2.87	0.50
1641	BD0610	26	6	<1	18	46	0.6	19	16	2.3	<0.5	19	2.0	25	3.4	3.5	<20	2.57	0.43
1642	BD0611	20	4	1	20	34	0.4	14	8	1.6	<0.5	19	2.1	25	1.8	3.4	<20	3.41	0.48
1643	BD0612	20	6	2	23	37	0.5	15	12	1.9	<0.5	19	2.5	28	3.6	4.1	<20	3.13	0.50
1644	BD0701	30	6	1	19	66	0.9	36	30	3.8	<0.5	15	2.4	32	7.0	5.7	<20	3.68	0.57
1645	BD0702	24	6	<1	20	49	1.0	29	20	3.0	0.7	14	2.4	30	3.0	5.2	<20	3.53	0.58
1646	BD0703	23	6	1	19	65	0.8	38	23	3.9	0.7	15	2.6	36	6.1	5.8	<20	3.74	0.57
1647	BD0704	28	5	1	16	56	0.8	29	19	3.2	0.7	13	1.9	31	5.6	5.6	<20	3.10	0.46
1648	BD0705	28	<4	1	19	59	0.8	33	22	3.2	<0.5	12	2.0	34	2.5	5.6	<20	3.17	0.51
1649	BD0706	22	6	2	22	66	0.8	40	25	3.8	<0.5	15	3.0	33	6.0	6.1	<20	3.44	0.52
1650	BD0707	23	5	1	17	50	0.8	32	26	3.4	0.8	15	2.0	33	3.7	5.8	<20	3.16	0.51
1651	BD0708	27	8	1	21	52	0.6	30	21	3.0	0.7	15	2.4	32	4.3	5.3	<20	3.57	0.54
1652	BD0709	23	30	1	14	41	0.6	23	19	2.4	0.6	9	1.4	28	1.0	4.2	<20	2.89	0.46
1653	BD0710	30	18	<1	16	46	0.6	25	16	2.6	<0.5	10	1.6	28	0.2	4.4	<20	3.13	0.49
1654	BD0711	35	7	<1	19	37	0.5	18	12	2.2	<0.5	15	2.0	26	2.6	4.1	<20	3.15	0.48
1655	BD0712	25	11	1	18	51	0.7	29	19	3.1	<0.5	15	2.8	28	6.4	4.3	<20	3.60	0.60
1656	BD0713	25	3	1	17	45	0.6	27	24	2.9	0.6	11	2.2	27	0.7	4.2	<20	3.47	0.54
1657	BD0714	22	9	1	21	39	0.6	23	19	2.9	0.6	16	3.3	28	3.3	4.4	<20	3.38	0.54
1658	BD0801	19	8	1	24	41	0.6	21	18	3.0	0.7	16	2.8	40	6.1	4.3	<20	4.35	0.69
1659	BD0802	23	8	1	22	3	0.5	14	11	1.7	<0.5	23	2.4	29	1.2	5.5	<20	3.66	0.59
1660	BD0803	24	5	2	22	31	0.5	12	12	1.6	<0.5	21	2.4	31	5.5	6.8	<20	3.59	0.58
1661	BD0804	23	5	1	20	29	0.5	12	9	1.6	<0.5	20	2.2	27	1.1	4.5	<20	3.53	0.59
1662	BD0805	20	4	<1	18	64	0.9	32	20	3.9	0.7	16	2.1	31	3.3	4.4	<20	3.46	0.56
1663	BD0806	25	6	1	16	52	0.7	29	21	3.1	0.6	12	1.4	30	4.9	5.0	<20	3.32	0.54
1664	BD0807	26	7	1	18	50	0.7	30	17	3.2	0.8	11	2.1	31	1.1	4.9	<20	3.51	0.55
1665	BD0808	33	6	2	16	51	0.7	30	18	3.1	0.7	11	1.9	29	4.8	4.2	<20	3.03	0.50
1666	BD0809	30	7	<1	20	54	0.8	34	20	3.6	<0.5	16	2.1	33	3.6	5.3	<20	3.40	0.55
1667	BD0810	28	5	<1	20	50	0.7	28	22	3.0	0.6	9.9	1.9	32	5.6	5.0	<20	3.29	0.57
1668	BD0811	34	6	1	18	53	0.7	30	20	3.2	0.7	16	2.3	31	3.1	5.0	<20	3.17	0.51
1669	BD0812	31	7	<1	16	65	1.0	37	28	4.2	0.8	14	2.2	37	5.9	5.6	<20	3.66	0.59
1670	BD0813	40	6	<1	17	79	1.2	44	31	5.1	0.8	14	2.5	35	6.2	6.2	<20	4.00	0.60
1671	BD0814	37	11	1	16	52	0.6	31	20	2.6	<0.5	14	1.9	25	2.5	3.7	<20	2.46	0.43
1672	BD0815	25	20	<1	17	41	0.5	13	8	1.6	<0.5	16	2.9	25	1.9	3.4	<20	2.71	0.49
1673	BD0816	27	18	2	17	17	0.3	18	<5	0.8	<0.5	21	2.9	21	0.9	3.0	<20	2.87	0.48
1674	BD0817																		



附表4 土壤地化学試料分析値一覽表

(19)

NO	SP.No.	Sn	U	Ta	Nb	Ce	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Er	Yb	Lu
unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1788	CA0414	17	5	<1	21	67	0.9	37	25	3.9	0.9	19	3.1	34	3.9	5.8	<20	3.86	0.57
1789	CA0415	15	<4	2	15	72	0.9	38	27	4.1	0.7	15	2.3	30	3.2	5.8	<20	3.15	0.51
1790	CA0416	18	<4	1	15	91	1.1	43	31	4.9	0.6	16	3.2	30	4.1	5.3	<20	3.57	0.47
1791	CA0417	14	5	<1	18	95	1.2	51	36	5.7	0.7	18	1.6	37	5.4	5.8	<20	3.77	0.57
1792	CA0418	24	<4	1	23	48	0.7	19	13	2.6	0.8	27	1.8	32	3.3	5.7	<20	4.26	0.54
1793	CA0419	17	<4	2	20	74	0.0	42	29	4.6	0.6	19	2.3	39	4.7	6.4	<20	3.83	0.54
1794	CA0420	17	<4	1	17	66	1.0	40	23	4.2	1.1	18	2.6	40	4.3	6.3	<20	3.61	0.52
1795	CA0421	16	<4	2	19	48	0.7	31	17	3.1	<0.5	19	2.3	33	3.4	5.1	<20	3.53	0.46
1796	CA0501	33	27	<1	22	75	0.9	37	24	3.7	<0.5	23	2.5	24	9.3	3.9	<20	2.81	0.39
1797	CA0502	30	18	2	21	96	1.0	44	22	4.6	<0.5	27	2.6	28	5.1	5.6	<20	3.51	0.49
1798	CA0503	16	10	1	16	100	1.4	47	37	5.9	<0.5	23	2.5	32	6.0	6.0	<20	3.68	0.55
1799	CA0504	22	8	<1	15	87	0.9	42	31	4.9	<0.5	21	1.7	29	5.4	5.4	<20	3.37	0.46
1800	CA0505	13	9	<1	18	88	1.3	47	39	5.5	0.9	20	2.1	31	2.8	5.9	<20	3.27	0.50
1801	CA0506	19	10	1	19	59	0.6	28	18	2.8	<0.5	23	2.5	29	3.9	5.2	<20	3.58	0.51
1802	CA0507	19	7	2	21	48	0.7	24	9	2.5	<0.5	24	2.6	30	1.8	4.9	<20	3.50	0.51
1803	CA0508	25	<4	2	22	59	6.0	29	19	4.4	5.6	24	1.5	34	8.9	0.8	<20	4.43	0.60
1804	CA0509	19	10	2	24	69	0.9	27	22	3.9	0.8	25	4.0	35	3.2	5.7	<20	4.44	0.60
1805	CA0510	15	<4	1	24	62	1.0	29	20	4.2	0.7	26	3.1	36	5.4	6.1	<20	4.31	0.59
1806	CA0511	17	5	2	26	56	0.6	27	22	3.7	0.6	22	2.8	38	1.7	6.8	<20	4.57	0.68
1807	CA0512	19	<4	1	25	58	0.8	25	16	3.2	0.5	20	2.7	36	4.6	5.7	<20	4.11	0.59
1808	CA0513	16	<4	2	24	52	0.8	24	16	2.9	0.9	20	2.4	34	4.4	4.9	<20	4.15	0.54
1809	CA0514	22	5	<1	11	62	0.8	36	25	4.1	0.6	11	2.0	24	6.0	3.8	<20	2.92	0.39
1810	CA0515	18	<4	2	18	89	1.2	51	33	5.8	0.6	19	1.9	36	5.6	6.2	<20	3.76	0.51
1811	CA0516	19	<4	<1	15	100	1.6	56	30	6.4	0.6	20	3.2	38	4.9	6.4	<20	4.13	0.56
1812	CA0517	16	<4	<1	17	79	1.0	47	37	5.0	0.9	19	3.1	41	5.9	6.4	<20	3.90	0.52
1813	CA0518	18	<4	<1	16	77	1.0	46	35	4.6	0.7	18	2.4	39	4.5	5.2	<20	3.67	0.45
1814	CA0519	12	<4	<1	17	77	1.2	46	30	5.0	0.7	18	2.1	37	5.4	6.6	<20	3.91	0.52
1815	CA0520	14	<4	1	16	89	1.2	50	30	5.2	0.9	20	2.4	41	4.4	6.6	<20	4.13	0.52
1816	CA0601	21	21	2	21	110	1.4	53	38	5.8	1.1	29	3.1	32	6.3	6.2	<20	4.41	0.55
1817	CA0602	15	27	1	19	99	1.2	43	37	5.4	0.9	26	2.3	31	6.4	6.0	<20	3.99	0.53
1818	CA0603	18	7	<1	17	93	1.2	49	38	5.8	0.6	26	2.0	33	9.2	5.6	<20	4.08	0.48
1819	CA0604	17	9	<1	20	75	0.9	37	25	4.6	0.7	24	<0.5	33	5.8	6.2	<20	4.32	0.56
1820	CA0605	17	<4	2	21	83	0.6	25	13	3.3	<0.5	24	3.3	30	5.1	4.4	<20	3.64	0.56
1821	CA0606	23	8	1	24	73	0.8	24	18	3.2	0.6	26	2.6	37	4.7	5.8	<20	4.58	0.61
1822	CA0607	21	9	2	22	75	0.9	30	20	3.8	0.6	24	2.6	37	5.6	5.9	25	4.35	0.56
1823	CA0608	24	12	<1	27	81	0.9	32	22	4.0	0.8	27	3.2	40	6.4	6.1	<20	4.96	0.64
1824	CA0609	22	<4	2	22	53	0.7	24	22	2.9	0.6	27	2.4	35	3.9	5.5	<20	4.22	0.60
1825	CA0610	15	<4	<1	28	73	0.7	22	13	2.7	0.5	26	2.7	38	2.5	5.1	<20	3.80	0.52
1826	CA0611	20	12	2	23	68	0.8	24	16	3.2	0.8	25	3.1	33	3.0	4.0	<20	4.38	0.59
1827	CA0612	17	<4	1	21	45	0.6	25	14	2.7	0.9	24	2.0	32	2.9	5.5	<20	3.85	0.57
1828	CA0613	14	<4	<1	22	150	1.4	65	41	7.1	1.1	24	4.0	45	3.7	5.1	<20	5.08	0.68
1829	CA0614	15	<4	1	16	82	1.3	47	36	5.5	1.1	16	3.1	32	5.7	5.2	<20	3.70	0.52
1830	CA0615	16	<4	<1	11	93	1.1	47	28	5.5	0.9	15	1.8	32	3.1	4.5	<20	3.46	0.46
1831	CA0616	19	<4	1	17	92	1.1	49	30	5.3	1.1	20	2.9	35	6.7	5.8	<20	3.90	0.56
1832	CA0617	14	<4	1	15	85	1.1	47	31	5.2	0.5	19	2.2	37	5.5	5.8	<20	3.72	0.54
1833	CA0618	18	<4	1	17	81	1.0	48	34	5.1	1.0	20	3.3	40	4.9	6.0	<20	3.93	0.53
1834	CA0619	9	<4	1	19	84	1.2	50	37	5.3	0.7	19	2.2	40	5.9	6.3	<20	4.27	0.60
1835	CA0701	18	12	1	16	100	1.3	46	37	5.5	<0.5	23	2.6	31	5.3	5.9	<20	3.46	0.50
1836	CA0702	16	12	1	19	81	1.0	39	27	4.9	0.5	21	2.2	29	7.6	5.1	<20	3.96	0.53
1837	CA0703	27	12	2	19	75	1.0	33	22	4.3	0.7	28	2.2	37	1.9	5.9	<20	4.52	0.68
1838	CA0704	18	10	1	21	87	0.8	25	19	3.4	0.5	24	2.3	33	2.6	5.8	<20	4.03	0.60
1839	CA0705	21	7	1	20	50	0.6	22	14	3.0	0.7	28	3.3	39	5.1	6.5	<20	4.92	0.65
1840	CA0706	19	7	2	26	61	0.9	26	20	3.3	0.9	27	2.4	36	5.2	5.9	<20	4.22	0.61
1841	CA0707	22	10	2	23	88	1.0	36	23	4.5	1.1	28	3.6	37	5.5	3.2	<20	4.52	0.57
1842	CA0708	20	7	1	21	150	0.8	21	16	3.0	0.6	30	3.3	34	3.7	5.6	<20	4.24	0.61
1843	CA0709	20	<4	1	18	71	0.6	17	16	2.4	<0.5	27	3.7	32	1.8	5.2	<20	3.83	0.55
1844	CA0710	18	<4	1	21	56	0.7	20	13	2.8	0.7	22	2.5	35	3.5	5.3	<20	4.37	0.60
1845	CA0711	19	6	<1	19	79	0.7	31	26	3.9	0.7	27	3.3	36	4.4	5.4	<20	4.44	0.67
1846	CA0712	23	<4	1	13	73	1.0	43	28	4.7	0.8	14	1.9	27	5.4	5.2	<20	3.57	0.43
1847	CA0713	16	<4	1	12	62	0.9	37	23	4.8	<0.5	12	1.8	30	2.7	5.0	<20	2.85	0.43
1848	CA0714	16	<4	<1	17	78	0.9	42	30	4.6	<0.5	19	2.6	37	6.5	5.9	<20	3.46	0.59
1849	CA0715	13	<4	1	19	65	0.8	35	24	3.5	<0.5	13	2.4	34	3.7	5.6	<20	3.17	0.55
1850	CA0716	18	5	<1	18	61	0.9	37	37	3.9	0.6	15	2.0	33	3.7	5.4	<20	3.48	0.54
1851	CA0717	14	<4	<1	19	50	0.7	27	22	2.9	0.9	18	1.6	35	5.0	5.3	<20	3.70	0.56
1852	CA0718	18	<4	1	19	53	0.6	21	16	2.5	<0.5	18	2.3	33	2.4	5.0	<20	3.04	0.46
1853	CA0801	21	15	2	20	83	1.0	42	34	4.7	<0.5	18	2.3	33	6.2	8.0	<20	3.81	0.47
1854	CA0802	27	15	1	21	82	1.0	42	29	4.6	<0.5	23	2.4	35	5.7	6.2	<20	3.63	0.55
1855	CA0803	18	11	2	19	75	1.0	33	24	4.0	<0.5	24	2.3	34	4.7	5.9	<20	3.66	0.60
1856	CA0804	16	15	<1	22	67	0.8	26	20	3.4	0.8	25	2.2	31	4.9	5.5	<20	3.78	0.57
1857	CA0805	20	13	2	25	59	0.8	24	19	3.0	<0.5	22	2.0	37	4.1	7.2	<20	3.43	0.59
1858	CA0806	20	10	<1	23	56	0.6	22	17	2.8	<0.5	22	2.0	34	4.2	5.6	<20	3.66	0.57
1859	CA0807	23	9	2	20	62	0.8	27	22	3.3	<0.5	21	2.5	31	2.1	5.3	<20	3.44	0.55
1860	CA0808	21	6	1	23	42	0.4	15	9	2.1	<0.5	25	2.2	34	1.5	6.0	<20	3.88	0.64
1861	CA0809	31	<4	2	20	91	0.6	17	7										

付表4 土壤地化学試料分析値一覽表

(20)

NO	SP.No.	Sn	H	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1882	CA0911	23	8	<1	20	90	0.9	44	39	5.0	<0.5	20	0.9	36	3.3	5.3	<20	3.02	0.60
1883	CA0912	26	<4	2	16	78	1.1	42	28	4.8	1.0	14	<0.5	32	4.5	5.3	<20	3.33	0.56
1884	CA0913	20	5	<1	20	69	1.0	43	35	4.6	0.7	21	2.5	39	5.9	6.1	<20	3.42	0.58
1885	CA0914	20	<4	<1	18	55	0.8	32	22	3.5	<0.5	18	<0.5	33	4.1	5.7	<20	3.09	0.56
1886	CA0915	17	<4	2	19	60	0.7	35	28	3.5	<0.5	21	2.7	34	4.3	5.3	<20	3.66	0.55
1887	CA0916	18	<4	<1	27	54	0.7	25	20	2.8	0.7	20	3.0	37	3.7	6.0	<20	4.16	0.62
1888	CA0917	19	<4	3	22	74	0.6	19	14	2.4	0.5	23	3.0	30	2.6	4.6	<20	3.08	0.52
1889	CA0918	12	<4	2	24	84	0.5	17	12	2.0	<0.5	23	2.3	27	3.2	4.3	<20	3.33	0.50
1890	CA1001	37	25	1	19	55	0.3	16	10	1.0	<0.5	18	1.1	9	0.8	1.4	<20	1.29	0.25
1891	CA1002	21	<4	<1	21	76	0.8	22	21	2.9	1.5	23	2.1	33	4.7	5.5	<20	3.70	0.63
1892	CA1003	47	32	3	22	47	0.5	22	9	1.9	<0.5	19	2.3	16	3.7	2.6	<20	2.10	0.28
1893	CA1004	28	28	<1	22	53	0.7	24	8	2.7	<0.5	24	<0.5	27	7.3	3.7	<20	3.01	0.53
1894	CA1005	16	19	<1	21	86	0.9	34	21	3.9	<0.5	27	<0.5	32	3.1	5.0	<20	3.47	0.53
1895	CA1006	26	22	3	21	71	0.8	29	18	3.3	<0.5	26	2.1	31	4.8	5.4	<20	3.17	0.59
1896	CA1007	30	20	3	23	74	0.8	27	36	3.4	<0.5	25	<0.5	34	5.6	5.9	<20	3.22	0.49
1897	CA1008	22	13	<1	24	75	0.5	22	15	2.9	<0.5	26	<0.5	34	3.9	6.0	<20	3.47	0.53
1898	CA1009	23	9	2	23	56	0.7	21	15	2.6	<0.5	26	2.4	34	2.0	5.7	<20	3.54	0.54
1899	CA1010	17	10	<1	26	65	0.8	25	15	2.9	0.7	26	2.6	35	4.5	6.0	<20	4.01	0.65
1900	CA1011	13	<4	<1	19	60	0.6	36	24	3.6	0.7	11	1.6	31	1.6	4.8	<20	3.00	0.54
1901	CA1012	15	5	2	22	68	0.7	37	18	3.7	0.5	12	2.4	32	5.6	5.5	<20	3.38	0.58
1902	CA1013	<5	<4	<1	25	58	0.7	33	17	3.5	0.5	11	2.0	32	3.6	5.7	<20	3.32	0.40
1903	CA1014	9	6	<1	22	75	0.9	42	30	4.4	0.7	17	2.2	33	6.0	6.4	<20	3.10	0.56
1904	CA1015	9	6	3	25	86	1.4	48	40	5.4	0.6	20	2.8	38	1.6	7.1	<20	3.82	0.60
1905	CA1016	13	<4	<1	15	70	1.0	41	32	4.6	0.8	13	2.0	30	6.0	5.1	<20	2.91	0.46
1906	CA1017	9	<4	<1	18	81	1.0	43	28	4.7	0.9	19	2.6	30	7.0	5.8	<20	3.46	0.62
1907	CA1018	8	<4	<1	21	63	0.8	39	10	4.1	0.1	19	2.5	30	4.6	5.7	<20	4.02	0.54
1908	CA1019	16	<4	1	33	90	0.3	34	20	4.2	0.9	23	2.4	37	6.0	6.3	<20	4.38	0.63
1909	CA1020	29	26	2	21	46	0.3	21	9	1.4	<0.5	19	2.0	10	3.9	2.2	<20	1.61	0.20
1910	CA1101	22	29	2	21	49	0.4	18	9	1.5	<0.5	24	1.7	12	3.2	2.9	<20	1.97	0.32
1911	CA1102	20	24	1	19	47	0.5	23	9	2.2	<0.5	19	1.8	11	1.7	2.9	<20	2.36	0.39
1912	CA1103	17	15	2	18	55	0.6	30	21	2.8	<0.5	17	<0.5	11	1.7	2.4	<20	2.05	0.29
1913	CA1104	38	26	4	28	67	0.7	29	15	2.6	<0.5	23	2.6	17	2.2	3.2	<20	3.31	0.45
1914	CA1105	25	21	2	28	68	0.7	28	21	3.4	<0.5	23	2.3	24	3.5	3.7	<20	3.64	0.50
1915	CA1106	19	21	<1	27	91	1.9	54	42	8.2	1.9	23	1.8	40	7.2	9.0	<20	5.76	0.65
1916	CA1107	<5	<4	<1	24	58	0.9	37	16	4.0	<0.5	15	2.5	28	6.1	4.9	<20	3.52	0.41
1917	CA1108	11	7	<1	26	120	2.3	79	55	9.9	1.1	22	6.8	49	9.5	9.4	<20	5.14	0.64
1918	CA1109	9	<4	<1	22	76	1.3	46	26	5.1	<0.5	16	1.4	32	4.8	6.2	<20	3.99	0.54
1919	CA1110	11	<4	2	25	85	1.4	51	26	5.7	0.8	25	3.0	35	4.0	6.5	<20	4.90	0.62
1920	CA1111	7	<4	2	21	58	0.8	29	15	3.5	0.8	19	2.2	27	3.5	5.2	<20	4.24	0.49
1921	CA1112	14	<4	1	22	39	0.6	18	8	2.3	0.8	24	2.3	28	3.0	5.1	<20	4.59	0.56
1922	CA1113	8	<4	2	26	36	0.7	19	15	2.5	1.1	22	2.8	32	2.7	5.6	<20	4.76	0.66
1923	CA1114	13	<4	2	26	42	0.8	16	8	2.5	0.8	21	1.6	30	1.6	6.3	<20	4.52	0.57
1924	CA1115	7	9	<1	27	53	0.9	28	19	3.6	0.8	22	1.9	35	6.3	5.8	<20	4.60	0.61
1925	CA1116	12	5	<1	18	75	1.1	47	29	5.0	0.8	19	3.2	31	7.8	5.8	<20	4.04	0.61
1926	CA1117	8	<4	<1	21	86	1.1	48	36	5.3	1.6	20	2.1	31	5.1	5.9	<20	3.58	0.54
1927	CA1118	5	<4	<1	20	79	1.0	46	25	5.1	<0.5	15	<0.5	31	3.2	5.5	<20	3.69	0.54
1929	CA1119	10	<4	2	18	90	1.4	58	46	7.1	0.8	18	3.2	37	4.6	6.3	<20	4.79	0.61
1929	CA1120	14	<4	2	20	75	1.0	45	34	4.8	0.5	17	2.6	32	1.7	5.5	<20	3.69	0.56
1930	CA1201	26	12	2	21	110	0.7	23	18	3.0	<0.5	26	2.5	23	1.6	4.3	<20	3.37	0.55
1931	CA1202	10	<4	2	22	200	0.6	22	9	2.8	1.1	31	2.4	30	4.9	6.1	<20	4.52	0.69
1932	CA1203	9	<4	2	21	126	0.9	27	13	3.6	0.7	27	2.8	31	1.9	5.4	<20	4.31	0.64
1933	CA1204	11	<4	2	24	99	1.3	47	27	5.7	0.9	25	2.1	36	6.3	6.6	<20	4.50	0.61
1934	CA1205	10	12	1	27	60	1.0	26	14	3.3	0.9	27	3.3	35	2.1	6.2	<20	4.66	0.50
1935	CA1206	14	<4	2	27	52	0.9	29	15	3.2	<0.5	23	3.1	31	4.7	4.6	<20	3.75	0.45
1936	CA1207	17	<4	2	26	68	1.1	30	27	4.1	<0.5	23	2.6	35	6.9	5.3	<20	3.61	0.60
1937	CA1208	11	<4	<1	20	70	1.2	42	28	4.7	<0.5	14	1.8	27	4.7	5.1	<20	3.44	0.48
1938	CA1209	12	4	2	18	98	1.0	31	24	4.2	<0.5	24	3.4	26	3.9	5.5	<20	3.77	0.67
1939	CA1210	10	<4	2	21	79	0.7	16	9	2.5	0.7	27	2.0	32	4.2	5.7	<20	4.57	0.63
1940	CA1211	5	<4	2	19	48	0.6	13	8	1.7	0.8	20	2.8	27	1.6	4.0	<20	4.35	0.56
1941	CA1212	11	<4	<1	25	43	0.7	16	10	2.8	1.2	30	3.9	28	3.4	5.5	<20	4.53	0.66
1942	CA1213	7	<4	<1	19	65	1.0	41	34	4.4	0.8	17	2.3	31	6.0	5.6	<20	4.42	0.62
1943	CA1214	12	<4	2	23	71	0.9	44	24	4.8	0.6	17	2.0	33	5.1	6.4	<20	4.13	0.59
1944	CA1215	10	<4	1	19	70	1.0	43	31	4.8	0.5	17	2.0	31	3.9	5.7	<20	3.91	0.45
1945	CA1216	10	<4	1	21	96	1.3	56	29	6.2	0.7	20	2.3	36	6.1	6.8	<20	4.47	0.55
1946	CA1301	27	14	4	24	73	0.3	24	7	2.6	<0.5	24	<0.5	21	4.7	3.8	<20	3.25	0.40
1947	CA1302	14	<4	<1	22	120	1.0	36	28	4.2	1.2	25	2.9	29	5.5	5.7	<20	4.23	0.57
1948	CA1303	13	<4	<1	23	110	0.6	17	13	2.3	0.7	26	3.5	32	4.9	5.3	<20	4.19	0.60
1949	CA1304	17	7	<1	22	73	0.7	17	7	2.3	0.7	28	2.9	20	6.4	5.7	<20	4.19	0.60
1950	CA1305	32	<4	<1	20	38	0.7	14	14	2.1	1.6	27	2.8	29	2.0	5.2	<20	3.97	0.61
1951	CA1306	11	<4	2	26	57	0.9	24	18	3.3	0.9	25	2.9	32	4.4	5.7	<20	4.51	0.67
1952	CA1307	6	10	1	25	54	0.7	29	18	3.3	<0.5	18	1.9	30	3.2	4.5	<20	3.74	0.50
1953	CA1308	7	7	2	24	74	1.0	36	21	4.0	<0.5	19	<0.5	30	4.3	4.9	<20	3.51	0.50
1954	CA1309	19	<4	<1	23	75	1.4	56	43	6.1	<0.5	14	1.9	32	4.8	6.0	<20	3.63	0.50
1955	CA1310	17	&lt																

附表4 土壤地化学試料分析値一覽表

(21)

NO	SP.No.	Sn	W	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
1976	CA1504	8	<4	2	26	140	0.7	20	18	3.0	0.7	24	2.7	38	3.6	6.6	<20	4.09	0.58
1977	CA1505	7	6	1	30	93	0.6	16	9	3.0	0.7	24	2.2	40	4.6	6.5	<20	4.56	0.65
1978	CA1506	6	6	2	28	59	0.8	23	13	3.6	0.7	22	2.6	36	6.2	6.1	<20	4.45	0.57
1979	CA1507	11	<4	<1	28	72	1.1	36	33	4.7	0.5	28	3.2	33	2.5	6.0	<20	3.90	0.61
1980	CA1508	7	<4	<1	20	45	0.7	22	11	2.0	<0.5	16	2.4	26	4.6	4.8	<20	3.66	0.53
1981	CA1509	8	<4	1	22	43	0.7	21	15	2.7	0.5	19	2.1	30	4.3	5.1	<20	3.48	0.51
1982	CA1510	11	<4	<1	23	35	0.6	14	6	2.0	0.9	25	1.8	35	2.8	6.2	<20	4.10	0.53
1983	CA1511	9	<4	<1	21	74	0.7	25	13	3.3	<0.5	24	2.3	32	4.0	5.2	<20	3.86	0.56
1984	CA1512	8	<4	2	24	55	0.3	18	13	2.7	<0.5	27	<0.5	33	1.3	5.0	<20	3.62	0.52
1985	CA1513	<5	<4	2	20	63	0.6	24	18	3.4	<0.5	19	1.9	29	2.3	5.3	<20	3.71	0.57
1986	CA1514	10	<4	2	24	86	0.9	27	26	4.2	<0.5	30	<0.5	37	2.9	7.0	<20	3.78	0.62
1987	CA1601	8	12	<1	19	74	0.9	35	27	4.7	<0.5	19	1.9	28	6.2	4.9	<20	3.13	0.50
1988	CA1602	7	8	2	21	67	0.9	32	22	4.8	<0.5	16	<0.5	31	7.4	5.1	<20	2.98	0.54
1989	CA1603	11	9	<1	21	72	1.0	30	15	4.6	<0.5	17	2.3	31	7.7	5.4	<20	3.27	0.53
1990	CA1604	5	7	<1	21	72	1.0	24	10	3.6	<0.5	19	1.8	31	4.3	5.5	<20	3.87	0.51
1991	CA1605	7	7	<1	22	77	0.7	23	25	3.6	<0.5	17	3.0	33	2.9	5.7	<20	3.68	0.51
1992	CA1606	9	5	1	19	86	1.4	37	35	7.3	<0.5	13	1.6	33	5.5	7.9	<20	3.48	0.52
1993	CA1607	25	<4	<1	26	78	0.6	29	15	2.9	<0.5	22	2.6	32	3.7	5.7	<20	3.90	0.57
1994	CA1608	7	<4	1	28	42	0.5	21	12	2.7	0.9	15	2.3	35	1.9	6.5	<20	4.00	0.54
1995	CA1609	<5	<4	<1	21	68	0.7	19	15	2.9	0.5	24	2.4	28	1.3	5.9	<20	3.54	0.53
1996	CA1610	6	<4	2	21	43	0.6	16	10	2.3	<0.5	23	2.9	31	3.8	5.6	<20	2.79	0.50
1997	CA1611	6	6	2	20	94	1.1	36	22	4.1	<0.5	23	2.1	29	6.0	5.7	<20	3.71	0.53
1998	CA1612	13	<4	2	24	110	0.9	29	22	4.1	1.2	26	2.9	33	2.1	6.3	<20	3.91	0.53
1999	CA1613	9	9	<1	24	120	1.2	50	43	6.4	1.1	28	3.2	38	5.9	6.3	<20	3.63	0.50
2000	CA1614	10	7	2	26	110	0.9	35	28	4.7	0.5	31	2.9	40	3.1	7.2	<20	3.81	0.53
2001	CA1701	13	7	2	25	84	1.4	42	31	6.1	0.5	21	1.6	37	7.0	7.5	<20	3.81	0.49
2002	CA1702	11	<4	2	23	92	0.7	15	10	2.7	<0.5	23	1.4	34	3.2	6.2	<20	4.04	0.51
2003	CA1703	8	8	2	25	61	0.6	15	13	2.6	0.5	21	2.3	33	2.3	5.7	<20	3.73	0.58
2004	CA1704	9	<4	1	23	62	0.7	19	14	3.0	<0.5	21	2.4	31	3.8	5.4	<20	3.58	0.51
2005	CA1705	11	6	<1	23	89	0.8	27	16	3.6	<0.5	21	2.3	27	2.8	5.6	<20	3.64	0.53
2006	CA1706	6	<4	2	22	93	0.7	22	23	3.0	0.7	24	1.9	33	2.9	5.7	<20	4.09	0.55
2007	CA1707	10	<4	<1	24	84	0.8	19	9	2.8	0.6	26	2.6	31	3.4	6.8	<20	4.03	0.63
2008	CA1708	8	5	<1	21	62	0.6	16	13	2.4	<0.5	23	1.9	30	4.7	5.9	<20	3.37	0.54
2009	CA1709	8	<4	2	22	75	0.7	22	23	3.3	<0.5	23	2.3	29	6.0	5.8	<20	3.81	0.53
2010	CA1710	7	<4	<1	20	75	0.6	14	9	2.3	0.8	27	2.1	28	2.6	5.2	<20	4.00	0.46
2011	CA1801	<5	6	<1	19	91	1.3	49	31	6.3	<0.5	15	1.2	34	5.9	6.0	<20	2.71	0.44
2012	CA1802	<5	8	<1	19	85	1.3	46	32	5.9	<0.5	17	1.9	34	7.9	7.0	<20	2.79	0.39
2013	CA1803	<5	8	2	16	81	0.9	37	22	4.9	<0.5	15	2.6	30	7.0	5.6	<20	3.25	0.49
2014	CA1804	7	7	<1	20	61	1.0	34	22	4.5	<0.5	19	1.4	34	4.9	5.7	<20	3.33	0.53
2015	CA1805	<5	6	2	18	58	0.7	32	22	4.1	<0.5	20	1.5	30	3.6	6.6	<20	3.22	0.47
2016	CA1806	8	<4	<1	22	83	1.1	50	36	5.4	<0.5	18	3.0	34	4.5	6.6	<20	3.78	0.45
2017	CA1807	8	<4	<1	28	59	0.5	12	7	1.9	0.9	23	2.5	32	3.8	7.7	<20	4.26	0.54
2018	CA1808	7	<4	2	22	95	0.5	17	9	2.8	1.4	25	2.7	31	4.6	6.0	<20	3.91	0.56
2019	CA1809	9	<4	1	21	79	0.7	19	15	2.9	0.7	21	2.1	28	2.2	5.2	<20	3.42	0.46
2020	CA1810	10	<4	<1	20	38	0.4	15	12	1.8	<0.5	20	1.6	24	4.5	5.4	<20	3.21	0.43
2021	CA1901	<5	10	<1	18	90	1.4	51	31	6.5	1.1	19	1.5	34	5.2	7.0	<20	3.46	0.45
2022	CA1902	<5	7	<1	20	74	1.0	39	31	4.8	<0.5	16	2.5	32	5.6	5.4	<20	2.77	0.40
2023	CA1903	9	7	<1	18	79	1.2	41	24	5.3	<0.5	18	2.4	32	5.3	6.2	<20	3.73	0.42
2024	CA1904	18	5	2	19	68	0.9	31	19	4.3	<0.5	18	2.1	30	4.7	6.4	<20	3.17	0.46
2025	CA1905	<5	5	1	21	39	0.8	18	11	2.8	<0.5	19	2.0	31	4.2	5.6	<20	3.51	0.53
2026	CA1906	<5	<4	1	20	54	0.3	19	10	2.9	<0.5	20	1.9	32	3.8	5.2	<20	3.48	0.57
2027	CA1907	7	<4	<1	25	80	1.1	40	31	5.3	<0.5	20	2.5	36	8.4	7.3	<20	3.88	0.52
2028	CA1908	10	<4	<1	20	85	0.6	27	12	3.7	<0.5	23	2.3	30	4.8	4.9	<20	3.42	0.58
2029	CA1909	11	<4	2	21	100	0.3	20	16	2.8	<0.5	25	3.4	28	2.5	5.2	<20	3.52	0.46
2030	CA1910	9	<4	2	23	88	0.8	21	15	3.3	1.0	24	2.0	31	4.7	5.7	<20	3.30	0.57
2031	CA2001	8	7	2	18	87	1.2	49	33	6.2	<0.5	18	1.5	32	8.5	6.3	<20	3.03	0.41
2032	CA2002	14	<4	1	18	78	1.0	43	35	5.4	<0.5	15	1.2	30	6.6	5.7	<20	2.99	0.41
2033	CA2003	13	9	<1	19	76	1.0	42	39	5.5	<0.5	19	1.4	33	7.0	6.8	<20	6.43	0.45
2034	CA2004	11	6	1	19	68	0.9	31	22	4.1	<0.5	16	2.0	31	5.9	6.1	<20	3.26	0.46
2035	CA2005	9	<4	1	21	47	0.5	13	11	2.2	<0.5	19	1.4	31	6.3	6.8	<20	3.68	0.53
2036	CA2006	6	<4	2	22	48	0.6	14	11	2.1	<0.5	22	2.2	30	2.5	5.7	<20	3.62	0.42
2037	CA2007	9	<4	1	24	57	0.8	27	22	3.8	<0.5	18	2.5	35	5.5	5.9	<20	3.85	0.55
2038	CA2008	7	6	1	20	110	0.9	42	32	4.6	<0.5	21	3.0	33	4.7	5.9	<20	3.92	0.52
2039	CA2009	12	<4	1	20	100	0.7	25	14	3.5	<0.5	20	2.4	31	3.7	5.7	<20	3.14	0.48
2040	CA2101	9	<4	<1	17	120	0.8	25	15	3.9	<0.5	22	2.3	28	0.5	5.3	<20	3.52	0.45
2041	CA2111	26	<4	<1	27	120	1.1	43	32	5.9	<0.5	28	1.5	43	5.2	7.7	<20	4.26	0.66
2042	CA2101	10	6	<1	20	84	1.0	49	38	5.9	<0.5	17	1.9	30	8.2	6.6	<20	3.03	0.41
2043	CA2102	11	<4	<1	20	72	0.9	32	24	4.3	<0.5	17	1.6	29	3.7	5.1	<20	3.63	0.50
2044	CA2103	<5	6	<1	19	63	0.8	25	25	3.4	<0.5	18	2.2	32	2.8	6.2	<20	3.86	0.44
2045	CA2104	8	<4	2	18	80	0.7	23	14	3.2	<0.5	21	2.1	29	5.4	5.7	<20	3.13	0.47
2046	CA2105	6	<4	1	22	82	0.6	20	9	2.4	<0.5	22	2.0	29	1.5	5.7	<20	3.45	0.49
2047	CA2106	<5	<4	<1	25	50	0.4	13	9	1.8	0.9	24	3.1	32	3.8	6.5	<20	4.16	0.49
2048	CA2107	9	<4	2	24	69	0.6	18	14	2.0	0.8	24	3.1	33	4.8	6.4	<20	4.26	0.62
2049	CA2108	7	&																

付表4 土壤地化学試料分析値一覧表

(22)

NO	SP.No.	Sn	W	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Tb	U	Y	Gd	Dy	Pr	Yb	Lu
	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
2070	CA2307	8	<4	2	22	150	1.7	70	52	0.5	0.7	26	3.2	37	7.3	7.7	<20	4.02	0.57
2071	CA2308	12	<4	<1	25	100	1.7	84	58	10.0	0.9	37	<0.5	41	7.5	7.7	<20	5.36	0.70
2072	CA2309	10	<4	<1	30	110	1.4	66	26	6.8	0.9	26	<0.5	39	4.9	6.8	<20	4.56	0.59
2073	CA2310	9	<4	2	26	140	1.3	55	26	7.5	1.0	32	4.0	31	4.9	5.9	<20	4.33	0.64
2074	DA0301	41	<4	6	28	130	1.2	60	59	9.4	0.9	30	0.0	44	5.0	7.0	<20	4.77	0.74
2075	DA0302	28	<4	<1	25	120	1.5	65	47	9.1	1.1	29	7.4	42	6.3	6.8	<20	4.69	0.66
2076	DA0303	17	<4	<1	26	100	1.4	54	40	8.0	1.1	25	7.3	43	5.7	6.8	<20	4.41	0.76
2077	DA0304	35	16	6	25	110	1.1	61	29	8.4	0.7	29	7.5	43	3.1	6.6	<20	4.31	0.62
2078	DA0305	24	11	4	25	120	1.5	57	46	8.4	0.7	27	6.4	44	7.5	7.4	<20	4.21	0.64
2079	DA0306	23	<4	<1	25	110	1.7	62	48	8.8	2.6	29	7.0	42	6.5	6.5	<20	4.65	0.55
2080	DA0307	27	11	4	25	110	1.5	58	45	8.6	0.9	28	6.8	40	5.1	6.6	<20	4.64	0.59
2081	DA0308	37	<4	5	24	100	1.3	53	35	7.7	0.9	28	6.1	42	4.4	7.7	<20	4.37	0.52
2082	DA0309	21	<4	<1	22	100	1.2	49	42	7.4	0.6	25	6.9	38	7.3	6.3	<20	3.60	0.56
2083	DA0401	22	<4	<1	23	82	1.2	50	39	6.0	<0.5	30	5.9	31	4.7	5.6	<20	3.36	0.49
2084	DA0402	17	<4	<1	25	85	1.0	53	30	6.4	0.7	27	5.8	34	4.0	4.5	<20	4.12	0.60
2085	DA0403	36	15	5	27	140	1.5	70	57	9.9	1.0	33	7.9	45	7.1	7.2	<20	5.21	0.77
2086	DA0404	18	<4	4	25	92	1.0	54	48	6.6	0.6	30	8.3	36	4.2	5.7	<20	3.95	0.46
2087	DA0405	20	<4	<1	25	100	1.3	57	40	8.8	0.8	30	8.7	39	5.5	7.2	<20	4.18	0.68
2088	DA0406	33	<4	<1	28	120	1.6	59	61	8.4	<0.5	28	7.0	45	7.8	7.7	<20	3.78	0.70
2089	DA0407	32	<4	4	28	100	1.3	55	43	7.7	0.9	25	5.6	42	4.8	7.5	<20	4.22	0.53
2090	DA0408	24	<4	2	24	78	1.0	46	34	6.2	<0.5	27	7.4	37	3.9	5.7	<20	3.33	0.45
2091	DA0409	30	<4	4	27	120	1.6	59	31	8.6	0.9	31	6.8	42	4.8	7.0	<20	4.51	0.62
2092	DA0410	30	<4	6	29	140	1.9	72	51	10.0	1.1	33	6.6	49	5.6	8.4	<20	5.01	0.63
2093	DA0501	30	9	4	25	120	1.6	65	57	9.1	1.1	29	8.1	44	7.6	8.4	<20	4.58	0.66
2094	DA0502	23	<4	<1	24	120	1.6	56	39	8.4	1.0	30	8.0	48	3.9	6.8	<20	4.39	0.65
2095	DA0503	26	<4	<1	22	90	1.2	51	44	6.9	0.9	27	7.8	34	7.8	5.6	<20	4.24	0.50
2096	DA0504	26	<4	<1	23	100	1.3	54	43	8.2	1.6	27	6.8	41	6.5	6.9	<20	4.69	0.63
2097	DA0505	26	10	<1	22	120	1.6	68	51	9.4	0.9	28	5.6	45	6.4	7.0	<20	5.05	0.70
2098	DA0506	23	<4	3	23	140	1.8	68	52	9.8	1.1	29	7.3	43	6.4	7.3	<20	5.55	0.71
2099	DA0507	32	<4	7	26	130	1.7	68	53	9.6	0.7	28	6.8	41	4.6	7.3	<20	4.38	0.70
2100	DA0508	21	<4	<1	25	140	1.6	64	56	9.5	1.1	30	8.1	41	5.3	6.9	<20	5.22	0.83
2101	DA0509	21	<4	<1	25	120	1.3	61	38	9.1	0.9	30	8.9	43	5.7	7.3	<20	4.71	0.51
2102	DA0510	16	<4	<1	23	120	1.6	58	40	8.2	0.9	26	6.0	41	5.7	6.6	<20	4.41	0.55
2103	DA0511	43	<4	<1	25	110	1.1	59	39	7.2	1.3	30	4.8	46	5.6	8.5	<20	4.39	0.46
2104	DA0512	35	11	4	26	120	1.3	60	44	7.6	0.9	28	7.0	45	5.2	7.6	<20	4.36	0.64
2105	DA0513	24	<4	2	24	98	1.2	50	33	6.8	0.9	29	7.3	38	6.8	5.8	<20	4.07	0.48
2106	DA0601	21	6	<1	26	88	1.0	49	26	5.6	0.7	28	6.7	36	4.7	5.9	<20	3.40	0.50
2107	DA0602	16	5	1	23	84	1.2	47	30	5.8	0.7	25	6.9	39	5.3	5.4	<20	3.72	0.50
2108	DA0603	19	5	3	21	91	1.1	47	32	6.0	0.6	28	7.1	34	5.1	6.0	<20	3.35	0.47
2109	DA0604	29	8	2	24	66	0.9	42	24	4.4	0.8	25	7.1	33	3.8	5.3	<20	3.21	0.41
2110	DA0605	22	7	3	22	73	0.8	42	20	5.0	<0.5	26	6.6	34	5.8	6.3	<20	3.63	0.42
2111	DA0606	36	8	2	26	88	0.9	47	36	5.9	<0.5	31	7.2	36	4.9	6.9	<20	3.42	0.50
2112	DA0607	24	5	<1	26	96	1.2	50	36	6.3	<0.5	27	6.4	41	7.1	6.8	<20	3.79	0.48
2113	DA0608	40	7	5	27	110	1.3	56	39	7.0	<0.5	28	4.7	45	5.7	6.9	<20	3.01	0.52
2114	DA0609	24	7	2	25	100	1.2	51	37	6.5	0.9	30	7.0	40	4.2	7.4	<20	4.14	0.53
2115	DA0610	28	6	2	22	84	1.1	45	22	5.8	<0.5	26	7.5	39	5.6	8.0	<20	3.46	0.47
2116	DA0611	15	<4	2	24	69	0.9	48	33	4.5	<0.5	22	5.0	37	4.9	4.7	<20	3.06	0.42
2117	DA0612	32	7	3	25	99	1.1	51	41	6.4	0.8	24	6.4	43	6.5	6.4	<20	4.09	0.51
2118	DA0613	10	6	3	26	80	0.9	46	28	5.2	<0.5	28	6.7	35	3.7	5.8	<20	3.45	0.45
2119	DA0614	20	6	2	24	82	0.9	43	31	5.2	<0.5	25	6.0	37	4.2	6.1	<20	3.59	0.44
2120	DA0615	31	7	3	24	73	1.0	41	20	5.1	<0.5	26	6.0	33	6.1	5.3	<20	3.19	0.42
2121	DA0701	28	<4	2	26	77	0.9	41	34	5.2	<0.5	25	5.9	38	6.5	6.5	<20	3.05	0.44
2122	DA0702	29	<4	3	25	92	1.1	44	28	5.9	<0.5	30	8.4	37	4.4	6.6	<20	3.54	0.54
2123	DA0703	32	7	3	23	74	1.1	45	30	4.9	<0.5	31	8.2	31	2.9	4.5	<20	3.42	0.42
2124	DA0704	20	9	2	23	99	1.2	51	42	6.6	<0.5	29	9.0	33	4.4	5.2	<20	3.98	0.54
2125	DA0705	23	7	2	26	93	1.1	51	40	6.2	0.9	29	7.7	36	4.1	6.3	<20	4.03	0.46
2126	DA0706	25	7	2	24	83	0.9	46	35	5.6	0.9	27	7.5	38	5.6	5.9	<20	3.23	0.49
2127	DA0707	41	10	3	27	110	1.3	56	36	7.1	<0.5	29	6.3	46	6.1	6.9	<20	4.01	0.51
2128	DA0708	7	7	2	25	79	0.9	44	30	5.3	0.5	26	7.5	35	3.9	5.6	<20	3.36	0.48
2129	DA0709	30	7	3	22	88	1.2	47	44	6.4	0.5	31	8.5	37	3.7	6.5	<20	3.82	0.58
2130	DA0710	25	6	<1	22	79	0.9	50	27	5.3	0.5	31	6.1	35	3.0	4.9	<20	3.75	0.55
2131	DA0711	16	9	2	26	85	1.1	52	35	6.0	0.5	31	6.3	38	3.3	6.0	<20	3.86	0.48
2132	DA0712	30	7	<1	23	97	1.3	53	41	6.1	0.5	31	7.3	39	4.4	6.5	<20	4.19	0.55
2133	DA0713	26	7	4	22	87	1.2	47	31	5.7	0.5	27	5.8	36	7.6	5.7	<20	3.63	0.50
2134	DA0714	29	8	<1	22	95	1.0	50	39	6.0	0.5	26	7.7	40	5.1	6.7	<20	3.58	0.46
2135	DA0715	29	10	4	24	90	1.1	49	42	5.8	1.1	26	7.6	39	5.0	7.1	<20	3.56	0.46
2136	DA0716	23	9	3	43	82	0.6	42	28	4.3	0.6	23	5.4	41	4.0	6.0	<20	3.97	0.59
2137	DA0717	42	8	5	44	140	0.6	54	37	5.9	<0.5	40	6.5	34	6.4	6.4	<20	2.97	0.45
2138	DA0718	25	<4	<1	25	150	1.9	120	94	13.0	1.8	45	9.9	39	11.5	10.5	<20	3.32	0.44
2139	DA0719	60	13	4	41	230	1.9	110	81	12.0	1.7	41	11.0	33	12.5	9.9	<20	2.84	0.49
2140	DA0801	22	6	<1	22	74	0.9	45	34	4.7	0.7	28	5.5	35	4.7	5.6	<20	3.08	0.49
2141	DA0802	25	7	3	24	70	0.9	40	34	4.5	<0.5	26	6.5	36	5.0	5.6	<20	3.28	0.48
2142	DA0803	20	6	3	23	66	0.6	38	29	4.2	<0.5	25	8.0	33	4.8	5.7	<20	3.06	0.36
2143	DA0804	28	8	<1	25														

附表4 土壤地化学試料分析値一覽表

(23)

NO	SP.No.	Sn	H	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Lu
	unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
2164	DA0903	18	7	2	23	94	1.0	48	32	5.7	1.1	27	7.6	40	3.2	7.3	<20	3.51	0.55
2165	DA0904	26	7	<1	19	89	1.0	50	20	5.7	2.0	24	5.8	39	5.9	7.4	<20	3.27	0.49
2166	DA0905	20	10	3	24	93	1.1	50	28	5.7	<0.5	26	8.0	41	4.4	5.9	<20	3.46	0.44
2167	DA0906	25	<4	3	23	90	1.2	50	41	5.7	1.4	27	7.9	39	5.9	7.0	<20	3.59	0.50
2168	DA0907	21	6	2	23	68	0.8	42	32	4.0	<0.5	29	6.7	35	3.3	5.5	<20	3.16	0.51
2169	DA0908	21	<4	3	25	92	1.0	50	34	5.7	<0.5	30	7.3	42	4.8	6.6	<20	3.44	0.58
2170	DA0909	16	10	3	24	100	1.1	56	33	6.3	<0.5	26	6.0	41	6.2	6.6	<20	3.94	0.58
2171	DA0910	12	8	3	33	130	0.9	65	44	7.5	0.9	38	7.8	46	6.7	6.9	<20	4.41	0.66
2172	DA0911	27	8	<1	25	78	0.8	45	31	5.0	0.8	31	5.6	37	5.2	5.3	<20	3.20	0.49
2173	DA0912	25	8	3	26	94	1.0	47	32	5.6	1.3	30	8.0	39	4.8	6.1	<20	3.44	0.53
2174	DA0913	29	8	3	30	96	1.0	53	38	6.2	0.1	32	7.1	42	5.3	5.9	<20	3.34	0.50
2175	DA0914	59	10	7	63	368	0.5	130	92	14.0	0.9	150	8.0	44	12.7	9.9	22	4.40	0.57
2176	DA0915	55	7	6	65	490	0.5	110	76	12.0	1.1	180	6.9	40	6.9	8.8	<20	4.00	0.52
2177	DA0916	55	8	6	62	420	0.5	92	55	9.5	1.0	150	6.7	46	6.6	8.7	<20	4.57	0.62
2178	DA0917	52	8	6	72	350	0.4	120	94	12.0	0.9	150	6.5	52	10.4	10.7	30	4.35	0.61
2179	DA0918	44	13	4	51	310	0.4	120	61	7.9	<0.5	140	5.8	22	6.1	4.6	<20	1.84	0.24
2180	DA0919	37	11	2	34	180	0.5	100	35	4.2	<0.5	50	6.6	16	1.9	3.4	<20	1.02	0.27
2181	DA0920	51	10	5	45	130	0.7	53	39	5.4	<0.5	42	9.6	22	4.8	4.3	<20	2.20	0.31
2182	DA0921	60	11	6	44	120	1.1	85	75	9.1	1.0	42	9.8	28	8.7	6.9	<20	2.36	0.33
2183	DA1006	111	9	3	29	98	1.1	52	40	6.1	<0.5	25	4.6	49	7.3	7.2	<20	3.75	0.51
2184	DA1007	11	<4	2	26	92	1.0	49	36	5.6	0.8	27	6.4	42	6.5	7.2	<20	3.58	0.52
2185	DA1008	15	8	4	26	73	1.0	44	37	4.6	0.1	28	6.2	34	4.6	6.3	<20	3.36	0.62
2186	DA1009	18	5	2	29	79	0.9	46	32	4.8	0.8	29	5.7	38	5.4	5.6	<20	3.43	0.53
2187	DA1010	30	7	3	29	87	1.0	48	26	5.6	<0.5	32	7.2	39	5.9	7.3	<20	3.57	0.55
2188	DA1011	41	12	<1	30	110	1.2	50	42	6.8	0.8	31	7.3	46	6.8	7.0	<20	4.07	0.57
2189	DA1012	33	9	6	78	200	0.6	120	82	12.0	1.7	76	6.0	46	9.5	11.6	<20	5.37	0.86
2190	DA1013	36	10	7	77	230	0.6	130	99	14.0	0.8	84	6.8	49	10.2	12.1	<20	4.04	0.65
2191	DA1014	72	9	6	51	140	0.5	76	56	7.6	1.2	58	5.7	38	6.9	8.6	<20	4.41	0.74
2192	DA1015	44	<4	4	49	310	0.9	160	130	19.0	2.4	100	8.5	81	15.4	12.8	<20	5.11	0.95
2193	DA1016	56	7	3	57	340	0.3	46	42	5.5	<0.5	36	4.8	30	5.1	5.7	<20	3.11	0.46
2194	DA1017	55	16	6	77	440	0.3	110	68	9.0	<0.5	170	6.4	24	6.7	5.1	<20	2.46	0.27
2195	DA1018	50	12	8	80	420	0.3	120	73	9.2	<0.5	160	5.8	26	6.3	5.6	<20	2.74	0.29
2196	DA1019	33	10	3	45	190	0.5	63	33	5.3	<0.5	64	7.3	15	2.8	2.9	<20	1.82	0.31
2197	DA1020	42	8	4	49	180	0.9	64	45	7.0	<0.5	49	11.0	21	4.6	4.4	<20	1.70	0.33
2198	DA1101	35	9	4	26	100	1.2	53	37	6.1	0.5	28	5.5	42	5.6	7.0	<20	3.46	0.51
2199	DA1102	19	8	3	26	110	1.2	59	37	7.3	1.4	28	5.6	42	7.1	7.1	<20	4.34	0.56
2200	DA1103	17	7	3	25	110	1.3	60	44	7.5	0.7	30	7.5	42	3.5	6.4	<20	4.47	0.60
2201	DA1104	31	7	2	27	120	1.4	63	46	7.4	1.8	30	6.1	44	6.3	7.0	<20	3.99	0.58
2202	DA1105	31	8	3	28	120	1.3	63	41	7.7	1.4	31	5.4	40	5.0	6.9	<20	4.10	0.58
2203	DA1106	25	6	2	24	120	1.3	61	42	7.6	<0.5	28	8.2	41	6.9	7.2	32	3.73	0.54
2204	DA1107	20	5	<1	25	110	1.3	57	34	7.0	0.5	32	7.5	37	5.0	6.2	<20	4.34	0.56
2205	DA1108	38	11	3	29	120	1.3	62	41	7.7	2.3	33	7.1	42	5.7	6.7	<20	4.44	0.49
2206	DA1109	33	9	3	28	120	1.4	61	37	7.5	<0.5	32	6.6	41	6.0	6.5	<20	3.76	0.61
2207	DA1110	19	6	2	28	92	0.9	57	32	6.1	0.5	35	7.3	33	4.4	5.1	<20	4.09	0.60
2208	DA1111	20	10	5	52	140	1.0	100	69	12.0	1.5	70	9.3	45	6.9	8.2	<20	5.26	0.77
2209	DA1112	41	7	8	110	490	0.7	240	160	28.0	2.9	160	11.0	83	19.1	17.0	<20	9.92	1.36
2210	DA1113	44	10	12	126	390	0.7	210	130	23.0	2.1	130	7.8	49	15.4	10.6	<20	5.14	0.65
2211	DA1114	43	<4	5	70	360	0.4	95	54	10.0	1.3	170	7.5	32	6.5	6.5	<20	2.73	0.41
2212	DA1115	48	8	7	66	510	0.5	130	69	12.0	<0.5	180	8.0	33	6.2	6.2	<20	3.56	0.35
2213	DA1116	30	8	6	65	230	0.5	90	57	8.8	<0.5	120	8.2	25	4.9	5.0	<20	3.10	0.34
2214	DA1117	41	7	7	73	290	0.6	110	76	12.0	1.1	120	7.9	29	6.5	5.2	<20	3.80	0.48
2215	DA1118	40	7	4	51	300	0.6	97	53	9.2	<0.5	130	6.2	28	4.1	4.5	<20	2.28	0.29
2216	DA1201	11	<4	2	25	80	1.0	49	25	5.0	<0.5	20	6.7	33	4.7	4.6	<20	3.85	0.52
2217	DA1202	16	8	3	25	82	0.9	48	27	5.5	0.6	30	6.3	34	3.7	5.3	<20	4.04	0.53
2218	DA1203	14	<4	<1	24	92	1.1	49	35	5.9	<0.5	27	8.3	34	5.1	6.0	<20	3.89	0.50
2219	DA1204	20	6	2	28	93	1.0	56	32	5.6	<0.5	36	6.4	32	3.8	4.9	<20	3.74	0.57
2220	DA1205	39	8	2	27	120	1.3	63	49	7.9	0.6	32	5.2	42	5.3	6.1	<20	4.63	0.60
2221	DA1206	36	11	3	29	120	1.4	66	41	8.2	0.6	33	6.4	44	7.5	8.4	<20	4.40	0.56
2222	DA1207	28	5	3	27	88	1.0	51	32	5.3	<0.5	32	6.4	34	3.9	5.3	<20	3.83	0.56
2223	DA1208	20	5	2	26	79	1.1	49	31	5.5	0.7	31	8.0	32	4.5	5.0	<20	3.67	0.60
2224	DA1209	32	8	3	26	120	1.3	61	41	7.6	0.8	29	6.0	41	7.3	7.5	<20	4.04	0.54
2225	DA1210	28	6	3	32	110	0.9	64	39	6.5	0.8	41	6.8	34	6.2	6.2	<20	4.19	0.56
2226	DA1211	18	7	3	37	150	1.0	86	59	8.8	0.8	57	7.5	37	5.6	6.2	<20	4.19	0.54
2227	DA1212	28	10	4	54	250	0.9	140	90	15.0	1.0	100	11.0	46	8.5	8.5	<20	4.94	0.64
2228	DA1213	37	6	6	79	330	0.6	130	85	14.0	1.7	100	10.0	33	8.1	7.2	<20	4.19	0.49
2229	DA1214	39	7	6	77	370	0.6	150	110	16.0	2.2	100	8.6	34	8.9	8.6	<20	4.76	0.60
2230	DA1215	41	7	6	64	260	0.5	130	86	13.0	1.0	100	6.7	25	9.9	5.2	<20	2.71	0.31
2231	DA1216	48	6	7	89	290	<0.2	130	70	15.0	1.9	170	6.7	30	5.9	6.6	<20	4.01	0.50
2232	DA1217	37	8	5	68	320	<0.2	130	74	14.0	1.3	170	5.8	24	8.3	5.6	22	2.71	0.38
2233	DA1218	33	9	3	56	190	0.6	85	50	9.0	0.7	83	6.4	26	4.8	5.3	<20	3.15	0.62
2234	DA1219	49	9	5	64	630	<0.2	180	110	21.0	0.8	170	8.9	38	10.9	7.3	<20	4.11	0.69
2235	DA1220	42	7	6	69	290	0.8	110	68	12.0	0.8	110	8.2	28	4.8	5.9	<20	3.37	0.64
2236	DA1304	20	<4	2	24	95	1.2	50	37	6.9	0.7	24	6.3	39	4.9	6.6	<20	3.60	0.72
2237	DA1305	31																	

附表4 土壤地化学試料分析值一覽表

(24)

NO	SP.No. unit	Sn ppm	H ppm	Ta ppm	Nb ppm	Ce ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
2258	DA1400	16	<4	3	25	100	1.1	55	41	7.6	0.7	32	7.1	36	3.0	5.5	<20	4.10	0.75
2259	DA1407	14	8	2	24	110	1.4	57	44	8.3	0.7	29	6.4	39	4.8	6.0	<20	3.71	0.47
2260	DA1408	12	4	2	28	100	1.2	56	40	7.6	0.7	32	7.2	37	5.6	5.8	<20	3.67	0.47
2261	DA1409	18	4	2	30	130	1.1	65	31	8.3	0.8	36	6.8	42	6.0	6.2	<20	4.20	0.52
2262	DA1410	20	4	4	50	210	1.0	120	60	15.0	0.8	67	8.9	47	9.9	9.5	<20	4.02	0.50
2263	DA1411	20	4	4	50	190	0.9	110	65	13.0	1.2	84	14.0	47	9.0	8.9	<20	5.62	0.69
2264	DA1412	33	10	7	74	220	<0.2	100	79	12.0	1.7	140	9.5	35	6.2	7.2	<20	3.92	0.54
2265	DA1413	36	4	5	70	230	<0.2	120	85	13.0	0.9	200	7.2	30	8.1	6.8	<20	3.38	0.34
2266	DA1414	52	9	4	46	150	0.6	69	56	8.4	0.5	79	8.5	34	5.3	5.8	<20	3.70	0.42
2267	DA1415	47	4	5	66	390	0.6	120	86	14.0	0.5	100	12.0	30	9.9	7.8	<20	3.93	0.61
2268	DA1416	39	6	5	52	370	0.6	86	63	9.0	<0.5	150	9.1	25	5.1	5.2	<20	2.08	0.30
2269	DA1417	43	4	5	66	330	0.8	130	94	17.0	1.0	160	13.0	37	12.1	7.9	<20	3.11	0.33
2270	DA1418	42	6	5	79	200	0.5	93	71	11.0	1.0	160	10.0	33	10.3	6.4	<20	3.16	0.47
2271	DA1419	53	11	6	78	360	0.6	97	79	11.0	0.5	170	12.0	32	7.2	5.9	<20	2.87	0.42
2272	DA1420	41	10	7	74	300	0.7	90	76	12.0	<0.5	190	9.5	25	8.1	5.9	<20	2.21	0.38
2273	DA1506	33	4	3	26	94	1.2	54	31	6.9	0.7	33	9.3	41	6.8	6.7	<20	4.16	0.48
2274	DA1507	7	7	2	26	22	0.3	44	32	5.5	0.9	32	9.7	34	3.4	5.0	<20	4.01	0.47
2275	DA1508	9	6	2	29	94	1.3	51	36	7.0	1.6	33	8.3	41	6.0	6.1	<20	4.13	0.55
2276	DA1509	<5	4	3	37	130	1.0	76	52	9.2	1.2	59	11.0	40	7.5	7.0	<20	5.39	0.74
2277	DA1510	12	10	4	67	210	0.9	130	84	15.0	1.5	100	12.0	44	10.3	10.5	<20	5.41	0.71
2278	DA1511	16	4	4	59	140	0.5	86	56	9.2	1.9	140	7.5	23	4.5	5.3	<20	3.12	0.42
2279	DA1512	40	8	5	60	290	0.6	79	62	8.4	1.2	180	7.5	30	6.3	6.7	<20	3.51	0.57
2280	DA1513	39	4	6	72	240	0.5	110	79	12.0	1.6	150	10.0	41	7.3	7.3	<20	4.29	0.49
2281	DA1514	41	10	7	78	310	0.7	130	96	15.0	2.2	160	16.0	42	9.5	7.0	<20	3.44	0.53
2282	DA1515	43	4	6	72	290	0.6	130	85	15.0	1.0	190	13.0	38	8.1	8.1	<20	3.60	0.43
2283	DA1516	44	4	6	80	400	0.8	190	110	21.0	1.1	210	13.0	42	14.8	8.5	<20	4.49	0.41
2284	DA1517	47	11	5	71	370	0.7	140	100	17.0	1.5	180	13.0	34	9.5	7.5	<20	3.06	0.42
2285	DA1518	44	7	5	64	300	0.8	140	100	16.0	1.0	180	14.0	34	10.2	6.8	<20	3.00	0.36
2286	DA1519	51	4	7	74	310	1.0	140	110	17.0	0.9	170	11.0	41	10.1	6.0	<20	3.95	0.40
2287	DA1520	45	11	8	77	330	0.9	120	95	15.0	0.8	160	9.1	40	8.4	6.8	<20	3.96	0.52
2288	DA1521	42	8	6	62	280	0.9	120	84	16.0	2.4	150	13.0	43	8.8	7.8	<20	3.91	0.43
2289	DA1522	42	4	5	59	300	0.8	99	66	13.0	1.5	170	11.0	39	8.8	7.4	<20	3.00	0.46
2290	DA1606	<5	8	3	26	22	1.1	50	28	6.3	0.8	35	11.0	34	5.5	5.5	<20	4.30	0.49
2291	DA1607	8	4	2	26	84	1.0	48	37	6.1	0.8	35	7.4	37	6.6	6.2	24	4.24	0.59
2292	DA1608	7	13	<1	28	110	1.6	56	42	7.3	0.8	35	8.4	45	7.3	6.5	<20	4.46	0.56
2293	DA1609	26	4	4	36	110	0.8	60	49	7.2	1.5	47	10.0	39	7.4	6.2	<20	4.21	0.50
2294	DA1610	11	9	7	75	230	0.9	130	90	15.0	1.9	97	9.9	45	10.7	8.0	<20	5.09	0.74
2295	DA1611	37	4	4	66	250	0.9	130	93	15.0	1.2	140	19.0	47	10.4	9.2	26	5.02	0.59
2296	DA1612	20	4	3	54	130	0.9	76	44	8.2	<0.5	140	6.4	22	5.8	5.4	<20	2.21	0.27
2297	DA1613	36	4	5	51	280	0.6	92	62	8.3	<0.5	220	6.1	20	6.3	4.6	<20	1.88	0.22
2298	DA1614	37	4	5	68	350	0.7	170	110	19.0	1.8	260	9.6	32	10.7	8.2	<20	2.02	0.40
2299	DA1615	39	9	6	69	360	0.6	160	120	18.0	2.8	230	12.0	46	12.6	9.5	<20	5.23	0.68
2300	DA1616	34	4	6	70	360	0.6	150	85	18.0	2.5	220	9.2	62	10.8	12.4	<20	9.72	1.04
2301	DA1617	40	4	6	76	310	0.7	140	100	17.0	2.2	160	15.0	46	11.6	9.9	<20	4.50	0.47
2302	DA1618	39	4	4	61	360	1.0	170	130	20.0	2.3	190	12.0	41	10.5	8.0	<20	3.50	0.45
2303	DA1619	40	4	6	64	330	1.0	170	120	21.0	0.9	170	14.0	50	14.7	9.2	<20	3.98	0.50
2304	DA1620	43	4	4	63	340	0.8	130	93	14.0	1.8	180	9.8	35	8.7	7.1	<20	2.86	0.36
2305	DA1621	46	9	5	63	330	0.5	110	75	13.0	1.6	180	11.0	34	7.0	5.5	<20	2.63	0.32
2306	DA1622	42	8	6	69	340	0.8	86	71	11.0	<0.5	170	8.6	36	7.5	5.7	<20	2.49	0.37
2307	DA1703	<5	4	3	25	98	1.0	59	31	7.3	0.7	43	11.0	36	4.8	7.1	<20	4.16	0.50
2308	DA1704	6	4	3	27	110	1.5	58	37	7.7	0.9	39	8.5	42	7.1	7.2	<20	4.59	0.64
2309	DA1705	<5	6	2	26	75	1.1	47	28	5.5	0.9	34	9.6	36	5.0	5.7	<20	4.14	0.51
2310	DA1706	41	7	2	26	90	0.8	58	42	7.1	0.9	43	9.6	37	3.6	6.6	<20	4.35	0.58
2311	DA1707	20	4	4	27	90	1.3	57	35	7.2	0.7	33	7.5	43	7.1	6.6	<20	4.52	0.65
2312	DA1708	36	4	4	52	310	0.6	96	70	12.0	1.6	160	11.0	30	5.4	7.1	<20	2.05	0.24
2313	DA1709	20	6	3	26	78	1.1	46	29	5.2	0.5	33	7.2	34	7.2	5.4	<20	3.76	0.56
2314	DA1710	20	4	3	29	110	1.3	63	42	7.7	1.4	42	9.9	39	4.7	7.4	<20	5.06	0.61
2315	DA1711	34	7	5	72	200	0.8	100	78	12.0	0.7	130	11.0	38	6.1	6.6	<20	4.19	0.48
2316	DA1712	43	10	5	76	310	1.0	160	100	18.0	0.7	160	17.0	52	8.0	10.6	<20	4.25	0.56
2317	DA1713	43	4	7	70	310	0.8	140	90	16.0	1.0	180	13.0	42	10.3	7.3	<20	3.24	0.37
2318	DA1714	8	7	4	58	190	0.6	71	50	8.9	1.0	140	10.0	31	10.0	10.0	<20	4.39	0.52
2319	DA1715	20	4	4	59	240	0.5	84	56	11.0	1.9	140	9.7	43	5.5	6.9	<20	5.50	0.68
2320	DA1716	35	4	5	72	270	0.7	120	91	15.0	1.6	140	12.0	50	8.8	8.6	<20	4.72	0.56
2321	DA1717	39	9	6	72	330	0.7	130	90	14.0	<0.5	210	11.0	39	10.6	9.8	<20	3.94	0.43
2322	DA1718	40	4	6	65	420	0.7	150	110	16.0	<0.5	220	11.0	34	9.3	9.1	<20	2.81	0.37
2323	DA1719	37	4	3	66	420	0.9	190	140	21.0	<0.5	220	12.0	40	9.1	7.8	<20	3.34	0.39
2324	DA1720	41	4	6	70	380	0.9	150	120	19.0	<0.5	190	12.0	47	9.9	8.9	<20	4.24	0.47
2325	DA1721	33	4	5	68	340	0.9	160	100	18.0	1.8	200	14.0	47	10.8	8.5	<20	3.86	0.47
2326	DA1722	46	8	6	68	310	0.7	83	58	9.5	<0.5	150	8.5	29	9.4	9.3	<20	2.99	0.41
2327	DA1802	<5	4	4	20	100	1.4	53	36	8.8	1.2	33	8.2	45	6.7	7.6	<20	4.46	0.59
2328	DA1803	<5	8	2	28	120	1.3	69	41	8.1	1.1	49	8.7	39	5.6	8.2	<20	4.11	0.57
2329	DA1804	6	8	3	28	99	1.1	67	39	6.9	1.0	37	10.0	38	5.1	7.2	<20	3.92	0.51
2330	DA1805	9	4	4	29	160	1.3	87	58	10.0	1.2	60	11.0	41	9.8	8.6	<20	4.79	0.61
2331	DA1806	15	4	2	25	83	1.												

付表4 土壤地化学試料分析値一覽表

(25)

NO	SP.No.	Sn	W	Ta	Nb	Co	Eu	La	Nd	Sm	Tb	Th	U	Y	Gd	Dy	Pr	Yb	Tu
	Unit	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
2352	DA1906	16	<4	2	27	130	0.5	72	48	9.1	1.0	47	11.0	42	7.4	8.4	<20	5.76	0.69
2353	DA1907	18	<4	<1	20	170	1.0	100	57	9.9	1.6	67	12.0	36	8.4	8.8	<20	4.05	0.53
2354	DA1909	23	13	<1	35	230	0.8	140	93	13.0	1.8	130	9.8	27	6.9	7.5	<20	2.51	0.32
2355	DA1909	20	8	4	50	270	0.8	160	110	16.0	1.6	160	20.0	29	11.2	7.7	<20	3.41	0.45
2356	DA1910	20	<4	2	39	220	0.3	120	74	10.0	<0.5	160	11.0	15	8.3	4.7	<20	1.84	0.22
2357	DA1911	21	<4	2	30	260	0.6	120	77	10.0	<0.5	160	12.0	35	10.0	3.9	<20	1.19	0.17
2358	DA1912	20	6	2	42	250	0.4	60	25	5.7	<0.5	160	8.2	15	5.1	3.9	<20	1.39	0.14
2359	DA1913	30	<4	4	45	360	0.7	82	55	9.1	<0.5	140	4.9	24	7.4	5.2	<20	2.50	0.22
2360	DA1914	39	4	3	57	370	0.3	120	67	14.0	0.7	160	7.8	32	9.2	8.0	<20	3.10	0.38
2361	DA1915	20	<4	<1	35	280	0.3	120	84	14.0	1.3	130	4.5	27	6.6	7.0	<20	2.40	0.27
2362	DA1916	36	6	4	45	310	0.3	82	31	9.5	0.5	120	5.0	27	6.4	6.2	<20	2.45	0.21
2363	DA1917	47	<4	5	64	360	0.9	160	100	18.0	0.6	170	8.3	38	11.9	9.4	<20	3.33	0.34
2364	DA1919	50	<4	4	64	320	0.9	180	120	21.0	0.8	150	10.0	47	15.7	11.0	<20	3.97	0.38
2365	DA1919	50	<4	6	67	360	0.8	190	120	23.0	2.3	160	12.0	47	14.7	11.0	54	3.66	0.35
2366	DA1920	53	<4	6	72	420	0.3	190	110	21.0	0.7	190	8.1	40	13.7	10.2	45	3.12	0.30
2367	DA2001	<5	10	3	29	120	1.3	63	44	7.9	1.0	31	6.5	43	7.8	8.2	<20	4.48	0.57
2368	DA2002	8	<4	4	63	420	0.3	120	61	13.0	0.8	180	16.0	24	8.7	6.1	<20	3.06	0.30
2369	DA2003	12	<4	<1	31	200	0.8	120	67	12.0	1.1	74	7.4	42	10.2	8.9	<20	4.94	0.75
2370	DA2004	16	<4	<1	31	150	0.8	89	57	10.0	1.1	57	9.5	45	6.0	8.9	28	4.83	0.64
2371	DA2005	33	<4	3	63	210	0.9	120	71	13.0	1.1	110	13.0	48	11.9	9.9	<20	3.91	0.56
2372	DA2006	13	<4	4	26	130	1.2	73	44	7.3	1.6	77	6.4	29	4.5	6.1	<20	2.50	0.34
2373	DA2007	11	7	3	37	200	<0.2	110	60	9.1	<0.5	96	7.8	24	4.0	6.9	<20	2.86	0.38
2374	DA2009	9	<4	4	51	160	0.7	100	58	10.0	0.8	110	8.5	27	9.3	6.5	<20	3.73	0.46
2375	DA2009	19	<4	3	47	210	0.6	93	39	9.3	0.5	140	7.9	20	3.8	6.0	<20	2.62	0.30
2376	DA2010	21	<4	2	42	300	0.6	100	48	8.5	0.6	160	9.5	14	2.9	4.5	<20	2.03	0.08
2377	DA2011	19	<4	3	46	500	0.5	85	39	7.5	0.5	190	11.0	16	4.3	5.0	<20	2.18	0.21
2378	DA2012	28	<4	2	55	630	0.4	89	51	8.3	<0.5	170	13.0	16	8.2	5.2	<20	1.94	0.24
2379	DA2013	24	<4	<1	26	87	0.8	51	30	6.3	0.9	38	6.5	39	9.2	7.4	<20	4.24	0.52
2380	DA2014	27	<4	4	65	460	0.7	130	81	15.0	0.7	180	11.0	26	9.4	8.2	<20	3.27	0.44
2381	DA2015	27	<4	5	78	320	0.8	100	62	12.0	0.7	160	11.0	27	8.7	6.6	<20	3.17	0.40
2382	DA2016	41	<4	4	58	290	0.6	98	51	12.0	1.0	150	9.1	37	13.0	7.4	<20	3.16	0.43
2383	DA2017	42	<4	6	69	290	0.3	78	43	9.8	1.4	140	6.0	38	9.2	7.4	<20	3.85	0.46
2384	DA2018	45	<4	6	79	360	0.6	150	95	16.0	1.5	170	10.0	37	11.3	6.7	<20	3.20	0.35
2385	DA2019	51	<4	4	65	460	0.3	200	110	22.0	2.6	180	13.0	52	14.7	11.2	<20	4.11	0.35
2386	DA2020	50	8	5	65	430	1.0	220	130	24.0	1.2	180	13.0	55	14.3	12.9	<20	4.76	0.47
2387	DA2101	29	<4	2	26	130	1.0	78	43	8.3	1.7	48	6.4	32	4.8	6.6	<20	3.86	0.60
2388	DA2102	27	<4	<1	35	180	0.8	100	61	11.0	1.2	69	7.3	36	7.9	7.9	<20	4.18	0.47
2389	DA2103	36	<4	6	62	160	0.3	93	49	11.0	1.0	100	12.0	41	8.3	6.8	<20	3.80	0.51
2390	DA2104	35	<4	4	63	370	0.6	130	80	16.0	1.1	150	14.0	43	11.6	9.9	<20	4.57	0.48
2391	DA2105	35	<4	4	64	290	1.0	120	67	14.0	1.1	130	15.0	41	9.4	7.8	<20	4.39	0.48
2392	DA2106	38	<4	5	62	300	0.9	110	51	14.0	1.8	130	17.0	49	10.0	7.5	<20	4.08	0.44
2393	DA2107	34	<4	5	59	300	1.0	140	82	18.0	1.8	130	14.0	55	13.1	10.7	<20	4.94	0.64
2394	DA2108	47	<4	5	58	350	0.9	120	76	17.0	1.4	140	8.2	47	12.7	10.0	<20	4.92	0.57
2395	DA2109	49	14	4	39	120	1.4	88	58	10.0	1.4	35	5.6	22	9.9	5.5	<20	2.81	0.42
2396	DA2110	<5	6	3	58	450	0.8	98	41	9.2	0.6	180	13.0	21	6.2	5.0	<20	2.36	0.29
2397	DA2111	19	<4	2	44	490	0.9	150	96	17.0	0.5	210	14.0	22	10.3	6.0	<20	2.98	0.36
2398	DA2112	23	<4	4	58	400	0.4	130	74	15.0	1.2	180	15.0	29	12.7	6.7	<20	2.51	0.05
2399	DA2113	19	<4	3	54	410	1.0	160	120	22.0	1.5	170	14.0	43	15.4	10.6	<20	4.70	0.52
2400	DA2114	38	<4	5	53	360	1.3	180	130	25.0	1.5	160	11.0	60	15.9	13.5	<20	5.50	0.60
2401	DA2115	38	5	5	62	280	0.6	120	68	14.0	0.9	130	7.4	48	10.2	9.8	<20	4.82	0.56
2402	DA2116	38	<4	6	59	360	0.4	110	64	13.0	0.9	180	11.0	45	10.0	9.9	<20	4.81	0.57
2403	DA2117	33	<4	6	63	360	0.6	120	78	18.0	2.6	130	2.2	53	11.9	12.8	<20	5.33	0.72
2404	DA2118	33	<4	5	66	340	0.7	130	82	16.0	1.2	140	15.0	41	14.0	9.9	<20	4.78	0.48
2405	DA2201	39	<4	<1	40	180	0.9	100	61	11.0	1.2	70	8.1	35	7.8	6.1	<20	3.71	0.41
2406	DA2202	33	<4	4	74	330	0.8	160	100	20.0	3.0	150	16.0	64	14.1	12.3	<20	5.14	0.53
2407	DA2203	32	<4	5	68	300	1.0	160	93	19.0	2.6	140	16.0	64	16.4	11.2	<20	5.06	0.63
2408	DA2204	66	<4	5	63	240	0.5	90	40	11.0	1.6	120	9.1	41	8.3	7.3	<20	3.48	0.51
2409	DA2205	31	<4	5	59	250	0.8	100	63	13.0	1.8	120	11.0	44	11.6	8.6	<20	3.87	0.52
2410	DA2206	38	7	4	60	280	0.7	110	62	14.0	1.0	110	11.0	44	10.5	9.9	<20	4.07	0.49
2411	DA2207	32	<4	6	62	260	0.8	110	78	15.0	2.2	99	9.7	54	15.5	10.2	<20	4.64	0.56
2412	DA2208	35	<4	6	63	240	0.3	98	59	13.0	1.0	100	9.2	48	8.2	8.4	<20	4.22	0.54
2413	DA2209	34	<4	5	60	310	0.5	110	63	14.0	2.5	120	9.8	50	10.8	10.1	<20	4.68	0.62
2414	DA2210	36	<4	6	66	300	1.0	200	130	26.0	2.5	140	13.0	93	21.1	19.2	<20	7.18	0.80
2415	DA2211	33	<4	6	67	300	0.9	210	140	29.0	3.6	130	12.0	109	24.5	20.7	<20	8.17	0.98
2416	DA2212	35	<4	4	62	260	1.6	210	140	30.0	3.4	110	16.0	121	30.6	23.8	<20	9.01	0.97
2417	DA2213	41	<4	6	67	290	0.7	140	93	20.0	2.1	130	11.0	69	17.0	14.6	<20	5.08	0.66
2418	DA2214	39	<4	6	61	310	0.6	120	75	15.0	2.4	150	12.0	58	12.6	10.5	<20	4.53	0.53
2419	DA2215	39	<4	5	62	330	0.5	130	76	18.0	1.4	160	11.0	58	12.6	11.1	<20	5.51	0.55
2420	DA2301	<5	<4	1	36	400	2.6	310	190	32.0	2.5	160	18.0	69	19.3	15.7	<20	5.39	0.72
2421	DA2302	9	<4	5	51	230	0.7	130	82	13.0	1.2	120	11.0	34	10.4	7.6	<20	3.74	0.48
2422	DA2303	31	<4	6	63	230	0.3	100	57	12.0	1.1	140	11.0	34	9.2	7.8	<20	4.00	0.42
2423	DA2304	20	<4	4	59	220	0.8	91	60	11.									

附表4 土壤地化学試料分析値一覽表

(26)

NO	SP.No. unit	Sn ppm	H ppm	Ta ppm	Nb ppm	Co ppm	Eu ppm	La ppm	Nd ppm	Sm ppm	Tb ppm	Th ppm	U ppm	Y ppm	Gd ppm	Dy ppm	Pr ppm	Yb ppm	Lu ppm
2446	DB0304	25	<4	3	48	200	1.2	120	63	12.0	1.1	45	5.7	36	10.2	7.7	<20	4.02	0.59
2447	DB0305	21	10	3	44	110	0.5	72	31	6.9	0.7	57	4.9	25	8.4	0.5	<20	2.64	0.49
2448	DB0306	22	<4	5	52	160	0.5	78	52	9.5	1.3	93	7.3	32	6.4	5.1	<20	3.46	0.46
2449	DB0401	6	<4	<1	32	300	1.2	73	43	8.7	0.5	68	9.3	22	7.8	4.4	<20	2.39	0.32
2450	DB0402	9	<4	2	36	280	0.9	66	32	6.0	<0.5	72	11.0	15	3.8	2.9	<20	1.63	0.21
2451	DB0403	11	<4	2	41	260	0.9	98	62	10.0	1.1	170	11.0	20	7.1	6.7	<20	2.53	0.26
2452	DB0404	8	<4	2	36	120	0.4	57	19	5.9	1.6	80	10.0	19	5.6	5.3	<20	3.13	0.39
2453	DB0405	20	<4	<1	25	110	1.4	66	40	8.2	0.9	47	9.5	33	10.9	8.1	<20	4.23	0.70
2454	DB0406	39	7	4	39	130	0.8	75	38	8.0	0.9	49	11.0	36	5.4	6.6	<20	3.64	0.49
2455	DB0407	20	<4	5	76	280	0.4	160	110	10.0	2.2	100	9.4	47	16.6	12.1	<20	4.03	0.71
2456	DB0408	20	9	3	52	70	0.3	47	30	4.7	0.0	68	4.1	19	7.0	4.6	<20	2.13	0.27
2457	DB0409	32	7	4	54	100	0.3	91	58	9.4	1.1	150	5.7	21	11.1	6.5	<20	2.41	0.31
2458	DB0501	<5	<4	2	36	170	1.0	72	59	8.3	0.5	85	14.0	21	5.8	6.0	<20	2.62	0.38
2459	DB0502	8	<4	<1	39	230	0.7	82	58	7.2	0.7	110	12.0	24	8.9	6.0	<20	2.20	0.26
2460	DB0503	9	8	4	27	120	1.0	63	44	7.3	1.1	49	7.8	45	8.7	9.9	<20	3.44	0.42
2461	DB0504	16	<6	<1	27	80	0.6	53	36	5.9	1.5	37	8.3	33	7.1	8.0	<20	3.18	0.46
2462	DB0505	22	5	<1	29	90	0.8	58	35	5.2	0.7	29	5.1	41	4.4	7.5	<20	3.89	0.64
2463	DB0506	30	7	4	40	110	0.7	60	49	7.0	1.4	35	6.7	49	7.4	12.1	<20	6.86	0.92
2464	DB0507	20	10	<1	48	190	0.7	110	76	12.0	1.5	68	8.2	56	13.7	12.1	<20	4.83	0.90
2465	DB0508	34	12	<1	47	130	0.8	70	53	8.2	1.6	40	7.3	52	7.4	10.9	<20	5.96	0.98
2466	DB0509	40	8	4	43	110	0.6	56	41	6.1	1.0	42	11.0	33	8.1	6.5	<20	3.07	0.52
2467	DB0510	20	<4	2	37	230	1.0	87	76	10.0	1.1	70	12.0	25	8.4	6.4	<20	2.16	0.37
2468	DB0601	9	<4	<1	21	92	0.9	52	51	6.1	1.2	31	9.5	41	3.3	7.9	<20	4.53	0.79
2469	DB0602	15	6	2	29	80	0.6	52	30	5.4	1.1	39	7.9	38	4.5	8.0	<20	3.60	0.64
2470	DB0603	35	10	3	29	95	1.0	50	28	6.2	1.1	31	6.2	41	7.3	8.1	<20	4.05	0.56
2471	DB0604	20	<4	<1	28	97	1.1	51	33	6.2	1.1	33	8.8	42	10.6	8.7	<20	4.29	0.54
2472	DB0605	34	7	3	27	91	0.9	49	38	6.1	0.9	32	6.4	40	6.3	8.4	<20	3.76	0.56
2473	DB0606	31	8	<1	31	75	0.9	44	27	4.7	0.9	31	6.1	32	2.3	5.5	<20	3.45	0.51
2474	DB0607	37	7	3	32	79	0.9	45	24	4.8	0.6	30	8.1	35	8.1	6.4	<20	3.78	0.58
2475	DB0608	20	11	2	27	53	0.4	29	17	3.1	0.6	16	3.6	23	5.6	4.2	<20	2.56	0.43
2476	DB0609	20	6	1	29	100	0.8	63	32	6.3	1.2	45	9.6	39	10.2	8.5	<20	3.98	0.55
2477	DB0610	38	9	4	45	98	0.7	47	37	5.3	1.0	37	9.0	32	4.2	5.8	<20	3.34	0.52
2478	DB0701	20	10	5	36	99	0.9	50	35	6.4	1.6	37	5.9	47	10.5	11.0	<20	5.11	0.89
2479	DB0702	20	13	5	28	103	1.3	59	38	7.1	0.9	32	7.4	44	8.3	8.6	<20	3.65	0.65
2480	DB0703	35	8	2	27	91	1.1	48	31	5.7	1.1	20	4.4	47	7.3	7.2	<20	3.59	0.54
2481	DB0704	30	6	3	30	71	0.8	43	21	4.4	0.7	20	5.8	34	6.3	6.0	<20	3.32	0.50
2482	DB0705	32	9	3	31	100	0.8	56	48	6.7	0.9	36	6.6	44	6.3	9.0	<20	5.15	0.81
2483	DB0706	20	7	4	40	150	0.6	84	58	8.7	1.3	60	8.6	52	7.8	9.2	<20	5.26	0.74
2484	DB0707	24	9	5	41	91	0.7	45	31	5.0	0.8	27	6.1	39	7.4	6.8	<20	3.92	0.60
2485	DB0708	20	8	3	34	140	0.6	75	61	8.6	1.6	49	7.3	52	8.6	8.4	<20	5.80	0.89
2486	DB0709	38	10	5	42	97	0.9	52	37	6.0	0.6	40	12.0	31	8.3	6.2	<20	2.87	0.47
2487	DB0710	41	9	4	44	110	0.9	54	52	8.3	0.7	35	11.0	36	7.9	7.3	<20	3.19	0.53
2488	DB0802	32	11	<1	29	120	1.1	63	41	7.4	1.9	37	9.8	42	9.9	7.9	<20	3.95	0.61
2489	DB0803	20	6	4	37	83	0.7	56	42	5.7	1.6	30	7.9	37	5.5	6.7	<20	3.09	0.54
2490	DB0804	28	8	3	29	110	0.4	59	50	7.0	0.9	39	8.8	41	8.5	7.4	<20	4.67	0.75
2491	DB0805	20	5	4	35	100	0.8	52	42	6.0	1.2	31	7.7	43	9.0	7.7	<20	4.99	0.87
2492	DB0806	33	6	5	44	85	0.8	48	36	5.1	1.2	23	6.3	44	8.3	8.6	<20	5.27	0.90
2493	DB0807	30	10	4	54	83	0.7	47	38	5.2	0.8	30	5.6	37	6.1	6.4	<20	3.53	0.66
2494	DB0808	39	10	4	40	92	0.8	40	32	5.4	1.2	31	7.5	40	8.0	6.7	<20	4.31	0.63
2495	DB0809	38	11	4	45	100	0.9	50	49	5.6	1.0	35	11.0	33	7.6	6.3	24	3.65	0.55
2496	DB0810	41	11	4	44	95	0.9	49	43	6.0	1.2	34	10.0	36	8.7	6.3	<20	3.75	0.63
2497	DB0811	40	11	4	44	92	1.0	51	26	5.7	1.2	33	8.7	39	11.5	6.8	25	4.05	0.63
2498	DB0801	36	<4	4	25	93	1.4	54	39	6.3	0.9	20	9.0	41	10.8	6.3	<20	3.24	0.48
2499	DB0902	20	4	4	26	100	1.1	55	56	7.0	1.4	36	13.0	46	10.6	7.5	<20	3.78	0.69
2500	DB0903	20	40	<1	43	140	1.1	140	88	12.0	1.4	91	19.0	45	12.5	9.9	<20	4.40	0.58
2501	DB0904	34	8	3	33	140	1.4	83	59	9.5	1.2	60	12.0	60	9.5	9.5	<20	4.74	0.76
2502	DB0905	32	7	3	32	160	1.2	90	75	11.0	1.5	59	9.3	59	14.2	12.8	<20	6.96	1.12
2503	DB0906	31	9	3	33	63	0.7	46	29	5.1	1.1	28	7.5	43	6.2	7.6	<20	5.71	0.79
2504	DB0907	39	8	5	43	74	0.7	45	34	4.7	1.0	32	10.0	30	6.3	6.7	<20	3.58	0.52
2505	DB0908	32	6	5	40	93	1.0	49	42	5.9	1.3	25	10.0	51	5.6	10.2	<20	7.37	1.12
2506	DB0909	40	<4	5	41	97	0.8	52	34	5.9	1.0	35	9.8	33	6.5	6.8	<20	3.12	0.44
2507	DB0910	41	10	6	44	89	0.9	53	34	6.1	1.1	35	11.0	38	9.3	7.3	<20	4.26	0.66
2508	DB0911	58	12	4	51	95	1.0	57	29	6.4	1.1	25	8.5	42	6.6	7.3	<20	4.68	0.71
2509	DB1001	<5	<4	3	45	82	0.8	58	36	5.3	0.7	120	8.5	30	7.4	6.6	<20	3.24	0.46
2510	DB1002	16	<4	4	49	130	0.7	55	19	4.1	<0.5	130	7.9	14	3.7	3.2	<20	1.87	0.29
2511	DB1003	19	<4	4	29	120	0.8	65	75	8.4	1.6	45	11.0	44	8.1	9.0	<20	5.34	0.88
2512	DB1004	30	13	<1	30	94	1.0	50	43	6.0	1.7	31	6.7	50	6.9	8.3	<20	5.37	1.00
2513	DB1005	20	7	4	41	49	0.3	29	19	3.2	1.1	32	4.7	25	5.9	5.1	<20	3.42	0.58
2514	DB1006	45	12	4	43	94	1.2	49	48	6.1	1.1	34	9.5	37	6.4	6.3	<20	3.58	0.55
2515	DB1007	31	<4	<1	25	110	0.9	53	44	6.7	1.2	29	8.0	40	8.2	7.8	<20	4.66	0.72
2516	DB1008	19	6	4	55	200	0.7	57	25	2.0	0.5	190	8.4	10	2.0	2.6	<20	1.73	0.22
2517	DB1009	23	6	5	37	410	1.2	240	180	26.0	1.4	160	14.0	56	24.9	15.3	<20	5.33	0.67
2518	DB1101	44	11	4	33	120	0.8	49	36	6.3	0.7	36	11.0	34	8.1	5.8	<20	3.88	0.77
2519	DB1102	34	10	4	41	56	0.5	38	15	3.2	0.8	35	6.8	25	4.9	5.3	<20	3.78	0.61



付表5 磁石試料分析値一覽表

SP.No.	SK	V	W	TA	NA	CB	BU	LA	RD	SN	TB	TH	U	Y	GD	DY	PR	YB	LU	Tt. 2BE	Tt. 4D	BE, Th and U calculated in MONAZITE SENSITIVE POLYCRYSZ	VOLUME OF SAMPLING	WEIGHT OF SAMPLE	CASITERITE MONAZITE XENOTIME	ORE GRADE	
1	AAH-01	210000	490	3700	4553	5350	-2	2550	2570	500	500	38	2200	240	3300	449	402	348	314	15991.6	2440	16511.77	4300.20	5573.63	761.45	77.02	
2	AAH-02	111000	420	1400	2538	5210	-2	2470	2140	450	450	58	2200	300	3017	475	593	350	463	17331.9	2330	12542.77	5933.63	4035.35	186.47	25.60	
3	AAH-03	7555	380	1100	4384	8320	-2	3470	3170	700	700	20	2700	2500	8395	855	1081	338	530	27345.0	6200	20188.21	10096.55	8780.64	25.95	89.21	
4	AAH-04	8583	290	1300	5024	5870	-2	2730	2020	490	490	20	2700	2600	6538	619	904	245	756	15077.48	5200	15077.48	7884.22	8870.82	29.50	58.82	
5	AAH-05	2745	330	1200	5742	7620	-2	3480	2810	650	650	20	2700	3100	9265	914	1130	345	1030	19167.75	6800	19167.75	10398.85	1867.62	11.70	102.98	
6	AAH-06	525	340	640	3220	1320	-2	6090	4930	830	830	270	3700	1700	1897	1140	1438	445	1280	41543.0	7400	30173.15	13836.53	8639.72	2.62	152.96	
7	AAH-07	421	210	310	2120	1120	-2	5180	4960	830	830	180	4500	960	8239	839	995	582	754	33367.8	5760	29986.57	10228.11	5551.44	0.69	54.24	
8	AAH-08	631	250	390	2018	1030	-2	4740	4610	790	790	190	4500	1100	7351	795	1035	670	963.4	31304.4	4600	29986.57	9494.44	5354.14	0.96	21.20	
9	AAH-09	165	260	450	2205	7030	-2	3060	1990	590	590	130	2400	1500	8213	810	1244	275	686	17565.46	4500	17565.46	10336.11	5609.23	0.33	44.55	
10	AAH-10	722	140	510	2508	6730	-2	2890	4240	820	820	170	3500	390	7384	745	1035	354	774	23135.0	3540	15352.57	8908.99	5177.24	1.45	35.78	
11	AAH-11	7577	120	180	592	11100	-2	1710	1370	280	280	67	1200	180	3247	261	300	170	387	11324.9	1380	7832.62	3714.53	3105.66	6.99	28.37	
12	AAH-12	792	50	75	273	8480	-2	1170	817	180	180	66	1100	640	3368	290	400	106	339	8911.2	1740	6094.43	3734.72	3203.43	0.51	6.47	
13	AAH-13	7856	130	590	1927	2210	-2	1170	817	180	180	66	1100	640	3368	290	400	106	339	8911.2	1740	6094.43	3734.72	3203.43	0.51	6.47	
14	AAH-14	14000	210	850	2510	5930	-2	2570	2470	470	470	22	2600	1100	5982	534	420	282	852	19405.2	3700	14454.70	6695.98	5011.92	32.06	42.61	
15	AAH-15	8163	470	180	597	9360	27	4480	3630	640	640	120	2700	550	6769	610	750	495	598	20190.63	3250	20190.63	7895.61	2954.51	5.15	16.39	
16	AAH-16	157	250	340	1900	6600	-2	1300	6600	1500	1500	220	2700	610	670	9530	1300	477	1000	43000.68	6770	43000.68	11407.50	4041.52	0.46	21.11	
17	AAH-17	1215	29	170	342	1900	-2	340	2800	440	440	72	2200	380	2875	280	969	221	241	18555.0	2580	14921.93	4500.95	1831.72	1.55	19.29	
18	AAH-18	1543	7	150	290	530	-2	240	2000	440	440	72	2200	380	2875	280	969	221	241	18555.0	2580	14921.93	4500.95	1831.72	1.55	19.29	
19	AAH-19	2338	5	150	290	530	-2	240	2000	440	440	72	2200	380	2875	280	969	221	241	18555.0	2580	14921.93	4500.95	1831.72	1.55	19.29	
20	AAH-20	45100	310	200	608	2000	-2	1300	6600	1500	1500	220	2700	610	670	9530	1300	477	1000	43000.68	6770	43000.68	11407.50	4041.52	0.46	21.11	
21	AAH-21	6975	260	270	508	2170	-2	11500	9250	1600	1600	180	4500	650	6524	1316	1600	631	492	47151.22	6990	47151.22	12027.18	3872.62	5.83	57.31	
22	AAH-22	7235	260	270	508	2170	-2	11500	9250	1600	1600	180	4500	650	6524	1316	1600	631	492	47151.22	6990	47151.22	12027.18	3872.62	5.83	57.31	
23	AAH-23	203	37	36	95	1200	6	740	600	130	130	25	480	200	2182	129	88	60	171	5355.1	580	3197.85	2107.63	764.77	0.28	5.34	
24	AAH-24	7633	660	790	2035	8220	-2	3930	3250	650	650	150	2900	540	6664	540	6664	312	1500	19765.84	3440	19765.84	2867.26	4325.00	12.04	38.72	
25	AAH-25	4004	240	350	650	1970	-2	10600	8210	1500	1500	220	2700	610	670	9530	1300	477	1000	43000.68	6770	43000.68	11407.50	4041.52	0.46	21.11	
26	AAH-26	1887	1700	370	1071	7040	-2	3360	2890	540	540	97	2100	350	4346	583	529	240	445	18271.0	2490	15736.18	5724.72	2893.87	2.64	21.87	
27	AAH-27	21213	3700	450	1332	9530	-2	2360	2510	430	430	97	2100	350	4346	583	529	240	445	18271.0	2490	15736.18	5724.72	2893.87	2.64	21.87	
28	AAH-28	55800	960	280	6273	3380	-2	1380	1270	270	270	84	950	560	4646	388	180	180	160	15120.0	2170	8751.22	8901.91	9305.97	73.12	14.75	
29	AAH-29	27400	450	870	2904	3380	-2	1380	1270	270	270	84	950	560	4646	388	180	180	160	15120.0	2170	8751.22	8901.91	9305.97	73.12	14.75	
30	AAH-30	95600	570	430	928	8720	-2	4540	4290	600	600	35	2500	80	3123	560	453	308	282	23064.8	2990	19922.32	4472.12	2445.95	172.71	46.07	
31	AAH-31	2432	58	240	543	1300	-2	750	490	120	120	31	420	280	1192	115	167	40	213	351.9	700	3240.27	1512.58	1072.62	4.24	7.27	
32	AAH-32	56600	530	160	4859	8260	-2	4150	3340	640	640	160	2900	920	8985	741	1352	300	979	1320.0	3420	20541.66	13773.35	7468.89	89.48	27.57	
33	AAH-33	7858	560	690	2025	17400	-2	5120	6280	1300	1300	230	2900	610	8905	1205	1717	741	850	33233.9	4500	23571.19	8770.05	3974.05	21.18	138.12	
34	AAH-34	4977	420	590	1251	11400	-2	5970	4700	870	870	170	3900	610	6864	769	978	701	720	33233.9	4500	23571.19	8770.05	3974.05	17.28	48.45	
35	AAH-35	43900	430	510	1485	10300	-2	5240	4090	780	780	150	3500	620	7096	794	612	315	651	39117.6	4120	23265.05	8236.94	4090.71	79.19	53.31	
36	AAH-36	5968	380	210	1050	7070	-2	3700	2920	530	530	99	2400	310	5582	898	801	350	278	23274.0	2710	18279.80	7512.98	3008.22	12.91	45.30	
37	AAH-37	2047	28	4	152	534	5	429	262	74	74	12	250	47	336	48	40	30	30	4.3	1882.3	197	1505.23	441.58	279.33	8.19	1.66
38	AAH-38	7230	-4	43	330	1120	9	654	542	74	74	12	250	47	336	48	40	30	30	4.3	1882.3	197	1505.23	441.58	279.33	8.19	1.66
39	AAH-39	56000	78	200	354	2010	17	1300	830	120	120	22	370	59	1011	114	87	75	74.9	7.4	5663.3	429	4640.80	1156.23	656.35	23.51	3.90
40	AAH-40	65100	91	270	588	2090	23	1480	797	130	130	42	510	91	2588	208	159	100	125	12.1	601	5110.33	1958.73	1026.13	25.95	2.62	
41	AAH-41	5975	41	304	1520	1520	15	914	599	99	99	15	370	86	734	300	108	70	57.8	8.1	4230.9	425	3398.50	536.14	554.35	3.40	2.48
42	AAH-42	322	170	350	1650	8550	-2	4110	2960	560	560	110	3200	220	4049	439	570	334	433	22311.5	3420	16531.95	5411.11	3322.74	0.61	45.55	
43	AAH-43	216	23	220	1141	3700	34	2500	1200	350	350	210	1700	1200	4283	285	670	280	384	83814.7	18200	33981.74	9890.97	7993.59	0.55	285.87	
44	AAH-44	112	170	220	1405	6900	7	2730	2110	400	400	60	2100	140	2101	310	2										

付表6 岩石試料の主要化学成分分析値とノルム組成

(1)

	1	2	3	4	5	6	7	8	9	10	11
SP. NO.	92R-01	92R-02	92R-03	92R-04	92R-05	92R-06	92R-07	92R-08	92R-09	92R-10	92R-11
SiO <sub>2</sub>	73.62	74.06	73.37	71.07	73.50	67.20	71.21	72.30	69.41	71.91	70.30
TiO <sub>2</sub>	0.25	0.03	0.26	0.31	0.24	0.28	0.27	0.26	0.22	0.19	0.25
Al <sub>2</sub> O <sub>3</sub>	13.51	14.33	13.39	13.20	13.59	14.31	13.72	12.40	13.99	13.71	14.26
Fe <sub>2</sub> O <sub>3</sub>	0.10	0.21	0.09	0.20	0.78	0.01	0.01	0.04	1.17	0.58	0.35
FeO	1.57	0.51	1.75	2.11	1.00	2.33	2.11	2.02	0.67	1.12	1.21
MnO	0.02	0.01	0.04	0.06	0.02	0.04	0.06	0.03	0.02	0.02	0.03
MgO	0.30	0.13	0.36	0.65	0.38	0.52	0.51	0.52	0.22	0.34	0.30
CaO	1.49	0.90	0.86	1.43	0.28	1.39	1.41	0.62	0.22	0.61	1.32
Na <sub>2</sub> O	2.58	3.04	2.30	2.72	2.53	2.61	2.98	3.34	1.95	2.43	2.40
K <sub>2</sub> O	5.34	4.40	6.44	5.06	5.26	5.48	5.00	5.08	6.14	5.80	6.76
P <sub>2</sub> O <sub>5</sub>	0.08	0.04	0.12	0.12	0.14	0.18	0.10	0.16	0.08	0.08	0.10
BaO	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
LOI	0.76	1.19	0.88	0.72	1.34	0.79	0.61	0.90	1.60	0.90	0.44
total	99.62	98.85	99.86	97.65	99.06	95.14	97.99	97.67	95.69	97.69	97.72

-----Norm-----

Q	33.66	37.19	32.04	30.68	37.50	26.03	29.63	30.27	33.99	33.40	26.76
C	0.97	3.03	1.36	0.94	3.56	1.99	1.08	0.66	3.93	2.52	0.83
or	31.56	26.00	38.06	29.90	31.09	32.39	29.55	30.02	36.29	34.28	39.95
ab	21.83	25.72	19.46	23.02	21.41	22.09	25.22	28.26	16.50	20.56	20.31
an	6.87	4.20	3.48	6.31	0.47	5.72	6.34	2.03	0.57	2.50	5.90
ne	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
di	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
hd	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
en	0.75	0.32	0.90	1.62	0.95	1.30	1.27	1.30	0.55	0.85	0.75
fs	2.42	0.73	2.78	3.31	0.83	3.88	3.53	3.30	0.00	1.30	1.58
fo	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
fa	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
mt	0.14	0.30	0.13	0.29	1.13	0.01	0.01	0.06	1.59	0.84	0.51
ht	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.08	0.00	0.00
il	0.47	0.06	0.49	0.59	0.46	0.53	0.51	0.49	0.42	0.36	0.47
ru	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
ap	0.19	0.09	0.28	0.28	0.32	0.42	0.23	0.37	0.19	0.19	0.23
total	98.86	97.66	98.98	96.93	97.72	94.35	97.38	96.77	94.09	96.79	97.28

付表6 岩石試料の主要化学成分分析値とノルム組成

(2)

	12	13
SP. NO.	92R-12	92R-13
SiO <sub>2</sub>	84.98	59.45
TiO <sub>2</sub>	0.01	0.48
Al <sub>2</sub> O <sub>3</sub>	0.59	7.84
Fe <sub>2</sub> O <sub>3</sub>	0.11	25.99
FeO	0.36	0.08
MnO	0.01	0.01
MgO	0.05	0.13
CaO	0.05	0.15
Na <sub>2</sub> O	0.05	0.03
K <sub>2</sub> O	0.08	0.20
P <sub>2</sub> O <sub>5</sub>	0.01	0.06
BaO	0.00	0.00
LOI	0.26	6.03
total	86.56	100.45

-----Norm-----

Q	83.97	58.16
C	0.35	7.45
or	0.47	1.18
ab	0.42	0.25
an	0.18	0.35
ne	0.00	0.00
di	0.00	0.00
hd	0.00	0.00
en	0.12	0.32
fs	0.57	0.00
fo	0.00	0.00
fa	0.00	0.00
nt	0.16	0.00
ht	0.00	25.99
il	0.02	0.19
ru	0.00	0.38
ap	0.02	0.14
total	86.30	94.42

付表7 岩石試料微量成分析値一覽表

SP.NO.	SN	W	TA	NB	CE	EU	LA	ND	SM	TB	TH	U	Y	Gd	DY	PR	YB	LU
1	<5	<4	2	28	210	0.6	120	71	14	2.1	100	15	73	12.8	9.7	31	8.49	1.1
2	19	10	12	16	8	<0.2	6	<5	1	0.5	3.9	7	20	0.7	2.1	<20	3.43	0.45
3	6	22	4	29	160	0.8	85	40	11	0.5	74	16	51	8.7	0.8	<20	4.98	0.64
4	<5	<4	<1	23	110	1	65	40	8.3	2.1	47	9.8	65	8.3	10.4	<20	7.8	1.02
5	10	<4	4	22	110	1.3	73	45	9.9	1.7	33	9.3	61	10.4	9.8	<20	6.37	0.8
6	6	23	2	18	93	1.1	49	30	6.8	0.5	29	8	38	8.9	5.8	<20	3.55	0.45
7	<5	<4	3	22	99	1.9	110	73	20	4.8	40	16	187	20.4	28.3	<20	20.1	2.55
8	<5	<4	3	17	69	0.8	38	30	5.4	<0.5	22	7.8	28	4.5	3.7	<20	1.58	0.23
9	17	9	3	42	210	<0.2	120	72	17	<0.5	80	18	59	11.9	10.8	<20	3.86	0.51
10	7	<4	3	38	210	<0.2	120	64	16	<0.5	74	17	49	10.6	8.7	<20	2.66	0.38
11	<5	<4	<1	12	190	0.6	120	67	10	<0.5	120	16	35	5.8	6.4	<20	2.44	0.34
12	<5	<4	<1	<2	<3	<0.2	<1	<5	<0.1	<0.5	<0.5	<0.5	<2	2.2	<0.5	<20	0.07	<0.05
13	<5	8	<1	11	32	1	16	10	2.7	<0.5	11	2.2	19	5	4.4	<20	2.84	0.37

付表8 鈦石試料のEPMA分析値一覧表 (1)

min. name	cass	cass	cass	cass	cass	cass	cass
Sp. No.	CAI-12	CAI-12	CAI-12	CAI-12	CAI-12	BDI-07	DBP-08
Point No.	C-A11	C-A12	C-A21	C-B11	C-B21	B-A11	DB-A11
SnO <sub>2</sub>	90.80	92.32	97.33	96.91	95.24	98.04	98.90
TiO <sub>2</sub>	0.00	0.00	0.37	1.30	1.17	0.17	0.41
Fe <sub>2</sub> O <sub>3</sub> *	1.11	0.93	0.22	0.15	1.02	0.21	0.15
NiO	0.86	1.04	1.37	1.23	1.11	0.72	0.44
Y <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Nb <sub>2</sub> O <sub>5</sub>	1.36	1.11	0.00	0.00	1.48	0.00	0.12
La <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Ce <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00	0.43	0.00	0.00	0.00
Nd <sub>2</sub> O <sub>3</sub>	0.00	0.17	0.00	0.00	0.00	0.00	0.00
Sm <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Ta <sub>2</sub> O <sub>5</sub>	5.88	4.43	0.72	0.00	0.00	0.88	0.00
Total	100.01	100.00	100.01	100.02	100.02	100.02	100.02
Numbers of ions on the basis of two O.							
Sn	0.906	0.922	0.970	0.958	0.933	0.979	0.984
Ti	0.000	0.000	0.007	0.024	0.022	0.003	0.008
Fe	0.021	0.018	0.004	0.003	0.019	0.004	0.003
Ni	0.017	0.021	0.028	0.025	0.022	0.015	0.009
Y	0.000	0.000	0.000	0.000	0.000	0.000	0.000
Nb	0.015	0.013	0.000	0.000	0.016	0.000	0.001
La	0.000	0.000	0.000	0.000	0.000	0.000	0.000
Ce	0.000	0.000	0.000	0.004	0.000	0.000	0.000
Nd	0.000	0.002	0.000	0.000	0.000	0.000	0.000
Sm	0.000	0.000	0.000	0.000	0.000	0.000	0.000
Ta	0.040	0.030	0.005	0.000	0.000	0.006	0.000

\*: Total Fe as Fe<sub>2</sub>O<sub>3</sub>. cass: cassiterite

付表 8 鈦石試料 E P M A 分析値一覽表 (2)

Min. name	TiO2	TiO2	TiO2	TiO2	TiO2	TiO2
Sp. No.	DAM-03	DBP-08	DBP-08	CBP-08	DBP-08	DBP-08
Point No.	DA-A11	DB-B11	DB-B11	DB-B21	DB-A11	DB-A21
TiO2	94.68	49.96	94.93	94.64	91.59	95.68
SiO2	0.69	0.27	0.47	1.47	1.30	0.58
Al2O3	0.05	0.00	0.22	0.62	0.06	0.24
Fe2O3*	0.39	46.02	0.26	0.00	2.06	0.09
CaO	0.00	0.00	0.10	0.33	0.00	0.08
MnO	0.00	3.43	0.40	0.15	0.00	0.00
NiO	0.00	0.00	0.00	0.11	0.00	0.00
Y2O3	0.07	0.00	0.00	0.00	0.00	0.00
Nb2O5	1.56	0.35	0.30	0.32	2.62	0.54
La2O3	2.29	0.00	2.57	2.47	2.06	2.88
Ce2O3	0.00	0.00	0.00	0.00	0.00	0.00
Nd2O3	0.00	0.00	0.00	0.00	0.00	0.00
Sm2O3	0.00	0.00	0.83	0.00	0.39	0.00
Ta2O5	0.35	0.00	0.00	0.00	0.00	0.00
Total	100.08	100.03	100.08	100.11	100.08	100.09
Numbers of ions on the basis of two O.						
Ti	0.965	0.574	0.971	0.957	0.937	0.973
Si	0.009	0.004	0.006	0.020	0.018	0.008
Al	0.001	0.000	0.004	0.010	0.001	0.004
Fe	0.004	0.529	0.003	0.000	0.021	0.001
Ca	0.000	0.000	0.001	0.005	0.000	0.001
Mn	0.000	0.044	0.005	0.002	0.000	0.000
Ni	0.000	0.000	0.000	0.001	0.000	0.000
Y	0.001	0.000	0.000	0.000	0.000	0.000
Nb	0.010	0.002	0.002	0.002	0.016	0.003
La	0.011	0.000	0.013	0.012	0.010	0.014
Ce	0.000	0.000	0.000	0.000	0.000	0.000
Nd	0.000	0.000	0.000	0.000	0.000	0.000
Sm	0.000	0.000	0.004	0.000	0.002	0.000
Ta	0.001	0.000	0.000	0.000	0.000	0.000

\*: Total Fe as Fe2O3. TiO2: rutile or anatase

付表 8 鉍石試料 E P M A 分析値一覽表 (3)

Min. name	zir	zir	zir
Sp. No.	CAI-12	BDI-07	DAM-03
Point No.	C-B11	B-B11	DA-B11
SiO <sub>2</sub>	35.17	36.04	36.07
ZrO <sub>2</sub>	60.23	60.05	60.72
TiO <sub>2</sub>	0.00	0.00	0.10
HfO <sub>2</sub>	1.63	1.74	3.15
NiO	0.78	0.92	0.00
Y <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00
Nb <sub>2</sub> O <sub>5</sub>	1.13	1.29	0.00
La <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00
Ce <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00
Nd <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00
Sm <sub>2</sub> O <sub>3</sub>	0.00	0.00	0.00
Ta <sub>2</sub> O <sub>5</sub>	1.10	0.00	0.00
Total	100.04	100.04	100.04

Numbers of ions on the basis of four O.

Si	1.060	1.077	1.082
Zr	0.886	0.875	0.888
Ti	0.000	0.000	0.002
Hf	0.014	0.015	0.027
Ni	0.019	0.022	0.000
Y	0.000	0.000	0.000
Nb	0.015	0.017	0.000
La	0.000	0.000	0.000
Ce	0.000	0.000	0.000
Nd	0.000	0.000	0.000
Sm	0.000	0.000	0.000
Ta	0.009	0.000	0.000

zir: zircon

付表 8 鈳石試料 E PMA 分析値一覽表 (4)

Min. name	moz	moz	moz	moz	moz	moz	moz	moz
Sp. No.	CAI-12	BDI-07	BDI-07	AAM-06	AAM-06	AAM-06	AAM-06	DAM-03
Point No.	C-A11	B-A11	B-B11	A-A11	A-B11	A-C11	A-C21	D-A11
SiO <sub>2</sub>	0.00	0.92	1.53	2.06	0.34	1.76	1.80	0.00
TiO <sub>2</sub>	0.00	0.00	0.00	0.00	0.00	0.00	0.00	0.00
Fe <sub>2</sub> O <sub>3</sub> *								
CaO	0.22	0.56	0.57	0.59	0.45	0.22	0.73	0.90
NiO								
Y <sub>2</sub> O <sub>3</sub>	6.62	3.95	5.83	8.69	5.51	0.75	3.73	8.14
Nb <sub>2</sub> O <sub>5</sub>	0.40	0.17	0.00	0.38	0.20	0.90	0.00	0.90
La <sub>2</sub> O <sub>3</sub>	14.66	14.13	15.07	14.50	12.03	15.81	13.70	13.84
Ce <sub>2</sub> O <sub>3</sub>	35.57	28.49	30.14	27.55	30.20	32.01	29.82	29.09
Nd <sub>2</sub> O <sub>3</sub>	12.41	12.18	10.34	10.08	12.73	10.50	9.71	10.44
Sm <sub>2</sub> O <sub>3</sub>	2.87	3.06	1.87	1.90	3.01	2.21	2.88	3.77
Gd <sub>2</sub> O <sub>3</sub>	0.00	2.11	0.85	0.00	2.14	0.60	0.92	1.59
Tb <sub>2</sub> O <sub>3</sub>								
Dy <sub>2</sub> O <sub>3</sub>								
Er <sub>2</sub> O <sub>3</sub>								
Tm <sub>2</sub> O <sub>3</sub>								
Yb <sub>2</sub> O <sub>3</sub>								
Lu <sub>2</sub> O <sub>3</sub>								
ThO <sub>2</sub>	3.42	7.59	7.99	16.94	5.36	5.69	10.38	9.05
UO <sub>3</sub>	0.00	0.00	0.17	0.35	0.27	0.24	0.17	0.00
P <sub>2</sub> O <sub>5</sub>	23.90	26.93	25.74	17.08	27.86	29.41	26.27	22.40
Total	100.07	100.09	100.10	100.12	100.10	100.10	100.11	100.12
	Numbers of ions on the basis of four O.							
Si	0.000	0.037	0.062	0.096	0.014	0.068	0.073	0.000
Ti	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000
Fe								
Ca	0.010	0.024	0.025	0.029	0.019	0.009	0.032	0.042
Ni								
Y	0.150	0.085	0.126	0.216	0.117	0.015	0.080	0.188
Nb	0.008	0.003	0.000	0.008	0.004	0.016	0.000	0.018
La	0.230	0.211	0.226	0.250	0.177	0.225	0.204	0.222
Ce	0.555	0.422	0.449	0.471	0.442	0.452	0.442	0.463
Nd	0.189	0.176	0.150	0.168	0.182	0.145	0.140	0.162
Sm	0.042	0.043	0.026	0.031	0.041	0.029	0.040	0.057
Gd	0.000	0.028	0.011	0.000	0.028	0.008	0.012	0.023
Tb								
Dy								
Er								
Tm								
Yb								
Lu								
Th	0.033	0.070	0.074	0.180	0.049	0.050	0.096	0.090
U	0.000	0.000	0.001	0.003	0.002	0.002	0.001	0.000
P	0.862	0.923	0.886	0.675	0.943	0.960	0.900	0.825

\*: Total Fe as Fe<sub>2</sub>O<sub>3</sub>. moz: monazite



付表 8 鉍石試料 E P M A 分析値一覽表 (5)

Min. name	moz	moz
	DBP-08	DBP-08
Point No.	DB-A11	DB-B11
SiO <sub>2</sub>	3.10	0.43
TiO <sub>2</sub>	0.00	0.00
Fe <sub>2</sub> O <sub>3</sub> *	-----	-----
CaO	0.59	1.62
NiO	-----	-----
Y <sub>2</sub> O <sub>3</sub>	5.66	10.33
Nb <sub>2</sub> O <sub>5</sub>	1.16	0.53
La <sub>2</sub> O <sub>3</sub>	12.31	12.47
Ce <sub>2</sub> O <sub>3</sub>	26.09	25.11
Nd <sub>2</sub> O <sub>3</sub>	9.60	9.47
Sm <sub>2</sub> O <sub>3</sub>	1.53	3.33
Gd <sub>2</sub> O <sub>3</sub>	0.98	0.60
Tb <sub>2</sub> O <sub>3</sub>	-----	-----
Dy <sub>2</sub> O <sub>3</sub>	-----	-----
Er <sub>2</sub> O <sub>3</sub>	-----	-----
Tm <sub>2</sub> O <sub>3</sub>	-----	-----
Yb <sub>2</sub> O <sub>3</sub>	-----	-----
Lu <sub>2</sub> O <sub>3</sub>	-----	-----
ThO <sub>2</sub>	16.14	13.75
UO <sub>3</sub>	0.23	0.77
P <sub>2</sub> O <sub>5</sub>	22.76	21.28
Total	100.15	99.69

Numbers of ions on the basis of four O.

Si	0.129	0.019
Ti	0.000	0.000
Fe	-----	-----
Ca	0.026	0.076
Ni	-----	-----
Y	0.126	0.241
Nb	0.022	0.010
La	0.189	0.202
Ce	0.398	0.403
Nd	0.143	0.148
Sm	0.022	0.050
Gd	0.014	0.009
Tb	-----	-----
Dy	-----	-----
Er	-----	-----
Tm	-----	-----
Yb	-----	-----
Lu	-----	-----
Th	0.153	0.137
U	0.002	0.007
P	0.804	0.789

\*: Total Fe as Fe<sub>2</sub>O<sub>3</sub>. moz: monazite

付表8 鉍石試料E P M A分析値一覽表 (6)

Min. name	xeno	xeno	xeno	xeno	xeno
Sp. No.	AAM-06	AAM-06	AAM-06	DAM-03	DAM-03
Point No.	A-A11	A-A21	A-C11	DA-A11	DA-B11
SiO2	-----	-----	-----	-----	-----
TiO2	-----	-----	-----	-----	-----
Fe2O3*	0.00	1.03	0.46	0.00	0.20
CaO	-----	-----	-----	-----	-----
NiO	-----	-----	-----	-----	-----
Y2O3	30.78	29.81	29.80	31.77	32.03
Nb2O5	-----	-----	-----	-----	-----
La2O3	-----	-----	-----	-----	-----
Ce2O3	-----	-----	-----	-----	-----
Nd2O3	-----	-----	-----	-----	-----
Sm2O3	0.00	0.63	0.97	0.93	1.21
Gd2O3	1.99	1.73	2.55	1.76	2.61
Tb2O3	0.00	0.00	0.00	0.00	0.00
Dy2O3	6.34	0.00	5.51	7.01	6.61
Er2O3	6.24	6.10	5.84	4.93	4.68
Tm2O3	0.48	1.53	0.75	0.00	0.40
Yb2O3	7.83	11.92	8.06	3.67	5.15
Lu2O3	0.00	2.46	2.88	0.39	0.88
ThO2	0.00	0.36	0.77	0.85	0.38
UO3	0.42	0.52	0.79	2.04	0.73
P2O5	45.99	43.99	41.70	46.70	45.19
Total	100.07	100.08	100.08	100.05	100.07

Numbers of ions on the basis of four O.

Si	-----	-----	-----	-----	-----
Ti	-----	-----	-----	-----	-----
Fe	0.000	0.024	0.011	0.000	0.005
Ca	-----	-----	-----	-----	-----
Ni	-----	-----	-----	-----	-----
Y	0.493	0.489	0.504	0.502	0.515
Nb	-----	-----	-----	-----	-----
La	-----	-----	-----	-----	-----
Ce	-----	-----	-----	-----	-----
Nd	-----	-----	-----	-----	-----
Sm	0.000	0.007	0.011	0.010	0.013
Gd	0.020	0.018	0.027	0.017	0.026
Tb	0.000	0.000	0.000	0.000	0.000
Dy	0.061	0.000	0.056	0.067	0.064
Er	0.059	0.059	0.058	0.046	0.044
Tm	0.004	0.015	0.007	0.000	0.004
Yb	0.072	0.112	0.078	0.033	0.047
Lu	0.000	0.023	0.028	0.003	0.008
Th	0.000	0.003	0.006	0.006	0.003
U	0.003	0.003	0.005	0.013	0.005
P	1.171	1.147	1.121	1.173	1.156

\*: Total Fe as Fe2O3. xeno: xenotime

付表8 鈦石試料E P M A分析値一覽表 (7)

Min. name	poly	poly	poly	poly	poly	poly
Sp. No.	BDI-07	BDI-07	AAM-06	AAM-06	DAM-03	DAM-03
Point No.	B-A11	B-B21	A-A11	A-C11	DA-A11	DA-A11
SiO <sub>2</sub>						
TiO <sub>2</sub>	28.98	26.65	28.95	29.15	28.92	26.89
Fe <sub>2</sub> O <sub>3</sub> *	0.56	0.86	1.59	0.46	0.70	0.35
CaO	0.00	0.34	0.28	0.42	0.28	0.35
NiO						
Y <sub>2</sub> O <sub>3</sub>	0.80	10.52	9.54	10.64	8.74	8.91
Nb <sub>2</sub> O <sub>5</sub>	9.52	22.80	17.88	19.00	17.77	18.72
La <sub>2</sub> O <sub>3</sub>						
Ce <sub>2</sub> O <sub>3</sub>						
Nd <sub>2</sub> O <sub>3</sub>	0.00	0.50	0.00	0.40	0.00	0.59
Sm <sub>2</sub> O <sub>3</sub>	0.00	1.27	0.24	0.51	0.79	1.35
Gd <sub>2</sub> O <sub>3</sub>	0.21	2.75	1.34	1.30	0.94	2.43
Tb <sub>2</sub> O <sub>3</sub>						
Dy <sub>2</sub> O <sub>3</sub>	1.12	2.76	3.35	2.31	3.08	5.05
Er <sub>2</sub> O <sub>3</sub>	2.08	2.05	2.23	1.50	2.09	3.00
Tm <sub>2</sub> O <sub>3</sub>						
Yb <sub>2</sub> O <sub>3</sub>	7.37	6.38	5.79	5.70	3.99	3.67
Ta <sub>2</sub> O <sub>5</sub>	29.96	8.97	5.09	3.69	9.78	10.00
ThO <sub>2</sub>	2.60	2.30	3.33	3.57	3.49	4.42
UO <sub>3</sub>	16.82	11.92	20.46	21.43	19.49	14.35
Total	100.02	100.07	100.07	100.08	100.06	100.08

  

	Numbers of ions on the basis of six O.					
Si						
Ti	1.410	1.230	1.341	1.343	1.341	1.276
Fe	0.027	0.040	0.074	0.021	0.032	0.017
Ca	0.000	0.022	0.018	0.028	0.018	0.024
Ni						
Y	0.028	0.344	0.313	0.347	0.287	0.299
Nb	0.278	0.633	0.498	0.526	0.495	0.534
La						
Ce						
Nd	0.000	0.011	0.000	0.009	0.000	0.013
Sm	0.000	0.027	0.005	0.011	0.017	0.029
Gd	0.005	0.056	0.027	0.026	0.019	0.051
Tb						
Dy	0.023	0.055	0.066	0.046	0.061	0.103
Er	0.042	0.040	0.043	0.029	0.040	0.059
Tm						
Yb	0.145	0.119	0.109	0.106	0.075	0.071
Ta	0.527	0.150	0.085	0.061	0.164	0.172
Th	0.038	0.032	0.047	0.050	0.049	0.063
U	0.229	0.154	0.265	0.276	0.252	0.190

\*: Total Fe as Fe<sub>2</sub>O<sub>3</sub>. poly: polyclase

付表 8 鈦石試料 E P M A 分析値一覽表 (8)

Min. name	eux	eux	eux
Sp. No.	AAM-06	AAM-06	BDI-07
Point No.	A-A11	A-A12	B-B11
SiO <sub>2</sub>			
TiO <sub>2</sub>	1.62	1.73	1.38
Fe <sub>2</sub> O <sub>3</sub> *			
CaO	0.72	0.69	0.13
NiO			
Y <sub>2</sub> O <sub>3</sub>	24.65	25.04	16.57
Nb <sub>2</sub> O <sub>5</sub>	41.11	41.98	32.23
La <sub>2</sub> O <sub>3</sub>			
Ce <sub>2</sub> O <sub>3</sub>	0.00	0.20	0.16
Nd <sub>2</sub> O <sub>3</sub>	0.96	0.78	0.25
Sm <sub>2</sub> O <sub>3</sub>	1.51	1.23	1.01
Gd <sub>2</sub> O <sub>3</sub>	2.93	2.47	2.08
Tb <sub>2</sub> O <sub>3</sub>			
Dy <sub>2</sub> O <sub>3</sub>	4.51	4.72	4.34
Er <sub>2</sub> O <sub>3</sub>	2.84	2.40	4.06
Tm <sub>2</sub> O <sub>3</sub>			
Yb <sub>2</sub> O <sub>3</sub>	8.12	7.53	9.56
Ta <sub>2</sub> O <sub>5</sub>	2.82	1.35	23.32
ThO <sub>2</sub>	1.94	1.88	1.40
UO <sub>3</sub>	6.30	8.01	3.53
Total	100.03	100.01	100.02

Numbers of ions on the basis of six O.

Si			
Ti	0.085	0.090	0.077
Fe			
Ca	0.054	0.051	0.010
Ni			
Y	0.914	0.921	0.655
Nb	1.295	1.311	1.083
La			
Ce	0.000	0.005	0.004
Nd	0.024	0.019	0.007
Sm	0.036	0.029	0.026
Gd	0.068	0.057	0.051
Tb			
Dy	0.101	0.105	0.104
Er	0.062	0.052	0.095
Tm			
Yb	0.173	0.159	0.217
Ta	0.053	0.025	0.471
Th	0.031	0.030	0.024
U	0.092	0.116	0.055

\*: Total Fe as Fe<sub>2</sub>O<sub>3</sub>. eux: euxenite

付表 8 鉍石試料 E P M A 分析値一覽表 (9)

Min. name	thor	thor	thor
Sp. No.	DAM-03	DAM-03	DAM-03
Point No.	DA-A11	DA-A12	DA-A21
SiO <sub>2</sub>	12.28	11.87	11.42
Al <sub>2</sub> O <sub>3</sub>	1.83	2.17	1.55
Fe <sub>2</sub> O <sub>3</sub> *	8.09	11.14	4.32
CaO	-----	-----	-----
NiO	-----	-----	-----
La <sub>2</sub> O <sub>3</sub>	0.24	0.00	0.51
Ce <sub>2</sub> O <sub>3</sub>	0.41	0.25	0.33
Nd <sub>2</sub> O <sub>3</sub>	0.00	0.45	0.62
Sm <sub>2</sub> O <sub>3</sub>	0.65	0.00	0.54
Gd <sub>2</sub> O <sub>3</sub>	-----	-----	-----
Tb <sub>2</sub> O <sub>3</sub>	-----	-----	-----
Dy <sub>2</sub> O <sub>3</sub>	-----	-----	-----
Er <sub>2</sub> O <sub>3</sub>	-----	-----	-----
Tm <sub>2</sub> O <sub>3</sub>	-----	-----	-----
Nb <sub>2</sub> O <sub>5</sub>	-----	-----	-----
PbO	0.68	1.03	0.83
ThO <sub>2</sub>	65.60	62.17	71.97
UO <sub>3</sub>	5.98	6.77	2.46
P <sub>2</sub> O <sub>5</sub>	4.23	4.15	5.46
Total	99.99	100.00	100.01

Numbers of ions on the basis of four O.

Si	0.611	0.578	0.589
Al	0.107	0.125	0.094
Fe <sup>3+</sup>	0.303	0.408	0.168
Ca	-----	-----	-----
Ni	-----	-----	-----
La	0.004	0.000	0.010
Ce	0.007	0.004	0.006
Nd	0.000	0.008	0.011
Sm	0.011	0.000	0.010
Gd	-----	-----	-----
Tb	-----	-----	-----
Dy	-----	-----	-----
Er	-----	-----	-----
Tm	-----	-----	-----
Yb	-----	-----	-----
Pb	0.009	0.014	0.012
Th	0.743	0.689	0.844
U	0.063	0.069	0.027
P	0.178	0.171	0.238

\*: Total Fe as Fe<sub>2</sub>O<sub>3</sub>. thor: thorite

JICA