









Appendix 2-3 Photomicrographs of the Thin Sections(5/10)

Plane polarized light









Crossed polarized light



Appendix 2-3 Photomicrographs of the Thin Sections(G/10)

Plane polarized light









Crossed polarized light



Appendix 2-3 Photomicrographs of the Thin Sections(7/10)

Plane polarized light








Crossed polarized light



Appendix 2-3 Photomicrographs of the Thin Sections(8/10)

Plane polarized light








Crossed polarized light



Appendix 2-3 Photomicrographs of the Thin Sections(9/10)

Plane polarized light






Crossed polarized light




Appendix 2-3 Photomicrographs of the Thin Sections(10/10)

Plane polarized light

Crossed polarized light





Appendix 2-4 Microscopic Observations of the Polished Sections (1/2)

No.	Sample No.	Locality	Field Name	Minerals																				
				Pyrite	Marcasite	Arsenopyrite	Pyrhoite	Chalcopyrite	Sphalerite	Tetrahedrite	Native bismuth	Bismuthinite	Wittichenite	Lillianite	Chalcoite	Covellite	Goethite	Lepidocrocite	Magnetite	Ilmenite	Rutile	Graphite	Sphene	
1	T-11 L1	T-11 80.0 m	brecciated silicified rock														•							
2	T-11 L2	T-11 81.9 m	limestone														•							•
3	T-11 L3	T-11 88.8 m	skarn														Δ							
4	T-11 L4	T-11 155.0 m	skarn														Δ							
5	T-12 L3	T-12 24.0 m	silicified hornfels				•										Δ							Δ
6	T-14 L2	T-14 74.0 m	skarn				•										Δ							Δ
7	T-17 L1	T-17 23.0 m	hornfels														Δ							Δ
8	T-17 L4	T-17 95.5 m	brecciated silicified rock														Δ							
9	T-18 L2	T-18 51.0 m	brecciated silicified rock				•										⊙	○						Δ
10	T-18 L6	T-18 110.0 m	brecciated silicified rock with iron oxides				•										Δ							
11	T-19 L1	T-19 33.5 m	skarn																					○
12	T-22 L1	T-22 58.0 m	silicified rock	Δ													Δ							
13	T-22 L2	T-22 117.2 m	brecciated silicified rock with iron oxides														Δ							
14	T-29 L1	T-29 53.5 m	brecciated silicified rock with iron oxides														Δ							○
15	T-29 L2	T-29 63.0 m	quartz vein	Δ													•							
16	T-29 L3	T-29 129.0 m	silicified rock														○	•						
17	T-29 L4	T-29 137.3 m	brecciated silicified rock with iron oxides				•										Δ							
18	P-875 L1	P-875 38.0 m	silicified rock														○	○						⊙

⊙ : abundant ○ : common Δ : poor • : rare

Appendix 2-4 Microscopic Observations of the Polished Sections (2/2)

No.	Sample No.	Locality	Field Name	Minerals																				
				Pyrite	Marcasite	Asenopyrite	Pyrrhotite	Chalcopyrite	Sphalerite	Tetrahedrite	Native bismuth	Bismuthinite	Wittichenite	Lillianite	Chalcocite	Covellite	Goethite	Lepidocrocite	Magnetite	Ilmenite	Rutile	Graphite	Sphene	
19	B-8 L2	MIUB-8 24.6 m	pyrite vein	⊙			△	•									△							
20	B-8 L3	MIUB-8 28.3 m	silicified & skarnized metasomatite	△	⊙		•	○									○							
21	B-9 L4	MIUB-9 28.4 m	skarn	△	○	⊙		•									△							
22	B-9 L5	MIUB-9 47.5 m	quartz, sulfide vein	△	•	△	⊙	○																
23	B-12 L5	MIUB-12 138.3 m	skarn with sulfide	⊙	○		○	△	•															
24	B-12 L6	MIUB-12 143.5 m	silicified metasomatite with sulfide	⊙			△	•	•								•							•
25	B-13 L1	MIUB-13 41.0 m	quartz, calcite vein	○			•																	
26	B-13 L6	MIUB-13 87.5 m	sulfide vein	⊙	△		•	•									⊙							
27	B-14 L2	MIUB-14 85.8 m	silicified & skarnized metasomatite	⊙	○		•	•									△							
28	B-16 L6	MIUB-16 101.3 m	brecciated quartz vein	⊙													△							
29	B-17 L4	MIUB-17 75.4 m	silicified & skarnized metasomatite	⊙	○		•	○									•							
30	B-17 L6	MIUB-17 78.6 m	silicified & skarnized metasomatite	•		⊙		•									•							
31	B-18 L6	MIUB-18 69.3 m	quartz sulfide vein	⊙				○	△	•	△	•	•	•										
32	B-18 L9	MIUB-18 108.4 m	sulfide vein	○	⊙		•	△	•								○							
33	B-19 L2	MIUB-19 61.7 m	silicified & weakly skarnized metasomatite	⊙				△	△															
34	B-19 L3	MIUB-19 90.1 m	quartz vein	⊙			•	•	•															
35	B-20 L12	MIUB-20 417.9 m	quartz, diopside, actinolite, pyrite vein				○	△	•															
36	B-21 L4	MIUB-21 57.9 m	silicified & skarnized alteration (ss>>sl)	⊙	△		•	•	•	△														







⊙ : abundant ○ : common △ : poor • : rare

Appendix 2-5 Photomicrographs of the Polished Sections








Abbreviations

Asp	:	Arsenopyrite
Bi	:	Native bismuth
Bs	:	Bismuthinite
Cc	:	Chalcocite
Cp	:	Chalcopyrite
Cv	:	Covellite
Go	:	Goethite
Grp	:	Graphite
Lpd	:	Lepidocrocite
Mrc	:	Marcasite
Po	:	Pyrrhotite
Py	:	Pyrite
Rt	:	Rutile
Sp	:	Sphalerite








Appendix 2-5 Photomicrographs of the Polished Sections(1/5)










Appendix 2-5 Photomicrographs of the Polished Sections(2/5)






Appendix 2-5 Photomicrographs of the Polished Sections(3/5)



Appendix 2-5 Photomicrographs of the Polished Sections(4/5)



Appendix 2-5 Photomicrographs of the Polished Sections(5/5)



Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 1/22)

Ser. no.	Samp. no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
1	T-11 0 1	70.0 - 72.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
2	T-11 0 2	72.0 - 74.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
3	T-11 0 3	74.0 - 76.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
4	T-11 0 4	76.0 - 78.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.04	
5	T-11 0 5	78.0 - 80.0	2.0	< 0.1	< 1	0.01	< 0.01	< 0.01	0.03	
6	T-11 0 6	80.0 - 82.0	2.0	1.2	< 1	0.01	0.02	< 0.01	0.04	
7	T-11 0 7	82.0 - 84.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	0.03	
8	T-11 0 8	84.0 - 86.0	2.0	0.1	< 1	0.01	< 0.01	< 0.01	0.02	
9	T-11 0 9	86.0 - 88.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
10	T-11 0 10	88.0 - 90.0	2.0	0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
11	T-11 0 11	90.0 - 92.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
12	T-11 0 12	92.0 - 94.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
13	T-12 0 1	10.0 - 11.0	1.0	< 0.1	< 1	< 0.01	0.01	0.01	< 0.01	
14	T-12 0 2	11.0 - 12.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
15	T-12 0 3	20.0 - 22.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
16	T-12 0 4	22.0 - 24.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
17	T-12 0 5	24.0 - 26.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
18	T-12 0 6	26.0 - 28.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
19	T-12 0 7	28.0 - 30.0	2.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.02	
20	T-12 0 8	30.0 - 32.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
21	T-12 0 9	32.0 - 34.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
22	T-12 0 10	34.0 - 36.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
23	T-12 0 11	36.0 - 38.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
24	T-12 0 12	38.0 - 40.0	2.0	0.1	< 1	< 0.01	< 0.01	0.01	0.02	
25	T-12 0 13	63.0 - 63.2	0.2	< 0.1	< 1	< 0.01	0.01	0.01	< 0.01	
26	T-12 0 14	70.0 - 71.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
27	T-12 0 15	71.0 - 72.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
28	T-12 0 16	72.0 - 73.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
29	T-12 0 17	78.5 - 79.5	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
30	T-12 0 18	79.5 - 80.5	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 2/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
31	T-12 0 19	80.5 - 81.5	1.0	0.1	< 1	< 0.01	0.02	0.01	< 0.01	
32	T-12 0 20	118.0 - 120.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
33	T-12 0 21	120.0 - 122.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
34	T-12 0 22	122.0 - 124.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
35	T-12 0 23	124.0 - 126.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
36	T-12 0 24	126.0 - 128.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	0.04	
37	T-12 0 25	128.0 - 130.0	2.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
38	T-12 0 26	130.0 - 132.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
39	T-12 0 27	132.0 - 134.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
40	T-12 0 28	134.0 - 136.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
41	T-12 0 29	136.0 - 138.0	2.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
42	T-12 0 30	148.5 - 149.5	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.02	
43	T-12 0 31	149.5 - 150.5	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
44	T-12 0 32	150.5 - 151.5	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
45	T-13 0 1	15.5 - 17.0	1.5	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
46	T-13 0 2	17.0 - 18.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
47	T-13 0 3	18.0 - 19.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
48	T-13 0 4	19.0 - 20.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
49	T-13 0 5	20.0 - 21.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
50	T-13 0 6	21.0 - 22.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
51	T-13 0 7	22.0 - 23.0	1.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
52	T-13 0 8	23.0 - 24.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
53	T-13 0 9	24.0 - 25.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
54	T-13 0 10	25.0 - 26.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
55	T-13 0 11	26.0 - 27.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
56	T-13 0 12	27.0 - 28.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
57	T-13 0 13	28.0 - 29.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
58	T-13 0 14	29.0 - 30.0	1.0	0.7	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
59	T-13 0 15	30.0 - 31.0	1.0	0.7	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
60	T-13 0 16	31.0 - 32.0	1.0	0.5	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 3/22)

Ser. no.	Samp. no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
61	T-13 0 17	32.0 - 33.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
62	T-13 0 18	33.0 - 34.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
63	T-13 0 19	34.0 - 35.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
64	T-13 0 20	35.0 - 37.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
65	T-13 0 21	37.0 - 39.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
66	T-13 0 22	95.0 - 96.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
67	T-13 0 23	96.0 - 97.0	1.0	0.2	1.6	< 0.01	< 0.01	< 0.01	0.01	
68	T-13 0 24	97.0 - 98.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
69	T-13 0 25	98.0 - 99.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
70	T-13 0 26	99.0 - 100.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
71	T-14 0 1	4.3 - 6.0	1.7	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
72	T-14 0 2	6.0 - 7.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
73	T-14 0 3	7.0 - 8.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
74	T-14 0 4	8.0 - 9.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
75	T-14 0 5	9.0 - 10.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
76	T-14 0 6	10.0 - 11.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
77	T-14 0 7	11.0 - 12.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
78	T-14 0 8	12.0 - 13.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
79	T-14 0 9	13.0 - 14.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
80	T-14 0 10	14.0 - 15.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
81	T-14 0 11	15.0 - 16.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
82	T-14 0 12	16.0 - 17.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
83	T-14 0 13	17.0 - 18.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
84	T-14 0 14	18.0 - 19.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
85	T-14 0 15	19.0 - 20.0	1.0	0.2	< 1	0.05	< 0.01	< 0.01	< 0.01	
86	T-14 0 16	27.7 - 29.0	1.3	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
87	T-14 0 17	29.0 - 30.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
88	T-14 0 18	30.0 - 31.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
89	T-14 0 19	31.0 - 32.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
90	T-14 0 20	32.0 - 33.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 4/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
91	T-14 0 21	33.0 - 34.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
92	T-14 0 22	34.0 - 35.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
93	T-14 0 23	35.0 - 36.0	1.0	0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
94	T-14 0 24	36.0 - 37.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
95	T-14 0 25	37.0 - 38.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
96	T-14 0 26	38.0 - 39.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
97	T-14 0 27	39.0 - 40.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
98	T-14 0 28	40.0 - 41.0	1.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
99	T-14 0 30	42.0 - 43.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
100	T-14 0 31	43.0 - 44.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
101	T-15 0 1	0.0 - 1.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
102	T-15 0 2	1.0 - 2.0	1.0	0.4	< 1	< 0.01	< 0.01	< 0.01	0.01	
103	T-15 0 3	2.0 - 3.0	1.0	< 0.1	< 1	0.05	< 0.01	< 0.01	0.01	
104	T-15 0 4	3.0 - 4.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
105	T-15 0 5	4.0 - 5.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
106	T-15 0 6	5.0 - 6.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
107	T-15 0 7	6.0 - 7.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
108	T-15 0 8	7.0 - 8.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
109	T-15 0 9	8.0 - 9.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
110	T-15 0 10	11.0 - 12.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
111	T-15 0 11	12.0 - 13.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
112	T-15 0 12	13.0 - 14.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
113	T-15 0 13	14.0 - 15.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
114	T-15 0 14	15.0 - 16.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
115	T-15 0 15	16.0 - 17.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
116	T-15 0 16	17.0 - 18.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
117	T-15 0 17	18.0 - 19.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
118	T-15 0 18	19.0 - 20.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	0.01	
119	T-15 0 19	20.0 - 21.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
120	T-15 0 20	21.0 - 22.0	1.0	0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 5/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
121	T-15 0 21	22.0 - 23.0	1.0	0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
122	T-15 0 22	23.0 - 24.0	1.0	0.5	< 1	< 0.01	< 0.01	0.01	< 0.01	
123	T-15 0 23	24.0 - 25.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
124	T-15 0 24	25.0 - 26.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	0.01	
125	T-15 0 25	26.0 - 27.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	0.01	
126	T-15 0 26	27.0 - 28.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	< 0.01	
127	T-15 0 27	28.0 - 29.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
128	T-15 0 28	29.0 - 30.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
129	T-15 0 29	30.0 - 31.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	0.01	
130	T-15 0 30	31.0 - 32.0	1.0	0.1	< 1	< 0.01	< 0.01	0.02	< 0.01	
131	T-15 0 31	32.0 - 33.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	< 0.01	
132	T-15 0 32	33.0 - 34.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
133	T-15 0 33	34.0 - 35.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	< 0.01	
134	T-15 0 34	35.0 - 36.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	< 0.01	
135	T-15 0 35	36.0 - 37.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
136	T-15 0 36	37.0 - 38.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
137	T-15 0 37	38.0 - 39.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	0.01	
138	T-15 0 38	39.0 - 40.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	0.01	
139	T-15 0 39	40.0 - 41.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
140	T-15 0 40	41.0 - 42.0	1.0	0.1	< 1	< 0.01	< 0.01	0.02	0.01	
141	T-15 0 41	42.0 - 43.5	1.5	0.1	< 1	< 0.01	< 0.01	0.01	0.02	
142	T-15 0 42	46.6 - 48.0	1.4	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
143	T-15 0 43	48.0 - 49.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
144	T-15 0 44	49.0 - 50.0	1.0	0.2	< 1	< 0.01	< 0.01	0.01	0.01	
145	T-15 0 45	50.0 - 51.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.02	0.01	
146	T-16 0 1	8.0 - 10.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
147	T-16 0 2	10.0 - 12.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
148	T-16 0 3	12.0 - 14.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
149	T-16 0 4	14.0 - 16.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
150	T-16 0 5	16.0 - 18.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 6/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
151	T-16 0 6	18.0 - 20.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
152	T-16 0 7	20.0 - 22.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
153	T-16 0 8	22.0 - 23.0	1.0	0.2	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
154	T-16 0 9	23.0 - 24.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
155	T-16 0 10	24.0 - 25.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
156	T-16 0 11	25.0 - 26.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
157	T-16 0 12	26.0 - 27.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
158	T-16 0 13	27.0 - 28.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
159	T-16 0 14	28.0 - 29.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
160	T-16 0 15	29.0 - 30.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
161	T-16 0 16	30.0 - 31.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
162	T-16 0 17	31.0 - 32.0	1.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
163	T-16 0 18	32.0 - 33.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
164	T-16 0 19	33.0 - 34.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
165	T-16 0 20	34.0 - 35.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
166	T-16 0 21	35.0 - 36.0	1.0	< 0.1	1.2	< 0.01	< 0.01	< 0.01	< 0.01	
167	T-16 0 22	36.0 - 37.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
168	T-16 0 23	37.0 - 38.0	1.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
169	T-16 0 24	38.0 - 39.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
170	T-16 0 25	39.0 - 40.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
171	T-16 0 26	40.0 - 41.0	1.0	< 0.1	1.2	< 0.01	< 0.01	< 0.01	< 0.01	
172	T-16 0 27	41.0 - 42.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
173	T-16 0 28	42.0 - 44.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
174	T-16 0 29	44.0 - 46.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
175	T-16 0 30	46.0 - 48.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
176	T-16 0 31	48.0 - 50.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
177	T-16 0 32	50.0 - 52.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
178	T-16 0 33	52.0 - 54.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
179	T-16 0 34	54.0 - 56.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
180	T-16 0 35	56.0 - 58.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 7/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	WO3(%)	Discriptions
181	T-16 0 36	58.0 - 60.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
182	T-16 0 37	60.0 - 62.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
183	T-16 0 38	62.0 - 64.0	2.0	< 0.1	1.6	< 0.01	< 0.01	< 0.01	< 0.01	
184	T-16 0 39	64.0 - 66.0	2.0	< 0.1	2.4	< 0.01	< 0.01	< 0.01	< 0.01	
185	T-16 0 40	66.0 - 68.0	2.0	0.1	2.8	< 0.01	< 0.01	< 0.01	< 0.01	
186	T-16 0 41	68.0 - 70.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
187	T-16 0 42	70.0 - 72.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
188	T-16 0 43	72.0 - 74.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
189	T-16 0 44	74.0 - 76.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
190	T-16 0 45	76.0 - 78.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
191	T-17 0 1	80.0 - 81.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
192	T-17 0 2	81.0 - 82.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
193	T-17 0 3	82.0 - 83.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
194	T-17 0 4	83.0 - 84.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
195	T-17 0 5	84.0 - 85.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
196	T-17 0 6	85.0 - 86.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
197	T-17 0 7	86.0 - 87.0	1.0	< 0.1	< 1	0.03	< 0.01	< 0.01	< 0.01	
198	T-17 0 8	87.0 - 88.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
199	T-17 0 9	88.0 - 89.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
200	T-17 0 10	89.0 - 90.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
201	T-17 0 11	90.0 - 91.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
202	T-17 0 12	91.0 - 92.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
203	T-17 0 13	92.0 - 93.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
204	T-17 0 14	93.0 - 94.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
205	T-17 0 15	94.0 - 95.0	1.0	< 0.1	< 1	0.04	< 0.01	< 0.01	< 0.01	
206	T-17 0 16	95.0 - 96.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
207	T-17 0 17	96.0 - 97.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
208	T-17 0 18	97.0 - 98.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
209	T-17 0 19	98.0 - 99.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
210	T-17 0 20	99.0 - 100.0	1.0	< 0.1	2.2	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 8/22)

ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W33(%)	Discriptions
211	T-17 0 21	100.0 - 101.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
212	T-17 0 22	101.0 - 102.0	1.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
213	T-17 0 23	102.0 - 103.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
214	T-17 0 24	103.0 - 104.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
215	T-17 0 25	104.0 - 105.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
216	T-17 0 26	105.0 - 106.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
217	T-17 0 27	106.0 - 107.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
218	T-17 0 28	107.0 - 108.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
219	T-17 0 29	108.0 - 109.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
220	T-17 0 30	109.0 - 110.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
221	T-17 0 31	110.0 - 111.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
222	T-17 0 32	111.0 - 112.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
223	T-17 0 33	112.0 - 113.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
224	T-17 0 34	113.0 - 114.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
225	T-17 0 35	114.0 - 115.0	1.0	< 0.1	< 1	0.05	< 0.01	< 0.01	< 0.01	
226	T-17 0 36	115.0 - 116.0	1.0	0.1	< 1	0.03	< 0.01	< 0.01	< 0.01	
227	T-18 0 1	42.0 - 43.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
228	T-18 0 2	43.0 - 44.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
229	T-18 0 3	44.0 - 45.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
230	T-18 0 4	45.0 - 46.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
231	T-18 0 5	46.0 - 47.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
232	T-18 0 6	47.0 - 48.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
233	T-18 0 7	48.0 - 49.0	1.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
234	T-18 0 8	49.0 - 50.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
235	T-18 0 9	50.0 - 51.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
236	T-18 0 10	51.0 - 52.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
237	T-18 0 11	80.0 - 82.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
238	T-18 0 12	82.0 - 84.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
239	T-18 0 13	84.0 - 86.0	2.0	0.2	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
240	T-18 0 14	86.0 - 88.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 9/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
241	T-18 0 15	88.0 - 90.0	2.0	< 0.1	< 1	< 0.01	0.04	< 0.01	< 0.01	
242	T-18 0 16	90.0 - 92.0	2.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
243	T-18 0 17	92.0 - 93.4	1.4	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
244	T-18 0 18	93.4 - 95.3	1.9	0.2	< 1	< 0.01	0.01	< 0.01	0.04	
245	T-18 0 19	95.3 - 98.0	2.7	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
246	T-18 0 20	98.0 - 100.0	2.0	0.2	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
247	T-18 0 21	100.0 - 102.0	2.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
248	T-18 0 22	102.0 - 104.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
249	T-18 0 23	104.0 - 106.0	2.0	0.2	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
250	T-18 0 24	106.0 - 108.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
251	T-18 0 25	108.0 - 110.0	2.0	0.4	19.6	0.06	< 0.01	< 0.01	< 0.01	
252	T-18 0 26	110.0 - 112.0	2.0	0.1	3.2	0.06	< 0.01	< 0.01	< 0.01	
253	T-18 0 27	112.0 - 114.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
254	T-18 0 28	114.0 - 116.0	2.0	< 0.1	1.6	< 0.01	< 0.01	< 0.01	< 0.01	
255	T-19 0 1	13.7 - 15.7	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
256	T-19 0 2	15.7 - 17.0	1.3	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
257	T-19 0 3	17.0 - 19.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
258	T-19 0 4	19.0 - 21.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
259	T-19 0 5	21.0 - 23.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
260	T-19 0 6	23.0 - 25.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
261	T-19 0 7	25.0 - 27.0	2.0	0.2	< 1	0.01	< 0.01	< 0.01	< 0.01	
262	T-19 0 8	27.0 - 29.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
263	T-19 0 9	29.0 - 31.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
264	T-19 0 10	31.0 - 33.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
265	T-19 0 11	33.0 - 35.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
266	T-19 0 12	35.0 - 37.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
267	T-19 0 13	37.0 - 39.5	2.5	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
268	T-19 0 14	39.5 - 40.5	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
269	T-19 0 15	40.5 - 41.5	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
270	T-19 0 16	41.5 - 42.5	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 10/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
271	T-19 0 17	42.5 - 43.5	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
272	T-19 0 18	43.5 - 44.5	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
273	T-19 0 19	44.5 - 46.0	1.5	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
274	T-19 0 20	46.0 - 48.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
275	T-19 0 21	48.0 - 50.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
276	T-19 0 22	50.0 - 52.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
277	T-19 0 23	52.0 - 54.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
278	T-19 0 24	54.0 - 56.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.04	
279	T-19 0 25	56.0 - 58.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
280	T-19 0 26	58.0 - 60.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
281	T-20 0 1	5.0 - 7.0	2.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
282	T-20 0 2	7.0 - 9.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
283	T-20 0 3	9.0 - 11.0	2.0	< 0.1	3.4	< 0.01	< 0.01	< 0.01	< 0.01	
284	T-20 0 4	11.0 - 12.0	1.0	< 0.1	1.6	0.03	< 0.01	< 0.01	< 0.01	
285	T-20 0 5	12.0 - 13.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
286	T-20 0 6	13.0 - 14.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
287	T-20 0 7	14.0 - 15.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
288	T-20 0 8	15.0 - 16.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
289	T-20 0 9	16.0 - 17.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
290	T-20 0 10	17.0 - 18.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
291	T-20 0 11	18.0 - 19.0	1.0	< 0.1	1.6	< 0.01	< 0.01	< 0.01	< 0.01	
292	T-20 0 12	19.0 - 20.0	1.0	< 0.1	9.6	0.02	< 0.01	< 0.01	< 0.01	
293	T-20 0 13	20.0 - 21.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
294	T-20 0 14	21.0 - 22.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
295	T-20 0 15	22.0 - 23.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
296	T-20 0 16	23.0 - 24.0	1.0	< 0.1	1.6	0.02	< 0.01	< 0.01	< 0.01	
297	T-20 0 17	24.0 - 25.0	1.0	< 0.1	6.8	0.03	< 0.01	< 0.01	< 0.01	
298	T-20 0 18	25.0 - 26.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
299	T-20 0 19	26.0 - 27.0	1.0	< 0.1	2.6	< 0.01	< 0.01	< 0.01	< 0.01	
300	T-20 0 20	27.0 - 28.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 11/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
301	T-20 0 21	28.0 - 29.0	1.0	< 0.1	4.4	< 0.01	< 0.01	< 0.01	< 0.01	
302	T-20 0 22	29.0 - 30.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
303	T-20 0 23	30.0 - 31.0	1.0	< 0.1	1.6	< 0.01	< 0.01	< 0.01	< 0.01	
304	T-20 0 24	31.0 - 32.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
305	T-20 0 25	32.0 - 33.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
306	T-20 0 26	33.0 - 34.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
307	T-20 0 27	34.0 - 35.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
308	T-20 0 28	35.0 - 36.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
309	T-20 0 29	36.0 - 37.0	1.0	0.5	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
310	T-20 0 30	37.0 - 39.0	2.0	< 0.1	3.2	0.04	< 0.01	< 0.01	< 0.01	
311	T-20 0 31	39.0 - 41.0	2.0	< 0.1	< 1	0.08	< 0.01	< 0.01	< 0.01	
312	T-20 0 32	41.0 - 43.0	2.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
313	T-21 0 1	4.6 - 6.0	1.4	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
314	T-21 0 2	6.0 - 7.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
315	T-21 0 3	7.0 - 8.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
316	T-21 0 4	8.0 - 9.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
317	T-21 0 5	9.0 - 10.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
318	T-21 0 6	10.0 - 11.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
319	T-21 0 7	11.0 - 12.0	1.0	0.1	< 1	0.01	< 0.01	< 0.01	0.02	
320	T-21 0 8	12.0 - 13.0	1.0	0.1	< 1	0.02	< 0.01	< 0.01	0.02	
321	T-21 0 9	13.0 - 14.0	1.0	0.3	2.2	< 0.01	< 0.01	< 0.01	0.06	
322	T-21 0 10	14.0 - 16.0	2.0	< 0.1	< 1	0.01	< 0.01	< 0.01	0.01	
323	T-21 0 11	16.0 - 18.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
324	T-21 0 12	18.0 - 20.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
325	T-21 0 13	20.0 - 22.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
326	T-21 0 14	22.0 - 24.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
327	T-21 0 15	24.0 - 26.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
328	T-21 0 16	26.0 - 28.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
329	T-21 0 17	28.0 - 30.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
330	T-21 0 18	30.0 - 32.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 12/22)

Ser. no.	Samp. no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
331	T-21 0 19	32.0 - 34.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
332	T-21 0 20	34.0 - 36.0	2.0	0.3	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
333	T-22 0 1	48.0 - 50.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
334	T-22 0 2	50.0 - 52.0	2.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
335	T-22 0 3	52.0 - 54.0	2.0	< 0.1	< 1	0.04	< 0.01	< 0.01	< 0.01	
336	T-22 0 4	54.0 - 55.0	1.0	< 0.1	< 1	0.04	< 0.01	< 0.01	< 0.01	
337	T-22 0 5	55.0 - 56.0	1.0	< 0.1	2.8	0.02	< 0.01	< 0.01	< 0.01	
338	T-22 0 6	56.0 - 57.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
339	T-22 0 7	57.0 - 58.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
340	T-22 0 8	58.0 - 59.0	1.0	< 0.1	< 1	0.03	< 0.01	< 0.01	< 0.01	
341	T-22 0 9	59.0 - 60.0	1.0	< 0.1	< 1	0.02	0.02	< 0.01	< 0.01	
342	T-22 0 10	60.0 - 61.0	1.0	0.1	4.8	0.04	< 0.01	< 0.01	< 0.01	
343	T-22 0 11	61.0 - 62.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
344	T-22 0 12	62.0 - 63.0	1.0	< 0.1	< 1	0.04	0.02	< 0.01	< 0.01	
345	T-22 0 13	63.0 - 64.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
346	T-22 0 14	64.0 - 66.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
347	T-22 0 15	66.0 - 68.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
348	T-22 0 16	68.0 - 70.0	2.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
349	T-22 0 17	70.0 - 72.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
350	T-22 0 18	72.0 - 74.0	2.0	< 0.1	< 1	0.02	0.02	< 0.01	< 0.01	
351	T-22 0 19	74.0 - 76.0	2.0	< 0.1	1.8	0.02	< 0.01	< 0.01	< 0.01	
352	T-22 0 20	112.0 - 114.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
353	T-22 0 21	114.0 - 115.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
354	T-22 0 22	115.0 - 116.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
355	T-22 0 23	116.0 - 117.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
356	T-22 0 24	117.0 - 118.0	1.0	< 0.1	1.6	< 0.01	< 0.01	< 0.01	< 0.01	
357	T-22 0 25	118.0 - 119.0	1.0	0.1	1.6	< 0.01	0.02	< 0.01	< 0.01	
358	T-22 0 26	119.0 - 120.0	1.0	0.3	< 1	0.09	0.02	< 0.01	< 0.01	
359	T-22 0 27	120.0 - 121.0	1.0	< 0.1	< 1	0.08	0.02	< 0.01	< 0.01	
360	T-22 0 28	121.0 - 122.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 13/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
361	T-22 0 29	122.0 - 124.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
362	T-22 0 30	124.0 - 126.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
363	T-22 0 31	126.0 - 128.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
364	T-22 0 32	128.0 - 129.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
365	T-22 0 33	129.0 - 130.0	1.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
366	T-22 0 34	130.0 - 131.0	1.0	< 0.1	3.6	0.02	0.01	< 0.01	< 0.01	
367	T-22 0 35	131.0 - 132.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
368	T-22 0 36	132.0 - 133.0	1.0	< 0.1	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
369	T-23 0 1	19.3 - 21.0	1.7	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
370	T-23 0 2	21.0 - 22.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
371	T-23 0 3	22.0 - 23.0	1.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
372	T-23 0 4	23.0 - 24.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
373	T-23 0 5	24.0 - 25.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
374	T-23 0 6	25.0 - 26.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
375	T-23 0 7	26.0 - 27.0	1.0	0.3	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
376	T-23 0 8	27.0 - 28.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
377	T-23 0 9	28.0 - 29.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
378	T-23 0 10	29.0 - 30.0	1.0	0.1	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
379	T-23 0 11	30.0 - 31.0	1.0	0.2	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
380	T-23 0 12	31.0 - 32.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
381	T-23 0 13	32.0 - 33.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
382	T-23 0 14	33.0 - 34.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
383	T-23 0 15	34.0 - 35.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
384	T-23 0 16	35.0 - 36.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
385	T-23 0 17	77.0 - 78.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
386	T-23 0 18	78.0 - 79.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
387	T-23 0 19	79.0 - 80.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
388	T-23 0 20	80.0 - 81.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
389	T-23 0 21	81.0 - 82.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
390	T-23 0 22	82.0 - 83.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 14/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
391	T-24 0 1	51.8 - 53.0	1.2	< 0.1	< 1	0.03	0.04	< 0.01	< 0.01	
392	T-24 0 2	53.0 - 54.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.01	
393	T-24 0 3	54.0 - 55.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
394	T-24 0 4	55.0 - 56.0	1.0	0.2	2.6	< 0.01	0.02	< 0.01	< 0.01	
395	T-24 0 5	56.0 - 57.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
396	T-24 0 6	57.0 - 58.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
397	T-24 0 7	58.0 - 59.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
398	T-24 0 8	59.0 - 60.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
399	T-24 0 9	60.0 - 61.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
400	T-24 0 10	61.0 - 62.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
401	T-24 0 11	62.0 - 63.0	1.0	0.5	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
402	T-24 0 12	63.0 - 64.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
403	T-24 0 13	64.0 - 65.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
404	T-24 0 14	65.0 - 66.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
405	T-24 0 15	66.0 - 68.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
406	T-24 0 16	68.0 - 70.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
407	T-24 0 17	70.0 - 72.0	2.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
408	T-25 0 1	25.0 - 26.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
409	T-25 0 2	26.0 - 27.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	0.02	
410	T-25 0 3	27.0 - 28.0	1.0	0.1	< 1	< 0.01	< 0.01	0.01	0.01	
411	T-25 0 4	28.0 - 29.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
412	T-25 0 5	29.0 - 30.0	1.0	0.3	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
413	T-25 0 6	30.0 - 31.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
414	T-25 0 7	31.0 - 32.0	1.0	< 0.1	< 1	< 0.01	< 0.01	0.01	< 0.01	
415	T-25 0 8	32.0 - 33.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
416	T-25 0 9	33.0 - 34.0	1.0	< 0.1	< 1	< 0.01	0.05	< 0.01	< 0.01	
417	T-25 0 10	34.0 - 36.0	2.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
418	T-25 0 11	36.0 - 38.0	2.0	0.1	3.4	< 0.01	< 0.01	< 0.01	< 0.01	
419	T-25 0 12	38.0 - 40.0	2.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
420	T-25 0 13	40.0 - 42.0	2.0	0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 15/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
421	T- 25 0 14	42.0 - 43.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
422	T- 25 0 15	43.0 - 44.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
423	T- 25 0 16	44.0 - 45.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
424	T- 25 0 17	45.0 - 46.0	1.0	0.3	< 1	< 0.01	0.01	< 0.01	< 0.01	
425	T- 25 0 18	46.0 - 47.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
426	T- 25 0 19	47.0 - 48.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
427	T- 25 0 20	48.0 - 49.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
428	T- 25 0 21	49.0 - 50.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
429	T- 25 0 22	50.0 - 51.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
430	T- 25 0 23	51.0 - 52.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
431	T- 25 0 24	52.0 - 53.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	0.01	
432	T- 25 0 25	53.0 - 54.0	1.0	0.2	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
433	T- 25 0 26	54.0 - 55.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
434	T- 25 0 27	55.0 - 56.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
435	T- 25 0 28	56.0 - 57.0	1.0	< 0.1	< 1	0.05	0.01	< 0.01	< 0.01	
436	T- 25 0 29	57.0 - 58.0	1.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
437	T- 25 0 30	58.0 - 59.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
438	T- 25 0 31	59.0 - 60.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
439	T- 25 0 32	60.0 - 61.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
440	T- 25 0 33	61.0 - 62.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
441	T- 25 0 34	62.0 - 63.0	1.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
442	T- 25 0 35	63.0 - 64.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
443	T- 25 0 36	64.0 - 65.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
444	T- 25 0 37	65.0 - 66.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
445	T- 25 0 38	66.0 - 67.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
446	T- 25 0 39	67.0 - 68.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
447	T- 25 0 40	68.0 - 69.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
448	T- 25 0 41	69.0 - 70.0	1.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
449	T- 25 0 42	70.0 - 71.0	1.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
450	T- 25 0 43	71.0 - 72.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 16/22)

Ser. no.	Samp. no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
451	T-25 0 44	72.0 - 73.0	1.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
452	T-25 0 45	73.0 - 74.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
453	T-25 0 46	74.0 - 75.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
454	T-25 0 47	75.0 - 76.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
455	T-25 0 48	76.0 - 77.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
456	T-25 0 49	77.0 - 78.0	1.0	0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
457	T-25 0 50	78.0 - 79.0	1.0	< 0.1	< 1	0.03	< 0.01	< 0.01	< 0.01	
458	T-25 0 51	79.0 - 80.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
459	T-25 0 52	80.0 - 81.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
460	T-25 0 53	81.0 - 82.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
461	T-26 0 1	-46.0 - -44.0	2.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
462	T-26 0 2	-44.0 - -42.0	2.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
463	T-26 0 3	-42.0 - -40.0	2.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
464	T-26 0 4	-40.0 - -38.0	2.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
465	T-26 0 5	-38.0 - -36.0	2.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
466	T-26 0 6	-36.0 - -34.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
467	T-26 0 7	-34.0 - -33.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
468	T-26 0 8	-33.0 - -32.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
469	T-26 0 9	-32.0 - -31.0	1.0	0.1	< 1	< 0.01	0.03	< 0.01	< 0.01	
470	T-26 0 10	-31.0 - -30.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
471	T-26 0 11	-30.0 - -29.0	1.0	0.8	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
472	T-26 0 12	-29.0 - -27.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
473	T-26 0 13	-27.0 - -25.0	2.0	< 0.1	< 1	< 0.01	0.03	< 0.01	< 0.01	
474	T-26 0 14	-25.0 - -24.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
475	T-26 0 15	-24.0 - -23.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
476	T-26 0 16	-23.0 - -22.0	1.0	< 0.1	1.8	< 0.01	0.02	< 0.01	< 0.01	
477	T-26 0 17	-22.0 - -21.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
478	T-26 0 18	-21.0 - -20.0	1.0	< 0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
479	T-26 0 19	-20.0 - -19.0	1.0	0.1	< 1	< 0.01	0.02	< 0.01	< 0.01	
480	T-26 0 20	-19.0 - -18.0	1.0	0.4	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutukan Trench 17/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
481	T-26 0 21	-18.0 - -17.0	1.0	< 0.1	< 1	0.09	< 0.01	< 0.01	< 0.01	
482	T-26 0 22	-17.0 - -16.0	1.0	0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
483	T-26 0 23	-16.0 - -15.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
484	T-26 0 24	-15.0 - -14.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
485	T-26 0 25	-14.0 - -12.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
486	T-26 0 26	-12.0 - -10.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
487	T-26 0 27	-10.0 - -8.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
488	T-26 0 28	-8.0 - -6.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
489	T-26 0 29	-6.0 - -4.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
490	T-26 0 30	5.0 - 7.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
491	T-26 0 31	7.0 - 9.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
492	T-26 0 32	9.0 - 11.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
493	T-26 0 33	11.0 - 13.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
494	T-26 0 34	13.0 - 15.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
495	T-26 0 35	15.0 - 17.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
496	T-26 0 36	17.0 - 19.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
497	T-26 0 37	19.0 - 21.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
498	T-26 0 38	21.0 - 23.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
499	T-26 0 39	70.0 - 72.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
500	T-26 0 40	72.0 - 74.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
501	T-26 0 41	74.0 - 76.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
502	T-26 0 42	76.0 - 78.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
503	T-26 0 43	78.0 - 80.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
504	P8 75 0 1	20.0 - 22.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
505	P8 75 0 2	22.0 - 24.0	2.0	0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
506	P8 75 0 3	24.0 - 26.0	2.0	< 0.1	< 1	0.05	0.07	< 0.01	< 0.01	
507	P8 75 0 4	26.0 - 28.0	2.0	0.3	< 1	0.01	< 0.01	< 0.01	< 0.01	
508	P8 75 0 5	28.0 - 30.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
509	P8 75 0 6	30.0 - 32.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
510	P8 75 0 7	32.0 - 34.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 18/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
511	P8 75 0 8	34.0 - 36.0	2.0	0.3	< 1	< 0.01	0.02	< 0.01	< 0.01	
512	P8 75 0 9	36.0 - 37.0	1.0	0.2	1.6	0.02	< 0.01	< 0.01	< 0.01	
513	P8 75 0 10	37.0 - 38.0	1.0	0.3	< 1	0.01	< 0.01	< 0.01	< 0.01	
514	P8 75 0 11	38.0 - 39.0	1.0	< 0.1	6.8	< 0.01	< 0.01	< 0.01	< 0.01	
515	P8 75 0 12	39.0 - 40.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
516	T-27 0 1	1.5 - 3.0	1.5	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
517	T-27 0 2	3.0 - 4.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
518	T-27 0 3	4.0 - 5.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
519	T-27 0 4	5.0 - 6.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
520	T-27 0 5	6.0 - 7.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
521	T-27 0 6	7.0 - 8.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
522	T-27 0 7	8.0 - 9.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
523	T-27 0 8	9.0 - 10.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
524	T-27 0 9	10.0 - 11.0	1.0	< 0.1	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
525	T-27 0 10	11.0 - 12.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
526	T-27 0 11	12.0 - 13.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
527	T-27 0 12	13.0 - 14.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
528	T-27 0 13	14.0 - 15.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
529	T-27 0 14	15.0 - 16.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
530	T-27 0 15	16.0 - 17.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
531	T-27 0 16	17.0 - 18.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
532	T-27 0 17	18.0 - 19.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	0.02	
533	T-27 0 18	19.0 - 20.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
534	T-27 0 19	20.0 - 21.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
535	T-27 0 20	21.0 - 22.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
536	T-27 0 21	22.0 - 23.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
537	T-27 0 22	23.0 - 24.0	1.0	0.5	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
538	T-27 0 23	24.0 - 25.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
539	T-27 0 24	25.0 - 26.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
540	T-27 0 25	26.0 - 27.0	1.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 19/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
541	T-27 0 26	27.0 - 28.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
542	T-27 0 27	28.0 - 29.0	1.0	0.2	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
543	T-27 0 28	29.0 - 30.0	1.0	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
544	T-27 0 29	30.0 - 31.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
545	T-27 0 30	31.0 - 32.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
546	T-27 0 31	32.0 - 33.0	1.0	< 0.1	< 1	0.03	< 0.01	< 0.01	< 0.01	
547	T-27 0 32	33.0 - 34.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
548	T-27 0 33	34.0 - 35.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
549	T-27 0 34	35.0 - 36.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
550	T-27 0 35	36.0 - 37.0	1.0	< 0.1	< 1	0.03	< 0.01	< 0.01	< 0.01	
551	T-27 0 36	37.0 - 38.0	1.0	< 0.1	< 1	0.05	< 0.01	< 0.01	< 0.01	
552	T-27 0 37	59.0 - 60.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
553	T-27 0 38	60.0 - 61.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
554	T-27 0 39	61.0 - 62.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
555	T-27 0 40	62.0 - 63.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
556	T-27 0 41	63.0 - 64.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
557	T-27 0 42	64.0 - 65.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
558	T-27 0 43	65.0 - 66.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
559	T-27 0 44	66.0 - 67.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
560	T-28 0 1	20.0 - 21.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
561	T-28 0 2	21.0 - 22.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
562	T-28 0 3	22.0 - 23.0	1.0	0.4	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
563	T-28 0 4	23.0 - 24.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
564	T-28 0 5	24.0 - 25.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
565	T-28 0 6	25.0 - 26.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
566	T-28 0 7	26.0 - 27.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
567	T-28 0 8	27.0 - 28.0	1.0	< 0.1	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
568	T-28 0 9	28.0 - 29.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
569	T-28 0 10	29.0 - 30.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
570	T-28 0 11	30.0 - 31.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 20/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
571	T-28 0 12	31.0 - 32.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
572	T-28 0 13	32.0 - 33.0	1.0	0.2	< 1	0.02	< 0.01	< 0.01	0.02	
573	T-28 0 14	33.0 - 34.0	1.0	< 0.1	12.8	0.03	< 0.01	< 0.01	0.04	
574	T-28 0 15	34.0 - 35.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	0.01	
575	T-28 0 16	35.0 - 36.0	1.0	< 0.1	< 1	0.05	< 0.01	< 0.01	< 0.01	
576	T-28 0 17	36.0 - 37.0	1.0	3.8	< 1	0.01	< 0.01	< 0.01	< 0.01	
577	T-28 0 18	37.0 - 38.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
578	T-28 0 19	38.0 - 39.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
579	T-28 0 20	39.0 - 40.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
580	T-28 0 21	40.0 - 41.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
581	T-28 0 22	41.0 - 43.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
582	T-28 0 23	43.0 - 45.0	2.0	< 0.1	1.2	0.02	< 0.01	< 0.01	< 0.01	
583	T-28 0 24	45.0 - 47.0	2.0	< 0.1	< 1	0.07	< 0.01	< 0.01	< 0.01	
584	T-28 0 25	47.0 - 49.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
585	T-28 0 26	49.0 - 51.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
586	T-28 0 27	51.0 - 53.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
587	T-28 0 28	53.0 - 55.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
588	T-28 0 29	55.0 - 57.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
589	T-28 0 30	57.0 - 59.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
590	T-28 0 31	59.0 - 61.0	2.0	< 0.1	< 1	0.04	< 0.01	< 0.01	< 0.01	
591	T-29 0 1	28.0 - 30.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
592	T-29 0 2	30.0 - 32.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
593	T-29 0 3	32.0 - 34.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
594	T-29 0 4	34.0 - 36.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
595	T-29 0 5	36.0 - 38.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
596	T-29 0 6	38.0 - 40.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
597	T-29 0 7	40.0 - 42.0	2.0	< 0.1	9.8	< 0.01	< 0.01	< 0.01	< 0.01	
598	T-29 0 8	42.0 - 44.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
599	T-29 0 9	44.0 - 46.0	2.0	< 0.1	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
600	T-29 0 10	46.0 - 48.0	2.0	0.3	< 1	0.02	< 0.01	< 0.01	0.01	

Appendix 2-6(1) Assay Results of Ore Samples(Bulutkan Trench 21/22)

Ser.no.	Samp.no.	Position(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
601	T-29 0 11	48.0 - 50.0	2.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
602	T-29 0 12	50.0 - 52.0	2.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
603	T-29 0 13	52.0 - 53.0	1.0	0.9	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
604	T-29 0 14	53.0 - 54.0	1.0	1.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
605	T-29 0 15	54.0 - 55.0	1.0	1.4	< 1	0.02	< 0.01	< 0.01	< 0.01	
606	T-29 0 16	55.0 - 56.0	1.0	0.5	< 1	0.03	< 0.01	0.01	< 0.01	
607	T-29 0 17	56.0 - 57.0	1.0	0.6	< 1	0.03	< 0.01	< 0.01	< 0.01	
608	T-29 0 18	57.0 - 58.0	1.0	0.2	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
609	T-29 0 19	58.0 - 59.0	1.0	0.2	6.8	0.02	< 0.01	< 0.01	< 0.01	
610	T-29 0 20	59.0 - 60.0	1.0	4.4	< 1	0.05	0.14	< 0.01	0.02	
611	T-29 0 21	60.0 - 61.0	1.0	2.4	< 1	0.06	0.07	< 0.01	< 0.01	
612	T-29 0 22	61.0 - 62.0	1.0	1.7	< 1	0.02	0.04	< 0.01	< 0.01	
613	T-29 0 23	62.0 - 63.0	1.0	0.7	< 1	0.01	< 0.01	< 0.01	< 0.01	
614	T-29 0 24	63.0 - 64.0	1.0	1.8	< 1	0.01	< 0.01	< 0.01	< 0.01	
615	T-29 0 25	64.0 - 65.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
616	T-29 0 26	65.0 - 66.0	1.0	0.1	< 1	0.05	< 0.01	< 0.01	< 0.01	
617	T-29 0 27	66.0 - 67.0	1.0	0.2	1.8	< 0.01	< 0.01	< 0.01	< 0.01	
618	T-29 0 28	67.0 - 68.0	1.0	< 0.1	< 1	0.05	< 0.01	< 0.01	< 0.01	
619	T-29 0 29	68.0 - 69.0	1.0	< 0.1	< 1	0.05	< 0.01	< 0.01	< 0.01	
620	T-29 0 30	69.0 - 70.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
621	T-29 0 31	70.0 - 71.0	1.0	< 0.1	< 1	0.03	< 0.01	< 0.01	< 0.01	
622	T-29 0 32	71.0 - 72.0	1.0	< 0.1	2.4	0.05	< 0.01	< 0.01	< 0.01	
623	T-29 0 33	72.0 - 73.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
624	T-29 0 34	73.0 - 74.0	1.0	0.1	< 1	< 0.01	< 0.01	< 0.01	0.01	
625	T-29 0 35	74.0 - 75.0	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	0.02	
626	T-29 0 36	75.0 - 76.0	1.0	0.1	< 1	0.03	< 0.01	< 0.01	0.02	
627	T-29 0 37	76.0 - 77.0	1.0	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
628	T-29 0 38	77.0 - 78.0	1.0	0.2	< 1	0.05	< 0.01	< 0.01	< 0.01	
629	T-29 0 39	78.0 - 79.0	1.0	0.6	< 1	0.03	< 0.01	< 0.01	< 0.01	
630	T-29 0 40	79.0 - 80.0	1.0	0.8	< 1	0.01	< 0.01	< 0.01	< 0.01	

Appendix 2-6(2) Assay Results of Ore Samples(Bulutkan Drillcore 1/19)

Ser.no.	Samp.no.	Depth(m)	Length(m)	Au(g/t)	Ag(g/t)	Cu(%)	As(%)	Mo(%)	W03(%)	Discriptions
1	B-801	4.9 - 7.0	2.1	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
2	B-802	7.0 - 9.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
3	B-803	9.0 - 11.0	2.0	0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
4	B-804	11.0 - 12.5	1.5	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
5	B-805	12.5 - 14.2	1.7	< 0.1	< 1	< 0.01	0.01	< 0.01	< 0.01	
6	B-806	14.2 - 15.0	0.8	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
7	B-807	15.0 - 16.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
8	B-808	16.0 - 17.0	1.0	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
9	B-809	17.0 - 18.1	1.1	0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
10	B-8010	18.1 - 19.3	1.2	1.1	1.8	0.03	< 0.01	< 0.01	< 0.01	
11	B-8011	19.3 - 20.3	1.0	< 0.1	< 1	0.11	0.08	< 0.01	< 0.01	
12	B-8012	20.3 - 21.5	1.2	< 0.1	< 1	0.06	< 0.01	< 0.01	< 0.01	
13	B-8013	21.5 - 22.6	1.1	< 0.1	< 1	0.02	< 0.01	< 0.01	< 0.01	
14	B-8014	22.6 - 23.4	0.8	0.1	< 1	0.38	< 0.01	< 0.01	< 0.01	
15	B-8015	23.4 - 24.7	1.3	< 0.1	< 1	0.11	< 0.01	< 0.01	< 0.01	
16	B-8016	24.7 - 26.1	1.4	< 0.1	< 1	0.03	< 0.01	0.01	< 0.01	
17	B-8017	26.1 - 27.7	1.6	< 0.1	< 1	0.12	< 0.01	< 0.01	< 0.01	
18	B-8018	27.7 - 29.0	1.3	12	11.4	0.14	< 0.01	< 0.01	0.05	
19	B-8019	29.0 - 30.0	1.0	4	3.2	0.1	0.02	< 0.01	< 0.01	
20	B-8020	30.0 - 31.0	1.0	< 0.1	< 1	0.05	< 0.01	0.01	< 0.01	
21	B-8021	31.0 - 32.1	1.1	0.2	< 1	0.09	< 0.01	< 0.01	< 0.01	
22	B-8022	32.1 - 33.5	1.4	0.6	2.2	0.03	< 0.01	< 0.01	< 0.01	
23	B-8023	33.5 - 34.6	1.1	0.3	< 1	0.03	< 0.01	0.01	< 0.01	
24	B-8024	34.6 - 35.5	0.9	1.1	1.4	0.1	< 0.01	< 0.01	< 0.01	
25	B-8025	35.5 - 36.4	0.9	6.4	6.8	0.15	< 0.01	< 0.01	< 0.01	
26	B-8026	36.4 - 37.4	1.0	2.8	1.6	0.02	< 0.01	< 0.01	< 0.01	
27	B-901	4.5 - 5.5	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
28	B-902	5.5 - 6.5	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	
29	B-903	6.5 - 7.8	1.3	< 0.1	< 1	< 0.01	< 0.01	< 0.01	< 0.01	
30	B-904	7.8 - 8.8	1.0	< 0.1	< 1	0.01	< 0.01	< 0.01	< 0.01	