

Fig. 2-55 Contour Map of Apparent Resistivity in the Ngan Me Area (16 Hz)




Fig. 2-56 Resistivity Structure Section (1-D, Line N-1 to N-4)







Fig. 2-57 Resistivity Structure Section (1-D, Line N-5 to N-8)




Fig. 2-58 Resistivity Structure Section (1-D, Line N-1 to N-4)





Fig. 2-59 Resistivity Structure Section (1-D, Line N-5 to N-8)




Fig. 2-60 Resistivity Structure Map in the Ngan Me Area (2-D, SL 100 m)




Fig. 2-61 Resistivity Structure Map in the Ngan Me Area (2-D, SL 0 m)




Fig. 2-62 Resistivity Structure Map in the Ngan Me Area (2-D, SL -200 m)

0

0

0

5-3-4 Laboratory Test

The results of the laboratory test are shown in Table 2-14. The mean values of resistivity and chargeability for each rock are as follows.

Rock	Resistivity (ohm-m)	Chargeability (ms)
Quartz vein	16,919	25.9
Claystone · Siltstone	646	3.9
Shale	1,389	9.8
Sandstone	2,602	13.6
Phyllite	1,726	12.1
Schists	1,716	12.1
Granite	1,734	13.5

The laboratory test offered the result matched to the CSAMT data that the resistivity of the rock samples are higher than 1,000 ohm-m except claystone and siltstone. Especially, the resistivity of the quartz vein is a figure higher (more than 10,000 ohm-m) than that of the other rocks. However, the resistivity of the quartz vein varies widely, depending on the condition of fissures. The samples containing few fissures measured higher than 10,000 ohm-m, while the samples containing remarkable fissures measured a figure lower (about 2,000 ohm-m). The sandstone and schists of the host rock had high resistivity of about 2,000 ohm-m. The granite had the same value as the host rock. However, the samples of the granite were weathered and cataclastic. Thus, the resistivity of the fresh rock in the deep zone will be still higher. Claystone and siltstone were the lowest (about 600 ohm-m) of the rocks in the survey areas. A low resistivity of 600 ohm-m existed in the shale also.

The chargeability of the samples measured about 10 ms except the quartz vein. The mean value of the quartz vein is 25.9 ms. However, the chargeability of the quartz vein varies widely, depending on the existence of pyrite. The samples containing no pyrite measured several ms, while the samples containing pyrite measured the largest of 96 ms. Relatively large chargeability of about 20 ms existed in phyllite and schists. The graphite schist measured small (5.6 ms) in chargeability. This small chargeability is due to the sample containing few amounts of graphite. The laboratory test gave the obvious contrast between the quartz vein containing pyrite and the other rocks in the survey areas.

Table 2-15 Results of Laboratory Test

No.	Rock	Resistivity ohm-m	Chargeability ms	Remarks
1	Quartz vein	2,962	2.0	limonite diss., porous
2	Quartz vein	1,617	96.0	Py diss., porous
3	Quartz vine	27,539	5.4	limonite diss., porous
4	Quartzite	35,558	0.1	
	Average Value	16,919	25.9	
5	Claystone	689	2.9	
6	Claystone	782	5.0	
7	Siltstone	524	3.8	
8	Siltstone	590	3.9	
	Average Value	646	3.9	
9	Shale	627	23.4	
10	Shale	1,313	4.1	
11	Shale	2,228	2.0	
	Average Value	1,389	9.8	
12	Sandstone	2,685	10.2	sericit
13	Sandstone	905	6.5	
14	Sandstone	2,917	12.3	
15	Sandstone	3,567	19.6	reddish brown
16	Sandstone	2,934	19.3	reddish brown
	Average Value	2,602	13.6	
17	Phyllite	2,220	20.4	
18	Phyllite	1,012	4.0	
19	Phyllite	1,947	12.0	
	Average Value	1,726	12.1	
20	Schist	871	11.5	
21	Sericite schist	1,371	3.7	
22	Sericite schist	1,238	3.1	
23	Graphite schist	3,385	5.6	
	Average Value	1,716	6.0	
24	Granite	1,833	12.9	weathered, cataclastic
25	Granite	1,635	14.0	weathered, cataclastic
	Average Value	1,734	13.5	

5-4 Discussion

(1) Resistivity Features

The laboratory test results and geologic information led to the following resistivity features about the rocks and geologic structure in the survey areas.

1) High Resistivity

In the survey areas, the group of quartz veins and the granite are assumed to form higher resistivity than the host rock.

The quartz vein containing few fissures is extremely high (more than 10,000 ohm-m) in resistivity. However, it is very difficult to extract narrow high resistivity zone in width by this measurement system. In the case of the zone where many quartz veins are concentrated (the group of quartz veins), it is sufficiently possible to extract a high resistivity zone related to quartz veins. MT method is not much sensitive to high resistivity. Thus, the width of the group of quartz veins is expected to be more than 100 m if a high resistivity zone related to quartz veins is extracted by this measurement system. When fractures develop in the group of quartz veins, it is possible that the resistivity of the group is lowered and a high resistivity zone related to quartz veins is not extracted.

When the samples of granite were weathered and cataclastic, they had the same resistivity (1,734 ohm-m) as the host rock. When the granite is fresh in deep zone, it seems that granite is several times higher in resistivity and a high resistivity area related to granite is extracted.

The laboratory test shows that the existence of the other rocks might not form higher resistivity.

2) Low Resistivity

In the survey areas, claystone and siltstone, fracture zone and the layer containing graphite are assumed to form lower resistivity than the host rock.

The laboratory test showed that claystone, siltstone and one of the shale had the lowest resistivity (about 600 ohm-m). When fractures exist in these rocks, they lower further their resistivity..

In fracture zones, low resistivity zones are generally extracted, because they are high permeable (high conductible) . Many of fracture zones have a figure lower resistivity less than host rock.

Graphite has extremely low resistivity less than several ohm-m. The resistivity of the layer containing graphite is lowered depending on its content.

(2) Relations to Geologic Structure

The figure arranged the resistivity structure sections (2-D analysis) in the sequence of the lines is shown in Fig. 2-63 to grasp three dimensional resistivity structure. The followings are the geological interpretation to resistivity structure on the basis of the above resistivity features.

1) Da Mai Area

Resistivity structure : The high resistivity areas are distributed broadly below about 300 m from the surface. The high resistivity zones towards the surface were detected and at the Nos. 7 and 8 on lines D-3 to D-5, and in the southern part of lines D-7 to D-9.

Interpretation: The high resistivity areas in the deep zone seem to be reflected by the distribution of granite. The high resistivity zones seem to result from the group of quartz veins or the stock of granite. They are expected to be relatively steep and extend to the deep zone.

2) Gang Area

Resistivity structure : It is layered structure - NW-SE strike with 20 to 30 degree S dip. The high resistivity layer is distributed in the shallow zone and the low resistivity layer is distributed in the deep zone. In the shallow zone, the high resistivity zones more than 5,000 ohm-m were detected in the southern part of lines G-5 to G-7, the middle part of lines G-3 to G-4, and the northern part of lines G-4 to G-7. These high resistivity zones do not extend to the deeper zone.

Interpretation: The strike and dip of the resistivity structure matches with those of the geologic structure. The high resistivity zones in the shallow zone seems to result from the group of quartz veins. They will have gentle dip, since they are distributed rather broadly in the shallow zone. The low resistivity layer is considered the layer composed of claystone, siltstone, shale or the layer containing graphite. In the case of the former, fractures will develop in the layer because of the existence of the low resistivity zones less than 50 ohm-m. In the case of the latter, a considerable amount of graphite will be involved.

3) Ngan Ma Area

Resistivity structure :The resistivity is lowest of the three areas. The low resistivity areas in the western part will continue from the eastern part of Gang area. The high resistivity zones were detected in the southern part of line N-5 and the middle part of line N-2. The high resistivity zone in the southern part of line N-5 extends to the deeper zone. The vertical zone with low resistivity less than 50 ohm-m was detected from No. 8 on line N-1 to No. 10 on line N-2.

Interpretation: Since the host rocks in this area is relatively low, the high resistivity zone related to quartz veins is assumed to be extracted apparently smaller than in the other areas. The high resistivity zones noted above seems to result from the group of quartz veins. Especially, the zone in the southern part of line N-5 extends to the deeper zone with steep dip and is expected to extend to the east. The low resistivity zone seems to be attributed to fracture zone.

(3) IP Method

The laboratory test results gave the obvious contrast between the quartz vein containing pyrite and the other rocks in the survey areas. When the IP method is applied to this areas, it is graphite that adversely affects the data. The laboratory test showed that the IP effect is small, in the case of containing few amounts of graphite. If a layer contains a considerable amount of graphite, the CSAMT method sensitive to low resistivity should extract a low resistivity area because of the extremely low resistivity (less than several ohm-m) of graphite.

Consequently, it is considered that the high resistivity zones extracted by this survey contain few amounts of graphite and IP response is little affected in these zones. Thus, the IP method is available for these high resistivity zones in order to delineate prospective parts.

Since the CSAMT method is not much sensitive to high resistivity and this measurement was carried out with the potential electrode spacing of 100 m, the resistivity distribution related to the mineralization was not able to determine with sufficient accuracy. From this standpoint also, it is significant to carry out the IP method sensitive to high resistivity with high density.

1. The first part of the document discusses the importance of maintaining accurate records of all transactions. It emphasizes that proper record-keeping is essential for financial transparency and accountability. The text outlines various methods for recording transactions, including manual entry and the use of accounting software. It also highlights the need for regular audits to ensure the accuracy of the records.

0

2. The second part of the document focuses on the role of management in ensuring the success of the organization. It discusses the importance of setting clear goals and objectives, and the need for effective communication and collaboration among team members. The text also addresses the challenges of managing a diverse workforce and the importance of providing ongoing training and development opportunities. It concludes by emphasizing the need for a strong leadership team to guide the organization through times of change and uncertainty.

0

3. The third part of the document discusses the importance of maintaining a strong relationship with customers. It emphasizes that customer satisfaction is a key driver of business success, and that companies should strive to provide exceptional service and support. The text outlines various strategies for building customer loyalty, such as offering personalized products and services, and providing prompt and helpful customer support. It also discusses the importance of monitoring customer feedback and using it to improve the company's offerings.

0




Fig. 2-63 Results of the CSAMT Analysis

**PART III CONCLUSIONS AND
RECOMMENDATIONS**

PART III CONCLUSIONS AND RECOMMENDATIONS

Chapter 1 Conclusions

On the basis of the results of the first phase works comprising regional geological survey, stream sediment geochemical survey, panning survey, detailed geological survey and CSAMT geophysical survey, the following conclusions are obtained.

(1) Regional Geology and Geologic Structure

The distribution of six major stratigraphic units from the Cambrian to the Quaternary systems consisting of 14 formations was surveyed and the geologic map of 1:50,000 scale was prepared in the Bo Cu area by the regional geological survey this phase. Geosstructurally, the survey area is characterized by a series of anticlines and synclines called Bac Son anticlinorium whose axes orientate from NE, ENE to WNW. The Bo Cu anticline, whose axis trends WNW-ESE, is defined in the western part of the survey area where gold mineralization is extensively developed. Three major fault systems were distinguished in the survey area: NW, N-S, and NE systems. The main orogenic activity which resulted in the regional folding and tectonic faults in the Bo Cu area is interpreted to be occurred in the Triassic or later period. Small stocks of granite were found at the northern part of the survey area. The nature of this granite is discussed based on the whole rock analysis. It is concluded that this granite belongs to the granitoids of the magnetite series and of the S-type intruded at the marginal zone of the South China plate.

(2) Galena Mineralization

Regarding metallic mineral deposits in the Bo Cu area, two significant mineralizations, gold-bearing quartz veins and galena veins, were recognized. The galena veins occur mostly in the Carboniferous-Permian limestone. Several galena showings were found in the course of the regional geological survey and geochemical exploration. Some of them contain a significant amount of lead and silver. The similarity of geology and mineralization is discussed with the galena deposit in the Cho Dien area which is a famous Pb-Zn district in the northern Vietnam. The potential of galena resources in the Bo Cu area is estimated to be small from the survey results. As for the other mineral resources, a sedimentary phosphorite seam and a couple of magnetite lenses, both are considered to be small for that type of deposit, are known within the survey area.

(3) Gold Mineralization

Gold-bearing quartz veins occur extensively in the western part of the Bo Cu area. Although the width of each vein is not magnificent, they sometimes occur together forming a vein zone of 100-300 m wide and 500-1,000 m long. The system of quartz veins and the nature of gold mineralization were investigated by the detailed geological survey. On the basis

of the results of studies such as geologic environment, ore and gangue mineralogy, alteration, chemical analysis and fluid inclusion, it is interpreted that the type of mineralization is mesothermal gold vein hosted by sedimentary and metamorphic rocks of the Cambrian Mo Dong and Than Sa Formations. Two vein systems were distinguished by means of the stereo net analysis. One is N80°E with steeply dipping S, and another is E-W with gently dipping S. The veins occur on the wing of the Bo Cu anticline, and it is interpreted that the formation of veins is controlled structurally by the regional folding activity started probably from the Triassic period. According to the detailed geological survey together with the results of geochemical exploration, three areas for gold-bearing quartz veins have been examined, and potential for each area is preliminary evaluated. It is not likely to occur a big scale deposit in this area when seeing from the relative narrow and low grade quartz veins as well as the scale and intensity of geochemical anomalies. Among three areas and their extensions, Da Mai-Khe Dul and Ba Khe are promising prospects for gold resources.

(4) Geophysical Survey

The resistivity of the survey areas are high as a whole. The resistivity structure matches with the geologic structure. Especially, the Da Mai area has higher resistivity than the other areas and the high resistivity areas suggesting the distribution of granite were detected broadly below about 300m from the surface. With reference to the mineralized zone, the high resistivity zones resulting from the group of quartz veins more than 100m in width were extracted. The known prospects related to these zones and their features are as follows:

Da Mai area

- No.7 and 8 on lines D-3 to D-5 (Da Mai, extension to deep zone, steep dip)
- Southern part of lines D-7 to D-9 (Goc Sen, extension to deep zone, steep dip)

Gang Area

- Southern part of lines G-5 to G-7 (Khe Gang, shallow zone, gentle dip)
- Middle part of lines G-3 to G-4 (Khe Gang, shallow zone, gentle dip)
- Northern part of lines G-4 to G-7 (no known prospects in the vicinity, shallow zone, gentle dip)

Ngan Me area

- Southern part of line N-5 (Ba Khe, extension to deep zone and east, steep dip)
- Middle part of lines N-2 (Ba Khe, shallow zone)

The laboratory test results gave the obvious contrast between the quartz vein containing pyrite and the other rocks in the survey areas. IP method is available for the high

resistivity zones extracted by this survey in order to delineate prospective parts, because these zones seem to contain few amounts of graphite.

(5) Da Mai-Khe Dui Prospect

The distribution of gold mineralization in the Da Mai-Khe Dui prospect is approximately 200-300 m wide and more than 1 km long. Gold-bearing quartz veins in the Da Mai-Khe Dui prospect are characterized by the vein trend of steeply dipping S. A significant amount of sulfide minerals is contained in the vein. Assay results by the GSV survey were significant this prospect. The mining activity by local people there is already at the waning stage. High grade ores near the surface were nearly mined out. However it still has significant gold resources in the deeper part and the extensions. The gold mineralization is expected to extend to the east through the Northeast of N. Bo Cu until Khe Ma gold anomalous zones for approximately 5 km. Remarkable Au anomalies of stream sediments and some gold anomalies of pan concentrates were found in the Northeast of N. Bo Cu and Khe Ma this phase.

(6) Ba Khe Prospect

The Ba Khe prospect in the Ngan Me area is understood to be another target for the further exploration. Adits and inclined shafts are distributed for about 900 m along the creek. Two systems of veins, E-W with steeply dipping S and E-W with gently dipping S, occur together in this prospect. The width of veins changes variously; some part shows a lens-like shape. Branching and joining of veins are frequently observed. Although assay results of ore samples were rather disappointing this time, the visible gold occasionally occurs in some part of quartz veins. The activities of local miners are limited above the ground water level. The gold mineralization is likely to extend both westwards to the West Ba Khe creek and eastwards to the Bai Vang gold anomalous zone for approximately 3.5 km. In Bai Vang, a couple of significant Au anomalies in stream sediments and tens of gold anomalies of pan concentrates were detected this phase.

(7) Other Prospects

The Cay Thi and its surrounding zone in the Gang area also have some potential for gold resources. Two zones of veins both are gently dipping S occur in this prospect. These two zones run parallel each other at 40 m apart vertically. Several significant assay results were obtained this phase. The other interesting gold prospects in the Gang area are Khe Gang and Khe Hoac. Gold-bearing quartz veins in these prospects show similar trend and nature as in the Cay Thi prospect.

Chapter 2 Recommendations for the Second Phase Survey

Da Mai-Khe Dui Prospect

It is recommended that the detailed survey comprising IP survey and geological survey (including trenching and geochemical rock-chip survey) shall be made in this prospect and its eastern extension for the purpose of defining the drill target. After the detailed survey, a reconnaissance drilling for testing the IP anomalies shall be made.

Ba Khe Prospect

A detailed survey comprising IP survey and geological survey (including trenching and geochemical rock-chip survey) is recommended in the Ba Khe prospect and its extensions in the next phase. The purpose of this survey is to define the drill target for the further exploration.

REFERENCES

- Caniar, L., 1953, Basic theory of the magnetotellurics method of geophysical prospecting: *Geophysics*, v.37, p.605-635.
- Chappell, B.W., and White, A.J.R., 1974, Two contrasting granite types: *Pacific Geol.*, v.8, p.173-174.
- General Department of Mines and Geology, the Socialist Republic of Vietnam, 1988, *Geology and Mineral Resources of Vietnam: Mineral Resources Development Series, v.1*, Hanoi, 217p.
- General Department of Mines and Geology, the Socialist Republic of Vietnam, 1990, *Geology and Mineral Resources of Vietnam: Mineral Resources Development Series, v.1, 2nd Edition*, Hanoi, 182p.
- General Department of Mines and Geology, the Socialist Republic of Vietnam, 1988, *Geological Map of Vietnam: scale 1:500,000*, Hanoi.
- Geological Survey of Vietnam, 1991, *Geology of Cambodia, Lao and Vietnam: Explanatory note to the geological map of Cambodia, Lao and Vietnam at 1:1,000,000 scale, 2nd Edition*, Hanoi, 157p.
- Goldstein, M.A., and Strangway, D.W., 1975, Audio frequency magnetotellurics with a grounded electric dipole source: *Geophysics*, v.40, p.669-683.
- Ishihara, S., 1977, The magnetite-series and ilmenite-series granitic rocks: *Mining Geol.*, v.27, p.293-305.
- Kaufman, A.A., and Keller, G.V., 1981, *The magnetotelluric sounding method*: Elsevier, 595p.
- Ogawa, Y., 1988, Fortran program codes for two-dimensional magnetotelluric forward and inverse analysis: *Open File Report Geol. Surv. Japan*, n.59.
- Strangway, D.W., Swift, C.M. and Holmer, R.C., 1973, The application of audio frequency magnetotellurics (AMT) to mineral exploration: *Geophysics*, v.38, p.1159-1175.
- Takahashi, M., Aramaki, S., and Ishihara, S., 1980, Magnetite-series/ilmenite-series vs. I-type/S-type granitoids: *Mining Geol. Special Issue*, n.8, p.13-28.

Uchida,T., 1993, Smooth 2-D inversion for magnetotelluric data based on statistical Criterion
ABIC: J. Geomag. Geoelectr., v.45, p.841-858.


United Nations Economic and Social Commission for Asia and the Pacific, 1990, Atlas of
Mineral Resources of the ESCAP Region: v.6, Vietnam explanatory brochure, Bangkok, 124p.

Workman, D.R., 1977, Geology of Laos, Cambodia, South Vietnam and the Eastern Part of
Thailand: Overseas Geology and Mineral Resources, n.50, Natural Environment Research
Council, Institute of Geological Science, London, 34p.

Zonge Engineering and Reserch Organization,INC. ,1982, Interpretation guide for CSAMT
data.

PHOTOGRAPHS

Photo. 1 Photomicrographs of Thin Sections




Rock Name : Granite (T-C_g)
Sample No. : C025T
Locality : Mo Nhai
(Crossed Nicol)




Rock Name : Sericite Schist (C_{md})
Sample No. : D454T
Locality : Da Mai
(Crossed Nicol)

Abbreviations: Qz; Quartz, Pl; Plagioclase, Kf, Potash Feldspar
Hb; Hornblende, Px; Pyroxene, Ch; Chlorite



Rock Name : Rhyolite (T_{1.2st})
Sample No. : D183T
Locality : Ban It
(Crossed Nicol)



Rock Name : Tuff (T_{1.2st})
Sample No. : A212T
Locality : Song Trung
(Crossed Nicol)


Abbreviations: Qz; Quartz, Pl; Plagioclase, Kf; Potash Feldspar
Hb; Hornblende, Px; Pyroxene, Ch; Chlorite

()

Photo. 2 Photomicrographs of Ores

()

()




Minerals : Py-Au
Sample No. : C043M
Locality : Bai Vang
(Open Nicol)



Minerals : As-Au
Sample No. : D444M
Locality : Goc Sen
(Open Nicol)

Abbreviations: Py; Pyrite, As; Arsenopyrite, Po; Pyrrhotite
Cp; Chalcopyrite, Au; Native Gold



Minerals : Py, Au
Sample No. : A255M
Locality : Ba Khe
(Open Nicol)



Minerals : Cp-Po
Sample No. : B007M
Locality : Da Mai
(Open Nicol)


Abbreviations: Py; Pyrite, As; Arsenopyrite, Po; Pyrrhotite
Cp; Chalcopyrite, Au; Native Gold

()


Photo. 3 Photomicrographs of Fluid Inclusions

()


()




Inclusion Type : Two-phase
Sample No. : D419F
Locality : Ngan Me



Inclusion Type : Liquid-rich (CO₂)
Sample No. : D420F
Locality : Ngan Me



Inclusion Type : Liquid-rich
Sample No. : D391F
Locality : Khe Gang



Inclusion Type : Poly-phase
Sample No. : D376F
Locality : Khe Hoac

APPENDICES

**App. 1 Analytical Results of Stream Sediment
Samples**

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
A001	12	<0.2	17	16	23	<1	9	<0.03
A002	9	<0.2	31	14	24	<1	21	<0.03
A003	4	<0.2	17	13	19	<1	5	<0.03
A004	10	<0.2	19	14	21	1	7	<0.03
A005	22	<0.2	17	14	22	5	6	<0.03
A006	16	<0.2	15	140	19	<1	6	<0.03
A007	11	<0.2	24	19	27	<1	8	<0.03
A008	8	<0.2	15	15	23	4	4	<0.03
A009	9	<0.2	18	16	26	<1	5	<0.03
A010	12	<0.2	20	17	23	2	7	<0.03
A011	14	<0.2	14	15	20	1	4	<0.03
A012	4	<0.2	13	18	23	<1	4	<0.03
A013	7	<0.2	14	17	19	2	8	<0.03
A014	11	<0.2	21	23	37	<1	5	<0.03
A015	13	<0.2	31	26	40	6	11	<0.03
A016	6	0.6	22	25	38	<1	6	<0.03
A017	13	0.4	30	36	42	3	14	<0.03
A018	5	<0.2	10	15	21	<1	2	<0.03
A019	7	<0.2	15	21	31	<1	3	<0.03
A020	11	<0.2	23	22	35	6	12	<0.03
A021	10	<0.2	17	20	37	1	6	<0.03
A022	8	<0.2	21	20	35	3	5	<0.03
A023	9	<0.2	27	25	39	8	9	<0.03
A024	10	<0.2	23	25	37	1	7	<0.03
A025	14	0.3	30	25	44	6	12	<0.03
A026	10	0.5	24	24	39	2	11	<0.03
A027	12	0.4	24	25	40	<1	8	<0.03
A028	9	<0.2	19	50	37	3	14	<0.03
A029	5	0.3	10	38	32	7	4	<0.03
A030	6	<0.2	30	80	48	7	22	<0.03
A031	5	<0.2	32	66	44	11	19	<0.03
A032	7	<0.2	10	60	34	9	5	<0.03
A033	6	<0.2	15	64	40	8	7	<0.03
A034	5	<0.2	5	58	29	8	34	<0.03
A035	6	<0.2	13	17	19	5	13	<0.03
A036	6	<0.2	10	83	41	8	6	<0.03
A037	16	<0.2	8	59	30	9	4	0.03
A038	5	<0.2	12	64	35	6	9	<0.03
A039	4	<0.2	8	63	35	12	4	<0.03
A040	5	<0.2	21	127	40	6	15	<0.03
A041	3	<0.2	13	15	16	8	13	<0.03
A042	2	<0.2	22	112	49	16	17	<0.03
A043	4	<0.2	16	111	238	12	7	<0.03
A044	29	0.3	25	138	47	12	17	<0.03
A045	2	<0.2	15	151	51	15	6	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
A046	9	<0.2	22	168	49	16	10	<0.03
A047	4	<0.2	17	136	52	16	8	<0.03
A048	4	<0.2	11	17	14	16	7	<0.03
A049	5	<0.2	14	21	14	27	12	<0.03
A050	3	<0.2	24	257	86	21	10	<0.03
A051	3	<0.2	23	326	81	23	17	<0.03
A052	3	<0.2	28	314	97	23	18	<0.03
A053	25	0.8	105	8,725	878	220	49	0.06
A054	23	1.0	111	9,925	922	271	54	0.05
A055	4	<0.2	18	54	54	18	15	<0.03
A056	2	<0.2	16	63	80	15	13	<0.03
A057	3	<0.2	13	94	100	11	8	<0.03
A058	5	0.7	23	296	246	18	11	<0.03
A059	3	<0.2	11	36	32	8	5	<0.03
A060	7	<0.2	41	41	73	<1	2	<0.03
A061	7	<0.2	26	15	30	8	18	<0.03
A062	8	<0.2	44	37	75	<1	<1	<0.03
A063	5	<0.2	30	25	45	5	14	<0.03
A064	4	<0.2	22	18	31	11	15	<0.03
A065	8	<0.2	39	41	123	7	7	0.10
A066	6	<0.2	40	39	122	5	9	<0.03
A067	7	<0.2	38	41	111	6	8	<0.03
A068	14	<0.2	42	46	161	12	14	<0.03
A069	8	<0.2	43	44	155	15	15	<0.03
A070	12	<0.2	43	47	161	6	13	<0.03
A071	7	<0.2	39	40	127	9	10	0.16
A072	12	<0.2	42	43	109	<1	10	<0.03
A073	8	<0.2	39	43	139	6	10	<0.03
A074	8	<0.2	37	41	126	2	9	<0.03
A075	8	<0.2	34	31	64	<1	2	<0.03
A076	14	<0.2	44	35	84	<1	<1	<0.03
A077	8	<0.2	42	34	81	<1	2	<0.03
A078	7	<0.2	39	34	82	<1	2	<0.03
A079	7	<0.2	48	52	87	<1	5	0.04
A080	4	<0.2	30	51	78	6	9	0.48
A081	6	<0.2	39	46	122	4	6	<0.03
A082	3	<0.2	47	53	191	8	15	0.03
A083	6	<0.2	43	54	178	10	17	0.03
A086	5	<0.2	43	54	152	8	13	<0.03
A087	5	<0.2	55	54	129	<1	<1	0.03
A088	4	<0.2	51	62	225	22	34	<0.03
A089	8	<0.2	46	56	159	8	14	0.03
A090	5	<0.2	50	74	174	12	14	0.04
A091	6	<0.2	51	59	156	7	17	0.05
A092	10	<0.2	34	46	96	<1	<1	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
A093	9	<0.2	37	44	118	2	7	<0.03
A094	64	<0.2	42	45	133	2	4	<0.03
A095	15	<0.2	50	44	93	<1	<1	<0.03
A096	11	<0.2	51	53	106	<1	6	<0.03
A097	18	<0.2	46	56	147	<1	3	0.21
A098	14	<0.2	36	55	110	<1	4	<0.03
A099	7	<0.2	35	52	106	<1	8	<0.03
A100	3	<0.2	38	59	122	7	13	<0.03
A101	6	<0.2	41	66	113	<1	10	<0.03
A102	11	<0.2	40	53	168	7	9	<0.03
A103	8	<0.2	46	59	196	7	8	<0.03
A104	7	<0.2	36	53	59	<1	18	0.05
A105	9	<0.2	42	112	79	16	18	<0.03
A106	5	<0.2	33	70	81	9	9	0.07
A107	23	<0.2	56	104	208	5	5	0.03
A108	8	<0.2	49	91	111	<1	<1	0.03
A109	5	<0.2	36	58	95	6	5	<0.03
A110	11	<0.2	41	73	161	8	2	0.03
A111	4	<0.2	22	36	60	10	11	0.04
A112	7	<0.2	26	43	73	15	19	0.05
A113	5	<0.2	23	36	88	8	7	0.10
A114	3	<0.2	23	42	84	16	13	0.05
A115	7	<0.2	27	43	95	3	8	0.05
A116	5	<0.2	31	69	168	<1	6	0.09
A117	4	<0.2	31	70	155	10	14	0.08
A118	12	<0.2	40	215	314	8	8	0.10
A119	5	<0.2	26	51	103	4	10	0.04
A120	12	<0.2	25	53	91	7	10	0.03
A121	3	<0.2	19	41	76	4	6	<0.03
A122	5	<0.2	32	80	149	<1	10	0.04
A123	5	<0.2	25	61	122	<1	7	0.06
A124	14	<0.2	50	143	422	<1	<1	0.25
A125	8	<0.2	38	98	180	5	23	0.05
A126	12	<0.2	48	133	219	10	25	0.26
A127	10	<0.2	34	97	146	13	23	0.08
A128	11	<0.2	37	122	195	7	14	0.08
A129	7	<0.2	37	83	152	8	19	0.04
A130	5	<0.2	21	26	18	12	11	<0.03
A131	3	<0.2	24	28	19	8	12	0.09
A132	4	<0.2	24	26	18	8	12	0.07
A133	4	<0.2	22	31	15	7	10	<0.03
A134	6	<0.2	25	36	27	19	19	<0.03
A135	4	<0.2	25	32	25	4	10	<0.03
A136	3	<0.2	21	28	17	16	12	<0.03
A137	3	<0.2	19	33	15	16	9	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
A138	5	<0.2	20	26	14	19	13	<0.03
A148	5	<0.2	25	31	25	12	6	<0.03
A149	6	<0.2	39	55	68	9	8	<0.03
A150	5	<0.2	31	57	55	15	13	<0.03
A151	13	<0.2	28	50	53	<1	3	0.03
A152	5	<0.2	25	46	41	4	3	0.03
A153	2	<0.2	24	45	46	3	5	<0.03
A154	6	<0.2	29	42	47	6	10	<0.03
A155	6	<0.2	33	41	62	<1	7	<0.03
A156	7	<0.2	30	36	48	<1	3	0.11
A157	6	<0.2	19	28	27	4	3	<0.03
A158	4	<0.2	36	44	75	11	21	<0.03
A159	6	<0.2	24	32	36	<1	2	<0.03
A160	6	<0.2	26	33	39	1	3	<0.03
A161	6	<0.2	27	40	42	7	12	<0.03
A162	5	<0.2	27	35	40	<1	3	0.04
A163	5	<0.2	28	36	41	4	8	<0.03
A164	6	<0.2	27	51	42	11	8	<0.03
A165	7	<0.2	26	42	44	8	5	<0.03
A166	6	<0.2	24	46	36	14	12	0.04
A167	5	<0.2	24	40	32	8	5	<0.03
A168	6	<0.2	24	39	33	11	6	<0.03
A169	4	<0.2	28	50	43	18	15	<0.03
A170	6	<0.2	25	37	34	3	3	<0.03
A171	4	<0.2	25	34	33	4	5	<0.03
A172	3	<0.2	21	32	29	2	4	0.04
A173	4	<0.2	26	33	34	<1	5	<0.03
A174	3	<0.2	29	35	44	6	9	<0.03
A175	4	<0.2	25	34	33	9	8	<0.03
A176	5	<0.2	24	35	34	4	6	<0.03
A177	6	<0.2	24	33	31	8	7	<0.03
A179	5	<0.2	23	28	36	7	6	0.03
A180	5	<0.2	28	35	42	10	7	0.03
A181	5	<0.2	25	31	37	14	7	0.03
A182	6	<0.2	26	32	38	13	8	0.07
A183	6	<0.2	27	33	40	15	12	0.03
A184	5	<0.2	26	29	40	11	9	<0.03
A185	4	<0.2	31	43	49	15	12	<0.03
A186	5	<0.2	26	39	38	12	9	<0.03
A187	6	<0.2	26	25	33	13	8	<0.03
A188	6	<0.2	26	26	38	11	8	<0.03
A189	6	<0.2	25	28	36	11	7	0.03
A190	5	<0.2	26	30	40	11	8	<0.03
A191	6	<0.2	27	29	35	10	8	0.03
A192	8	<0.2	25	29	34	11	8	0.06

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
A193	4	<0.2	24	30	35	10	5	<0.03
A194	4	<0.2	26	30	36	11	6	0.03
A195	4	<0.2	24	29	34	14	10	<0.03
A196	5	<0.2	24	29	32	12	9	0.03
A197	4	<0.2	28	35	48	7	9	0.03
A198	7	<0.2	26	30	37	10	10	0.03
A199	4	<0.2	23	30	33	10	9	<0.03
A200	6	<0.2	27	32	39	14	14	0.03
A201	4	<0.2	22	30	31	10	8	<0.03
A202	6	<0.2	23	29	34	11	6	<0.03
A203	6	<0.2	27	30	32	13	12	0.08
A204	6	<0.2	24	33	34	13	9	<0.03
A205	8	<0.2	24	28	34	12	9	0.11
A206	18	<0.2	37	36	59	18	15	0.06
A207	12	<0.2	27	30	33	16	12	0.06
A208	6	<0.2	25	32	34	7	6	0.03
A209	8	<0.2	27	31	36	4	5	0.04
A210	9	<0.2	42	28	60	<1	<1	0.06
A213	500	0.5	78	112	111	91	16	0.12
A214	97	0.3	85	115	97	108	16	<0.03
A215	2,290	0.9	46	112	66	664	14	0.11
A216	250	0.7	28	52	41	122	23	0.05
A219	1,940	0.9	55	77	57	988	10	0.24
A220	418	0.3	72	400	30	311	11	0.03
A221	2,418	0.6	39	93	58	1,060	7	0.08
A222	48	0.2	13	54	17	26	14	<0.03
A223	571	0.2	56	91	66	71	14	0.03
A224	358	0.3	21	73	24	44	11	<0.03
A225	61	0.5	41	54	91	11	8	<0.03
A226	32	0.3	53	35	87	13	14	<0.03
A227	22	0.3	33	34	50	9	5	0.06
A228	10	0.3	41	45	74	6	4	0.03
A229	16	<0.2	32	28	35	<1	6	<0.03
A230	18	<0.2	44	108	48	<1	2	<0.03
A231	96	<0.2	29	26	24	<1	3	0.72
A232	65	<0.2	23	41	50	<1	6	0.29
A233	66	<0.2	23	125	34	<1	2	0.16
A234	26	<0.2	25	86	38	<1	2	0.86
A235	19	<0.2	23	39	36	<1	2	0.79
A236	19	<0.2	20	46	35	25	3	0.18
A237	14	<0.2	25	40	48	158	7	0.20
A238	112	<0.2	17	39	47	60	2	0.08
A239	1,272	0.2	23	50	29	708	8	0.16
A240	1,073	0.3	23	51	46	615	7	0.11
A241	714	0.2	30	56	56	298	11	0.07

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
A242	17	0.2	34	74	86	47	1	<0.03
A243	74	0.2	34	59	66	67	7	<0.03
A244	37	<0.2	24	131	72	41	11	0.03
A245	33	<0.2	29	39	41	15	7	0.03
A246	6	<0.2	16	20	23	1	3	0.04
A247	446	<0.2	23	36	17	19	11	<0.03
A248	3	<0.2	25	25	41	<1	<1	<0.03
A249	5	<0.2	24	23	33	<1	3	<0.03
A250	4	<0.2	17	19	23	<1	2	<0.03
A251	4	<0.2	19	31	27	18	6	<0.03
A252	589	<0.2	59	40	46	14	<1	0.10
A253	96	<0.2	33	59	69	50	<1	0.31
A254	8	<0.2	17	21	20	9	5	0.08
A256	1,036	0.3	27	34	33	135	1	0.20
A259	607	<0.2	24	26	36	38	7	0.05
A260	1,821	<0.2	24	31	37	48	5	<0.03
A261	194	<0.2	17	23	36	13	3	0.05
A264	642	<0.2	21	21	27	13	6	<0.03
A265	732	0.4	28	113	51	534	7	0.30
A266	714	0.3	21	100	38	472	6	0.10
A267	1,142	0.2	29	73	43	1,208	4	0.13
A268	1,411	0.2	30	77	39	1,021	9	0.09
A271	11	<0.2	15	23	18	11	6	<0.03
A272	9	<0.2	20	25	17	10	4	<0.03
A273	8	<0.2	21	23	36	10	5	<0.03
A274	85	0.2	14	21	23	11	2	0.03
A275	8	<0.2	14	23	22	8	2	<0.03
A276	10	<0.2	14	26	28	9	2	<0.03
A277	7	<0.2	10	16	12	14	4	<0.03
A278	12	<0.2	18	25	20	11	12	<0.03
A279	25	<0.2	16	20	20	9	9	<0.03
A280	10	<0.2	12	19	19	15	6	<0.03
B001	9	<0.2	19	27	32	18	9	<0.03
B002	6	<0.2	20	23	22	2	8	<0.03
B003	5	<0.2	37	34	81	<1	<1	<0.03
B004	2	<0.2	13	24	32	2	5	<0.03
B005	3	<0.2	10	35	34	5	3	<0.03
B006	13	<0.2	14	18	24	7	6	<0.03
B007	11	<0.2	21	25	41	<1	1	<0.03
B008	90	<0.2	6	24	31	7	3	<0.03
B009	3	<0.2	10	16	20	<1	2	<0.03
B010	8	<0.2	15	20	22	7	8	<0.03
B011	43	<0.2	23	25	41	18	5	<0.03
B012	356	<0.2	18	17	16	22	5	<0.03
B013	432	<0.2	27	29	36	12	9	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B014	455	<0.2	21	23	32	6	9	<0.03
B015	5	<0.2	14	17	21	6	7	<0.03
B016	315	<0.2	12	34	35	6	3	<0.03
B017	16	<0.2	12	22	24	4	9	<0.03
B018	1,184	<0.2	83	29	49	333	13	<0.03
B020	526	<0.2	13	22	18	7	9	<0.03
B021	18	<0.2	10	22	18	3	5	<0.03
B022	2,053	<0.2	123	34	51	710	17	<0.03
B023	23	<0.2	8	19	7	18	8	<0.03
B024	1,474	<0.2	150	38	57	891	18	0.04
B025	38	<0.2	19	20	18	14	10	<0.03
B026	947	<0.2	45	44	96	232	10	0.03
B027	1,316	<0.2	213	43	65	1,361	23	0.07
B028	1,316	<0.2	146	35	48	1,199	21	0.04
B029	1,368	<0.2	220	43	63	1,421	24	0.06
B030	1,736	0.2	154	52	68	932	22	0.07
B031	7,211	0.5	510	69	100	7,013	70	0.16
B032	15	<0.2	16	24	19	20	15	<0.03
B033	14	<0.2	12	21	18	16	11	<0.03
B034	28	<0.2	9	22	14	6	10	<0.03
B035	19	<0.2	18	22	21	17	16	<0.03
B036	1,105	<0.2	28	37	30	162	16	<0.03
B037	1,789	<0.2	30	34	34	177	16	0.29
B038	12,295	0.4	30	40	36	1,421	16	0.94
B039	173	<0.2	32	33	48	76	9	0.09
B040	137	<0.2	24	25	32	43	13	<0.03
B041	16	<0.2	18	25	30	6	10	<0.03
B042	88	<0.2	23	28	32	24	7	<0.03
B043	163	<0.2	20	28	35	11	7	<0.03
B044	134	<0.2	19	26	33	31	7	<0.03
B045	89	<0.2	20	20	30	11	7	<0.03
B046	15	<0.2	19	18	26	10	15	<0.03
B047	33	<0.2	10	17	21	11	8	<0.03
B048	19	<0.2	18	24	36	4	10	<0.03
B049	13	<0.2	14	18	47	2	10	<0.03
B050	20	<0.2	17	18	25	3	9	<0.03
B051	6	<0.2	18	21	35	<1	8	<0.03
B052	11	<0.2	15	17	17	5	12	<0.03
B053	7	<0.2	14	16	14	7	13	<0.03
B054	11	<0.2	8	17	17	11	5	<0.03
B055	19	<0.2	18	15	14	11	16	<0.03
B056	7	<0.2	12	15	12	10	11	<0.03
B057	5	<0.2	13	14	18	6	8	<0.03
B058	4	<0.2	6	15	10	6	6	<0.03
B059	6	<0.2	12	15	10	10	12	0.04

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B060	10	<0.2	12	17	14	12	9	<0.03
B061	30	<0.2	25	34	43	10	11	<0.03
B062	20	<0.2	26	28	27	5	12	<0.03
B063	62	<0.2	32	38	47	4	11	<0.03
B064	15	<0.2	18	28	29	7	11	<0.03
B065	11	<0.2	15	20	21	4	9	<0.03
B066	124	<0.2	36	34	38	49	11	<0.03
B067	17	<0.2	23	29	28	15	10	<0.03
B068	14	0.7	10	16	16	5	6	<0.03
B069	8	<0.2	22	26	38	<1	8	<0.03
B070	9	<0.2	17	19	25	7	12	<0.03
B071	9	<0.2	15	20	14	6	12	<0.03
B072	7	<0.2	19	22	18	7	15	<0.03
B073	5	<0.2	14	18	14	7	12	<0.03
B074	24	<0.2	16	21	24	7	14	<0.03
B075	5	<0.2	21	34	67	5	11	<0.03
B076	6	<0.2	16	26	30	8	13	0.03
B077	6	<0.2	19	31	36	12	15	<0.03
B078	6	<0.2	13	18	19	8	12	0.05
B079	7	<0.2	17	25	34	12	14	<0.03
B080	7	<0.2	13	23	35	9	7	<0.03
B081	9	<0.2	39	49	131	9	12	<0.03
B082	11	<0.2	29	35	63	3	11	<0.03
B083	8	<0.2	10	11	7	12	13	<0.03
B084	11	<0.2	20	19	36	12	12	<0.03
B085	9	<0.2	23	19	35	12	15	<0.03
B086	7	<0.2	16	21	23	11	10	<0.03
B087	<1	<0.2	23	29	28	11	11	<0.03
B088	6	<0.2	29	31	46	6	13	<0.03
B089	<1	<0.2	13	18	16	10	13	<0.03
B090	3	<0.2	28	23	39	3	11	<0.03
B091	<1	<0.2	22	16	38	6	12	<0.03
B092	11	<0.2	24	20	34	4	10	<0.03
B093	13	<0.2	26	20	37	5	14	<0.03
B094	17	<0.2	27	23	39	7	13	<0.03
B095	<1	<0.2	25	17	60	14	12	<0.03
B096	<1	<0.2	14	14	24	11	11	<0.03
B097	26	<0.2	10	12	19	12	8	<0.03
B098	26	<0.2	36	31	58	1	13	<0.03
B099	1	<0.2	24	26	39	5	10	<0.03
B100	<1	<0.2	27	27	42	5	10	<0.03
B101	1	<0.2	29	31	51	3	10	<0.03
B102	<1	<0.2	24	25	37	6	9	<0.03
B103	1	<0.2	29	29	42	4	7	<0.03
B104	<1	<0.2	26	30	44	4	7	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B105	3	<0.2	14	16	13	14	7	<0.03
B106	1	<0.2	26	26	38	6	10	<0.03
B107	2	<0.2	24	25	41	5	7	<0.03
B108	<1	<0.2	21	25	37	7	5	<0.03
B109	2	<0.2	25	27	38	4	11	<0.03
B110	<1	<0.2	16	20	24	5	6	<0.03
B111	<1	<0.2	20	17	11	13	11	<0.03
B112	<1	<0.2	20	20	22	11	9	<0.03
B113	<1	<0.2	23	25	35	6	10	<0.03
B114	2	<0.2	20	21	26	10	11	<0.03
B115	2	<0.2	24	23	31	2	8	<0.03
B116	1	<0.2	25	19	26	5	11	<0.03
B117	1	<0.2	21	20	25	3	10	<0.03
B118	1	<0.2	20	21	28	2	11	<0.03
B119	157	<0.2	13	15	14	7	8	<0.03
B120	<1	<0.2	19	19	31	6	7	<0.03
B121	1	<0.2	16	19	29	4	6	<0.03
B122	2	<0.2	17	19	25	4	7	<0.03
B123	1	<0.2	18	19	26	1	7	<0.03
B124	1	<0.2	17	20	25	4	7	<0.03
B125	<1	<0.2	24	24	36	6	11	<0.03
B126	<1	<0.2	15	18	25	7	8	<0.03
B127	1	<0.2	16	19	22	7	7	<0.03
B128	<1	<0.2	18	19	21	6	13	<0.03
B129	<1	<0.2	16	19	22	9	10	<0.03
B130	1	<0.2	19	20	21	6	10	<0.03
B131	<1	<0.2	20	18	20	9	12	0.05
B132	<1	<0.2	18	18	20	6	12	<0.03
B133	1	<0.2	21	20	20	6	13	<0.03
B134	1	<0.2	17	14	20	2	12	<0.03
B135	4	<0.2	11	17	15	11	11	0.05
B136	4	<0.2	14	20	27	9	9	0.03
B137	6	<0.2	28	25	37	10	13	<0.03
B138	4	<0.2	20	20	29	11	9	<0.03
B139	4	<0.2	25	29	39	16	15	<0.03
B140	5	<0.2	19	22	17	15	14	<0.03
B141	6	<0.2	28	35	54	19	11	<0.03
B142	7	<0.2	43	52	98	12	5	<0.03
B143	5	<0.2	34	24	67	18	15	<0.03
B144	5	<0.2	19	14	37	15	11	<0.03
B145	7	<0.2	33	24	64	17	14	<0.03
B146	4	<0.2	14	16	25	13	12	<0.03
B147	6	<0.2	19	19	25	19	15	<0.03
B148	9	<0.2	45	55	122	20	19	<0.03
B149	4	<0.2	15	18	25	12	11	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B150	7	<0.2	13	17	17	9	11	<0.03
B151	3	<0.2	20	22	26	8	15	<0.03
B152	5	<0.2	21	26	33	10	76	<0.03
B153	7	<0.2	17	18	22	6	16	<0.03
B154	4	<0.2	14	18	17	10	12	<0.03
B155	4	<0.2	18	18	29	8	16	<0.03
B156	5	<0.2	17	20	23	5	15	<0.03
B157	6	<0.2	20	19	25	10	12	<0.03
B158	6	<0.2	22	18	25	6	14	<0.03
B159	7	<0.2	12	18	20	8	9	<0.03
B160	5	<0.2	21	27	32	8	11	<0.03
B161	9	<0.2	16	21	20	7	10	<0.03
B162	5	<0.2	19	27	33	4	15	<0.03
B163	7	<0.2	18	23	32	5	16	<0.03
B164	7	<0.2	18	23	27	10	17	<0.03
B165	8	<0.2	16	20	24	13	12	<0.03
B166	11	<0.2	21	20	26	10	14	<0.03
B167	12	<0.2	20	20	24	15	13	<0.03
B168	11	<0.2	21	21	30	10	13	<0.03
B169	7	<0.2	19	24	35	10	13	<0.03
B170	10	<0.2	20	27	35	10	15	<0.03
B171	7	<0.2	20	29	39	10	15	<0.03
B172	7	<0.2	18	24	31	9	13	0.03
B173	7	<0.2	16	20	21	14	16	0.09
B174	8	<0.2	14	28	29	9	16	0.07
B175	7	<0.2	18	29	41	14	21	<0.03
B176	8	<0.2	11	25	21	12	15	<0.03
B177	10	<0.2	14	29	35	8	12	<0.03
B178	10	<0.2	11	23	28	11	12	<0.03
B179	11	<0.2	18	29	38	6	15	<0.03
B180	10	<0.2	18	28	32	7	12	<0.03
B181	13	<0.2	17	21	28	10	14	<0.03
B182	12	<0.2	21	28	38	6	12	<0.03
B183	9	<0.2	15	16	16	16	13	<0.03
B184	14	<0.2	13	16	16	16	13	<0.03
B185	13	<0.2	17	16	27	11	16	0.03
B186	7	<0.2	15	19	23	12	15	<0.03
B187	3	<0.2	18	20	17	<1	5	<0.03
B188	4	<0.2	17	19	16	<1	8	<0.03
B189	3	<0.2	13	19	13	6	3	<0.03
B190	4	<0.2	12	19	13	5	2	<0.03
B191	3	<0.2	18	23	18	<1	3	<0.03
B192	3	<0.2	21	25	19	3	6	<0.03
B193	<1	<0.2	13	22	14	2	2	<0.03
B194	1	<0.2	13	21	14	5	2	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B195	1	<0.2	12	20	14	2	1	<0.03
B196	2	<0.2	14	21	10	6	9	<0.03
B197	1	<0.2	13	13	12	<1	2	<0.03
B198	2	<0.2	13	12	11	<1	2	<0.03
B199	1	<0.2	14	10	23	<1	6	<0.03
B200	2	<0.2	16	19	21	<1	<1	<0.03
B201	3	<0.2	12	10	15	<1	3	<0.03
B202	2	<0.2	14	12	16	<1	3	<0.03
B203	3	<0.2	15	23	28	1	1	<0.03
B204	<1	<0.2	12	14	17	<1	2	<0.03
B205	<1	<0.2	14	19	12	1	4	<0.03
B206	2	<0.2	18	15	19	<1	3	<0.03
B207	<1	<0.2	16	17	22	<1	1	<0.03
B208	1	<0.2	14	17	14	<1	5	<0.03
B209	1	<0.2	13	19	22	<1	5	<0.03
B210	<1	<0.2	14	25	15	<1	6	<0.03
B211	2	<0.2	15	17	17	<1	9	<0.03
B212	2	<0.2	18	20	19	<1	6	0.03
B213	1	<0.2	18	12	13	<1	6	<0.03
B214	<1	<0.2	13	19	13	3	9	<0.03
B215	1	<0.2	13	10	10	2	7	<0.03
B216	<1	<0.2	21	52	77	<1	4	0.07
B217	1	<0.2	11	17	13	3	6	<0.03
B218	1	<0.2	13	12	9	<1	5	<0.03
B219	2	<0.2	15	15	12	2	4	<0.03
B220	2	<0.2	14	22	19	<1	5	<0.03
B221	2	<0.2	17	25	9	7	9	<0.03
B222	<1	<0.2	20	22	15	<1	<1	<0.03
B223	<1	<0.2	15	19	14	6	7	<0.03
B224	2	<0.2	16	24	15	<1	2	<0.03
B225	1	<0.2	14	15	1	19	10	<0.03
B226	2	<0.2	19	19	10	10	12	<0.03
B227	2	<0.2	17	20	6	18	12	<0.03
B228	2	<0.2	21	21	14	13	12	<0.03
B229	2	<0.2	26	21	13	8	3	<0.03
B230	2	<0.2	21	25	28	22	14	<0.03
B231	1	<0.2	15	20	9	15	9	<0.03
B232	2	<0.2	18	22	9	17	14	<0.03
B233	1	<0.2	16	19	8	16	13	<0.03
B234	1	<0.2	16	18	6	14	8	<0.03
B235	2	<0.2	17	20	10	11	9	<0.03
B236	1	<0.2	17	18	7	10	10	<0.03
B237	2	<0.2	18	18	8	10	10	<0.03
B238	1	<0.2	17	17	8	19	10	<0.03
B239	<1	<0.2	17	18	3	18	10	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B240	<1	<0.2	19	26	20	19	10	<0.03
B241	1	<0.2	19	21	5	18	9	<0.03
B242	<1	<0.2	19	22	10	12	10	<0.03
B243	<1	<0.2	19	24	10	12	10	<0.03
B244	<1	<0.2	20	24	29	14	10	<0.03
B245	2	<0.2	18	20	14	13	10	<0.03
B246	<1	<0.2	19	24	8	10	5	<0.03
B247	3	<0.2	18	17	8	10	12	<0.03
B248	2	<0.2	15	14	7	16	16	<0.03
B249	2	<0.2	20	17	17	<1	10	<0.03
B250	3	<0.2	18	20	11	15	13	<0.03
B251	1	<0.2	17	15	11	8	9	<0.03
B252	1	<0.2	16	16	8	12	7	<0.03
B253	2	<0.2	14	17	8	13	6	<0.03
B254	3	<0.2	18	17	10	10	12	<0.03
B255	3	<0.2	19	23	17	7	8	<0.03
B256	4	<0.2	12	10	16	<1	1	<0.03
B257	4	<0.2	19	16	20	<1	2	<0.03
B258	4	<0.2	22	20	19	4	6	<0.03
B259	5	<0.2	18	20	22	6	4	<0.03
B260	5	<0.2	18	15	15	2	4	<0.03
B261	4	<0.2	19	23	18	10	10	<0.03
B262	5	<0.2	25	42	58	5	1	<0.03
B263	4	<0.2	16	22	21	9	8	<0.03
B264	2	<0.2	17	18	19	5	2	<0.03
B265	1	<0.2	12	17	12	18	10	<0.03
B266	3	<0.2	20	24	19	16	13	<0.03
B267	1	<0.2	15	20	18	11	6	<0.03
B268	2	<0.2	7	18	10	21	15	<0.03
B269	2	<0.2	8	21	12	23	18	<0.03
B270	4	<0.2	28	89	138	7	3	<0.03
B271	6	<0.2	42	204	297	43	39	<0.03
B272	10	<0.2	36	77	179	24	8	0.03
B273	9	<0.2	45	90	232	18	5	0.07
B274	4	<0.2	30	88	125	27	18	0.04
B275	2	<0.2	16	16	16	9	7	<0.03
B276	2	<0.2	18	15	18	4	2	<0.03
B277	2	<0.2	16	18	19	6	7	<0.03
B278	2	<0.2	2	22	4	34	21	<0.03
B279	4	<0.2	14	16	16	10	7	<0.03
B280	1	<0.2	11	16	9	5	7	<0.03
B281	1	<0.2	1	2	<0.5	9	3	<0.03
B282	1	<0.2	7	7	1	11	4	<0.03
B283	1	<0.2	11	10	5	10	7	<0.03
B284	1	<0.2	11	11	5	10	5	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B285	2	<0.2	12	10	3	8	4	<0.03
B286	1	<0.2	11	14	5	18	12	<0.03
B287	1	<0.2	13	11	6	8	7	<0.03
B288	1	<0.2	13	13	10	15	12	<0.03
B289	1	<0.2	11	9	8	7	5	<0.03
B290	<1	<0.2	11	12	5	17	14	<0.03
B291	5	<0.2	25	19	34	11	28	<0.03
B292	8	<0.2	27	23	41	8	27	<0.03
B293	15	<0.2	41	37	36	24	39	<0.03
B294	9	<0.2	25	16	32	78	25	<0.03
B295	5	<0.2	19	16	21	3	3	<0.03
B296	7	<0.2	33	24	26	24	19	<0.03
B297	11	0.2	31	28	44	29	30	<0.03
B298	5	<0.2	28	25	41	7	16	<0.03
B299	4	<0.2	25	22	19	6	10	<0.03
B300	3	<0.2	15	15	20	<1	<1	<0.03
B301	19	0.2	67	51	88	28	37	<0.03
B302	6	<0.2	62	47	55	7	35	<0.03
B303	9	<0.2	63	74	100	54	83	<0.03
B304	10	<0.2	61	51	86	22	45	<0.03
B305	14	0.2	64	65	108	64	65	<0.03
B306	12	0.2	54	53	87	41	47	<0.03
B307	8	0.2	41	40	46	9	26	<0.03
B308	8	<0.2	34	23	23	13	22	<0.03
B309	4	<0.2	24	22	30	6	11	<0.03
B310	4	<0.2	14	14	19	<1	<1	<0.03
B311	9	<0.2	21	20	28	<1	5	<0.03
B312	9	<0.2	26	20	29	<1	16	<0.03
B313	10	<0.2	22	18	19	<1	11	<0.03
B314	5	<0.2	21	21	19	<1	17	<0.03
B315	5	<0.2	19	15	22	<1	8	<0.03
B316	4	<0.2	15	13	11	4	4	<0.03
B317	4	<0.2	18	15	12	2	7	<0.03
B318	12	<0.2	21	18	23	5	7	<0.03
B319	10	<0.2	58	37	33	16	38	<0.03
B320	7	<0.2	34	29	40	7	28	<0.03
B321	3	<0.2	15	14	14	5	<1	<0.03
B322	3	<0.2	32	29	35	14	12	<0.03
B323	5	<0.2	22	22	28	5	9	<0.03
B324	4	<0.2	19	14	15	4	2	<0.03
B325	11	<0.2	51	35	38	6	10	<0.03
B326	8	<0.2	33	23	31	3	13	<0.03
B327	3	<0.2	12	13	8	4	<1	<0.03
B328	4	<0.2	16	13	7	2	1	<0.03
B329	3	<0.2	16	17	12	2	1	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B330	3	<0.2	16	17	17	<1	4	<0.03
B331	2	<0.2	13	13	7	3	2	<0.03
B332	4	<0.2	22	20	24	<1	12	<0.03
B333	19	<0.2	19	17	24	<1	7	<0.03
B334	6	<0.2	16	14	12	1	6	<0.03
B335	4	<0.2	19	16	12	6	3	<0.03
B336	9	<0.2	23	19	22	<1	8	<0.03
B337	5	<0.2	24	26	21	16	14	<0.03
B338	8	<0.2	22	20	19	10	11	<0.03
B339	5	<0.2	24	19	21	8	8	<0.03
B340	6	<0.2	31	23	23	11	9	<0.03
B341	22	<0.2	51	30	60	29	16	<0.03
B342	7	<0.2	18	25	18	<1	8	<0.03
B343	3	<0.2	19	18	19	<1	5	<0.03
B344	4	<0.2	19	23	13	<1	6	<0.03
B345	5	<0.2	20	21	18	<1	5	<0.03
B346	2	<0.2	15	16	14	<1	1	<0.03
B347	2	<0.2	16	18	17	<1	1	<0.03
B348	2	<0.2	17	19	10	<1	4	<0.03
B349	2	<0.2	18	21	9	<1	7	<0.03
B350	2	<0.2	13	12	5	2	<1	<0.03
B351	2	<0.2	16	16	6	3	4	<0.03
B352	3	<0.2	15	16	9	<1	3	<0.03
B353	1	<0.2	33	26	34	11	9	<0.03
B354	3	<0.2	19	18	16	2	3	<0.03
B355	21	<0.2	35	17	38	24	5	<0.03
B356	3	<0.2	27	17	23	<1	2	<0.03
B357	2	<0.2	18	26	15	14	11	<0.03
B358	3	<0.2	17	25	15	14	5	<0.03
B359	3	<0.2	19	22	22	3	2	<0.03
B360	3	<0.2	24	28	27	5	10	<0.03
B361	6	<0.2	28	37	47	21	17	<0.03
B362	3	<0.2	12	20	14	11	<1	<0.03
B363	3	<0.2	13	17	9	6	4	<0.03
B364	4	<0.2	8	19	7	20	8	<0.03
B365	3	<0.2	12	20	2	14	18	<0.03
B366	4	<0.2	21	22	9	13	13	<0.03
B367	6	<0.2	19	21	11	<1	14	<0.03
B368	3	<0.2	19	33	36	12	11	<0.03
B369	3	<0.2	18	25	25	3	<1	<0.03
B370	3	<0.2	12	20	8	9	3	<0.03
B371	3	<0.2	15	15	11	3	<1	<0.03
B372	19	<0.2	12	11	3	4	<1	<0.03
B373	11	<0.2	27	19	15	12	4	<0.03
B374	14	<0.2	24	32	42	32	25	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B375	8	<0.2	33	25	33	16	1	<0.03
B376	9	<0.2	24	30	16	41	24	<0.03
B377	19	<0.2	35	23	34	20	9	<0.03
B378	38	<0.2	54	36	65	15	5	<0.03
B379	59	<0.2	30	23	37	2	3	0.12
B380	13	<0.2	15	23	23	25	8	<0.03
B381	7	<0.2	16	20	14	<1	1	<0.03
B382	10	<0.2	18	31	28	29	27	<0.03
B383	5	<0.2	19	18	20	1	4	<0.03
B384	4	<0.2	13	19	13	17	3	<0.03
B385	3	<0.2	25	52	36	<1	13	<0.03
B386	9	<0.2	22	27	37	6	18	<0.03
B387	4	<0.2	18	22	22	<1	6	<0.03
B388	4	<0.2	20	18	18	10	6	<0.03
B389	6	<0.2	19	25	11	11	15	<0.03
B390	8	<0.2	19	36	20	27	27	<0.03
B391	4	<0.2	25	21	18	<1	11	<0.03
B392	4	<0.2	22	22	30	<1	6	<0.03
B393	7	<0.2	24	25	19	<1	4	<0.03
B394	7	<0.2	16	32	26	33	31	<0.03
B395	5	<0.2	29	31	34	16	28	<0.03
B396	3	<0.2	25	22	19	7	8	<0.03
B397	3	<0.2	12	25	10	22	23	0.38
B398	1	<0.2	15	20	10	4	2	0.46
B399	4	<0.2	21	26	29	<1	7	<0.03
B400	22	<0.2	20	34	24	<1	24	<0.03
B401	4	<0.2	13	20	16	9	5	<0.03
B402	3	<0.2	17	24	14	8	6	<0.03
B403	3	<0.2	19	21	23	<1	<1	<0.03
B404	3	<0.2	10	22	6	14	18	<0.03
B405	4	<0.2	16	21	34	<1	<1	<0.03
B406	3	<0.2	19	19	14	<1	1	<0.03
B407	3	<0.2	22	21	26	<1	<1	<0.03
B408	4	<0.2	17	21	15	<1	<1	<0.03
B409	3	<0.2	11	18	9	11	2	<0.03
B410	3	<0.2	17	13	7	<1	<1	<0.03
B411	6	<0.2	15	17	7	9	<1	<0.03
B412	5	<0.2	24	16	10	2	2	<0.03
B413	4	<0.2	15	15	3	10	7	<0.03
B414	3	<0.2	19	13	8	4	<1	<0.03
B415	7	<0.2	19	17	9	10	5	<0.03
B416	2	<0.2	16	11	2	6	<1	<0.03
B417	5	<0.2	15	16	3	7	4	<0.03
B418	6	<0.2	20	12	5	5	<1	<0.03
B419	8	<0.2	25	17	10	7	1	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
B420	2	<0.2	28	16	8	<1	<1	<0.03
B421	6	<0.2	21	19	13	13	2	<0.03
B422	3	<0.2	28	24	17	1	7	<0.03
B423	3	<0.2	14	16	6	10	<1	<0.03
B424	2	<0.2	19	18	13	8	<1	<0.03
B425	4	<0.2	18	19	11	10	<1	<0.03
B426	2	<0.2	26	18	14	4	<1	<0.03
B427	1	<0.2	16	14	3	5	<1	<0.03
B428	2	<0.2	15	15	6	13	<1	<0.03
B429	13	<0.2	23	15	8	6	<1	<0.03
B430	6	<0.2	24	18	7	10	<1	<0.03
B431	4	<0.2	12	18	2	17	7	<0.03
B432	2	<0.2	20	15	6	6	2	<0.03
B433	7	<0.2	25	15	9	7	1	<0.03
B434	4	<0.2	23	35	8	7	1	<0.03
C001	4	<0.2	7	13	16	14	11	<0.03
C002	3	<0.2	13	11	11	13	17	<0.03
C003	3	<0.2	14	17	17	8	13	<0.03
C004	3	<0.2	13	15	13	8	15	<0.03
C005	14	<0.2	13	20	17	10	14	<0.03
C006	9	<0.2	9	13	8	12	13	<0.03
C007	4	<0.2	15	21	18	9	15	<0.03
C008	3	<0.2	8	19	15	9	8	<0.03
C009	4	<0.2	4	16	18	5	4	<0.03
C010	4	<0.2	11	20	20	1	9	<0.03
C011	12	<0.2	13	16	15	12	17	<0.03
C012	10	<0.2	9	20	17	9	10	<0.03
C013	8	<0.2	13	19	13	12	15	<0.03
C014	5	<0.2	11	21	19	7	11	<0.03
C015	3	<0.2	6	20	19	11	6	<0.03
C016	3	<0.2	13	20	16	13	9	<0.03
C017	4	<0.2	5	21	28	5	6	<0.03
C018	6	<0.2	18	20	17	10	19	<0.03
C019	7	<0.2	5	22	17	6	6	<0.03
C020	4	<0.2	15	20	13	12	18	<0.03
C021	3	<0.2	5	20	12	10	7	<0.03
C022	4	<0.2	7	20	18	6	6	<0.03
C023	1	<0.2	5	14	8	10	5	<0.03
C024	10	<0.2	20	17	15	6	12	0.10
C025	4	<0.2	7	18	15	7	4	<0.03
C026	6	<0.2	7	17	15	7	3	<0.03
C027	6	<0.2	11	13	10	9	8	<0.03
C028	3	<0.2	4	14	9	7	4	<0.03
C029	3	<0.2	9	16	12	6	6	<0.03
C030	4	<0.2	10	14	7	7	10	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C031	2	<0.2	9	12	5	10	10	<0.03
C032	3	<0.2	10	16	12	7	6	<0.03
C033	7	<0.2	45	47	83	<1	<1	<0.03
C034	2	<0.2	11	17	11	9	6	<0.03
C035	4	<0.2	9	18	19	4	4	<0.03
C036	4	<0.2	11	18	22	5	4	<0.03
C037	8	<0.2	46	39	87	<1	2	<0.03
C038	11	<0.2	46	47	96	<1	131	0.04
C039	9	<0.2	37	29	69	2	8	0.33
C040	9	<0.2	36	30	72	1	5	0.03
C041	4	<0.2	34	29	60	5	13	<0.03
C042	7	<0.2	36	35	63	10	14	<0.03
C043	8	<0.2	36	32	72	<1	8	0.03
C044	5	<0.2	38	37	76	<1	12	0.03
C045	9	<0.2	30	32	69	<1	9	<0.03
C046	15	<0.2	35	34	63	7	17	<0.03
C047	15	<0.2	43	31	69	11	19	<0.03
C048	13	<0.2	32	31	62	2	13	<0.03
C049	16	0.3	43	459	142	58	25	0.15
C050	16	<0.2	47	41	85	12	18	0.12
C051	16	<0.2	52	45	112	17	10	2.84
C052	14	<0.2	47	48	99	11	15	0.04
C053	14	<0.2	39	32	80	6	14	0.03
C054	1	<0.2	51	53	108	15	19	<0.03
C055	18	<0.2	52	51	98	15	23	0.03
C056	8	<0.2	24	20	40	3	9	<0.03
C057	7	<0.2	20	21	37	3	10	<0.03
C058	11	<0.2	33	27	65	3	10	<0.03
C059	16	1.4	46	1,047	201	386	34	0.07
C060	10	0.2	28	161	120	40	15	0.62
C061	20	1.1	75	3,055	431	397	28	0.04
C062	22	2.4	45	1,174	302	355	29	0.03
C063	106	<0.2	32	67	55	23	10	<0.03
C064	20	1.2	79	2,382	450	346	41	0.05
C065	10	<0.2	31	139	95	27	14	<0.03
C066	10	<0.2	41	102	142	22	16	<0.03
C067	7	<0.2	21	31	32	13	12	<0.03
C068	7	<0.2	24	36	53	11	13	<0.03
C069	7	<0.2	27	34	59	13	13	<0.03
C070	8	<0.2	20	24	46	11	11	<0.03
C071	11	<0.2	25	23	54	7	14	<0.03
C072	10	<0.2	35	42	85	11	14	<0.03
C073	13	<0.2	35	37	83	11	14	<0.03
C074	8	<0.2	16	10	15	14	17	<0.03
C075	5	<0.2	27	63	142	16	10	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C076	5	<0.2	18	12	17	16	19	<0.03
C077	15	<0.2	14	23	26	12	10	<0.03
C078	11	<0.2	19	14	22	15	21	<0.03
C079	28	<0.2	16	22	24	15	11	<0.03
C080	7	<0.2	17	28	31	10	11	<0.03
C081	5	<0.2	9	15	22	12	7	<0.03
C082	4	<0.2	29	34	38	14	14	0.05
C083	3	<0.2	14	26	41	14	8	<0.03
C084	8	<0.2	457	45	248	4	13	<0.03
C085	4	<0.2	14	23	25	4	8	<0.03
C086	7	<0.2	13	21	26	9	8	<0.03
C087	9	<0.2	23	29	29	7	13	<0.03
C088	8	<0.2	15	19	25	2	8	<0.03
C089	8	<0.2	19	26	23	4	10	<0.03
C090	10	<0.2	19	22	23	15	15	<0.03
C091	5	<0.2	3	12	6	6	8	<0.03
C092	7	<0.2	16	21	19	15	18	<0.03
C093	5	<0.2	25	30	37	19	14	0.04
C094	7	<0.2	34	33	41	17	20	0.13
C095	8	<0.2	20	28	28	11	17	<0.03
C096	11	<0.2	57	248	480	10	17	0.10
C097	4	<0.2	10	22	20	17	11	0.04
C098	5	<0.2	16	21	25	16	14	<0.03
C099	5	<0.2	47	194	390	25	16	0.08
C100	4	<0.2	7	16	14	9	7	<0.03
C101	8	<0.2	38	55	72	27	17	<0.03
C102	4	<0.2	8	17	12	9	7	<0.03
C103	6	<0.2	12	19	16	14	9	<0.03
C104	6	<0.2	35	55	54	18	7	0.03
C105	3	<0.2	8	14	6	11	7	<0.03
C106	11	<0.2	9	13	5	17	9	<0.03
C107	2	<0.2	16	14	25	<1	2	<0.03
C108	1	<0.2	13	11	21	<1	1	<0.03
C109	2	<0.2	19	24	19	7	6	<0.03
C110	3	0.2	11	19	23	12	6	<0.03
C111	<1	<0.2	18	18	36	9	7	<0.03
C112	3	<0.2	8	14	12	6	2	<0.03
C113	4	<0.2	15	22	23	6	6	<0.03
C114	2	<0.2	11	13	13	7	6	<0.03
C115	4	<0.2	19	20	25	3	12	<0.03
C116	3	<0.2	10	19	20	4	4	<0.03
C117	6	<0.2	51	44	100	<1	<1	<0.03
C118	10	<0.2	40	34	84	<1	<1	<0.03
C119	4	<0.2	28	26	50	<1	5	<0.03
C120	3	<0.2	22	20	32	2	7	0.10

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C121	5	<0.2	14	17	20	5	5	<0.03
C122	4	<0.2	18	18	24	3	6	<0.03
C123	3	<0.2	13	18	23	6	3	<0.03
C124	2	<0.2	16	17	28	7	5	<0.03
C125	3	<0.2	8	16	18	8	2	<0.03
C126	1	<0.2	11	14	13	8	5	0.04
C127	3	<0.2	12	17	27	11	5	<0.03
C128	2	<0.2	13	19	19	7	5	<0.03
C129	3	<0.2	18	18	25	12	6	<0.03
C130	4	<0.2	38	46	134	17	17	<0.03
C131	6	<0.2	37	47	145	9	18	<0.03
C132	4	<0.2	47	56	203	15	39	<0.03
C133	5	<0.2	34	45	124	11	14	<0.03
C134	12	<0.2	45	54	203	16	25	<0.03
C135	8	<0.2	41	56	92	9	14	<0.03
C136	9	<0.2	40	45	153	11	18	<0.03
C137	4	<0.2	22	48	58	3	9	<0.03
C138	5	<0.2	33	42	113	9	15	<0.03
C139	5	<0.2	34	44	150	9	13	<0.03
C140	6	<0.2	38	40	178	12	13	<0.03
C141	19	<0.2	32	45	142	8	8	<0.03
C142	5	<0.2	38	45	113	<1	7	<0.03
C143	6	<0.2	57	54	60	<1	<1	<0.03
C144	6	<0.2	51	44	86	<1	<1	<0.03
C145	8	<0.2	40	36	70	<1	4	<0.03
C146	6	<0.2	44	47	75	23	8	<0.03
C147	15	<0.2	40	41	77	<1	4	<0.03
C148	4	<0.2	43	45	82	<1	3	<0.03
C149	4	<0.2	42	42	76	<1	6	<0.03
C150	6	<0.2	48	45	92	<1	5	<0.03
C151	4	<0.2	29	70	35	12	21	<0.03
C152	4	<0.2	29	79	91	11	23	<0.03
C153	4	<0.2	34	76	77	2	13	<0.03
C154	4	<0.2	40	64	190	5	21	<0.03
C155	8	<0.2	39	58	209	24	17	<0.03
C156	4	<0.2	48	104	212	17	19	0.05
C157	3	<0.2	38	71	131	13	9	0.03
C158	1	<0.2	10	22	23	14	20	<0.03
C159	1	<0.2	13	22	29	12	5	<0.03
C160	<1	<0.2	15	35	44	12	7	0.04
C161	<1	<0.2	13	20	28	13	3	<0.03
C162	2	<0.2	18	31	56	11	4	0.03
C163	2	<0.2	15	34	40	9	12	<0.03
C164	4	<0.2	18	33	34	12	10	0.03
C165	2	<0.2	22	37	47	12	7	0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C166	3	<0.2	12	18	49	12	4	0.03
C167	2	<0.2	18	17	26	10	4	0.03
C168	14	<0.2	16	20	36	13	8	<0.03
C169	2	<0.2	11	12	27	18	18	<0.03
C170	2	<0.2	17	24	33	14	2	0.03
C171	11	<0.2	57	99	100	<1	<1	0.06
C172	4	<0.2	29	28	32	11	<1	<0.03
C173	11	<0.2	39	53	59	<1	<1	<0.03
C174	10	<0.2	13	16	27	16	<1	<0.03
C175	6	<0.2	33	49	76	15	9	0.03
C176	10	<0.2	15	18	21	8	<1	<0.03
C177	8	<0.2	41	69	94	7	<1	0.07
C178	6	<0.2	32	59	118	10	7	0.03
C179	15	<0.2	30	56	161	11	6	0.03
C180	7	<0.2	26	45	88	13	11	0.03
C181	6	<0.2	25	42	83	14	7	0.04
C182	4	<0.2	17	32	60	13	14	0.03
C183	3	<0.2	12	18	40	15	1	0.03
C184	5	<0.2	11	10	19	18	5	<0.03
C185	6	<0.2	36	61	77	5	<1	0.05
C186	5	<0.2	23	39	32	17	8	<0.03
C187	5	<0.2	15	24	18	6	35	<0.03
C188	4	<0.2	12	24	14	5	48	<0.03
C189	9	<0.2	30	65	53	15	24	<0.03
C190	3	<0.2	10	19	16	12	42	<0.03
C191	4	<0.2	12	16	15	4	26	<0.03
C192	7	<0.2	28	39	28	15	3	0.03
C193	3	<0.2	11	14	10	9	3	<0.03
C194	3	<0.2	8	14	13	6	1	<0.03
C195	1	<0.2	12	14	11	10	3	<0.03
C196	3	<0.2	12	15	12	11	3	<0.03
C197	2	<0.2	4	6	6	13	1	<0.03
C198	8	<0.2	9	8	17	11	21	<0.03
C199	3	<0.2	9	16	23	6	5	<0.03
C200	5	<0.2	15	15	35	8	5	0.03
C201	2	<0.2	14	24	59	9	11	0.04
C202	3	<0.2	15	18	51	8	5	0.05
C203	3	<0.2	10	8	9	7	5	<0.03
C204	5	<0.2	10	13	18	<1	<1	0.03
C205	5	<0.2	19	19	24	<1	11	0.03
C206	3	<0.2	11	12	12	<1	7	0.03
C207	5	<0.2	15	17	22	<1	8	0.03
C208	5	<0.2	12	14	13	<1	7	0.03
C209	3	<0.2	9	12	13	<1	8	0.20
C210	<1	<0.2	7	11	14	<1	8	0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C211	2	<0.2	12	10	8	3	8	0.03
C212	2	<0.2	9	7	10	1	3	0.03
C213	3	<0.2	9	9	8	4	3	<0.03
C214	3	<0.2	13	9	10	<1	4	0.03
C215	3	<0.2	7	6	7	<1	5	<0.03
C216	3	<0.2	9	10	9	5	8	<0.03
C217	10	<0.2	12	12	11	<1	6	0.03
C218	1	<0.2	7	9	9	3	6	<0.03
C219	5	<0.2	12	12	13	<1	5	<0.03
C220	3	<0.2	16	16	14	<1	9	<0.03
C221	5	<0.2	13	14	15	<1	5	0.03
C222	3	<0.2	10	12	12	3	7	0.03
C223	6	<0.2	14	16	15	<1	4	0.04
C224	2	<0.2	16	17	12	7	11	<0.03
C225	2	<0.2	11	14	10	5	12	<0.03
C226	2	<0.2	9	13	8	4	10	<0.03
C227	<1	<0.2	7	12	8	8	9	0.03
C228	2	<0.2	12	14	10	7	11	<0.03
C229	3	<0.2	7	11	7	14	12	<0.03
C230	6	<0.2	19	18	19	11	12	0.03
C231	9	<0.2	40	30	60	<1	<1	0.04
C232	<1	<0.2	8	6	8	9	10	0.04
C233	2	<0.2	13	14	11	16	12	0.04
C234	7	<0.2	33	125	280	6	11	0.08
C235	<1	<0.2	11	27	40	14	11	0.03
C236	<1	<0.2	8	27	30	16	7	0.04
C237	1	<0.2	14	26	36	14	12	0.03
C238	<1	<0.2	15	23	21	9	5	<0.03
C239	<1	<0.2	15	15	13	8	5	0.04
C240	1	<0.2	16	25	8	8	7	0.04
C241	8	<0.2	56	50	154	13	14	0.04
C242	8	<0.2	46	44	92	9	7	0.07
C243	2	<0.2	19	11	9	4	8	0.03
C244	<1	<0.2	15	16	8	<1	3	0.03
C245	1	<0.2	17	9	11	8	10	0.07
C246	2	<0.2	16	16	10	2	5	0.05
C247	<1	<0.2	13	13	24	7	3	0.04
C248	1	<0.2	13	14	3	6	5	0.23
C249	1	<0.2	18	16	4	9	14	0.06
C250	<1	<0.2	12	13	3	10	38	0.04
C251	1	<0.2	19	18	6	8	8	0.03
C252	<1	<0.2	17	15	6	7	6	<0.03
C253	2	<0.2	24	22	14	3	8	0.05
C254	2	<0.2	15	16	5	11	5	<0.03
C255	3	<0.2	23	29	13	10	15	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C256	1	<0.2	16	20	4	14	9	0.03
C257	2	<0.2	14	16	3	15	8	<0.03
C258	1	<0.2	17	18	2	11	9	<0.03
C259	1	<0.2	17	20	3	7	8	<0.03
C260	1	<0.2	17	15	2	7	5	<0.03
C261	1	<0.2	18	22	6	6	5	<0.03
C262	2	<0.2	16	16	4	7	8	<0.03
C263	1	<0.2	17	18	5	3	2	<0.03
C264	4	<0.2	21	18	5	9	5	<0.03
C265	2	<0.2	19	16	5	6	12	<0.03
C266	1	<0.2	16	15	3	10	5	<0.03
C267	2	<0.2	15	15	7	9	4	<0.03
C268	3	<0.2	22	22	15	1	5	<0.03
C269	6	<0.2	24	24	17	<1	5	<0.03
C270	<1	<0.2	21	18	14	4	6	<0.03
C271	1	<0.2	28	24	30	<1	2	<0.03
C272	<1	<0.2	13	16	5	4	3	<0.03
C273	1	<0.2	19	17	8	3	5	<0.03
C274	2	<0.2	19	15	3	5	4	<0.03
C275	<1	<0.2	18	22	6	6	2	<0.03
C276	1	<0.2	15	17	5	8	6	<0.03
C277	<1	<0.2	18	16	5	9	5	<0.03
C278	1	<0.2	15	15	4	5	5	<0.03
C279	1	<0.2	17	19	9	2	1	<0.03
C280	1	<0.2	19	17	5	8	2	<0.03
C281	2	<0.2	25	19	21	7	7	<0.03
C282	1	<0.2	16	18	7	6	2	<0.03
C283	1	<0.2	18	15	10	7	6	<0.03
C284	1	<0.2	17	16	8	8	4	<0.03
C285	<1	<0.2	18	16	8	7	6	<0.03
C286	2	<0.2	14	15	7	11	8	<0.03
C287	2	<0.2	18	18	9	6	6	<0.03
C288	2	<0.2	17	16	11	3	2	<0.03
C289	2	<0.2	16	16	13	1	<1	<0.03
C290	2	<0.2	21	17	18	2	4	<0.03
C291	3	<0.2	14	14	4	8	3	<0.03
C292	2	<0.2	23	19	16	<1	5	<0.03
C293	5	<0.2	36	25	42	<1	5	<0.03
C294	3	<0.2	22	23	17	5	4	<0.03
C295	2	<0.2	21	20	14	3	6	<0.03
C296	<1	<0.2	18	15	12	7	4	<0.03
C297	2,054	<0.2	29	27	33	118	3	0.39
C298	23	<0.2	16	14	17	25	7	0.04
C299	80	<0.2	29	23	39	50	<1	<0.03
C300	10	<0.2	22	16	21	23	5	0.12

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C301	13	<0.2	18	17	16	28	3	0.03
C302	18	<0.2	18	15	23	15	2	<0.03
C303	46	<0.2	17	14	15	25	2	0.12
C304	24	<0.2	24	14	24	10	<1	<0.03
C305	51	<0.2	21	19	25	25	2	0.09
C306	10	<0.2	28	23	45	19	5	0.06
C307	11	<0.2	18	23	29	32	3	0.03
C308	16	<0.2	27	25	41	25	2	<0.03
C309	70	<0.2	17	12	14	15	8	0.03
C310	38	<0.2	13	10	10	13	3	<0.03
C311	10	<0.2	26	21	37	17	2	<0.03
C312	28	<0.2	23	22	29	14	2	0.09
C313	74	<0.2	23	19	28	11	1	<0.03
C314	28	<0.2	25	22	31	19	2	<0.03
C315	77	<0.2	20	18	25	10	<1	<0.03
C316	59	<0.2	24	22	28	17	5	<0.03
C317	32	<0.2	23	15	23	5	12	<0.03
C318	26	<0.2	22	16	30	4	<1	<0.03
C319	23	<0.2	16	12	19	<1	<1	<0.03
C320	11	<0.2	15	13	12	13	2	<0.03
C321	10	<0.2	28	23	29	23	4	<0.03
C322	7	<0.2	46	22	52	8	1	<0.03
C323	200	<0.2	18	17	30	11	2	<0.03
C324	10	<0.2	25	20	31	17	3	<0.03
C325	3	<0.2	26	14	23	6	4	0.03
C326	35	<0.2	21	18	23	15	4	0.03
C327	23	<0.2	19	18	25	13	4	<0.03
C328	60	<0.2	18	13	18	12	4	0.03
C329	43	<0.2	7	7	4	6	1	<0.03
C330	42	<0.2	8	7	8	5	1	<0.03
C331	49	<0.2	12	11	17	9	2	<0.03
C332	5	<0.2	13	15	22	13	1	<0.03
C333	3	<0.2	13	9	11	11	5	<0.03
C334	1	<0.2	8	4	2	10	5	<0.03
C335	1	<0.2	9	7	8	8	2	0.03
C336	17	<0.2	15	12	15	13	5	<0.03
C337	7	<0.2	5	6	1	12	3	<0.03
C338	7	<0.2	14	11	9	14	7	<0.03
C339	35	<0.2	31	23	33	43	4	<0.03
C340	33	<0.2	22	19	32	9	1	<0.03
C341	8	<0.2	12	14	15	<1	<1	<0.03
C342	47	<0.2	12	11	25	<1	<1	<0.03
C343	23	<0.2	13	40	20	<1	<1	<0.03
C344	12	<0.2	8	58	13	<1	<1	<0.03
C345	14	<0.2	6	16	3	10	<1	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C346	17	<0.2	11	8	12	4	<1	<0.03
C347	12	<0.2	6	5	3	7	<1	<0.03
C348	17	<0.2	15	9	16	9	1	<0.03
C349	25	<0.2	8	8	7	9	<1	<0.03
C350	11	<0.2	9	8	9	5	<1	<0.03
C351	54	<0.2	17	13	23	6	5	<0.03
C352	20	<0.2	12	6	7	6	6	<0.03
C353	23	<0.2	13	7	11	7	4	<0.03
C354	13	<0.2	12	9	9	7	<1	<0.03
C355	18	<0.2	7	6	6	6	<1	<0.03
C356	27	<0.2	12	6	6	10	5	0.52
C357	21	<0.2	8	4	2	13	<1	<0.03
C358	12	<0.2	13	9	9	13	8	0.03
C359	10	<0.2	11	8	13	9	4	<0.03
C360	11	<0.2	14	11	13	11	6	<0.03
C361	11	<0.2	9	11	9	13	5	<0.03
C362	13	<0.2	15	9	9	10	6	<0.03
C363	8	<0.2	8	11	11	7	<1	<0.03
C364	8	<0.2	6	8	7	7	<1	<0.03
C365	9	<0.2	7	13	2	3	<1	<0.03
C366	22	<0.2	10	12	8	<1	<1	<0.03
C367	10	<0.2	11	6	5	13	2	<0.03
C368	24	<0.2	14	14	18	3	8	<0.03
C369	19	<0.2	13	17	23	<1	4	<0.03
C370	10	<0.2	7	9	9	7	1	<0.03
C371	15	<0.2	14	13	21	<1	5	<0.03
C372	24	<0.2	19	20	16	3	12	<0.03
C373	98	<0.2	18	19	26	3	9	<0.03
C374	16	<0.2	14	14	15	3	6	<0.03
C375	26	<0.2	12	16	20	<1	2	<0.03
C376	11	<0.2	13	10	10	<1	<1	<0.03
C377	11	<0.2	8	10	10	3	<1	<0.03
C378	21	<0.2	12	16	10	4	5	<0.03
C379	18	<0.2	8	12	19	1	<1	<0.03
C380	11	<0.2	7	17	7	4	<1	<0.03
C381	41	<0.2	14	25	13	7	7	<0.03
C382	16	<0.2	15	12	15	9	5	<0.03
C383	21	<0.2	16	11	9	9	13	<0.03
C384	11	<0.2	14	13	22	5	8	<0.03
C385	17	<0.2	22	16	31	5	7	<0.03
C386	6	<0.2	12	9	6	9	<1	<0.03
C387	27	<0.2	41	30	54	3	18	<0.03
C388	5	<0.2	11	9	14	10	<1	0.03
C389	35	<0.2	39	37	42	<1	17	0.03
C390	32	<0.2	34	36	45	<1	16	0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C391	23	<0.2	40	142	140	<1	11	<0.03
C392	5	<0.2	10	7	9	11	<1	<0.03
C393	19	<0.2	17	15	12	7	10	<0.03
C394	17	<0.2	14	7	8	15	6	<0.03
C395	8	<0.2	10	18	11	4	<1	<0.03
C396	2	<0.2	11	13	8	11	<1	<0.03
C397	10	<0.2	15	14	19	6	5	<0.03
C398	7	<0.2	16	11	16	13	2	<0.03
C399	9	<0.2	15	12	18	13	6	<0.03
C400	23	<0.2	16	12	21	8	6	<0.03
C401	11	<0.2	17	15	20	5	4	<0.03
C402	14	<0.2	16	16	16	7	7	<0.03
C403	11	<0.2	12	11	15	6	1	<0.03
C404	10	<0.2	12	10	12	11	1	<0.03
C405	14	<0.2	15	11	20	11	3	<0.03
C406	10	<0.2	21	14	20	13	11	<0.03
C407	7	<0.2	16	9	13	11	3	<0.03
C408	5	<0.2	13	11	16	8	1	<0.03
C409	5	<0.2	13	9	7	12	6	<0.03
C410	5	<0.2	7	13	10	24	4	<0.03
C411	5	<0.2	9	14	15	18	2	<0.03
C412	5	<0.2	15	15	16	13	8	<0.03
C413	3	<0.2	9	10	11	11	2	<0.03
C414	5	<0.2	10	20	10	8	1	<0.03
C415	5	<0.2	12	37	12	14	4	<0.03
C416	4	<0.2	11	15	6	11	6	<0.03
C417	3	<0.2	9	9	10	6	<1	<0.03
C418	9	<0.2	10	29	16	5	<1	<0.03
C419	3	<0.2	7	15	4	8	<1	<0.03
C420	5	<0.2	11	9	9	8	<1	<0.03
C421	3	<0.2	8	10	6	6	<1	<0.03
C422	5	<0.2	5	5	4	7	<1	<0.03
C423	7	<0.2	11	7	8	7	1	<0.03
C424	283	<0.2	15	6	5	6	1	<0.03
C425	13	<0.2	11	10	14	<1	<1	<0.03
C426	19	<0.2	12	15	13	<1	<1	<0.03
C427	5	<0.2	12	10	6	<1	<1	<0.03
C428	5	<0.2	11	5	10	5	<1	<0.03
C429	5	<0.2	12	7	10	6	<1	<0.03
C430	5	<0.2	13	13	12	6	2	<0.03
C431	5	<0.2	6	10	15	7	<1	<0.03
C432	4	<0.2	8	10	12	6	<1	<0.03
C433	5	<0.2	14	12	10	4	4	<0.03
C434	5	<0.2	8	13	13	6	<1	<0.03
C435	3	<0.2	8	9	10	4	<1	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
C436	3	<0.2	7	6	5	4	<1	<0.03
C437	7	<0.2	11	13	12	4	2	<0.03
C438	4	<0.2	11	11	12	5	2	<0.03
C439	3	<0.2	7	8	7	4	<1	<0.03
C440	4	<0.2	11	10	8	4	<1	<0.03
C441	3	<0.2	12	3	5	3	1	<0.03
C442	8	<0.2	12	4	5	3	1	<0.03
C443	3	<0.2	11	10	8	2	2	<0.03
C444	3	<0.2	11	9	6	2	2	<0.03
D001	3	<0.2	6	14	16	9	3	<0.03
D002	4	<0.2	16	25	23	5	7	<0.03
D003	2	<0.2	17	21	25	3	2	<0.03
D004	3	<0.2	13	16	10	8	3	<0.03
D005	<1	<0.2	14	15	13	7	1	<0.03
D006	1	<0.2	7	21	18	5	<1	<0.03
D007	1	<0.2	8	25	17	1	<1	<0.03
D008	3	<0.2	15	24	23	4	<1	<0.03
D009	1	<0.2	17	23	19	5	2	<0.03
D010	3	<0.2	15	23	23	4	2	<0.03
D011	3	<0.2	14	24	21	4	5	<0.03
D012	6	<0.2	13	15	8	8	7	<0.03
D013	3	<0.2	17	23	16	4	9	<0.03
D014	7	<0.2	19	27	16	3	10	<0.03
D015	8	<0.2	21	29	32	9	2	<0.03
D016	4	<0.2	15	25	20	6	4	<0.03
D017	3	<0.2	13	14	9	8	2	<0.03
D018	4	<0.2	19	23	18	2	6	<0.03
D019	3	<0.2	11	14	11	8	<1	<0.03
D020	7	<0.2	21	29	24	7	3	<0.03
D021	3	<0.2	18	20	17	10	1	<0.03
D022	4	<0.2	13	28	19	9	1	<0.03
D023	9	<0.2	33	47	74	1	<1	0.03
D024	8	<0.2	34	43	47	7	4	<0.03
D025	1	<0.2	16	23	18	9	<1	<0.03
D026	6	<0.2	19	26	20	8	4	<0.03
D027	5	<0.2	16	27	23	6	<1	<0.03
D028	6	<0.2	18	30	26	10	<1	<0.03
D029	7	<0.2	25	54	52	16	2	<0.03
D030	6	<0.2	23	36	43	18	2	<0.03
D031	4	<0.2	24	30	25	13	5	<0.03
D032	2	<0.2	20	33	29	10	2	<0.03
D033	33	<0.2	24	32	27	16	4	<0.03
D034	9	<0.2	21	25	20	12	7	<0.03
D035	5	<0.2	20	29	22	13	5	<0.03
D036	4	<0.2	22	34	26	14	9	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
D037	6	<0.2	22	30	25	13	7	<0.03
D038	5	<0.2	21	34	24	12	9	<0.03
D039	5	<0.2	19	34	26	11	4	<0.03
D040	7	<0.2	18	24	15	13	7	<0.03
D041	3	<0.2	10	17	10	15	1	<0.03
D042	2	<0.2	12	16	11	15	5	<0.03
D043	5	<0.2	17	29	21	11	3	<0.03
D044	6	<0.2	24	40	23	14	10	0.09
D045	7	<0.2	14	19	10	8	4	<0.03
D046	5	<0.2	18	32	24	18	11	<0.03
D047	10	<0.2	18	31	29	2	7	<0.03
D048	8	<0.2	24	29	31	3	5	<0.03
D049	8	<0.2	24	37	30	6	8	<0.03
D050	6	<0.2	15	24	21	10	5	<0.03
D051	5	<0.2	21	39	26	16	16	<0.03
D052	6	<0.2	15	21	18	9	2	<0.03
D053	12	<0.2	21	40	31	8	7	<0.03
D054	11	<0.2	20	31	26	6	6	<0.03
D055	11	<0.2	18	32	27	3	3	<0.03
D056	3	<0.2	18	22	18	<1	3	<0.03
D057	6	<0.2	24	37	29	9	7	<0.03
D058	4	<0.2	14	23	16	3	1	<0.03
D059	8	<0.2	24	47	35	18	19	<0.03
D060	8	<0.2	21	27	21	<1	2	<0.03
D061	4	<0.2	19	38	25	4	8	<0.03
D062	6	<0.2	14	26	21	<1	1	<0.03
D063	6	<0.2	16	20	18	3	2	<0.03
D064	9	<0.2	23	44	32	10	14	<0.03
D065	12	<0.2	45	59	101	<1	2	0.06
D066	5	<0.2	16	17	16	12	1	<0.03
D067	3	<0.2	17	17	12	11	<1	<0.03
D068	6	<0.2	34	41	153	17	5	0.06
D069	2	<0.2	13	17	12	9	<1	<0.03
D071	7	<0.2	13	19	13	12	<1	<0.03
D072	6	<0.2	17	26	24	6	1	0.04
D073	6	<0.2	17	33	21	23	17	<0.03
D074	201	<0.2	17	25	27	9	1	<0.03
D075	8	<0.2	16	26	24	7	1	<0.03
D076	7	<0.2	15	18	15	14	2	<0.03
D077	8	<0.2	22	30	27	13	6	<0.03
D078	9	<0.2	18	32	25	19	8	<0.03
D079	10	<0.2	20	31	26	10	2	<0.03
D080	4	<0.2	21	33	24	18	11	<0.03
D081	3	<0.2	14	27	23	15	2	<0.03
D082	3	<0.2	14	25	24	11	<1	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
D083	3	<0.2	17	28	25	12	2	<0.03
D084	16	<0.2	31	50	62	32	15	0.05
D086	7	<0.2	15	27	18	17	5	0.03
D087	18	<0.2	48	43	61	26	19	<0.03
D088	4	<0.2	19	28	22	4	5	<0.03
D089	9	<0.2	22	26	23	2	9	<0.03
D090	9	<0.2	23	27	23	3	8	<0.03
D091	8	<0.2	18	28	22	3	8	<0.03
D092	5	<0.2	24	32	23	7	13	<0.03
D093	6	<0.2	20	31	24	18	20	<0.03
D094	7	<0.2	17	25	22	4	<1	<0.03
D095	5	<0.2	15	26	22	1	1	<0.03
D096	8	<0.2	13	22	21	2	<1	<0.03
D097	2	<0.2	11	24	19	11	6	<0.03
D099	3	0.2	15	23	20	<1	<1	<0.03
D100	6	<0.2	15	20	22	<1	<1	<0.03
D101	4	<0.2	11	17	15	4	<1	<0.03
D102	3	<0.2	16	28	28	10	9	<0.03
D103	6	<0.2	30	37	50	7	18	<0.03
D104	4	<0.2	15	18	17	2	2	<0.03
D105	5	<0.2	19	24	28	1	11	<0.03
D106	4	<0.2	14	22	16	5	3	<0.03
D107	8	<0.2	24	28	35	<1	11	0.06
D108	2	<0.2	15	19	21	<1	2	<0.03
D109	4	<0.2	20	32	27	17	17	<0.03
D110	6	<0.2	22	21	28	<1	5	<0.03
D111	7	<0.2	27	24	26	<1	10	0.04
D112	9	<0.2	27	22	60	<1	7	<0.03
D113	10	<0.2	56	26	151	7	12	0.06
D114	10	<0.2	34	28	76	<1	7	<0.03
D115	7	<0.2	25	24	41	<1	7	<0.03
D116	6	<0.2	26	30	35	12	16	0.10
D117	7	<0.2	53	43	100	<1	12	0.03
D118	5	<0.2	27	23	36	<1	5	<0.03
D119	9	<0.2	28	25	46	<1	4	<0.03
D120	6	<0.2	26	30	34	7	15	<0.03
D121	6	<0.2	26	26	41	<1	6	<0.03
D122	7	<0.2	36	42	60	17	21	<0.03
D123	6	<0.2	36	32	60	<1	4	0.05
D124	8	<0.2	42	74	69	21	50	<0.03
D126	5	<0.2	19	31	32	19	4	<0.03
D128	6	<0.2	24	43	29	<1	3	<0.03
D129	8	<0.2	23	21	25	7	6	<0.03
D130	17	<0.2	17	19	16	2	7	<0.03
D131	6	<0.2	18	20	13	5	9	<0.03

Sample No.	Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	As ppm	Sb ppm	Hg ppm
D132	2	<0.2	15	18	11	7	12	<0.03
D133	6	<0.2	20	19	17	<1	12	<0.03
D134	4	<0.2	16	23	21	3	11	<0.03
D135	4	<0.2	17	18	21	<1	4	<0.03
D136	6	<0.2	18	20	23	<1	6	<0.03
D137	5	<0.2	23	27	27	11	14	<0.03
D138	4	<0.2	18	20	15	10	7	<0.03
D139	2	<0.2	17	21	22	9	7	<0.03
D140	2	<0.2	14	17	15	14	8	<0.03
D141	5	<0.2	15	22	18	6	2	<0.03
D142	5	<0.2	19	25	17	13	14	<0.03
D143	3	<0.2	17	29	23	17	12	<0.03
D144	5	<0.2	24	19	11	12	12	<0.03
D145	5	<0.2	16	27	21	15	9	<0.03
D146	5	<0.2	16	19	19	6	5	<0.03
D147	5	<0.2	16	20	14	9	5	<0.03
D148	8	<0.2	15	23	11	16	9	<0.03
D149	6	<0.2	22	29	23	8	8	<0.03
D150	4	<0.2	22	29	22	11	7	<0.03
D151	7	<0.2	26	34	22	21	15	<0.03
D152	5	<0.2	17	28	17	4	<1	<0.03
D153	5	<0.2	21	27	20	17	8	0.06
D154	4	<0.2	17	25	16	9	6	<0.03
D155	8	<0.2	27	30	31	14	5	<0.03
D156	3	<0.2	16	40	18	21	13	<0.03
D157	6	<0.2	26	32	33	13	3	<0.03
D158	7	<0.2	25	39	25	18	12	<0.03
D159	6	<0.2	19	30	21	14	10	<0.03
D160	8	<0.2	27	42	29	26	17	<0.03
D161	4	<0.2	15	23	10	9	1	<0.03
D162	5	<0.2	22	29	30	5	<1	<0.03
D163	3	<0.2	22	36	26	<1	6	<0.03
D164	5	<0.2	27	39	33	14	13	<0.03
D165	5	<0.2	20	30	22	<1	<1	<0.03
D166	7	<0.2	30	34	34	6	10	<0.03
D167	8	<0.2	32	32	34	4	5	<0.03
D168	8	<0.2	30	32	37	8	<1	<0.03
D169	7	<0.2	22	31	21	9	5	<0.03
D170	2	<0.2	39	66	82	24	4	<0.03
D171	3	<0.2	51	60	76	19	15	<0.03
D172	10	<0.2	48	54	76	14	6	<0.03
D173	11	<0.2	50	59	76	19	15	<0.03
D174	11	<0.2	39	52	56	7	3	<0.03
D175	8	<0.2	38	47	62	6	2	<0.03
D176	5	<0.2	39	59	57	4	8	<0.03