

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m)	Au(g/t)		Ag(g/t)	As(%)		W(%)		Discriptions
				Lower limits	0.1g/t		0.1g/t	1g/t	0.01%	0.001%	
421	B- 619	38.00 ~ 39.70	1.70	< 0.1	< 1	< 1	0.02	0.001			
422	B- 620	39.70 ~ 41.30	1.60	< 0.1	< 1	< 1	< 0.01	0.001			
423	B- 621	41.30 ~ 42.50	1.20	< 0.1	< 1	< 1	0.02	0.001			
424	B- 622	42.50 ~ 43.70	1.20	0.2	< 1	< 1	0.02	0.001			
425	B- 623	43.70 ~ 44.90	1.20	< 0.1	< 1	< 1	< 0.01	< 0.001			
426	B- 624	44.90 ~ 45.90	1.00	< 0.1	< 1	< 1	0.03	< 0.001			
427	B- 625	47.90 ~ 49.00	1.10	< 0.1	< 1	< 1	< 0.01	< 0.001			
428	B- 626	49.00 ~ 50.00	1.00	< 0.1	1.6	< 1	0.01	< 0.001			
429	B- 627	51.70 ~ 53.00	1.30	0.2	< 1	< 1	0.02	< 0.001			
430	B- 628	53.00 ~ 54.40	1.40	0.2	< 1	< 1	< 0.01	< 0.001			
431	B- 629	54.40 ~ 56.40	2.00	< 0.1	< 1	< 1	0.02	< 0.001			
432	B- 630	61.60 ~ 63.00	1.40	0.3	1.4	< 1	0.04	< 0.001			
433	B- 631	63.00 ~ 64.50	1.50	< 0.1	< 1	< 1	0.02	0.001			
434	B- 632	64.50 ~ 65.70	1.20	< 0.1	< 1	< 1	0.02	< 0.001			
435	B- 633	66.50 ~ 67.50	1.00	0.3	< 1	< 1	< 0.01	< 0.001			
436	B- 634	74.90 ~ 76.00	1.10	0.1	< 1	< 1	0.02	< 0.001			
437	B- 635	76.00 ~ 77.00	1.00	0.2	3.0	< 1	0.05	0.002			
438	B- 636	77.00 ~ 78.00	1.00	0.1	< 1	< 1	0.08	0.002			
439	B- 637	78.00 ~ 79.00	1.00	0.1	2.0	< 1	0.04	0.001			
440	B- 638	82.60 ~ 83.80	1.20	0.3	< 1	< 1	0.08	< 0.001			
441	B- 639	84.70 ~ 85.80	1.10	< 0.1	< 1	< 1	0.02	< 0.001			
442	B- 640	86.50 ~ 87.40	0.90	0.6	2.2	< 1	0.02	0.007			
443	B- 641	135.40 ~ 136.40	1.00	0.2	< 1	< 1	0.02	0.001			
444	B- 642	136.40 ~ 137.40	1.00	< 0.1	< 1	< 1	< 0.01	< 0.001			
445	B- 643	140.40 ~ 140.65	0.25	0.8	1.6	< 1	0.03	0.003			
446	B- 644	144.00 ~ 144.50	0.50	0.2	1.8	< 1	0.04	0.001			
447	B- 645	149.50 ~ 150.50	1.00	< 0.1	< 1	< 1	< 0.01	0.001			
448	B- 646	150.50 ~ 151.50	1.00	0.1	< 1	< 1	0.01	< 0.001			
449	B- 647	151.50 ~ 152.50	1.00	< 0.1	< 1	< 1	0.01	< 0.001			
450	B- 648	152.50 ~ 153.50	1.00	< 0.1	< 1	< 1	< 0.01	< 0.001			

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)		As(%)		W(%)		Discriptions
				0.1g/t	< 0.1	1g/t	< 1	0.01%	< 0.01	0.001%	< 0.001	
451	B-649	153.50 ~ 154.20	0.70	< 0.1	< 1	< 0.01	< 0.001	< 0.01	< 0.001			
452	B-650	154.20 ~ 155.20	1.00	< 0.1	< 1	< 0.01	< 0.001	< 0.01	< 0.001			
453	B-651	155.20 ~ 156.40	1.20	< 0.1	< 1	< 0.01	< 0.001	< 0.01	< 0.001			
454	B-652	158.35 ~ 159.00	0.65	< 0.1	< 1	< 0.01	< 0.001	< 0.01	< 0.001			
455	B-653	159.00 ~ 160.00	1.00	< 0.1	< 1	< 0.01	< 0.001	< 0.01	< 0.001			
456	B-654	171.70 ~ 173.00	1.30	< 0.1	< 1	< 0.01	< 0.001	< 0.01	< 0.001			
457	B-655	6.50 ~ 7.50	1.00	< 0.1	< 1	0.02	< 0.001	0.02	< 0.001			
458	B-656	7.50 ~ 8.50	1.00	< 0.1	< 1	0.01	< 0.001	0.01	< 0.001			
459	B-657	8.50 ~ 9.50	1.00	< 0.1	< 1	0.02	0.001	0.02	0.001			
460	B-658	9.50 ~ 10.70	1.20	< 0.1	< 1	0.02	0.001	0.02	0.001			
461	B-659	22.30 ~ 23.50	1.20	0.2	< 1	0.02	< 0.001	0.02	< 0.001			
462	B-660	23.50 ~ 24.70	1.20	< 0.1	< 1	0.01	< 0.001	0.01	< 0.001			
463	B-661	24.70 ~ 26.00	1.30	< 0.1	< 1	0.02	< 0.001	0.02	< 0.001			
464	B-662	28.30 ~ 29.30	1.00	0.2	< 1	0.02	< 0.001	0.02	< 0.001			
465	B-663	29.30 ~ 30.30	1.00	0.2	< 1	0.03	< 0.001	0.03	< 0.001			
466	B-664	50.00 ~ 51.70	1.70	0.2	3.2	0.02	0.001	0.02	0.001			
467	B-665	56.40 ~ 57.25	0.85	0.3	< 1	0.02	0.001	0.02	0.001			
468	B-666	60.40 ~ 61.60	1.20	0.4	< 1	0.21	0.003	0.21	0.003			
469	B-667	65.70 ~ 66.50	0.80	< 0.1	< 1	0.02	< 0.001	0.02	< 0.001			
470	B-668	67.50 ~ 69.00	1.50	< 0.1	< 1	< 0.01	< 0.001	< 0.01	< 0.001			
471	B-669	69.00 ~ 70.20	1.20	< 0.1	< 1	< 0.01	0.001	< 0.01	0.001			
472	B-670	73.00 ~ 74.00	1.00	< 0.1	< 1	0.02	< 0.001	0.02	< 0.001			
473	B-671	74.00 ~ 74.90	0.90	< 0.1	< 1	0.02	< 0.001	0.02	< 0.001			
474	B-672	89.40 ~ 90.00	0.60	< 0.1	< 1	0.04	0.001	0.04	0.001			
475	B-673	140.65 ~ 141.60	0.95	0.2	< 1	< 0.01	0.001	< 0.01	0.001			
476	B-674	141.60 ~ 142.60	1.00	0.2	< 1	< 0.01	< 0.001	< 0.01	< 0.001			
477	B-701	3.00 ~ 4.40	1.40	< 0.1	1.0	0.02	0.002	0.02	0.002			
478	B-702	4.40 ~ 5.40	1.00	< 0.1	< 1	0.02	0.001	0.02	0.001			
479	B-703	9.40 ~ 11.00	1.60	0.2	< 1	0.02	0.001	0.02	0.001			
480	B-704	13.90 ~ 15.20	1.30	0.2	< 1	0.01	0.001	0.01	0.001			

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)		As(%)		W(%)		Discriptions
				0.1g/t	< 0.1	1g/t	< 1	0.01%	< 0.02	0.001%	< 0.001	
481	B-705	15.20 ~ 16.20	1.00	< 0.1	< 1	< 0.02	< 0.001					
482	B-706	16.20 ~ 17.25	1.05	< 0.1	< 1	0.01	0.001					
483	B-707	22.00 ~ 23.00	1.00	< 0.1	0.6	0.02	0.003					
484	B-708	26.20 ~ 27.20	1.00	< 0.1	< 1	0.02	0.002					
485	B-709	27.20 ~ 28.50	1.30	< 0.1	< 1	0.02	0.001					
486	B-710	28.50 ~ 30.00	1.50	< 0.1	3.0	0.02	0.002					
487	B-711	30.00 ~ 31.00	1.00	< 0.1	< 1	0.03	< 0.001					
488	B-712	31.00 ~ 32.15	1.15	< 0.1	< 1	0.02	< 0.001					
489	B-713	32.15 ~ 33.05	0.90	< 0.1	3.4	0.02	< 0.001					
490	B-714	33.05 ~ 34.00	0.95	0.5	2.6	0.09	0.004					
491	B-715	34.00 ~ 35.00	1.00	0.2	< 1	0.02	0.001					
492	B-716	35.00 ~ 35.60	0.60	0.4	< 1	0.10	0.004					
493	B-717	35.60 ~ 36.70	1.10	0.7	4.6	0.31	0.003					
494	B-718	36.70 ~ 37.90	1.20	0.6	7.2	0.12	0.007					
495	B-719	37.90 ~ 39.55	1.65	0.8	1.6	0.07	0.002					
496	B-720	39.55 ~ 41.00	1.45	< 0.1	7.6	0.03	0.002					
497	B-721	41.00 ~ 42.50	1.50	< 0.1	< 1	0.02	< 0.001					
498	B-722	42.50 ~ 43.50	1.00	< 0.1	< 1	0.01	< 0.001					
499	B-723	43.50 ~ 44.50	1.00	< 0.1	8.0	0.02	< 0.001					
500	B-724	49.50 ~ 50.80	1.30	< 0.1	< 1	< 0.01	0.002					
501	B-725	50.80 ~ 51.90	1.10	< 0.1	< 1	0.05	0.002					
502	B-726	53.40 ~ 54.35	0.95	< 0.1	< 1	0.04	0.005					
503	B-727	55.15 ~ 56.55	1.40	< 0.1	< 1	< 0.01	0.005					
504	B-728	56.55 ~ 57.60	1.05	< 0.1	< 1	0.01	0.001					
505	B-729	57.60 ~ 58.70	1.10	0.2	< 1	0.08	0.003					
506	B-730	58.70 ~ 59.30	0.60	< 0.1	7.0	0.07	0.003					
507	B-731	61.40 ~ 63.00	1.60	< 0.1	< 1	< 0.01	0.002					
508	B-732	65.00 ~ 66.65	1.65	< 0.1	< 1	< 0.01	0.002					
509	B-733	66.65 ~ 67.75	1.10	< 0.1	< 1	< 0.01	0.002					
510	B-734	67.75 ~ 68.85	1.10	< 0.1	< 1	0.01	0.001					

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) <small>Lower limit⇒</small>	Au(g/t)		Ag(g/t)	As(%)	W(%)	Discriptions
				0.1g/t	< 0.1				
511	B-735	68.85 ~ 70.00	1.15	< 0.1	< 1	0.03	< 0.001		
512	B-736	70.00 ~ 71.50	1.50	0.2	< 1	0.03	< 0.001		
513	B-737	71.50 ~ 72.90	1.40	0.3	< 1	0.20	< 0.001		
514	B-738	78.90 ~ 79.10	0.20	< 0.1	< 1	0.05	< 0.001		
515	B-739	115.50 ~ 116.50	1.00	0.1	< 1	0.04	0.001		
516	B-740	116.50 ~ 117.50	1.00	< 0.1	< 1	0.02	0.003		
517	B-741	117.50 ~ 118.35	0.85	0.1	< 1	0.02	0.002		
518	B-742	118.35 ~ 119.50	1.15	< 0.1	< 1	0.03	0.002		
519	B-743	119.50 ~ 120.95	1.45	< 0.1	< 1	0.02	0.001		
520	B-744	120.95 ~ 121.80	0.85	< 0.1	< 1	< 0.01	0.001		
521	B-745	121.80 ~ 123.20	1.40	< 0.1	< 1	0.14	0.002		
522	B-746	123.20 ~ 124.30	1.10	0.2	< 1	0.02	0.002		
523	B-747	124.30 ~ 125.30	1.00	< 0.1	< 1	0.02	0.002		
524	B-748	125.30 ~ 126.30	1.00	0.2	< 1	0.04	0.002		
525	B-749	126.30 ~ 127.30	1.00	0.2	< 1	0.02	0.002		
526	B-750	137.50 ~ 138.20	0.70	0.3	< 1	0.02	0.002		
527	B-751	138.20 ~ 139.00	0.80	< 0.1	< 1	< 0.01	0.002		
528	B-752	139.00 ~ 139.70	0.70	< 0.1	< 1	0.06	0.002		
529	B-753	139.70 ~ 140.50	0.80	0.1	< 1	0.67	0.002		
530	B-754	140.50 ~ 141.30	0.80	0.1	< 1	0.06	0.001		
531	B-755	141.30 ~ 142.30	1.00	0.4	< 1	< 0.01	0.003		
532	B-756	142.30 ~ 143.30	1.00	0.4	< 1	0.09	0.004		
533	B-757	143.30 ~ 144.30	1.00	0.2	< 1	0.04	0.002		
534	B-758	144.30 ~ 145.20	0.90	0.1	< 1	0.03	0.003		
535	B-759	145.20 ~ 146.50	1.30	< 0.1	< 1	0.01	0.001		
536	B-760	147.80 ~ 148.90	1.10	0.2	< 1	0.05	0.001		
537	B-761	149.50 ~ 151.00	1.50	0.1	< 1	0.02	0.002		
538	B-762	151.00 ~ 152.50	1.50	< 0.1	< 1	0.02	0.005		
539	B-763	152.50 ~ 154.00	1.50	< 0.1	< 1	< 0.01	0.003		
540	B-764	154.00 ~ 155.20	1.20	< 0.1	< 1	0.02	0.002		

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)		As(%)		W(%)		Discriptions
				0.1g/t	< 0.1	1g/t	< 1	0.01%	< 0.01%	0.001%	< 0.001	
541	B- 765	157.30 ~ 158.50	1.20	< 0.1	< 1	< 0.01	< 0.001					
542	B- 766	158.50 ~ 159.50	1.00	< 0.1	< 1	0.02	0.001					
543	B- 767	159.50 ~ 160.50	1.00	0.1	< 1	0.02	0.001					
544	B- 768	160.50 ~ 161.50	1.00	0.1	< 1	0.06	0.001					
545	B- 769	167.40 ~ 168.50	1.10	0.5	< 1	0.05	0.003					
546	B- 770	168.50 ~ 169.50	1.00	< 0.1	< 1	< 0.01	0.001					
547	B- 771	169.50 ~ 170.50	1.00	< 0.1	< 1	0.01	0.001					
548	B- 772	170.50 ~ 171.50	1.00	0.4	< 1	0.04	0.001					
549	B- 773	171.50 ~ 172.50	1.00	0.1	< 1	0.04	0.008					
550	B- 774	172.50 ~ 173.50	1.00	0.1	< 1	0.01	0.002					
551	B- 775	173.50 ~ 174.33	0.83	< 0.1	< 1	0.01	0.002					
552	B- 776	174.33 ~ 174.70	0.37	< 0.1	< 1	0.01	0.001					
553	B- 777	174.70 ~ 175.70	1.00	< 0.1	< 1	< 0.01	< 0.001					
554	B- 778	175.70 ~ 176.60	0.90	< 0.1	< 1	0.04	0.002					
555	B- 779	176.60 ~ 177.60	1.00	0.2	< 1	0.25	0.004					
556	B- 780	177.60 ~ 178.80	1.20	< 0.1	< 1	0.02	0.001					
557	B- 801	4.70 ~ 6.00	1.30	< 0.1	< 1	0.03	0.001					
558	B- 802	6.00 ~ 7.30	1.30	0.1	< 1	0.01	0.002					
559	B- 803	7.30 ~ 9.00	1.70	0.2	< 1	0.01	0.002					
560	B- 804	9.00 ~ 10.50	1.50	0.4	< 1	0.04	0.003					
561	B- 805	14.30 ~ 15.90	1.60	0.3	< 1	0.06	0.003					
562	B- 806	15.90 ~ 17.60	1.70	0.2	< 1	0.02	0.002					
563	B- 807	17.60 ~ 18.90	1.30	0.3	< 1	0.01	0.003					
564	B- 808	18.90 ~ 20.00	1.10	0.4	< 1	0.06	0.003					
565	B- 809	20.00 ~ 21.60	1.60	0.8	< 1	0.02	0.004					
566	B- 810	27.80 ~ 28.90	1.10	1.6	< 1	0.05	0.001					
567	B- 811	30.70 ~ 32.30	1.60	< 0.1	< 1	0.01	0.001					
568	B- 812	33.40 ~ 34.65	1.25	0.1	< 1	0.01	0.002					
569	B- 813	36.30 ~ 38.10	1.80	0.1	3.2	0.04	0.001					
570	B- 814	38.10 ~ 39.30	1.20	0.1	1.2	0.05	0.002					

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)	As(%)	W(%)	Discriptions
				0.1g/t	1g/t				
571	B-815	39.30 ~ 40.30	1.00	0.1	< 1	0.05	0.001		
572	B-816	40.30 ~ 41.50	1.20	0.1	< 1	0.01	0.002		
573	B-817	41.50 ~ 42.50	1.00	0.1	< 1	0.02	0.003		
574	B-818	45.00 ~ 46.40	1.40	< 0.1	< 1	0.02	0.001		
575	B-819	46.40 ~ 47.90	1.50	0.3	< 1	0.04	0.003		
576	B-820	47.90 ~ 48.90	1.00	0.2	< 1	0.02	0.003		
577	B-821	48.90 ~ 49.90	1.00	0.1	< 1	< 0.01	0.003		
578	B-822	49.90 ~ 50.80	0.90	0.1	< 1	< 0.01	0.002		
579	B-823	50.80 ~ 51.05	0.25	1.5	< 1	0.27	0.002		
580	B-824	51.05 ~ 52.30	1.25	0.1	< 1	0.01	0.002		
581	B-825	52.30 ~ 53.30	1.00	< 0.1	< 1	< 0.01	0.002		
582	B-826	53.30 ~ 54.50	1.20	0.4	< 1	0.02	< 0.001		
583	B-827	54.50 ~ 55.30	0.80	< 0.1	< 1	0.02	0.002		
584	B-828	55.30 ~ 56.35	1.05	0.1	2.4	0.01	0.002		
585	B-829	57.90 ~ 59.00	1.10	0.4	< 1	0.10	0.003		
586	B-830	60.25 ~ 61.40	1.15	< 0.1	< 1	< 0.01	0.001		
587	B-831	61.40 ~ 62.80	1.40	1.6	5.2	0.10	0.010		
588	B-832	62.80 ~ 63.30	0.50	0.1	< 1	< 0.01	0.002		
589	B-833	63.30 ~ 64.70	1.40	0.2	< 1	0.04	0.002		
590	B-834	64.70 ~ 65.70	1.00	0.8	< 1	0.05	0.004		
591	B-835	65.70 ~ 66.70	1.00	0.1	2.4	0.03	0.003		
592	B-836	66.70 ~ 68.00	1.30	< 0.1	5.2	< 0.01	0.003		
593	B-837	68.00 ~ 69.50	1.50	< 0.1	< 1	< 0.01	0.002		
594	B-838	69.50 ~ 71.00	1.50	0.1	< 1	< 0.01	0.002		
595	B-839	71.00 ~ 72.00	1.00	0.1	< 1	0.02	< 0.001		
596	B-840	72.00 ~ 73.40	1.40	< 0.1	< 1	< 0.01	< 0.001		
597	B-841	73.40 ~ 74.40	1.00	0.5	1.8	0.04	0.002		
598	B-842	80.40 ~ 80.80	0.40	2.2	< 1	0.12	0.020		
599	B-843	82.30 ~ 83.40	1.10	0.4	< 1	0.13	0.004		
600	B-844	83.40 ~ 84.40	1.00	1.0	< 1	0.14	0.080		

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)	As(%)	W(%)		Discriptions
				0.1g/t	1g/t			0.01%	0.001%	
601	B-845	84.40 ~ 85.40	1.00	0.4	< 1	< 1	0.06	0.003		
602	B-846	85.40 ~ 86.60	1.20	0.2	< 1	< 1	0.03	0.004		
603	B-847	86.60 ~ 87.40	0.80	0.2	< 1	< 1	0.02	0.010		
604	B-848	87.40 ~ 88.40	1.00	0.8	< 1	< 1	0.07	0.004		
605	B-849	88.40 ~ 89.70	1.30	0.1	< 1	< 1	0.02	0.002		
606	B-850	89.70 ~ 90.90	1.20	0.1	< 1	< 1	0.05	0.005		
607	B-851	94.40 ~ 95.50	1.10	0.1	< 1	< 1	0.02	0.001		
608	B-852	95.50 ~ 96.50	1.00	0.6	< 1	< 1	0.01	0.003		
609	B-853	96.50 ~ 97.50	1.00	0.6	< 1	< 1	0.12	0.003		
610	B-854	97.50 ~ 98.40	0.90	< 0.1	< 1	< 1	0.03	0.002		
611	B-855	98.40 ~ 99.60	1.20	0.2	< 1	< 1	0.05	0.001		
612	B-856	99.60 ~ 100.50	0.90	0.2	2.8	2.8	0.06	0.004		
613	B-857	100.50 ~ 101.60	1.10	< 0.1	< 1	< 1	0.05	0.004		
614	B-858	103.60 ~ 104.40	0.80	0.2	< 1	< 1	0.07	0.002		
615	B-859	104.40 ~ 105.70	1.30	0.8	< 1	< 1	0.12	0.001		
616	B-860	107.50 ~ 108.90	1.40	0.1	< 1	< 1	0.04	0.003		
617	B-861	108.90 ~ 109.70	0.80	0.1	< 1	< 1	0.08	0.002		
618	B-862	115.70 ~ 116.40	0.70	< 0.1	< 1	< 1	0.02	0.002		
619	B-863	117.80 ~ 119.20	1.40	< 0.1	< 1	< 1	0.15	0.002		
620	B-864	119.20 ~ 120.80	1.60	< 0.1	< 1	< 1	0.06	0.002		
621	B-865	120.80 ~ 122.00	1.20	0.4	< 1	< 1	0.04	0.002		
622	B-866	122.00 ~ 123.20	1.20	0.1	< 1	< 1	0.01	0.002		
623	B-867	123.20 ~ 124.40	1.20	0.4	< 1	< 1	0.05	0.002		
624	B-868	125.50 ~ 126.70	1.20	0.6	3.6	3.6	0.08	0.003		
625	B-869	127.80 ~ 128.50	0.70	0.4	< 1	< 1	0.04	0.002		
626	B-870	128.50 ~ 130.00	1.50	0.8	< 1	< 1	0.02	0.002		
627	B-871	130.00 ~ 131.20	1.20	0.4	< 1	< 1	0.07	0.002		
628	B-872	131.20 ~ 132.40	1.20	1.2	< 1	< 1	0.14	0.002		
629	B-873	132.40 ~ 133.90	1.50	0.1	< 1	< 1	0.02	< 0.001		
630	B-874	133.90 ~ 135.00	1.10	0.2	< 1	< 1	0.02	0.002		

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t) 0.1g/t	Ag(g/t) 1g/t	As(%)		W(%)		Discriptions
						0.01%	0.04	0.01%	0.001%	
631	B-875	135.00 ~ 136.10	1.10	0.5	< 1	< 1	0.04	0.002		
632	B-876	136.10 ~ 137.80	1.70	0.8	< 1	< 1	0.03	0.001		
633	B-877	137.80 ~ 139.00	1.20	0.4	< 1	< 1	0.02	0.002		
634	B-878	139.00 ~ 140.50	1.50	0.8	< 1	< 1	0.03	0.002		
635	B-879	140.50 ~ 142.00	1.50	0.6	< 1	< 1	0.03	0.003		
636	B-880	142.00 ~ 143.60	1.60	0.4	< 1	< 1	0.05	0.003		
637	B-881	143.60 ~ 144.60	1.00	0.4	< 1	< 1	0.03	0.001		
638	B-882	144.60 ~ 145.60	1.00	0.2	< 1	< 1	0.04	0.004		
639	B-883	145.60 ~ 146.70	1.10	0.5	< 1	< 1	0.07	0.004		
640	B-884	146.70 ~ 147.90	1.20	0.4	2.4	2.4	0.03	0.005		
641	B-885	147.90 ~ 148.90	1.00	0.6	< 1	< 1	0.04	0.003		
642	B-886	148.90 ~ 149.90	1.00	3.0	< 1	< 1	0.08	0.003		
643	B-887	149.90 ~ 151.00	1.10	1.6	< 1	< 1	0.03	0.002		
644	B-888	151.00 ~ 152.00	1.00	0.2	< 1	< 1	0.03	0.003		
645	B-889	152.00 ~ 153.00	1.00	0.5	< 1	< 1	0.03	0.003		
646	B-890	153.00 ~ 154.50	1.50	0.6	< 1	< 1	0.08	0.003		
647	B-891	154.50 ~ 155.50	1.00	1.8	4.2	4.2	0.13	0.003		
648	B-892	155.50 ~ 156.80	1.30	1.0	< 1	< 1	< 0.01	0.060		
649	B-893	159.60 ~ 160.60	1.00	2.8	< 1	< 1	0.03	0.020		
650	B-894	160.60 ~ 162.20	1.60	1.2	< 1	< 1	0.04	0.005		
651	B-895	163.60 ~ 164.50	0.90	0.8	< 1	< 1	0.05	0.004		
652	B-896	169.20 ~ 170.40	1.20	0.2	< 1	< 1	0.02	0.006		
653	B-897	170.40 ~ 172.00	1.60	0.4	< 1	< 1	0.02	0.004		
654	B-898	172.00 ~ 173.20	1.20	0.8	< 1	< 1	0.03	0.003		
655	B-899	173.20 ~ 174.50	1.30	0.2	< 1	< 1	0.09	0.003		
656	B-901	18.80 ~ 19.60	0.80	< 0.1	1.6	1.6	0.02	0.004		
657	B-902	20.70 ~ 22.00	1.30	0.1	< 1	< 1	0.02	0.007		
658	B-903	22.00 ~ 23.20	1.20	0.4	2.6	2.6	0.02	0.004		
659	B-904	23.20 ~ 24.50	1.30	0.1	4.6	4.6	0.02	0.006		
660	B-905	24.50 ~ 25.90	1.40	0.1	2.4	2.4	0.02	0.004		

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)	As(%)	W(%)		Discriptions
				0.1g/t	1g/t			0.01%	0.001%	
661	B-906	25.90 ~ 27.50	1.60	0.2	3.2	0.02	0.008			
662	B-907	27.50 ~ 28.70	1.20	0.4	3.2	0.02	0.005			
663	B-908	28.70 ~ 30.00	1.30	0.1	< 1	0.02	0.004			
664	B-909	30.00 ~ 31.30	1.30	< 0.1	< 1	0.02	0.005			
665	B-910	31.30 ~ 32.70	1.40	0.1	4.8	0.02	0.005			
666	B-911	32.70 ~ 34.10	1.40	0.4	2.4	0.03	0.006			
667	B-912	34.10 ~ 35.30	1.20	0.5	< 1	0.02	0.007			
668	B-913	35.30 ~ 36.60	1.30	0.1	< 1	0.02	0.006			
669	B-914	36.60 ~ 37.80	1.20	0.1	< 1	0.02	0.004			
670	B-915	37.80 ~ 39.00	1.20	0.4	< 1	0.04	0.005			
671	B-916	39.00 ~ 40.40	1.40	0.1	3.6	0.04	0.004			
672	B-917	44.20 ~ 45.20	1.00	0.4	< 1	0.03	0.020			
673	B-918	45.20 ~ 46.70	1.50	0.2	2.4	0.06	0.005			
674	B-919	46.70 ~ 47.70	1.00	0.1	2.4	0.02	0.004			
675	B-920	48.80 ~ 49.90	1.10	0.1	3.2	0.02	0.020			
676	B-921	49.90 ~ 51.00	1.10	0.3	4.2	0.02	0.007			
677	B-922	51.10 ~ 51.50	0.40	0.3	< 1	0.02	0.004			
678	B-923	51.50 ~ 53.00	1.50	0.1	3.2	0.02	0.004			
679	B-924	53.00 ~ 54.00	1.00	0.4	< 1	0.03	0.005			
680	B-925	54.00 ~ 55.00	1.00	0.5	< 1	0.02	0.004			
681	B-926	55.00 ~ 56.20	1.20	0.4	< 1	0.02	0.002			
682	B-927	56.20 ~ 57.30	1.10	0.1	< 1	0.02	0.002			
683	B-928	57.30 ~ 58.30	1.00	0.4	2.4	0.04	0.003			
684	B-929	59.00 ~ 60.60	1.60	0.2	< 1	0.03	0.002			
685	B-930	64.20 ~ 65.60	1.40	0.8	2.4	0.06	0.020			
686	B-931	70.10 ~ 70.90	0.80	0.1	< 1	0.02	0.004			
687	B-932	70.90 ~ 72.10	1.20	0.1	< 1	0.02	0.003			
688	B-933	72.10 ~ 72.40	0.30	0.2	< 1	0.02	0.008			
689	B-934	72.40 ~ 73.60	1.20	0.4	2.6	0.02	0.002			
690	B-935	73.60 ~ 73.80	0.20	2.0	< 1	0.04	0.002			

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t) 0.1g/t	Ag(g/t) 1g/t	As(%) 0.01%	W(%) 0.001%	Discriptions
691	B-936	73.80 ~ 74.70	0.90	0.2	< 1	0.02	0.003	
692	B-937	74.70 ~ 75.60	0.90	0.4	< 1	0.05	0.002	
693	B-938	75.60 ~ 76.70	1.10	0.4	< 1	0.02	0.003	
694	B-939	76.70 ~ 77.80	1.10	0.3	< 1	< 0.01	0.002	
695	B-940	77.80 ~ 78.80	1.00	1.1	< 1	< 0.01	0.003	
696	B-941	78.80 ~ 79.90	1.10	0.1	< 1	< 0.01	0.003	
697	B-942	83.30 ~ 84.30	1.00	0.1	< 1	0.01	0.003	
698	B-943	84.30 ~ 85.10	0.80	0.1	< 1	0.04	0.003	
699	B-944	85.10 ~ 86.60	1.50	0.1	< 1	< 0.01	0.003	
700	B-945	86.60 ~ 87.80	1.20	< 0.1	< 1	0.03	0.003	
701	B-946	87.80 ~ 89.40	1.60	0.4	< 1	0.03	0.003	
702	B-947	89.40 ~ 91.10	1.70	0.4	< 1	0.03	0.004	
703	B-948	91.10 ~ 92.20	1.10	0.2	< 1	0.02	0.010	
704	B-949	92.20 ~ 93.50	1.30	< 0.1	< 1	0.02	0.002	
705	B-950	93.50 ~ 94.20	0.70	4.6	3.4	0.04	0.002	
706	B-951	94.20 ~ 94.90	0.70	0.1	< 1	0.02	0.004	
707	B-952	94.90 ~ 96.00	1.10	2.2	4.6	0.08	0.007	
708	B-953	96.00 ~ 97.00	1.00	1.2	< 1	0.03	0.005	
709	B-954	97.00 ~ 98.00	1.00	0.8	< 1	0.03	0.005	
710	B-955	99.70 ~ 101.10	1.40	0.1	< 1	0.02	0.005	
711	B-956	101.10 ~ 102.20	1.10	0.1	< 1	< 0.01	0.003	
712	B-957	102.20 ~ 103.40	1.20	< 0.1	3.2	0.02	0.006	
713	B-958	103.40 ~ 104.50	1.10	0.1	< 1	0.01	0.005	
714	B-959	104.50 ~ 105.60	1.10	0.2	< 1	0.02	0.004	
715	B-960	105.60 ~ 107.20	1.60	0.6	< 1	< 0.01	0.005	
716	B-961	107.20 ~ 108.80	1.60	0.6	< 1	0.11	0.004	
717	B-962	112.40 ~ 113.50	1.10	0.4	1.4	0.06	0.004	
718	B-963	114.20 ~ 115.40	1.20	< 0.1	< 1	0.02	0.002	
719	B-964	115.40 ~ 116.40	1.00	< 0.1	< 1	0.02	0.003	
720	B-965	118.20 ~ 119.20	1.00	0.4	< 1	< 0.01	0.002	

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t) 0.1g/t	Ag(g/t) 1g/t	As(%) 0.01%	W(%) 0.001%	Discriptions
721	B-966	119.20 ~ 120.20	1.00	0.1	1.8	0.01	0.002	
722	B-967	120.20 ~ 121.20	1.00	0.8	2.4	0.02	0.002	
723	B-968	121.20 ~ 122.60	1.40	0.5	< 1	0.02	0.002	
724	B-969	122.60 ~ 123.70	1.10	0.1	< 1	0.05	0.003	
725	B-970	123.70 ~ 124.10	0.40	0.1	< 1	0.02	0.006	
726	B-971	124.10 ~ 125.00	0.90	0.1	< 1	0.03	0.010	
727	B-972	125.00 ~ 126.00	1.00	0.1	1.6	< 0.01	0.002	
728	B-973	126.00 ~ 127.00	1.00	0.1	4.4	0.01	0.002	
729	B-974	127.00 ~ 128.00	1.00	0.1	3.6	0.04	0.002	
730	B-975	128.00 ~ 129.10	1.10	0.1	1.8	< 0.01	0.002	
731	B-976	129.10 ~ 130.10	1.00	0.1	< 1	0.02	0.002	
732	B-977	130.10 ~ 131.10	1.00	0.1	< 1	0.05	0.060	
733	B-978	132.70 ~ 134.20	1.50	0.1	< 1	0.02	0.040	
734	B-979	134.20 ~ 135.50	1.30	0.1	< 1	< 0.01	0.002	
735	B-980	135.50 ~ 136.60	1.10	0.1	2.0	0.03	0.002	
736	B-981	136.60 ~ 137.60	1.00	0.1	< 1	0.02	0.003	
737	B-982	140.10 ~ 141.30	1.20	0.1	< 1	< 0.01	0.007	
738	B-983	141.30 ~ 142.60	1.30	0.2	< 1	0.05	0.008	
739	B-984	142.60 ~ 143.60	1.00	0.1	1.6	0.03	0.002	
740	B-985	143.60 ~ 144.60	1.00	1.8	1.8	0.06	0.003	
741	B-986	144.60 ~ 145.60	1.00	0.6	3.6	0.12	0.003	
742	B-987	145.60 ~ 146.30	0.70	0.6	< 1	0.07	0.002	
743	B-988	152.10 ~ 153.00	0.90	0.1	< 1	0.12	0.002	
744	B-989	153.00 ~ 153.80	0.80	0.1	< 1	0.09	0.003	
745	B-990	153.80 ~ 155.10	1.30	0.1	2.2	0.05	0.004	
746	B-991	155.10 ~ 155.60	0.50	0.1	< 1	0.34	0.003	
747	B-992	155.60 ~ 157.00	1.40	0.1	< 1	0.08	0.004	
748	B-993	159.60 ~ 160.60	1.00	0.5	3.2	0.04	0.005	
749	B-994	160.60 ~ 161.60	1.00	0.5	6.4	0.13	0.004	
750	B-995	161.60 ~ 162.40	0.80	0.6	2.0	0.05	0.002	

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)		As(%)		W(%)		Discriptions
				0.1g/t	1g/t	1g/t	1g/t	0.01%	0.001%	0.01%	0.001%	
751	B-996	162.40 ~ 163.40	1.00	0.1	2.0	0.01	0.003					
752	B-997	166.70 ~ 167.80	1.10	0.2	< 1	0.06	0.002					
753	B-998	167.80 ~ 168.80	1.00	0.3	3.7	0.13	0.003					
754	B-999	168.80 ~ 170.00	1.20	0.1	< 1	0.04	0.002					
755	B-1001	6.00 ~ 7.30	1.30	0.6	< 1	0.07	0.003					
756	B-1002	7.30 ~ 8.80	1.50	0.1	2.8	0.05	0.004					
757	B-1003	8.80 ~ 9.80	1.00	< 0.1	< 1	0.05	0.004					
758	B-1004	9.80 ~ 11.20	1.40	0.1	< 1	0.05	0.005					
759	B-1005	37.10 ~ 37.70	0.60	0.4	< 1	0.07	0.004					
760	B-1006	40.00 ~ 41.00	1.00	1.0	< 1	0.02	0.003					
761	B-1007	41.00 ~ 42.00	1.00	0.6	< 1	0.02	0.009					
762	B-1008	42.00 ~ 43.00	1.00	0.2	< 1	0.02	0.004					
763	B-1009	43.00 ~ 44.00	1.00	0.6	< 1	0.02	0.004					
764	B-1010	44.00 ~ 45.00	1.00	0.4	< 1	0.02	0.004					
765	B-1011	45.00 ~ 46.10	1.10	0.4	< 1	0.02	0.003					
766	B-1012	51.20 ~ 52.60	1.40	0.4	< 1	0.03	0.003					
767	B-1013	54.60 ~ 55.40	0.80	0.8	< 1	0.10	0.002					
768	B-1014	63.50 ~ 64.20	0.70	0.1	< 1	0.02	0.004					
769	B-1015	64.20 ~ 65.20	1.00	0.2	< 1	0.02	0.003					
770	B-1016	74.80 ~ 75.80	1.00	0.4	< 1	0.11	0.003					
771	B-1017	75.80 ~ 76.80	1.00	0.5	< 1	0.03	0.004					
772	B-1018	76.80 ~ 78.40	1.60	0.4	< 1	0.07	0.004					
773	B-1019	81.80 ~ 83.00	1.20	0.3	< 1	0.04	0.010					
774	B-1020	83.00 ~ 84.10	1.10	< 0.1	2.8	0.02	0.002					
775	B-1021	86.70 ~ 88.20	1.50	0.8	< 1	0.05	0.003					
776	B-1022	91.40 ~ 92.70	1.30	0.4	< 1	0.03	0.003					
777	B-1023	95.10 ~ 96.10	1.00	0.1	< 1	0.08	0.003					
778	B-1024	96.10 ~ 97.00	0.90	< 0.1	< 1	0.05	0.002					
779	B-1025	107.30 ~ 108.70	1.40	0.1	< 1	0.05	0.030					
780	B-1026	108.70 ~ 110.20	1.50	0.8	< 1	0.07	0.010					

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)	As(%)	W(%)		Discriptions
				0.1g/t	1g/t			0.01%	0.001%	
781	B-1027	110.80 ~ 112.50	1.70	1.2	< 1	0.04	0.010			
782	B-1028	112.50 ~ 114.10	1.60	0.4	1.8	0.02	0.007			
783	B-1029	114.10 ~ 115.20	1.10	0.4	< 1	0.09	0.004			
784	B-1030	117.50 ~ 118.70	1.20	0.4	< 1	0.10	0.003			
785	B-1031	118.70 ~ 120.10	1.40	0.4	< 1	0.07	0.003			
786	B-1032	120.10 ~ 120.45	0.35	3.7	< 1	0.03	0.002			
787	B-1033	120.45 ~ 121.20	0.75	0.4	< 1	0.09	0.006			
788	B-1034	121.20 ~ 122.00	0.80	0.5	< 1	0.50	0.004			
789	B-1035	122.00 ~ 123.20	1.20	0.1	< 1	0.04	0.005			
790	B-1036	123.20 ~ 124.30	1.10	0.1	< 1	0.06	0.005			
791	B-1037	124.30 ~ 125.30	1.00	0.6	< 1	0.03	0.006			
792	B-1038	125.30 ~ 125.58	0.28	2.8	3.4	2.26	0.080			
793	B-1039	125.58 ~ 126.30	0.72	0.5	< 1	0.08	0.050			
794	B-1040	126.30 ~ 127.50	1.20	0.4	< 1	0.12	0.006			
795	B-1041	127.50 ~ 128.70	1.20	0.4	< 1	0.04	0.003			
796	B-1042	128.70 ~ 129.80	1.10	0.6	2.2	0.09	0.006			
797	B-1043	129.80 ~ 131.00	1.20	0.4	< 1	0.05	0.004			
798	B-1044	131.00 ~ 132.50	1.50	0.1	< 1	0.03	0.004			
799	B-1045	132.50 ~ 133.90	1.40	0.1	< 1	0.02	0.003			
800	B-1046	133.90 ~ 134.90	1.00	0.1	< 1	0.04	0.003			
801	B-1047	134.90 ~ 136.20	1.30	0.1	< 1	0.03	0.002			
802	B-1048	142.50 ~ 143.20	0.70	0.4	< 1	0.03	0.002			
803	B-1049	143.70 ~ 145.20	1.50	0.4	< 1	0.08	0.002			
804	B-1050	148.00 ~ 148.80	0.80	0.2	< 1	0.04	0.004			
805	B-1051	151.90 ~ 152.80	0.90	0.1	< 1	0.06	0.003			
806	B-1052	153.80 ~ 155.30	1.50	0.1	< 1	0.02	0.002			
807	B-1053	155.30 ~ 156.30	1.00	0.1	< 1	0.03	0.003			
808	B-1054	156.30 ~ 157.10	0.80	0.5	< 1	0.10	0.007			
809	B-1055	157.10 ~ 158.00	0.90	0.2	< 1	0.02	0.002			
810	B-1056	158.00 ~ 159.60	1.60	< 0.1	< 1	0.02	< 0.001			

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m)	Au(g/t)		Ag(g/t)	As(%)	W(%)		Discriptions
				0.1g/t	1g/t			0.01%	0.001%	
811	B-1057	159.60 ~ 161.00	1.40	0.1	< 1	0.02	0.001			
812	B-1058	161.00 ~ 162.30	1.30	0.5	< 1	< 0.01	< 0.001			
813	B-1059	162.30 ~ 163.40	1.10	2.0	2.4	0.02	0.002			
814	B-1060	173.80 ~ 175.55	1.75	1.2	1.4	0.09	0.002			
815	B-1061	178.90 ~ 180.20	1.30	0.2	< 1	< 0.01	0.003			
816	B-1062	180.20 ~ 181.40	1.20	1.2	< 1	0.06	0.007			
817	B-1063	181.40 ~ 182.45	1.05	0.1	< 1	0.02	0.002			
818	B-1064	182.45 ~ 183.20	0.75	< 0.1	< 1	< 0.01	0.001			
819	B-1065	183.20 ~ 184.20	1.00	0.2	< 1	0.01	0.004			
820	B-1066	184.20 ~ 185.60	1.40	0.1	< 1	0.10	0.002			
821	B-1067	185.60 ~ 186.50	0.90	0.1	< 1	0.02	0.002			
822	B-1068	186.50 ~ 187.45	0.95	0.2	< 1	0.07	0.002			
823	B-1069	187.45 ~ 188.15	0.70	0.6	< 1	0.60	0.004			
824	B-1070	188.15 ~ 189.10	0.95	0.1	< 1	0.06	0.002			
825	B-1071	189.10 ~ 190.80	1.70	< 0.1	< 1	0.02	0.003			
826	B-1072	190.80 ~ 192.00	1.20	0.8	< 1	0.09	0.002			
827	B-1073	192.00 ~ 193.70	1.70	0.1	< 1	0.02	0.002			
828	B-1074	193.70 ~ 194.60	0.90	0.4	< 1	0.07	0.002			
829	B-1075	203.30 ~ 203.80	0.50	0.2	< 1	0.09	0.005			
830	B-1076	203.80 ~ 204.85	1.05	< 0.1	< 1	0.03	0.002			
831	B-1077	204.85 ~ 206.00	1.15	< 0.1	< 1	0.15	0.010			
832	B-1078	206.00 ~ 207.00	1.00	0.1	2.4	0.03	0.003			
833	B-1079	207.00 ~ 207.70	0.70	0.4	< 1	0.00	0.007			
834	B-1080	207.70 ~ 208.50	0.80	0.1	1.8	0.09	0.005			
835	B-1081	210.10 ~ 211.15	1.05	0.2	< 1	0.40	0.002			
836	B-1082	213.40 ~ 214.80	1.40	0.1	1.8	0.08	0.001			
837	B-3100	231.80 ~ 232.70	0.90	< 0.1	< 1	0.03	0.002			
838	B-3101	234.10 ~ 235.00	0.90	0.6	< 1	0.02	0.004			
839	B-3102	235.00 ~ 236.00	1.00	< 0.1	< 1	< 0.01	0.002			
840	B-3103	236.00 ~ 236.60	0.60	0.2	< 1	< 0.01	0.002			

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)	As(%)	W(%)		Discriptions
				0.1g/t	1g/t			0.01%	0.001%	
841	B-3104	239.60 ~ 240.80	1.20	0.4	< 1	< 0.01	0.007			
842	B-3105	247.90 ~ 248.35	0.45	0.4	< 1	0.02	0.008			
843	B-3106	248.35 ~ 249.40	1.05	< 0.1	< 1	0.02	0.020			
844	B-3107	249.40 ~ 250.40	1.00	< 0.1	< 1	0.02	0.005			
845	B-3108	250.40 ~ 251.40	1.00	< 0.1	< 1	0.03	0.008			
846	B-3109	251.40 ~ 252.40	1.00	< 0.1	< 1	0.02	0.008			
847	B-3110	252.40 ~ 253.40	1.00	< 0.1	< 1	0.02	0.010			
848	B-3111	253.40 ~ 254.40	1.00	< 0.1	< 1	0.02	0.020			
849	B-3112	254.40 ~ 255.40	1.00	< 0.1	< 1	0.02	0.020			
850	B-3113	255.40 ~ 256.60	1.20	< 0.1	< 1	0.03	0.020			
851	B-3114	256.60 ~ 257.60	1.00	< 0.1	< 1	0.02	0.020			
852	B-3115	257.60 ~ 259.20	1.60	< 0.1	< 1	0.02	0.050			
853	B-3116	259.20 ~ 260.50	1.30	0.1	4.6	0.02	0.007			
854	B-3117	260.50 ~ 261.80	1.30	< 0.1	3.6	0.02	0.005			
855	B-3118	261.80 ~ 263.00	1.20	0.1	< 1	0.02	0.007			
856	B-3119	263.90 ~ 264.70	0.80	< 0.1	2.8	0.02	0.040			
857	B-3120	269.50 ~ 270.40	0.90	0.1	< 1	0.02	0.008			
858	B-3121	274.95 ~ 276.20	1.25	0.1	< 1	< 0.01	0.004			
859	B-3122	276.20 ~ 277.60	1.40	< 0.1	< 1	< 0.01	0.003			
860	B-3123	279.55 ~ 281.00	1.45	< 0.1	< 1	< 0.01	0.002			
861	B-3124	281.00 ~ 282.50	1.50	0.1	< 1	0.02	0.003			
862	B-3125	282.50 ~ 284.00	1.50	< 0.1	< 1	0.03	0.003			
863	B-3126	285.80 ~ 286.95	1.15	< 0.1	< 1	< 0.01	0.002			
864	B-3127	286.95 ~ 287.90	0.95	0.1	< 1	< 0.01	0.004			
865	B-3128	290.40 ~ 291.70	1.30	0.4	< 1	< 0.01	0.003			
866	B-3129	295.80 ~ 297.40	1.60	< 0.1	< 1	< 0.01	0.003			
867	B-3130	307.00 ~ 308.00	1.00	0.1	< 1	< 0.01	0.002			
868	B-3131	308.00 ~ 309.00	1.00	< 0.1	< 1	< 0.01	< 0.001			
869	B-3132	309.00 ~ 310.00	1.00	< 0.1	< 1	0.01	0.007			
870	B-3133	310.00 ~ 311.20	1.20	< 0.1	< 1	< 0.01	0.006			

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) <small>Lower limit⇒</small>	Au(g/t)		Ag(g/t) <small>lg/t</small>	As(%) <small>0.01%</small>	W(%) <small>0.001%</small>	Discriptions
				<small>0.1g/t</small>	<small>0.3</small>				
871	B-3134	311.20 ~ 312.20	1.00	0.3	< 1	0.02	0.008		
872	B-3135	312.20 ~ 313.40	1.20	0.1	2.8	0.02	0.006		
873	B-3136	313.40 ~ 314.30	0.90	0.4	< 1	0.02	0.030		
874	B-3137	314.30 ~ 315.20	0.90	0.5	< 1	0.02	0.004		
875	B-3138	315.20 ~ 316.20	1.00	0.4	< 1	< 0.01	0.004		
876	B-3139	316.20 ~ 317.20	1.00	0.4	< 1	0.02	0.005		
877	B-3140	317.20 ~ 318.20	1.00	0.4	< 1	0.03	0.002		
878	B-3141	318.20 ~ 319.40	1.20	0.4	< 1	0.05	0.004		
879	B-3142	319.40 ~ 320.50	1.10	< 0.1	< 1	0.02	0.004		
880	B-3143	320.50 ~ 321.50	1.00	0.6	1.4	< 0.01	< 0.001		
881	B-3144	321.50 ~ 322.70	1.20	0.8	< 1	0.05	< 0.001		
882	B-3145	322.70 ~ 324.00	1.30	0.2	< 1	0.07	0.002		
883	B-3146	324.00 ~ 325.00	1.00	0.6	< 1	0.02	0.001		
884	B-3147	325.00 ~ 326.00	1.00	0.5	< 1	0.04	0.003		
885	B-3148	326.00 ~ 327.20	1.20	< 0.1	< 1	0.04	0.002		
886	B-3149	327.20 ~ 328.50	1.30	0.6	< 1	0.06	0.002		
887	B-3150	328.50 ~ 329.50	1.00	1.2	< 1	0.01	0.002		
888	B-3151	329.50 ~ 330.60	1.10	0.5	1.4	0.04	0.002		
889	B-3152	330.60 ~ 332.00	1.40	0.2	1.2	0.02	0.001		
890	B-3153	333.00 ~ 333.70	0.70	0.4	< 1	0.35	0.004		
891	B-3154	333.70 ~ 335.00	1.30	0.4	< 1	0.03	0.001		
892	B-3155	335.00 ~ 336.00	1.00	< 0.1	< 1	0.05	< 0.001		
893	B-3156	336.00 ~ 337.10	1.10	0.1	< 1	0.02	0.002		
894	B-3157	338.60 ~ 339.70	1.10	0.3	< 1	0.08	0.002		
895	B-3158	339.70 ~ 341.00	1.30	0.4	3.2	0.06	0.002		
896	B-4100	127.10 ~ 128.00	0.90	0.1	< 1	0.03	0.005		
897	B-4101	128.00 ~ 129.00	1.00	0.1	< 1	0.03	0.001		
898	B-4102	129.00 ~ 130.00	1.00	0.2	< 1	0.16	0.003		
899	B-4103	130.00 ~ 131.00	1.00	< 0.1	< 1	0.03	0.001		
900	B-4104	131.00 ~ 132.00	1.00	0.2	< 1	0.01	0.002		

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)		As(%)		W(%)		Discriptions
				0.1g/t	0.1g/t	1g/t	1g/t	0.01%	0.01%	0.001%	0.001%	
901	B-4105	132.00 ~ 132.75	0.75	0.4	< 1	< 1	< 1	0.15	0.002			
902	B-4106	134.55 ~ 135.90	1.35	0.2	< 1	< 1	< 1	0.15	0.002			
903	B-4107	135.90 ~ 136.80	0.90	0.5	< 1	< 1	< 1	0.10	0.003			
904	B-4108	136.80 ~ 138.00	1.20	0.1	< 1	< 1	< 1	0.01	0.001			
905	B-4109	138.00 ~ 139.30	1.30	0.4	< 1	< 1	< 1	0.12	0.001			
906	B-4110	139.30 ~ 140.00	0.70	0.5	< 1	< 1	< 1	0.05	0.001			
907	B-4111	142.40 ~ 143.60	1.20	0.1	< 1	< 1	< 1	0.04	0.002			
908	B-4112	143.60 ~ 144.80	1.20	0.1	< 1	< 1	< 1	0.02	0.001			
909	B-4113	144.80 ~ 146.00	1.20	< 0.1	< 1	< 1	< 1	0.04	0.003			
910	B-4114	146.00 ~ 147.00	1.00	0.6	< 1	< 1	< 1	0.08	0.003			
911	B-4115	147.00 ~ 148.00	1.00	< 0.1	< 1	< 1	< 1	0.01	0.007			
912	B-4116	148.00 ~ 149.00	1.00	< 0.1	< 1	< 1	< 1	0.05	0.007			
913	B-4117	149.00 ~ 150.00	1.00	0.2	< 1	< 1	< 1	0.05	0.003			
914	B-4118	150.00 ~ 151.00	1.00	0.2	< 1	< 1	< 1	0.04	0.003			
915	B-4119	151.00 ~ 152.00	1.00	0.1	< 1	< 1	< 1	0.02	0.002			
916	B-4120	155.10 ~ 156.50	1.40	2.4	1.2	1.2	1.2	0.02	0.002			
917	B-4121	156.50 ~ 157.55	1.05	2.4	< 1	< 1	< 1	0.01	0.001			
918	B-4122	161.30 ~ 162.40	1.10	0.3	6.0	6.0	6.0	0.05	0.001			
919	B-4123	165.30 ~ 166.35	1.05	0.2	5.2	5.2	5.2	0.01	0.002			
920	B-4124	168.20 ~ 168.80	0.60	0.4	3.2	3.2	3.2	0.05	0.002			
921	B-4125	168.80 ~ 169.80	1.00	0.2	5.8	5.8	5.8	0.03	0.002			
922	B-4126	169.80 ~ 171.35	1.55	0.4	2.8	2.8	2.8	0.04	0.004			
923	B-4127	171.35 ~ 172.70	1.35	0.2	< 1	< 1	< 1	0.02	0.002			
924	B-4128	172.70 ~ 174.60	1.90	0.1	< 1	< 1	< 1	0.06	0.004			
925	B-4129	182.00 ~ 183.40	1.40	2.2	6.4	6.4	6.4	0.37	0.004			
926	B-4130	183.40 ~ 184.40	1.00	0.5	3.6	3.6	3.6	0.11	0.003			
927	B-4131	187.90 ~ 188.90	1.00	0.1	2.4	2.4	2.4	< 0.01	0.001			
928	B-4132	188.90 ~ 189.90	1.00	3.8	< 1	< 1	< 1	0.02	0.010			
929	B-4133	189.90 ~ 190.75	0.85	0.8	2.8	2.8	2.8	0.32	0.004			
930	B-4134	194.40 ~ 195.60	1.20	2.2	< 1	< 1	< 1	0.10	0.010			

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)	As(%)	W(%)	Discriptions
				0.1g/t	1g/t				
931	B-4135	195.60 ~ 196.60	1.00	0.3	< 1	0.03	0.006		
932	B-4136	196.60 ~ 197.60	1.00	1.0	1.6	0.08	0.007		
933	B-4137	198.35 ~ 198.60	0.25	1.4	< 1	0.20	0.004		
934	B-4138	198.60 ~ 199.60	1.00	< 0.1	< 1	0.01	0.007		
935	B-4139	199.60 ~ 200.60	1.00	0.2	5.8	0.01	0.008		
936	B-4140	200.60 ~ 201.50	0.90	0.2	< 1	0.02	< 0.001		
937	B-4141	201.50 ~ 202.60	1.10	0.2	1.2	0.02	< 0.001		
938	B-4142	206.60 ~ 207.40	0.80	0.5	< 1	0.11	0.003		
939	B-4143	213.00 ~ 214.00	1.00	0.7	< 1	0.10	0.002		
940	B-4144	214.00 ~ 215.00	1.00	0.4	< 1	0.02	< 0.001		
941	B-4145	215.00 ~ 216.00	1.00	1.3	< 1	0.22	0.008		
942	B-4146	216.00 ~ 216.90	0.90	0.4	< 1	0.09	0.002		
943	B-4147	216.90 ~ 217.60	0.70	0.5	< 1	0.05	0.003		
944	B-4148	217.60 ~ 218.50	0.90	0.3	< 1	0.07	0.002		
945	B-4149	218.50 ~ 219.70	1.20	0.7	< 1	0.04	0.002		
946	B-4150	219.70 ~ 220.50	0.80	0.6	< 1	0.02	0.001		
947	B-4151	220.50 ~ 221.40	0.90	0.3	< 1	0.02	0.001		
948	B-4152	222.20 ~ 223.20	1.00	0.4	< 1	0.02	0.002		
949	B-4153	223.20 ~ 224.20	1.00	0.2	< 1	0.05	0.020		
950	B-4154	224.20 ~ 225.20	1.00	< 0.1	< 1	< 0.01	0.002		
951	B-4155	225.20 ~ 226.00	0.80	1.3	< 1	< 0.01	0.003		
952	B-4156	226.00 ~ 226.90	0.90	0.1	< 1	0.01	0.003		
953	B-4157	226.90 ~ 228.10	1.20	0.2	< 1	< 0.01	0.004		
954	B-4158	228.10 ~ 229.10	1.00	0.2	< 1	0.01	0.004		
955	B-4159	229.10 ~ 230.50	1.40	0.5	< 1	0.04	0.002		
956	B-4160	230.50 ~ 231.20	0.70	< 0.1	< 1	< 0.01	0.003		
957	B-4161	231.20 ~ 231.90	0.70	< 0.1	< 1	< 0.01	0.003		
958	B-4162	231.90 ~ 232.90	1.00	< 0.1	< 1	0.02	0.005		
959	B-4163	232.90 ~ 233.80	0.90	0.2	< 1	< 0.01	0.005		
960	B-4164	234.90 ~ 236.00	1.10	5.8	< 1	0.03	0.680		

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit→	Au(g/t)		Ag(g/t) lg/t	As(%) 0.01%	W(%) 0.001%	Discriptions
				0.1g/t	0.4				
961	B-4165	236.00 ~ 237.00	1.00	0.4	< 1	< 1	0.02	0.020	
962	B-4166	237.00 ~ 238.50	1.50	0.2	< 1	< 1	0.02	0.008	
963	B-4167	238.50 ~ 239.50	1.00	0.5	< 1	< 1	0.08	0.003	
964	B-4168	239.50 ~ 240.50	1.00	0.4	< 1	< 1	0.03	0.010	
965	B-4169	240.50 ~ 241.80	1.30	0.5	< 1	< 1	0.03	0.060	
966	B-4170	244.10 ~ 245.50	1.40	0.2	< 1	< 1	0.01	0.002	
967	B-4171	247.30 ~ 248.40	1.10	0.4	< 1	< 1	0.07	0.003	
968	B-4172	248.40 ~ 249.70	1.30	0.4	< 1	< 1	0.05	0.001	
969	B-4173	251.45 ~ 252.45	1.00	0.2	< 1	< 1	0.01	0.002	
970	B-4174	252.45 ~ 253.40	0.95	< 0.1	< 1	< 1	0.01	0.004	
971	B-4175	253.40 ~ 254.30	0.90	< 0.1	< 1	< 1	< 0.01	0.001	
972	B-4176	256.30 ~ 257.40	1.10	< 0.1	< 1	< 1	< 0.01	0.002	
973	B-4177	257.40 ~ 258.40	1.00	0.2	< 1	< 1	0.01	0.005	
974	B-4178	261.20 ~ 262.50	1.30	< 0.1	< 1	< 1	< 0.01	0.002	
975	B-4179	262.50 ~ 263.50	1.00	< 0.1	< 1	< 1	< 0.01	0.001	
976	B-4180	263.50 ~ 264.90	1.40	< 0.1	< 1	< 1	0.01	0.002	
977	B-4181	264.90 ~ 265.90	1.00	< 0.1	< 1	< 1	0.01	0.003	
978	B-4182	265.90 ~ 266.90	1.00	0.2	< 1	< 1	0.02	0.002	
979	B-4183	269.40 ~ 270.40	1.00	< 0.1	< 1	< 1	< 0.01	0.003	
980	B-4184	273.20 ~ 273.90	0.70	0.2	< 1	< 1	0.01	0.002	
981	B-4185	273.90 ~ 275.10	1.20	0.2	< 1	< 1	< 0.01	0.004	
982	B-4186	275.10 ~ 276.40	1.30	0.2	< 1	< 1	0.01	0.004	
983	B-4187	276.40 ~ 277.50	1.10	< 0.1	< 1	< 1	0.01	0.003	
984	B-4188	294.00 ~ 294.80	0.80	0.5	< 1	< 1	0.07	0.002	
985	B-4189	296.20 ~ 297.00	0.80	0.2	< 1	< 1	0.10	0.004	
986	B-4190	297.00 ~ 298.50	1.50	0.1	< 1	< 1	< 0.01	0.002	
987	B-4191	298.50 ~ 300.00	1.50	0.4	2.8	2.8	0.05	0.002	
988	B-4192	300.00 ~ 301.20	1.20	< 0.1	< 1	< 1	< 0.01	0.002	
989	B-4193	301.20 ~ 302.50	1.30	0.4	< 1	< 1	0.04	0.003	
990	B-4194	302.50 ~ 303.40	0.90	0.4	1.8	1.8	0.02	0.005	

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t) lg/t	As(%)	W(%)	Discriptions
				0.1g/t	0.01%				
991	B-4195	303.40 ~ 304.30	0.90	0.2	< 1	0.04	0.007		
992	B-4196	305.60 ~ 306.30	0.70	0.1	< 1	< 0.01	0.002		
993	B-5100	177.20 ~ 177.65	0.45	2.8	< 1	0.10	0.002		
994	B-5101	180.30 ~ 181.50	1.20	2.0	< 1	0.06	0.003		
995	B-5102	181.50 ~ 182.50	1.00	2.2	< 1	0.07	0.003		
996	B-5103	182.50 ~ 183.70	1.20	0.6	< 1	0.07	0.002		
997	B-5104	183.70 ~ 184.70	1.00	0.1	< 1	0.03	0.002		
998	B-5105	186.40 ~ 187.50	1.10	< 0.1	< 1	0.01	0.005		
999	B-5106	187.50 ~ 188.50	1.00	0.2	< 1	< 0.01	0.004		
1000	B-5107	188.50 ~ 189.60	1.10	0.1	< 1	< 0.01	0.003		
1001	B-5108	189.60 ~ 190.70	1.10	0.4	< 1	0.02	0.003		
1002	B-5109	190.70 ~ 192.00	1.30	0.8	< 1	< 0.01	0.010		
1003	B-5110	192.00 ~ 193.50	1.50	1.2	< 1	0.07	0.002		
1004	B-5111	195.70 ~ 196.70	1.00	0.5	< 1	0.02	0.002		
1005	B-5112	196.70 ~ 197.60	0.90	0.4	< 1	0.02	0.004		
1006	B-5113	197.60 ~ 199.10	1.50	< 0.1	< 1	0.01	0.003		
1007	B-5114	199.10 ~ 200.50	1.40	< 0.1	< 1	0.02	0.002		
1008	B-5115	200.50 ~ 201.80	1.30	< 0.1	< 1	0.05	0.004		
1009	B-5116	201.80 ~ 202.10	0.30	0.5	< 1	0.46	0.002		
1010	B-5117	202.10 ~ 203.50	1.40	0.1	< 1	0.02	0.004		
1011	B-5118	203.50 ~ 204.50	1.00	0.8	< 1	0.05	0.001		
1012	B-5119	204.50 ~ 205.60	1.10	0.2	< 1	0.07	0.002		
1013	B-5120	215.50 ~ 216.20	0.70	0.4	< 1	0.05	0.005		
1014	B-5121	220.60 ~ 221.50	0.90	0.6	< 1	0.02	0.005		
1015	B-5122	221.50 ~ 222.20	0.70	0.4	< 1	0.02	0.060		
1016	B-5123	222.20 ~ 223.00	0.80	0.1	< 1	0.02	0.005		
1017	B-5124	223.00 ~ 224.00	1.00	0.2	< 1	0.04	0.005		
1018	B-5125	224.00 ~ 225.00	1.00	< 0.1	< 1	0.02	0.004		
1019	B-5126	225.00 ~ 226.00	1.00	0.1	< 1	0.02	0.001		
1020	B-5127	227.70 ~ 228.70	1.00	0.1	< 1	0.03	0.003		

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) <small>Lower limit⇒</small>	Au(g/t)		Ag(g/t)	As(%)	W(%)	Discriptions
				0.1g/t	0.4				
1021	B- 5128	231.50 ~ 232.70	1.20	0.4	< 1	0.02	0.003		
1022	B- 5129	234.00 ~ 235.10	1.10	0.1	< 1	0.02	0.003		
1023	B- 5130	243.80 ~ 244.80	1.00	0.1	< 1	0.02	0.004		
1024	B- 5131	244.80 ~ 245.80	1.00	0.8	< 1	0.02	0.002		
1025	B- 5132	245.80 ~ 246.80	1.00	0.5	< 1	0.06	0.002		
1026	B- 5133	250.25 ~ 251.50	1.25	0.1	< 1	0.02	0.003		
1027	B- 5134	251.50 ~ 252.50	1.00	0.2	< 1	< 0.01	0.002		
1028	B- 5135	252.50 ~ 253.60	1.10	0.2	< 1	0.02	0.002		
1029	B- 5136	253.60 ~ 255.00	1.40	0.4	< 1	0.07	0.001		
1030	B- 5137	258.60 ~ 259.60	1.00	0.5	< 1	0.02	0.001		
1031	B- 5138	260.90 ~ 262.00	1.10	0.8	< 1	0.12	0.003		
1032	B- 5139	262.00 ~ 262.70	0.70	0.6	< 1	0.07	0.002		
1033	B- 5140	273.40 ~ 274.50	1.10	2.0	< 1	0.03	0.001		
1034	B- 5141	274.50 ~ 275.50	1.00	1.6	< 1	0.01	0.001		
1035	B- 5142	275.50 ~ 277.20	1.70	0.4	< 1	< 0.01	0.001		
1036	B- 5143	277.20 ~ 278.20	1.00	0.6	< 1	0.03	0.002		
1037	B- 5144	278.20 ~ 279.20	1.00	0.5	< 1	0.04	0.002		
1038	B- 5145	279.20 ~ 280.20	1.00	3.2	< 1	0.04	0.002		
1039	B- 5146	291.40 ~ 292.40	1.00	0.5	< 1	0.31	0.001		
1040	B- 5147	292.40 ~ 293.80	1.40	0.2	< 1	0.03	0.002		
1041	B- 5148	293.80 ~ 295.00	1.20	0.4	< 1	0.02	0.002		
1042	B- 5149	297.60 ~ 299.10	1.50	0.2	< 1	0.03	0.002		
1043	B- 5150	300.80 ~ 301.80	1.00	0.2	5.2	0.04	0.005		
1044	B- 5151	315.10 ~ 315.50	0.40	2.8	< 1	0.14	< 0.001		
1045	B- 8100	174.50 ~ 175.50	1.00	0.3	2.4	0.07	0.060		
1046	B- 8101	175.50 ~ 176.50	1.00	0.1	< 1	0.02	0.003		
1047	B- 8102	176.50 ~ 177.80	1.30	1.2	3.8	0.14	0.002		
1048	B- 8103	177.80 ~ 179.20	1.40	1.2	< 1	0.13	0.007		
1049	B- 8104	179.20 ~ 180.20	1.00	3.6	5.6	0.14	0.003		
1050	B- 8105	180.20 ~ 181.20	1.00	0.6	< 1	0.06	0.002		

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limits⇒	Au(g/t) 0.1g/t	Ag(g/t) 1g/t	As(%) 0.01%	W(%) 0.001%	Discriptions
1051	B- 8106	181.20 ~ 182.50	1.30	0.3	< 1	0.02	0.002	
1052	B- 8107	182.50 ~ 183.60	1.10	0.3	< 1	0.02	0.002	
1053	B- 8108	183.60 ~ 184.80	1.20	0.4	< 1	0.01	0.002	
1054	B- 8109	184.80 ~ 186.00	1.20	0.5	< 1	0.06	0.004	
1055	B- 8110	186.00 ~ 186.70	0.70	2.0	< 1	0.07	0.080	
1056	B- 8111	186.70 ~ 188.30	1.60	0.2	< 1	0.01	0.002	
1057	B- 8112	188.30 ~ 189.80	1.50	0.2	< 1	0.02	0.002	
1058	B- 8113	189.80 ~ 191.40	1.60	0.8	1.6	0.10	0.004	
1059	B- 8114	191.40 ~ 193.00	1.60	0.4	< 1	0.05	0.002	
1060	B- 8115	193.00 ~ 194.55	1.55	0.2	3.4	0.04	0.002	
1061	B- 8116	198.80 ~ 199.90	1.10	0.3	< 1	0.01	0.002	
1062	B- 8117	199.90 ~ 201.30	1.40	0.2	< 1	0.03	0.002	
1063	B- 8118	201.30 ~ 202.70	1.40	0.4	2.4	0.03	0.002	
1064	B- 8119	202.70 ~ 204.30	1.60	0.1	< 1	0.03	0.003	
1065	B- 8120	207.10 ~ 208.30	1.20	< 0.1	< 1	0.01	< 0.001	
1066	B- 8121	208.30 ~ 209.60	1.30	0.1	< 1	0.01	0.001	
1067	B- 8122	209.60 ~ 210.70	1.10	0.1	< 1	0.02	0.002	
1068	B- 8123	210.70 ~ 211.80	1.10	0.5	< 1	0.02	< 0.001	
1069	B- 8124	211.80 ~ 212.80	1.00	0.3	3.6	0.04	0.002	
1070	B- 8125	212.80 ~ 213.70	0.90	< 0.1	< 1	0.02	0.002	
1071	B- 8126	213.70 ~ 214.90	1.20	0.2	2.6	0.01	0.002	
1072	B- 8127	214.90 ~ 216.20	1.30	< 0.1	3.6	< 0.01	0.002	
1073	B- 8128	216.20 ~ 217.50	1.30	0.3	2.4	0.02	0.003	
1074	B- 8129	220.80 ~ 221.40	0.60	0.6	< 1	0.02	0.002	
1075	B- 8130	229.30 ~ 230.60	1.30	0.4	< 1	0.02	0.002	
1076	B- 8131	230.60 ~ 232.00	1.40	0.7	< 1	0.01	0.002	
1077	B- 8132	232.00 ~ 233.50	1.50	0.4	< 1	0.02	0.002	
1078	B- 8133	233.50 ~ 234.50	1.00	0.2	< 1	0.02	0.002	
1079	B- 8134	234.50 ~ 235.90	1.40	0.5	< 1	0.05	0.002	
1080	B- 8135	235.90 ~ 237.00	1.10	0.2	< 1	0.02	0.002	

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser. no.	Samp. no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t) 0.1g/t	Ag(g/t) 1g/t	As(%) 0.01%	W(%) 0.001%	Discriptions
1081	B-8136	237.00 ~ 238.10	1.10	0.4	< 1	0.04	0.002	
1082	B-8137	238.10 ~ 239.10	1.00	2.0	< 1	0.22	0.002	
1083	B-8138	239.10 ~ 240.00	0.90	0.6	< 1	0.22	0.002	
1084	B-8139	240.00 ~ 241.15	1.15	0.8	< 1	0.34	0.003	
1085	B-8140	241.15 ~ 242.10	0.95	24.6	1.4	0.32	0.004	
1086	B-8141	242.10 ~ 243.00	0.90	5.4	< 1	0.14	0.001	
1087	B-8142	243.00 ~ 244.10	1.10	0.8	< 1	0.16	0.002	
1088	B-8143	244.10 ~ 245.10	1.00	0.8	< 1	0.05	0.002	
1089	B-8144	245.10 ~ 246.30	1.20	0.4	3.2	0.09	0.002	
1090	B-8145	254.30 ~ 255.20	0.90	6.2	< 1	0.15	0.480	
1091	B-8146	261.70 ~ 262.10	0.40	0.5	< 1	0.06	0.008	
1092	B-8147	263.80 ~ 264.80	1.00	0.8	< 1	0.06	0.020	
1093	B-8148	264.80 ~ 265.80	1.00	0.2	1.8	0.05	0.003	
1094	B-8149	267.60 ~ 269.00	1.40	< 0.1	< 1	< 0.01	0.004	
1095	B-8150	269.00 ~ 270.00	1.00	0.1	< 1	0.01	0.002	
1096	B-8151	270.00 ~ 271.00	1.00	0.1	< 1	0.02	0.003	
1097	B-8152	271.00 ~ 272.50	1.50	0.2	< 1	0.02	0.003	
1098	B-8153	273.60 ~ 274.40	0.80	0.1	2.4	< 0.01	0.004	
1099	B-8154	276.90 ~ 278.00	1.10	0.1	< 1	< 0.01	0.003	
1100	B-8155	278.00 ~ 279.00	1.00	0.6	1.2	< 0.01	0.007	
1101	B-8156	279.00 ~ 280.30	1.30	0.2	< 1	< 0.01	0.005	
1102	B-8157	285.00 ~ 286.00	1.00	0.3	< 1	0.10	0.030	
1103	B-8158	286.00 ~ 286.90	0.90	0.3	< 1	< 0.01	0.003	
1104	B-8159	286.90 ~ 287.60	0.70	< 0.1	< 1	< 0.01	0.007	
1105	B-8160	287.60 ~ 288.20	0.60	0.4	< 1	0.05	0.007	
1106	B-8161	288.20 ~ 289.20	1.00	0.2	< 1	< 0.01	0.002	
1107	B-8162	289.20 ~ 290.70	1.50	0.2	1.8	0.01	< 0.004	
1108	B-8163	290.70 ~ 292.20	1.50	0.1	< 1	0.02	0.002	
1109	B-8164	298.20 ~ 299.40	1.20	0.4	5.1	0.06	0.002	
1110	B-8165	314.20 ~ 315.00	0.80	0.4	< 1	0.02	0.003	

Appendix 2-6 Assay Results of Ore Samples (Altynsai Drillcore)

Ser.no.	Samp.no.	Depth(m)	Length(m) Lower limit⇒	Au(g/t)		Ag(g/t)		AS(%)	W(%)	Discriptions
				0.1g/t	g/t	g/t	g/t			
1111	B-8166	315.00 ~ 315.80	0.80	2.4	1.6	0.06	0.001%	0.004		
1112	B-8167	315.80 ~ 317.00	1.20	0.5	< 1	0.01	0.001	0.001		
1113	B-8168	317.00 ~ 318.00	1.00	0.1	< 1	0.02	0.002	0.002		
1114	B-8169	318.00 ~ 319.30	1.30	0.2	< 1	0.08	0.003	0.003		
1115	B-8170	319.30 ~ 320.10	0.80	0.4	< 1	0.03	0.002	0.002		
1116	B-8171	320.10 ~ 321.60	1.50	0.2	< 1	0.07	0.002	0.002		
1117	B-8172	321.60 ~ 322.60	1.00	0.4	< 1	< 0.01	< 0.001	< 0.001		
1118	B-8173	322.60 ~ 323.30	0.70	0.2	< 1	< 0.01	< 0.001	< 0.001		
1119	B-8174	323.30 ~ 324.30	1.00	0.3	< 1	< 0.01	0.002	0.002		
1120	B-8175	324.30 ~ 325.30	1.00	< 0.1	< 1	0.01	0.003	0.003		
1121	B-9100	170.00 ~ 171.20	1.20	0.2	< 1	0.04	< 0.001	< 0.001		
1122	B-9101	171.20 ~ 172.10	0.90	0.4	< 1	0.09	0.002	0.002		
1123	B-9102	174.70 ~ 175.50	0.80	0.1	< 1	0.01	0.002	0.002		
1124	B-9103	175.50 ~ 176.50	1.00	0.6	< 1	0.10	0.003	0.003		
1125	B-9104	176.50 ~ 177.50	1.00	0.1	< 1	0.02	0.002	0.002		
1126	B-9105	192.70 ~ 193.70	1.00	0.5	< 1	0.21	0.002	0.002		
1127	B-9106	194.60 ~ 196.20	1.60	0.6	< 1	0.09	0.003	0.003		

Appendix 2-7 Results of X-ray Diffraction Analyses

No.	Sample No.	Locality		Rock description	Quartz	Analcite	Kaolinite	Sericite	Chlorite	Ser-Sm mixed	Plagioclase	K-feldspar	Hornblende	Clinopyroxene	Epidote	Calcite	Pyrite	Marcasite	Goethite	Molybdenite	Tourmaline	Garnet	
		Grid (x-y)	Manifestations																				
1	HGX01	84	Sarrakchi	Syenitic albite	△					⊙													
2	HGX02	83	Sarrakchi	Syenitic albite	△																		
3	HGX03	73	Aktau	Gabbroic diabase dyke	△		○	△					⊙										
4	HGX04	60	-	Carbonatized rock	△		○									⊙							
5	HGX05	69	Maulyan	Biotite-muscovite schist	⊙		△	△															
6	HGX06	61	-	Cataclastic tonalite	⊙		○	○															
7	HGX07	61	-	Myronitic hornblende-biotite granodiorite	⊙								△										
8	HGX08	57	-	Fe-Mn oxide ore (hydrothermal)	⊙											⊙							
9	HGX09	40	-	Altered schist	⊙			○															
10	HGX10	40	-	Silicified rock	⊙			△															
11	HGX11	51	Lyngar	Greenish yellow skarn	⊙											⊙							
12	HGX12	51	Lyngar	Silicified-limonitized rock	⊙																		
13	HGX13	79	-	Amphibolite	⊙		⊙	○					⊙										
14	HGX14	84	Sarrakchi	Graphite granite	⊙							○											
15	HGX15	40	Karamchet	Meta-porphyrite	⊙		○	○															
16	HGX16	51	Lyngar	Skarn with sulfides	⊙		⊙	△					△										
17	HGX17	40	Karamchet	Quartz vein with sulfides	⊙																		
18	HGX18	51	Lyngar	Skarn with anenopyrite	⊙																		
19	HGX19	51	Lyngar	Skarn with molibdenite	⊙																		
20	HGX20	84	-	Biotite-muscovite-staurolite schist	⊙		○	○													⊙		○
21	HGX21	83	Sebastian	Andalusite-chlorite-muscovite-biotite schist	⊙		○	○	△														
22	HGX22	36	-	Biotite-muscovite hornfels	⊙																		
23	HGX23	36	-	Green silicified diorite	⊙		△	△															
24	HGX24	36	-	Green diorite	⊙		⊙	○															
25	HGX25	34	Bashtut	Grey silicified rock	⊙																		
26	HGX26	34	Bashtut	Purple silicified rock	⊙																		
27	HGX27	34	Bashtut	White grey silicified altered rock	⊙			○															
28	HGX28	34	Bashtut	Greenish grey sandy phyllite	⊙		△	○															
29	HGX29	34	Bashtut	Black phyllite	⊙		⊙	○															
30	HGX30	35	Bashtut	White veinlets in silicified rock	⊙																		
31	HGX31	33	-	Sandstone hornfels	⊙		○	○															
32	HGX32	31	Birab-South	Meta-dolerite	△		⊙	○															
33	HGX33	35	Bashtut	White veinlets in silicified rock	⊙		⊙	○															
34	HGX34	35	Bashtut	White altered schist	⊙		⊙	○															

⊙ : abundant, ○ : common, △ : poor, . : rare, *Ser-Sm mixed layer, Serpentine-Saectite mixed layer mineral

Appendix 2-7 Results of X-ray Diffraction Analyses

No.	Sample No.	Locality		Rock description	Quartz	Analcite	Kaolinite	Sericite	Chlorite	*Ser-Sm mixed	Plagioclase	K-feldspar	Hornblende	Clinopyroxene	Epidote	Calcite	Pyrite	Marcasite	Goethite	Molybdenite	Tourmaline	Garnet
		Grid (xy)	Manifestations																			
35	HGX35	29	79	Green altered dyke	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
36	HGX36	29	80	Boitite diorite porphyry	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
37	HGX37	29	80	Orange brown silicified diorite dyke	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
38	HGX38	52	77	Reddish brown weathered diorite	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
39	HGX39	52	77	Greenish grey weathered diorite	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
40	HGX40	52	77	Brown weathered diorite	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
41	HDX01	753.39	461.08	Chlorite-sericite schist	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
42	HDX02	753.39	461.08	Spotted chlorite-sericite schist	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
43	HDX03	753.52	460.97	Silicified rock	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
44	SDX04	754.26	461.46	Spotted chlorite-sericite schist	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
45	SDX05	754.23	461.05	Pinkish white altered rock in shear zone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
46	SDX06	754.37	460.94	Quartz-tourmaline veinlets	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
47	SDX07	754.58	460.61	Altered sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
48	SDX08	754.64	460.54	Altered sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
49	SDX10	754.71	460.52	Altered sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
50	SDX11	752.76	461.03	Altered sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
51	SDX12	752.79	461.03	Limonitized rock	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
52	SDX13	752.79	461.03	Altered sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
53	SDX14	752.87	460.96	Limonitized rock	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
54	SDX15	752.87	460.96	Limonitized rock	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
55	SDX16	752.87	460.96	Limonitized sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
56	SDX22	754.02	460.15	Limonitized sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
57	SDX26	755.30	460.22	Limonitized altered rock	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
58	SDX29	753.99	461.45	Quartz vein with sulfides	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
59	SDX30	754.27	461.09	Silicified limonitized sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
60	SDX31	754.27	461.09	Quartz-tourmaline veinlets	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
61	SDX32	754.27	461.09	Silicified sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
62	SDX33	754.34	461.06	Silicified sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
63	SDX34	754.34	461.06	Silicified sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
64	SDX35	755.37	460.54	Silicified limonitized sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
65	SDX36	755.37	460.54	Silicified sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
66	SDX37	755.37	460.54	Silicified sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
67	SDX38	54.689	60.942	Sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○
68	SDX39	54.690	60.943	Silicified sandstone	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○	○

○ : abundant, ○ : common, △ : poor, . : rare *Ser-Sm mixed layer : Sericite-Saectite mixed layer mineral.




Appendix 2-7 Results of X-ray Diffraction Analyses

No.	Sample No.	Locality		Rock description	Quartz	Analcite	Kaolinite	Sericite	Chlorite	Ser-Sm mixed	Plagioclase	K-feldspar	Hornblende	Clinopyroxene	Epidote	Calcite	Pyrite	Marcasite	Goeschite	Molybdenite	Tourmaline	Garnet
		Grid (x-y)	Manifestations																			
69	SDX40	54.690	60.944	sulfide	⊙			○			△											
70	SDX41	54.690	60.944	Quartz vein	⊙																	
71	SDX42	54.690	60.944	Quartz vein	⊙			⊙			△											
72	SDX43	54.691	60.946	Quartz vein	⊙						△											
73	SDX44	54.691	60.947	Quartz vein	⊙																	
74	SDX45	54.691	60.948	sulfides	⊙			⊙			△											
75	SDX46	54.692	60.948	Silicified sandstone	⊙			⊙			△											
76	SDX47	54.692	60.949	Tourmaline-muscovite hornfels	⊙			⊙			△											
77	SDX49	54.678	60.946	sulfides	⊙			⊙			△											
78	SDX51	54.678	60.942	Biotite-muscovite hornfels	⊙			⊙			△											
79	SDX55	54.713	60.947	Sandstone	⊙			⊙			△											
80	SDX56	54.713	60.945	Sandstone	⊙			○			△											
81	B1-4	MJSN-1	180.4	Quartz-pyrite-chlorite vein	⊙																	
82	B2-7	MJSN-2	154.1	Quartz-pyrite-chlorite vein	⊙																	
83	B3-1	MJSN-3	33.6	Quartz-pyrite-arsenopyrite vein	⊙			○														
84	B5-5	MJSN-3	206.3	Quartz-pyrite-arsenopyrite vein	⊙			○														
85	B3-10	MJSN-3	319.2	Biotite-muscovite hornfels	⊙			△														
86	B4-2	MJSN-4	50.2	Silicified rock	⊙			○														
87	B4-3	MJSN-4	66.85	Silicified rock	⊙			○														
88	B4-10	MJSN-4	145.3	Quartz-pyrite-arsenopyrite-tourmaline vein	⊙			○														
89	B4-17	MJSN-4	302.8	Silicified sandstone	⊙			○														
90	B5-6	MJSN-5	122.0	Silicified rock with pyrite, hematite and arsenopyrite	⊙			⊙														
91	B5-7	MJSN-5	177.5	Quartz-pyrite-arsenopyrite-tourmaline vein	⊙			⊙														
92	B5-8	MJSN-5	301.5	Spotted biotite-muscovite hornfels	⊙			○														
93	B6-3	MJSN-6	152.9	Biotite-muscovite hornfels	⊙			⊙														
94	B7-2	MJSN-7	51.7	Silicified rock	⊙			○														
95	B7-5	MJSN-7	140.3	Quartz-pyrite-arsenopyrite-tourmaline vein	⊙			○														
96	B7-6	MJSN-7	141.8	Silicified slate	⊙			○														
97	B8-2	MJSN-8	51.3	Silicified sandstone	⊙			⊙														
98	B8-11	MJSN-8	237.0	Biotite-muscovite hornfels	⊙			⊙														
99	B9-3	MJSN-9	71.0	Silicified slate	⊙			○														
100	B10-2	MJSN-10	74.8	Silicified rock	⊙			○														

⊙ : abundant, ○ : common, △ : poor, ... : rare

Appendix 2-8 Homogenization Temperatures of the Fluid Inclusions

	Primary inclusions(609 data)		Secondary inclusions(131 data)	
	Temp.(°C)	Au(g/t)	Temp.(°C)	Au(g/t)
The entire area	309.7 (609 data)	2.8 (40 data)	182.4 (131 data)	0.3 (12 data)
General survey area	302.8 (57 data)	0.37 (9 data)	157.6 (26 data)	0.2 (5 data)
Detailed survey area	310.4 (552 data)	3.6 (31 data)	188.6 (105 data)	0.4 (7 data)



Appendix 2-8 Homogenization Temperatures of the Fluid Inclusions

Appendix 2-8 Homogenization Temperatures of the Fluid Inclusions

Ser. No.	Sample No.	Locality	Average temp.(°C)	Max. temp.(°C)	Min. temp.(°C)	Number of inclusions	Primary(p) / Secondary(s)	Au(g/t)	Drill No.	Depth (m)	Remarks
1	HGF01	Sebistan west	279.3	321	223	3	p	0.1			
2	HGF02	Sebistan west	168.7	202	142	6	s	<0.1			no inclusions
3	HGF03	Sebistan	-	-	-	0	-	<0.1			no inclusions
4	HGF04	Sebistan	-	-	-	0	-	<0.1			no inclusions
5	HGF05	Sebistan	150.0	158	137	4	s	0.3			
6	HGF06	Sartakchi	-	-	-	0	-	-			no inclusions
7	HGF07	Sartakchi	139.3	145	135	3	s	-			
8	HGF08	Beshbulak	337.0	352	294	5	p	<0.1			
9	HGF09	Beshbulak	287.4	327	241	5	p	<0.1			
10	HGF09	"	-	-	-	0	-	"			no inclusions
11	HGF10	Beshbulak	-	-	-	0	-	<0.1			no inclusions
12	HGF13	Taulyan	313.3	350	189	8	p	<0.1			
13	HGF14	Kurai	-	-	-	0	-	<0.1			no inclusions
14	HGF15	Kurai	145.3	152	137	4	s	<0.1			
15	HGF16	Kurai	-	-	-	0	-	0.2			no inclusions
16	HGF17	Kurai	-	-	-	0	-	<0.1			no inclusions
17	HGF18	Karamechet	-	-	-	0	-	<0.1			no inclusions
18	HGF21	Karamechet	321.8	351	298	5	p	<0.1			no inclusions
19	HGF22	Karamechet	-	-	-	0	-	0.1			no inclusions
20	HGF23	Quartz Vein II	-	-	-	0	-	0.1			no inclusions
21	HGF24	Bashrut	307.1	331	287	7	p	<0.1			no inclusions
22	HGF26	Lyngar	275.7	357	212	16	p	<0.1			no inclusions
23	HGF30	Bashrut	-	-	-	0	-	<0.1			no inclusions
24	HGF32	Kurai	-	-	-	0	-	0.1			no inclusions
25	HGF33	Bashrut	-	-	-	0	-	2.8			no inclusions
26	HGF36	Bashrut	159.8	179	145	5	s	0.1			
27	HGF39	Biab-South	173.0	184	155	4	s	0.4			
28	HGF39	"	-	-	-	0	-	"			no inclusions
29	HGF40	Biab	-	-	-	0	-	8.8			no inclusions
30	HGF41	Maulyan	328.1	356	284	8	p	0.2			
31	HDF01	Altynsai	299.1	321	253	7	p	-			
32	HDF02	Altynsai	310.8	351	255	11	p	2.4			
33	HDF03	Altynsai	-	-	-	0	-	4.4			no inclusions
34	HDF04	Altynsai	333.6	381	204	16	p	0.4			
35	SDF01	Altynsai	171.8	181	163	4	s	-			
36	SDF02	Altynsai	329.1	381	287	17	p	-			

Appendix 2-8 Homogenization Temperatures of the Fluid Inclusions

Ser. No.	Sample No.	Locality	Average temp.(°C)	Max. temp.(°C)	Min. temp.(°C)	Number of inclusions	Primary(p) / Secondary(s)	Au(g/t)	Drill No.	Depth (m)	Remarks
37	SDF03	Altynsai	311.0	339	284	8	p	-			
38	SDF04	Altynsai	-	-	-	0	-	0.2			no inclusions
39	SDF05	Altynsai	311.9	341	289	12	p	-			
40	SDF06	Altynsai	244.6	294	212	8	p	-			No.6 Vein
41	SDF07	Altynsai	336.2	369	317	9	p	-			
42	SDF08	Altynsai	327.7	351	306	16	p	<0.1			
43	SDF09	Altynsai	304.6	357	242	16	p	0.8			
44	SDF10	Altynsai	307.4	366	264	16	p	-			
45	SDF12	Altynsai	126.4	135	114	5	s	-			No.1 Vein
46	SDF13	Altynsai	201.4	213	187	7	s	0.8			No.3 Vein
47	SDF14	Altynsai	-	-	-	0	-	3.2			no inclusions
48	SDF16	Altynsai	305.9	342	244	9	p	0.8			No.7 Vein
49	SDF18	Altynsai	323.6	368	264	15	p	1.2			No.7 Vein
50	SDF19	Altynsai	323.2	342	294	11	p	0.3			No.7 Vein
51	SDF20	Altynsai	241.1	278	196	21	p	0.7			No.7 Vein
52	SDF21	Altynsai	-	-	-	0	-	-			no inclusions
53	SDF22	Altynsai	247.6	291	196	11	p	-			Berkut Vein
54	SDF23	Altynsai	275.4	305	249	13	p	-			Berkut Vein
55	SDF24	Altynsai	108.0	112	105	4	s	<0.1			Berkut Vein
56	SDF27	Altynsai	185.2	249	139	13	s	<0.1			
57	SDF28	Altynsai	321.1	382	242	12	p	-			
58	SDF29	Altynsai	205.0	241	154	15	s	<0.1			
59	SDF30	Altynsai	242.3	271	204	13	s	-			
60	SDF31	Altynsai	179.0	179	179	1	s	-			
61	SDF32	Altynsai	331.3	379	291	6	p	0.2			Kazanbulak Vein
62	SDF34	Altynsai	295.1	344	225	13	p	<0.1			
63	SDF35	Altynsai	308.0	311	305	2	p	<0.1			
64	SDF36	Altynsai	198.5	224	178	8	s	0.2			
65	SDF37	Altynsai	324.1	428	269	13	p	-			
			192.3	212	174	7	s	-			
66	SDF38	Altynsai	-	-	-	0	-	1.2			no inclusions
67	SDF39	Altynsai	302.6	364	187	20	p	-			
68	SDF40	Altynsai	326.6	346	307	7	p	-			Northwest Vein
69	SDF41	Altynsai	321.0	354	244	21	p	-			No.2 Vein
70	SDF42	Altynsai	308.6	337	276	17	p	-			No.2 Vein
71	SDF43	Altynsai	342.6	378	317	11	p	-			No.2 Vein

Appendix 2-8 Homogenization Temperatures of the Fluid Inclusions

Ser. No.	Sample No.	Locality	Average temp.(°C)	Max. temp.(°C)	Min. temp.(°C)	Number of inclusions	Primary(p)/ Secondary(s)	Aug(%)	Drill No.	Depth (m)	Remarks
72	SDF44	Altynsai	311.0	342	274	11	p	0.4			No.2 Vein
	"	"	227.3	231	223	3	s				
73	SDF45	Altynsai	326.3	356	275	12	p				No.6 Vein
74	SDF46	Altynsai	-	-	-	0	-	8.2			no inclusions
75	SDF47	Altynsai	318.9	364	251	11	p	69.6			No.1 Vein, tunnel
76	SDF48	Altynsai	350.2	375	332	12	p	14.2			No.2 Vein, tunnel
77	SDF49	Altynsai	334.3	361	309	13	p	4.8			No.3 Vein, tunnel
78	SDF50	Altynsai	310.1	351	216	11	p	2.8			No.4 Vein, tunnel
79	SDF51	Altynsai	-	-	-	0	-	0.2			no inclusions
80	SDF52	Altynsai	308.4	352	248	7	p	0.1			Kazanbulak Vein
	"	"	121.5	135	108	2	s				
81	B1-4	Altynsai	324.5	389	238	15	p	<0.1	MJSN-1	180.4	
82	B2-6	Altynsai	349.3	361	342	3	p	<0.1	MJSN-2	120.8	
	"	"	183.5	192	177	6	s				
83	B3-2	Altynsai	325.2	354	288	9	p	0.4	MJSN-3	80.35	
84	B3-6	Altynsai	110.0	115	102	3	s	0.2	MJSN-3	211	
85	B4-4	Altynsai	-	-	-	0	-	-	MJSN-4	68	no inclusions
86	B4-6	Altynsai	195.3	234	177	7	s	1.4	MJSN-4	77.8	
87	B4-8	Altynsai	280.2	305	221	5	p	1.2	MJSN-4	102.6	
88	B4-13	Altynsai	329.4	352	288	14	p	1.8	MJSN-4	215.8	
89	B5-4	Altynsai	336.1	372	206	16	p	0.1	MJSN-5	61.4	
90	B5-10	Altynsai	280.9	331	240	8	p	2.8	MJSN-5	315.4	
	"	"	164.8	178	149	5	s				
91	B6-1	Altynsai	280.2	357	195	10	p	0.2	MJSN-6	35.2	
92	B7-1	Altynsai	340.0	386	308	10	p	0.4	MJSN-7	35.05	
93	B7-4	Altynsai	-	-	-	0	-	-	MJSN-7	139.3	no inclusions
94	B7-7	Altynsai	-	-	-	0	-	-	MJSN-7	176.9	no inclusions
95	B8-4	Altynsai	326.0	327	325	2	p	1.6	MJSN-8	61.8	
	"	"	159.0	159	159	1	s				
96	B8-5	Altynsai	262.0	267	257	2	p	1.6	MJSN-8	62.5	
	"	"	189.0	189	189	1	s				
97	B8-12	Altynsai	321.1	342	308	8	p	2	MJSN-8	238.2	
98	B9-4	Altynsai	291.8	379	243	12	p	0.2	MJSN-9	72.2	
99	B10-1	Altynsai	301.5	337	261	8	p	-	MJSN-10	33.9	
100	B10-5	Altynsai	282.6	335	202	15	p	0.1	MJSN-10	108.6	

Appendix 3. Miscellaneous Data for the Drilling Survey

Appendix 3-1(1) List of the Used Equipments for Drilling

(MJSN-1,2,7,10)

Item	Model	Quantity	Capacity, type and specification
Drilling machine	SKB-4	1	Capacity ϕ 76mm:300m ϕ 59mm:500m Inner diameter of spindle:60mm
Motor for drill	4AM-140	1	22kw
Pump	NB-3	1	Piston ϕ 40mm, Capacity 40/120 liter/min Pressure 4 kg/min
Motor for pump	4AM-132	1	7.5kw
Wire line hoist	LB-5	1	
Motor for hoist		1	3kw
Mud mixer	GKL-2M	1	
Derrick	UKB-200	1	Maximum load 15T
Rod holder	TD	1	
Drill rods	SSK-59	60	4.50 m/pc
	ϕ 50mm	5	4.00 m/pc
	ϕ 42mm	5	4.00 m/pc
Casing pipes	ϕ 108mm	4	3.00 m/pc
	ϕ 89mm	5	3.00 m/pc
	ϕ 73mm	15	4.00 m/pc
Core tube assembly	SSK-59	6	3.00 m/pc
	SSK-59	10	2.50 m/pc
	ϕ 108mm	1	1.00 m/pc
	ϕ 93mm	1	1.00 m/pc
	ϕ 76mm	1	1.00 m/pc
	OKS-73	1	1.00 m/pc (Ejector)

Appendix 3-1(2) List of the Used Equipments for Drilling

(MJSN-3)

Item	Model	Quantity	Capacity, type and specification
Drilling machine	SKB-41	1	Capacity $\phi 76\text{mm}$:300m $\phi 59\text{mm}$:500m Inner diameter of spindle:63mm
Motor for drill	4AM-180	1	22kw
Pump	NB-4	1	Piston $\phi 60\text{mm}$, Capacity 40/160 liter/min Pressure kg/min
Motor for pump	4AM-132	1	7 kw
Wire line hoist	—	—	
Motor for hoist	—	—	
Mud mixer	TD	1	
Derrick	MPGY-3	1	Maximum load 20T
Rod holder	PT-1200	1	
Drill rods	SSK-59 $\phi 50\text{mm}$ $\phi 42\text{mm}$	110 30	4.50 m/pc 4.00 m/pc 4.00 m/pc
Casing pipes	$\phi 108\text{mm}$ $\phi 89\text{mm}$ $\phi 73\text{mm}$	5 20 5	3.00 m/pc 3.00 m/pc 4.00 m/pc
Core tube assembly	SSK-59 SSK-59 $\phi 108\text{mm}$ $\phi 93\text{mm}$ $\phi 76\text{mm}$ OKS-73	— — — 1 4 2	3.00 m/pc 2.50 m/pc 3.00 m/pc 3.00 m/pc 3.00 m/pc 1.00 m/pc (Ejector)

Appendix 3-1(3) List of the Used Equipments for Drilling

(MJSN-4,6,9)

Item	Model	Quantity	Capacity, type and specification
Drilling machine	SKB-41	1	Capacity ϕ 76mm:300m ϕ 59mm:500m Inner diameter of spindle:60mm
Motor for drill	4AM-180	1	22kw
Pump	NB-4	1	Piston ϕ 50mm, Capacity 40/160 liter/min Pressure kg/min
Motor for pump	4AM-132	1	7.5kw
Wire line hoist	LB-5	1	
Motor for hoist		1	4 kw
Mud mixer	GKL-2M	1	
Derrick	UKB-500	1	Maximum load 15T
Rod holder	TD	1	
Drill rods	SSK-59 ϕ 50mm ϕ 42mm	80 5 5	4.50 m/pc 4.00 m/pc 4.00 m/pc
Casing pipes	ϕ 108mm ϕ 89mm ϕ 73mm	3 5 15	3.00 m/pc 3.00 m/pc 4.00 m/pc
Core tube assembly	SSK-59 SSK-59 ϕ 108mm ϕ 93mm ϕ 76mm	6 6 1 1 1	3.00 m/pc 2.50 m/pc 1.00 m/pc 1.00 m/pc 1.00 m/pc

Appendix 3-1(4) List of the Used Equipments for Drilling

(MJSN-5,8)

Item	Model	Quantity	Capacity, type and specification
Drilling machine	ZIF-650	1	Capacity ϕ 76mm:500m ϕ 59mm:650m Inner diameter of spindle:64mm
Motor for drill	4AM-180	1	22kw
Pump	NB-4	1	Piston ϕ 60mm, Capacity 60/320 liter/min Pressure kg/min
Motor for pump	4AM-132	1	7.5kw
Wire line hoist	LB-5	1	
Motor for hoist		1	4 kw
Mud mixer	GKL-2M	1	7.5kw
Derrick	MRGU	1	Maximum load 15T
Rod holder	TD	1	
Drill rods	SSK-59 ϕ 50mm ϕ 42mm	80 5 5	4.50 m/pc 4.00 m/pc 4.00 m/pc
Casing pipes	ϕ 108mm ϕ 89mm ϕ 73mm	4 10 10	3.00 m/pc 3.00 m/pc 4.00 m/pc
Core tube assembly	SSK-59 SSK-59 ϕ 108mm ϕ 93mm ϕ 76mm	2 6 1 1 1	3.00 m/pc 2.50 m/pc 1.00 m/pc 1.00 m/pc 1.00 m/pc

Appendix 3-2(1) Results of Drilling Works on Individual Drillhole

(MJSN-1)

	Survey period		Breakdown of period			
	Period	Total days	Working days	No working days	Total workers	
Preparation	Aug. 24, '97~Sept. 1, '97	9.0	3.4	5.6	41	
Drilling	Sept. 2, '97~Oct. 1, '97	29.2	25.7	3.5	161	
Dismount	Oct. 1, '97~Oct. 1, '97	0.8	0.3	0.5	3	
Total	Aug. 24, '97~Oct. 1, '97	39.0	29.4	9.6	205	
Drilling length						
Programmed length	190.00m	Overburden			2.00m	
Prolongation	0 m	Core length			155.95m	
Effective length	190.00m	Core recovery			83.0 %	
Working hours			Core recovery by each 100m			
			Length (m)	Each (%)	Cumula. (%)	
Drilling	158.0H	22.4 %	0-100	79.2	79.2	
Out drilling	327.0H	46.4 %	100-190	87.0	83.0	
Regain of accident	87.0H	12.3 %				
Preparation	9.0H	1.3 %				
Dismount/Mobilization	25.0H	3.5 %				
Others	99.0H	14.1 %	Efficiency			
			Effective length/Total days			
			4.87m/d			
Total	705.0H	100 %	Effective length/Working days			
			6.46m/d			
Drilling length by diameter						
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/m	Total
Drilling length	7.00m	183.00m				190.00m
Core length	1.95m	154.00m				155.95m
Inserted casing pipes						
Inserted length by diameter		Inserted length/Drilling length×100		Casing Recovery		
73 m/m	23.00m	12.1 %		100 %		
m/m	m	%		%		

Appendix 3-2(2) Results of Drilling Works on Individual Drillhole

(MJSN-2)

	Survey period		Breakdown of period		Total workers	
	Period	Total days	Working days	No working days		
Preparation	Oct. 5, '97~Oct. 30, '97	26.0	4.3	21.7	30	
Drilling	Oct. 31, '97~Nov. 14, '97	25.0	24.0	1.0	142	
Dismount	Nov. 25, '97~Nov. 25, '97	1.0	0.5	0.5	6	
Total	Oct. 5, '97~Nov. 25, '97	52.0	28.8	23.2	178	
Drilling length						
Programmed length	160.00m	Overburden	3.70m			
Prolongation	0.10m	Core length	129.70m			
Effective length	160.10m	Core recovery	82.9%			
Working hours			Core recovery by each 100m			
			Length (m)	Each (%)	Cumula. (%)	
Drilling	132.5H	19.2%	0.00-100.40	83.4	83.4%	
Out drilling	262.5H	38.0%	100.40-160.10	82.2	82.9%	
Regain of accident	85.0H	12.3%				
Preparation	— H	— %				
Dismount/Mobilization	24.0H	3.5%				
Others	186.0H	27.0%	Efficiency			
			Effective length/Total days			
			3.08m/d			
Total	690.0H	100.0%	Effective length/Working days			
			5.56m/d			
Drilling length by diameter						
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/m	Total
Drilling length	8.50m	151.60m				160.10m
Core length	5.20m	124.50m				129.70m
Inserted casing pipes						
Inserted length by diameter		Inserted length/Drilling length×100		Casing Recovery		
89 m/m	1.00m	0.6%		100%		
73 m/m	22.60m	14.1%		100%		

Appendix 3-2(3) Results of Drilling Works on Individual Drillhole

(MJSN-3)

	Survey period		Breakdown of period		Total workers	
	Period	Total days	Working days	No working days		
Preparation	Aug. 29, '97~Sept. 20, '97	23.0	8.3	14.7	82	
Drilling	Sept. 21, '97~Dec. 26, '97	97.0	94.0	3.0	484	
Dismount	Dec. 27, '97~Dec. 28, '97	2.0	2.0	0.0	16	
Total	Aug. 29, '97~Dec. 28, '97	122.0	104.3	17.7	582	
Drilling length						
Programmed length	400.00m	Overburden		1.90m		
Prolongation Cut dwn	-58.60m	Core length		275.55m		
Effective length	341.40m	Core recovery		81.2 %		
Working hours			Core recovery by each 100m			
			Length (m)	Each (%)	Cumula. (%)	
Drilling	393.5H	15.7 %	0.00-100.55	85.1	85.1	
Out drilling	809.5H	32.4 %	100.55-200.40	78.0	82.8	
Regain of accident	1,053.0H	42.1 %	200.40-300.80	76.0	80.5	
Preparation	36.0H	1.4 %	300.80-341.40	85.8	81.2	
Dismount/Mobilization	84.0H	3.4 %				
Others	126.0H	5.0 %	Efficiency			
			Effective length/Total days			
			2.80m/d			
Total			Effective length/Working days			
			3.27m/d			
Drilling length by diameter						
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/m	Total
Drilling length	325.20m	16.20m				341.40m
Core length	260.35m	15.20m				275.55m
Inserted casing pipes						
Inserted length by diameter		Inserted length/Drilling lengthx100			Casing Recovery	
89 m/m	29.00m	8.5 %			100 %	
m/m	m	%			%	

Appendix 3-2(4) Results of Drilling Works on Individual Drillhole

(MJSN-4)

	Survey period		Breakdown of period		Total workers	
	Period	Total days	Working days	No working days		
Preparation	Sept. 14, '97~Oct. 8, '97	24.5	4.4	20.1	39	
Drilling	Oct. 8, '97~Nov. 28, '97	51.5	50.5	1.0	252	
Dismount	Nov. 29, '97~Nov. 29, '97	1.0	1.0	0	5	
Total	Sept. 14, '97~Nov. 29, '97	77.0	55.9	21.1	296	
Drilling length						
Programmed length	300.00m	Overburden		2.20m		
Prolongation	20.00m	Core length		261.40m		
Effective length	320.00m	Core recovery		82.3 %		
Working hours			Core recovery by each 100m			
			Length (m)	Each (%)	Cumula. (%)	
Drilling	291.5H	21.7 %	0.00-100.45	81.6	81.6	
Out drilling	732.5H	54.6 %	100.45-200.20	81.3	81.4	
Regain of accident	188.0H	14.0 %	200.20-320.00	83.6	82.3	
Preparation	- H	- %				
Dismount/Mobilization	48.0H	3.6 %				
Others	81.0H	6.1 %				
			Efficiency			
			Effective length/Total days			
			4.16m/d			
Total			Effective length/Working days			
1,341.0H			5.72m/d			
Drilling length by diameter						
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/m	Total
Drilling length	4.00m	316.00m				320.00m
Core length	0.30m	261.10m				261.40m
Inserted casing pipes						
Inserted length by diameter		Inserted length/Drilling length×100		Casing Recovery		
73 m/m	5.00m	1.6 %		100 %		
m/m	m	%		%		

Appendix 3-2(5) Results of Drilling Works on Individual Drillhole

(MJSN-5)

	Survey period		Breakdown of period		Total workers		
	Period	Total days	Working days	No working days			
Preparation	Sept. 22, '97~Oct. 2, '97	10.5	4.8	5.7	33		
Drilling	Oct. 2, '97~Nov. 13, '97	42.5	41.0	1.5	242		
Dismount	Nov. 14, '97~Nov. 14, '97	1.0	0.5	0.5	6		
Total	Sept. 22, '97~Nov. 14, '97	54.0	46.3	7.7	281		
Drilling length							
Programmed length	320.00m	Overburden		2.50m			
Prolongation	0 m	Core length		269.20m			
Effective length	320.00m	Core recovery		84.8 %			
Working hours			Core recovery by each 100m				
			Length (m)	Each (%)	Cumula. (%)		
Drilling	283.0H	25.5 %	0.00-102.70	87.0	87.0		
Out drilling	559.0H	50.4 %	102.70-198.30	86.2	86.6		
Regain of accident	142.0H	12.8 %	198.30-320.00	81.8	84.8		
Preparation	60.0H	5.4 %					
Dismount/Mobilization	21.0H	1.9 %					
Others	45.0H	4.0 %	Efficiency				
			Effective length/Total days				
			5.93m/d				
Total	1,110.0H	100.0 %	Effective length/Working days				
			6.91m/d				
Drilling length by diameter							
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/p	m/m	Total
Drilling length	9.00m	311.00m	m				320.00m
Core length	5.00m	264.20m	m				269.20m
Inserted casing pipes							
Inserted length by diameter		Inserted length/Drilling length×100			Casing Recovery		
73 m/m	9.00m	2.8 %			100 %		
m/m	m	%			%		

Appendix 3-2(6) Results of Drilling Works on Individual Drillhole

(MJSN-6)

	Survey period		Breakdown of period			Total workers	
	Period	Total days	Working days	No working days			
Preparation	Sept. 10, '97 - Sept. 19, '97	10.0	3.8	6.2		49	
Drilling	Sept. 20, '97 ~ Oct. 6, '97	16.5	16.5	—		98	
Dismount	Oct. 6, '97 ~ Oct. 6, '97	0.5	0.7	—		4	
Total	Sept. 10, '97 ~ Oct. 6, '97	27.0	20.8	6.2		151	
Drilling length							
Programmed length	130.0 m	Overburden			1.0 m		
Prolongation	43.0 m	Core length			144.8 m		
Effective length	173.0 m	Core recovery			84.1 %		
Working hours			Core recovery by each 100m				
			Length (m)	Each (%)	Cumula. (%)		
Drilling	126.5H	25.4 %	0-102.00	82.7	82.7		
Out drilling	208.5H	41.9 %	102.00-173.00	85.2	84.1		
Regain of accident	47.0H	9.4 %					
Preparation	18.0H	3.6 %					
Dismount/Mobilization	33.0H	6.6 %					
Others	65.0H	13.1 %					
			Efficiency				
			Effective length/Total days				
			6.41m/d				
Total			Effective length/Working days				
			8.32m/d				
Drilling length by diameter							
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/m	m/m	Total
Drilling length	4.50m	168.50m					173.00m
Core length	2.10m	142.70m					144.80m
Inserted casing pipes							
Inserted length by diameter		Inserted length/Drilling length×100			Casing Recovery		
73 m/m	4.50m	2.6 %			100 %		
m/m	m	%			%		

Appendix 3-2(7) Results of Drilling Works on Individual Drillhole

(MJSN-7)

	Survey period		Breakdown of period		Total workers	
	Period	Total days	Working days	No working days		
Preparation	Sept. 22, '97~Oct. 2, '97	10.5	3.9	6.6	40	
Drilling	Oct. 2, '97~Oct. 28, '97	26.5	25.5	1.0	146	
Dismount	Oct. 29, '97~Oct. 29, '97	1.0	0.5	0.5	6	
Total	Sept. 22, '97~Oct. 29, '97	38.0	29.9	8.1	192	
Drilling length						
Programmed length	180.00m	Overburden			1.00m	
Prolongation	11.10m	Core length			176.00m	
Effective length	191.10m	Core recovery			92.6 %	
Working hours			Core recovery by each 100m			
			Length (m)	Each (%)	Cumula. (%)	
Drilling	158.5H	22.1 %	0.00-102.80	90.6	90.6	
Out drilling	335.5H	46.8 %	102.80-191.10	94.9	92.6	
Regain of accident	94.0H	13.1 %				
Preparation	-- H	-- %				
Dismount/Mobilization	33.0H	4.6 %				
Others	96.0H	13.4 %	Efficiency			
			Effective length/Total days			
			5.03m/d			
Total	717.0H	100.0 %	Effective length/Working days			
			6.39m/d			
Drilling length by diameter						
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/m	Total
Drilling length	3.00m	188.10m				191.10m
Core length	1.60m	174.40m				176.00m
Inserted casing pipes						
Inserted length by diameter		Inserted length/Drilling length×100		Casing Recovery		
73 m/m	25.00m	13.1 %		100 %		
m/m	m	%		%		

Appendix 3-2(8) Results of Drilling Works on Individual Drillhole

(MJSN-8)

	Survey period		Breakdown of period		Total workers	
	Period	Total days	Working days	No working days		
Preparation	Oct. 29, '97~Nov. 17, '97	19.5	4.3	15.2	51	
Drilling	Nov. 17, '97~Jan. 13, '98	57.5	56.5	1.0	282	
Dismount	Jan. 14, '98~Jan. 16, '98	3.0	2.5	0.5	18	
Total	Oct. 29, '97~Jan. 16, '98	80.0	63.3	16.7	351	
Drilling length						
Programmed length	320.00m	Overburden			2.00m	
Prolongation	15.50m	Core length			278.10m	
Effective length	335.50m	Core recovery			83.4 %	
Working hours			Core recovery by each 100m			
			Length (m)	Each (%)	Cumula. (%)	
Drilling	338.5H	22.3 %	0.00-99.50	76.4	76.4	
Out drilling	554.5H	36.5 %	99.50-199.90	80.8	78.7	
Regain of accident	463.0H	30.5 %	199.90-335.50	90.1	83.4	
Preparation	9.0H	0.6 %				
Dismount/Mobilization	90.0H	5.9 %				
Others	63.0H	4.2 %				
			Efficiency			
			Effective length/Total days			
			4.19m/d			
Total			Effective length/Working days			
1.518.0H			5.30m/d			
Drilling length by diameter						
Bit diameter	93 m/m	76 m/m	59 m/m	m/m	m/m	Total
Drilling length	5.00m	4.30m	326.20m			335.50m
Core length	2.35m	2.80m	272.95m			278.10m
Inserted casing pipes						
Inserted length by diameter		Inserted length/Drilling length×100			Casing Recovery	
89 m/m	5.00m	1.5 %			100 %	
73 m/m	9.30m	2.8 %			100 %	

Appendix 3-2(9) Results of Drilling Works on Individual Drillhole

(MJSN-9)

	Survey period		Breakdown of period		Total workers	
	Period	Total days	Working days	No working days		
Preparation	Nov. 26, '97~Dec. 5, '97	10.0	4.1	5.9	59	
Drilling	Dec. 6, '97~Jan. 15, '98	41.0	41.0	0.0	235	
Dismount	Jan. 16, '98~Jan. 17, '98	2.0	1.5	0.5	10	
Total	Nov. 26, '97~Jan. 17, '98	53.0	46.6	6.4	304	
Drilling length						
Programmed length	200.00m	Overburden			4.00m	
Prolongation	0 m	Core length			171.70m	
Effective length	200.00m	Core recovery			87.6 %	
Working hours			Core recovery by each 100m			
			Length (m)	Each (%)	Cumula. (%)	
Drilling	184.5H	16.5 %	0.00-99.70	87.3	87.3	
Out drilling	409.5H	36.6 %	99.70-200.00	87.9	87.6	
Regain of accident	390.0H	34.9 %				
Preparation	9.0H	0.8 %				
Dismount/Mobilization	72.0H	6.4 %				
Others	54.0H	4.8 %	Efficiency			
			Effective length/Total days			
			3.77m/d			
Total	1,119.0H	100.0 %	Effective length/Working days			
			4.29m/d			
Drilling length by diameter						
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/m	Total
Drilling length	7.00m	193.00m				200.00m
Core length	2.00m	169.50m				171.70m
Inserted casing pipes						
Inserted length by diameter		Inserted length/Drilling length×100			Casing Recovery	
73 m/m	7.00m	3.5 %			100 %	
m/m	m	%			%	

Appendix 3-2(10) Results of Drilling Works on Individual Drillhole

(MJSN-10)

	Survey period		Breakdown of period		Total workers	
	Period	Total days	Working days	No working days		
Preparation	Nov. 19, '97~ Nov. 26, '97	8.0	3.1	4.9	35	
Drilling	Nov. 27, '97~ Jan. 2, '98	36.5	35.5	1.0	214	
Dismount	Jan. 2, '98~ Jan. 3, '98	1.5	1.5	0.0	8	
Total	Nov. 19, '97~ Jan. 3, '98	46.0	40.1	5.9	257	
Drilling length						
Programmed length	200.00m	Overburden		1.00m		
Prolongation	20.00m	Core length		188.25m		
Effective length	220.00m	Core recovery		86.0 %		
Working hours			Core recovery by each 100m			
			Length (m)	Each (%)	Cumula. (%)	
Drilling	245.0H	25.4 %	0.00-100.00	80.5	80.5	
Out drilling	437.0H	45.4 %	100.00-220.00	91.4	85.9	
Regain of accident	170.0H	17.6 %	200.00-220.00	86.4	86.0	
Preparation	9.0H	1.0 %				
Dismount/Mobilization	48.0H	5.0 %				
Others	54.0	5.6 %				
			Efficiency			
			Effective length/Total days			
			4.78m/d			
Total			Effective length/Working days			
			5.49m/d			
Drilling length by diameter						
Bit diameter	76 m/m	59 m/m	m/m	m/m	m/m	Total
Drilling length	3.70m	216.30m				220.00m
Core length	1.30m	186.95m				188.25
Inserted casing pipes						
Inserted length by diameter		Inserted length/Drilling length×100		Casing Recovery		
89 m/m	4.00m	1.8 %		100 %		
73 m/m	11.60m	5.3 %		100 %		

Application of the ...

No. 1000

Vertical text on the left margin, possibly a page number or reference code.

Main body of text, containing the primary content of the document.


Small text or mark on the right side of the page.


Small text or mark on the right side of the page.

Small text or mark on the right side of the page.

Appendix 3-3(3) PROGRESS RECORD OF DIAMOND DRILLING

(MJSN-3)





A-182

