

Appendix 11 Descriptions of polished sections for drilling survey

Ser. No.	Hole No.	Depth (m)	Coordination		Descriptions	Identified minerals											Gangue M	Remarks							
			S	W		pyrite	goethite	hematite	limonite	magnetite	chalcopyrite	chalcocite	covellite	sphalerite	bismuthinite	gold grain			quartz	titanite	rutile				
1	MJBA-1	25.50	9°58'16"	54°58'32"	Quartz vein			○																	
2	MJBA-1	38.90	9°58'16"	54°58'32"	Quartz vein																				
3	MJBA-1	48.70	9°58'16"	54°58'32"	strong sheared, silicified pink granite with epi-chl alteration																				
4	MJBA-1	61.90	9°58'16"	54°58'32"	Strong silicified talc-chl schist with Py dissemination					○															
5	MJBA-1	74.00	9°58'16"	54°58'32"	Strong silicified talc-chl schist with Py-Cp dissemination and Calc-Qz veinlets			○		●															
6	MJBA-2	30.70	9°58'14"	54°58'44"	Quartz vein with Py dissemination and veinlets in diabase (W: 6 cm)	○					○														
7	MJBA-2	32.70	9°58'14"	54°58'44"	Quartz vein with Py veinlets in diabase (W: 4 cm)	○					●														
8	MJBA-2	46.00	9°58'14"	54°58'44"	Quartz vein with strong Py dissemination and Py veinlets in granite	○					●														
9	MJBA-2	63.80	9°58'14"	54°58'44"	Quartz vein with Py dissemination in schistose diabase (W: 1 cm)	○					○														
10	MJBA-2	100.15	9°58'14"	54°58'44"	Strong to moderate Py dissemination in silicified granite with Epi-Chl alteration	○					●														
11	MJBA-3	49.07	9°29'52"	56°35'30"	Quartz vein with Py dissemination in granite with Epi-Chl alteration and Potassium alteration		●																		
12	MJBA-3	49.30	9°29'52"	56°35'30"	Py dissemination in silicified granite with Epi-Chl alteration																				
13	MJBA-4	28.45	9°29'58"	56°35'30"	Py dissemination in quartz vein	○																			
14	MJBA-4	39.95	9°29'58"	56°35'30"	Py dissemination in strong silicified and bleached granite	○																			
15	MJBA-5	38.28	9°30'05"	56°35'30"	Py-Mt dissemination in strong silicified and brecciated granite	○		●			●														
16	MJBA-5	39.90	9°30'05"	56°35'30"	Strong Py dissemination along the fracture in granite with Epi-Chl alteration along the fracture	●	○	●																	
17	MJBA-6	22.45	9°30'11"	56°35'129"	Py dissemination in strong silicified aplite with potassium alteration																				
18	MJBA-6	26.15	9°28'43"	56°36'29"	Py dissemination in strong silicified aplite with potassium alteration																				
19	MJBA-6	27.4	9°28'43"	56°36'29"	Py dissemination in strong silicified aplite with potassium alteration	○		●																	
20	MJBA-7	37.50	9°23'47"	57°27'18"	Py dissemination in altered granite with epi-chl alteration	●																			
21	MJBA-7	48.55	9°23'47"	57°27'18"	Py dissemination in altered graniten with epi-chl-K alteration																				
22	MJBA-8	43.20	9°23'56"	57°27'18"	Py dissemination in boudin quartz vein with oxidation	○																			
23	MJBA-8	44.20	9°23'56"	57°27'18"	Py dissemination in boudin quartz vein with oxidation																				
24	MJBA-8	50.50	9°23'56"	57°27'18"	Py dissemination and films in silicified and brecciated granite	○					●														
25	MJBA-8	63.90	9°23'56"	57°27'18"	Py dissemination in quartz vein with Epi-Chl alteration			●																	
26	MJBA-8	68.30	9°23'56"	57°27'18"	Py dissemination in altered granite	○																			
27	MJBA-8	78.80	9°23'56"	57°27'18"	Py dissemination in potassium altered granite	●																			
28	MJBA-8	85.60	9°23'56"	57°27'18"	Py dissemination and films in granite potassium alteration and brecciation	●																			
29	MJBA-8	90.40	9°23'56"	57°27'18"	Py dissemination and films in granite with potassium alteration and brecciation	●																			
30	MJBA-9	41.60	9°24'05"	57°27'17"	Py dissemination in granite	●																			
31	MJBA-10	42.25	9°24'10"	57°27'17"	spotted and disseminated py in granite																				
32	MJBA-11	47.70	9°22'19"	57°29'07"	Py dissemination in sheared granite						●														
33	MJBA-11	47.93	9°22'19"	57°29'07"	quartz vein with py dissemination in granite with epi-chl alteration																				
34	MJBA-11	48.40	9°22'19"	57°29'07"	Py dissemination in sheared granite with chl alteration	●					●														
35	MJBA-12	35.00	9°22'25"	57°29'07"	Milky quartz vein																				
36	MJBA-12	36.00	9°22'25"	57°29'07"	Py dissemination in sheared and silicified granite	●					●														
37	MJBA-12	39.15	9°22'25"	57°29'07"	Py dissemination in sheared and silicified granite	●					●														
38	MJBA-12	46.20	9°22'25"	57°29'07"	Py dissemination in strong silicified granite	●																			
39	MJBA-12	49.50	9°22'25"	57°29'07"	Py dissemination in strong silicified granite with Epi																				
40	MJBA-13	22.80	9°22'32"	57°29'07"	Py dissemination in sheared granite	●																			
41	MJBA-13	24.50	9°22'32"	57°29'07"	Py dissemination in granite	●																			
42	MJBA-13	30.00	9°22'32"	57°29'07"	Py dissemination in sheared granite	●																			
43	MJBA-13	47.00	9°22'32"	57°29'07"	Py dissemination in granite	●																			
44	MJBA-13	49.70	9°22'32"	57°29'07"	Py dissemination in silicified granite																				

Appendix 12 Results of X-ray diffraction analyses for drilling survey

Ser. No.	Hole No.	Depth (m)	Coordination		Descriptions	Detected Minerals														Remarks				
			S	W		quartz	K-feldspar	albite	hornblende	biotite	sericite	chlorite	kaolinite	smectite	talc	l/S	Tremolite	calcite	dolomite		pyrite	goethite	sphalerite	rutile
1	MJBA-1	23.00	9°58'16"	54°58'32"	quartz rich schist with epi-chl alteration	⊙																		
2	MJBA-1	39.50	9°58'16"	54°58'32"	strong sheared schist with quartz vein	⊙									⊙	Δ								
3	MJBA-1	50.70	9°58'16"	54°58'32"	chl-epi-K alteration in sheared schist			⊙		⊙														
4	MJBA-1	56.45	9°58'16"	54°58'32"	strong silicified talc-chl schist		⊙								⊙		⊙		Δ					
5	MJBA-1	75.50	9°58'16"	54°58'32"	strong silicified bi-chl schist with py-op dissemination	⊙									⊙		⊙							
6	MJBA-1	92.50	9°58'16"	54°58'32"	slightly silicified granitic gneiss	⊙	⊙	⊙									Δ							
7	MJBA-2	30.70	9°58'14"	54°58'44"	quartz vein with py veinlets in diabase	⊙								Δ					⊙		Δ			
8	MJBA-2	32.60	9°58'14"	54°58'44"	argillized and silicified diabase with py dissemination	⊙								Δ						Δ		Δ		
9	MJBA-2	46.00	9°58'14"	54°58'44"	quartz vein in granite with py dissemination	⊙		⊙												⊙		Δ		
10	MJBA-2	63.80	9°58'14"	54°58'44"	quartz vein with py dissemination in slightly schistose diabase	⊙															Δ			
11	MJBA-3	44.80	9°29'52"	56°35'30"	sheared zone in granite with epi-chl alteration	⊙	⊙	⊙																
12	MJBA-3	49.30	9°29'52"	56°35'30"	silicified granite with py dissemination and epi-chl	⊙	⊙	⊙							Δ									
13	MJBA-4	28.30	9°29'58"	56°35'30"	bleached and sheared granite with epi-chl alteration	⊙																		
14	MJBA-4	39.95	9°29'58"	56°35'30"	strong silicified granite with py dissemination	⊙	⊙	⊙																
15	MJBA-5	39.90	9°30'05"	56°35'30"	py dissemination fracture in silicified granite with epi-chl	⊙	⊙	⊙							⊙	Δ								
16	MJBA-5	45.30	9°30'05"	56°35'30"	py disseminated fracture in silicified granite with epi-chl	⊙	⊙	⊙							⊙	Δ								
17	MJBA-6	22.45	9°30'11"	56°35'129"	strongly silicified apatite with py dissemination and epi-chl-K alter	⊙	⊙	⊙																
18	MJBA-6	26.15	9°30'11"	56°35'129"	strongly silicified apatite with py dissemination and epi-chl-K alter	⊙	⊙	⊙																
19	MJBA-6	27.40	9°30'11"	56°35'129"	strongly silicified apatite with py dissemination and epi-chl-K alter	⊙	⊙	⊙																
20	MJBA-7	25.90	9°23'47"	57°27'18"	weathered granite with epi-chl-K alteration and py dissemination	⊙	⊙	⊙													Δ			
21	MJBA-7	28.30	9°23'47"	57°27'18"	py dissemination and epi-chl-K alteration in silicified granite	⊙	⊙	⊙													Δ			
22	MJBA-7	48.70	9°23'47"	57°27'18"	strong K-epi-chl alteration in granite	⊙	⊙	⊙													Δ			
23	MJBA-8	39.00	9°23'56"	57°27'18"	altered granite with epi-chl alteration and py dissemination	⊙	⊙	⊙																
24	MJBA-8	44.30	9°23'56"	57°27'18"	silicified and sheared granite py dissemination and epi-chl alteration	⊙	⊙	Δ														Δ		
25	MJBA-8	50.05	9°23'56"	57°27'18"	silicified sheared zone in granite with py dissemination and fine silicified and brecciated granite with py dissemination and epi-chl	⊙	Δ																	
26	MJBA-8	57.50	9°23'56"	57°27'18"	altered granite with py dissems and chl-epi alteration	⊙	⊙	⊙																
27	MJBA-8	83.60	9°23'56"	57°27'18"	altered granite with epi-chl alteration and chl-epi alteration	⊙	⊙	⊙																
28	MJBA-9	16.00	9°24'05"	57°27'17"	silicified, granite with Epi and Chl	⊙	⊙	⊙							Δ						Δ			
29	MJBA-9	28.00	9°24'05"	57°27'17"	porphyritic granite with Epi, Chl and Py	⊙	⊙	⊙													Δ			
30	MJBA-9	40.40	9°24'05"	57°27'17"	porphyritic granite with epidote and potassium alteration	⊙	⊙	⊙													Δ		Δ	
31	MJBA-9	44.65	9°24'05"	57°27'17"	ho-bi granite with potassium feldspar	⊙	⊙	⊙														Δ		
32	MJBA-10	22.00	9°24'10"	57°27'17"	sheared and mylonitized, argillized granite	⊙		⊙																
33	MJBA-10	29.90	9°24'10"	57°27'17"	silicified granite with epi-K alteration	⊙	⊙	⊙																
34	MJBA-10	31.65	9°24'10"	57°27'17"	sheared, silicified granite with py dissemination	⊙	Δ	Δ							⊙	⊙								
35	MJBA-10	33.12	9°24'10"	57°27'17"	chl-epi sheared zone in granite with py dissemination	⊙		⊙	Δ	⊙	Δ													
36	MJBA-10	35.50	9°24'10"	57°27'17"	epi-chl-K alteration in silicified granite	⊙	⊙	⊙													Δ			
37	MJBA-10	47.60	9°24'10"	57°27'17"	brecciated, altered granite with chl-epi alteration	⊙	⊙	⊙													Δ			
38	MJBA-11	44.65	9°22'19"	57°29'07"	chl-epi-K alteration in granite	⊙	⊙	⊙													Δ			
39	MJBA-11	47.70	9°22'19"	57°29'07"	py dissemination in sheared zone in granite	⊙	⊙	⊙																
40	MJBA-11	49.70	9°22'19"	57°29'07"	py dissemination in chl alteration	⊙	⊙	⊙													Δ			
41	MJBA-12	16.00	9°22'25"	57°29'07"	apophite of brecciated granite with Kao. and reddish spot	⊙																		
42	MJBA-12	26.50	9°22'25"	57°29'07"	apophite of brecciated granite with Py dissemination	⊙																		
43	MJBA-12	36.00	9°22'25"	57°29'07"	silicified, sheared porphyritic granite with Py dissemination	⊙	⊙	⊙																
44	MJBA-12	39.15	9°22'25"	57°29'07"	silicified, sheared porphyritic granite with Py dissemination	⊙	⊙	⊙													Δ			
45	MJBA-12	49.50	9°22'25"	57°29'07"	strongly silicified granite with Epi alteration	⊙	⊙	⊙																
46	MJBA-13	17.50	9°22'32"	57°29'07"	silicified, sheared porphyritic granite	⊙	⊙	⊙													Δ			
47	MJBA-13	21.00	9°22'32"	57°29'07"	sheared and brecciated granite	⊙	⊙	⊙																
48	MJBA-13	22.80	9°22'32"	57°29'07"	sheared granite with Py dissemination	⊙	⊙	⊙																
49	MJBA-13	30.00	9°22'32"	57°29'07"	silicified, sheared granite with epi alteration and Py dissemination	⊙	⊙	⊙														Δ		
50	MJBA-13	42.70	9°22'32"	57°29'07"	silicified, sheared granite with epi alteration and Py dissemination	⊙	⊙	⊙																

Appendix 13 List of ore assay for drilling survey

List of analytical results of drilling

Ser No	Sample No	Depth (m)	Length (m)	Au (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	Fe (%)	As (ppm)	Sb (ppm)	Hg (ppm)	Bi (ppm)	Cd (ppm)	Co (ppm)	Ni (ppm)	V (ppm)	Mn (ppm)	Mo (ppm)	K (%)	W (ppm)
1	MJBA01001	0.0	1.0	1310	3.5	14000	51	307	8.81	-1	-0.2	0.025	12.9	0.5	113	891	188	3588	-1	1.17	-20
2	MJBA01002	1.0	2.0	128	-0.2	2576	15	94	10	-1	-0.2	0.017	3.2	0.3	225	325	171	3520	-1	0.32	-20
3	MJBA01003	2.0	3.0	44	-0.2	1946	12	113	10	-1	-0.2	0.011	1.2	-0.2	118	298	168	2786	-1	0.63	-20
4	MJBA01004	3.0	4.0	24	-0.2	2235	12	116	10	-1	-0.2	-0.01	-0.2	0.3	119	296	161	2865	-1	0.5	-20
5	MJBA01005	4.0	5.0	29	0.3	2547	9	146	10	-1	-0.2	-0.01	0.3	0.4	105	330	180	2746	-1	0.78	-20
6	MJBA01006	5.0	6.0	31	0.2	2503	10	211	9.04	-1	-0.2	-0.01	0.2	0.3	85	417	137	2000	-1	1.13	-20
7	MJBA01007	6.0	7.0	24	0.3	3126	8	297	10	-1	-0.2	-0.01	0.3	0.4	96	664	160	2373	-1	0.71	-20
8	MJBA01008	7.0	8.0	27	0.4	1273	6	209	8.6	-1	-0.2	-0.01	-0.2	0.2	78	401	108	1942	-1	0.78	-20
9	MJBA01009	8.0	9.0	19	0.6	243	6	159	6.24	-1	-0.2	-0.01	-0.2	0.4	49	265	67	1220	-1	0.56	-20
10	MJBA01010	9.0	10.0	557	0.6	203	3	146	5.89	-1	-0.2	-0.01	0.4	0.3	48	236	82	1355	-1	0.71	-20
11	MJBA01011	10.0	11.0	27	0.8	185	3	92	5.23	-1	-0.2	-0.01	0.6	0.3	38	208	59	901	-1	0.71	-20
12	MJBA01012	11.0	12.0	20	0.7	440	-2	89	4.18	-1	-0.2	-0.01	0.6	0.2	32	144	59	704	-1	0.88	-20
13	MJBA01013	12.0	13.0	27	0.9	534	4	71	4.41	-1	-0.2	-0.01	0.4	0.3	33	132	81	760	-1	1.04	-20
14	MJBA01014	13.0	14.0	31	1.2	524	2	62	4.13	-1	-0.2	-0.01	1.2	0.4	32	129	58	744	-1	0.87	-20
15	MJBA01015	14.0	15.0	34	1.2	68	3	80	6.2	-1	-0.2	-0.01	-0.2	0.5	47	145	52	1222	-1	0.57	-20
16	MJBA01016	15.0	16.0	1759	1.7	1703	5	117	8.2	-1	-0.2	-0.01	0.8	0.6	88	175	90	2017	-1	0.21	-20
17	MJBA01017	16.0	17.0	38	1.2	1344	-2	124	7.18	-1	-0.2	-0.01	-0.2	0.5	55	239	54	1520	-1	0.09	-20
18	MJBA01018	17.0	18.0	88	1.3	1467	-2	117	5.03	-1	-0.2	-0.01	1.9	0.4	39	208	72	1071	-1	0.81	-20
19	MJBA01019	18.0	19.0	88	1.3	1109	-2	81	4.72	-1	-0.2	-0.01	0.6	0.4	36	147	60	985	-1	0.48	-20
20	MJBA01020	19.0	20.0	185	3	3886	7	202	8.21	-1	-0.2	-0.01	6.2	0.4	57	251	98	1883	-1	0.83	-20
21	MJBA01021	20.0	21.0	207	4	1836	6	103	9.27	-1	-0.2	-0.01	1.2	0.7	60	149	94	1975	-1	0.58	-20
22	MJBA01022	21.0	22.0	26	3.5	1836	5	222	8.88	-1	-0.2	-0.01	-0.2	0.6	90	402	77	2388	-1	1.12	-20
23	MJBA01023	22.0	23.0	25	3.4	2478	10	206	8.57	-1	-0.2	-0.01	-0.2	0.6	74	318	105	2241	-1	1.33	-20
24	MJBA01024	23.0	24.0	67	3	2615	5	140	8.18	-1	-0.2	-0.01	2.6	0.4	53	191	158	1749	-1	1.46	-20
25	MJBA01025	24.0	25.0	2253	6.1	5690	14	294	8.83	-1	-0.2	0.021	8.5	0.4	110	467	219	3864	-1	1.84	-20
26	MJBA01026	25.0	26.0	91	3.4	2945	8	137	4.93	-1	-0.2	0.039	6.1	0.3	40	230	124	1343	3	0.93	-20
27	MJBA01027	26.0	27.0	7674	2.1	488	9	124	2.62	-1	-0.2	0.017	4.6	0.3	29	271	58	1227	-1	0.47	-20
28	MJBA01028	27.0	28.0	37	1	250	3	294	8.24	-1	-0.2	-0.01	0.5	0.7	66	683	188	1626	-1	4.03	-20
29	MJBA01029	28.0	29.0	8	0.7	178	-2	294	8.84	-1	-0.2	-0.01	-0.2	0.3	69	646	199	1847	-1	5.49	-20
30	MJBA01030	29.0	30.0	23	0.6	708	-2	283	8.56	-1	-0.2	-0.01	0.6	0.3	67	672	185	1712	-1	5.45	-20
31	MJBA01031	30.0	31.0	5	0.2	131	-2	316	9.26	-1	-0.2	-0.01	-0.2	0.3	69	624	196	1990	-1	6.09	-20
32	MJBA01032	31.0	32.0	8	0.5	191	-2	268	7.98	-1	-0.2	-0.01	-0.2	0.4	65	732	170	1404	-1	4.5	-20
33	MJBA01033	32.0	33.0	6	22.9	316	6	244	9.18	-1	-0.2	-0.01	-0.2	6.3	68	742	167	14964	-1	3.42	-20
34	MJBA01034	33.0	34.0	5	1.7	144	7	285	8.15	-1	-0.2	-0.01	-0.2	1	64	741	183	2579	-1	4.77	-20
35	MJBA01035	34.0	35.0	21	5	379	-2	252	7.6	-1	-0.2	-0.01	0.2	0.7	59	601	186	1178	-1	3.72	-20
36	MJBA01036	35.0	36.0	7	1.3	1154	-2	255	6.37	-1	-0.2	-0.01	-0.2	0.4	58	768	152	841	-1	3	-20
37	MJBA01037	36.0	37.0	5	2.4	12000	8	402	8.78	-1	-0.2	-0.01	0.4	0.7	72	1015	206	1313	-1	3.64	-20
38	MJBA01038	37.0	38.0	5	12.1	41000	32	354	9.28	-1	-0.2	0.014	-0.2	0.4	91	1041	178	5138	-1	2.36	-20
39	MJBA01039	38.0	39.0	2030	51.4	8371	10	96	3.55	-1	-0.2	0.037	28.9	0.2	22	219	85	2378	-1	0.77	-20
40	MJBA01040	39.0	40.0	458	10.2	32000	30	247	7.31	1.2	-0.2	0.028	18.7	0.3	58	689	143	1325	-1	1.47	-20
41	MJBA01041	40.0	41.0	45	2.2	25000	12	245	7.76	-1	-0.2	-0.01	0.8	0.4	49	806	156	493	-1	2.15	-20
42	MJBA01042	41.0	42.0	49	14.3	14000	5	276	7.34	-1	0.3	0.012	1.6	0.4	76	893	152	3731	-1	2.74	-20
43	MJBA01043	42.0	43.0	17	2	3595	11	125	3.81	-1	-0.2	-0.01	-0.2	0.2	37	496	75	274	-1	0.9	-20
44	MJBA01044	43.0	44.0	66	2.1	2963	2	156	5.6	-1	-0.2	-0.01	-0.2	0.7	53	859	98	339	-1	1.4	-20
45	MJBA01045	44.0	45.0	8	1.9	1329	3	162	6.53	-1	-0.2	-0.01	-0.2	0.9	49	676	93	343	-1	2.01	-20
46	MJBA01046	45.0	46.0	43	2.5	230	4	116	6.04	-1	-0.2	-0.01	-0.2	1.3	57	707	99	532	-1	1.71	-20
47	MJBA01047	46.0	47.0	5	4.7	106	26	88	5.62	-1	-0.2	-0.01	-0.2	0.8	36	364	79	483	-1	0.3	-20
48	MJBA01048	47.0	48.0	5	3.4	67	7	87	4.47	-1	-0.2	-0.01	-0.2	0.4	31	305	78	979	-1	0.31	-20
49	MJBA01049	48.0	49.0	8	1.2	52	8	126	6.23	-1	-0.2	-0.01	-0.2	0.4	51	587	113	1445	-1	0.68	-20
50	MJBA01050	49.0	50.0	8	-0.2	24	-2	70	5.58	-1	-0.2	-0.01	-0.2	0.2	45	514	95	1381	-1	1.51	-20
51	MJBA01051	50.0	51.0	5	-0.2	69	-2	51	5.23	-1	-0.2	-0.01	-0.2	0.2	43	463	93	1352	2	2.22	-20
52	MJBA01052	51.0	52.0	5	-0.2	4	-2	46	4.85	-1	-0.2	-0.01	-0.2	0.2	40	443	78	825	-1	1.72	-20
53	MJBA01053	52.0	53.0	5	-0.2	6	-2	44	5.12	-1	-0.2	-0.01	-0.2	0.2	41	436	87	895	-1	1.78	-20
54	MJBA01054	53.0	54.0	5	-0.2	6	-2	45	5.04	-1	-0.2	-0.01	-0.2	0.2	42	464	85	870	-1	2.14	-20
55	MJBA01055	54.0	55.0	5	-0.2	32	2	40	4.96	-1	-0.2	-0.01	-0.2	0.2	37	434	82	1252	-1	0.74	-20
56	MJBA01056	55.0	56.0	5	-0.2	54	-2	45	4.92	-1	-0.2	-0.01	-0.2	0.2	37	428	92	1170	-1	1.27	-20
57	MJBA01057	56.0	57.0	6	-0.2	43	2	46	4.92	-1	-0.2	-0.01	-0.2	0.2	35	410	84	1308	-1	0.89	-20
58	MJBA01058	57.0	58.0	5	-0.2	26	4	56	5.02	-1	-0.2	-0.01	-0.2	0.2	38	446	86	1150	-1	0.97	-20
59	MJBA01059	58.0	59.0	5	-0.2	27	5	69	5.1	-1	-0.2	-0.01	-0.2	0.2	38	432	93	1182	-1	0.97	-20
60	MJBA01060	59.0	60.0	12	0.2	58	2	66	5.31	-1	-0.2	-0.01	-0.2	0.2	38	371	105	1352	-1	1.32	-20
61	MJBA01061	60.0	61.0	8	-0.2	95	-2	58	5.96	-1	-0.2	-0.01	-0.2	0.2	42	322	119	1271	-1	1.32	-20
62	MJBA01062	61.0	62.0	6	-0.2	103	2	46	5.94	-1	-0.2	-0.01	-0.2	0.2	42	283	114	1234	-1	1.33	-20
63	MJBA01063	62.0	63.0	5	-0.2	79	6	51	5.67	-1	-0.2	-0.01	-0.2	0.2	38	268	111	1043	-1	1.04	-20
64	MJBA01064	63.0	64.0	8	-0.2	3	4	46	4.4	-1	-0.2	-0.01	-0.2	0.2	36	407	89	1052	-1	1.1	-20
65	MJBA01065	64.0	65.0	5	-0.2	2	-2	43	4.65	-1	-0.2	-0.01	-0.2	0.2	38	458	85	873	-1	1.34	-20
66	MJBA01066	65.0	66.0	5	-0.2	3	3	48	4.91	-1	-0.2	-0.01	-0.2	0.2	38	453	88	967	-1	1.46	-20
67	MJBA01067	66.0	67.0	5	-0.2	1	-2	62	5.04	-1	-0.2	-0.01	-0.2	0.2	40	435	89	1105	-1	1.9	-20
68	MJBA01068	67.0	68.0	5	-0.2	74	-2														

List of analytical results of drilling

Ser No	Sample No	Depth (m) From To	Length (m)	Au (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	Fe (%)	As (ppm)	Sb (ppm)	Hg (ppm)	Bi (ppm)	Cd (ppm)	Co (ppm)	Ni (ppm)	V (ppm)	Mn (ppm)	Mo (ppm)	K (%)	W (ppm)
101	MJBA02001	0.0 1.0	1.0	98	-0.2	158	11	22	3.9	2	-0.2	0.025	1.8	-0.2	4	8	59	150	3	0.11	-20
102	MJBA02002	1.0 2.0	1.0	167	-0.2	242	18	27	6.74	3.6	-0.2	0.044	13.3	0.2	7	20	92	120	14	0.17	-20
103	MJBA02003	2.0 3.0	1.0	48	-0.2	138	17	19	6.81	1.2	-0.2	0.064	2.5	0.3	2	10	110	94	2	0.06	-20
104	MJBA02004	3.0 4.0	1.0	118	0.2	184	42	20	7.1	1.2	-0.2	0.054	5.8	0.3	5	11	113	340	3	0.08	-20
105	MJBA02005	4.0 5.0	1.0	38	-0.2	200	55	21	7.71	-1	-0.2	0.037	2	0.3	5	10	112	341	2	0.06	-20
106	MJBA02006	5.0 6.0	1.0	22	-0.2	123	43	13	3.11	1.5	-0.2	0.028	0.6	0.2	4	8	59	376	1	0.09	-20
107	MJBA02007	6.0 7.0	1.0	184	-0.2	278	118	21	5.15	-1	-0.2	0.017	8.1	0.3	14	29	82	1488	1	0.11	-20
108	MJBA02008	7.0 8.0	1.0	14	-0.2	577	83	37	8.44	-1	-0.2	0.013	0.3	0.3	28	57	118	3336	-1	0.19	-20
109	MJBA02009	8.0 9.0	1.0	15	-0.2	511	22	34	7.69	-1	-0.2	-0.01	0.2	0.3	37	63	106	3404	2	0.13	-20
110	MJBA02010	9.0 10.0	1.0	230	-0.2	743	11	31	7.74	-1	-0.2	0.012	7.2	0.4	35	43	103	2049	1	0.24	-20
111	MJBA02011	10.0 11.0	1.0	1506	-0.2	847	16	36	8.03	-1	-0.2	0.011	16.4	0.3	28	36	118	1431	5	0.09	-20
112	MJBA02012	11.0 12.0	1.0	52	-0.2	142	6	16	1.42	-1	-0.2	0.001	1.8	0.2	11	11	17	378	12	0.28	-20
113	MJBA02013	12.0 13.0	1.0	13	0.3	157	5	18	1.17	-1	-0.2	-0.001	0.9	0.3	10	9	9	233	12	0.17	-20
114	MJBA02014	13.0 14.0	1.0	20	-0.2	129	10	13	1.16	-1	-0.2	0.011	5.4	-0.2	13	7	13	534	16	0.16	-20
115	MJBA02015	14.0 15.0	1.0	21	-0.2	151	6	11	1.68	-1	-0.2	-0.01	1.8	0.3	9	8	13	319	15	0.12	-20
116	MJBA02016	15.0 16.0	1.0	9	-0.2	104	5	8	0.91	-1	-0.2	-0.01	0.3	-0.2	8	5	8	535	3	0.13	-20
117	MJBA02017	16.0 17.0	1.0	-5	-0.2	104	5	10	0.79	-1	-0.2	-0.01	-0.2	-0.2	6	5	7	487	1	0.13	-20
118	MJBA02018	17.0 18.0	1.0	11	-0.2	110	5	9	0.86	-1	-0.2	-0.01	-0.2	-0.2	5	2	7	353	7	0.06	-20
119	MJBA02019	18.0 19.0	1.0	12	-0.2	162	9	14	1.38	-1	-0.2	-0.01	1	-0.2	8	3	9	460	6	0.14	-20
120	MJBA02020	19.0 20.0	1.0	8	-0.2	132	5	18	0.82	-1	-0.2	-0.01	-0.2	0.3	7	5	8	349	-1	0.13	-20
121	MJBA02021	20.0 21.0	1.0	5	-0.2	126	3	19	0.67	-1	-0.2	-0.01	-0.2	0.2	5	5	6	418	-1	0.15	-20
122	MJBA02022	21.0 22.0	1.0	10	-0.2	110	3	20	0.77	-1	-0.2	-0.01	-0.2	-0.2	5	4	6	451	1	0.15	-20
123	MJBA02023	22.0 23.0	1.0	-5	2.3	118	4	24	0.76	-1	-0.2	0.011	-0.2	1.4	4	4	6	367	1	0.14	-20
124	MJBA02024	23.0 24.0	1.0	22	4.5	149	5	19	0.96	-1	-0.2	-0.01	0.4	2.6	6	6	7	387	1	0.14	-20
125	MJBA02025	24.0 25.0	1.0	81	4.6	144	6	16	1.38	-1	-0.2	-0.01	1.1	2.6	8	9	14	415	4	0.1	-20
126	MJBA02026	25.0 26.0	1.0	8	0.5	843	6	197	7.63	-1	-0.2	0.012	0.9	0.7	45	102	84	1818	3	0.21	-20
127	MJBA02027	26.0 27.0	1.0	9	-0.2	1054	5	270	8.92	-1	-0.2	-0.01	0.8	0.5	40	140	99	1562	-1	0.22	-20
128	MJBA02028	27.0 28.0	1.0	10	-0.2	1017	5	280	7.87	-1	-0.2	-0.01	0.2	0.4	38	163	98	1873	-1	0.17	-20
129	MJBA02029	28.0 29.0	1.0	5	-0.2	974	4	220	6.73	-1	-0.2	-0.01	-0.2	0.3	42	201	99	1248	-1	0.22	-20
130	MJBA02030	29.0 30.0	1.0	34	-0.2	1336	4	191	7.04	-1	-0.2	0.01	0.4	0.3	44	126	89	3715	5	0.14	-20
131	MJBA02031	30.0 31.0	1.0	625	-0.2	892	5	93	8.7	-1	-0.2	-0.01	31.4	0.2	33	50	47	738	12	0.14	-20
132	MJBA02032	31.0 32.0	1.0	28	-0.2	395	5	114	5.99	-1	-0.2	-0.01	-0.2	0.3	38	165	80	1335	-1	0.07	-20
133	MJBA02033	32.0 33.0	1.0	1174	1.4	1011	23	105	10	17	-0.2	-0.01	50	0.4	52	139	60	1266	51	0.09	-20
134	MJBA02034	33.0 34.0	1.0	12	0.2	833	5	100	5.73	-1	-0.2	-0.01	2.9	0.3	26	134	72	1492	-1	0.12	-20
135	MJBA02035	34.0 35.0	1.0	10	-0.2	821	6	251	7.34	-1	-0.2	-0.01	0.2	0.3	37	139	74	2653	-1	0.13	-20
136	MJBA02036	35.0 36.0	1.0	5	-0.2	94	3	120	4.33	-1	-0.2	-0.01	0.2	0.3	28	98	57	1084	-1	0.11	-20
137	MJBA02037	36.0 37.0	1.0	5	-0.2	100	3	99	2.93	-1	-0.2	-0.01	-0.2	0.2	24	79	53	897	-1	0.29	-20
138	MJBA02038	37.0 38.0	1.0	6	0.2	186	3	54	2.37	-1	-0.2	-0.01	0.6	-0.2	18	55	38	560	-1	0.16	-20
139	MJBA02039	38.0 39.0	1.0	14	-0.2	305	10	488	1.85	-1	-0.2	0.013	-0.2	2	10	26	24	671	-1	0.13	-20
140	MJBA02040	39.0 40.0	1.0	5	-0.2	15	7	17	0.72	-1	-0.2	-0.01	0.2	-0.2	2	2	7	301	-1	0.11	-20
141	MJBA02041	40.0 41.0	1.0	-5	-0.2	27	3	16	0.79	-1	-0.2	-0.01	-0.2	-0.2	2	3	7	313	1	0.16	-20
142	MJBA02042	41.0 42.0	1.0	-5	-0.2	36	4	21	0.69	-1	-0.2	-0.01	-0.2	-0.2	2	3	6	368	2	0.16	-20
143	MJBA02043	42.0 43.0	1.0	-5	-0.2	46	3	22	0.74	-1	-0.2	-0.01	-0.2	-0.2	2	3	5	325	2	0.15	-20
144	MJBA02044	43.0 44.0	1.0	7	-0.2	64	3	20	0.82	-1	-0.2	0.011	-0.2	-0.2	2	3	5	437	2	0.18	-20
145	MJBA02045	44.0 45.0	1.0	6	-0.2	9	4	16	0.78	-1	-0.2	-0.01	-0.2	-0.2	2	3	6	344	2	0.14	-20
146	MJBA02046	45.0 46.0	1.0	44	-0.2	429	5	19	2.36	-1	-0.2	-0.01	0.4	-0.2	26	4	5	303	2	0.19	-20
147	MJBA02047	46.0 47.0	1.0	5	-0.2	14	5	17	0.74	-1	-0.2	-0.01	-0.2	-0.2	2	3	6	301	2	0.15	-20
148	MJBA02048	47.0 48.0	1.0	-5	-0.2	9	6	16	0.67	-1	-0.2	-0.01	-0.2	-0.2	2	3	6	294	2	0.13	-20
149	MJBA02049	48.0 49.0	1.0	3	-0.2	38	2	24	0.97	-1	-0.2	-0.01	-0.2	-0.2	2	4	9	339	-1	0.18	-20
150	MJBA02050	49.0 50.0	1.0	-5	-0.2	9	4	17	0.73	-1	-0.2	-0.01	-0.2	-0.2	2	3	7	298	-1	0.15	-20
151	MJBA02051	50.0 51.0	1.0	-5	-0.2	6	3	67	2.21	-1	-0.2	-0.01	-0.2	-0.2	13	65	24	732	1	0.14	-20
152	MJBA02052	51.0 52.0	1.0	19	-0.2	15	4	101	3.41	-1	-0.2	-0.01	-0.2	-0.2	21	113	34	1114	-1	0.1	-20
153	MJBA02053	52.0 53.0	1.0	-5	-0.2	13	5	16	0.77	-1	-0.2	-0.01	-0.2	-0.2	2	3	7	252	2	0.13	-20
154	MJBA02054	53.0 54.0	1.0	-5	-0.2	8	6	19	0.91	-1	-0.2	-0.01	-0.2	-0.2	3	4	8	270	2	0.12	-20
155	MJBA02055	54.0 55.0	1.0	-5	-0.2	5	5	19	0.87	-1	-0.2	-0.01	-0.2	-0.2	3	3	10	238	1	0.13	-20
156	MJBA02056	55.0 56.0	1.0	-5	-0.2	6	4	19	0.84	-1	-0.2	-0.01	-0.2	-0.2	3	2	9	247	-1	0.13	-20
157	MJBA02057	56.0 57.0	1.0	-5	-0.2	5	7	19	0.84	1.1	-0.2	-0.01	-0.2	-0.2	2	3	9	268	-1	0.16	-20
158	MJBA02058	57.0 58.0	1.0	6	-0.2	3	5	18	0.8	-1	-0.2	-0.01	-0.2	-0.2	2	3	8	239	1	0.17	-20
159	MJBA02059	58.0 59.0	1.0	6	-0.2	3	4	20	0.6	-1	-0.2	-0.01	-0.2	-0.2	2	2	5	243	1	0.12	-20
160	MJBA02060	59.0 60.0	1.0	-5	-0.2	4	4	19	0.83	-1	-0.2	0.012	-0.2	-0.2	2	3	9	284	2	0.16	-20
161	MJBA02061	60.0 61.0	1.0	6	-0.2	6	4	18	0.69	-1	-0.2	-0.01	-0.2	-0.2	2	2	8	264	1	0.06	-20
162	MJBA02062	61.0 62.0	1.0	6	-0.2	36	5	20	0.69	-1	-0.2	-0.01	-0.2	-0.2	2	3	7	316	1	0.17	-20
163	MJBA02063	62.0 63.0	1.0	8	-0.2	105	2	22	0.46	-1	-0.2	-0.01	-0.2	-0.2	1	4	3	392	-1	0.13	-20
164	MJBA02064	63.0 64.0	1.0	43	0.4	1651	4	133	2.72	-1	-0.2	-0.01	5.2	-0.2	11	52	15	1257	62	0.19	-20
165	MJBA02065	64.0 65.0	1.0	-5	-0.2	9	3	18	0.62	-1	-0.2	0.011	-0.2	-0.2	1	5	5	390	2	0.23	-20
166	MJBA02066	65.0 66.0	1.0	-5	-0.2	34	3	20	0.77	-1	-0.2	0.013	-0.2	-0.2	2	4	8	303	1	0.17	-20
167	MJBA02067	66.0 67.0	1.0	-5	-0.2	26	3	25	0.78	1.1	-0.2	-0.01	-0.2	-0.2	2	4	5	342	2	0.21	

List of analytical results of drilling

Ser. No.	Sample No.	Depth (m)		Length (m)	Au	Ag	Cu	Pb	Zn	Fe	As	Sb	Hg	Bi	Cd	Co	Ni	V	Mn	Mo	K	W
		From	To		(ppb)	(ppm)	(ppm)	(ppm)	(ppm)	(%)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(%)
201	MJBA03001	0.0	1.0	1.0	525	-0.2	9	21	21	193	1.5	-0.2	0.131	1.4	-0.2	3	7	38	484	1	0.07	-20
202	MJBA03002	1.0	2.0	1.0	17	-0.2	14	20	27	257	1.9	-0.2	0.121	0.9	-0.2	3	8	48	327	2	0.07	-20
203	MJBA03003	2.0	3.0	1.0	26	-0.2	25	18	31	302	1.7	0.2	0.082	0.5	-0.2	3	8	51	109	1	0.07	-20
204	MJBA03004	3.0	4.0	1.0	6	-0.2	15	20	22	285	1.6	-0.2	0.046	0.3	-0.2	3	7	49	97	2	0.07	-20
205	MJBA03005	4.0	5.0	1.0	7	-0.2	14	17	22	259	1.3	-0.2	0.018	0.4	-0.2	2	6	43	76	-1	0.08	-20
206	MJBA03006	5.0	6.0	1.0	11	0.2	13	31	18	268	1.7	0.3	0.014	0.6	-0.2	2	8	46	119	2	0.11	-20
207	MJBA03007	6.0	7.0	1.0	241	0.2	16	54	30	234	2	-0.2	-0.01	0.6	-0.2	5	8	40	633	-1	0.24	-20
208	MJBA03008	7.0	8.0	1.0	6	-0.2	12	41	49	243	-1	-0.2	-0.01	0.2	-0.2	8	8	44	687	2	0.36	-20
209	MJBA03009	8.0	9.0	1.0	17	-0.2	18	30	56	2.2	1	-0.2	-0.01	0.2	-0.2	8	10	36	738	1	0.4	-20
210	MJBA03010	9.0	10.0	1.0	49	-0.2	15	29	74	2.55	-1	-0.2	-0.01	-0.2	-0.2	12	12	41	1035	3	0.63	-20
211	MJBA03011	10.0	11.0	1.0	8	-0.2	18	21	91	2.26	-1	-0.2	-0.01	0.5	-0.2	12	10	35	824	-1	0.56	-20
212	MJBA03012	11.0	12.0	1.0	-5	-0.2	28	35	82	2.18	-1	-0.2	-0.01	0.4	-0.2	16	11	34	1497	2	0.67	-20
213	MJBA03013	12.0	13.0	1.0	69	-0.2	20	26	75	2.17	-1	-0.2	-0.01	0.4	-0.2	9	10	30	701	-1	0.74	-20
214	MJBA03014	13.0	14.0	1.0	-5	-0.2	19	33	68	1.96	1	-0.2	-0.01	0.3	-0.2	10	11	25	975	2	0.72	-20
215	MJBA03015	14.0	15.0	1.0	15	-0.2	18	25	59	1.8	1	-0.2	-0.01	0.2	-0.2	8	8	24	798	1	0.65	-20
216	MJBA03016	15.0	16.0	1.0	19	-0.2	23	24	69	1.99	-1	-0.2	-0.01	0.3	-0.2	9	10	29	622	2	0.74	-20
217	MJBA03017	16.0	17.0	1.0	46	-0.2	34	27	49	1.75	1.8	-0.2	-0.01	0.4	-0.2	9	8	25	1027	-1	0.58	-20
218	MJBA03018	17.0	18.0	1.0	35	-0.2	52	21	74	2.2	-1	-0.2	-0.01	0.2	-0.2	11	10	34	826	2	0.73	-20
219	MJBA03019	18.0	19.0	1.0	101	-0.2	58	23	64	1.97	1.4	-0.2	-0.01	0.4	-0.2	11	9	26	1069	-1	0.7	-20
220	MJBA03020	19.0	20.0	1.0	61	-0.2	45	26	77	2.32	1.1	-0.2	-0.01	0.4	-0.2	13	11	34	1003	2	0.8	-20
221	MJBA03021	20.0	21.0	1.0	13	-0.2	39	25	67	2.04	1.1	-0.2	-0.01	0.3	-0.2	10	10	29	722	-1	0.7	-20
222	MJBA03022	21.0	22.0	1.0	22	-0.2	33	25	66	1.94	1.7	-0.2	-0.01	0.3	-0.2	10	10	28	1080	2	0.66	-20
223	MJBA03023	22.0	23.0	1.0	67	-0.2	46	25	59	1.67	1.6	-0.2	-0.01	0.2	-0.2	9	8	22	712	-1	0.62	-20
224	MJBA03024	23.0	24.0	1.0	12	-0.2	36	22	66	1.79	1.9	-0.2	-0.01	0.4	-0.2	9	9	24	414	2	0.64	-20
225	MJBA03025	24.0	25.0	1.0	18	-0.2	39	23	66	1.76	2.7	0.2	0.01	0.4	-0.2	10	6	26	781	-1	0.65	-20
226	MJBA03026	25.0	26.0	1.0	146	-0.2	29	22	33	0.84	1.7	-0.2	-0.01	-0.2	-0.2	4	3	12	220	-1	0.3	-20
227	MJBA03027	26.0	27.0	1.0	22	-0.2	26	61	18	0.37	1.4	-0.2	-0.01	-0.2	-0.2	3	1	5	182	-1	0.15	-20
228	MJBA03028	27.0	28.0	1.0	387	-0.2	94	22	60	1.57	2.3	-0.2	-0.01	0.3	-0.2	8	5	23	415	-1	0.59	-20
229	MJBA03029	28.0	29.0	1.0	8	-0.2	64	19	70	1.91	2.2	-0.2	-0.01	0.5	-0.2	10	5	30	488	-1	0.66	-20
230	MJBA03030	29.0	30.0	1.0	341	-0.2	42	20	65	1.47	4	-0.2	-0.01	0.4	-0.2	11	6	19	909	-1	0.64	-20
231	MJBA03031	30.0	31.0	1.0	14	-0.2	79	16	62	1.64	2.9	-0.2	-0.01	0.2	-0.2	8	5	23	387	-1	0.67	-20
232	MJBA03032	31.0	32.0	1.0	26	-0.2	35	20	73	1.54	3.5	-0.2	-0.01	0.3	-0.2	7	6	21	407	-1	0.73	-20
233	MJBA03033	32.0	33.0	1.0	90	-0.2	30	57	76	1.68	5.5	-0.2	-0.01	0.6	-0.2	10	8	22	463	1	0.7	-20
234	MJBA03034	33.0	34.0	1.0	24	-0.2	25	20	87	1.8	3.7	-0.2	-0.01	0.3	-0.2	12	9	20	449	2	0.7	-20
235	MJBA03035	34.0	35.0	1.0	547	-0.2	22	23	97	1.79	7.9	-0.2	-0.01	0.6	-0.2	8	8	19	365	-1	0.62	-20
236	MJBA03036	35.0	36.0	1.0	47	-0.2	27	16	100	1.25	5.3	-0.2	-0.01	0.4	-0.2	9	7	11	404	2	0.46	-20
237	MJBA03037	36.0	37.0	1.0	19	-0.2	29	124	92	1.22	9.2	0.3	0.012	0.7	0.3	10	6	8	1975	1	0.38	-20
238	MJBA03038	37.0	38.0	1.0	46	-0.2	16	118	36	0.6	11.5	-0.2	-0.01	0.9	-0.2	7	5	3	719	2	0.2	-20
239	MJBA03039	38.0	39.0	1.0	29	-0.2	28	70	171	1.49	11	0.3	-0.01	0.6	0.5	6	6	9	550	-1	0.36	-20
240	MJBA03040	39.0	40.0	1.0	78	1.2	29	185	136	1.17	12.6	0.4	-0.01	0.7	0.9	8	7	10	2475	2	0.45	-20
241	MJBA03041	40.0	41.0	1.0	20	0.3	18	65	105	0.78	6.9	0.3	-0.01	0.6	0.4	5	6	7	1067	-1	0.42	-20
242	MJBA03042	41.0	42.0	1.0	67	1.3	32	173	180	1.14	13	0.3	-0.01	1.1	0.9	7	7	9	2164	2	0.41	-20
243	MJBA03043	42.0	43.0	1.0	26	1.5	78	544	295	1.74	5.3	0.2	-0.01	9	1.4	12	8	19	2379	1	0.57	-20
244	MJBA03044	43.0	44.0	1.0	12	0.6	72	215	168	1.58	2.5	0.3	-0.01	8.1	0.5	8	8	26	464	1	0.71	-20
245	MJBA03045	44.0	45.0	1.0	9	-0.2	72	236	146	1.59	3	0.3	-0.01	3.2	0.4	6	7	23	380	-1	0.62	-20
246	MJBA03046	45.0	46.0	1.0	8	-0.2	55	111	199	1.76	3.3	0.4	-0.01	2.8	2.2	9	8	28	486	2	0.77	-20
247	MJBA03047	46.0	47.0	1.0	-5	-0.2	32	29	100	1.85	2.9	0.3	-0.01	1	0.2	11	7	27	607	2	0.82	-20
248	MJBA03048	47.0	48.0	1.0	-5	-0.2	29	16	63	1.71	2.5	0.2	-0.01	0.8	-0.2	10	7	31	500	3	0.81	-20
249	MJBA03049	48.0	49.0	1.0	-5	-0.2	27	12	50	1.69	2	0.2	-0.01	0.7	-0.2	10	7	30	451	3	0.79	-20
250	MJBA03050	49.0	50.0	1.0	-5	-0.2	13	15	33	1.2	2.9	-0.2	-0.01	0.6	-0.2	6	6	18	371	1	0.53	-20
251	MJBA04001	0.0	1.0	1.0	531	0.3	34	158	48	2.78	13.2	0.3	3.53	1	-0.2	3	7	48	130	2	0.11	-20
252	MJBA04002	1.0	2.0	1.0	31	-0.2	12	20	38	2.92	2.2	-0.2	0.255	0.7	0.3	3	6	58	141	1	0.08	-20
253	MJBA04003	2.0	3.0	1.0	15	-0.2	9	17	26	3.22	2.4	-0.2	0.102	0.7	-0.2	2	5	66	75	2	0.06	-20
254	MJBA04004	3.0	4.0	1.0	15	-0.2	8	12	17	2.52	1.9	-0.2	0.084	0.4	-0.2	2	6	47	35	1	0.05	-20
255	MJBA04005	4.0	5.0	1.0	8	-0.2	7	9	10	1.66	1.8	-0.2	0.048	0.9	-0.2	1	8	27	19	2	0.05	-20
256	MJBA04006	5.0	6.0	1.0	61	-0.2	6	7	12	1.67	2.9	-0.2	0.027	0.7	-0.2	-1	5	20	30	-1	0.14	-20
257	MJBA04007	6.0	7.0	1.0	14	-0.2	7	9	8	1.55	1.7	-0.2	0.029	0.6	-0.2	1	6	21	18	3	0.06	-20
258	MJBA04008	7.0	8.0	1.0	6	-0.2	6	7	16	1.12	1.5	-0.2	0.014	0.4	-0.2	2	6	15	51	-1	0.22	-20
259	MJBA04009	8.0	9.0	1.0	-5	-0.2	8	13	38	1.2	1.4	-0.2	-0.01	-0.2	-0.2	4	9	15	143	2	0.42	-20
260	MJBA04010	9.0	10.0	1.0	-5	-0.2	9	41	66	1.6	1.9	0.2	-0.01	-0.2	-0.2	8	8	17	543	1	0.53	-20
261	MJBA04011	10.0	11.0	1.0	-5	-0.2	10	31	60	1.62	1.8	-0.2	-0.01	0.3	-0.2	8	9	20	552	3	0.58	-20
262	MJBA04012	11.0	12.0	1.0	-5	-0.2	12	19	54	2.07	2	-0.2	-0.01	0.9	-0.2	10	8	28	587	-1	0.63	-20
263	MJBA04013	12.0	13.0	1.0	-5	-0.2	13	21	58	2.13	1.9	-0.2	-0.01	0.6	-0.2	9	5	29	505	-1	0.63	-20
264	MJBA04014	13.0	14.0	1.0	-5	-0.2	17	24	54	2.07	2.3	-0.2	-0.01	0.9	-0.2	9	5	32	718	-1	0.57	-20
265	MJBA04015	14.0	15.0	1.0	6	-0.2	16	18	50	2.11	2.3	-0.2										

List of analytical results of drilling

Ser No.	Sample No.	Depth (m)		Length (m)	Au	Ag	Cu	Pb	Zn	Fe	As	Sb	Hg	Bi	Cd	Co	Ni	V	Mn	Mo	K	W
		From	To		(ppb)	(ppm)	(ppm)	(ppm)	(ppm)	(%)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(%)
301	MJBA05001	0.0	1.0	1.0	292	-0.2	32	92	40	3.73	3.8	-0.2	0.106	1	-0.2	3	5	72	583	3	0.15	-20
302	MJBA05002	1.0	2.0	1.0	670	-0.2	28	31	34	4.31	2.4	-0.2	0.113	0.6	-0.2	3	3	84	203	3	0.09	-20
303	MJBA05003	2.0	3.0	1.0	57	-0.2	17	15	23	3.62	2	-0.2	0.067	0.4	-0.2	2	2	77	50	1	0.03	-20
304	MJBA05004	3.0	4.0	1.0	59	-0.2	21	17	25	3.45	2	-0.2	0.077	0.4	-0.2	2	2	71	73	2	0.06	-20
305	MJBA05005	4.0	5.0	1.0	34	-0.2	12	30	17	2.82	1.8	-0.2	0.026	0.3	-0.2	1	2	54	153	2	0.05	-20
306	MJBA05006	5.0	6.0	1.0	24	-0.2	11	15	16	2.81	1.4	-0.2	0.01	0.2	-0.2	-1	1	50	48	2	0.07	-20
307	MJBA05007	6.0	7.0	1.0	22	-0.2	16	40	29	2.62	1.5	-0.2	-0.01	3.4	-0.2	1	4	49	209	1	0.13	-20
308	MJBA05008	7.0	8.0	1.0	-5	-0.2	30	54	66	2.47	1.2	-0.2	-0.01	0.2	-0.2	2	10	45	357	1	0.45	-20
309	MJBA05009	8.0	9.0	1.0	-5	-0.2	23	55	53	2.79	1.2	-0.2	-0.01	-0.2	-0.2	4	9	54	846	2	0.31	-20
310	MJBA05010	9.0	10.0	1.0	-5	-0.2	14	39	41	2.49	-1	-0.2	-0.01	0.3	-0.2	8	9	49	724	2	0.28	-20
311	MJBA05011	10.0	11.0	1.0	-5	-0.2	29	32	120	2.89	-1	-0.2	-0.01	-0.2	-0.2	8	15	52	493	1	0.55	-20
312	MJBA05012	11.0	12.0	1.0	-5	-0.2	15	18	63	2.5	2	-0.2	-0.01	-0.2	-0.2	10	16	51	1162	3	0.5	-20
313	MJBA05013	12.0	13.0	1.0	-5	-0.2	17	25	55	2.16	2.7	-0.2	-0.01	-0.2	-0.2	9	11	45	1062	2	0.41	-20
314	MJBA05014	13.0	14.0	1.0	26	-0.2	13	33	24	1.86	3.1	-0.2	-0.01	-0.2	-0.2	9	8	42	721	2	0.09	-20
315	MJBA05015	14.0	15.0	1.0	-5	-0.2	14	27	51	2.31	1.6	-0.2	-0.01	-0.2	-0.2	8	9	44	762	2	0.38	-20
316	MJBA05016	15.0	16.0	1.0	-5	-0.2	9	20	60	1.87	-1	-0.2	-0.01	-0.2	-0.2	10	10	35	576	2	0.56	-20
317	MJBA05017	16.0	17.0	1.0	-5	-0.2	14	19	63	2.21	-1	-0.2	-0.01	-0.2	-0.2	8	11	40	687	1	0.64	-20
318	MJBA05018	17.0	18.0	1.0	-5	-0.2	11	19	62	1.98	-1	-0.2	-0.01	-0.2	-0.2	13	11	39	704	2	0.62	-20
319	MJBA05019	18.0	19.0	1.0	-5	-0.2	9	17	66	2.26	-1	-0.2	-0.01	-0.2	-0.2	8	12	43	840	1	0.69	-20
320	MJBA05020	19.0	20.0	1.0	61	-0.2	13	29	69	1.84	1.1	-0.2	-0.01	-0.2	-0.2	12	11	31	597	1	0.54	-20
321	MJBA05021	20.0	21.0	1.0	42	-0.2	12	26	72	1.8	1.1	-0.2	-0.01	-0.2	-0.2	8	13	33	780	1	0.37	-20
322	MJBA05022	21.0	22.0	1.0	-5	-0.2	5	7	51	1.83	-1	-0.2	-0.01	-0.2	-0.2	8	10	40	582	-1	0.61	-20
323	MJBA05023	22.0	23.0	1.0	-5	-0.2	5	6	47	1.92	-1	-0.2	-0.01	-0.2	-0.2	8	11	43	533	1	0.66	-20
324	MJBA05024	23.0	24.0	1.0	-5	-0.2	5	9	47	1.94	-1	-0.2	-0.01	-0.2	-0.2	9	10	41	502	1	0.67	-20
325	MJBA05025	24.0	25.0	1.0	-5	-0.2	4	10	45	2.06	-1	-0.2	-0.01	-0.2	-0.2	8	11	43	524	1	0.68	-20
326	MJBA05026	25.0	26.0	1.0	-5	-0.2	3	8	43	1.98	-1	-0.2	-0.01	-0.2	-0.2	10	11	41	510	2	0.7	-20
327	MJBA05027	26.0	27.0	1.0	-5	-0.2	4	7	43	1.92	-1	-0.2	-0.01	-0.2	-0.2	10	10	39	473	1	0.68	-20
328	MJBA05028	27.0	28.0	1.0	-5	-0.2	3	8	41	1.88	-1	-0.2	-0.01	-0.2	-0.2	10	10	39	466	2	0.67	-20
329	MJBA05029	28.0	29.0	1.0	-5	-0.2	4	8	43	1.96	-1	-0.2	-0.01	-0.2	-0.2	8	11	41	513	2	0.69	-20
330	MJBA05030	29.0	30.0	1.0	-5	-0.2	15	10	42	1.7	-1	-0.2	-0.01	-0.2	-0.2	11	9	35	430	2	0.63	-20
331	MJBA05031	30.0	31.0	1.0	-5	-0.2	2	17	6	0.46	-1	-0.2	-0.01	-0.2	-0.2	12	1	2	140	2	0.1	-20
332	MJBA05032	31.0	32.0	1.0	-5	-0.2	2	14	10	0.56	-1	-0.2	-0.01	-0.2	-0.2	11	3	8	144	3	0.17	-20
333	MJBA05033	32.0	33.0	1.0	-5	-0.2	6	9	47	2.26	-1	-0.2	-0.01	-0.2	-0.2	12	11	38	524	2	0.72	-20
334	MJBA05034	33.0	34.0	1.0	-5	-0.2	5	8	36	1.49	-1	-0.2	-0.01	-0.2	-0.2	11	8	30	375	2	0.57	-20
335	MJBA05035	34.0	35.0	1.0	-5	-0.2	4	8	44	1.7	-1	-0.2	-0.01	-0.2	-0.2	11	10	32	429	-1	0.57	-20
336	MJBA05036	35.0	36.0	1.0	-5	-0.2	6	6	50	1.91	-1	-0.2	-0.01	-0.2	-0.2	10	11	39	499	2	0.73	-20
337	MJBA05037	36.0	37.0	1.0	-5	-0.2	19	9	51	2.03	-1	-0.2	-0.01	0.2	-0.2	11	12	41	531	2	0.76	-20
338	MJBA05038	37.0	38.0	1.0	7	-0.2	53	17	55	2.27	-1	-0.2	-0.01	0.9	-0.2	11	14	40	559	2	0.74	-20
339	MJBA05039	38.0	39.0	1.0	75	5.8	3075	23	143	4.44	-1	-0.2	-0.01	2.7	3.2	10	30	65	823	1	0.75	-20
340	MJBA05040	39.0	40.0	1.0	73	-0.2	28	8	269	1.93	-1	-0.2	-0.01	-0.2	2.1	7	11	38	596	2	0.8	-20
341	MJBA05041	40.0	41.0	1.0	192	0.4	24	10	61	1.73	-1	-0.2	-0.01	-0.2	-0.2	5	10	29	562	1	0.72	-20
342	MJBA05042	41.0	42.0	1.0	-5	-0.2	6	11	52	2.06	-1	-0.2	-0.01	-0.2	-0.2	8	11	40	541	2	0.75	-20
343	MJBA05043	42.0	43.0	1.0	-5	-0.2	6	7	49	2.22	-1	-0.2	-0.01	-0.2	-0.2	11	10	40	509	3	0.72	-20
344	MJBA05044	43.0	44.0	1.0	-5	-0.2	5	5	51	1.98	-1	-0.2	-0.01	-0.2	-0.2	10	10	39	521	2	0.7	-20
345	MJBA05045	44.0	45.0	1.0	-5	-0.2	12	8	48	1.87	-1	-0.2	-0.01	-0.2	-0.2	10	10	37	481	2	0.74	-20
346	MJBA05046	45.0	46.0	1.0	23	-0.2	13	7	60	2.07	-1	-0.2	-0.01	0.3	-0.2	11	12	40	584	2	0.83	-20
347	MJBA05047	46.0	47.0	1.0	-5	-0.2	11	11	45	1.76	-1	-0.2	-0.01	-0.2	-0.2	10	10	34	447	2	0.49	-20
348	MJBA05048	47.0	48.0	1.0	-5	-0.2	9	10	40	1.58	-1	-0.2	-0.01	-0.2	-0.2	10	8	30	388	2	0.45	-20
349	MJBA05049	48.0	49.0	1.0	-5	-0.2	15	12	39	1.43	-1	-0.2	-0.01	-0.2	-0.2	11	7	27	358	3	0.47	-20
350	MJBA05050	49.0	50.0	1.0	-5	-0.2	29	26	64	2	-1	-0.2	-0.01	0.5	-0.2	11	11	39	516	4	0.73	-20
351	MJBA08001	0.0	1.0	1.0	22	-0.2	28	26	28	2.27	-1	-0.2	0.088	0.2	-0.2	6	10	44	1029	3	0.03	-20
352	MJBA08002	1.0	2.0	1.0	19	-0.2	18	20	27	2.96	-1	-0.2	0.16	0.3	-0.2	5	7	59	506	2	0.04	-20
353	MJBA08003	2.0	3.0	1.0	232	-0.2	65	19	26	3.5	1.1	-0.2	0.066	0.4	-0.2	5	15	66	207	4	0.05	-20
354	MJBA08004	3.0	4.0	1.0	13	-0.2	148	18	31	4.05	-1	-0.2	0.08	0.7	-0.2	5	18	80	164	2	0.06	-20
355	MJBA08005	4.0	5.0	1.0	16	-0.2	23	15	20	3.99	-1	-0.2	0.059	0.7	-0.2	3	9	78	94	3	0.03	-20
356	MJBA08006	5.0	6.0	1.0	-5	-0.2	29	32	20	4.37	-1	-0.2	0.015	1.3	-0.2	4	11	80	117	2	0.04	-20
357	MJBA08007	6.0	7.0	1.0	-5	-0.2	14	38	16	3.52	-1	-0.2	-0.01	0.4	-0.2	8	8	73	417	2	0.05	-20
358	MJBA08008	7.0	8.0	1.0	-5	-0.2	15	49	30	4.06	-1	-0.2	-0.01	0.7	-0.2	13	9	85	785	2	0.11	-20
359	MJBA08009	8.0	9.0	1.0	-5	-0.2	13	27	30	3.72	-1	-0.2	-0.01	0.5	-0.2	30	8	79	1318	2	0.18	-20
360	MJBA08010	9.0	10.0	1.0	-5	-0.2	10	10	21	1.7	-1	-0.2	-0.01	-0.2	-0.2	6	6	35	275	1	0.14	-20
361	MJBA08011	10.0	11.0	1.0	6	-0.2	14	21	45	2.27	-1	-0.2	-0.01	-0.2	-0.2	10	11	44	653	2	0.47	-20
362	MJBA08012	11.0	12.0	1.0	-5	-0.2	22	23	61	2.99	-1	-0.2	-0.01	-0.2	-0.2	16	12	56	1165	2	0.72	-20
363	MJBA08013	12.0	13.0	1.0	-5	-0.2	32	18	85	2.82	-1	-0.2	-0.01	0.3	-0.2	16	10	54	927	2	0.82	-20
364	MJBA08014	13.0	14.0	1.0	-5	-0.2	10	7	84	2.6	-1	-0.2	-0.01	-0.2	-0.2	28	9	41	745	16	0.97	-20
365	MJBA08015	14.0	15.0	1.0	-5	-0.2	10	8	67	2.38	-1	-0.2	-0.01	-0.2	-0.2	14	8	46	638	3	0.89	-20
366	MJ																					

List of analytical results of drilling

Ser No	Sample No	Depth (m)		Length (m)	Au	Ag	Cu	Pb	Zn	Fe	As	Sb	Hg	Bi	Cd	Co	Ni	V	Mn	Mo	K	W
		From	To		(ppb)	(ppm)	(ppm)	(ppm)	(ppm)	(%)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(ppm)	(%)
401	MJBA07001	0.0	1.0	1.0	39	-0.2	45	29	16	3.22	2.1	0.3	0.107	1.7	-0.2	2	6	65	188	25	0.04	-20
402	MJBA07002	1.0	2.0	1.0	49	-0.2	71	34	22	7	6.8	1.3	0.189	3	-0.2	2	6	143	183	64	0.03	-20
403	MJBA07003	2.0	3.0	1.0	36	-0.2	66	27	19	4.38	2.1	0.6	0.116	1.8	-0.2	3	9	82	409	37	0.03	-20
404	MJBA07004	3.0	4.0	1.0	29	-0.2	71	21	22	3.65	2.2	0.4	0.093	1.9	-0.2	2	8	68	75	27	0.03	-20
405	MJBA07005	4.0	5.0	1.0	30	-0.2	59	23	16	2.98	1.3	0.3	0.072	1.7	-0.2	2	9	53	44	22	0.02	-20
406	MJBA07006	5.0	6.0	1.0	31	-0.2	55	25	13	2.73	1.1	0.3	0.055	1.9	-0.2	2	8	48	42	20	0.03	-20
407	MJBA07007	6.0	7.0	1.0	45	-0.2	52	35	13	2.67	1	0.3	0.024	1.3	-0.2	2	10	44	73	21	0.02	-20
408	MJBA07008	7.0	8.0	1.0	33	-0.2	41	22	9	2.1	-1	0.2	0.011	2.1	-0.2	1	7	33	42	14	0.02	-20
409	MJBA07009	8.0	9.0	1.0	15	-0.2	62	38	12	2.6	-1	0.3	-0.01	2.4	-0.2	6	9	41	364	19	0.01	-20
410	MJBA07010	9.0	10.0	1.0	6	-0.2	68	21	13	1.97	-1	-0.2	-0.01	1.8	-0.2	10	8	31	754	9	0.03	-20
411	MJBA07011	10.0	11.0	1.0	10	-0.2	63	22	14	2.09	-1	-0.2	-0.01	3.3	-0.2	10	7	35	767	10	0.03	-20
412	MJBA07012	11.0	12.0	1.0	8	-0.2	71	24	15	1.96	-1	-0.2	-0.01	4.6	-0.2	6	4	33	306	26	0.04	-20
413	MJBA07013	12.0	13.0	1.0	17	-0.2	94	49	20	2.48	-1	0.2	-0.01	4.3	-0.2	15	8	38	855	13	0.04	-20
414	MJBA07014	13.0	14.0	1.0	49	-0.2	89	74	25	2.18	-1	0.2	-0.01	6.8	-0.2	9	6	35	608	10	0.06	-20
415	MJBA07015	14.0	15.0	1.0	18	-0.2	76	19	33	1.93	-1	-0.2	-0.01	0.8	-0.2	9	8	32	731	9	0.18	-20
416	MJBA07016	15.0	16.0	1.0	153	-0.2	93	41	48	1.79	-1	-0.2	-0.01	1.1	-0.2	8	7	28	793	6	0.33	-20
417	MJBA07017	16.0	17.0	1.0	18	-0.2	97	64	29	1.67	-1	0.2	-0.01	9.8	-0.2	9	9	25	983	8	0.13	-20
418	MJBA07018	17.0	18.0	1.0	-5	-0.2	28	23	10	0.52	-1	-0.2	-0.01	0.4	-0.2	2	5	5	110	2	0.05	-20
419	MJBA07019	18.0	19.0	1.0	-5	-0.2	23	17	9	0.53	-1	-0.2	-0.01	0.5	-0.2	2	7	6	98	3	0.05	-20
420	MJBA07020	19.0	20.0	1.0	5	-0.2	19	21	9	0.43	-1	-0.2	-0.01	0.3	-0.2	2	5	4	179	1	0.05	-20
421	MJBA07021	20.0	21.0	1.0	8	-0.2	41	24	34	1.07	-1	0.4	-0.01	0.7	-0.2	4	8	14	325	3	0.19	-20
422	MJBA07022	21.0	22.0	1.0	8	-0.2	53	16	55	1.44	-1	-0.2	-0.01	0.6	-0.2	6	8	25	401	3	0.41	-20
423	MJBA07023	22.0	23.0	1.0	-5	-0.2	68	17	49	1.47	-1	-0.2	-0.01	1.1	-0.2	6	9	22	750	5	0.33	-20
424	MJBA07024	23.0	24.0	1.0	10	-0.2	115	38	51	1.53	-1	-0.2	-0.01	2.3	-0.2	7	7	18	739	4	0.22	-20
425	MJBA07025	24.0	25.0	1.0	-5	-0.2	115	24	54	1.4	-1	-0.2	-0.01	4.9	-0.2	7	10	15	328	9	0.35	-20
426	MJBA07026	25.0	26.0	1.0	-5	-0.2	76	13	58	1.44	-1	-0.2	-0.01	0.2	-0.2	6	9	20	387	5	0.49	-20
427	MJBA07027	26.0	27.0	1.0	-5	-0.2	60	14	52	1.34	-1	-0.2	-0.01	-0.2	-0.2	6	9	21	362	2	0.46	-20
428	MJBA07028	27.0	28.0	1.0	-5	-0.2	26	12	55	1.78	-1	-0.2	-0.01	-0.2	-0.2	8	11	29	474	3	0.62	-20
429	MJBA07029	28.0	29.0	1.0	-5	-0.2	15	14	47	1.44	-1	-0.2	-0.01	-0.2	-0.2	5	10	18	371	4	0.4	-20
430	MJBA07030	29.0	30.0	1.0	19	-0.2	37	25	51	1.2	-1	-0.2	-0.01	0.8	-0.2	6	8	15	308	2	0.32	-20
431	MJBA07031	30.0	31.0	1.0	-5	-0.2	37	16	55	1.32	-1	-0.2	-0.01	0.4	-0.2	7	9	19	368	2	0.43	-20
432	MJBA07032	31.0	32.0	1.0	-5	-0.2	44	17	52	1.37	-1	-0.2	-0.01	0.3	-0.2	7	8	19	446	3	0.46	37
433	MJBA07033	32.0	33.0	1.0	-5	-0.2	41	14	48	1.31	-1	-0.2	-0.01	0.3	-0.2	7	10	17	383	3	0.43	-20
434	MJBA07034	33.0	34.0	1.0	-5	-0.2	41	17	48	1.33	-1	-0.2	-0.01	0.6	-0.2	7	8	18	393	2	0.44	-20
435	MJBA07035	34.0	35.0	1.0	-5	-0.2	45	15	46	1.31	-1	-0.2	-0.01	0.3	-0.2	8	8	18	397	3	0.42	-20
436	MJBA07036	35.0	36.0	1.0	-5	-0.2	52	16	49	1.4	-1	-0.2	-0.01	0.8	-0.2	8	9	17	391	5	0.42	-20
437	MJBA07037	36.0	37.0	1.0	8	-0.2	71	18	48	1.26	-1	-0.2	-0.01	0.9	-0.2	8	8	17	483	5	0.41	-20
438	MJBA07038	37.0	38.0	1.0	-5	-0.2	31	17	43	1.25	-1	0.3	-0.01	1.2	-0.2	8	8	17	390	3	0.41	36
439	MJBA07039	38.0	39.0	1.0	-5	-0.2	14	18	40	1.29	-1	-0.2	-0.01	0.5	-0.2	8	9	16	363	2	0.4	-20
440	MJBA07040	39.0	40.0	1.0	-5	-0.2	13	17	28	0.97	-1	-0.2	-0.01	-0.2	-0.2	6	7	13	282	2	0.32	-20
441	MJBA07041	40.0	41.0	1.0	-5	-0.2	15	18	32	1.12	-1	-0.2	-0.01	-0.2	-0.2	7	8	17	318	3	0.35	-20
442	MJBA07042	41.0	42.0	1.0	-5	-0.2	32	15	38	1.1	-1	-0.2	-0.01	0.2	-0.2	7	8	18	327	2	0.39	-20
443	MJBA07043	42.0	43.0	1.0	-5	-0.2	31	16	47	1.42	-1	-0.2	0.019	0.7	-0.2	9	10	21	419	3	0.45	-20
444	MJBA07044	43.0	44.0	1.0	-5	-0.2	36	14	48	1.4	-1	-0.2	-0.01	0.5	-0.2	8	9	19	412	3	0.53	-20
445	MJBA07045	44.0	45.0	1.0	-5	-0.2	33	13	45	1.45	-1	-0.2	-0.01	0.4	-0.2	9	10	19	418	4	0.5	28
446	MJBA07046	45.0	46.0	1.0	-5	-0.2	32	16	39	1.42	-1	-0.2	-0.01	0.8	-0.2	9	9	19	434	2	0.43	-20
447	MJBA07047	46.0	47.0	1.0	-5	-0.2	32	16	37	1.42	-1	-0.2	-0.01	0.7	-0.2	9	10	18	425	3	0.4	-20
448	MJBA07048	47.0	48.0	1.0	-5	-0.2	73	16	34	1.16	-1	-0.2	-0.01	0.6	-0.2	7	8	17	393	2	0.31	-20
449	MJBA07049	48.0	49.0	1.0	-5	-0.2	110	29	43	1.26	-1	-0.2	-0.01	0.6	1.3	7	10	18	407	5	0.09	-20
450	MJBA07050	49.0	50.0	1.0	8	-0.2	21	13	41	1.18	-1	-0.2	-0.01	0.3	-0.2	6	8	18	423	2	0.2	-20
451	MJBA07051	50.0	51.0	1.0	-5	-0.2	17	14	38	1.12	2	-0.2	-0.01	-0.2	-0.2	6	7	18	366	2	0.35	-20
452	MJBA08001	0.0	1.0	1.0	23	-0.2	40	17	13	2.82	2.4	0.2	0.081	1.4	-0.2	1	10	53	91	9	0.05	-20
453	MJBA08002	1.0	2.0	1.0	37	-0.2	41	20	19	3.87	5.3	0.2	0.124	4.7	-0.2	2	8	78	160	10	0.05	-20
454	MJBA08003	2.0	3.0	1.0	71	-0.2	47	21	14	3.02	2.1	-0.2	0.088	1	-0.2	2	11	58	125	9	0.07	-20
455	MJBA08004	3.0	4.0	1.0	35	-0.2	31	15	10	2.57	1.8	-0.2	0.045	0.7	-0.2	1	8	49	42	6	0.05	-20
456	MJBA08005	4.0	5.0	1.0	23	-0.2	24	15	8	2.28	1.1	-0.2	0.014	0.5	-0.2	-1	6	42	26	4	0.04	-20
457	MJBA08006	5.0	6.0	1.0	11	-0.2	41	32	14	3.04	1.1	-0.2	0.012	0.7	-0.2	3	13	57	32	5	0.06	-20
458	MJBA08007	6.0	7.0	1.0	15	-0.2	40	33	12	2.83	-1	-0.2	-0.01	0.5	-0.2	2	12	49	56	5	0.07	-20
459	MJBA08008	7.0	8.0	1.0	8	-0.2	41	44	13	2.51	-1	-0.2	-0.01	0.5	-0.2	3	10	46	164	4	0.07	-20
460	MJBA08009	8.0	9.0	1.0	5	-0.2	40	31	19	2.24	-1	-0.2	-0.01	0.4	-0.2	4	10	39	330	8	0.14	-20
461	MJBA08010	9.0	10.0	1.0	-5	-0.2	41	20	42	1.95	-1	-0.2	-0.01	0.4	-0.2	9	11	37	765	4	0.34	-20
462	MJBA08011	10.0	11.0	1.0	9	-0.2	48	17	47	1.87	-1	-0.2	-0.01	0.4	-0.2	11	11	35	1129	5	0.44	-20
463	MJBA08012	11.0	12.0	1.0	-5	-0.2	50	16	45	1.89	1.1	-0.2	-0.01	0.4	-0.2	9	11	34	759	3	0.38	-20
464	MJBA08013	12.0	13.0	1.0	-5	-0.2	57	16	36	2.19	1.8	0.3	-0.01	0.6	-0.2	10	8	43	1542	5	0.1	-20
465	MJBA08014	13.0	14.0	1.0	5	-0.2	51	14	44	1.61	-1	-0.2	-0.01	-0.2	-0.2	7	10	27	576	4	0.41	-20
466	MJBA08																					

List of analytical results of drilling

Ser No	Sample No	Depth (m)		Length (m)	Au (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	Fe (%)	As (ppm)	Sb (ppm)	Hg (ppm)	Bi (ppm)	Cd (ppm)	Co (ppm)	Ni (ppm)	V (ppm)	Mn (ppm)	Mo (ppm)	K (%)	W (ppm)
		From	To																			
502	MJBA08051	50.0	51.0	1.0	484	1.1	140	146	120	1.39	3.6	0.2	0.01	3.3	0.5	8	9	8	435	26	0.43	-20
503	MJBA08052	51.0	52.0	1.0	15	-0.2	76	16	39	1.67	1.9	0.3	-0.01	1.7	-0.2	9	8	16	858	63	0.56	61
504	MJBA08053	52.0	53.0	1.0	15	-0.2	104	12	29	1.49	3.2	-0.2	-0.01	3.3	-0.2	8	9	14	741	16	0.54	62
505	MJBA08054	53.0	54.0	1.0	534	1.5	72	15	27	1.65	12.8	0.4	-0.01	1.3	-0.2	8	9	13	879	18	0.53	-20
506	MJBA08055	54.0	55.0	1.0	63	0.5	104	21	26	1.61	2.3	0.3	-0.01	3.1	-0.2	7	9	9	471	33	0.4	-20
507	MJBA08056	55.0	56.0	1.0	21	0.3	131	26	42	1.35	2.7	0.4	-0.01	10	-0.2	8	9	14	557	30	0.53	20
508	MJBA08057	56.0	57.0	1.0	170	1.6	72	156	182	1.78	11.9	0.3	0.011	6	2.3	8	11	17	834	11	0.45	-20
509	MJBA08058	57.0	58.0	1.0	66	1	41	95	169	1.37	4.3	0.2	-0.01	3.2	1.4	7	8	21	1272	6	0.31	-20
510	MJBA08059	58.0	59.0	1.0	158	1.5	108	65	75	2.01	10.4	0.2	-0.01	5.4	0.5	9	10	20	873	7	0.39	-20
511	MJBA08060	59.0	60.0	1.0	117	1.8	207	76	71	2.55	16.6	0.2	-0.01	7.1	0.2	9	10	24	1941	8	0.37	-20
512	MJBA08061	60.0	61.0	1.0	259	1.7	94	67	59	2.35	50	0.3	-0.01	7.1	-0.2	9	12	16	1069	10	0.36	-20
513	MJBA08062	61.0	62.0	1.0	248	1.5	70	57	119	1.72	29.2	0.2	-0.01	2.8	0.5	7	9	18	1099	7	0.45	-20
514	MJBA08063	62.0	63.0	1.0	94	0.6	129	54	57	1.55	3.7	0.3	-0.01	2.1	-0.2	8	10	16	581	27	0.44	-20
515	MJBA08064	63.0	64.0	1.0	94	0.7	72	45	40	1.2	3.5	0.3	-0.01	2.3	-0.2	6	7	12	428	81	0.37	-20
516	MJBA08065	64.0	65.0	1.0	511	2.4	68	64	96	1.75	21.4	0.3	-0.01	1.8	0.3	7	10	16	854	6	0.39	-20
517	MJBA08066	65.0	66.0	1.0	733	3.2	28	93	194	1.46	17.5	-0.2	-0.01	2	0.9	6	8	17	1793	2	0.49	-20
518	MJBA08067	66.0	67.0	1.0	730	2.7	46	47	86	1.5	22.3	-0.2	-0.01	3.1	0.3	7	9	17	967	2	0.42	-20
519	MJBA08068	67.0	68.0	1.0	146	0.5	50	31	29	1.08	16.9	0.2	-0.01	3.1	-0.2	5	6	10	585	5	0.24	-20
520	MJBA08069	68.0	69.0	1.0	366	1.5	74	22	47	1.44	21.1	0.3	-0.01	3.4	-0.2	7	9	19	740	3	0.36	-20
521	MJBA08070	69.0	70.0	1.0	58	-0.2	49	28	55	1.6	13.5	0.4	-0.01	6.9	-0.2	8	10	20	710	5	0.35	-20
522	MJBA08071	70.0	71.0	1.0	14	-0.2	59	20	45	1.35	1.3	-0.2	-0.01	8.5	-0.2	8	10	22	624	7	0.39	87
523	MJBA08072	71.0	72.0	1.0	13	-0.2	80	29	70	1.39	1.5	0.2	-0.01	2.9	0.4	8	11	19	594	120	0.37	78
524	MJBA08073	72.0	73.0	1.0	17	0.3	50	62	42	1.48	1.7	0.3	-0.01	50	-0.2	8	8	17	473	281	0.32	1139
525	MJBA08074	73.0	74.0	1.0	13	-0.2	54	91	63	1.52	1.3	0.2	-0.01	32.1	0.3	8	11	19	486	22	0.32	156
526	MJBA08075	74.0	75.0	1.0	13	-0.2	59	51	69	1.45	1.4	-0.2	-0.01	13.7	0.4	8	10	19	558	24	0.32	142
527	MJBA08076	75.0	76.0	1.0	-5	0.2	49	103	46	1.37	1.1	0.2	-0.01	3.1	0.2	8	10	21	569	16	0.27	55
528	MJBA08077	76.0	77.0	1.0	-5	-0.2	82	30	32	1.07	1	-0.2	-0.01	11.7	-0.2	6	7	14	384	11	0.3	57
529	MJBA08078	77.0	78.0	1.0	-5	-0.2	27	9	56	1.39	-1	-0.2	-0.01	5.6	-0.2	8	10	22	517	8	0.29	128
530	MJBA08079	78.0	79.0	1.0	6	0.2	39	27	47	1.22	-1	-0.2	-0.01	23.5	-0.2	7	9	19	445	229	0.3	163
531	MJBA08080	79.0	80.0	1.0	6	0.7	42	18	35	1.04	-1	-0.2	-0.01	13.6	-0.2	5	7	12	290	15	0.13	77
532	MJBA08081	80.0	81.0	1.0	17	1	47	31	39	1.57	-1	0.2	-0.01	48	-0.2	8	9	19	442	132	0.22	250
533	MJBA08082	81.0	82.0	1.0	6	0.5	142	40	69	0.97	-1	0.3	-0.01	24.2	0.3	4	7	9	311	22	0.22	173
534	MJBA08083	82.0	83.0	1.0	71	0.4	487	253	77	1.39	-1	0.2	-0.01	13.8	0.5	8	10	13	402	17	0.4	154
535	MJBA08084	83.0	84.0	1.0	10	-0.2	145	31	64	1.41	1.1	0.2	-0.01	4.1	0.5	7	10	13	388	9	0.38	121
536	MJBA08085	84.0	85.0	1.0	12	-0.2	76	31	39	1.34	-1	-0.2	-0.01	25.1	0.2	8	9	14	388	8	0.4	102
537	MJBA08086	85.0	86.0	1.0	15	-0.2	57	22	36	1.17	1.1	0.2	-0.01	5.5	-0.2	7	10	11	358	22	0.3	-20
538	MJBA08087	86.0	87.0	1.0	18	-0.2	66	38	50	1.24	1.4	0.3	-0.01	2.5	0.2	8	12	12	405	4	0.27	22
539	MJBA08088	87.0	88.0	1.0	14	0.3	52	41	134	2.6	1.9	0.3	-0.01	5.1	-0.2	25	111	40	1256	12	1.54	-20
540	MJBA08089	88.0	89.0	1.0	13	-0.2	33	37	36	1.36	-1	0.2	-0.01	5.6	-0.2	9	10	16	345	10	0.35	51
541	MJBA08090	89.0	90.0	1.0	6	-0.2	18	16	43	1.47	-1	-0.2	-0.01	13.5	-0.2	8	9	22	441	3	0.32	149
542	MJBA08091	90.0	91.0	1.0	6	-0.2	29	17	39	1.49	-1	-0.2	-0.01	13.6	-0.2	9	10	21	374	3	0.29	94
543	MJBA08092	91.0	92.0	1.0	8	-0.2	62	34	41	1.47	-1	-0.2	-0.01	8.5	-0.2	9	9	20	366	4	0.45	149
544	MJBA08093	92.0	93.0	1.0	28	-0.2	68	11	39	1.51	1.1	-0.2	-0.01	14.2	-0.2	7	11	20	395	6	0.51	255
545	MJBA08094	93.0	94.0	1.0	7	0.2	22	7	41	1.39	1.6	0.2	-0.01	9.4	-0.2	7	10	23	403	2	0.47	24
546	MJBA08095	94.0	95.0	1.0	7	-0.2	22	7	43	1.33	2.4	-0.2	-0.01	6.3	-0.2	8	10	24	382	2	0.44	-20
547	MJBA08096	95.0	96.0	1.0	16	-0.2	114	18	47	1.3	1.6	0.4	-0.01	10.4	-0.2	8	9	21	397	12	0.4	24
548	MJBA08097	96.0	97.0	1.0	-5	-0.2	141	19	40	1.38	-1	-0.2	-0.01	9.5	-0.2	9	10	23	388	36	0.47	50
549	MJBA08098	97.0	98.0	1.0	-5	-0.2	67	28	58	1.76	-1	-0.2	-0.01	8.4	-0.2	12	13	31	478	5	0.6	176
550	MJBA08099	98.0	99.0	1.0	8	-0.2	39	17	55	1.46	-1	-0.2	-0.01	6.7	0.4	9	10	26	378	20	0.55	93
551	MJBA08100	99.0	100.0	1.0	7	-0.2	127	21	48	1.36	-1	0.2	-0.01	8.9	0.3	8	9	21	344	43	0.44	68
552	MJBA09001	0.0	1.0	1.0	68	-0.2	36	15	13	1.7	1.5	-0.2	-0.01	0.4	-0.2	2	8	30	190	6	0.04	-20
553	MJBA09002	1.0	2.0	1.0	35	-0.2	77	15	27	2.33	2	0.2	0.146	0.5	-0.2	2	6	39	98	9	0.05	-20
554	MJBA09003	2.0	3.0	1.0	36	-0.2	103	15	30	2.56	2.5	-0.2	0.126	0.4	-0.2	2	7	44	108	12	0.05	-20
555	MJBA09004	3.0	4.0	1.0	38	-0.2	110	16	46	2.44	2.7	-0.2	0.128	0.5	-0.2	3	8	44	100	9	0.05	-20
556	MJBA09005	4.0	5.0	1.0	54	-0.2	85	21	35	2.9	2.6	0.2	0.121	0.6	-0.2	3	8	52	92	9	0.05	-20
557	MJBA09006	5.0	6.0	1.0	22	-0.2	81	20	36	2.67	2	-0.2	0.103	0.4	-0.2	3	5	46	78	7	0.05	-20
558	MJBA09007	6.0	7.0	1.0	23	-0.2	62	31	24	3.49	1.5	-0.2	0.103	0.3	-0.2	3	10	54	57	7	0.07	-20
559	MJBA09008	7.0	8.0	1.0	18	-0.2	63	38	30	3.46	1.2	-0.2	0.074	0.3	-0.2	3	7	53	52	5	0.08	-20
560	MJBA09009	8.0	9.0	1.0	33	-0.2	29	21	13	2.59	1.6	-0.2	0.053	0.3	-0.2	2	8	45	37	6	0.06	-20
561	MJBA09010	9.0	10.0	1.0	15	-0.2	25	28	11	2.01	-1	-0.2	0.03	-0.2	-0.2	3	7	29	43	4	0.07	-20
562	MJBA09011	10.0	11.0	1.0	5	-0.2	16	14	6	0.82	-1	-0.2	-0.01	-0.2	-0.2	2	9	8	52	4	0.03	-20
563	MJBA09012	11.0	12.0	1.0	-5	-0.2	16	15	6	0.71	-1	-0.2	-0.01	-0.2	-0.2	2	7	7	51	4	0.07	-20
564	MJBA09013	12.0	13.0	1.0	54	-0.2	16	28	7	0.83	-1	-0.2	-0.01	-0.2	-0.2	7	9	8	85	5	0.07	-20
565	MJBA09014	13.0	14.0	1.0	-5	-0.2	13	25	6	0.68	-1	-0.2	-0.01	-0.2	-0.2	2	7	7	85	4	0.07	-20
566	MJBA09015	14.0	15.0	1.0	21	-0.2																

List of analytical results of drilling																						
Ser. No.	Sample No.	Depth (m)		Length (m)	Au (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	Fe (%)	As (ppm)	Sb (ppm)	Hg (ppm)	Bi (ppm)	Cd (ppm)	Co (ppm)	Ni (ppm)	V (ppm)	Mn (ppm)	Mo (ppm)	K (%)	W (ppm)
		From	To																			
602	MJBA10001	0.0	1.0	1.0	35	-0.2	35	30	19	2.1	1.9	-0.2	0.108	0.7	-0.2	4	10	38	288	6	0.06	-20
603	MJBA10002	1.0	2.0	1.0	118	-0.2	50	32	27	3.19	2.1	-0.2	0.11	0.6	-0.2	4	12	56	135	6	0.08	-20
604	MJBA10003	2.0	3.0	1.0	12	-0.2	52	48	31	3.32	1.2	-0.2	0.063	0.3	-0.2	5	11	57	112	5	0.12	-20
605	MJBA10004	3.0	4.0	1.0	-5	-0.2	84	37	67	2.24	-1	-0.2	0.029	-0.2	-0.2	9	13	40	314	3	0.5	-20
606	MJBA10005	4.0	5.0	1.0	-5	-0.2	38	13	45	1.59	-1	-0.2	-0.01	-0.2	-0.2	8	10	30	333	2	0.55	-20
607	MJBA10006	5.0	6.0	1.0	-5	-0.2	19	13	43	1.72	-1	-0.2	-0.01	-0.2	-0.2	9	11	33	337	2	0.61	-20
608	MJBA10007	6.0	7.0	1.0	-5	-0.2	31	25	49	2.31	-1	-0.2	-0.01	0.3	-0.2	9	14	40	267	3	0.49	-20
609	MJBA10008	7.0	8.0	1.0	-5	-0.2	31	21	50	2.02	-1	-0.2	-0.01	0.2	-0.2	10	14	35	337	2	0.63	-20
610	MJBA10009	8.0	9.0	1.0	-5	-0.2	25	15	42	1.56	-1	-0.2	-0.01	-0.2	-0.2	9	11	29	298	3	0.55	-20
611	MJBA10010	9.0	10.0	1.0	-5	-0.2	34	22	47	1.99	-1	-0.2	0.011	0.4	-0.2	10	13	32	440	3	0.48	-20
612	MJBA10011	10.0	11.0	1.0	64	-0.2	33	21	43	2.39	1.5	-0.2	-0.01	1.6	-0.2	11	15	34	491	4	0.31	-20
613	MJBA10012	11.0	12.0	1.0	-5	-0.2	31	17	67	2.45	-1	-0.2	-0.01	0.3	-0.2	11	20	41	406	3	0.55	-20
614	MJBA10013	12.0	13.0	1.0	-5	-0.2	30	16	65	2.2	-1	-0.2	-0.01	0.6	-0.2	19	22	38	578	4	0.45	-20
615	MJBA10014	13.0	14.0	1.0	-5	-0.2	23	13	58	2.04	-1	-0.2	-0.01	-0.2	-0.2	15	16	37	502	3	0.5	-20
616	MJBA10015	14.0	15.0	1.0	-5	-0.2	10	10	40	1.63	-1	-0.2	-0.01	0.4	-0.2	8	11	30	326	3	0.59	-20
617	MJBA10016	15.0	16.0	1.0	-5	-0.2	14	10	36	1.68	-1	-0.2	-0.01	1	-0.2	10	10	29	327	3	0.6	-20
618	MJBA10017	16.0	17.0	1.0	-5	-0.2	13	8	39	1.67	-1	-0.2	-0.01	0.6	-0.2	10	10	29	345	2	0.85	-20
619	MJBA10018	17.0	18.0	1.0	-5	-0.2	14	9	35	1.51	-1	-0.2	-0.01	-0.2	-0.2	9	9	27	339	2	0.6	-20
620	MJBA10019	18.0	19.0	1.0	-5	-0.2	12	9	36	1.49	-1	-0.2	-0.01	-0.2	-0.2	9	9	28	321	1	0.61	-20
621	MJBA10020	19.0	20.0	1.0	-5	-0.2	13	11	39	1.44	-1	-0.2	-0.01	-0.2	-0.2	8	10	27	372	2	0.55	-20
622	MJBA10021	20.0	21.0	1.0	-5	-0.2	43	15	48	1.51	-1	-0.2	-0.01	0.5	-0.2	8	11	24	533	2	0.51	-20
623	MJBA10022	21.0	22.0	1.0	-5	-0.2	30	27	63	2	-1	-0.2	-0.01	0.9	-0.2	10	12	29	1017	3	0.58	-20
624	MJBA10023	22.0	23.0	1.0	-5	-0.2	49	17	42	1.71	1.1	-0.2	0.016	0.6	-0.2	8	16	26	458	4	0.29	-20
625	MJBA10024	23.0	24.0	1.0	21	-0.2	68	34	39	1.61	-1	-0.2	0.028	0.3	-0.2	6	14	26	349	5	0.22	23
626	MJBA10025	24.0	25.0	1.0	9	-0.2	24	12	44	1.49	-1	0.3	-0.01	0.2	-0.2	7	12	24	473	3	0.44	-20
627	MJBA10026	25.0	26.0	1.0	-5	-0.2	9	10	42	1.44	-1	-0.2	-0.01	-0.2	-0.2	6	9	22	446	2	0.52	-20
628	MJBA10027	26.0	27.0	1.0	-5	-0.2	12	13	46	1.55	-1	-0.2	-0.01	-0.2	-0.2	7	10	23	498	2	0.56	-20
629	MJBA10028	27.0	28.0	1.0	-5	0.5	57	22	37	1.24	-1	-0.2	-0.01	1.2	-0.2	5	8	20	506	2	0.37	-20
630	MJBA10029	28.0	29.0	1.0	5	0.3	39	19	38	1.24	1	-0.2	-0.01	0.8	-0.2	5	8	19	490	1	0.44	-20
631	MJBA10030	29.0	30.0	1.0	-5	0.3	27	18	44	1.26	1.3	-0.2	-0.01	1	-0.2	4	9	19	567	-1	0.44	-20
632	MJBA10031	30.0	31.0	1.0	-5	0.2	15	19	48	1.01	1.2	-0.2	-0.01	0.7	-0.2	5	11	16	547	-1	0.51	-20
633	MJBA10032	31.0	32.0	1.0	-5	0.3	14	15	69	1.36	1.3	-0.2	-0.01	1.2	-0.2	7	25	20	555	-1	0.88	-20
634	MJBA10033	32.0	33.0	1.0	-5	0.3	10	12	83	1.52	1.5	-0.2	-0.01	1.1	-0.2	11	56	21	589	-1	0.84	-20
635	MJBA10034	33.0	34.0	1.0	-5	-0.2	13	10	149	2.16	1.1	-0.2	-0.01	-0.2	-0.2	19	90	37	945	2	1.35	-20
636	MJBA10035	34.0	35.0	1.0	-5	-0.2	10	13	52	1.63	-1	-0.2	-0.01	-0.2	-0.2	8	9	23	586	1	0.55	-20
637	MJBA10036	35.0	36.0	1.0	-5	-0.2	21	15	49	1.39	-1	-0.2	-0.01	0.4	-0.2	8	11	19	462	2	0.23	-20
638	MJBA10037	36.0	37.0	1.0	-5	-0.2	38	8	80	1.37	1.3	-0.2	-0.01	1.8	-0.2	9	19	23	616	1	0.58	-20
639	MJBA10038	37.0	38.0	1.0	-5	-0.2	38	13	37	0.92	1.2	-0.2	-0.01	0.7	-0.2	6	11	13	426	-1	0.23	-20
640	MJBA10039	38.0	39.0	1.0	-5	0.3	55	14	59	1.46	1.1	-0.2	-0.01	0.7	-0.2	6	14	17	662	-1	0.49	-20
641	MJBA10040	39.0	40.0	1.0	15	0.2	66	16	38	1.14	1.2	-0.2	-0.01	0.4	-0.2	4	8	16	409	-1	0.2	-20
642	MJBA10041	40.0	41.0	1.0	-5	0.3	107	17	57	1.4	-1	-0.2	-0.01	0.7	-0.2	5	9	17	655	-1	0.41	-20
643	MJBA10042	41.0	42.0	1.0	-5	0.8	70	35	66	1.87	1.1	0.2	-0.01	2.7	-0.2	10	12	18	739	-1	0.63	-20
644	MJBA10043	42.0	43.0	1.0	-5	-0.2	23	20	65	1.77	-1	-0.2	-0.01	1	-0.2	7	12	24	778	-1	0.67	-20
645	MJBA10044	43.0	44.0	1.0	-5	-0.2	15	12	55	1.35	-1	0.3	-0.01	0.4	-0.2	5	9	23	632	-1	0.5	-20
646	MJBA10045	44.0	45.0	1.0	-5	-0.2	20	24	65	1.44	-1	-0.2	-0.01	0.5	-0.2	6	10	22	809	1	0.46	-20
647	MJBA10046	45.0	46.0	1.0	-5	0.8	28	39	58	1.27	-1	0.2	-0.01	4.5	-0.2	5	9	22	493	-1	0.34	-20
648	MJBA10047	46.0	47.0	1.0	-5	2.3	120	124	92	1.62	-1	-0.2	-0.01	5.2	0.5	8	9	27	532	1	0.66	-20
649	MJBA10048	47.0	48.0	1.0	5	0.6	25	61	74	1.54	-1	-0.2	-0.01	1.4	0.4	8	9	28	477	2	0.67	-20
650	MJBA10049	48.0	49.0	1.0	-5	-0.2	37	27	62	1.53	-1	-0.2	-0.01	0.5	-0.2	8	9	27	440	1	0.62	-20
651	MJBA10050	49.0	50.0	1.0	-5	-0.2	14	23	57	1.51	-1	-0.2	-0.01	0.5	-0.2	8	8	27	435	1	0.63	-20
652	MJBA10051	50.0	51.0	1.0	-5	1.3	170	100	58	1.62	-1	-0.2	-0.01	2.4	-0.2	8	9	28	466	1	0.54	-20
653	MJBA11001	0.0	1.0	1.0	28	-0.2	9	47	33	10	27.7	3.4	0.116	1.8	0.3	1	4	259	869	7	0.06	-20
654	MJBA11002	1.0	2.0	1.0	32	-0.2	8	9	18	3.33	3.5	0.4	0.093	0.5	-0.2	-1	3	59	158	2	0.09	-20
655	MJBA11003	2.0	3.0	1.0	36	-0.2	9	19	22	6.66	10.4	1.2	0.093	1	-0.2	1	4	122	351	3	0.09	-20
656	MJBA11004	3.0	4.0	1.0	27	-0.2	8	34	22	8.22	13.2	1.7	0.094	0.9	-0.2	-1	2	119	152	2	0.08	-20
657	MJBA11005	4.0	5.0	1.0	42	-0.2	8	35	23	5.83	10.2	1.3	0.089	0.8	-0.2	-1	3	86	110	2	0.09	-20
658	MJBA11006	5.0	6.0	1.0	75	-0.2	7	30	21	5.32	9.7	1	0.087	0.6	-0.2	1	2	76	116	2	0.09	-20
659	MJBA11007	6.0	7.0	1.0	72	-0.2	5	17	17	3.46	5.4	0.6	0.046	0.3	-0.2	-1	5	47	38	1	0.16	-20
660	MJBA11008	7.0	8.0	1.0	51	-0.2	5	14	12	2.75	4.9	0.7	0.022	-0.2	-0.2	-1	4	33	32	2	0.16	-20
661	MJBA11009	8.0	9.0	1.0	23	-0.2	5	13	10	2.08	3.6	0.5	-0.01	0.2	-0.2	-1	5	24	28	2	0.14	-20
662	MJBA11010	9.0	10.0	1.0	15	-0.2	5	20	11	1.75	3.3	0.7	-0.01	-0.2	-0.2	1	4	21	129	2	0.12	-20
663	MJBA11011	10.0	11.0	1.0	38	-0.2	6	13	10	1.35	7.1	0.6	-0.01	0.4	-0.2	-1	6	14	119	2	0.17	-20
664	MJBA11012	11.0	12.0	1.0	359	-0.2	7	423	19	1.86	13.4	1.1	-0.01	0.7	-0.2	10	3	17	9229	2	0.18	118
665	MJBA11013	12.0	13.0	1.0	1364	-0.2	8	32	17	1.8	10.3	0.5	-0.01	-0.2	-0.2	1	6	17	274	2	0.18	-20
666	MJBA11014	13.0	14.0	1.0	644	-0.2	7	94	18	1.79	8.9	0.6	-0.01	-0.2	-0.2	6	3	18	799	3	0.12	-20
667	MJBA11015	14.0	1																			

List of analytical results of drilling

Ser No	Sample No	Depth (m) From To	Length (m)	Au (ppb)	Ag (ppm)	Cu (ppm)	Pb (ppm)	Zn (ppm)	Fe (%)	As (ppm)	Sb (ppm)	Hg (ppm)	Bi (ppm)	Cd (ppm)	Co (ppm)	Ni (ppm)	V (ppm)	Mn (ppm)	Mo (ppm)	K (%)	W (ppm)
703	MJBA12001	0.0 1.0	1.0	34	-0.2	12	13	17	3.79	2.9	0.5	0.091	0.6	-0.2	1	4	67	173	2	0.08	-20
704	MJBA12002	1.0 2.0	1.0	42	-0.2	12	12	18	4.15	3.5	0.6	0.11	0.6	-0.2	1	4	73	207	-1	0.09	-20
705	MJBA12003	2.0 3.0	1.0	33	-0.2	18	35	35	10	35.7	1.9	0.182	1.6	0.4	2	3	402	199	8	0.05	-20
706	MJBA12004	3.0 4.0	1.0	53	-0.2	13	12	20	5.03	5.6	0.6	0.14	0.7	-0.2	1	5	94	160	3	0.09	-20
707	MJBA12005	4.0 5.0	1.0	127	-0.2	13	41	24	7.09	13.3	0.6	0.08	1.1	0.2	4	4	135	643	3	0.08	-20
708	MJBA12006	5.0 6.0	1.0	34	-0.2	17	40	33	10	31.3	2	0.12	1.7	0.4	2	5	359	301	7	0.05	-20
709	MJBA12007	6.0 7.0	1.0	225	-0.2	8	17	20	3.36	10.4	0.6	0.032	0.5	-0.2	2	4	54	179	2	0.11	-20
710	MJBA12008	7.0 8.0	1.0	39	-0.2	9	23	28	2.56	5.4	0.6	0.013	0.3	-0.2	2	5	37	323	2	0.12	-20
711	MJBA12009	8.0 9.0	1.0	16	-0.2	6	11	19	2.42	5.9	0.6	-0.01	0.2	-0.2	1	4	33	155	3	0.12	-20
712	MJBA12010	9.0 10.0	1.0	9	0.2	5	22	28	3.25	5.7	0.6	0.01	0.8	-0.2	2	3	50	263	2	0.05	-20
713	MJBA12011	10.0 11.0	1.0	13	-0.2	8	20	22	2.9	6.3	0.6	-0.01	0.6	-0.2	2	5	42	314	2	0.09	-20
714	MJBA12012	11.0 12.0	1.0	11	-0.2	8	20	14	2.07	5.5	0.6	-0.01	0.4	-0.2	2	6	28	175	2	0.11	-20
715	MJBA12013	12.0 13.0	1.0	5	-0.2	7	34	10	1.98	2.6	0.5	-0.01	0.3	-0.2	3	5	27	329	2	0.09	-20
716	MJBA12014	13.0 14.0	1.0	5	-0.2	8	105	8	1.97	1.9	0.6	-0.01	0.3	-0.2	5	4	31	908	2	0.09	-20
717	MJBA12015	14.0 15.0	1.0	5	-0.2	13	86	9	1.65	2.3	0.6	-0.01	0.3	-0.2	15	5	29	1549	2	0.11	-20
718	MJBA12016	15.0 16.0	1.0	8	-0.2	14	29	10	1.83	3.3	0.5	-0.01	0.4	-0.2	3	5	26	440	1	0.08	-20
719	MJBA12017	16.0 17.0	1.0	20	-0.2	33	46	18	3.28	6.2	0.6	-0.01	0.3	-0.2	8	4	49	1200	-1	0.17	-20
720	MJBA12018	17.0 18.0	1.0	51	-0.2	37	103	35	4.11	13.1	0.6	-0.01	0.8	-0.2	22	8	53	7055	2	0.17	-20
721	MJBA12019	18.0 19.0	1.0	20	-0.2	34	46	28	4.09	7.7	0.5	0.01	0.8	-0.2	15	5	52	3661	1	0.19	-20
722	MJBA12020	19.0 20.0	1.0	30	-0.2	29	48	30	4.44	8.7	-0.2	-0.01	0.3	-0.2	12	7	58	4569	2	0.18	-20
723	MJBA12021	20.0 21.0	1.0	5	-0.2	20	25	17	3.93	3.3	-0.2	-0.01	0.3	-0.2	4	2	62	463	-1	0.15	-20
724	MJBA12022	21.0 22.0	1.0	5	-0.2	34	50	23	4.05	4.1	-0.2	-0.01	0.8	-0.2	11	4	62	1932	-1	0.13	-20
725	MJBA12023	22.0 23.0	1.0	5	-0.2	36	41	26	4.45	4.4	-0.2	-0.01	0.7	-0.2	10	4	72	1262	-1	0.11	-20
726	MJBA12024	23.0 24.0	1.0	5	-0.2	45	28	36	4.74	3	-0.2	-0.01	0.4	-0.2	18	4	72	1622	-1	0.1	-20
727	MJBA12025	24.0 25.0	1.0	5	-0.2	44	16	46	4.47	3.1	-0.2	-0.01	0.2	-0.2	15	6	65	1177	-1	0.12	-20
728	MJBA12026	25.0 26.0	1.0	18	-0.2	37	19	75	2.45	4.2	-0.2	-0.01	0.3	-0.2	31	12	34	944	2	0.41	-20
729	MJBA12027	26.0 27.0	1.0	644	-0.2	20	16	70	1.08	1.7	-0.2	-0.01	0.2	-0.2	29	9	17	1702	2	0.32	-20
730	MJBA12028	27.0 28.0	1.0	226	-0.2	11	23	104	1.49	1.2	-0.2	-0.01	0.3	-0.2	7	9	16	324	-1	0.42	-20
731	MJBA12029	28.0 29.0	1.0	281	-0.2	10	34	75	1.3	1.3	-0.2	-0.01	0.3	-0.2	14	7	12	1432	1	0.33	-20
732	MJBA12030	29.0 30.0	1.0	121	-0.2	8	27	94	1.55	-1	-0.2	-0.01	0.2	-0.2	9	8	17	660	1	0.4	-20
733	MJBA12031	30.0 31.0	1.0	27	-0.2	7	22	79	1.62	-1	-0.2	-0.01	0.2	-0.2	8	8	17	356	2	0.43	-20
734	MJBA12032	31.0 32.0	1.0	5	-0.2	7	20	90	1.59	1.2	-0.2	-0.01	0.2	0.6	7	7	15	1166	2	0.38	-20
735	MJBA12033	32.0 33.0	1.0	5	-0.2	8	28	83	1.47	-1	-0.2	-0.01	0.3	0.3	5	6	17	564	-1	0.39	-20
736	MJBA12034	33.0 34.0	1.0	5	-0.2	8	30	78	1.47	1	-0.2	-0.01	0.3	0.2	6	7	16	654	1	0.4	-20
737	MJBA12035	34.0 35.0	1.0	5	-0.2	10	19	83	1.53	1	-0.2	-0.01	0.3	-0.2	5	6	17	438	1	0.35	-20
738	MJBA12036	35.0 36.0	1.0	7	0.2	25	36	102	1.94	2.1	-0.2	-0.01	0.9	0.3	8	6	20	633	2	0.35	-20
739	MJBA12037	36.0 37.0	1.0	17	0.5	37	89	112	2.04	1.9	0.2	-0.01	2.5	-0.2	8	5	25	720	2	0.33	-20
740	MJBA12038	37.0 38.0	1.0	12	-0.2	23	29	108	2.07	1.9	0.3	-0.01	0.9	-0.2	9	5	31	819	-1	0.37	-20
741	MJBA12039	38.0 39.0	1.0	91	-0.2	28	35	196	2.27	1.9	0.3	-0.01	0.7	0.7	11	6	30	856	1	0.3	-20
742	MJBA12040	39.0 40.0	1.0	12	-0.2	13	22	128	2.28	1.8	0.5	-0.01	0.5	0.3	11	6	30	1345	2	0.32	-20
743	MJBA12041	40.0 41.0	1.0	9	-0.2	13	19	126	2.45	2	0.3	-0.01	0.6	-0.2	12	6	30	1644	2	0.39	-20
744	MJBA12042	41.0 42.0	1.0	6	-0.2	15	16	131	2.38	2	0.3	-0.01	0.5	-0.2	13	7	27	1694	2	0.4	-20
745	MJBA12043	42.0 43.0	1.0	8	-0.2	6	25	132	2.31	2	0.4	-0.01	0.4	0.4	12	6	31	1456	1	0.35	-20
746	MJBA12044	43.0 44.0	1.0	5	-0.2	8	31	130	2.27	1.4	0.3	-0.01	0.6	0.6	8	4	28	846	1	0.19	-20
747	MJBA12045	44.0 45.0	1.0	16	-0.2	7	14	130	2.37	1.6	0.3	-0.01	0.2	0.3	10	5	30	2101	2	0.25	-20
748	MJBA12046	45.0 46.0	1.0	8	-0.2	7	22	145	2.23	1.7	0.3	-0.01	0.3	0.6	10	5	28	1252	2	0.36	-20
749	MJBA12047	46.0 47.0	1.0	7	-0.2	7	20	91	1.56	2.2	0.3	-0.01	0.3	0.4	7	6	18	693	2	0.15	-20
750	MJBA12048	47.0 48.0	1.0	5	-0.2	7	9	58	1.32	1.9	0.3	-0.01	0.2	-0.2	3	5	18	930	2	0.12	-20
751	MJBA12049	48.0 49.0	1.0	5	-0.2	6	9	93	1.77	1.9	0.2	-0.01	0.2	-0.2	5	6	25	1344	1	0.13	-20
752	MJBA12050	49.0 50.0	1.0	5	-0.2	6	15	98	1.85	2.1	0.3	-0.01	0.3	-0.2	3	6	22	801	1	0.2	-20
753	MJBA12051	50.0 51.0	1.0	5	-0.2	7	19	64	1.49	2	0.3	-0.01	0.4	0.3	4	4	19	357	1	0.14	-20
754	MJBA13001	0.0 1.0	1.0	50	-0.2	18	29	24	5.36	2.1	0.3	0.066	0.5	-0.2	4	7	132	351	-1	0.08	-20
755	MJBA13002	1.0 2.0	1.0	25	-0.2	26	78	35	10	3.7	0.4	0.089	0.3	0.6	10	5	352	622	-1	0.04	-20
756	MJBA13003	2.0 3.0	1.0	24	-0.2	27	79	36	10	2.6	0.4	0.047	0.2	0.6	13	6	388	343	-1	0.03	-20
757	MJBA13004	3.0 4.0	1.0	35	-0.2	30	86	38	10	3.6	0.4	0.015	0.2	0.5	12	3	354	533	-1	0.01	-20
758	MJBA13005	4.0 5.0	1.0	54	-0.2	20	73	22	6.04	2.1	0.2	-0.01	0.6	-0.2	5	5	151	258	-1	0.03	-20
759	MJBA13006	5.0 6.0	1.0	62	-0.2	14	36	19	2.77	1.7	0.3	-0.01	2.5	-0.2	3	4	62	145	1	0.03	-20
760	MJBA13007	6.0 7.0	1.0	139	-0.2	16	24	20	2.49	1.9	0.3	0.01	1.1	-0.2	2	6	58	86	2	0.02	-20
761	MJBA13008	7.0 8.0	1.0	247	-0.2	18	56	30	2.27	1.5	0.3	-0.01	0.5	-0.2	7	5	42	476	1	0.05	-20
762	MJBA13009	8.0 9.0	1.0	18	-0.2	20	47	31	2.09	1.1	0.2	-0.01	0.3	-0.2	7	8	35	381	1	0.08	-20
763	MJBA13010	9.0 10.0	1.0	5	-0.2	21	53	40	2.22	1.1	-0.2	-0.01	0.3	-0.2	8	5	38	713	-1	0.14	-20
764	MJBA13011	10.0 11.0	1.0	11	-0.2	41	76	57	3.02	1.4	0.2	-0.01	0.7	-0.2	14	7	43	1466	-1	0.19	-20
765	MJBA13012	11.0 12.0	1.0	5	-0.2	19	40	66	2.26	-1	-0.2	-0.01	0.2	-0.2	10	8	31	722	2	0.34	-20
766	MJBA13013	12.0 13.0	1.0	5	-0.2	23	43	92	2.18	-1	-0.2	-0.01	0.3	-0.2	11	12	27	843	1	0.4	-20
767	MJBA13014	13.0 14.0	1.0	5	-0.2	22	32	76	1.76	-1	-0.2	-0.01	0.5	-0.2	17	9	44	815	1	0.25	-20
768	MJBA13015	14.0 15.0	1.0	305	-0.2	12	26	67	1.86	-1	-0.2	-0.01	0.2	-0.2	7	7	36	570	1	0.32	-20
769	MJBA13016	15.0 16.0	1.0	5	-0.2	10	17	64	1.69	-1	-0.2	-0.01	0.2</								