

Appendix 9

Assay results of the drill core samples, 1/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
1	MJT-3	6.2	9.0	2.8	70	0.35	53.0	17.25	45.00	10.0	-	-	-
2	MJT-3	9.0	11.0	2.0	30	0.20	53.5	8.35	36.00	6.0	-	-	-
3	MJT-3	11.0	13.0	2.0	30	0.20	45.5	7.50	31.00	8.0	-	-	-
4	MJT-3	13.0	15.0	2.0	20	0.50	132.5	9.05	31.00	11.0	-	-	-
5	MJT-3	15.0	17.0	2.0	70	0.30	98.5	9.00	39.00	20.0	-	-	-
6	MJT-3	17.0	19.0	2.0	100	0.15	157.0	6.85	26.50	28.0	-	-	-
7	MJT-3	19.0	21.0	2.0	140	0.10	39.5	4.60	25.50	3.0	-	-	-
8	MJT-3	21.0	23.0	2.0	60	<0.10	16.0	8.20	33.50	16.0	-	-	-
9	MJT-3	23.0	25.0	2.0	30	0.10	9.5	10.75	44.00	9.0	-	-	-
10	MJT-3	25.0	27.0	2.0	30	0.15	21.0	10.70	44.00	3.0	-	-	-
11	MJT-3	27.0	29.0	2.0	30	0.15	22.5	12.75	51.50	7.0	-	-	-
12	MJT-3	29.0	31.0	2.0	40	0.15	86.0	7.10	39.00	11.0	-	-	-
13	MJT-3	31.0	33.0	2.0	30	0.55	60.0	8.55	36.50	26.0	-	-	-
14	MJT-3	33.0	35.0	2.0	30	<0.10	43.5	8.50	33.50	4.0	-	-	-
15	MJT-3	35.0	38.0	3.0	20	0.15	20.0	8.20	33.00	3.0	-	-	-
16	MJT-3	38.0	41.0	3.0	40	0.15	178.5	7.90	34.00	23.0	-	-	-
17	MJT-3	41.0	44.0	3.0	50	0.15	120.0	7.40	35.50	20.0	-	-	-
18	MJT-3	44.0	47.0	3.0	30	<0.10	70.0	7.20	38.00	7.0	-	-	-
19	MJT-3	47.0	50.0	3.0	30	0.15	186.0	7.10	12.50	10.0	-	-	-
20	MJT-3	50.0	53.0	3.0	60	0.45	210.0	8.10	11.00	19.0	-	-	-
21	MJT-3	53.0	54.0	1.0	60	0.25	180.0	7.65	10.00	48.0	-	-	-
22	MJT-3	54.0	55.0	1.0	30	0.15	107.5	22.95	8.50	44.0	-	-	-
23	MJT-3	55.0	56.0	1.0	40	0.20	95.5	6.90	9.00	9.0	-	-	-
24	MJT-3	56.0	59.0	3.0	40	0.50	111.5	5.20	8.50	10.0	-	-	-
25	MJT-3	59.0	62.0	3.0	70	0.20	150.0	8.75	18.50	10.0	-	-	-
26	MJT-3	62.0	65.0	3.0	60	0.90	61.5	26.05	9.00	3.0	-	-	-
27	MJT-3	65.0	68.0	3.0	20	0.20	413.0	8.60	13.00	3.0	-	-	-
28	MJT-3	68.0	71.0	3.0	120	0.10	30.0	7.35	14.50	3.0	-	-	-
29	MJT-3	71.0	74.0	3.0	30	0.20	148.5	9.65	17.00	7.0	-	-	-
30	MJT-3	74.0	77.0	3.0	30	0.25	429.0	6.35	48.50	3.0	-	-	-
31	MJT-3	77.0	78.0	1.0	40	0.15	46.0	13.15	17.25	<2.0	-	-	-
32	MJT-3	78.0	79.0	1.0	850	0.20	33.0	4.10	14.00	4.0	0.497	<0.01	0.497
33	MJT-3	79.0	80.0	1.0	210	<0.10	516.0	5.70	10.00	<2.0	3.478	<0.01	3.478
34	MJT-3	80.0	81.0	1.0	230	0.45	182.0	4.45	12.50	<2.0	-	-	-
35	MJT-3	81.0	84.0	3.0	430	0.20	83.0	2.90	13.50	<2.0	-	-	-
36	MJT-3	84.0	87.0	3.0	140	0.10	117.5	7.35	15.00	<2.0	-	-	-
37	MJT-3	87.0	90.0	3.0	60	0.10	115.0	5.05	10.00	<2.0	-	-	-
38	MJT-3	90.0	93.0	3.0	50	0.20	97.0	5.20	16.50	<2.0	-	-	-
39	MJT-3	93.0	96.0	3.0	70	0.15	66.0	4.10	19.00	28.0	-	-	-
40	MJT-3	96.0	99.0	3.0	40	0.10	39.5	3.45	17.50	<2.0	-	-	-
41	MJT-3	99.0	102.0	3.0	10	0.10	76.5	4.60	19.00	<2.0	-	-	-
42	MJT-3	102.0	103.0	1.0	30	0.15	257.0	6.05	20.00	<2.0	-	-	-
43	MJT-3	103.0	104.0	1.0	50	0.85	352.0	91.55	22.00	3.0	0.607	0.032	0.575
44	MJT-3	104.0	105.0	1.0	30	0.15	105.5	6.00	26.00	7.0	0.412	<0.01	0.412
45	MJT-3	105.0	108.0	3.0	150	0.10	63.0	6.45	19.00	<2.0	0.224	<0.01	0.224
46	MJT-3	108.0	111.0	3.0	20	0.20	99.5	6.95	22.50	<2.0	-	-	-
47	MJT-3	111.0	114.0	3.0	40	0.30	111.0	7.65	20.00	<2.0	-	-	-
48	MJT-3	114.0	117.0	3.0	30	0.20	99.5	7.35	20.00	<2.0	-	-	-
49	MJT-3	117.0	120.0	3.0	10	0.10	102.5	6.35	17.50	<2.0	-	-	-
50	MJT-3	120.0	121.0	1.0	20	0.15	29.0	6.25	15.50	<2.0	0.055	<0.01	0.052
51	MJT-3	121.0	122.0	1.0	50	0.15	136.0	4.75	18.50	<2.0	0.148	<0.01	0.148
52	MJT-3	122.0	123.0	1.0	90	0.40	517.5	4.95	22.00	11.0	1.059	0.042	1.017
53	MJT-3	123.0	126.0	3.0	70	0.35	545.0	4.75	21.50	<2.0	-	-	-
54	MJT-3	126.0	129.0	3.0	130	0.40	575.0	4.00	20.00	34.0	-	-	-
55	MJT-3	129.0	132.0	3.0	50	0.10	80.5	4.75	18.50	<2.0	-	-	-
56	MJT-3	132.0	135.0	3.0	40	0.10	98.5	0.70	21.00	<2.0	-	-	-
57	MJT-3	135.0	138.0	3.0	30	0.15	117.5	11.50	22.50	12.0	-	-	-
58	MJT-3	138.0	141.0	3.0	20	0.15	152.5	12.90	25.00	<2.0	-	-	-
59	MJT-3	141.0	144.0	3.0	20	0.15	135.5	10.60	34.00	<2.0	-	-	-
60	MJT-3	144.0	147.0	3.0	30	0.40	415.0	16.10	33.50	<2.0	-	-	-
61	MJT-3	147.0	150.0	3.0	30	0.10	70.5	7.00	23.50	5.0	-	-	-
62	MJT-3	150.0	153.0	3.0	30	0.15	91.5	7.10	26.50	2.0	-	-	-
63	MJT-3	153.0	156.0	3.0	40	0.15	127.5	5.75	26.00	<2.0	-	-	-
64	MJT-3	156.0	159.0	3.0	70	0.30	355.0	8.85	28.50	<2.0	-	-	-

Appendix 9 Assay results of the drill core samples, 2/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
65	MJT-3	159.0	162.0	3.0	40	0.15	162.5	8.10	37.50	<2.0	-	-	-
66	MJT-3	162.0	165.0	3.0	50	0.15	201.0	6.95	48.00	<2.0	-	-	-
67	MJT-3	165.0	168.0	3.0	40	0.20	210.0	9.95	43.50	<2.0	-	-	-
68	MJT-3	168.0	171.0	3.0	40	0.15	177.0	6.15	24.00	<2.0	-	-	-
69	MJT-3	171.0	172.0	1.0	140	0.35	541.5	3.45	43.50	400.0	-	-	-
70	MJT-3	172.0	173.0	1.0	160	0.35	545.0	3.05	44.50	7.0	-	-	-
71	MJT-3	173.0	174.0	1.0	50	0.20	306.5	4.35	26.00	<2.0	-	-	-
72	MJT-3	174.0	177.0	3.0	110	0.65	523.5	7.00	29.50	39.0	-	-	-
73	MJT-3	177.0	180.0	3.0	50	0.20	349.0	6.80	35.50	<2.0	-	-	-
74	MJT-3	180.0	183.0	3.0	20	0.15	111.5	7.10	26.00	<2.0	-	-	-
75	MJT-3	183.0	186.0	3.0	10	0.15	141.5	7.50	40.50	<2.0	-	-	-
76	MJT-3	186.0	187.0	1.0	190	0.40	569.5	5.70	43.50	21.0	0.559	0.129	0.430
77	MJT-3	187.0	188.0	1.0	60	0.35	513.5	5.60	52.50	<2.0	0.216	0.011	0.205
78	MJT-3	188.0	189.0	1.0	20	0.15	198.5	6.75	20.00	9.0	-	-	-
79	MJT-3	189.0	192.0	3.0	30	0.25	339.0	12.35	47.00	<2.0	-	-	-
80	MJT-3	192.0	195.0	3.0	40	0.35	475.5	8.20	41.50	2.0	-	-	-
81	MJT-3	195.0	196.0	1.0	170	0.85	571.5	16.90	50.00	18.0	2.326	0.025	2.301
82	MJT-3	196.0	197.0	1.0	100	0.35	529.5	8.15	48.50	16.0	-	-	-
83	MJT-3	197.0	200.0	3.0	40	0.25	514.5	4.65	54.00	17.0	-	-	-
84	MJT-3	200.0	203.0	3.0	30	0.20	250.0	6.65	30.00	5.0	-	-	-
85	MJT-3	203.0	206.0	3.0	20	<0.10	240.0	9.75	47.00	7.0	-	-	-
86	MJT-3	206.0	209.0	3.0	50	0.10	507.5	6.40	33.50	10.0	-	-	-
87	MJT-3	209.0	212.0	3.0	40	<0.10	416.0	6.05	28.00	10.0	-	-	-
88	MJT-3	212.0	213.0	1.0	110	0.40	595.0	8.35	32.50	17.0	-	-	-
89	MJT-3	213.0	214.0	1.0	30	<0.10	287.0	7.35	23.50	11.0	-	-	-
90	MJT-3	214.0	215.0	1.0	140	0.35	575.0	9.90	30.00	13.0	-	-	-
91	MJT-3	215.0	216.0	1.0	200	0.90	645.0	6.30	37.50	51.0	-	-	-
92	MJT-3	216.0	219.0	3.0	20	0.10	173.5	6.90	26.00	25.0	-	-	-
93	MJT-3	219.0	222.0	3.0	<10	<0.10	210.0	5.90	27.00	29.0	-	-	-
94	MJT-3	222.0	225.0	3.0	10	1.50	140.0	7.55	25.50	18.0	-	-	-
95	MJT-3	225.0	228.0	3.0	10	0.15	81.5	8.60	28.50	11.0	-	-	-
96	MJT-3	228.0	231.0	3.0	10	<0.10	84.0	7.45	27.50	17.0	-	-	-
97	MJT-3	231.0	233.0	2.0	100	0.30	375.5	18.60	31.00	10.0	-	-	-
98	MJT-3	233.0	234.0	1.0	70	0.50	595.0	62.35	37.50	<2.0	3.886	0.135	3.751
99	MJT-3	234.0	235.0	1.0	70	0.45	605.0	3.55	30.50	3.0	1.115	0.054	1.061
100	MJT-3	235.0	236.0	1.0	30	0.10	221.0	3.55	24.50	<2.0	-	-	-
101	MJT-3	236.0	238.0	2.0	30	0.45	473.0	5.45	27.50	<2.0	-	-	-
102	MJT-3	238.0	239.0	1.0	20	0.30	340.0	6.60	26.00	<2.0	-	-	-
103	MJT-3	239.0	240.0	1.0	40	0.30	190.0	7.20	47.00	<2.0	-	-	-
104	MJT-3	240.0	242.0	2.0	10	0.10	35.5	6.80	52.50	<2.0	-	-	-
105	MJT-3	242.0	244.0	2.0	20	0.10	28.5	5.30	52.00	<2.0	-	-	-
106	MJT-3	244.0	247.0	3.0	30	0.10	62.0	4.55	50.50	<2.0	-	-	-
107	MJT-3	247.0	250.0	3.0	50	0.20	299.0	12.35	24.50	<2.0	-	-	-
108	MJT-4	6.0	7.5	1.5	20	0.60	194.0	10.60	84.00	<2.0	-	-	-
109	MJT-4	7.5	9.0	1.5	10	0.60	290.0	13.00	74.00	<2.0	-	-	-
110	MJT-4	9.0	10.5	1.5	50	0.80	306.0	10.60	76.00	<2.0	-	-	-
111	MJT-4	10.5	12.0	1.5	20	0.80	374.0	10.40	76.00	<2.0	-	-	-
112	MJT-4	12.0	13.5	1.5	10	10.40	266.0	10.20	68.00	<2.0	-	-	-
113	MJT-4	13.5	15.0	1.5	60	0.40	236.0	9.60	56.00	<2.0	-	-	-
114	MJT-4	15.0	16.5	1.5	40	0.80	860.0	10.80	90.00	<2.0	-	-	-
115	MJT-4	16.5	18.0	1.5	40	0.80	424.0	9.80	60.00	<2.0	-	-	-
116	MJT-4	18.0	20.0	2.0	160	0.40	175.5	4.85	38.00	<2.0	-	-	-
117	MJT-4	20.0	22.0	2.0	10	0.40	362.0	9.60	54.00	50.0	-	-	-
118	MJT-4	22.0	24.0	2.0	10	0.40	232.0	11.20	56.00	<2.0	1.181	0.059	1.122
119	MJT-4	24.0	27.0	3.0	10	0.20	242.0	9.00	60.00	<2.0	0.821	0.039	0.782
120	MJT-4	27.0	30.0	3.0	60	0.10	379.5	4.10	30.50	<2.0	-	-	-
121	MJT-4	30.0	33.0	3.0	10	0.60	130.0	9.60	68.00	<2.0	-	-	-
122	MJT-4	33.0	36.0	3.0	50	0.20	106.0	7.20	52.00	<2.0	-	-	-
123	MJT-4	36.0	39.0	3.0	40	<0.10	80.0	9.00	52.00	10.0	-	-	-
124	MJT-4	39.0	41.0	2.0	10	0.60	182.0	6.60	44.00	6.0	-	-	-
125	MJT-4	41.0	42.0	1.0	200	0.40	370.0	9.80	44.00	7.0	-	-	-
126	MJT-4	42.0	43.0	1.0	200	1.80	266.0	9.60	46.00	10.0	-	-	-
127	MJT-4	43.0	44.0	1.0	20	0.80	244.0	13.80	54.00	6.0	-	-	-
128	MJT-4	44.0	47.0	3.0	10	<0.10	168.0	9.60	46.00	<2.0	-	-	-

Appendix 9

Assay results of the drill core samples, 3/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
129	MJT-4	47.0	50.0	3.0	20	0.60	342.0	10.00	50.00	13.0	-	-	-
130	MJT-4	50.0	53.0	3.0	310	0.20	120.0	11.00	56.00	6.0	-	-	-
131	MJT-4	53.0	56.0	3.0	80	<0.10	162.0	9.00	46.00	39.0	-	-	-
132	MJT-4	56.0	59.0	3.0	90	0.40	142.0	13.80	56.00	29.0	-	-	-
133	MJT-4	59.0	61.0	2.0	110	24.00	160.0	20.00	56.00	4.0	-	-	-
134	MJT-4	61.0	62.0	1.0	80	0.20	168.0	11.80	52.00	50.0	2.046	0.129	1.917
135	MJT-4	62.0	63.0	1.0	40	<0.10	112.0	13.20	46.00	<2.0	1.926	0.076	1.850
136	MJT-4	63.0	64.0	1.0	30	0.80	182.0	17.60	60.00	14.0	2.926	0.109	2.817
137	MJT-4	64.0	65.0	1.0	110	<0.10	220.0	10.00	46.00	<2.0	1.134	0.069	1.065
138	MJT-4	65.0	67.0	2.0	140	0.40	346.0	20.40	52.00	20.0	-	-	-
139	MJT-4	67.0	70.5	3.5	90	0.40	122.0	12.80	58.00	5.0	-	-	-
140	MJT-4	70.5	72.5	2.0	20	<0.10	132.0	10.20	52.00	2.0	-	-	-
141	MJT-4	72.5	75.0	2.5	20	0.40	92.0	11.40	66.00	2.0	-	-	-
142	MJT-4	75.0	78.0	3.0	50	<0.10	93.6	4.00	25.03	21.0	1.351	0.044	1.307
143	MJT-4	78.0	81.0	3.0	37	0.15	43.2	3.00	37.57	<2.0	-	-	-
144	MJT-4	81.0	84.0	3.0	50	<0.10	56.0	2.00	45.15	<2.0	-	-	-
145	MJT-4	84.0	87.0	3.0	53	<0.10	138.7	4.75	27.15	<2.0	-	-	-
146	MJT-4	87.0	90.0	3.0	80	<0.10	202.4	3.00	24.92	<2.0	-	-	-
147	MJT-4	90.0	92.0	2.0	47	<0.10	53.9	4.65	36.52	2.0	-	-	-
148	MJT-4	92.0	93.0	1.0	67	<0.10	36.2	6.85	44.52	<2.0	-	-	-
149	MJT-4	93.0	94.0	1.0	57	<0.10	27.1	12.90	41.37	<2.0	-	-	-
150	MJT-4	94.0	95.0	1.0	57	<0.10	66.0	14.10	45.08	<2.0	-	-	-
151	MJT-4	95.0	98.0	3.0	470	<0.10	1308.0	7.55	33.72	<2.0	-	-	-
152	MJT-4	98.0	101.0	3.0	77	<0.10	148.7	8.70	29.40	<2.0	-	-	-
153	MJT-4	101.0	104.0	3.0	130	0.10	143.0	14.50	27.95	12.0	-	-	-
154	MJT-4	104.0	105.0	1.0	120	0.10	376.5	4.00	23.20	33.0	-	-	-
155	MJT-4	105.0	106.0	1.0	67	<0.10	149.1	4.00	26.36	<2.0	-	-	-
156	MJT-4	106.0	107.0	1.0	80	<0.10	253.5	4.85	22.72	<2.0	1.841	0.098	1.743
157	MJT-4	107.0	110.0	3.0	50	<0.10	131.5	5.55	27.01	<2.0	1.556	0.095	1.461
158	MJT-4	110.0	113.0	3.0	47	0.10	70.4	5.05	58.81	2.0	-	-	-
159	MJT-4	113.0	116.0	3.0	57	<0.10	78.5	4.00	41.60	<2.0	-	-	-
160	MJT-4	116.0	119.0	3.0	73	<0.10	122.0	7.55	42.50	<2.0	-	-	-
161	MJT-4	119.0	122.0	3.0	57	<0.10	64.1	4.50	50.19	2.0	-	-	-
162	MJT-4	122.0	125.0	3.0	63	<0.10	31.5	6.35	50.87	<2.0	-	-	-
163	MJT-4	125.0	128.0	3.0	57	<0.10	36.2	4.00	37.28	2.0	-	-	-
164	MJT-4	128.0	131.0	3.0	60	<0.10	74.5	9.95	39.58	2.0	-	-	-
165	MJT-4	131.0	133.0	2.0	50	0.95	151.2	5.00	31.24	<2.0	-	-	-
166	MJT-4	133.0	134.0	1.0	47	<0.10	110.6	6.85	20.57	<2.0	3.415	0.092	3.323
167	MJT-4	134.0	135.0	1.0	67	<0.10	252.5	4.00	22.95	<2.0	1.630	0.054	1.576
168	MJT-4	135.0	136.0	1.0	80	<0.10	162.8	6.25	23.78	3.0	-	-	-
169	MJT-4	136.0	139.0	3.0	37	<0.10	138.6	7.10	23.68	22.0	-	-	-
170	MJT-4	139.0	142.0	3.0	43	<0.10	122.7	7.50	26.68	9.0	-	-	-
171	MJT-4	142.0	145.0	3.0	67	<0.10	82.5	4.50	25.60	<2.0	-	-	-
172	MJT-4	145.0	148.0	3.0	70	<0.10	89.1	3.00	25.58	3.0	-	-	-
173	MJT-4	148.0	151.0	3.0	110	0.10	282.3	13.25	27.95	28.0	-	-	-
174	MJT-4	151.0	154.0	3.0	137	0.10	934.0	5.40	35.53	6.0	-	-	-
175	MJT-4	154.0	157.0	3.0	10	<0.10	62.0	15.40	57.80	4.0	-	-	-
176	MJT-4	157.0	160.0	3.0	10	<0.10	58.0	11.00	41.40	<2.0	-	-	-
177	MJT-4	160.0	163.0	3.0	80	<0.10	102.0	14.20	49.20	2.0	-	-	-
178	MJT-4	163.0	167.0	4.0	<10	<0.10	88.0	9.40	34.80	5.0	-	-	-
179	MJT-4	167.0	169.0	2.0	27	<0.10	504.0	8.80	33.60	<2.0	1.773	0.069	1.704
180	MJT-4	169.0	172.0	3.0	10	<0.10	144.0	9.60	40.20	6.0	-	-	-
181	MJT-4	172.0	175.0	3.0	20	<0.10	132.0	10.20	31.00	2.0	-	-	-
182	MJT-4	175.0	178.0	3.0	17	<0.10	222.0	9.20	36.60	2.0	-	-	-
183	MJT-4	178.0	181.0	3.0	<10	0.10	66.0	6.80	41.40	7.0	-	-	-
184	MJT-4	181.0	184.0	3.0	43	<0.10	110.0	17.80	84.80	5.0	-	-	-
185	MJT-4	184.0	187.0	3.0	170	0.20	680.0	9.00	43.00	19.0	-	-	-
186	MJT-4	187.0	190.0	3.0	<10	14.00	188.0	11.80	51.20	5.0	-	-	-
187	MJT-4	190.0	193.0	3.0	<10	1.20	258.0	29.60	72.80	13.0	-	-	-
188	MJT-4	193.0	196.0	3.0	<10	<0.10	136.0	10.40	37.40	7.0	-	-	-
189	MJT-4	196.0	198.0	2.0	30	42.20	302.0	7.60	43.80	2.0	-	-	-
190	MJT-4	198.0	200.0	2.0	33	<0.10	218.0	27.80	56.00	19.0	-	-	-
191	MJT-4	200.0	203.0	3.0	<10	<0.10	204.0	10.00	59.40	7.0	-	-	-
192	MJT-4	203.0	206.0	3.0	<10	7.80	158.0	40.80	83.00	9.0	-	-	-

Appendix 9 Assay results of the drill core samples, 4/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
193	MJT-4	206.0	209.0	3.0	<10	3.80	129.2	10.80	62.73	5.0	-	-	-
194	MJT-4	209.0	210.0	1.0	10	<0.10	88.0	8.20	44.80	7.0	-	-	-
195	MJT-4	210.0	211.0	1.0	<10	<0.10	176.0	80.20	74.20	5.0	-	-	-
196	MJT-4	211.0	212.0	1.0	37	6.40	254.0	45.00	80.20	6.0	-	-	-
197	MJT-4	212.0	215.0	3.0	<10	2.20	150.0	10.40	49.60	13.0	-	-	-
198	MJT-4	215.0	218.0	3.0	<10	6.20	172.0	50.00	65.60	14.0	-	-	-
199	MJT-4	218.0	221.0	3.0	<10	<0.10	52.0	8.00	69.60	6.0	-	-	-
200	MJT-4	221.0	224.0	3.0	<10	<0.10	126.0	9.20	54.00	<2.0	-	-	-
201	MJT-4	224.0	227.0	3.0	<10	4.20	133.3	82.20	63.40	<2.0	-	-	-
202	MJT-4	227.0	230.0	3.0	<10	<0.10	128.0	15.80	56.99	<2.0	-	-	-
203	MJT-4	230.0	233.0	3.0	<10	<0.10	80.0	8.40	52.00	<2.0	-	-	-
204	MJT-4	233.0	236.0	3.0	<10	47.60	54.0	17.80	47.80	<2.0	-	-	-
205	MJT-4	236.0	239.0	3.0	17	<0.10	52.0	10.60	63.60	<2.0	-	-	-
206	MJT-4	239.0	242.0	3.0	<10	<0.10	62.0	7.80	56.40	<2.0	-	-	-
207	MJT-4	242.0	245.0	3.0	<10	<0.10	60.0	13.40	61.00	<2.0	-	-	-
208	MJT-4	245.0	248.0	3.0	<10	<0.10	80.0	8.20	59.00	5.0	-	-	-
209	MJT-4	248.0	250.0	2.0	67	0.40	436.0	5.60	51.20	<2.0	-	-	-
210	MJT-5	0.0	3.0	3.0	<10	0.20	122.0	12.00	89.00	<2.0	-	-	-
211	MJT-5	3.0	6.0	3.0	40	<0.10	59.0	9.00	40.00	<2.0	-	-	-
212	MJT-5	6.0	9.0	3.0	<10	0.60	370.0	19.00	53.00	<2.0	-	-	-
213	MJT-5	9.0	12.0	3.0	<10	<0.10	251.0	14.00	55.00	<2.0	-	-	-
214	MJT-5	12.0	15.0	3.0	<10	3.40	1249.0	27.00	89.00	<2.0	-	-	-
215	MJT-5	15.0	18.0	3.0	<10	2.20	268.0	18.00	60.00	<2.0	-	-	-
216	MJT-5	18.0	21.0	3.0	30	<0.10	127.0	29.00	51.00	<2.0	-	-	-
217	MJT-5	21.0	24.0	3.0	<10	<0.10	52.0	17.00	44.00	<2.0	-	-	-
218	MJT-5	24.0	27.0	3.0	10	<0.10	88.0	15.00	49.00	<2.0	-	-	-
219	MJT-5	27.0	30.0	3.0	<10	0.60	179.0	11.00	38.00	2.0	-	-	-
220	MJT-5	30.0	33.0	3.0	<10	<0.10	122.0	19.00	47.00	12.0	-	-	-
221	MJT-5	33.0	36.0	3.0	<10	<0.10	87.0	10.00	42.00	<2.0	-	-	-
222	MJT-5	36.0	39.0	3.0	<10	<0.10	84.0	7.00	38.00	<2.0	-	-	-
223	MJT-5	39.0	42.0	3.0	10	<0.10	56.0	15.00	48.00	<2.0	-	-	-
224	MJT-5	42.0	45.0	3.0	<10	2.80	78.0	12.00	45.00	<2.0	-	-	-
225	MJT-5	45.0	48.0	3.0	30	<0.10	222.0	14.00	46.00	6.0	-	-	-
226	MJT-5	48.0	51.0	3.0	10	<0.10	92.0	13.00	39.00	<2.0	-	-	-
227	MJT-5	51.0	54.0	3.0	20	<0.10	110.0	30.00	55.00	<2.0	-	-	-
228	MJT-5	54.0	57.0	3.0	<10	<0.10	68.0	12.00	39.00	<2.0	-	-	-
229	MJT-5	57.0	60.0	3.0	20	<0.10	56.0	16.00	47.00	<2.0	-	-	-
230	MJT-5	60.0	63.0	3.0	10	<0.10	57.0	26.00	47.00	3.0	-	-	-
231	MJT-5	63.0	66.0	3.0	20	<0.10	21.0	9.00	43.00	<2.0	-	-	-
232	MJT-5	66.0	69.0	3.0	20	<0.10	117.0	12.00	45.00	68.0	-	-	-
233	MJT-5	69.0	72.0	3.0	20	<0.10	261.0	15.00	60.00	15.0	-	-	-
234	MJT-5	72.0	75.0	3.0	20	<0.10	81.0	29.00	44.00	<2.0	-	-	-
235	MJT-5	75.0	78.0	3.0	20	<0.10	202.0	17.00	42.00	<2.0	-	-	-
236	MJT-5	78.0	81.0	3.0	30	<0.10	66.0	9.00	44.00	3.0	-	-	-
237	MJT-5	81.0	84.0	3.0	30	3.80	86.0	26.00	52.00	<2.0	-	-	-
238	MJT-5	84.0	85.0	1.0	20	<0.10	20.0	11.00	47.00	<2.0	-	-	-
239	MJT-5	85.0	85.5	0.5	20	<0.10	193.0	55.00	57.00	<2.0	-	-	-
240	MJT-5	85.5	88.0	2.5	20	1.20	200.0	25.00	58.00	33.0	-	-	-
241	MJT-5	88.0	91.0	3.0	20	<0.10	95.0	12.00	51.00	<2.0	-	-	-
242	MJT-5	91.0	92.0	1.0	30	2.00	120.0	84.00	63.00	<2.0	-	-	-
243	MJT-5	92.0	95.0	3.0	20	1.20	46.0	12.00	54.00	<2.0	-	-	-
244	MJT-5	95.0	98.0	3.0	10	<0.10	160.0	27.00	53.00	<2.0	-	-	-
245	MJT-5	98.0	101.0	3.0	20	<0.10	115.0	32.00	54.00	25.0	-	-	-
246	MJT-5	101.0	104.0	3.0	20	<0.10	24.0	8.00	39.00	16.0	-	-	-
247	MJT-5	104.0	107.0	3.0	10	<0.10	51.0	47.00	54.00	<2.0	-	-	-
248	MJT-5	107.0	110.0	3.0	20	<0.10	28.0	17.00	50.00	13.0	0.160	<0.01	0.160
249	MJT-5	110.0	113.0	3.0	20	<0.10	51.0	11.00	42.00	66.0	-	-	-
250	MJT-5	113.0	116.0	3.0	30	<0.10	50.0	10.00	41.00	23.0	-	-	-
251	MJT-5	116.0	119.0	3.0	10	1.00	100.0	9.00	35.00	15.0	-	-	-
252	MJT-5	119.0	121.4	2.4	20	<0.10	54.0	15.00	46.00	27.0	-	-	-
253	MJT-5	121.4	123.6	2.2	20	<0.10	53.0	30.00	55.00	34.0	-	-	-
254	MJT-5	123.6	127.0	3.4	30	<0.10	109.0	25.00	55.00	26.0	-	-	-
255	MJT-5	127.0	130.0	3.0	30	1.60	206.0	18.00	42.00	17.0	-	-	-
256	MJT-5	130.0	134.2	4.2	20	<0.10	81.0	8.00	36.00	22.0	-	-	-

Appendix 9

Assay results of the drill core samples, 5/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
257	MJT-5	134.2	135.0	0.8	20	<0.10	42.0	4.00	62.00	12.0	-	-	-
258	MJT-5	135.0	138.0	3.0	20	1.00	69.0	9.00	39.00	12.0	-	-	-
259	MJT-5	138.0	141.0	3.0	40	<0.10	35.0	13.00	41.00	17.0	-	-	-
260	MJT-5	141.0	142.5	1.5	20	0.60	60.0	19.00	61.00	16.0	-	-	-
261	MJT-5	142.5	144.6	2.1	10	0.60	44.0	31.00	85.00	14.0	-	-	-
262	MJT-5	144.6	147.5	2.9	10	1.40	113.0	39.00	81.00	7.0	-	-	-
263	MJT-5	147.5	150.0	2.5	20	0.40	44.0	25.00	62.00	<2.0	-	-	-
264	MJT-5	150.0	153.0	3.0	70	0.20	26.0	16.00	52.00	40.0	-	-	-
265	MJT-5	153.0	156.0	3.0	50	<0.10	34.0	14.00	59.00	<2.0	-	-	-
266	MJT-5	156.0	159.0	3.0	40	0.20	67.0	16.00	54.00	54.0	-	-	-
267	MJT-5	159.0	162.0	3.0	30	<0.10	19.0	14.00	56.00	<2.0	-	-	-
268	MJT-5	162.0	165.0	3.0	60	<0.10	26.0	12.00	50.00	52.0	0.026	<0.01	0.030
269	MJT-5	165.0	168.0	3.0	40	<0.10	47.0	12.00	66.00	<2.0	-	-	-
270	MJT-5	168.0	171.0	3.0	50	<0.10	82.0	18.00	69.00	<2.0	-	-	-
271	MJT-5	171.0	174.0	3.0	50	<0.10	22.0	15.00	57.00	<2.0	-	-	-
272	MJT-5	174.0	177.0	3.0	140	5.40	146.0	324.00	305.00	11.0	-	-	-
273	MJT-5	177.0	180.0	3.0	80	3.40	183.0	187.00	270.00	23.0	-	-	-
274	MJT-5	180.0	183.0	3.0	60	0.40	147.0	36.00	237.00	16.0	-	-	-
275	MJT-5	183.0	186.0	3.0	50	<0.10	83.0	16.00	131.00	34.0	-	-	-
276	MJT-5	186.0	189.0	3.0	30	0.20	48.0	16.00	67.00	18.0	0.117	<0.01	0.117
277	MJT-5	189.0	192.0	3.0	50	<0.10	22.0	14.00	56.00	20.0	-	-	-
278	MJT-5	192.0	195.0	3.0	40	0.20	30.0	17.00	53.00	26.0	-	-	-
279	MJT-5	195.0	198.0	3.0	30	<0.10	27.0	34.00	73.00	<2.0	-	-	-
280	MJT-5	198.0	201.0	3.0	30	<0.10	17.0	20.00	66.00	<2.0	-	-	-
281	MJT-5	201.0	204.0	3.0	50	0.20	36.0	14.00	53.00	<2.0	-	-	-
282	MJT-5	204.0	207.0	3.0	30	0.80	35.0	37.00	49.00	13.0	-	-	-
283	MJT-5	207.0	208.0	1.0	30	0.20	37.0	19.00	96.00	<2.0	-	-	-
284	MJT-5	208.0	210.0	2.0	120	0.80	123.0	23.00	224.00	25.0	-	-	-
285	MJT-5	210.0	211.0	1.0	110	0.80	134.0	29.00	104.00	26.0	-	-	-
286	MJT-5	211.0	214.0	3.0	130	1.00	192.0	53.00	132.00	26.0	1.480	<0.01	1.480
287	MJT-5	214.0	217.0	3.0	100	0.20	365.0	20.00	89.00	81.0	-	-	-
288	MJT-5	217.0	219.0	2.0	120	0.40	289.0	26.00	71.00	37.0	-	-	-
289	MJT-5	219.0	220.0	1.0	280	14.00	2064.0	1060.00	403.00	85.0	-	-	-
290	MJT-5	220.0	221.0	1.0	200	3.40	388.0	279.00	120.00	695.0	-	-	-
291	MJT-5	221.0	222.0	1.0	100	0.20	119.0	41.00	87.00	27.0	-	-	-
292	MJT-5	222.0	223.0	1.0	100	0.80	296.0	40.00	91.00	20.0	-	-	-
293	MJT-5	223.0	226.0	3.0	100	0.40	166.0	31.00	132.00	8.0	-	-	-
294	MJT-5	226.0	229.0	3.0	140	0.60	280.0	35.00	175.00	49.0	-	-	-
295	MJT-5	229.0	232.0	3.0	140	<0.10	110.0	18.00	82.00	4.0	-	-	-
296	MJT-5	232.0	234.0	2.0	110	0.60	189.0	25.00	71.00	108.0	0.740	0.011	0.729
297	MJT-5	234.0	235.0	1.0	90	0.60	141.0	20.00	72.00	452.0	-	-	-
298	MJT-5	235.0	238.0	3.0	100	0.60	184.0	30.00	90.00	7.0	-	-	-
299	MJT-5	238.0	241.0	3.0	130	0.40	202.0	19.00	67.00	<2.0	-	-	-
300	MJT-5	241.0	244.0	3.0	90	1.40	152.0	23.00	119.00	6.0	-	-	-
301	MJT-5	244.0	247.0	3.0	120	0.80	108.0	30.00	96.00	6.0	-	-	-
302	MJT-5	247.0	250.0	3.0	112	0.80	140.0	26.00	71.00	6.0	-	-	-
303	MJT-5	250.0	253.0	3.0	100	1.80	146.0	82.00	209.00	19.0	-	-	-
304	MJT-5	253.0	256.0	3.0	11	0.80	159.0	33.00	164.00	<2.0	-	-	-
305	MJT-5	256.0	259.0	3.0	10	1.20	90.0	45.00	163.00	27.0	-	-	-
306	MJT-5	259.0	262.0	3.0	90	0.80	66.0	20.00	74.00	16.0	-	-	-
307	MJT-5	262.0	265.0	3.0	20	1.60	85.0	44.00	175.00	7.0	-	-	-
308	MJT-5	265.0	268.0	3.0	10	1.20	152.0	41.00	185.00	19.0	-	-	-
309	MJT-5	268.0	271.0	3.0	10	2.20	231.0	85.00	98.00	9.0	-	-	-
310	MJT-5	271.0	274.0	3.0	10	1.40	268.0	131.00	107.00	94.0	-	-	-
311	MJT-5	274.0	277.0	3.0	10	3.20	98.0	542.00	66.00	12.0	-	-	-
312	MJT-5	277.0	280.0	3.0	10	1.20	59.0	28.00	85.00	59.0	-	-	-
313	MJT-5	280.0	283.0	3.0	10	0.40	58.0	25.00	77.00	80.0	-	-	-
314	MJT-5	283.0	286.0	3.0	10	1.00	64.0	22.00	91.00	13.0	-	-	-
315	MJT-5	286.0	289.0	3.0	10	2.80	33.0	20.00	98.00	96.0	-	-	-
316	MJT-5	289.0	292.0	3.0	20	2.00	59.0	20.00	104.00	<2.0	-	-	-
317	MJT-5	292.0	295.0	3.0	10	0.40	15.0	15.00	65.00	29.0	-	-	-
318	MJT-5	295.0	298.0	3.0	10	1.00	18.0	19.00	60.00	11.0	-	-	-
319	MJT-5	298.0	300.0	2.0	10	0.40	12.0	15.00	80.00	33.0	-	-	-
320	MJT-6	0.0	3.5	3.5	10	<0.10	88.0	6.30	31.50	<2.0	-	-	-

Appendix 9 Assay results of the drill core samples, 6/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
321	MJT-6	3.5	6.0	2.5	10	0.40	40.0	5.45	11.50	<2.0	-	-	-
322	MJT-6	6.0	9.0	3.0	10	0.10	44.0	6.95	10.50	<2.0	-	-	-
323	MJT-6	9.0	12.0	3.0	20	0.60	52.5	7.70	16.50	<2.0	-	-	-
324	MJT-6	12.0	15.0	3.0	20	0.15	30.0	17.75	23.00	<2.0	-	-	-
325	MJT-6	15.0	16.0	1.0	20	0.90	44.5	21.45	33.00	<2.0	-	-	-
326	MJT-6	16.0	17.0	1.0	50	0.15	49.5	10.40	22.00	7.0	-	-	-
327	MJT-6	17.0	18.0	1.0	50	6.45	44.5	7.40	38.00	<2.0	0.037	<0.01	0.037
328	MJT-6	18.0	19.0	1.0	40	0.25	36.5	6.35	26.00	<2.0	<0.01	<0.01	<0.01
329	MJT-6	19.0	20.0	1.0	60	0.45	33.5	6.60	25.00	2.0	-	-	-
330	MJT-6	20.0	21.0	1.0	30	0.45	27.5	8.40	14.00	19.0	-	-	-
331	MJT-6	21.0	24.0	3.0	20	0.10	37.0	6.85	34.00	<2.0	-	-	-
332	MJT-6	24.0	27.0	3.0	10	0.35	28.5	9.35	43.50	<2.0	-	-	-
333	MJT-6	27.0	30.0	3.0	10	<0.10	22.0	3.65	70.00	<2.0	-	-	-
334	MJT-6	30.0	32.7	2.7	43	<0.10	20.0	11.60	55.80	<2.0	-	-	-
335	MJT-6	32.7	36.0	3.3	50	<0.10	24.0	16.20	60.60	<2.0	-	-	-
336	MJT-6	36.0	39.0	3.0	50	<0.10	24.0	9.60	55.80	<2.0	-	-	-
337	MJT-6	39.0	42.0	3.0	<10	<0.10	30.0	12.80	57.60	<2.0	-	-	-
338	MJT-6	42.0	45.0	3.0	23	<0.10	30.0	11.00	58.40	<2.0	-	-	-
339	MJT-6	45.0	48.0	3.0	23	0.80	36.0	152.60	229.80	<2.0	-	-	-
340	MJT-6	48.0	49.0	1.0	30	<0.10	78.0	191.60	81.20	<2.0	-	-	-
341	MJT-6	49.0	50.0	1.0	27	4.40	360.0	839.60	288.00	7.0	-	-	-
342	MJT-6	50.0	51.0	1.0	17	1.20	59.5	79.40	99.20	<2.0	-	-	-
343	MJT-6	51.0	52.0	1.0	23	0.80	46.0	108.60	98.60	<2.0	1.509	0.062	1.447
344	MJT-6	52.0	55.0	3.0	17	0.80	26.0	14.00	73.20	<2.0	-	-	-
345	MJT-6	55.0	58.0	3.0	10	<0.10	24.0	11.40	60.40	<2.0	-	-	-
346	MJT-6	58.0	61.0	3.0	20	0.20	24.0	9.60	57.80	<2.0	-	-	-
347	MJT-6	61.0	62.0	1.0	20	0.40	18.0	15.60	60.20	<2.0	1.159	0.006	1.153
348	MJT-6	62.0	63.0	1.0	17	0.20	38.0	15.20	63.40	<2.0	1.306	0.081	1.225
349	MJT-6	63.0	67.0	4.0	<10	<0.10	4.0	7.60	125.40	<2.0	-	-	-
350	MJT-6	67.0	71.0	4.0	10	<0.10	32.0	8.40	111.20	<2.0	-	-	-
351	MJT-6	71.0	74.0	3.0	13	<0.10	18.0	7.20	76.20	<2.0	-	-	-
352	MJT-6	74.0	77.0	3.0	23	1.80	168.0	18.00	73.20	<2.0	-	-	-
353	MJT-6	77.0	80.0	3.0	27	3.80	62.0	14.80	81.00	<2.0	-	-	-
354	MJT-6	80.0	83.0	3.0	33	1.60	50.0	10.00	74.20	2.0	-	-	-
355	MJT-6	83.0	86.0	3.0	<10	1.00	32.0	8.80	87.60	<2.0	-	-	-
356	MJT-6	86.0	89.0	3.0	<10	4.20	40.0	24.20	94.20	<2.0	-	-	-
357	MJT-6	89.0	92.0	3.0	17	0.40	34.0	20.80	86.40	<2.0	-	-	-
358	MJT-6	92.0	95.0	3.0	20	2.20	18.0	22.80	81.00	<2.0	-	-	-
359	MJT-6	95.0	96.0	1.0	40	0.80	60.0	85.00	75.20	<2.0	-	-	-
360	MJT-6	96.0	97.0	1.0	47	1.40	54.0	80.40	72.00	<2.0	1.199	0.040	1.159
361	MJT-6	97.0	100.0	3.0	20	0.60	34.0	38.60	65.40	<2.0	-	-	-
362	MJT-6	100.0	103.0	3.0	30	5.60	32.0	48.60	89.40	<2.0	-	-	-
363	MJT-6	103.0	106.0	3.0	33	1.00	72.0	33.60	71.40	<2.0	-	-	-
364	MJT-6	106.0	109.0	3.0	23	0.60	36.0	39.20	63.40	<2.0	-	-	-
365	MJT-6	109.0	112.0	3.0	43	0.80	40.0	18.40	60.20	<2.0	-	-	-
366	MJT-6	112.0	113.0	1.0	33	30.40	24.0	20.20	45.20	<2.0	-	-	-
367	MJT-6	113.0	116.0	3.0	37	0.60	34.0	12.40	77.20	<2.0	-	-	-
368	MJT-6	116.0	119.0	3.0	37	18.40	166.0	33.60	44.80	<2.0	-	-	-
369	MJT-6	119.0	121.0	2.0	37	1.60	48.0	221.00	65.20	<2.0	-	-	-
370	MJT-6	121.0	123.0	2.0	23	1.60	20.0	14.00	56.20	<2.0	1.504	<0.01	1.500
371	MJT-6	123.0	124.0	1.0	67	4.60	152.0	818.00	66.80	<2.0	3.164	0.154	3.010
372	MJT-6	124.0	127.0	3.0	37	2.80	66.0	15.60	48.00	<2.0	-	-	-
373	MJT-6	127.0	130.0	3.0	47	1.20	120.0	24.80	57.20	<2.0	-	-	-
374	MJT-6	130.0	133.0	3.0	23	1.60	152.0	36.40	71.00	<2.0	-	-	-
375	MJT-6	133.0	136.0	3.0	23	3.20	120.0	37.00	74.00	<2.0	-	-	-
376	MJT-6	136.0	139.0	3.0	40	0.80	56.0	20.80	63.40	<2.0	-	-	-
377	MJT-6	139.0	142.0	3.0	67	0.20	80.0	17.40	39.00	<2.0	-	-	-
378	MJT-6	142.0	143.0	1.0	50	<0.10	112.0	18.00	41.20	<2.0	2.518	0.077	2.441
379	MJT-6	143.0	144.0	1.0	43	0.60	72.0	12.80	42.80	<2.0	2.235	0.100	2.135
380	MJT-6	144.0	145.0	1.0	147	2.00	66.0	130.20	35.80	<2.0	3.470	0.161	3.309
381	MJT-6	145.0	146.0	1.0	93	0.10	95.0	12.00	40.00	<2.0	-	-	-
382	MJT-6	146.0	147.0	1.0	347	0.40	94.0	25.60	36.20	<2.0	-	-	-
383	MJT-6	147.0	148.0	1.0	137	<0.10	66.0	12.20	36.40	<2.0	-	-	-
384	MJT-6	148.0	151.0	3.0	27	0.40	54.0	10.80	42.40	<2.0	-	-	-

Appendix 9 Assay results of the drill core samples, 7/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
385	MJT-6	151.0	152.0	1.0	47	0.20	84.0	15.80	50.20	<2.0	-	-	-
386	MJT-6	152.0	153.0	1.0	40	0.60	52.0	12.60	64.80	<2.0	-	-	-
387	MJT-6	153.0	154.0	1.0	17	2.20	38.0	11.60	40.60	<2.0	-	-	-
388	MJT-6	154.0	157.0	3.0	50	0.40	34.0	12.40	35.40	<2.0	2.259	0.074	2.185
389	MJT-6	157.0	160.0	3.0	17	1.80	110.0	14.00	43.20	<2.0	-	-	-
390	MJT-6	160.0	163.0	3.0	17	1.80	58.0	14.40	43.40	<2.0	-	-	-
391	MJT-6	163.0	166.0	3.0	33	<0.10	56.0	15.20	46.00	<2.0	-	-	-
392	MJT-6	166.0	169.0	3.0	17	<0.10	56.0	21.60	39.60	<2.0	-	-	-
393	MJT-6	169.0	172.0	3.0	<10	0.80	78.0	24.00	53.40	<2.0	-	-	-
394	MJT-6	172.0	175.0	3.0	13	<0.10	52.0	23.60	55.60	<2.0	-	-	-
395	MJT-6	175.0	178.0	3.0	47	<0.10	52.0	40.20	58.60	<2.0	-	-	-
396	MJT-6	178.0	181.0	3.0	10	0.60	32.0	41.00	57.80	<2.0	-	-	-
397	MJT-6	181.0	184.0	3.0	20	<0.10	52.0	31.60	51.20	<2.0	-	-	-
398	MJT-6	184.0	186.0	2.0	20	<0.10	82.0	24.80	47.20	<2.0	-	-	-
399	MJT-6	186.0	187.0	1.0	27	<0.10	66.0	21.00	48.80	3.0	-	-	-
400	MJT-6	187.0	188.0	1.0	37	0.20	46.0	20.60	39.20	<2.0	-	-	-
401	MJT-6	188.0	189.0	1.0	<10	0.80	44.0	31.00	36.80	93.0	-	-	-
402	MJT-6	189.0	190.0	1.0	20	<0.10	46.0	17.60	35.60	2.0	-	-	-
403	MJT-6	190.0	193.0	3.0	<10	0.20	24.0	29.40	46.20	8.0	-	-	-
404	MJT-6	193.0	196.0	3.0	<10	<0.10	34.0	32.20	48.20	8.0	-	-	-
405	MJT-6	196.0	199.0	3.0	<10	<0.10	26.0	31.60	46.20	7.0	-	-	-
406	MJT-6	199.0	202.0	3.0	<10	<0.10	34.0	31.00	40.80	12.0	-	-	-
407	MJT-6	202.0	203.0	1.0	<10	<0.10	42.0	22.40	40.80	<2.0	-	-	-
408	MJT-6	203.0	206.0	3.0	<10	<0.10	34.0	27.80	52.00	14.0	-	-	-
409	MJT-6	206.0	209.0	3.0	<10	<0.10	18.0	26.00	42.60	7.0	-	-	-
410	MJT-6	209.0	212.0	3.0	<10	1.40	24.0	17.60	43.00	6.0	-	-	-
411	MJT-6	212.0	215.0	3.0	<10	<0.10	28.0	17.80	46.40	2.0	-	-	-
412	MJT-6	215.0	218.0	3.0	<10	0.20	26.0	34.40	47.20	7.0	-	-	-
413	MJT-6	218.0	221.0	3.0	<10	0.40	38.0	29.00	43.40	11.0	-	-	-
414	MJT-6	221.0	224.0	3.0	<10	0.20	34.0	29.40	44.20	23.0	-	-	-
415	MJT-6	224.0	225.0	1.0	<10	<0.10	32.0	10.60	39.40	14.0	-	-	-
416	MJT-6	225.0	226.0	1.0	<10	<0.10	28.0	12.40	29.40	<2.0	2.123	0.135	1.988
417	MJT-6	226.0	227.0	1.0	30	0.20	24.0	15.40	43.80	14.0	-	-	-
418	MJT-6	227.0	228.0	1.0	<10	0.40	18.0	16.40	31.80	<2.0	1.501	0.073	1.428
419	MJT-6	228.0	229.0	1.0	30	0.20	44.0	15.20	33.00	<2.0	1.823	0.104	1.719
420	MJT-6	229.0	230.0	1.0	<10	<0.10	54.0	11.60	39.20	7.0	-	-	-
421	MJT-6	230.0	233.0	3.0	<10	<0.10	42.0	12.40	40.60	15.0	-	-	-
422	MJT-6	233.0	236.0	3.0	<10	<0.10	44.0	15.00	44.40	8.0	-	-	-
423	MJT-6	236.0	239.0	3.0	<10	<0.10	72.0	15.80	46.60	15.0	-	-	-
424	MJT-6	239.0	242.0	3.0	30	<0.10	86.0	11.40	33.00	14.0	-	-	-
425	MJT-6	242.0	245.0	3.0	37	<0.10	126.0	16.80	34.80	8.0	-	-	-
426	MJT-6	245.0	248.0	3.0	27	<0.10	70.0	16.60	42.00	12.0	-	-	-
427	MJT-6	248.0	250.0	2.0	<10	0.60	78.0	15.80	36.20	<2.0	1.656	0.041	1.615
428	MJT-7	0.0	3.0	3.0	30	1.20	44.0	22.60	104.60	5.0	-	-	-
429	MJT-7	3.0	6.0	3.0	20	0.20	32.0	24.00	125.40	6.0	-	-	-
430	MJT-7	6.0	9.0	3.0	27	0.20	18.0	20.80	79.20	7.0	-	-	-
431	MJT-7	9.0	12.0	3.0	17	0.80	16.0	18.60	52.00	4.0	-	-	-
432	MJT-7	12.0	15.0	3.0	13	0.40	18.0	24.80	49.60	2.0	-	-	-
433	MJT-7	15.0	18.0	3.0	40	2.40	18.0	19.80	66.40	4.0	-	-	-
434	MJT-7	18.0	21.0	3.0	30	0.80	22.0	30.60	63.20	3.0	-	-	-
435	MJT-7	21.0	23.0	2.0	23	1.60	26.0	23.60	61.40	2.0	-	-	-
436	MJT-7	23.0	26.0	3.0	23	0.40	98.0	28.00	95.40	3.0	-	-	-
437	MJT-7	26.0	29.0	3.0	30	1.20	32.0	20.80	54.80	8.0	-	-	-
438	MJT-7	29.0	32.0	3.0	20	0.80	26.0	19.00	59.80	3.0	-	-	-
439	MJT-7	32.0	35.0	3.0	37	0.80	48.0	19.20	69.20	7.0	-	-	-
440	MJT-7	35.0	36.2	1.2	50	16.60	46.0	16.00	59.00	25.0	-	-	-
441	MJT-7	36.2	38.2	2.0	33	0.40	42.0	13.20	65.80	<2.0	-	-	-
442	MJT-7	38.2	40.0	1.8	37	1.20	18.0	14.60	62.20	<2.0	-	-	-
443	MJT-7	40.0	41.8	1.8	23	0.20	52.0	13.20	54.80	<2.0	-	-	-
444	MJT-7	41.8	43.4	1.6	30	0.80	46.0	131.00	68.40	<2.0	-	-	-
445	MJT-7	43.4	46.0	2.6	27	0.20	16.0	27.00	42.00	<2.0	-	-	-
446	MJT-7	46.0	49.0	3.0	27	0.20	24.0	23.80	53.20	<2.0	-	-	-
447	MJT-7	49.0	52.0	3.0	33	0.60	24.0	23.00	57.00	<2.0	-	-	-
448	MJT-7	52.0	54.0	2.0	13	0.60	38.0	15.40	53.20	<2.0	-	-	-

Appendix 9 Assay results of the drill core samples, 8/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
449	MJT-7	54.0	55.4	1.4	13	0.60	56.0	17.60	95.80	<2.0	-	-	-
450	MJT-7	55.4	57.6	2.2	20	0.60	66.0	22.40	63.80	<2.0	-	-	-
451	MJT-7	57.6	59.6	2.0	17	1.40	24.0	11.80	71.00	5.0	-	-	-
452	MJT-7	59.6	63.0	3.4	10	15.80	19.8	29.00	57.40	13.0	-	-	-
453	MJT-7	63.0	66.0	3.0	20	<0.10	21.4	16.60	54.60	14.0	-	-	-
454	MJT-7	66.0	69.0	3.0	17	0.20	14.4	16.00	49.60	9.0	-	-	-
455	MJT-7	69.0	72.0	3.0	13	1.00	13.4	16.00	42.00	7.0	-	-	-
456	MJT-7	72.0	75.0	3.0	13	0.20	10.6	15.80	35.20	13.0	-	-	-
457	MJT-7	75.0	78.0	3.0	23	0.20	27.8	20.20	53.60	19.0	-	-	-
458	MJT-7	78.0	81.0	3.0	33	<0.10	25.0	84.60	84.80	<2.0	-	-	-
459	MJT-7	81.0	84.0	3.0	13	0.40	31.2	27.80	63.20	<2.0	-	-	-
460	MJT-7	84.0	87.0	3.0	13	0.60	29.7	22.00	52.40	<2.0	-	-	-
461	MJT-7	87.0	90.0	3.0	30	0.40	28.8	25.40	64.60	<2.0	-	-	-
462	MJT-7	90.0	93.0	3.0	30	<0.10	24.8	26.80	56.00	<2.0	-	-	-
463	MJT-7	93.0	96.0	3.0	17	0.20	27.2	21.00	53.00	<2.0	-	-	-
464	MJT-7	96.0	97.0	1.0	20	0.40	37.4	45.20	78.40	<2.0	-	-	-
465	MJT-7	97.0	100.0	3.0	17	0.20	22.6	28.40	67.40	<2.0	-	-	-
466	MJT-7	100.0	103.0	3.0	27	<0.10	37.0	24.20	61.60	<2.0	-	-	-
467	MJT-7	103.0	105.0	2.0	27	<0.10	43.6	20.60	53.20	<2.0	-	-	-
468	MJT-7	105.0	108.0	3.0	23	0.20	56.4	22.80	58.40	<2.0	-	-	-
469	MJT-7	108.0	110.0	2.0	37	1.00	67.4	25.20	48.20	<2.0	-	-	-
470	MJT-7	110.0	113.0	3.0	27	2.60	46.6	25.40	69.80	<2.0	-	-	-
471	MJT-7	113.0	116.0	3.0	23	<0.10	33.0	19.00	59.80	<2.0	-	-	-
472	MJT-7	116.0	119.0	3.0	23	0.40	28.4	16.60	56.20	16.0	-	-	-
473	MJT-7	119.0	122.0	3.0	10	0.40	15.4	8.80	44.60	11.0	-	-	-
474	MJT-7	122.0	123.2	1.2	20	0.60	56.4	14.40	57.20	18.0	-	-	-
475	MJT-7	123.2	124.2	1.0	23	0.40	16.8	23.20	51.40	<2.0	2.233	0.048	2.185
476	MJT-7	124.2	127.1	2.9	33	0.40	30.0	21.80	70.20	<2.0	0.844	0.008	0.836
477	MJT-7	127.1	128.6	1.5	40	1.60	56.6	17.40	113.00	<2.0	2.447	0.045	2.402
478	MJT-7	128.6	132.6	4.0	17	0.20	16.8	15.60	58.20	25.0	-	-	-
479	MJT-7	132.6	133.4	0.8	27	0.20	33.2	27.00	44.20	24.0	-	-	-
480	MJT-7	133.4	136.0	2.6	33	0.20	46.2	21.80	57.40	27.0	-	-	-
481	MJT-7	136.0	139.0	3.0	13	0.20	29.8	21.80	53.00	28.0	-	-	-
482	MJT-7	139.0	142.0	3.0	10	0.20	33.0	19.40	44.60	35.0	-	-	-
483	MJT-7	142.0	145.0	3.0	30	0.20	19.4	24.40	53.20	39.0	-	-	-
484	MJT-7	145.0	148.0	3.0	20	1.00	19.0	20.40	46.60	35.0	-	-	-
485	MJT-7	148.0	151.0	3.0	30	7.80	25.4	14.60	40.80	22.0	-	-	-
486	MJT-7	151.0	154.0	3.0	23	0.80	32.8	18.00	52.40	40.0	-	-	-
487	MJT-7	154.0	156.6	2.6	17	6.00	30.6	15.00	46.80	23.0	-	-	-
488	MJT-7	156.6	157.3	0.7	30	0.40	37.8	14.20	53.80	26.0	-	-	-
489	MJT-7	157.3	160.0	2.7	33	<0.10	24.4	33.00	49.80	27.0	-	-	-
490	MJT-7	160.0	164.1	4.1	17	0.40	34.0	14.20	48.80	17.0	-	-	-
491	MJT-7	164.1	165.3	1.2	27	0.40	25.0	12.20	50.00	<2.0	1.086	0.030	1.056
492	MJT-7	165.3	168.0	2.7	40	0.40	36.8	14.40	53.80	28.0	-	-	-
493	MJT-7	168.0	171.0	3.0	27	1.00	120.0	37.00	74.00	19.0	-	-	-
494	MJT-7	171.0	172.0	1.0	33	<0.10	55.2	13.00	54.00	22.0	-	-	-
495	MJT-7	172.0	173.7	1.7	27	0.20	77.8	13.80	50.80	23.0	-	-	-
496	MJT-7	173.7	176.0	2.3	23	<0.10	32.8	12.20	44.00	24.0	-	-	-
497	MJT-7	176.0	179.0	3.0	20	<0.10	38.0	17.20	47.40	21.0	-	-	-
498	MJT-7	179.0	182.0	3.0	40	0.40	56.0	29.80	64.20	24.0	-	-	-
499	MJT-7	182.0	188.0	6.0	33	0.80	95.0	12.00	40.00	27.0	-	-	-
501	MJT-7	188.0	191.0	3.0	23	2.00	41.8	16.00	49.60	23.0	-	-	-
500	MJT-7	188.0	188.0	0.0	27	1.40	28.2	22.60	91.40	18.0	-	-	-
502	MJT-7	191.0	194.0	3.0	20	0.40	26.0	2.20	28.60	<2.0	-	-	-
503	MJT-7	194.0	197.0	3.0	33	1.00	14.0	18.40	23.00	<2.0	-	-	-
504	MJT-7	197.0	199.0	2.0	20	<0.10	28.0	62.60	37.80	<2.0	-	-	-
505	MJT-7	199.0	200.0	1.0	20	0.80	11.0	7.80	34.20	<2.0	-	-	-
506	MJT-7	200.0	201.0	1.0	17	0.40	16.0	5.00	43.80	<2.0	-	-	-
507	MJT-7	201.0	202.0	1.0	27	0.20	21.6	8.40	25.40	<2.0	-	-	-
508	MJT-7	202.0	205.0	3.0	30	<0.10	31.0	4.80	97.20	<2.0	-	-	-
509	MJT-7	205.0	207.0	2.0	27	0.20	20.2	13.00	42.20	<2.0	-	-	-
510	MJT-7	207.0	209.0	2.0	20	0.60	29.0	12.00	101.60	<2.0	-	-	-
511	MJT-7	209.0	211.0	2.0	33	1.00	49.0	11.60	55.80	<2.0	-	-	-
512	MJT-7	211.0	215.0	4.0	30	1.20	32.2	23.20	119.20	<2.0	-	-	-

Appendix 9

Assay results of the drill core samples, 9/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
513	MJT-7	215.0	216.0	1.0	53	6.80	124.0	6.60	267.00	195.0	-	-	-
514	MJT-7	216.0	217.0	1.0	30	9.80	121.0	1946.00	95.80	11.0	-	-	-
515	MJT-7	217.0	218.0	1.0	40	1.00	22.4	614.00	76.80	8.0	-	-	-
516	MJT-7	218.0	219.0	1.0	27	2.20	36.4	164.60	74.20	4.0	-	-	-
517	MJT-7	219.0	220.0	1.0	23	4.60	106.2	149.20	215.00	9.0	-	-	-
518	MJT-7	220.0	221.0	1.0	37	1.00	149.4	530.00	75.40	<2.0	-	-	-
519	MJT-7	221.0	222.0	1.0	30	1.20	54.4	90.80	43.40	<2.0	-	-	-
520	MJT-7	222.0	223.0	1.0	13	0.60	35.0	43.00	51.40	<2.0	-	-	-
521	MJT-7	223.0	226.0	3.0	40	1.00	156.0	24.60	103.80	<2.0	-	-	-
522	MJT-7	226.0	229.0	3.0	37	1.60	135.2	96.00	154.20	<2.0	-	-	-
523	MJT-7	229.0	232.0	3.0	53	0.20	29.2	258.00	155.60	<2.0	-	-	-
524	MJT-7	232.0	235.0	3.0	30	0.20	66.0	68.60	106.80	<2.0	-	-	-
525	MJT-7	235.0	238.0	3.0	13	0.60	78.0	68.60	83.80	<2.0	-	-	-
526	MJT-7	238.0	241.0	3.0	30	1.40	33.2	95.40	39.80	<2.0	-	-	-
527	MJT-7	241.0	244.0	3.0	10	1.20	49.4	37.60	42.00	<2.0	-	-	-
528	MJT-7	244.0	247.0	3.0	27	1.00	58.8	17.60	29.20	<2.0	-	-	-
529	MJT-7	247.0	250.0	3.0	10	2.60	69.2	12.60	31.20	<2.0	-	-	-
530	MJT-8	0.0	3.0	3.0	10	<0.10	235.8	19.80	81.40	33.0	-	-	-
531	MJT-8	3.0	6.0	3.0	17	0.60	154.2	6.60	72.00	44.0	-	-	-
532	MJT-8	6.0	9.0	3.0	23	0.40	72.2	10.20	12.60	20.0	-	-	-
533	MJT-8	9.0	12.0	3.0	10	0.20	161.6	6.20	117.60	12.0	-	-	-
534	MJT-8	12.0	15.0	3.0	33	<0.10	35.0	8.80	94.60	7.0	-	-	-
535	MJT-8	15.0	18.0	3.0	13	0.80	43.4	18.80	132.80	17.0	-	-	-
536	MJT-8	18.0	21.0	3.0	110	0.20	118.8	29.40	51.00	3.0	-	-	-
537	MJT-8	21.0	24.0	3.0	50	0.20	69.4	5.40	105.80	4.0	-	-	-
538	MJT-8	24.0	27.0	3.0	33	0.20	59.2	14.20	112.20	<2.0	-	-	-
539	MJT-8	27.0	30.0	3.0	67	0.20	121.4	14.60	72.40	4.0	-	-	-
540	MJT-8	30.0	33.0	3.0	50	0.20	117.0	20.00	79.60	22.0	-	-	-
541	MJT-8	33.0	36.0	3.0	80	0.20	145.2	25.80	78.60	33.0	-	-	-
542	MJT-8	36.0	38.5	2.5	40	<0.10	70.4	17.80	64.40	15.0	-	-	-
543	MJT-8	38.5	41.6	3.1	57	0.20	103.8	8.00	70.00	11.0	-	-	-
544	MJT-8	41.6	42.6	1.0	127	0.20	70.8	8.00	80.00	<2.0	3.446	0.033	3.413
545	MJT-8	42.6	44.0	1.4	77	0.40	108.0	7.40	39.80	44.0	-	-	-
546	MJT-8	44.0	46.3	2.3	77	<0.10	151.4	8.40	60.60	7.0	-	-	-
547	MJT-8	46.3	49.0	2.7	37	<0.10	96.6	6.80	68.80	<2.0	-	-	-
548	MJT-8	49.0	51.0	2.0	37	1.60	62.4	7.00	51.80	12.0	-	-	-
549	MJT-8	51.0	53.0	2.0	40	<0.10	52.6	4.60	47.60	<2.0	-	-	-
550	MJT-8	53.0	54.0	1.0	30	<0.10	49.0	4.80	49.00	<2.0	-	-	-
551	MJT-8	54.0	55.0	1.0	50	0.60	64.2	5.60	50.20	<2.0	-	-	-
552	MJT-8	55.0	58.0	3.0	33	<0.10	48.2	16.20	64.00	<2.0	-	-	-
553	MJT-8	58.0	59.0	1.0	27	<0.10	54.6	12.00	66.80	13.0	-	-	-
554	MJT-8	59.0	62.0	3.0	33	<0.10	45.6	10.60	66.40	<2.0	-	-	-
555	MJT-8	62.0	65.0	3.0	27	<0.10	54.4	13.80	76.80	<2.0	-	-	-
556	MJT-8	65.0	68.0	3.0	<10	<0.10	37.6	11.00	73.40	<2.0	-	-	-
557	MJT-8	68.0	71.0	3.0	17	<0.10	64.8	11.00	99.40	<2.0	0.667	0.001	0.666
558	MJT-8	71.0	72.0	1.0	70	<0.10	49.2	12.40	93.80	55.0	-	-	-
559	MJT-8	72.0	73.0	1.0	27	<0.10	19.6	11.20	83.40	7.0	-	-	-
560	MJT-8	73.0	76.0	3.0	33	<0.10	30.6	13.80	81.60	<2.0	-	-	-
561	MJT-8	76.0	79.0	3.0	40	<0.10	29.6	26.60	73.00	11.0	-	-	-
562	MJT-8	79.0	81.0	2.0	37	<0.10	40.6	21.60	76.60	11.0	-	-	-
563	MJT-8	81.0	83.0	2.0	37	<0.10	37.0	16.40	91.80	6.0	-	-	-
564	MJT-8	83.0	84.0	1.0	67	<0.10	45.0	16.80	59.40	26.0	-	-	-
565	MJT-8	84.0	85.0	1.0	60	<0.10	45.6	12.00	38.60	20.0	-	-	-
566	MJT-8	85.0	86.0	1.0	93	<0.10	99.8	16.00	57.80	19.0	-	-	-
567	MJT-8	86.0	87.0	1.0	103	<0.10	44.2	18.60	36.20	28.0	3.212	0.069	3.143
568	MJT-8	87.0	89.0	2.0	130	<0.10	96.2	18.00	54.20	50.0	3.334	0.047	3.287
569	MJT-8	89.0	92.0	3.0	97	0.20	147.6	18.40	68.00	8.0	-	-	-
570	MJT-8	92.0	95.0	3.0	47	<0.10	61.6	21.80	60.80	8.0	-	-	-
571	MJT-8	95.0	98.3	3.3	113	<0.10	64.2	14.80	75.40	15.0	-	-	-
572	MJT-8	98.3	100.0	1.7	80	<0.10	31.6	14.80	49.00	<2.0	3.326	0.010	3.316
573	MJT-8	100.0	101.0	1.0	43	<0.10	45.0	17.80	55.20	<2.0	3.511	0.061	3.450
574	MJT-8	101.0	102.0	1.0	30	<0.10	22.8	13.40	43.60	<2.0	3.880	0.017	3.863
575	MJT-8	102.0	103.0	1.0	30	0.20	50.0	16.60	54.20	23.0	-	-	-
576	MJT-8	103.0	105.5	2.5	97	<0.10	157.4	14.40	81.00	26.0	-	-	-

Appendix 9

Assay results of the drill core samples, 10/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
577	MJT-8	105.5	109.5	4.0	93	0.20	117.6	23.00	101.20	34.0	-	-	-
578	MJT-8	109.5	113.0	3.5	73	0.20	102.0	22.00	72.00	49.0	-	-	-
579	MJT-8	113.0	114.7	1.7	57	<0.10	83.8	28.80	103.40	47.0	-	-	-
580	MJT-8	114.7	118.0	3.3	113	0.20	129.0	50.20	56.40	58.0	-	-	-
581	MJT-8	118.0	119.0	1.0	110	0.20	46.4	54.00	46.00	<2.0	3.503	0.066	3.437
582	MJT-8	119.0	120.0	1.0	77	0.40	52.6	101.80	30.80	28.0	-	-	-
583	MJT-8	120.0	121.0	1.0	70	0.60	39.0	137.80	27.00	43.0	-	-	-
584	MJT-8	121.0	122.0	1.0	93	0.40	51.2	78.00	44.80	29.0	-	-	-
585	MJT-8	122.0	123.0	1.0	40	<0.10	11.4	40.20	38.00	20.0	-	-	-
586	MJT-8	123.0	124.0	1.0	23	<0.10	24.6	41.40	52.60	18.0	-	-	-
587	MJT-8	124.0	125.0	1.0	30	<0.10	20.8	33.20	39.20	28.0	-	-	-
588	MJT-8	125.0	127.0	2.0	30	0.40	30.2	127.40	56.60	<2.0	3.273	0.087	3.186
589	MJT-8	127.0	129.0	2.0	63	0.20	88.8	70.20	53.80	<2.0	2.548	0.099	2.449
590	MJT-8	129.0	132.0	3.0	80	<0.10	71.8	43.20	53.40	23.0	-	-	-
591	MJT-8	132.0	135.0	3.0	53	<0.10	85.2	23.00	81.60	30.0	-	-	-
592	MJT-8	135.0	138.0	3.0	77	<0.10	107.0	25.40	83.60	34.0	-	-	-
593	MJT-8	138.0	141.0	3.0	90	<0.10	169.2	30.00	73.80	48.0	-	-	-
594	MJT-8	141.0	144.0	3.0	67	<0.10	94.4	33.40	56.00	23.0	-	-	-
595	MJT-8	144.0	147.0	3.0	57	<0.10	75.2	33.40	68.60	35.0	-	-	-
596	MJT-8	147.0	150.0	3.0	70	<0.10	126.4	65.60	92.00	44.0	-	-	-
597	MJT-8	150.0	151.0	1.0	60	<0.10	225.0	22.80	68.40	<2.0	1.932	0.070	1.862
598	MJT-8	151.0	152.0	1.0	50	<0.10	144.4	31.40	80.60	30.0	-	-	-
599	MJT-8	152.0	153.0	1.0	57	0.80	83.4	22.80	73.20	<2.0	2.294	0.080	2.214
600	MJT-8	153.0	154.0	1.0	43	<0.10	121.6	32.00	56.00	<2.0	-	-	-
601	MJT-8	154.0	155.0	1.0	53	0.40	102.2	50.00	77.60	<2.0	-	-	-
602	MJT-8	155.0	156.0	1.0	57	3.00	189.4	19.80	91.20	<2.0	2.818	0.078	2.740
603	MJT-8	156.0	157.0	1.0	53	0.60	63.4	41.20	47.20	<2.0	4.177	0.131	4.046
604	MJT-8	157.0	158.0	1.0	103	1.40	67.4	68.80	45.20	<2.0	4.748	0.096	4.652
605	MJT-8	158.0	161.0	3.0	50	0.20	135.8	87.20	40.40	<2.0	-	-	-
606	MJT-8	161.0	163.0	2.0	90	1.20	152.0	36.20	74.80	<2.0	-	-	-
607	MJT-8	163.0	165.0	2.0	127	<0.10	249.4	43.80	66.40	<2.0	-	-	-
608	MJT-8	165.0	168.0	3.0	70	<0.10	95.0	64.60	71.80	<2.0	-	-	-
609	MJT-8	168.0	171.0	3.0	90	0.60	94.6	22.80	75.00	<2.0	-	-	-
610	MJT-8	171.0	172.0	1.0	60	3.40	137.2	19.20	77.20	<2.0	-	-	-
611	MJT-8	172.0	175.0	3.0	77	0.20	132.8	26.00	68.00	<2.0	-	-	-
612	MJT-8	175.0	178.0	3.0	37	<0.10	76.0	34.60	98.40	2.0	-	-	-
613	MJT-8	178.0	181.0	3.0	23	0.40	100.8	15.00	148.00	<2.0	-	-	-
614	MJT-8	181.0	184.0	3.0	<10	<0.10	93.0	10.60	127.00	<2.0	-	-	-
615	MJT-8	184.0	186.0	2.0	17	1.00	39.2	11.60	115.80	<2.0	0.124	0.014	0.110
616	MJT-8	186.0	189.0	3.0	210	1.80	78.0	11.40	70.00	<2.0	-	-	-
617	MJT-8	189.0	192.0	3.0	70	<0.10	147.2	24.80	81.40	<2.0	-	-	-
618	MJT-8	192.0	195.0	3.0	70	<0.10	69.2	19.20	87.80	<2.0	-	-	-
619	MJT-8	195.0	198.0	3.0	60	<0.10	154.0	28.80	80.40	2.0	-	-	-
620	MJT-8	198.0	201.0	3.0	50	1.20	98.2	34.20	85.80	<2.0	-	-	-
621	MJT-8	201.0	204.0	3.0	50	0.20	104.8	16.20	94.60	<2.0	-	-	-
622	MJT-8	204.0	207.0	3.0	40	0.80	97.0	22.80	86.80	<2.0	-	-	-
623	MJT-8	207.0	210.0	3.0	70	<0.10	86.4	25.20	81.20	<2.0	-	-	-
624	MJT-8	210.0	213.0	3.0	80	<0.10	115.6	37.00	79.00	<2.0	-	-	-
625	MJT-8	213.0	216.0	3.0	100	<0.10	116.4	43.40	74.60	<2.0	-	-	-
626	MJT-8	216.0	219.0	3.0	80	<0.10	88.8	29.20	63.80	<2.0	-	-	-
627	MJT-8	219.0	222.0	3.0	50	0.20	96.0	39.00	86.00	15.0	-	-	-
628	MJT-8	222.0	224.0	2.0	40	<0.10	82.0	26.00	80.00	46.0	1.914	<0.01	1.910
629	MJT-8	224.0	227.0	3.0	30	<0.10	87.0	24.00	76.00	10.0	-	-	-
630	MJT-8	227.0	230.0	3.0	30	<0.10	37.0	24.00	80.00	8.0	-	-	-
631	MJT-8	230.0	233.0	3.0	20	<0.10	67.0	51.00	109.00	8.0	-	-	-
632	MJT-8	233.0	237.0	4.0	50	<0.10	34.0	36.00	73.00	15.0	-	-	-
633	MJT-8	237.0	240.0	3.0	30	<0.10	76.0	17.00	55.00	2.0	-	-	-
634	MJT-8	240.0	243.0	3.0	40	<0.10	84.0	19.00	68.00	<2.0	-	-	-
635	MJT-8	243.0	246.0	3.0	30	<0.10	59.0	18.00	62.00	<2.0	-	-	-
636	MJT-8	246.0	248.0	2.0	20	<0.10	101.0	21.00	57.00	<2.0	-	-	-
637	MJT-8	248.0	250.0	2.0	30	<0.10	82.0	36.00	62.00	<2.0	-	-	-
638	MJT-8				30	<0.10	231.0	15.00	77.00	<2.0	-	-	-
639	MJT-9	0.0	3.0	3.0	70	2.80	77.0	22.00	53.00	8.0	-	-	-
640	MJT-9	3.0	6.0	3.0	20	4.20	119.0	17.00	51.00	<2.0	-	-	-

Appendix 9 Assay results of the drill core samples, 11/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
641	MJT-9	6.0	9.0	3.0	30	3.00	66.0	14.00	41.00	<2.0	-	-	-
642	MJT-9	9.0	12.0	3.0	30	1.00	34.0	15.00	27.00	<2.0	-	-	-
643	MJT-9	12.0	15.0	3.0	<10	1.00	21.0	18.00	29.00	<2.0	-	-	-
644	MJT-9	15.0	18.0	3.0	10	0.60	16.0	21.00	35.00	<2.0	-	-	-
645	MJT-9	18.0	21.0	3.0	<10	0.60	16.0	16.00	28.00	<2.0	-	-	-
646	MJT-9	21.0	24.0	3.0	10	1.00	19.0	15.00	30.00	13.0	-	-	-
647	MJT-9	24.0	27.0	3.0	20	1.00	23.0	13.00	27.00	<2.0	-	-	-
648	MJT-9	27.0	30.0	3.0	20	1.00	23.0	22.00	38.00	20.0	-	-	-
649	MJT-9	30.0	33.0	3.0	10	1.00	16.0	15.00	26.00	30.0	-	-	-
650	MJT-9	33.0	36.0	3.0	20	1.20	27.0	30.00	26.00	20.0	-	-	-
651	MJT-9	36.0	39.0	3.0	30	0.80	21.0	16.00	27.00	13.0	-	-	-
652	MJT-9	39.0	42.0	3.0	10	1.00	13.0	27.00	27.00	16.0	-	-	-
653	MJT-9	42.0	43.0	1.0	20	1.20	19.0	16.00	26.00	8.0	-	-	-
654	MJT-9	43.0	44.0	1.0	20	1.40	17.0	15.00	27.00	<2.0	-	-	-
655	MJT-9	44.0	45.0	1.0	30	1.20	28.0	16.00	26.00	<2.0	-	-	-
656	MJT-9	45.0	46.0	1.0	10	1.80	27.0	35.00	42.00	16.0	-	-	-
657	MJT-9	46.0	47.0	1.0	40	1.20	29.0	22.00	34.00	20.0	-	-	-
658	MJT-9	47.0	48.0	1.0	10	2.60	29.0	19.00	27.00	10.0	-	-	-
659	MJT-9	48.0	51.0	3.0	20	3.40	54.0	19.00	28.00	8.0	-	-	-
660	MJT-9	51.0	54.0	3.0	20	0.80	26.0	18.00	31.00	2.0	-	-	-
661	MJT-9	54.0	57.0	3.0	40	1.20	46.0	16.00	27.00	7.0	-	-	-
662	MJT-9	57.0	60.0	3.0	40	0.80	42.0	20.00	30.00	8.0	-	-	-
663	MJT-9	60.0	63.0	3.0	30	1.40	60.0	19.00	35.00	<2.0	-	-	-
664	MJT-9	63.0	66.0	3.0	30	1.60	67.0	21.00	41.00	8.0	-	-	-
665	MJT-9	66.0	69.0	3.0	60	1.40	148.0	23.00	35.00	13.0	-	-	-
666	MJT-9	69.0	72.0	3.0	40	1.40	264.0	19.00	52.00	13.0	-	-	-
667	MJT-9	72.0	75.0	3.0	30	1.60	163.0	20.00	61.00	<2.0	-	-	-
668	MJT-9	75.0	78.0	3.0	30	0.80	57.0	22.00	30.00	7.0	-	-	-
669	MJT-9	78.0	81.0	3.0	50	1.20	157.0	26.00	27.00	6.0	-	-	-
670	MJT-9	81.0	84.0	3.0	10	1.40	43.0	32.00	52.00	48.0	2.779	0.026	2.753
671	MJT-9	84.0	87.0	3.0	10	0.90	27.0	31.00	26.00	8.0	-	-	-
672	MJT-9	87.0	90.0	3.0	20	0.40	80.0	29.00	28.00	24.0	-	-	-
673	MJT-9	90.0	93.0	3.0	20	0.60	50.0	39.00	29.00	<2.0	-	-	-
674	MJT-9	93.0	95.0	2.0	10	1.20	22.0	37.00	27.00	<2.0	-	-	-
675	MJT-9	95.0	96.0	1.0	20	1.40	31.0	41.00	29.00	<2.0	-	-	-
676	MJT-9	96.0	99.0	3.0	20	1.20	41.0	24.00	29.00	<2.0	-	-	-
677	MJT-9	99.0	102.0	3.0	30	1.40	45.0	29.00	48.00	<2.0	-	-	-
678	MJT-9	102.0	105.0	3.0	40	0.40	52.0	30.00	33.00	<2.0	-	-	-
679	MJT-9	105.0	108.0	3.0	30	2.60	52.0	32.00	29.00	14.0	3.098	0.110	2.988
680	MJT-9	108.0	111.0	3.0	30	2.20	39.0	72.00	37.00	<2.0	-	-	-
681	MJT-9	111.0	114.0	3.0	30	1.40	38.0	21.00	32.00	<2.0	-	-	-
682	MJT-9	114.0	117.0	3.0	40	1.60	17.0	25.00	37.00	<2.0	-	-	-
683	MJT-9	117.0	120.0	3.0	40	2.80	56.0	112.00	54.00	<2.0	-	-	-
684	MJT-9	120.0	123.0	3.0	50	2.20	217.0	17.00	50.00	<2.0	-	-	-
685	MJT-9	123.0	126.0	3.0	30	1.00	56.0	20.00	78.00	<2.0	-	-	-
686	MJT-9	126.0	129.0	3.0	30	2.00	26.0	12.00	140.00	<2.0	-	-	-
687	MJT-9	129.0	132.0	3.0	30	1.80	23.0	9.00	143.00	<2.0	-	-	-
688	MJT-9	132.0	135.0	3.0	40	1.80	132.0	11.00	116.00	<2.0	-	-	-
689	MJT-9	135.0	138.0	3.0	40	2.20	49.0	21.00	36.00	<2.0	-	-	-
690	MJT-9	138.0	141.0	3.0	40	1.00	29.0	7.00	84.00	<2.0	-	-	-
691	MJT-9	141.0	144.0	3.0	30	1.00	109.0	9.00	52.00	<2.0	-	-	-
692	MJT-9	144.0	147.0	3.0	30	1.00	13.0	8.00	45.00	<2.0	-	-	-
693	MJT-9	147.0	150.0	3.0	30	1.80	19.0	6.00	52.00	<2.0	-	-	-
694	MJT-9	150.0	152.0	2.0	30	1.60	13.0	5.00	51.00	<2.0	-	-	-
695	MJT-9	152.0	154.0	2.0	30	1.40	24.0	13.00	49.00	<2.0	-	-	-
696	MJT-9	154.0	157.0	3.0	30	2.00	41.0	9.00	52.00	<2.0	-	-	-
697	MJT-9	157.0	160.0	3.0	40	2.60	28.0	11.00	44.00	<2.0	-	-	-
698	MJT-9	160.0	161.0	1.0	40	2.80	28.0	24.00	25.00	17.0	-	-	-
699	MJT-9	161.0	162.0	1.0	30	2.80	19.0	15.00	27.00	<2.0	-	-	-
700	MJT-9	162.0	163.0	1.0	30	4.00	18.0	50.00	28.00	<2.0	-	-	-
701	MJT-9	163.0	164.0	1.0	60	3.20	37.0	73.00	32.00	<2.0	-	-	-
702	MJT-9	164.0	165.0	1.0	40	2.00	37.0	14.00	46.00	15.0	3.687	0.015	3.672
703	MJT-9	165.0	168.0	3.0	30	3.60	37.0	22.00	27.00	<2.0	-	-	-
704	MJT-9	168.0	171.0	3.0	40	2.80	29.0	21.00	40.00	16.0	5.250	0.068	5.182

Appendix 9

Assay results of the drill core samples, 12/12

Seri. No.	Drill hole	Interval (m)			Au ppb	Ag ppm	Cu ppm	Pb ppm	Zn ppm	Mo ppm	S total %	S sulfate %	S sulfide %
		from	to	m									
705	MJT-9	171.0	174.0	3.0	20	3.80	91.0	7.00	50.00	<2.0	-	-	-
706	MJT-9	174.0	177.0	3.0	20	1.80	22.0	15.00	44.00	<2.0	-	-	-
707	MJT-9	177.0	180.0	3.0	20	2.60	15.0	9.00	54.00	<2.0	-	-	-
708	MJT-9	180.0	181.5	1.5	53	3.00	24.0	15.00	37.00	<2.0	-	-	-
709	MJT-9	181.5	182.5	1.0	43	2.80	244.0	14.00	75.00	<2.0	-	-	-
710	MJT-9	182.5	185.0	2.5	43	3.60	44.0	17.00	36.00	21.0	-	-	-
711	MJT-9	185.0	186.5	1.5	117	11.40	61.0	20.00	37.00	46.0	4.027	0.048	3.979
712	MJT-9	186.5	190.0	3.5	77	5.20	105.0	17.00	54.00	41.0	2.826	0.033	2.793
713	MJT-9	190.0	193.0	3.0	20	3.80	15.0	17.00	38.00	8.0	-	-	-
714	MJT-9	193.0	196.0	3.0	40	1.80	156.0	16.00	47.00	13.0	-	-	-
715	MJT-9	196.0	199.0	3.0	20	1.80	36.0	15.00	43.00	<2.0	-	-	-
716	MJT-9	199.0	201.0	2.0	37	3.60	19.0	21.00	32.00	5.0	-	-	-
717	MJT-9	201.0	204.0	3.0	37	4.00	25.0	17.00	44.00	27.0	-	-	-
718	MJT-9	204.0	207.0	3.0	33	0.40	28.0	16.00	43.00	10.0	-	-	-
719	MJT-9	207.0	210.0	3.0	37	0.20	12.0	12.00	32.00	20.0	-	-	-
720	MJT-9	210.0	211.8	1.8	37	2.40	16.0	21.00	37.00	692.0	-	-	-
721	MJT-9	211.8	213.5	1.7	3883	13.80	37.0	80.00	36.00	22.0	5.430	0.074	5.356
722	MJT-9	213.5	217.0	3.5	37	1.60	21.0	50.00	44.00	913.0	-	-	-
723	MJT-9	217.0	220.0	3.0	40	1.80	75.0	70.00	46.00	275.0	-	-	-
724	MJT-9	220.0	223.0	3.0	33	1.60	45.0	54.00	45.00	865.0	-	-	-
725	MJT-9	223.0	226.0	3.0	37	0.80	52.0	41.00	49.00	298.0	-	-	-
726	MJT-9	226.0	229.0	3.0	30	0.80	68.0	29.00	54.00	715.0	-	-	-
727	MJT-9	229.0	232.0	3.0	43	0.40	33.0	19.00	60.00	153.0	-	-	-
728	MJT-9	232.0	234.2	2.2	80	<0.10	36.0	17.00	45.00	510.0	-	-	-
729	MJT-9	234.2	235.8	1.6	50	<0.10	87.0	28.00	36.00	288.0	-	-	-
730	MJT-9	235.8	239.0	3.2	30	<0.10	39.0	18.00	62.00	510.0	-	-	-
731	MJT-9	239.0	242.0	3.0	23	0.20	44.0	19.00	55.00	106.0	-	-	-
732	MJT-9	242.0	245.0	3.0	27	0.40	73.0	21.00	52.00	155.0	-	-	-
733	MJT-9	245.0	248.0	3.0	23	0.80	51.0	18.00	67.00	511.0	-	-	-
734	MJT-9	248.0	251.0	3.0	33	0.20	28.0	21.00	52.00	11.0	-	-	-
735	MJT-9	251.0	254.0	3.0	37	0.60	50.0	45.00	39.00	61.0	-	-	-
736	MJT-9	254.0	257.0	3.0	27	0.20	84.0	31.00	123.00	44.0	-	-	-
737	MJT-9	257.0	259.0	2.0	40	0.20	81.0	63.00	94.00	52.0	-	-	-
738	MJT-9	259.0	261.5	2.5	27	0.20	38.0	25.00	152.00	24.0	-	-	-
739	MJT-9	261.5	265.0	3.5	33	0.80	134.0	28.00	69.00	49.0	-	-	-
740	MJT-9	265.0	268.0	3.0	20	<0.10	56.0	16.00	68.00	33.0	-	-	-
741	MJT-9	268.0	271.0	3.0	30	<0.10	99.0	22.00	79.00	32.0	-	-	-
742	MJT-9	271.0	274.0	3.0	23	0.20	37.0	19.00	85.00	38.0	-	-	-
743	MJT-9	274.0	277.0	3.0	40	0.20	157.0	17.00	59.00	31.0	-	-	-
744	MJT-9	277.0	280.0	3.0	17	2.60	64.0	19.00	76.00	37.0	-	-	-
745	MJT-9	280.0	281.5	1.5	17	0.80	76.0	27.00	117.00	44.0	-	-	-
746	MJT-9	281.5	282.0	0.5	17	<0.10	83.0	18.00	71.00	<2.0	-	-	-
747	MJT-9	282.0	283.7	1.7	23	<0.10	137.0	18.00	44.00	<2.0	-	-	-
748	MJT-9	283.7	286.0	2.3	207	13.00	313.0	368.00	60.00	14.0	-	-	-
749	MJT-9	286.0	288.0	2.0	40	2.40	246.0	27.00	73.00	<2.0	-	-	-
750	MJT-9				17	0.40	285.0	23.00	99.00	<2.0	-	-	-