

Appendix 4

Assay results of drilling cores

[The page contains extremely faint and illegible text, likely due to low contrast or scanning quality. The text is distributed across the page but cannot be transcribed.]



MJOB-G40

Sample No.	Depth(m)		Length (m)	Au(g/t)	Ag(g/t)	Cu(%)	Pb(ppm)	Zn(%)	Fe2O3 (%)
	From	To							
G40- 1	126.00	128.00	2	<0.1	0.8	0.70	<10	0.14	9.73
G40- 2	128.00	129.30	1.3	<0.1	0.9	0.71	12	0.03	11.65
G40- 3	141.95	142.55	0.6	<0.1	1.1	0.51	33	0.13	32.10
G40- 4	142.55	143.55	1	<0.1	<0.2	0.16	10	0.02	22.36
G40- 5	143.55	144.55	1	0.20	2.5	1.67	60	0.08	55.74
G40- 6	144.55	145.55	1	0.20	2.8	2.62	78	0.08	51.91
G40- 7	145.55	146.55	1	0.20	2.1	1.95	72	0.07	55.74
G40- 8	146.55	147.55	1	0.20	2.4	2.93	60	0.05	54.94
G40- 9	147.55	148.55	1	0.10	1.8	1.30	45	0.04	47.60
G40- 10	148.55	149.55	1	<0.1	1.7	1.21	50	0.05	54.63
G40- 11	149.55	150.55	1	<0.1	1.4	0.83	44	0.06	56.70
G40- 12	150.55	151.55	1	<0.1	1.3	0.47	31	0.05	54.31
G40- 13	151.55	153.75	2.2	<0.1	0.3	0.13	10	0.01	15.33
G40- 14	153.75	154.75	1	<0.1	1.1	0.23	20	0.04	52.71
G40- 15	154.75	155.75	1	<0.1	1.3	1.18	32	0.05	57.50
G40- 16	155.75	156.75	1	<0.1	1.7	2.91	43	0.04	58.79
G40- 17	156.75	157.75	1	0.10	2.7	6.13	67	0.04	54.63
G40- 18	157.75	158.75	1	0.10	3.2	6.00	81	0.07	57.50
G40- 19	158.75	159.75	1	0.10	2.5	5.03	88	0.04	59.26
G40- 20	159.75	160.75	1	<0.1	2.1	2.46	49	0.06	61.02
G40- 21	160.75	161.55	0.8	0.10	2.3	1.42	41	0.04	52.71
G40- 22	161.55	162.60	1.05	0.10	1.5	0.50	24	0.04	41.06
G40- 23	162.60	163.60	1	0.10	2.6	1.00	40	0.05	60.70
G40- 24	163.60	164.60	1	0.10	2.3	1.60	27	0.03	61.66
G40- 25	164.60	165.60	1	0.20	2.3	1.39	37	0.03	64.69
G40- 26	165.60	166.60	1	0.10	1.4	0.63	15	0.02	61.84
G40- 27	166.60	167.60	1	0.10	1.4	0.73	25	0.03	60.22
G40- 28	167.60	168.60	1	0.20	2.1	1.43	80	0.07	59.57
G40- 29	168.60	169.60	1	0.10	2.1	1.23	47	0.07	60.06
G40- 30	169.60	170.60	1	0.10	2.0	1.14	41	0.05	61.06
G40- 31	170.60	171.60	1	0.10	2.0	2.10	55	0.05	59.26
G40- 32	171.60	172.60	1	0.20	2.6	1.82	58	0.05	61.49
G40- 33	172.60	173.60	1	0.30	2.7	2.12	77	0.07	61.49
G40- 34	173.60	174.60	1	0.30	2.6	1.80	62	0.06	61.64
G40- 35	174.60	175.60	1	0.20	2.2	1.66	60	0.07	59.41
G40- 36	175.60	176.60	1	0.30	2.5	1.97	56	0.07	60.22
G40- 37	176.60	177.60	1	0.10	1.7	1.24	36	0.06	62.13
G40- 38	177.60	178.60	1	0.10	1.5	0.67	29	0.04	61.33
G40- 39	178.60	179.60	1	0.10	1.4	0.91	30	0.05	60.86
G40- 40	179.60	180.60	1	<0.1	1.5	1.35	30	0.04	61.49
G40- 41	180.60	181.60	1	0.20	1.7	2.75	50	0.05	61.00
G40- 42	181.60	182.60	1	0.20	2.2	2.89	61	0.05	60.69
G40- 43	182.60	183.60	1	0.20	2.2	4.53	55	0.05	61.82
G40- 44	183.60	184.60	1	0.20	1.9	5.34	72	0.06	62.29
G40- 45	184.60	185.60	1	0.20	1.9	4.65	76	0.06	62.61
G40- 46	185.60	186.60	1	0.30	2.2	2.08	70	0.04	63.89

MJOB-G40

Sample No.	Depth(m)		Length (m)	Au(g/t)	Ag(g/t)	Cu(%)	Pb(ppm)	Zn(%)	Fe2O3 (%)
	From	To							
G40- 47	186.60	187.60	1	0.20	2.0	2.89	56	0.06	64.21
G40- 48	187.60	188.60	1	0.10	1.2	2.00	49	0.06	63.57
G40- 49	188.60	189.60	1	0.10	1.4	2.09	52	0.05	63.09
G40- 50	189.60	190.60	1	0.10	1.3	2.07	62	0.06	63.57
G40- 51	190.60	191.60	1	0.10	1.4	3.35	59	0.06	63.41
G40- 52	191.60	192.60	1	0.10	1.6	3.00	53	0.07	64.21
G40- 53	192.60	193.60	1	0.20	1.5	2.92	46	0.06	63.25
G40- 54	193.60	194.60	1	0.10	1.0	2.46	44	0.07	64.69
G40- 55	194.60	195.60	1	0.10	1.4	2.63	56	0.09	65.17
G40- 56	195.60	196.60	1	0.10	1.2	2.66	49	0.06	62.45
G40- 57	196.60	197.60	1	0.10	1.5	2.08	45	0.06	58.94
G40- 58	197.60	199.05	1.45	<0.1	1.4	3.53	56	0.06	49.04
G40- 59	199.05	200.10	1.05	<0.1	1.6	0.14	<10	0.02	13.89
G40- 60	200.10	200.40	0.3	<0.1	1.7	2.02	60	0.11	40.25
G40- 61	200.40	201.65	1.25	<0.1	0.3	0.05	15	0.33	11.02
G40- 62	201.65	202.65	1	<0.1	1.1	0.39	16	0.43	18.21
G40- 63	202.65	203.65	1	0.10	2.2	2.65	16	1.05	29.71
G40- 64	203.65	204.65	1	0.10	2.2	3.15	16	0.21	22.36
G40- 65	204.65	205.65	1	0.10	2.7	2.53	16	1.05	26.35
G40- 66	205.65	206.65	1	<0.1	2.6	2.08	11	0.35	28.91
G40- 67	206.65	207.65	1	<0.1	1.3	0.07	10	0.03	32.11
G40- 68	207.65	208.65	1	<0.1	0.7	0.02	13	0.04	25.55
G40- 69	208.65	209.65	1	<0.1	1.2	0.65	14	0.05	26.99
G40- 70	209.65	210.65	1	<0.1	1.6	1.52	16	0.06	31.15
G40- 71	210.65	211.65	1	<0.1	1.4	1.52	18	0.05	26.35
G40- 72	211.65	212.65	1	<0.1	1.4	1.31	15	0.04	26.04
G40- 73	212.65	213.65	1	<0.1	0.8	0.80	17	0.04	20.60
G40- 74	213.65	214.65	1	<0.1	1.2	1.06	15	0.04	27.95
G40- 75	214.65	215.65	1	<0.1	0.7	0.20	15	0.03	23.00
G40- 76	215.65	216.80	1.15	<0.1	0.6	0.03	12	0.03	22.20

Mineral Laboratory, Directorate of Minerals, Ministry of Commerce & Industry, Oman

AVERAGE		Length(m)	Cu(%)	Zn(%)
massive sulphide	141.95-199.05	57.1	2.10	0.05
stockwork	199.05-216.80	17.75	1.06	0.22


MJOB-G44


Sample No.	Depth(m)		Length (m)	Au(g/t)	Ag(g/t)	Cu(%)	Pb(ppm)	Zn(%)	Fe2O3 (%)
	From	To							
G44- 1	274.95	275.70	0.75	<0.1	0.6	0.12	8	0.03	14.60
G44- 2	275.70	277.10	1.4	<0.1	0.2	0.07	13	0.02	16.60
G44- 3	277.10	277.95	0.85	<0.1	0.5	0.62	12	0.03	33.30
G44- 4	277.95	278.35	0.4	<0.1	<0.2	0.02	19	0.02	21.10
G44- 5	278.35	279.35	1	0.20	1.7	0.64	39	0.01	34.10
G44- 6	279.35	280.00	0.65	<0.1	2.4	1.70	13	0.04	17.80


Mineral Laboratory, Directorate of Minerals, Ministry of Commerce & Industry, Oman

AVERAGE		Length(m)	Cu(%)	Zn(%)
massive sulphide	277.10-280.00	2.9	0.79	0.02









JICA