

**Apx. 13 Assay results (57 elements) of drilling core samples
(MJVD-1~16)**

MJVD-1 (1/126)

Sample Name	F %	Ba %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm	Mo ppm	Na %	P ppm
MJVD-1-1	0.3	7.70	1.60	162	<10	<5.0	<10	0.14	<0.5	119	3.14	<100	<1	0.20	0.06	4,610	7	<0.01	1,660
MJVD-1-2	0.3	5.69	1.10	120	<10	<5.0	<10	0.17	<0.5	111	2.41	<100	1	0.21	0.05	4,990	7	<0.01	1,390
MJVD-1-3	0.2	8.54	0.64	164	<10	<5.0	<10	0.11	<0.5	96	1.99	<100	1	0.12	0.04	3,540	7	<0.01	2,250
MJVD-1-4	0.1	9.21	0.89	240	<10	<5.0	<10	0.17	0.5	98	3.18	<100	1	0.09	0.08	5,390	13	<0.01	2,350
MJVD-1-5	0.2	15.95	1.12	300	<10	5	<10	0.16	0.5	84	3.52	<100	4	0.11	0.06	>10,000	16	<0.01	1,840
MJVD-1-6	0.1	16.30	1.06	370	<10	10	<10	0.12	2.5	81	4.12	<100	6	0.08	0.04	>10,000	28	0.01	3,170
MJVD-1-7	0.1	14.15	0.53	194	<10	<5.0	<10	0.22	1.5	103	3.06	<100	1	0.05	0.07	4,980	16	<0.01	1,670
MJVD-1-8	0.2	10.20	0.81	170	<10	<5.0	<10	0.62	0.5	127	2.51	<100	1	0.09	0.07	5,510	14	<0.01	2,080
MJVD-1-9	0.1	7.82	0.67	124	<10	<5.0	<10	0.45	0.5	123	2.45	<100	1	0.09	0.05	4,610	31	<0.01	2,700
MJVD-1-10	0.2	4.06	0.45	52	<10	<5.0	<10	11.55	0.5	82	1.45	<100	<1	0.17	0.21	2,440	33	<0.01	1,440
MJVD-1-11	0.2	2.84	0.46	54	<10	<5.0	<10	10.90	1.0	78	1.69	<100	<1	0.14	0.12	2,690	31	<0.01	1,500
MJVD-1-12	0.3	0.86	0.77	40	<10	<5.0	<10	9.24	1.5	86	1.64	<100	<1	0.23	0.13	2,860	7	<0.01	1,720
MJVD-1-13	0.2	3.75	0.43	56	<10	<5.0	<10	9.39	2.0	74	1.37	<100	<1	0.14	0.81	2,260	63	<0.01	1,940
MJVD-1-14	0.3	3.87	0.47	68	<10	<5.0	<10	9.61	1.5	79	1.62	<100	<1	0.17	1.11	2,380	88	<0.01	1,850
MJVD-1-15	0.2	4.47	0.22	56	<10	<5.0	<10	8.60	1.5	81	1.24	<100	<1	0.07	0.30	1,895	36	<0.01	2,020
MJVD-1-16	0.2	7.21	0.22	86	<10	<5.0	<10	7.31	2.5	82	1.38	<100	1	0.07	0.30	1,450	243	<0.01	2,120
MJVD-1-17	1.0	4.75	0.29	66	100	<5.0	<10	>15.00	1.0	35	0.59	<100	<1	0.10	2.54	1,810	90	0.03	960
MJVD-1-18	1.0	4.41	0.28	40	60	<5.0	<10	>15.00	0.5	21	0.42	<100	<1	0.08	5.27	1,535	67	0.02	400
MJVD-1-19	2.9	9.42	0.26	66	720	<5.0	<10	>15.00	0.5	16	0.46	<100	<1	0.12	3.97	1,470	99	0.13	290
MJVD-1-20	1.6	4.71	0.17	34	460	<5.0	<10	>15.00	0.5	14	0.39	<100	<1	0.08	5.31	1,500	55	0.08	220
MJVD-1-21	0.8	6.19	0.16	40	100	<5.0	<10	>15.00	1.5	18	0.41	<100	<1	0.06	3.73	1,505	73	0.03	310
MJVD-1-22	1.1	2.82	0.12	16	230	<5.0	<10	>15.00	1.5	10	0.36	<100	<1	0.05	4.99	1,795	48	0.05	180
MJVD-1-23	0.8	6.25	0.12	18	120	<5.0	<10	>15.00	1.5	10	0.57	<100	<1	0.05	5.07	1,465	51	0.03	170
MJVD-1-24	0.7	3.14	0.19	14	40	<5.0	<10	>15.00	0.5	11	0.63	<100	<1	0.05	6.79	1,325	67	0.02	150
MJVD-1-25	1.1	4.08	0.30	34	90	<5.0	<10	>15.00	0.5	17	0.48	<100	<1	0.06	4.62	1,715	42	0.03	270
MJVD-1-26	0.8	3.70	0.68	28	<10	<5.0	<10	>15.00	0.5	28	0.53	<100	<1	0.06	5.10	1,305	52	0.01	510
MJVD-1-27	1.0	8.13	0.76	48	<10	<5.0	<10	>15.00	1.0	36	0.69	<100	<1	0.09	2.27	1,530	8	0.01	1,040
MJVD-1-28	1.0	5.33	0.51	24	50	<5.0	<10	>15.00	0.5	25	0.49	<100	<1	0.10	5.29	1,630	4	0.02	430
MJVD-1-29	0.9	7.68	0.46	30	10	<5.0	<10	>15.00	0.5	22	0.63	<100	<1	0.06	4.33	1,790	3	0.01	360
MJVD-1-30	0.5	2.24	1.14	54	<10	<5.0	<10	11.80	0.5	82	1.56	<100	<1	0.10	0.69	1,490	21	<0.01	1,710
MJVD-1-31	0.6	2.57	1.21	58	<10	<5.0	<10	10.65	<0.5	87	1.65	<100	<1	0.18	0.57	1,600	17	<0.01	1,820
MJVD-1-32	0.8	3.69	1.21	58	<10	<5.0	<10	9.44	0.5	107	1.53	<100	<1	0.37	0.18	2,100	9	<0.01	1,650
MJVD-1-33	0.9	16.20	0.44	64	10	<5.0	<10	13.25	2.0	53	0.97	<100	<1	0.13	0.12	1,335	46	0.01	750
MJVD-1-34	0.5	10.15	0.33	100	<10	<5.0	<10	11.25	2.5	61	1.58	<100	1	0.11	0.19	1,630	145	<0.01	1,680
MJVD-1-35	1.5	3.21	0.27	10	240	<5.0	<10	>15.00	1.0	12	0.43	<100	<1	0.11	4.90	2,430	4	0.05	90
MJVD-1-36	0.8	12.35	0.15	38	140	<5.0	<10	>15.00	1.0	27	0.71	<100	<1	0.07	2.28	2,220	1	0.03	210
MJVD-1-37	1.5	16.25	0.30	122	350	<5.0	<10	9.99	1.5	51	0.76	<100	<1	0.12	0.59	1,310	23	0.06	380
MJVD-1-38	0.7	15.05	0.17	60	50	<5.0	<10	10.65	1.5	42	0.88	<100	<1	0.07	2.84	1,475	11	0.01	420
MJVD-1-39	0.4	14.75	0.27	112	<10	<5.0	<10	6.35	3.5	64	1.77	<100	<1	0.09	0.11	1,715	9	<0.01	1,470
MJVD-1-40	0.3	14.40	0.21	138	<10	<5.0	<10	7.52	4.5	57	1.86	<100	<1	0.06	0.10	1,965	10	<0.01	1,320
MJVD-1-41	0.4	18.55	0.17	274	<10	<5.0	<10	5.45	3.0	64	2.01	<100	<1	0.06	0.11	2,050	8	<0.01	1,590
MJVD-1-42	0.9	19.35	0.56	232	<10	<5.0	<10	7.18	1.5	96	2.03	<100	<1	0.17	0.34	1,455	61	0.01	1,120
MJVD-1-43	1.0	16.30	0.34	232	40	<5.0	<10	6.19	2.5	55	1.77	<100	<1	0.11	0.40	1,370	68	0.01	1,160
MJVD-1-44	0.6	11.10	0.80	230	<10	<5.0	10	3.78	1.5	95	2.05	<100	<1	0.16	0.20	2,350	29	<0.01	1,390
MJVD-1-45	0.4	25.80	0.96	232	<10	<5.0	10	3.66	2.0	55	2.73	<100	<1	0.07	0.12	4,960	23	<0.01	1,620
MJVD-1-46	0.5	22.40	1.65	354	<10	<5.0	<10	3.99	2.5	67	3.46	<100	2	0.10	0.07	6,480	16	0.01	1,840
MJVD-1-47	0.4	17.05	0.15	300	<10	<5.0	<10	7.48	2.5	51	1.99	<100	<1	0.05	0.23	2,740	12	<0.01	940
MJVD-1-48	0.2	3.94	0.06	152	<10	<5.0	<10	11.10	0.5	36	1.31	<100	1	0.01	2.60	5,100	17	<0.01	430
MJVD-1-49	0.2	8.30	0.06	136	<10	<5.0	<10	10.60	1.5	45	1.26	<100	1	0.01	0.39	2,740	7	<0.01	630
MJVD-1-50	0.2	9.74	0.17	144	<10	<5.0	<10	10.35	1.5	43	1.11	<100	<1	0.06	0.26	3,860	40	<0.01	410
MJVD-1-51	0.2	15.15	0.21	162	<10	<5.0	<10	8.71	3.0	49	1.23	<100	<1	0.07	0.16	3,470	41	<0.01	710
MJVD-1-52	0.3	13.95	0.31	152	<10	<5.0	<10	8.12	2.0	61	1.00	<100	<1	0.11	0.15	2,270	9	<0.01	510
MJVD-1-53	0.2	11.15	1.12	208	<10	<5.0	<10	0.35	2.0	106	3.24	<100	1	0.08	0.05	5,300	22	<0.01	1,660
MJVD-1-54	0.2	10.25	0.88	196	<10	<5.0	<10	0.56	2.5	98	2.81	<100	1	0.10	0.06	4,980	23	<0.01	1,410
MJVD-1-55	0.2	11.35	1.02	184	<10	<5.0	<10	0.48	2.0	105	3.11	<100	1	0.09	0.08	4,700	17	0.01	1,620
MJVD-1-56	0.2	9.12	0.48	138	<10	<5.0	<10	0.70	2.5	114	2.40	<100	<1	0.13	0.08	2,590	17	<0.01	1,070
MJVD-1-57	0.3	12.30	0.41	156	<10	<5.0	<10	0.57	3.0	95	3.45	<100	<1	0.11	0.05	2,890	16	<0.01	1,250

MJVD-1 (2/126)

Sample Name	F	Ba	Al	As	B	Be	Bi	Ca	Cd	Cr	Fe	Ga	Hg	K	Mg	Mn	Mo	Na	P
	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%	ppm	ppm	%	ppm
MJVD-1-58	0.2	32.20	0.28	148	<10	<5.0	<10	0.62	2.0	66	1.45	<100	<1	0.07	0.06	1,715	8	<0.01	1,040
MJVD-1-59	0.2	17.60	0.31	112	<10	<5.0	<10	0.54	0.5	99	2.01	<100	<1	0.06	0.03	920	10	0.01	1,350
MJVD-1-60	0.3	15.85	0.51	162	<10	<5.0	<10	1.93	1.0	97	2.48	<100	<1	0.10	0.07	1,130	17	0.01	1,340
MJVD-1-61	0.3	12.85	0.53	136	<10	<5.0	<10	1.66	1.5	94	2.17	<100	<1	0.11	0.06	1,130	13	0.01	1,210
MJVD-1-62	0.3	17.10	0.39	170	<10	<5.0	<10	1.11	1.0	90	2.20	<100	<1	0.08	0.07	1,880	11	0.01	1,450
MJVD-1-63	0.2	24.00	0.14	138	<10	<5.0	<10	6.01	3.0	57	1.44	<100	<1	0.05	0.05	1,065	10	<0.01	970
MJVD-1-64	0.2	31.40	0.09	122	<10	<5.0	<10	3.43	2.0	51	1.09	<100	<1	0.03	0.03	905	54	<0.01	780
MJVD-1-65	0.2	29.00	0.13	162	<10	<5.0	<10	3.73	2.5	40	1.07	<100	<1	0.04	0.03	980	216	<0.01	880
MJVD-1-66	0.2	31.50	0.18	146	<10	<5.0	<10	2.39	3.0	45	1.43	<100	<1	0.05	0.03	965	184	<0.01	1,030
MJVD-1-67	0.2	27.50	0.15	122	<10	<5.0	<10	4.66	3.0	45	0.92	<100	<1	0.04	0.04	1,105	45	<0.01	1,040
MJVD-1-68	0.3	26.70	0.14	184	<10	<5.0	<10	5.46	2.0	42	1.18	<100	<1	0.03	0.04	2,080	8	<0.01	2,120
MJVD-1-69	0.2	25.00	0.10	80	<10	<5.0	<10	12.65	2.0	22	0.75	<100	<1	0.02	0.06	1,205	5	<0.01	890
MJVD-1-70	0.2	8.77	0.07	38	<10	<5.0	<10	>15.00	2.0	12	0.54	<100	<1	0.02	0.13	1,770	1	0.01	540
MJVD-1-71	0.4	14.75	0.10	60	10	<5.0	<10	>15.00	2.0	13	0.43	<100	<1	0.03	0.08	1,770	<1	0.01	760
MJVD-1-72	0.2	6.78	0.07	26	<10	<5.0	<10	>15.00	1.0	8	0.40	<100	<1	0.02	0.14	2,230	<1	0.01	380
MJVD-1-73	0.9	21.10	0.10	92	160	<5.0	<10	>15.00	2.0	8	0.63	<100	<1	0.04	0.09	1,800	30	0.04	940
MJVD-1-74	0.1	41.30	0.02	22	10	<5.0	<10	8.60	<0.5	3	0.16	<100	<1	<0.01	0.02	760	1	0.01	160
MJVD-1-75	0.2	30.20	0.04	56	<10	<5.0	<10	14.00	0.5	6	0.44	<100	<1	0.01	0.04	1,435	<1	0.01	850
MJVD-1-76	0.2	27.60	0.07	64	<10	<5.0	<10	14.80	1.0	9	0.67	<100	<1	0.01	0.06	1,535	1	0.01	680
MJVD-1-77	0.3	15.35	0.43	74	<10	<5.0	<10	>15.00	1.0	14	0.85	<100	<1	0.04	0.16	2,360	<1	0.01	1,120
MJVD-1-78	0.7	17.30	1.14	114	<10	<5.0	<10	>15.00	1.0	27	1.07	<100	1	0.09	0.22	3,820	2	0.01	930
MJVD-1-79	1.5	8.55	0.25	112	250	<5.0	<10	>15.00	1.5	6	0.44	<100	<1	0.07	0.08	3,500	<1	0.06	460
MJVD-1-80	0.9	7.07	1.56	158	<10	<5.0	<10	>15.00	2.5	38	1.35	<100	<1	0.14	0.20	3,180	<1	0.01	1,250

MJVD-1 (3/126)

Sample Name	S	Sb	Sc	Ti	Ce	Cs	Co	Cu	Dy	Er	Eu	Gd	Hf	Ho	La	Pb	Lu	Nd	Ni
	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-1-1	0.01	2	<20	<0.01	2,520	4	15.0	75	24.7	12.3	<70.0	72	3	4.3	3,180	1,465	0.9	1,310	20
MJVD-1-2	0.02	2	<20	<0.01	2,330	3.6	12.5	65	23.6	11.4	<50.0	70	2	3.7	2,800	1,550	0.6	1,190	10
MJVD-1-3	0.03	10	<20	<0.01	4,420	2.1	9.5	70	33.0	15.7	<80.0	101	2	5.2	3,870	1,500	0.8	1,765	10
MJVD-1-4	0.03	32	<20	<0.01	6,400	1.8	11.0	95	52.5	23.2	<90.0	139	<1	7.6	4,170	2,300	0.8	2,330	15
MJVD-1-5	0.02	38	<20	0.01	5,420	2.5	18.5	110	47.8	26.2	<150.0	135	1	7.5	4,640	3,800	1.2	2,250	25
MJVD-1-6	0.01	66	<20	0.01	10,980	2.2	31.5	170	68.2	33.1	<150.0	204	<1	11.0	5,890	6,400	1.6	3,550	45
MJVD-1-7	0.04	36	<20	<0.01	9,100	0.5	5.5	70	47.5	21.4	<150.0	143	<1	7.4	3,530	2,070	0.9	2,230	15
MJVD-1-8	0.03	22	<20	<0.01	5,100	1.4	13.5	55	45.6	21.6	<100.0	114	<1	7.8	3,510	2,580	0.9	1,800	30
MJVD-1-9	0.03	20	<20	<0.01	3,610	1	9.5	90	33.2	17.0	<80.0	92	<1	6.1	2,490	2,000	0.8	1,280	15
MJVD-1-10	0.13	12	<20	<0.01	1,800	1	7.0	55	16.8	9.5	<40.0	38	<1	3.0	1,210	930	0.5	547	15
MJVD-1-11	0.13	10	<20	<0.01	1,320	1.7	10.0	55	15.8	8.4	<20.0	31	<1	2.4	857	2,700	0.5	425	10
MJVD-1-12	0.04	6	<20	<0.01	689	2.3	12.5	55	9.8	6.5	8	15	2	2.1	456	550	0.6	221	30
MJVD-1-13	0.41	14	<20	<0.01	2,060	1.5	10.0	75	23.1	10.0	<40.0	53	<1	4.0	1,315	1,420	0.4	677	15
MJVD-1-14	0.57	20	<20	<0.01	2,190	1.3	11.0	80	22.7	10.1	<40.0	54	<1	4.0	1,360	1,950	0.4	747	5
MJVD-1-15	0.17	18	<20	<0.01	2,480	0.4	6.0	70	32.9	12.6	<40.0	62	<1	4.6	1,600	1,810	0.4	810	20
MJVD-1-16	0.15	58	<20	<0.01	3,710	0.3	9.0	150	36.2	12.8	<70.0	91	<1	5.9	2,470	3,420	0.3	1,190	5
MJVD-1-17	0.31	20	<20	<0.01	3,270	0.2	4.0	50	23.4	10.3	<50.0	70	<1	3.7	2,430	1,310	0.4	907	<5
MJVD-1-18	0.23	12	<20	<0.01	2,120	0.1	4.0	30	15.0	6.9	<40.0	38	<1	2.4	1,555	530	0.4	576	<5
MJVD-1-19	0.19	18	<20	<0.01	3,460	0.2	3.5	50	16.7	8.6	<100.0	52	<1	2.8	2,650	970	0.3	883	5
MJVD-1-20	0.1	10	<20	<0.01	2,100	0.1	3.5	20	12.7	5.7	<50.0	37	<1	2.2	1,530	790	0.2	602	10
MJVD-1-21	0.05	14	<1	<0.01	2,210	0.1	3.5	40	16.6	7.3	<60.0	42	<1	2.7	1,625	810	0.4	593	10
MJVD-1-22	0.15	10	<20	<0.01	1,280	<0.1	5.0	30	12.8	6.6	<20.0	29	<1	2.0	915	910	0.3	374	5
MJVD-1-23	0.49	20	<20	<0.01	1,090	0.3	2.0	50	9.3	4.9	<60.0	24	<1	1.4	778	860	0.2	327	<5
MJVD-1-24	0.49	10	<20	<0.01	818	<0.1	11.5	50	8.1	3.5	<30.0	20	<1	1.2	572	350	0.2	252	5
MJVD-1-25	0.31	18	<20	<0.01	1,760	0.1	6.0	40	11.9	5.9	<40.0	32	<1	1.8	1,275	620	0.3	484	10
MJVD-1-26	0.31	10	<20	<0.01	1,440	0.3	8.5	40	10.4	5.4	<40.0	27	<1	1.8	1,060	910	0.4	403	30
MJVD-1-27	0.05	16	<20	<0.01	2,210	0.3	6.5	45	13.4	7.3	<80.0	34	<1	2.3	1,720	1,140	0.5	573	<5
MJVD-1-28	0.04	10	<20	<0.01	1,355	0.4	5.5	35	12.2	6.1	<50.0	30	<1	1.9	975	840	0.3	391	5
MJVD-1-29	0.04	10	<20	<0.01	1,430	0.1	7.5	30	12.7	6.1	<70.0	34	<1	2.2	994	1,090	0.4	458	35
MJVD-1-30	0.04	10	<20	<0.01	1,015	1.2	11.0	55	10.0	5.1	<20.0	21	1	1.8	709	720	0.3	308	30
MJVD-1-31	0.04	6	<20	<0.01	1,070	1.9	15.0	50	8.0	6.0	<20.0	20	2	1.9	799	820	0.4	292	35
MJVD-1-32	0.04	20	<20	<0.01	1,775	2	12.5	55	16.4	9.0	<30.0	36	1	3.0	1,185	1,080	0.5	560	35
MJVD-1-33	0.05	36	<20	<0.01	2,640	0.5	4.5	90	22.0	10.8	<150.0	56	<1	3.7	1,770	1,550	0.4	847	5
MJVD-1-34	0.05	64	<20	<0.01	3,700	0.3	7.5	230	33.4	14.7	<100.0	81	<1	5.1	2,420	3,960	0.5	1,180	15
MJVD-1-35	0.05	18	<20	<0.01	798	0.2	2.5	65	19.7	7.2	<30.0	34	<1	3.3	449	950	0.5	316	<5
MJVD-1-36	0.04	32	<20	<0.01	1,985	0.1	5.0	65	19.8	10.0	<150.0	57	<1	3.2	1,105	1,020	0.3	786	<5
MJVD-1-37	0.05	26	<20	<0.01	5,460	0.4	4.5	80	31.1	13.4	<150.0	98	<1	4.7	3,690	1,350	0.3	1,665	<5
MJVD-1-38	0.04	24	<20	<0.01	3,500	0.2	3.5	80	25.6	10.8	<150.0	92	<1	3.4	1,915	1,390	0.3	1,385	<5
MJVD-1-39	0.04	48	<20	<0.01	4,290	0.3	6.0	190	40.8	17.3	<150.0	105	<1	6.9	2,670	3,260	0.5	1,460	5
MJVD-1-40	0.04	58	<20	<0.01	5,890	0.2	5.5	200	49.3	19.8	<150.0	141	<1	7.9	3,690	3,510	0.6	2,010	<5
MJVD-1-41	0.04	40	<20	<0.01	11,170	0.2	5.0	140	48.6	21.4	<150.0	160	<1	7.2	8,310	2,400	0.6	2,980	<5
MJVD-1-42	0.06	44	<20	<0.01	8,700	0.6	8.0	100	32.9	15.8	<150.0	107	<1	5.0	6,920	2,270	0.7	2,200	5
MJVD-1-43	0.06	30	<20	<0.01	8,600	0.5	4.5	110	34.8	16.7	<150.0	117	<1	5.6	6,490	2,310	0.4	2,260	<5
MJVD-1-44	0.04	28	<20	<0.01	7,630	1.1	8.0	95	32.7	13.9	<100.0	111	<1	5.2	5,850	3,020	0.5	1,970	<5
MJVD-1-45	0.04	48	<20	0.01	10,780	0.9	8.0	150	37.6	17.9	<150.0	109	<1	5.6	5,810	3,330	0.7	2,030	5
MJVD-1-46	0.04	48	<20	0.02	13,580	1.5	9.5	160	45.4	19.3	<150.0	138	1	6.6	8,670	3,470	0.7	2,510	5
MJVD-1-47	0.04	16	<20	<0.01	10,420	0.2	4.0	95	45.7	18.6	<150.0	126	<1	6.1	8,260	2,580	0.4	2,570	<5
MJVD-1-48	0.03	22	<20	<0.01	6,020	0.2	2.0	30	28.2	9.8	<40.0	79	<1	3.9	4,980	1,720	0.2	1,485	10
MJVD-1-49	0.03	38	<20	<0.01	4,210	0.2	1.5	35	16.2	6.1	<80.0	53	<1	2.0	3,390	900	0.2	1,015	<5
MJVD-1-50	0.03	12	<20	<0.01	5,050	0.6	5.5	45	23.4	8.8	<100.0	73	<1	3.4	3,910	2,280	0.3	1,300	35
MJVD-1-51	0.04	10	<20	<0.01	5,200	0.5	3.0	55	25.0	10.8	<150.0	80	<1	3.8	3,960	2,050	0.3	1,425	20
MJVD-1-52	0.04	8	<20	<0.01	4,590	0.9	9.5	55	19.4	8.3	<150.0	58	<1	3.0	3,700	730	0.4	1,145	5
MJVD-1-53	0.03	24	<20	<0.01	4,610	2	12.5	130	29.5	14.5	<100.0	83	1	5.1	2,990	2,370	0.7	1,315	20
MJVD-1-54	0.03	24	<20	<0.01	4,780	1.9	16.5	120	29.7	14.7	<100.0	80	1	5.2	3,190	1,870	0.8	1,325	45
MJVD-1-55	0.03	24	<20	<0.01	4,370	1.9	14.0	140	26.8	14.4	<100.0	70	1	4.6	2,750	2,330	0.7	1,180	15
MJVD-1-56	0.04	26	<20	<0.01	3,130	1.6	12.0	120	24.4	10.9	<100.0	62	1	3.9	2,150	1,580	0.5	938	25
MJVD-1-57	0.04	32	<20	<0.01	4,450	1	13.0	150	29.5	12.8	<100.0	96	<1	4.9	2,750	3,020	0.5	1,495	30

MJVD-1 (4/126)

Sample Name	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm	Ho ppm	La ppm	Pb ppm	Lu ppm	Nd ppm	Ni ppm
MJVD-1-58	0.05	18	<20	<0.01	4,420	0.6	5.0	80	18.2	7.5	<150.0	59	<1	2.9	3,420	1,240	0.3	1,120	5
MJVD-1-59	0.05	26	<20	<0.01	3,430	0.4	5.0	80	20.4	8.3	<150.0	61	<1	2.9	2,410	1,110	0.3	975	10
MJVD-1-60	0.05	26	<20	<0.01	4,390	1	6.0	100	20.2	9.8	<150.0	71	<1	3.2	3,230	1,530	0.4	1,195	<5
MJVD-1-61	0.04	26	2	<0.01	4,140	0.8	5.5	85	22.1	9.3	<150.0	67	<1	3.5	3,000	1,580	0.4	1,140	10
MJVD-1-62	0.05	28	<20	<0.01	5,170	1.1	4.0	100	29.7	12.5	<100.0	92	<1	4.2	3,610	1,880	0.3	1,580	15
MJVD-1-63	0.05	28	<20	<0.01	4,850	0.3	5.0	90	22.4	9.5	<150.0	81	<1	3.1	3,380	1,800	0.3	1,435	<5
MJVD-1-64	0.05	20	<20	<0.01	3,800	0.2	2.5	90	22.0	8.9	<200	67	<1	2.9	2,670	1,190	0.2	1,095	<5
MJVD-1-65	0.05	26	<20	<0.01	5,580	0.2	3.0	100	27.9	10.8	<300	88	<1	4.0	3,980	3,110	0.3	1,520	<5
MJVD-1-66	0.05	42	<20	<0.01	5,020	0.5	5.5	120	24.3	9.6	<300	81	<1	3.3	3,510	2,890	0.2	1,440	<5
MJVD-1-67	0.05	42	<20	<0.01	4,520	0.3	4.0	120	22.7	9.3	<300	71	<1	3.3	3,270	1,780	0.3	1,210	<5
MJVD-1-68	0.04	62	<20	<0.01	6,710	0.1	7.0	95	33.5	14.3	<300	119	<1	4.8	4,380	1,270	0.3	2,100	<5
MJVD-1-69	0.04	20	<20	<0.01	3,200	0.2	3.0	55	23.4	9.6	<200	64	<1	4.0	2,270	880	0.4	935	<5
MJVD-1-70	0.04	14	<20	<0.01	1,445	0.1	4.5	55	15.4	7.1	<100.0	34	<1	2.0	979	800	0.5	444	25
MJVD-1-71	0.04	14	<20	<0.01	2,240	0.1	2.5	50	21.2	9.5	<150.0	55	<1	3.3	1,540	810	0.5	710	5
MJVD-1-72	0.04	14	<20	<0.01	1,175	0.1	2.0	30	15.4	6.7	<70.0	34	<1	2.6	744	590	0.5	418	<5
MJVD-1-73	0.05	14	<20	<0.01	3,510	0.1	1.5	65	18.6	9.4	<200	52	<1	3.2	2,560	600	0.4	968	<5
MJVD-1-74	0.05	8	<20	<0.01	656	0.1	<0.5	10	4.1	2.5	<100.0	11	<1	0.8	483	300	0.2	176	<5
MJVD-1-75	0.03	14	<20	<0.01	1,785	0.3	2.0	30	10.8	5.0	<100.0	34	<1	1.9	1,265	320	0.4	501	<5
MJVD-1-76	0.04	26	<20	<0.01	1,890	<0.1	3.5	40	11.9	5.3	<100.0	36	<1	1.9	1,310	660	0.2	562	<5
MJVD-1-77	0.04	22	<20	<0.01	2,420	0.8	3.5	50	15.2	8.2	<100.0	44	<1	2.5	1,690	640	0.3	685	<5
MJVD-1-78	0.05	30	<20	0.01	3,220	1.9	10.0	45	20.0	9.2	<100.0	58	<1	3.0	2,250	1,600	0.5	925	15
MJVD-1-79	0.04	20	<20	<0.01	4,840	0.3	4.0	25	25.6	14.4	<80.0	76	<1	4.3	3,500	1,210	0.6	1,305	<5
MJVD-1-80	0.04	40	<20	0.01	3,810	3.4	9.5	55	27.3	14.1	<70.0	68	<1	4.9	2,750	1,970	0.6	1,045	40

MJVD-1 (5/126)

Sample Name	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-1-1	91	439	84.8	142	<1	1,835	1.0	8.2	3.5	33	1.4	2	99	30.0	145	7.5	116	625	195
MJVD-1-2	92	396	73.6	132	<1	1,925	1.5	7.3	2.5	25	1.3	1	84	30.0	160	5.5	100	610	190
MJVD-1-3	97	581	54.6	204	<1	2,130	2.0	11.1	2.0	29	1.5	1	61	40.0	120	8.0	136	450	131
MJVD-1-4	98	729	29.2	282	<1	1,835	1.0	16.0	2.5	40	1.6	1	73	50.0	85	7.0	200	635	74
MJVD-1-5	95	713	48.0	277	<1	2,610	1.0	15.2	6.0	43	2.8	1	258	40.0	100	11.3	228	760	113
MJVD-1-6	119	1,100	30.4	453	<1	2,540	1.5	24.0	10.5	71	3.4	<1	383	45.0	100	14.9	274	1,260	82
MJVD-1-7	117	694	16.2	296	<1	2,290	2.0	16.5	2.5	57	1.8	<1	43	70.0	50	8.9	188	825	51
MJVD-1-8	125	567	29.2	220	<1	1,935	2.0	13.6	1.5	30	1.7	1	71	55.0	115	9.5	206	750	82
MJVD-1-9	160	397	33.0	167	<1	1,730	2.0	10.5	2.0	19	1.4	<1	61	75.0	70	6.2	167	585	65
MJVD-1-10	67	182	37.4	73	<1	1,290	1.0	4.5	0.5	7	0.8	<1	27	40.0	65	4.0	83	635	85
MJVD-1-11	54	133	39.4	58	<1	1,175	1.0	4.4	1.0	6	1.1	<1	26	35.0	95	3.9	77	1,000	101
MJVD-1-12	45	67	63.6	29	<1	1,160	1.0	2.2	1.5	6	0.8	1	33	20.0	105	4.8	59	1,185	147
MJVD-1-13	56	215	36.4	92	<1	1,595	0.5	6.4	1.0	14	0.9	3	19	105.0	65	4.9	102	1,400	89
MJVD-1-14	114	227	35.2	102	<1	1,475	1.5	6.7	1.0	13	1.1	<1	21	165.0	75	5.0	105	1,185	89
MJVD-1-15	87	252	16.0	110	<1	1,415	1.0	8.1	0.5	6	0.9	<1	5	60.0	585	4.7	131	1,075	43
MJVD-1-16	68	379	11.8	163	<1	1,885	0.5	10.3	<0.5	19	0.8	<1	3	45.0	30	4.8	142	1,110	22
MJVD-1-17	39	309	8.0	123	<1	3,050	3.5	8.0	<0.5	14	0.9	<1	3	30.0	30	3.6	117	600	31
MJVD-1-18	48	197	5.2	69	<1	2,520	0.5	4.5	<0.5	4	0.6	<1	<1	40.0	25	2.5	73	435	15
MJVD-1-19	33	315	4.4	106	<1	3,070	0.5	5.7	<0.5	13	0.8	<1	<1	25.0	20	3.2	86	525	24
MJVD-1-20	28	200	3.6	76	<1	2,710	0.5	4.8	<0.5	8	0.6	<1	<1	20.0	35	2.5	72	435	12
MJVD-1-21	38	204	5.2	76	<1	2,380	0.5	4.6	1.5	4	0.7	<1	<1	20.0	30	4.0	71	560	25
MJVD-1-22	25	125	3.0	50	<1	2,310	<0.5	3.4	<0.5	5	0.5	<1	<1	20.0	40	3.5	62	575	31
MJVD-1-23	19	108	2.8	51	<1	2,510	<0.5	2.8	<0.5	<1	0.5	<1	<1	30.0	30	2.3	46	435	19
MJVD-1-24	21	81	3.4	36	<1	2,520	<0.5	2.4	<0.5	<1	0.3	<1	2	15.0	20	3.1	45	360	45
MJVD-1-25	27	165	4.8	61	<1	3,040	<0.5	3.8	<0.5	3	0.7	<1	<1	30.0	30	3.0	62	360	29
MJVD-1-26	32	135	7.0	52	<1	2,360	1.0	3.1	<0.5	6	0.5	<1	4	25.0	65	2.7	53	310	43
MJVD-1-27	127	201	8.8	72	<1	2,730	2.5	4.5	<0.5	5	0.8	<1	6	40.0	20	3.8	66	510	50
MJVD-1-28	24	133	9.4	55	<1	2,960	<0.5	3.4	<0.5	1	0.6	<1	2	10.0	15	3.1	61	460	30
MJVD-1-29	31	143	5.0	70	<1	3,180	0.5	4.0	<0.5	6	0.6	<1	1	10.0	40	3.3	64	435	31
MJVD-1-30	76	98	24.6	42	<1	1,045	1.0	3.0	0.5	9	0.5	2	40	25.0	70	2.8	52	600	125
MJVD-1-31	63	101	46.2	37	<1	1,175	1.0	2.6	0.5	11	0.4	1	44	20.0	120	3.8	50	785	156
MJVD-1-32	64	183	48.6	75	2	1,485	0.5	5.0	0.5	13	1.3	<1	36	20.0	105	5.0	90	950	135
MJVD-1-33	63	268	11.6	130	<1	2,670	0.5	7.1	<0.5	14	0.9	<1	4	25.0	30	4.5	101	685	28
MJVD-1-34	118	375	16.0	159	<1	2,470	1.5	9.5	<0.5	21	1.2	<1	6	50.0	40	4.7	154	1,300	26
MJVD-1-35	51	90	9.0	57	<1	4,060	0.5	4.3	<0.5	2	1.0	<1	<1	20.0	50	3.9	107	835	21
MJVD-1-36	65	225	5.2	129	<1	3,450	0.5	6.8	<0.5	12	0.8	<1	<1	20.0	20	3.0	96	525	9
MJVD-1-37	74	535	10.0	218	<1	2,790	0.5	10.8	<0.5	31	0.9	1	<1	35.0	30	3.6	123	685	18
MJVD-1-38	63	395	6.8	211	<1	3,040	0.5	9.1	<0.5	28	0.6	<1	<1	30.0	50	3.1	107	700	24
MJVD-1-39	101	451	14.2	212	<1	3,010	1.5	12.6	<0.5	22	1.3	2	4	55.0	30	4.7	184	1,200	17
MJVD-1-40	118	621	13.0	275	<1	3,090	1.5	15.9	0.5	37	1.6	1	5	70.0	35	5.5	218	1,260	17
MJVD-1-41	74	1,040	8.6	323	<1	3,310	1.5	17.5	<0.5	45	1.1	<1	30	60.0	45	6.0	201	1,000	17
MJVD-1-42	56	771	17.8	237	<1	3,520	1.0	12.0	<0.5	39	0.8	<1	8	35.0	35	4.2	137	985	33
MJVD-1-43	66	785	9.2	248	<1	3,210	1.0	13.2	0.5	33	0.9	<1	4	45.0	20	4.3	151	810	24
MJVD-1-44	80	691	24.6	213	<1	2,390	1.0	12.0	0.5	31	1.3	2	35	50.0	65	4.5	147	750	51
MJVD-1-45	130	710	18.2	242	<1	3,510	2.0	13.9	2.0	41	1.2	1	39	65.0	85	5.4	167	1,010	56
MJVD-1-46	152	920	22.2	263	<1	3,480	4.0	15.9	1.5	57	1.5	3	58	70.0	120	5.7	192	1,010	85
MJVD-1-47	52	929	5.8	260	<1	3,340	0.5	15.0	<0.5	24	0.8	<1	0	55.0	50	3.9	170	1,185	16
MJVD-1-48	21	527	3.2	152	<1	1,465	<0.5	9.8	<0.5	10	0.7	<1	<1	30.0	60	2.7	120	485	29
MJVD-1-49	24	369	3.6	113	<1	2,420	0.5	6.1	<0.5	12	0.5	1	<1	20.0	50	2.1	69	475	17
MJVD-1-50	25	459	11.0	142	<1	2,750	<0.5	7.8	<0.5	10	0.7	3	1	30.0	90	2.5	104	950	42
MJVD-1-51	38	481	13.2	174	<1	3,470	1.0	9.0	<0.5	16	0.8	3	<1	30.0	80	3.5	111	835	29
MJVD-1-52	59	398	22.2	128	<1	3,770	0.5	6.8	0.5	12	0.6	3	6	25.0	40	3.7	80	775	55
MJVD-1-53	99	424	43.6	166	4	2,620	1.5	9.9	2.5	30	1.4	2	78	45.0	110	5.9	128	1,060	126
MJVD-1-54	135	434	42.8	161	3	3,010	2.0	10.1	2.0	31	1.4	3	53	55.0	110	6.2	137	1,650	147
MJVD-1-55	110	398	44.2	152	4	2,840	1.5	8.4	2.0	29	1.3	2	62	45.0	110	6.4	124	1,235	131
MJVD-1-56	117	305	41.6	128	1	3,040	1.0	7.1	1.0	20	1.2	2	34	45.0	100	5.1	113	1,275	118
MJVD-1-57	123	456	34.2	197	2	3,090	1.5	10.7	1.0	35	1.0	1	16	40.0	85	4.5	129	1,460	71

MJVD-1 (6/126)

Sample Name	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-1-58	56	392	18.2	167	<1	4,560	0.5	6.4	<0.5	15	0.6	3	4	25.0	60	2.8	75	900	33
MJVD-1-59	91	326	17.4	142	<1	3,220	5.0	7.0	0.5	12	0.7	5	26	30.0	75	2.6	87	675	54
MJVD-1-60	84	402	19.4	149	<1	2,990	3.0	8.0	<0.5	15	0.8	2	17	30.0	50	3.2	96	750	58
MJVD-1-61	105	393	26.6	137	<1	3,070	3.5	7.2	0.5	16	0.9	1	21	35.0	75	3.3	95	860	79
MJVD-1-62	83	505	21.0	221	2	3,410	3.0	10.2	0.5	43	0.9	4	11	35.0	60	4.1	122	885	61
MJVD-1-63	62	472	9.6	200	1	4,350	1.0	8.3	<0.5	26	0.5	1	1	30.0	45	2.4	88	710	21
MJVD-1-64	49	365	6.2	179	<1	4,760	1.0	7.4	<0.5	14	0.4	<1	<1	25.0	45	2.1	78	585	16
MJVD-1-65	63	518	7.4	212	<1	4,580	1.5	9.7	<0.5	20	0.7	1	<1	35.0	30	2.4	110	675	23
MJVD-1-66	63	486	10.8	208	1	4,950	1.0	9.8	<0.5	21	0.7	<1	<1	35.0	45	3.1	97	635	24
MJVD-1-67	59	420	8.6	180	<1	4,970	2.5	8.3	<0.5	12	0.4	1	<1	25.0	40	1.9	92	810	12
MJVD-1-68	137	685	5.0	284	<1	4,730	5.0	12.4	<0.5	40	0.7	2	14	50.0	60	3.4	125	850	12
MJVD-1-69	58	302	4.6	156	<1	4,970	2.0	7.7	<0.5	10	0.9	<1	3	25.0	35	3.1	104	575	11
MJVD-1-70	30	142	3.8	69	<1	3,240	1.0	4.6	<0.5	2	0.8	<1	1	15.0	35	4.2	70	375	9
MJVD-1-71	57	223	2.6	121	<1	3,590	1.0	5.9	<0.5	17	1.1	<1	3	20.0	35	4.8	91	310	7
MJVD-1-72	55	123	3.8	75	<1	2,600	0.5	4.3	<0.5	10	0.9	<1	1	15.0	30	4.2	76	200	2
MJVD-1-73	39	331	2.0	135	<1	7,410	1.0	6.3	<0.5	12	0.7	<1	<1	15.0	30	4.3	99	460	7
MJVD-1-74	5	58	0.6	98	<1	8,380	<0.5	1.4	<0.5	<1	0.2	<1	<1	<0.5	5	1.6	20	50	8
MJVD-1-75	16	170	0.8	119	<1	4,970	0.5	3.7	<0.5	3	0.6	<1	<1	5.0	25	3.4	51	175	<0.5
MJVD-1-76	51	184	3.2	120	<1	5,740	1.0	3.8	<0.5	5	0.5	2	12	15.0	10	3.1	56	310	5
MJVD-1-77	121	235	11.6	98	1	5,270	1.0	5.2	<0.5	6	0.7	1	13	30.0	35	3.1	68	400	23
MJVD-1-78	86	307	21.0	139	<1	5,370	1.0	6.5	1.5	17	0.8	3	57	20.0	50	3.8	86	660	65
MJVD-1-79	50	446	2.4	150	<1	4,240	0.5	8.3	0.5	6	1.2	<1	31	25.0	35	5.4	127	460	26
MJVD-1-80	150	356	21.0	125	<1	4,050	1.0	8.2	1.0	6	1.3	5	31	50.0	55	5.9	134	710	84

MJVD-2 (7/126)

Sample Name	F	Ba	Al	As	B	Be	Bi	Ca	Cd	Cr	Fe	Ga	Hg	K	Mg	Mn	Mo
	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%	ppm	ppm
MJVD-2-1	0.1	31.70	2.83	114	<10	<5.0	<10	0.13	0.5	63	5.62	<100	3	0.05	0.04	>10,000	16
MJVD-2-2	0.1	38.80	1.53	138	<10	<5.0	<10	0.08	0.5	37	3.82	<100	3	0.04	0.02	9,120	13
MJVD-2-3	0.1	34.80	1.01	244	<10	<5.0	<10	0.08	0.5	21	4.32	<100	3	0.04	0.01	>10,000	34
MJVD-2-4	0.1	29.50	1.43	166	<10	<5.0	<10	0.08	0.5	31	3.81	<100	1	0.07	0.04	7,780	26
MJVD-2-5	0.2	20.00	1.52	102	<10	<5.0	<10	0.09	<0.5	14	1.78	<100	1	0.12	0.03	>10,000	7
MJVD-2-6	0.2	3.66	1.60	110	<10	<5.0	<10	0.05	<0.5	8	1.37	<100	<1	0.15	0.03	>10,000	3
MJVD-2-7	0.1	1.59	1.32	104	<10	<5.0	<10	0.03	<0.5	8	1.26	<100	<1	0.13	0.02	1,440	1
MJVD-2-8	0.1	4.46	1.66	116	<10	<5.0	<10	0.09	<0.5	10	1.56	<100	1	0.13	0.04	3,100	5
MJVD-2-9	0.2	2.16	1.59	122	<10	<5.0	<10	0.09	<0.5	6	1.45	<100	<1	0.14	0.03	3,850	2
MJVD-2-10	0.2	18.05	1.37	248	<10	<5.0	<10	0.08	<0.5	18	2.72	<100	4	0.12	0.03	>10,000	12
MJVD-2-11	0.4	45.80	0.72	454	<10	<5.0	<10	0.27	<0.5	16	1.04	<100	<1	0.11	0.03	1,915	6
MJVD-2-12	0.5	44.90	0.22	712	<10	<5.0	<10	0.13	<0.5	15	0.39	<100	<1	0.04	0.01	1,845	6
MJVD-2-13	0.1	41.40	0.52	1,240	<10	<5.0	<10	0.16	<0.5	13	0.61	<100	<1	0.11	0.01	4,410	11
MJVD-2-14	3.6	41.90	0.39	656	920	<5.0	<10	3.32	0.5	9	0.46	<100	<1	0.13	0.01	4,270	6
MJVD-2-15	7.8	35.10	0.86	426	840	<5.0	<10	7.13	0.5	8	0.54	<100	<1	0.63	0.07	2,400	9
MJVD-2-16	9.8	36.30	0.61	276	1,770	<5.0	<10	6.84	0.5	9	0.56	<100	<1	0.23	0.02	2,690	4
MJVD-2-17	7.7	31.60	0.76	508	1,100	<5.0	<10	5.40	0.5	15	1.69	<100	<1	0.24	0.05	7,060	9
MJVD-2-18	11.3	30.10	0.53	490	1,630	<5.0	<10	6.07	0.5	7	0.45	<100	<1	0.20	0.02	3,010	8
MJVD-2-19	1.0	47.00	0.61	196	<10	<5.0	<10	0.84	<0.5	21	1.74	<100	<1	0.07	0.03	1,450	34
MJVD-2-20	1.9	39.60	0.54	404	20	<5.0	<10	1.97	0.5	49	5.11	<100	4	0.29	0.17	>10,000	25
MJVD-2-21	0.4	49.80	0.19	526	<10	<5.0	<10	0.22	0.5	15	1.16	<100	<1	0.05	0.03	3,720	11
MJVD-2-22	0.4	46.80	0.17	360	<10	<5.0	<10	0.12	0.5	10	0.90	<100	<1	0.04	0.01	3,870	7
MJVD-2-23	1.3	45.60	0.31	306	10	<5.0	<10	1.15	0.5	15	1.24	<100	<1	0.14	0.08	2,620	8
MJVD-2-24	0.3	46.80	0.48	356	<10	<5.0	<10	0.07	1.5	21	2.16	<100	<1	0.06	0.06	7,510	15
MJVD-2-25	0.2	44.90	0.26	362	<10	<5.0	10	0.07	1.5	16	1.85	<100	4	0.04	0.03	>10,000	19
MJVD-2-26	0.2	45.90	0.24	430	<10	<5.0	10	0.07	2.0	16	1.78	<100	2	0.02	0.01	>10,000	17
MJVD-2-27	1.0	47.00	0.48	226	<10	<5.0	<10	1.08	0.5	18	1.93	<100	2	0.13	0.06	6,100	13
MJVD-2-28	0.3	40.80	0.73	420	<10	5	10	0.25	3.0	31	3.42	<100	4	0.05	0.02	>10,000	28
MJVD-2-29	0.2	35.80	0.99	444	<10	5	10	0.12	2.5	51	4.84	<100	5	0.04	0.03	>10,000	33
MJVD-2-30	0.3	38.50	0.77	422	<10	5	40	0.16	2.0	41	4.99	<100	5	0.04	0.03	>10,000	47
MJVD-2-31	0.7	33.60	1.67	736	<10	5	10	0.23	3.0	121	3.85	<100	1	0.14	0.08	7,690	28
MJVD-2-32	0.3	41.60	0.94	220	<10	5	<10	0.18	1.0	46	2.86	<100	1	0.06	0.02	6,110	14
MJVD-2-33	0.4	12.05	1.27	258	<10	10	<10	0.12	1.5	195	5.41	<100	2	0.12	0.14	3,810	9
MJVD-2-34	0.5	24.20	1.95	292	<10	5	<10	0.16	4.0	239	4.25	<100	1	0.14	0.50	5,960	10
MJVD-2-35	0.4	45.50	0.45	580	<10	<5.0	<10	0.07	3.0	42	1.92	<100	<1	0.05	0.03	4,010	12
MJVD-2-36	0.6	23.70	2.06	718	<10	5	<10	0.25	3.5	142	3.18	<100	1	0.15	0.60	6,360	12
MJVD-2-37	0.2	2.52	2.05	160	<10	10	<10	0.62	1.5	323	5.13	<100	<1	0.36	1.53	2,110	3
MJVD-2-38	0.5	4.94	2.16	146	<10	10	<10	2.06	3.0	308	4.19	<100	<1	0.34	1.93	1,415	4
MJVD-2-39	0.9	12.40	2.65	308	<10	5	<10	4.02	3.0	218	3.67	<100	1	0.28	1.52	1,825	5
MJVD-2-40	1.1	4.80	0.29	424	40	<5.0	<10	>15.00	1.5	10	0.62	<100	<1	0.10	0.16	2,700	2
MJVD-2-41	0.9	6.57	1.26	240	<10	5	<10	>15.00	2.0	40	1.56	<100	<1	0.13	0.17	4,780	4
MJVD-2-42	1.6	8.73	0.23	154	270	<5.0	<10	>15.00	1.5	14	0.77	<100	<1	0.09	0.15	2,950	<1
MJVD-2-43	0.5	11.45	0.15	98	<10	<5.0	<10	>15.00	3.5	13	0.91	<100	<1	0.05	0.07	3,560	3
MJVD-2-44	3.8	9.85	0.31	88	820	<5.0	<10	>15.00	1.0	10	0.51	<100	<1	0.13	0.09	2,660	<1
MJVD-2-45	0.4	3.54	0.09	22	<10	<5.0	<10	>15.00	<0.5	4	0.28	<100	<1	0.04	0.40	1,495	<1
MJVD-2-46	0.4	3.16	0.07	88	30	<5.0	<10	>15.00	<0.5	3	0.11	<100	<1	0.03	0.26	1,715	<1
MJVD-2-47	0.9	9.29	0.21	42	30	<5.0	<10	>15.00	0.5	6	0.28	<100	<1	0.08	0.09	2,440	<1
MJVD-2-48	1.1	9.80	1.51	372	<10	<5.0	<10	>15.00	1.5	37	1.36	<100	<1	0.15	0.22	3,640	4
MJVD-2-49	0.3	2.07	0.32	82	<10	<5.0	<10	>15.00	1.5	13	0.64	<100	<1	0.06	0.25	3,160	<1
MJVD-2-50	0.3	1.32	0.07	26	<10	<5.0	<10	>15.00	0.5	4	0.25	<100	<1	0.03	0.15	2,170	9
MJVD-2-51	2.2	8.91	0.16	90	600	<5.0	<10	>15.00	3.5	6	0.43	<100	<1	0.08	0.06	2,850	10
MJVD-2-52	1.9	18.95	0.41	94	280	<5.0	<10	>15.00	1.5	14	0.94	<100	<1	0.11	0.09	2,790	10
MJVD-2-53	0.7	12.20	0.10	84	130	<5.0	<10	>15.00	1.5	9	0.90	<100	2	0.04	0.07	2,340	11
MJVD-2-54	3.1	18.95	1.06	284	60	10	<10	9.46	1.0	37	1.60	<100	<1	0.55	0.52	8,500	11
MJVD-2-55	2.1	35.30	1.23	212	30	5	<10	2.88	<0.5	26	1.58	<100	<1	0.33	0.16	5,960	9
MJVD-2-56	1.3	12.15	1.56	188	<10	10	<10	9.01	1.5	51	2.70	<100	1	0.36	0.19	3,950	6
MJVD-2-57	0.9	13.20	2.14	192	<10	10	<10	3.30	0.5	189	3.85	<100	<1	0.36	0.91	3,200	9

MJVD-2 (8/126)

Sample Name	F %	Ba %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm	Mo ppm
MJVD-2-58	1.1	16.00	0.85	220	<10	5	<10	12.25	1.5	53	1.99	<100	<1	0.16	0.25	3,840	11
MJVD-2-59	1.4	24.10	1.16	272	<10	5	<10	9.45	0.5	110	2.18	<100	<1	0.23	0.49	7,740	11
MJVD-2-60	2.3	26.40	1.21	362	20	5	<10	7.27	0.5	77	2.86	<100	<1	0.30	0.35	5,330	14
MJVD-2-61	1.6	28.20	1.42	298	<10	10	<10	5.55	0.5	149	2.51	<100	<1	0.26	0.57	6,600	12
MJVD-2-62	1.9	22.80	1.54	500	10	10	<10	4.39	0.5	115	2.37	<100	<1	0.44	0.68	9,720	17
MJVD-2-63	2.2	27.30	1.24	386	20	5	<10	6.99	1.0	58	2.27	<100	<1	0.26	0.34	7,990	13
MJVD-2-64	1.1	25.70	0.48	330	10	5	<10	9.71	0.5	26	2.01	<100	<1	0.14	0.08	4,480	7
MJVD-2-65	2.9	22.20	1.01	782	160	5	<10	5.00	0.5	49	2.18	<100	<1	0.35	0.28	>10,000	21
MJVD-2-66	1.6	26.70	0.69	266	10	5	<10	9.04	1.0	32	2.30	<100	<1	0.21	0.12	4,650	10
MJVD-2-67	1.5	18.75	1.65	236	10	5	<10	8.84	1.0	27	1.81	<100	<1	0.60	0.13	4,030	7
MJVD-2-68	0.3	0.60	0.62	30	<10	<5.0	<10	2.69	<0.5	12	0.57	<100	1	0.23	0.05	3,160	5
MJVD-2-69	0.4	13.90	0.71	194	<10	5	<10	11.45	0.5	22	1.76	<100	<1	0.24	0.10	6,800	8
MJVD-2-70	1.1	9.63	0.75	362	10	5	<10	>15.00	1.5	22	0.81	<100	<1	0.16	0.13	7,850	14
MJVD-2-71	0.8	15.15	0.99	322	<10	5	<10	12.05	1.5	34	1.85	<100	<1	0.16	0.20	7,090	9
MJVD-2-72	0.4	15.15	0.55	150	<10	<5.0	<10	>15.00	1.5	16	0.97	<100	<1	0.10	0.13	3,590	11
MJVD-2-73	0.7	4.67	0.24	376	20	<5.0	<10	>15.00	1.5	7	0.39	<100	<1	0.09	0.13	2,790	9
MJVD-2-74	0.4	4.72	0.09	198	40	<5.0	<10	>15.00	0.5	3	0.25	<100	<1	0.05	0.12	2,190	9
MJVD-2-75	0.3	5.63	0.07	144	<10	<5.0	<10	>15.00	<0.5	3	0.17	<100	<1	0.07	0.22	1,585	7
MJVD-2-76	0.3	9.06	0.06	84	<10	<5.0	<10	>15.00	0.5	5	0.45	<100	<1	0.05	0.16	2,370	10
MJVD-2-77	0.8	9.13	0.10	80	20	<5.0	<10	>15.00	1.0	3	0.32	<100	<1	0.14	0.20	2,960	12
MJVD-2-78	1.4	15.15	0.08	152	160	<5.0	<10	>15.00	3.5	2	0.19	<100	<1	0.12	0.14	3,250	10
MJVD-2-79	0.7	12.75	0.05	52	<10	<5.0	<10	>15.00	1.5	2	0.37	<100	<1	0.18	0.25	3,020	9
MJVD-2-80	0.4	4.43	0.11	90	<10	<5.0	<10	>15.00	0.5	5	0.34	<100	<1	0.14	0.24	2,060	9

MJVD-2 (9/126)

Sample Name	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm	Ho ppm
MJVD-2-1	<0.01	1,770	0.05	14	<20	0.02	16,990	3.1	11.5	95	26.3	12.1	<100.0	53	1	4.4
MJVD-2-2	<0.01	1,640	0.04	18	<20	0.01	11,200	1.8	7.5	90	30.5	13.3	<100.0	72	<1	5.0
MJVD-2-3	<0.01	2,800	0.04	14	<20	<0.01	8,430	2.4	8.0	120	62.6	28.0	<100.0	157	2	10.6
MJVD-2-4	<0.01	1,600	0.04	8	<20	<0.01	8,450	4.2	7.0	110	39.5	17.2	<100.0	93	<1	5.9
MJVD-2-5	<0.01	630	0.04	2	<20	<0.01	4,460	6.1	3.5	50	22.1	10.2	<100.0	71	2	3.2
MJVD-2-6	<0.01	390	0.04	<2	<20	<0.01	2,060	8.8	1.5	30	14.6	7.9	<30.0	47	4	2.3
MJVD-2-7	<0.01	280	0.05	<2	<20	<0.01	1,570	7.5	2.5	20	13.1	7.9	<20.0	48	4	2.3
MJVD-2-8	0.01	440	0.04	<2	<20	<0.01	2,980	8.8	5.5	30	15.8	9.0	<40.0	51	3	2.5
MJVD-2-9	<0.01	330	0.05	<2	<20	<0.01	2,860	9.3	3.5	25	14.1	9.3	<20.0	46	5	2.4
MJVD-2-10	<0.01	1,830	0.04	4	<20	<0.01	10,390	8.8	8.5	75	39.5	18.0	<150.0	113	2	6.0
MJVD-2-11	0.01	460	0.05	14	<20	<0.01	11,420	1.2	2.5	45	43.9	23.2	<200	191	<1	6.4
MJVD-2-12	0.01	330	0.05	12	<20	<0.01	16,770	0.3	<0.5	25	53.6	30.6	<200	255	<1	8.0
MJVD-2-13	0.01	1,020	0.03	10	<20	<0.01	37,400	0.5	1.5	55	110.5	57.2	<400	542	<1	13.6
MJVD-2-14	0.14	1,500	0.03	12	<20	<0.01	22,600	0.3	1.0	70	115.5	57.2	<400	470	<1	17.3
MJVD-2-15	0.14	930	0.04	10	<20	<0.01	25,400	0.7	2.0	30	91.5	47.4	<400	328	7	15.1
MJVD-2-16	0.27	590	0.03	8	<20	<0.01	22,800	0.4	1.5	45	54.3	33.8	<400	261	2	8.4
MJVD-2-17	0.18	1,040	0.02	34	<20	0.01	41,400	0.7	5.0	130	70.7	45.1	<400	385	1	10.4
MJVD-2-18	0.25	560	0.03	22	<20	<0.01	63,800	0.3	2.0	45	70.8	52.5	<300	472	1	9.4
MJVD-2-19	<0.01	640	0.04	16	<20	<0.01	17,500	0.3	1.0	25	12.8	6.2	<100.0	53	<1	2.0
MJVD-2-20	0.01	2,320	0.02	104	<20	0.01	10,350	0.8	8.5	180	72.7	33.8	<100.0	198	<1	11.3
MJVD-2-21	<0.01	900	0.03	26	1	<0.01	13,090	0.4	2.0	55	36.7	21.3	<200	147	<1	6.0
MJVD-2-22	<0.01	600	0.04	24	<20	<0.01	12,290	0.3	1.5	55	35.5	17.9	<200	134	<1	5.0
MJVD-2-23	0.01	1,110	0.03	18	<20	<0.01	14,640	0.6	1.5	40	46.2	28.7	<200	174	<1	7.7
MJVD-2-24	<0.01	3,190	0.02	38	<20	<0.01	12,620	0.7	3.0	135	66.3	34.2	<200	225	<1	10.9
MJVD-2-25	<0.01	1,900	0.03	50	<20	<0.01	12,120	0.6	7.5	260	66.1	34.3	<200	190	<1	10.9
MJVD-2-26	<0.01	3,120	0.03	54	<20	<0.01	14,240	0.3	4.0	230	75.8	36.8	<200	223	<1	12.1
MJVD-2-27	0.01	1,760	0.03	40	<20	<0.01	8,730	0.4	3.5	140	41.5	20.4	<200	129	<1	6.9
MJVD-2-28	0.01	4,440	0.02	108	<20	0.01	13,460	1.4	10.0	350	96.0	46.3	<200	287	<1	16.3
MJVD-2-29	<0.01	3,040	0.01	134	<20	0.03	13,740	1.7	20.0	420	99.7	48.2	<200	238	1	16.9
MJVD-2-30	<0.01	4,190	0.01	158	<20	0.01	11,540	1	11.5	450	87.8	42.1	<200	219	<1	15.3
MJVD-2-31	0.01	2,850	0.01	36	<20	0.02	22,500	3.8	28.5	190	89.6	58.1	<200	246	1	17.1
MJVD-2-32	<0.01	2,740	0.01	42	<20	0.01	5,150	1.4	15.0	190	26.0	13.5	<200	68	<1	4.0
MJVD-2-33	<0.01	2,710	0.01	22	<20	0.01	2,840	8.6	38.0	160	19.0	11.1	<100.0	48	4	3.7
MJVD-2-34	<0.01	2,640	0.01	14	<20	0.03	6,830	8.3	26.5	135	32.7	16.8	<200	86	2	5.3
MJVD-2-35	0.01	1,200	0.03	20	<20	<0.01	19,070	1	5.0	55	38.0	23.5	<200	177	<1	5.7
MJVD-2-36	0.01	2,600	0.01	24	<20	0.05	24,800	5.7	15.0	120	50.2	29.6	<200	203	1	7.6
MJVD-2-37	0.01	2,730	0.03	<2	<20	0.11	1,170	12.1	30.0	95	19.5	9.9	<20.0	47	4	3.6
MJVD-2-38	0.01	2,710	0.03	4	<20	0.11	2,900	9.3	30.5	60	11.1	6.4	<50.0	31	4	1.7
MJVD-2-39	0.03	2,190	0.03	18	<20	0.1	10,010	7	21.5	95	21.0	13.4	<100.0	101	3	3.4
MJVD-2-40	0.03	470	0.03	10	<20	<0.01	19,930	0.4	3.0	40	37.5	22.1	50	190	<1	5.7
MJVD-2-41	0.01	1,300	0.03	26	<20	0.01	8,510	3.3	7.5	80	32.9	18.1	<80.0	109	<1	5.2
MJVD-2-42	0.06	820	0.03	14	<20	<0.01	6,390	0.6	4.5	55	25.1	12.5	<100.0	73	<1	4.2
MJVD-2-43	0.01	760	0.03	36	<20	<0.01	3,130	0.3	4.0	90	24.3	12.2	<100.0	62	<1	4.1
MJVD-2-44	0.15	500	0.04	18	<20	<0.01	3,740	0.3	3.5	55	22.9	11.5	<100.0	65	<1	4.0
MJVD-2-45	0.03	120	0.05	2	<20	<0.01	1,800	0.3	3.0	10	18.9	7.9	<30.0	54	<1	2.5
MJVD-2-46	0.03	150	0.04	<2	<20	<0.01	5,220	0.1	4.5	5	14.6	8.8	<30.0	60	<1	2.5
MJVD-2-47	0.03	1,840	0.03	4	<20	<0.01	2,190	0.4	4.0	20	19.4	9.4	<100.0	47	<1	3.5
MJVD-2-48	0.01	1,190	0.03	22	<20	0.02	14,640	4.5	7.0	70	38.3	23.6	<100.0	162	<1	5.9
MJVD-2-49	0.01	590	0.04	16	<20	<0.01	2,540	1.6	5.5	55	16.2	8.8	<20.0	43	<1	2.9
MJVD-2-50	0.01	180	0.05	2	<20	<0.01	940	0.2	3.0	50	13.8	5.5	10	28	<1	2.3
MJVD-2-51	0.09	380	0.04	10	<20	<0.01	5,000	0.3	7.5	50	22.9	11.4	<100.0	70	<1	3.5
MJVD-2-52	0.05	810	0.04	16	<20	<0.01	4,490	0.7	4.5	55	24.6	11.9	<200	77	<1	3.8
MJVD-2-53	0.03	560	0.03	18	<20	<0.01	3,060	0.3	4.0	55	19.2	8.6	<100.0	56	<1	3.2
MJVD-2-54	0.03	5,960	0.03	48	<20	0.02	13,890	2.7	12.0	90	49.9	27.1	<200	179	<1	7.7
MJVD-2-55	0.01	1,150	0.03	32	<20	0.01	8,400	1.4	8.5	55	30.7	15.1	<300	106	<1	4.4
MJVD-2-56	0.01	1,550	0.03	22	<20	0.01	5,420	3	12.0	80	24.0	11.6	<100.0	69	<1	3.5
MJVD-2-57	0.02	2,660	0.03	22	<20	0.07	3,590	6.9	16.5	100	16.0	8.7	<100.0	50	3	2.5

MJVD-2 (10/126)

Sample Name	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm	Ho ppm
MJVD-2-58	0.01	1,020	0.03	50	<20	0.02	9,660	2	12.5	95	32.5	17.5	<150.0	119	<1	5.0
MJVD-2-59	0.01	2,640	0.03	56	<20	0.04	10,050	3.4	15.0	110	36.2	17.9	<200	132	<1	5.4
MJVD-2-60	0.01	1,790	0.03	58	<20	0.03	15,210	2.7	17.5	120	41.0	21.2	<200	181	<1	6.3
MJVD-2-61	0.01	2,480	0.03	60	4	0.04	10,910	4.1	15.5	110	37.8	20.1	<250	138	<1	6.0
MJVD-2-62	0.02	3,900	0.03	74	<20	0.04	24,400	3.7	16.5	120	70.5	36.1	<200	278	<1	10.7
MJVD-2-63	0.01	2,110	0.03	48	<20	0.03	18,790	2.2	14.0	95	47.5	27.0	<200	205	<1	7.1
MJVD-2-64	0.01	670	0.03	36	<20	<0.01	16,430	0.9	9.0	55	42.0	22.3	<200	179	<1	5.5
MJVD-2-65	0.04	2,080	0.02	90	<20	0.02	45,800	2.1	24.0	130	114.0	59.0	100	468	<1	17.0
MJVD-2-66	0.02	1,180	0.03	34	<20	<0.01	11,780	1.2	10.5	80	28.0	14.9	<200	126	<1	3.8
MJVD-2-67	0.01	1,000	0.03	28	<20	<0.01	10,430	2.2	7.5	55	24.3	15.2	<200	111	<1	4.3
MJVD-2-68	<0.01	360	0.05	2	<20	<0.01	412	5.6	7.0	40	4.9	2.8	2.6	7	2	1.0
MJVD-2-69	0.01	1,280	0.03	36	<20	<0.01	5,410	2.3	10.5	55	28.1	15.7	<100.0	80	<1	4.1
MJVD-2-70	0.01	1,120	0.02	40	<20	0.01	20,800	1.6	9.0	55	55.9	32.1	<100.0	223	<1	9.5
MJVD-2-71	0.01	1,880	0.03	48	<20	0.01	12,910	2.4	10.0	60	50.7	26.3	<100.0	165	<1	8.5
MJVD-2-72	0.01	1,240	0.03	16	<20	0.01	6,520	2	4.5	55	25.7	13.7	<100.0	84	<1	4.5
MJVD-2-73	0.01	740	0.03	10	<20	<0.01	25,600	0.4	5.5	50	40.3	28.3	50	230	<1	5.6
MJVD-2-74	0.01	510	0.03	2	<20	<0.01	14,340	0.2	1.0	20	30.1	18.9	50	138	<1	3.9
MJVD-2-75	0.01	430	0.04	4	<20	<0.01	8,830	0.2	2.5	10	19.2	11.6	<50.0	88	<1	3.3
MJVD-2-76	0.01	610	0.04	8	<20	<0.01	4,870	0.2	2.0	25	23.5	11.3	<50.0	69	<1	3.5
MJVD-2-77	0.03	5,610	0.04	10	<20	<0.01	4,270	0.3	2.0	55	26.7	13.7	<50.0	81	<1	4.7
MJVD-2-78	0.04	440	0.04	6	<20	<0.01	9,440	0.3	2.5	55	32.8	16.1	<150.0	117	<1	4.7
MJVD-2-79	0.01	1,210	0.04	6	<20	<0.01	2,960	0.7	2.5	45	22.9	12.3	<100.0	58	<1	3.8
MJVD-2-80	0.01	860	0.03	6	<20	<0.01	5,350	0.3	4.0	30	16.4	10.3	<50.0	64	<1	3.2

MJVD-2 (11/126)

Sample Name	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-2-1	2,170	2,450	0.8	858	5	240	318	27.0	156	<1	3,180	3.0	8.4	2.5	65	1.4	5
MJVD-2-2	2,880	2,650	0.8	1,215	20	196	428	22.8	202	<1	3,960	3.0	9.7	2.0	81	1.4	3
MJVD-2-3	5,880	3,540	1.2	2,610	10	259	885	31.4	340	<1	3,660	4.5	19.6	1.5	57	2.6	2
MJVD-2-4	3,570	2,240	0.9	1,630	<5	159	544	46.8	229	<1	3,520	2.5	12.1	2.0	62	1.5	2
MJVD-2-5	2,640	900	0.5	1,275	5	69	424	94.8	162	<1	2,090	1.5	8.5	2.5	125	0.8	4
MJVD-2-6	2,530	885	0.3	1,060	<5	34	361	131.0	96	<1	447	1.5	5.1	3.5	16	0.6	3
MJVD-2-7	2,480	650	0.3	1,035	<5	26	364	124.5	94	<1	270	1.5	5.5	3.5	19	0.6	5
MJVD-2-8	2,640	1,325	0.4	1,120	35	46	385	110.0	107	<1	546	1.5	5.8	4.0	17	0.8	5
MJVD-2-9	2,670	1,560	0.4	1,135	<5	24	391	124.0	96	<1	288	1.5	5.1	4.5	9	0.6	2
MJVD-2-10	5,120	4,860	0.7	2,310	<5	184	803	92.6	266	<1	2,670	3.0	14.4	7.0	39	1.6	2
MJVD-2-11	10,920	850	0.7	4,060	<5	34	1,400	16.8	445	<1	6,200	0.5	20.0	0.5	45	1.4	1
MJVD-2-12	16,760	575	0.9	5,900	<5	28	2,100	5.0	564	<1	4,960	0.5	25.8	<0.5	40	1.8	2
MJVD-2-13	29,400	675	1.5	12,390	<5	18	4,190	12.0	1,220	<1	4,290	0.5	55.6	0.5	123	3.2	5
MJVD-2-14	24,200	1,300	2.0	8,520	<5	39	2,860	6.2	870	<1	5,050	0.5	48.0	1.0	68	3.8	4
MJVD-2-15	19,940	1,075	1.8	6,760	<5	78	2,430	29.8	631	<1	5,560	4.0	36.0	0.5	70	3.5	6
MJVD-2-16	17,640	800	0.8	6,030	<5	30	2,170	8.8	548	<1	5,430	2.0	26.4	<0.5	56	1.7	3
MJVD-2-17	30,400	1,410	1.1	9,510	5	108	3,550	13.0	756	<1	4,690	3.0	39.4	1.0	85	2.0	2
MJVD-2-18	51,900	1,125	1.1	13,870	<5	14	5,290	8.0	968	<1	4,770	2.0	49.7	0.5	95	1.8	3
MJVD-2-19	3,880	1,160	0.3	1,225	<5	29	455	9.0	202	<1	5,770	1.0	7.1	1.0	103	0.5	2
MJVD-2-20	7,490	5,130	1.5	3,030	<5	239	1,020	31.8	418	<1	4,880	2.5	23.0	3.0	41	2.7	2
MJVD-2-21	10,650	1,135	0.7	3,160	<5	42	1,165	7.8	351	<1	5,680	0.5	16.5	1.0	153	1.3	1
MJVD-2-22	10,090	1,400	0.8	2,930	<5	21	1,070	6.4	335	<1	5,730	0.5	13.9	0.5	66	1.2	2
MJVD-2-23	9,410	990	1.4	3,790	<5	29	1,305	16.2	441	<1	6,260	0.5	19.1	1.0	81	2.0	3
MJVD-2-24	9,660	4,510	1.5	3,760	5	148	1,250	22.8	509	<1	6,770	3.0	24.4	3.0	68	2.9	1
MJVD-2-25	9,470	5,800	1.7	3,220	25	161	1,135	12.4	412	<1	6,480	3.0	22.0	3.0	34	2.8	2
MJVD-2-26	11,220	5,510	1.9	3,980	5	132	1,380	5.8	463	<1	6,230	2.0	25.7	3.5	30	3.1	2
MJVD-2-27	5,700	3,260	0.9	2,140	10	121	725	15.0	325	<1	6,570	3.0	14.9	2.0	33	2.0	<1
MJVD-2-28	9,980	6,060	2.0	4,500	55	395	1,445	26.4	569	<1	4,980	6.0	32.1	6.5	54	4.0	1
MJVD-2-29	9,850	6,610	2.4	3,620	60	405	1,235	19.2	454	<1	4,370	4.5	29.1	6.5	47	4.6	2
MJVD-2-30	8,990	7,040	2.3	3,400	35	469	1,140	17.0	438	<1	4,460	6.0	26.1	5.0	36	3.7	2
MJVD-2-31	21,200	4,630	2.9	5,160	65	82	1,965	51.8	452	<1	3,550	1.5	30.7	5.0	28	5.3	1
MJVD-2-32	3,880	2,830	0.7	1,255	25	146	442	20.0	196	<1	4,760	3.0	8.1	2.5	11	1.2	<1
MJVD-2-33	2,280	2,190	0.7	705	155	89	248	101.0	92	<1	3,380	2.0	5.4	3.5	23	1.3	2
MJVD-2-34	5,220	2,650	0.9	1,680	200	112	588	90.6	201	<1	3,220	1.0	10.4	2.5	20	1.7	1
MJVD-2-35	15,000	1,135	0.8	4,380	10	66	1,610	10.8	427	<1	4,600	0.5	18.8	1.5	38	1.5	<1
MJVD-2-36	19,270	2,950	0.9	5,180	45	59	1,970	59.2	428	<1	2,330	3.0	24.1	5.0	51	1.9	1
MJVD-2-37	3,080	600	0.6	847	95	20	302	171.0	74	<1	717	1.5	5.3	4.5	17	1.2	4
MJVD-2-38	2,260	680	0.3	692	90	30	250	194.5	63	<1	1,355	1.0	3.5	4.5	15	0.5	2
MJVD-2-39	7,760	900	0.5	2,440	45	50	879	105.0	202	<1	2,350	1.5	10.4	2.5	26	0.7	1
MJVD-2-40	15,550	910	0.6	4,880	<5	40	1,800	8.4	360	<1	2,180	0.5	20.7	<0.5	30	1.1	<1
MJVD-2-41	6,210	3,100	0.8	2,240	20	50	786	26.8	210	<1	2,360	1.0	12.4	1.5	14	1.5	2
MJVD-2-42	5,190	1,080	0.7	1,555	<5	77	561	6.8	147	<1	4,330	1.0	8.8	<0.5	21	1.0	<1
MJVD-2-43	2,130	2,230	0.5	966	5	98	313	7.6	125	1	2,840	2.0	7.2	0.5	6	1.1	<1
MJVD-2-44	2,720	835	0.5	1,070	5	38	363	7.4	130	<1	3,760	0.5	7.9	<0.5	9	0.9	1
MJVD-2-45	1,075	125	0.3	664	<5	18	197	6.2	95	<1	3,980	<0.5	6.2	<0.5	126	0.7	1
MJVD-2-46	3,980	225	0.3	1,325	<5	92	474	3.2	116	<1	3,030	<0.5	6.1	<0.5	7	0.6	<1
MJVD-2-47	1,460	550	0.5	661	25	414	216	7.4	98	<1	3,610	1.5	5.9	0.5	<1	0.9	<1
MJVD-2-48	11,100	1,835	0.7	3,770	45	98	1,345	31.2	319	<1	2,700	1.5	18.2	1.0	30	1.9	1
MJVD-2-49	1,785	2,000	0.3	713	15	86	238	25.6	73	<1	2,160	1.5	5.4	0.5	<1	0.7	1
MJVD-2-50	581	550	0.3	302	<5	36	95	10.0	40	<1	2,940	<0.5	3.5	<0.5	<1	0.8	<1
MJVD-2-51	3,830	1,775	0.5	1,295	30	20	458	5.6	139	<1	3,500	<0.5	8.0	1.0	2	0.9	2
MJVD-2-52	3,060	975	0.6	1,315	<5	52	443	8.0	169	<1	3,920	1.5	8.4	<0.5	7	1.1	<1
MJVD-2-53	2,080	910	0.4	947	30	107	305	6.4	128	<1	2,460	1.5	6.3	0.5	5	0.9	<1
MJVD-2-54	10,480	5,150	1.0	3,760	10	813	1,315	88.4	366	<1	4,960	6.0	21.1	3.5	27	1.8	2
MJVD-2-55	6,300	2,130	0.6	2,250	<5	131	787	32.6	269	<1	5,520	1.5	12.1	2.5	17	1.3	<1
MJVD-2-56	4,030	2,100	0.5	1,435	20	182	497	68.6	151	<1	3,210	2.0	7.9	3.0	11	0.9	1
MJVD-2-57	2,650	1,500	0.3	950	55	83	336	123.5	113	<1	2,740	1.0	5.8	3.0	16	0.7	1

MJVD-2 (12/126)

Sample Name	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-2-58	7,210	1,725	0.7	2,520	20	112	896	23.8	245	<1	3,280	1.0	13.2	1.5	25	1.1	1
MJVD-2-59	7,700	4,000	0.6	2,660	40	340	938	40.4	281	<1	4,270	3.0	14.7	4.0	20	1.3	<1
MJVD-2-60	11,480	2,860	0.6	4,060	30	165	1,410	33.4	386	2	4,330	2.0	19.2	2.5	31	1.4	1
MJVD-2-61	8,200	2,760	0.7	2,880	55	246	1,015	43.2	304	<1	4,250	2.0	15.0	3.0	22	1.2	<1
MJVD-2-62	18,620	4,410	1.2	6,400	30	559	2,300	67.2	569	<1	4,540	4.0	31.6	5.0	49	2.3	<1
MJVD-2-63	14,270	2,330	0.8	4,870	15	183	1,740	34.2	449	1	4,510	1.5	22.4	2.5	42	1.8	<1
MJVD-2-64	12,500	1,760	0.7	4,150	<5	68	1,505	15.2	376	<1	4,000	0.5	19.5	1.5	35	1.3	<1
MJVD-2-65	33,400	4,890	1.6	11,380	10	212	4,090	33.4	914	<1	4,790	2.5	50.3	4.5	83	3.5	3
MJVD-2-66	9,060	1,450	0.5	2,970	5	111	1,080	19.8	285	<1	4,520	1.5	13.3	1.5	17	1.0	<1
MJVD-2-67	7,960	1,150	0.5	2,650	5	85	943	55.8	235	<1	3,270	1.0	12.0	2.0	15	0.9	<1
MJVD-2-68	288	1,110	0.3	113	<5	14	37	159.5	11	<1	254	1.5	1.2	4.0	<1	0.4	<1
MJVD-2-69	4,100	3,230	0.7	1,455	10	109	504	60.4	165	1	2,740	1.0	9.5	3.5	8	1.3	1
MJVD-2-70	15,850	3,510	1.0	5,380	15	115	1,920	20.2	430	<1	2,750	0.5	25.0	3.5	34	2.3	<1
MJVD-2-71	9,590	3,700	1.1	3,390	10	200	1,195	37.6	321	<1	3,490	1.5	18.6	4.0	21	2.1	<1
MJVD-2-72	4,790	1,425	0.6	1,710	10	166	605	31.6	182	<1	3,270	1.5	9.4	1.5	7	1.0	1
MJVD-2-73	20,200	900	0.6	6,470	5	71	2,370	12.0	467	<1	2,380	0.5	24.4	0.5	52	1.4	<1
MJVD-2-74	11,130	400	0.4	3,600	10	107	1,310	7.4	268	<1	2,670	1.0	14.9	<0.5	15	0.9	<1
MJVD-2-75	6,750	310	0.4	2,240	20	56	811	9.4	176	<1	3,850	0.5	10.2	<0.5	9	0.8	<1
MJVD-2-76	3,700	385	0.4	1,290	<5	93	449	12.6	136	<1	5,060	0.5	7.8	<0.5	2	1.0	1
MJVD-2-77	3,050	1,150	0.7	1,230	<5	504	407	22.8	149	<1	6,880	2.0	9.0	0.5	2	1.0	1
MJVD-2-78	7,250	1,860	0.6	2,450	<5	46	862	14.4	237	<1	8,780	1.0	12.6	0.5	12	1.1	<1
MJVD-2-79	1,985	1,100	0.5	897	<5	105	292	66.4	118	<1	3,990	1.0	6.6	0.5	<1	0.8	<1
MJVD-2-80	4,000	910	0.4	1,370	<5	107	492	33.6	116	<1	2,830	0.5	6.6	<0.5	<1	0.7	1

MJVD-2 (13/126)

Sample Name	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-2-1	40	70.0	240	6.0	118	660	124
MJVD-2-2	30	70.0	150	6.2	134	710	86
MJVD-2-3	21	95.0	130	12.6	260	860	183
MJVD-2-4	17	65.0	120	8.4	158	825	105
MJVD-2-5	7	25.0	75	4.2	85	350	144
MJVD-2-6	0	15.0	55	3.0	61	250	212
MJVD-2-7	<1	15.0	55	3.4	59	175	213
MJVD-2-8	4	20.0	85	3.1	72	250	209
MJVD-2-9	<1	15.0	55	3.3	59	225	234
MJVD-2-10	18	75.0	115	7.9	154	460	147
MJVD-2-11	<1	25.0	25	6.6	182	385	36
MJVD-2-12	<1	15.0	10	9.3	242	110	16
MJVD-2-13	1	40.0	30	15.2	424	250	21
MJVD-2-14	<1	35.0	45	18.6	650	200	44
MJVD-2-15	6	25.0	35	13.5	501	200	222
MJVD-2-16	3	20.0	25	7.4	274	260	55
MJVD-2-17	8	55.0	45	10.5	296	350	53
MJVD-2-18	13	30.0	25	8.6	306	225	57
MJVD-2-19	<1	35.0	150	2.7	52	275	19
MJVD-2-20	46	50.0	100	13.2	289	1,210	54
MJVD-2-21	5	30.0	10	6.5	196	310	18
MJVD-2-22	<1	25.0	20	6.9	191	260	13
MJVD-2-23	<1	60.0	20	10.8	324	385	34
MJVD-2-24	20	55.0	50	12.0	362	800	26
MJVD-2-25	20	65.0	50	14.7	293	975	40
MJVD-2-26	23	65.0	45	14.8	334	925	24
MJVD-2-27	13	45.0	65	9.5	183	710	35
MJVD-2-28	62	125.0	120	20.7	456	1,620	49
MJVD-2-29	131	105.0	120	22.9	493	1,760	92
MJVD-2-30	130	120.0	120	19.1	439	1,560	82
MJVD-2-31	65	105.0	115	23.9	610	900	115
MJVD-2-32	68	40.0	55	5.6	134	675	84
MJVD-2-33	100	30.0	155	5.7	136	1,110	226
MJVD-2-34	37	35.0	85	7.4	163	1,325	131
MJVD-2-35	18	25.0	35	7.3	150	450	22
MJVD-2-36	65	30.0	90	8.7	203	1,300	136
MJVD-2-37	33	5.0	195	4.9	118	2,510	232
MJVD-2-38	32	10.0	145	2.6	54	2,580	197
MJVD-2-39	26	25.0	125	3.9	94	1,810	172
MJVD-2-40	10	25.0	30	6.4	146	325	20
MJVD-2-41	33	15.0	65	7.3	150	850	88
MJVD-2-42	7	20.0	65	4.7	109	360	27
MJVD-2-43	16	25.0	40	4.2	101	460	19
MJVD-2-44	13	10.0	15	4.3	107	275	25
MJVD-2-45	<1	5.0	20	3.1	72	150	9
MJVD-2-46	<1	25.0	5	2.3	65	125	9
MJVD-2-47	14	130.0	5	4.1	97	185	27
MJVD-2-48	33	30.0	50	7.7	175	850	83
MJVD-2-49	25	20.0	15	3.5	80	410	26
MJVD-2-50	1	10.0	20	3.1	63	160	5
MJVD-2-51	4	10.0	20	5.4	103	610	24
MJVD-2-52	13	15.0	10	5.1	105	525	26
MJVD-2-53	9	25.0	40	3.6	82	335	6
MJVD-2-54	214	215.0	45	9.2	216	775	55
MJVD-2-55	136	35.0	25	5.5	126	400	36
MJVD-2-56	96	35.0	50	4.5	102	1,050	85
MJVD-2-57	103	20.0	115	3.6	71	2,160	168

MJVD-2 (14/126)

Sample Name	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-2-58	143	55.0	45	5.7	137	775	44
MJVD-2-59	195	80.0	40	5.4	153	1,000	41
MJVD-2-60	123	50.0	45	6.0	163	1,035	56
MJVD-2-61	140	55.0	55	5.9	157	1,110	56
MJVD-2-62	215	140.0	70	10.3	293	1,200	58
MJVD-2-63	201	55.0	55	8.6	190	835	50
MJVD-2-64	116	40.0	40	5.7	179	510	18
MJVD-2-65	368	110.0	45	16.7	476	760	43
MJVD-2-66	89	35.0	45	4.6	111	635	34
MJVD-2-67	81	30.0	40	4.3	108	450	64
MJVD-2-68	52	5.0	40	2.2	31	175	153
MJVD-2-69	146	35.0	50	6.0	132	500	59
MJVD-2-70	194	80.0	50	10.3	251	375	39
MJVD-2-71	178	60.0	65	9.9	232	710	71
MJVD-2-72	50	45.0	50	5.0	105	425	39
MJVD-2-73	27	35.0	35	6.0	139	225	11
MJVD-2-74	4	35.0	15	4.3	110	225	8
MJVD-2-75	<1	15.0	95	3.1	78	150	13
MJVD-2-76	<1	25.0	10	4.2	95	260	21
MJVD-2-77	3	165.0	<5	4.9	113	360	3
MJVD-2-78	<1	15.0	10	5.7	134	350	11
MJVD-2-79	1	20.0	15	3.8	99	300	8
MJVD-2-80	10	25.0	40	3.7	80	275	13

MJVD-3 (15/126)

Sample Name	F %	Ba %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm	Mo ppm
MJVD-3-1	1.5	29.40	2.14	618	<10	<5.0	<10	1.07	3.0	46	3.00	<100	<1	0.15	0.06	>10,000	30
MJVD-3-2	2.8	24.20	0.90	1,115	320	<5.0	<10	1.15	4.0	19	1.37	<100	<1	0.17	0.04	5,860	18
MJVD-3-3	1.4	35.10	1.20	530	<10	<5.0	10	0.90	2.5	37	2.55	<100	<1	0.17	0.05	7,380	18
MJVD-3-4	1.5	33.30	1.31	660	40	5	<10	1.51	8.5	26	2.87	<100	<1	0.42	0.30	7,750	10
MJVD-3-5	0.5	39.70	0.57	262	<10	10	20	1.48	12.5	27	4.81	<100	<1	0.11	0.10	>10,000	9
MJVD-3-6	0.5	40.10	0.91	160	<10	10	20	0.15	8.0	39	4.95	<100	<1	0.24	0.30	>10,000	9
MJVD-3-7	0.4	43.80	1.00	194	<10	10	20	0.09	3.5	20	2.92	<100	<1	0.05	0.05	7,620	10
MJVD-3-8	0.2	42.50	0.45	404	<10	5	<10	0.17	5.5	15	2.23	<100	<1	0.03	0.01	6,680	14
MJVD-3-9	0.2	45.20	0.60	260	<10	5	20	0.08	3.5	20	3.30	<100	<1	0.02	0.01	9,900	11
MJVD-3-10	0.1	43.80	0.45	250	<10	5	20	0.09	5.5	17	2.97	<100	<1	0.02	0.01	7,760	10
MJVD-3-11	0.3	41.70	1.08	326	<10	15	20	0.16	7.0	26	3.51	<100	<1	0.05	0.04	8,280	12
MJVD-3-12	0.4	40.50	1.02	404	<10	15	10	0.23	7.5	22	3.48	<100	<1	0.07	0.05	>10,000	19
MJVD-3-13	0.3	38.70	0.95	426	<10	15	20	0.27	11.5	18	3.29	<100	<1	0.04	0.02	>10,000	22
MJVD-3-14	1.2	33.70	1.57	350	<10	10	<10	1.79	11.5	30	2.34	<100	<1	0.21	0.26	>10,000	36
MJVD-3-15	2.3	25.00	0.78	642	170	10	10	4.59	26.0	34	3.31	<100	<1	0.31	0.23	>10,000	17
MJVD-3-16	1.9	18.00	0.83	346	100	5	<10	12.90	3.0	25	1.65	<100	<1	0.26	0.10	3,730	6
MJVD-3-17	0.8	17.30	1.15	94	<10	<5.0	<10	12.50	1.5	22	1.85	<100	1	0.32	0.08	2,290	7
MJVD-3-18	2.1	26.60	0.42	172	370	5	<10	12.70	3.5	13	1.34	<100	1	0.15	0.07	2,090	4
MJVD-3-19	3.0	21.40	1.05	302	340	<5.0	<10	12.20	2.5	15	0.92	<100	1	0.34	0.08	1,835	4
MJVD-3-20	0.6	21.00	0.17	88	50	<5.0	<10	>15.00	2.0	4	0.40	<100	<1	0.06	0.07	2,030	6
MJVD-3-21	0.5	18.25	0.10	84	100	<5.0	<10	>15.00	2.0	4	0.37	<100	<1	0.04	0.09	2,020	8
MJVD-3-22	0.7	21.50	0.24	106	30	<5.0	<10	>15.00	2.0	8	1.05	<100	2	0.08	0.08	2,250	10
MJVD-3-29	0.1	4.49	0.05	16	<10	<5.0	<10	>15.00	0.5	6	0.32	<100	<1	0.02	0.19	1,640	9
MJVD-3-30	0.4	2.62	0.11	62	30	<5.0	<10	>15.00	1.0	3	0.30	<100	<1	0.05	0.19	1,860	7
MJVD-3-31	0.3	9.82	0.25	152	40	<5.0	<10	>15.00	3.5	7	0.96	<100	<1	0.12	0.17	4,130	10
MJVD-3-32	0.9	2.17	0.10	48	10	<5.0	<10	>15.00	0.5	3	0.24	<100	<1	0.05	0.18	1,850	7
MJVD-3-33	0.1	1.08	0.04	14	<10	<5.0	<10	>15.00	0.5	1	0.13	<100	<1	0.01	0.19	1,345	6
MJVD-3-35	0.9	8.10	0.45	78	20	<5.0	<10	>15.00	2.0	9	0.74	<100	<1	0.16	0.15	3,600	9
MJVD-3-36	0.6	5.37	0.23	42	<10	<5.0	<10	>15.00	1.5	6	0.46	<100	<1	0.08	0.13	2,960	9
MJVD-3-37	0.5	6.11	0.33	42	<10	<5.0	<10	>15.00	1.5	6	0.52	<100	<1	0.11	0.14	2,720	9
MJVD-3-38	1.5	13.55	1.08	80	10	<5.0	<10	>15.00	1.5	19	0.87	<100	<1	0.22	0.16	2,460	6
MJVD-3-39	1.3	8.54	1.44	60	<10	<5.0	<10	>15.00	0.5	30	1.26	<100	1	0.25	0.24	1,825	<1
MJVD-3-40	0.5	4.66	0.08	28	50	<5.0	<10	>15.00	1.0	2	0.14	<100	<1	0.04	0.13	1,650	9
MJVD-3-41	0.4	1.92	0.14	14	<10	<5.0	<10	>15.00	0.5	3	0.24	<100	<1	0.06	0.20	1,450	8
MJVD-3-42	0.2	0.86	0.06	14	<10	<5.0	<10	>15.00	0.5	3	0.21	<100	2	0.03	0.17	1,305	6
MJVD-3-43	0.6	6.14	0.50	38	<10	<5.0	<10	>15.00	0.5	8	0.72	<100	1	0.14	0.14	1,715	8
MJVD-3-44	0.5	3.03	0.37	144	<10	<5.0	<10	>15.00	1.0	7	0.44	<100	<1	0.06	0.21	1,250	11
MJVD-3-45	0.4	4.57	0.12	20	<10	<5.0	<10	>15.00	1.0	4	0.29	<100	2	0.05	0.16	1,670	8
MJVD-3-46	0.2	4.65	0.05	20	<10	<5.0	<10	>15.00	0.5	2	0.18	<100	3	0.03	0.15	1,515	7
MJVD-3-47	0.4	8.05	0.28	46	<10	<5.0	<10	>15.00	1.0	7	0.56	<100	<1	0.05	0.12	2,000	9
MJVD-3-48	0.3	3.63	0.05	32	<10	<5.0	<10	>15.00	2.0	2	0.27	<100	<1	0.01	0.15	1,430	7
MJVD-3-49	3.0	17.00	0.16	88	810	<5.0	<10	>15.00	1.5	3	0.55	<100	<1	0.08	0.05	2,040	10
MJVD-3-50	2.9	16.15	0.17	88	720	<5.0	<10	>15.00	1.5	3	0.40	<100	<1	0.08	0.05	1,995	7
MJVD-3-51	1.8	8.55	0.18	44	380	<5.0	<10	>15.00	1.5	3	0.33	<100	<1	0.07	0.09	2,010	8
MJVD-3-52	0.8	4.19	0.36	60	<10	<5.0	<10	>15.00	2.0	10	0.78	<100	<1	0.05	0.10	2,360	8
MJVD-3-53	0.6	6.56	0.20	68	10	<5.0	10	>15.00	3.5	12	0.74	<100	<1	0.03	0.07	2,410	8
MJVD-3-54	0.5	8.04	0.07	54	40	<5.0	20	>15.00	4.5	9	1.02	<100	<1	0.01	0.09	1,785	9
MJVD-3-55	0.7	6.15	0.06	36	180	<5.0	10	>15.00	3.0	7	0.82	<100	3	0.02	0.14	2,210	9
MJVD-3-56	0.6	3.07	0.06	100	170	<5.0	<10	>15.00	3.0	4	0.41	<100	<1	0.02	0.10	2,070	9
MJVD-3-57	0.6	4.78	0.04	86	200	<5.0	<10	>15.00	2.0	2	0.27	<100	<1	0.01	0.10	2,300	9
MJVD-3-58	0.6	3.48	0.05	114	190	<5.0	<10	>15.00	1.5	2	0.22	<100	<1	0.02	0.11	2,110	6
MJVD-3-59	0.9	3.37	0.06	172	230	<5.0	<10	>15.00	1.5	1	0.33	<100	<1	0.02	0.12	2,210	9
MJVD-3-60	0.4	1.82	0.04	46	90	<5.0	<10	>15.00	1.5	1	0.24	<100	<1	0.01	0.12	2,000	8
MJVD-3-61	0.6	3.64	0.10	58	90	<5.0	<10	>15.00	1.5	2	0.27	<100	<1	0.03	0.11	2,300	8
MJVD-3-62	0.4	5.59	0.10	72	10	<5.0	<10	>15.00	3.0	3	0.34	<100	<1	0.01	0.09	2,200	8
MJVD-3-63	1.0	3.60	0.10	76	240	<5.0	<10	>15.00	2.0	1	0.29	<100	<1	0.11	0.12	2,490	7
MJVD-3-64	0.7	4.77	0.07	136	180	<5.0	<10	>15.00	1.5	1	0.39	<100	<1	0.02	0.12	2,490	9

MJVD-3 (16/126)

Sample Name	F	Ba	Al	As	B	Be	Bi	Ca	Cd	Cr	Fe	Ga	Hg	K	Mg	Mn	Mo
	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%	ppm	ppm
MJVD-3-65	1.4	6.84	0.10	94	450	<5.0	<10	>15.00	1.0	<1	0.16	<100	<1	0.04	0.14	2,120	7
MJVD-3-66	1.9	9.03	0.14	100	610	<5.0	<10	>15.00	1.0	<1	0.37	<100	<1	0.06	0.11	2,490	9
MJVD-3-67	1.3	2.28	0.08	26	350	<5.0	<10	>15.00	1.5	<1	0.24	<100	<1	0.03	0.12	2,590	22
MJVD-3-68	0.8	17.50	0.06	236	240	<5.0	<10	>15.00	0.5	1	0.27	<100	<1	0.03	0.11	1,745	8
MJVD-3-69	0.7	8.88	0.05	48	210	<5.0	<10	>15.00	0.5	2	0.40	<100	<1	0.01	0.15	2,050	10
MJVD-3-70	2.2	4.99	0.10	74	620	<5.0	<10	>15.00	1.0	3	0.42	<100	<1	0.05	0.09	2,230	9
MJVD-3-71	1.8	9.88	0.10	64	580	<5.0	<10	>15.00	1.5	1	0.24	<100	<1	0.05	0.08	2,440	7
MJVD-3-72	0.4	4.86	0.08	26	30	<5.0	<10	>15.00	1.0	1	0.20	<100	<1	0.02	0.14	2,970	7
MJVD-3-73	0.6	3.07	0.08	24	110	<5.0	<10	>15.00	1.5	<1	0.17	<100	<1	0.02	0.10	3,770	6
MJVD-3-74	3.3	12.25	1.37	230	140	5	<10	13.90	1.5	20	1.09	<100	<1	0.27	0.13	3,720	6
MJVD-3-75	0.9	11.10	0.07	196	210	<5.0	<10	>15.00	0.5	1	0.43	<100	<1	0.02	0.12	1,610	8
MJVD-3-76	1.4	8.14	1.07	168	<10	5	<10	>15.00	1.5	23	1.06	<100	<1	0.19	0.12	3,490	12
MJVD-3-77	0.3	4.58	0.10	58	<10	<5.0	<10	>15.00	1.5	3	0.33	<100	<1	0.02	0.10	2,610	7
MJVD-3-78	0.2	2.29	0.27	38	<10	<5.0	<10	>15.00	0.5	6	0.42	<100	1	0.05	0.20	1,905	6
MJVD-3-79	0.5	4.27	0.31	130	<10	<5.0	<10	>15.00	1.0	8	0.45	<100	<1	0.06	0.16	2,390	7
MJVD-3-80	0.8	4.38	0.41	48	<10	<5.0	<10	>15.00	1.5	10	0.70	<100	<1	0.08	0.18	2,040	7

MJVD-3 (17/126)

Sample Name	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm	Ho ppm
MJVD-3-1	0.01	2,820	0.03	56	<20	0.02	38,600	2.3	9.5	120	133.5	71.6	<300	507	3	21.3
MJVD-3-2	0.06	1,210	0.03	40	<20	0.01	85,900	1.3	5.5	145	154.5	122.0	200	755	1	22.5
MJVD-3-3	0.01	2,190	0.03	46	<20	0.01	32,500	1.9	5.5	140	78.1	47.3	<300	329	1	11.9
MJVD-3-4	0.02	4,330	0.03	44	<20	0.01	43,100	2	7.0	170	95.2	59.5	<300	408	<1	15.1
MJVD-3-5	0.01	>10,000	0.02	56	<20	<0.01	13,800	1	5.5	205	96.2	48.4	<400	246	<1	16.9
MJVD-3-6	<0.01	4,280	0.01	36	<20	0.01	6,490	1.6	7.0	175	98.3	48.6	<400	196	<1	17.8
MJVD-3-7	<0.01	4,630	0.01	30	<20	<0.01	5,610	0.7	2.0	110	116.5	54.6	<500	257	<1	20.4
MJVD-3-8	<0.01	8,800	0.02	38	<20	<0.01	17,950	0.5	2.0	160	154.0	74.5	<400	386	1	25.8
MJVD-3-9	<0.01	5,280	0.03	26	<20	<0.01	7,930	0.5	2.5	185	184.5	86.5	<400	393	<1	33.2
MJVD-3-10	<0.01	6,450	0.02	28	<20	<0.01	9,930	0.5	1.5	140	157.5	78.4	<400	326	<1	29.2
MJVD-3-11	<0.01	4,620	0.02	32	<20	<0.01	14,140	0.6	3.0	150	115.0	60.9	<400	294	<1	20.0
MJVD-3-12	<0.01	3,870	0.01	44	<20	0.01	14,620	1.2	6.5	210	168.5	80.4	<400	425	1	29.2
MJVD-3-13	<0.01	6,640	0.01	46	<20	<0.01	18,460	0.9	4.5	200	203.0	96.4	<400	488	1	34.8
MJVD-3-14	<0.01	3,590	0.01	84	<20	0.03	19,600	2	24.5	175	90.1	48.1	<300	275	1	15.1
MJVD-3-15	0.04	5,530	0.01	78	<20	0.01	47,100	1.2	7.5	245	152.5	82.9	200	530	1	23.9
MJVD-3-16	0.03	1,390	0.03	22	<20	<0.01	22,900	1.5	95.5	70	49.8	31.3	<100.0	215	<1	7.9
MJVD-3-17	0.03	1,500	0.05	14	<20	<0.01	4,880	3.7	4.5	50	18.6	11.2	<100.0	60	1	3.2
MJVD-3-18	0.07	2,310	0.05	10	<20	<0.01	11,490	0.6	2.0	45	27.2	15.2	<300	113	<1	3.8
MJVD-3-19	0.07	740	0.05	8	<20	<0.01	19,360	1.9	2.0	50	36.3	25.1	<200	188	1	5.3
MJVD-3-20	0.02	650	0.05	6	<20	<0.01	5,190	0.5	1.0	35	18.8	10.0	<200	61	<1	2.9
MJVD-3-21	0.03	740	0.05	2	<1	<0.01	5,050	0.2	0.5	20	19.2	9.9	<200	64	<1	2.9
MJVD-3-22	0.02	980	0.05	2	<20	<0.01	5,450	0.6	2.0	30	20.9	11.1	<200	69	<1	3.1
MJVD-3-29	0.01	200	0.04	4	<20	<0.01	816	0.3	0.5	10	7.4	3.6	<40.0	14	<1	1.3
MJVD-3-30	0.01	280	0.04	8	<20	<0.01	3,730	0.5	1.0	20	13.6	7.5	<20.0	48	<1	2.2
MJVD-3-31	0.01	1,190	0.03	12	<20	<0.01	10,660	0.5	3.0	50	38.6	20.6	<100.0	134	<1	6.2
MJVD-3-32	0.01	240	0.04	6	<20	<0.01	2,670	0.3	1.0	20	12.3	6.5	<20.0	37	<1	2.0
MJVD-3-33	0.01	130	0.06	2	<20	<0.01	736	0.5	1.0	10	7.1	3.5	<10.0	14	<1	1.1
MJVD-3-35	0.02	1,290	0.04	12	<20	<0.01	4,510	1.2	2.5	40	23.9	12.8	<80.0	71	<1	4.1
MJVD-3-36	0.01	820	0.04	10	<20	<0.01	2,490	0.9	3.0	30	20.1	10.2	<50.0	48	<1	3.5
MJVD-3-37	0.01	660	0.04	8	<20	<0.01	2,380	0.9	1.5	30	18.0	9.5	<60.0	41	<1	3.2
MJVD-3-38	0.02	780	0.04	6	<20	0.01	4,410	2.5	5.5	50	24.8	12.4	<150.0	71	<1	4.2
MJVD-3-39	0.01	700	0.04	4	<20	0.02	2,730	4.2	6.5	40	18.4	9.1	<90.0	46	1	3.0
MJVD-3-40	0.02	540	0.04	6	<20	<0.01	1,480	0.3	0.5	10	13.3	6.2	<40.0	32	<1	2.2
MJVD-3-41	0.01	190	0.04	2	<20	<0.01	733	0.4	1.0	10	8.9	4.2	<20.0	17	<1	1.4
MJVD-3-42	0.01	110	0.05	<2	<20	<0.01	714	0.1	1.0	10	9.6	4.2	8	18	<1	1.6
MJVD-3-43	0.01	440	0.04	6	<20	<0.01	1,700	1.4	2.0	20	12.9	6.3	<60.0	31	<1	2.0
MJVD-3-44	0.01	210	0.04	8	<20	<0.01	9,630	1.1	2.0	20	23.4	14.3	30	105	<1	3.3
MJVD-3-45	<0.01	200	0.04	8	<20	<0.01	768	0.3	1.5	20	10.8	5.4	<40.0	23	<1	1.8
MJVD-3-46	0.01	310	0.04	2	<20	<0.01	842	0.2	1.0	20	10.4	5.2	<40.0	20	<1	1.9
MJVD-3-47	0.01	820	0.04	8	<20	<0.01	2,200	0.8	2.0	25	17.9	9.2	<80.0	41	<1	3.1
MJVD-3-48	0.01	200	0.04	2	<20	<0.01	1,835	0.1	1.0	20	13.8	6.8	<30.0	36	<1	2.4
MJVD-3-49	0.12	290	0.04	8	<20	<0.01	4,900	0.1	1.5	30	21.4	10.4	<150.0	65	<1	3.4
MJVD-3-50	0.11	370	0.04	8	<20	<0.01	5,040	0.2	1.0	30	26.0	12.9	<150.0	79	<1	4.5
MJVD-3-51	0.06	330	0.03	2	<20	<0.01	3,080	0.2	2.0	20	19.2	9.9	<90.0	52	<1	3.3
MJVD-3-52	<0.01	280	0.04	16	<20	<0.01	3,010	0.7	2.0	30	24.6	12.4	<40.0	68	<1	4.4
MJVD-3-53	0.01	1,290	0.04	26	<20	<0.01	2,750	0.4	2.0	30	21.6	11.2	<60.0	51	<1	3.8
MJVD-3-54	0.02	4,270	0.04	14	<20	<0.01	1,915	0.2	1.0	30	19.0	9.4	<80.0	49	<1	3.2
MJVD-3-55	0.04	2,410	0.04	10	<20	<0.01	1,495	0.2	1.5	35	18.3	9.3	<60.0	39	<1	3.3
MJVD-3-56	0.03	980	0.04	8	<20	<0.01	6,570	0.2	2.0	35	27.4	15.6	30	94	<1	4.5
MJVD-3-57	0.04	810	0.04	8	<20	<0.01	6,560	0.1	1.0	20	26.7	15.8	<40.0	92	<1	4.4
MJVD-3-58	0.04	510	0.04	6	<20	<0.01	7,460	0.2	0.5	20	23.1	13.9	30	89	<1	3.5
MJVD-3-59	0.04	200	0.05	12	<20	<0.01	13,170	0.2	1.5	35	30.5	19.2	30	139	<1	4.9
MJVD-3-60	0.02	180	0.04	6	<20	<0.01	2,900	0.2	0.5	15	23.2	11.0	20	56	<1	3.9
MJVD-3-61	0.02	370	0.05	8	<20	<0.01	3,560	0.2	1.0	20	21.5	11.0	<30.0	59	<1	3.9
MJVD-3-62	0.01	440	0.04	10	<20	<0.01	5,040	0.4	1.5	50	29.9	15.9	<50.0	85	<1	4.9
MJVD-3-63	0.05	230	0.07	8	<20	<0.01	5,270	0.3	1.0	30	31.5	15.6	30	89	<1	5.0
MJVD-3-64	0.04	320	0.05	8	<20	<0.01	9,420	0.1	1.0	30	30.6	18.0	<40.0	112	<1	4.7

MJVD-3 (18/126)

Sample Name	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm	Ho ppm
MJVD-3-65	0.08	120	0.05	6	<20	<0.01	6,150	0.2	0.5	20	22.9	13.1	<60.0	80	<1	3.6
MJVD-3-66	0.10	710	0.04	8	<20	<0.01	6,560	0.2	1.0	20	28.1	16.1	<100.0	94	<1	4.1
MJVD-3-67	0.06	410	0.04	10	<20	<0.01	1,925	0.1	1.0	30	19.8	8.8	<20.0	42	<1	3.3
MJVD-3-68	0.04	410	0.04	10	1	<0.01	16,280	0.2	0.5	20	27.9	18.5	<150.0	156	<1	4.1
MJVD-3-69	0.04	250	0.04	10	<20	<0.01	3,120	0.1	1.0	20	18.8	8.9	<100.0	55	<1	3.0
MJVD-3-70	0.10	760	0.04	10	<20	<0.01	5,210	0.1	1.5	25	32.9	15.3	<50.0	90	<1	5.2
MJVD-3-71	0.09	500	0.05	12	<20	<0.01	4,860	0.1	0.5	20	30.1	14.1	<100.0	84	<1	5.2
MJVD-3-72	0.01	400	0.07	6	<20	<0.01	1,420	0.4	1.0	20	26.2	10.9	<50.0	49	<1	4.5
MJVD-3-73	0.03	1,130	0.06	8	<20	<0.01	1,730	0.2	0.5	20	37.6	16.5	<30.0	68	<1	6.4
MJVD-3-74	0.04	1,220	0.04	24	<20	0.01	15,070	3.7	7.5	240	55.0	29.2	<100.0	201	1	8.7
MJVD-3-75	0.04	260	0.04	10	<20	<0.01	14,660	0.1	1.5	30	26.9	17.8	<100.0	142	<1	3.5
MJVD-3-76	0.01	550	0.03	26	<20	0.01	9,390	2.9	10.0	120	39.3	21.1	<80.0	129	<1	6.3
MJVD-3-77	0.01	620	0.04	26	<20	<0.01	2,880	0.1	1.5	50	22.3	11.2	<40.0	59	<1	3.5
MJVD-3-78	0.01	240	0.04	10	<20	<0.01	1,740	1	1.5	30	15.8	8.9	<20.0	37	<1	2.8
MJVD-3-79	<0.01	320	0.04	18	<20	<0.01	6,230	1	2.0	30	34.4	19.3	40	118	<1	5.6
MJVD-3-80	0.01	550	0.04	12	<20	<0.01	2,480	0.6	2.0	30	19.2	9.7	<40.0	47	<1	3.3

MJVD-3 (19/126)

Sample Name	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn	W
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-3-1	31,600	4,460	3.2	10,890	25	346	3,500	17.8	1,010	<1	3,560	5.0	58.0	2.5	107	4.5	3	42
MJVD-3-2	70,200	2,860	3.0	20,200	15	174	6,920	12.4	1,470	<1	3,230	2.5	89.4	1.5	177	4.4	1	58
MJVD-3-3	25,400	3,330	1.9	8,020	20	153	2,660	19.0	709	<1	4,010	2.5	39.3	1.0	77	2.8	2	64
MJVD-3-4	34,100	3,410	2.6	10,360	30	338	3,450	52.2	824	<1	4,320	3.5	48.4	2.5	77	3.9	1	55
MJVD-3-5	10,360	5,600	3.2	3,960	15	387	1,225	25.6	508	<1	5,270	5.0	30.9	2.0	149	4.4	1	37
MJVD-3-6	5,840	4,060	3.5	2,270	20	129	667	78.2	365	<1	3,890	1.5	26.0	2.5	24	5.0	1	19
MJVD-3-7	6,960	4,110	4.0	2,930	10	55	846	36.0	476	<1	3,720	1.0	31.9	1.5	21	5.6	1	88
MJVD-3-8	17,780	2,700	4.9	5,770	15	110	1,830	8.2	697	<1	4,390	2.0	48.7	2.5	61	6.7	2	10
MJVD-3-9	11,280	4,060	5.8	4,200	25	163	1,205	11.8	607	<1	4,140	2.0	48.8	2.5	31	8.6	1	5
MJVD-3-10	10,780	4,400	6.1	3,760	15	101	1,125	9.8	537	<1	4,070	1.5	41.0	1.5	33	8.3	5	2
MJVD-3-11	13,480	4,450	4.1	4,650	20	60	1,450	20.6	562	<1	3,870	2.0	36.6	1.5	37	5.6	2	3
MJVD-3-12	16,830	4,650	5.4	5,690	40	234	1,710	27.0	676	<1	4,720	2.0	50.2	2.0	43	7.6	1	72
MJVD-3-13	18,140	4,160	6.0	6,620	45	343	1,990	18.0	786	<1	3,920	3.0	61.1	2.5	50	8.9	<1	44
MJVD-3-14	14,890	5,740	2.8	5,130	40	271	1,625	34.6	554	1	4,330	2.5	32.8	4.0	65	4.1	1	197
MJVD-3-15	36,300	5,030	3.5	11,520	15	548	3,760	36.4	990	<1	4,640	5.5	65.8	3.5	87	5.7	1	81
MJVD-3-16	18,160	1,310	1.2	5,380	15	97	1,795	21.4	435	<1	4,310	2.0	25.7	0.5	45	1.7	2	856
MJVD-3-17	3,830	560	0.8	1,245	15	42	411	57.8	152	<1	5,260	2.0	7.3	<0.5	16	1.0	4	24
MJVD-3-18	9,120	1,000	0.8	2,720	5	39	905	10.0	286	<1	6,420	1.0	13.0	<0.5	33	1.0	2	4
MJVD-3-19	17,200	780	0.9	4,700	10	40	1,600	24.0	401	<1	5,430	1.0	21.2	<0.5	34	1.3	2	2
MJVD-3-20	4,170	600	0.6	1,280	15	16	424	6.2	165	<1	6,290	0.5	7.4	<0.5	13	0.8	<1	<1
MJVD-3-21	3,860	650	0.6	1,285	5	36	425	3.4	166	<1	7,650	0.5	7.6	<0.5	16	0.7	1	<1
MJVD-3-22	4,220	1,200	0.6	1,425	5	69	461	8.6	183	<1	7,840	1.0	8.0	<0.5	14	0.8	1	<1
MJVD-3-29	425	160	0.2	191	5	27	57	3.6	35	<1	4,610	<0.5	2.0	<0.5	1	0.4	1	<1
MJVD-3-30	2,820	335	0.4	980	5	41	316	8.0	89	<1	3,820	0.5	5.5	<0.5	8	0.5	<1	<1
MJVD-3-31	7,550	1,210	1.0	2,760	15	110	873	12.6	260	<1	4,120	1.0	15.6	<0.5	27	1.6	2	<1
MJVD-3-32	1,990	700	0.3	715	5	27	230	4.8	69	<1	3,480	<0.5	4.5	<0.5	6	0.5	<1	<1
MJVD-3-33	510	100	0.2	211	15	17	63	5.2	24	<1	3,990	<0.5	1.9	<0.5	<1	0.3	<1	<1
MJVD-3-35	3,340	810	0.9	1,260	15	192	397	16.6	143	<1	4,050	1.5	8.4	<0.5	14	1.1	1	<1
MJVD-3-36	1,820	700	0.7	729	10	111	223	10.4	89	<1	3,300	1.0	6.0	<0.5	6	1.1	2	48
MJVD-3-37	1,740	650	0.6	677	10	74	210	12.6	85	<1	3,870	0.5	5.2	<0.5	5	0.8	<1	<1
MJVD-3-38	3,190	910	0.7	1,270	20	53	393	29.4	167	<1	4,150	1.0	8.7	<0.5	17	1.2	<1	1
MJVD-3-39	1,985	535	0.6	786	30	47	242	69.4	102	<1	3,470	1.0	5.6	0.5	19	0.8	2	1
MJVD-3-40	1,030	300	0.4	435	5	91	134	4.2	62	<1	3,290	0.5	3.8	<0.5	8	0.5	<1	<1
MJVD-3-41	500	340	0.3	223	10	20	66	7.4	32	<1	3,750	<0.5	2.3	<0.5	4	0.4	<1	<1
MJVD-3-42	470	250	0.3	231	15	10	67	4.4	30	<1	3,090	<0.5	2.5	<0.5	1	0.5	<1	<1
MJVD-3-43	1,245	300	0.4	490	10	37	148	21.6	65	<1	3,570	0.5	3.9	<0.5	5	0.6	<1	<1
MJVD-3-44	7,080	360	0.5	2,390	10	16	779	11.2	195	<1	3,220	<0.5	12.0	<0.5	33	0.8	<1	<1
MJVD-3-45	468	360	0.4	276	10	24	75	6.0	50	<1	3,270	<0.5	2.9	<0.5	4	0.5	<1	<1
MJVD-3-46	586	160	0.3	257	10	106	76	4.0	45	<1	3,590	0.5	2.9	<0.5	4	0.5	<1	<1
MJVD-3-47	1,645	735	0.6	633	10	139	191	11.2	93	<1	3,530	0.5	5.4	<0.5	16	0.8	<1	<1
MJVD-3-48	1,315	330	0.3	555	15	30	170	2.4	70	<1	2,840	1.5	3.9	0.5	12	0.6	1	<1
MJVD-3-49	4,180	685	0.5	1,235	10	23	406	1.8	155	<1	5,310	1.5	7.1	<0.5	34	0.8	1	<1
MJVD-3-50	4,190	660	0.5	1,300	15	46	428	2.4	170	<1	4,820	1.5	8.5	<0.5	30	0.9	4	<1
MJVD-3-51	2,310	550	0.4	871	10	51	273	3.8	113	<1	3,740	1.0	5.7	<0.5	11	0.7	5	<1
MJVD-3-52	2,100	1,625	0.6	968	10	43	287	7.4	120	<1	2,500	1.0	7.4	<0.5	103	0.9	1	8
MJVD-3-53	2,030	1,735	0.6	803	15	40	250	3.4	99	<1	2,500	0.5	5.9	<0.5	10	0.9	1	13
MJVD-3-54	1,390	1,825	0.5	583	10	14	177	1.6	85	<1	3,250	3.0	4.5	<0.5	6	0.8	1	6
MJVD-3-55	998	1,800	0.5	494	15	28	144	1.2	77	<1	3,480	1.0	4.2	<0.5	3	0.8	2	<1
MJVD-3-56	5,010	1,480	0.5	1,840	10	43	593	1.8	166	<1	2,990	0.5	10.2	<0.5	7	1.1	2	<1
MJVD-3-57	4,990	1,260	0.6	1,830	5	32	592	1.2	174	<1	3,820	0.5	9.8	<0.5	10	1.0	2	<1
MJVD-3-58	5,870	875	0.4	2,010	5	32	667	1.4	167	<1	3,520	1.0	9.3	<0.5	9	0.8	2	<1
MJVD-3-59	10,370	1,250	0.5	3,260	5	29	1,085	1.0	256	<1	4,110	0.5	14.5	<0.5	17	0.9	2	<1
MJVD-3-60	2,060	775	0.4	848	10	26	261	1.0	94	<1	4,300	0.5	6.4	<0.5	4	0.9	1	<1
MJVD-3-61	2,600	1,030	0.4	1,020	5	75	315	1.8	107	<1	4,440	1.0	6.5	<0.5	5	0.7	1	<1
MJVD-3-62	3,710	2,000	0.5	1,460	10	86	457	2.8	153	<1	3,540	1.5	9.3	<0.5	8	1.1	2	<1
MJVD-3-63	3,920	1,725	0.6	1,505	10	67	473	1.8	151	<1	4,920	1.5	9.5	<0.5	7	1.0	2	<1
MJVD-3-64	6,850	1,275	0.6	2,370	10	67	781	1.2	202	<1	4,380	1.0	11.7	<0.5	10	1.0	2	<1

MJVD-3 (20/126)

Sample Name	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn	W
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-3-65	4,740	475	0.4	1,645	25	22	536	1.6	159	<1	5,470	1.5	8.6	<0.5	9	0.7	2	<1
MJVD-3-66	5,060	625	0.4	1,785	15	86	581	1.8	183	<1	6,040	1.0	9.8	<0.5	9	0.9	2	<1
MJVD-3-67	1,460	1,080	0.4	564	10	65	172	2.0	70	<1	6,200	0.5	4.9	<0.5	1	0.7	1	<1
MJVD-3-68	12,860	610	0.4	3,940	10	88	1,325	1.4	335	<1	4,510	1.5	15.9	<0.5	19	0.6	1	<1
MJVD-3-69	2,340	700	0.3	867	15	65	273	1.0	114	<1	3,620	0.5	5.9	<0.5	4	0.6	2	<1
MJVD-3-70	4,030	985	0.5	1,465	15	99	466	0.6	159	<1	4,060	2.0	10.1	<0.5	8	1.0	2	<1
MJVD-3-71	3,690	760	0.5	1,380	15	72	434	2.2	163	<1	5,480	1.5	9.3	<0.5	7	1.0	1	<1
MJVD-3-72	937	800	0.5	483	15	114	135	2.6	79	<1	5,010	1.0	5.8	<0.5	<1	0.9	1	<1
MJVD-3-73	1,225	1,000	0.9	601	15	164	170	1.8	98	<1	5,600	1.5	8.5	<0.5	1	1.5	1	<1
MJVD-3-74	11,700	2,240	0.9	3,880	30	88	1,260	31.2	368	<1	3,620	2.0	20.6	1.0	37	1.6	2	22
MJVD-3-75	11,630	685	0.4	3,540	10	47	1,190	2.0	288	<1	4,250	1.0	14.1	<0.5	16	0.6	1	<1
MJVD-3-76	7,050	2,090	0.8	2,490	35	54	804	31.2	241	<1	2,600	1.0	13.5	1.0	25	1.3	1	79
MJVD-3-77	2,490	1,285	0.5	980	10	79	307	3.2	106	<1	2,990	0.5	6.3	<0.5	4	0.7	1	6
MJVD-3-78	1,300	640	0.4	540	20	45	165	10.4	62	<1	2,740	0.5	4.5	<0.5	3	0.7	<1	<1
MJVD-3-79	6,370	870	0.6	2,380	10	48	782	10.4	213	<1	3,110	0.5	12.1	<0.5	12	1.2	1	<1
MJVD-3-80	1,855	615	0.4	734	25	62	230	12.0	88	<1	3,330	1.0	5.3	<0.5	6	0.7	1	<1

MJVD-3 (21/126)

Sample Name	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-3-1	179.0	150	26.9	548	1,035	87
MJVD-3-2	282.0	100	25.3	669	715	47
MJVD-3-3	124.5	85	14.9	324	1,055	49
MJVD-3-4	201.0	85	22.4	410	1,785	25
MJVD-3-5	142.0	110	24.3	491	2,220	22
MJVD-3-6	41.5	80	26.0	552	1,600	14
MJVD-3-7	53.5	55	28.9	653	1,085	4
MJVD-3-8	103.5	65	37.8	744	895	23
MJVD-3-9	94.5	45	46.9	973	1,150	2
MJVD-3-10	68.0	55	42.6	915	1,080	6
MJVD-3-11	71.5	65	28.7	715	2,460	3
MJVD-3-12	103.0	90	42.3	959	1,965	25
MJVD-3-13	141.0	90	38.3	997	3,150	22
MJVD-3-14	105.0	105	18.5	453	3,990	64
MJVD-3-15	261.0	75	24.7	602	5,370	28
MJVD-3-16	86.5	25	8.2	209	955	42
MJVD-3-17	22.5	70	4.4	91	565	89
MJVD-3-18	33.5	5	4.3	110	650	18
MJVD-3-19	39.5	35	6.5	149	530	48
MJVD-3-20	16.5	10	3.9	82	290	8
MJVD-3-21	20.0	25	3.1	78	285	11
MJVD-3-22	31.5	40	3.4	88	610	10
MJVD-3-29	12.0	10	1.6	38	110	2
MJVD-3-30	19.5	20	2.2	66	290	15
MJVD-3-31	52.5	30	7.3	179	1,540	12
MJVD-3-32	16.5	<5	2.0	60	240	1
MJVD-3-33	8.5	15	1.5	38	155	3
MJVD-3-35	64.5	60	5.1	114	975	18
MJVD-3-36	36.0	30	4.2	96	710	11
MJVD-3-37	28.0	30	4.1	85	530	42
MJVD-3-38	27.5	50	4.3	126	915	51
MJVD-3-39	21.0	60	4.1	91	845	98
MJVD-3-40	25.0	<5	2.6	67	175	1
MJVD-3-41	8.5	10	1.9	47	185	4
MJVD-3-42	5.0	<5	1.8	51	190	3
MJVD-3-43	15.0	25	3.5	65	465	23
MJVD-3-44	7.5	<5	3.7	107	405	14
MJVD-3-45	7.5	<5	2.4	55	285	5
MJVD-3-46	28.0	<5	2.1	55	230	2
MJVD-3-47	39.0	5	4.3	92	480	12
MJVD-3-48	12.0	<5	2.5	69	180	44
MJVD-3-49	13.5	<5	3.3	95	430	23
MJVD-3-50	19.5	<5	4.7	131	365	17
MJVD-3-51	25.0	10	3.3	89	265	19
MJVD-3-52	25.0	30	5.1	117	705	26
MJVD-3-53	24.0	25	4.3	112	825	23
MJVD-3-54	13.0	45	3.7	89	705	11
MJVD-3-55	18.0	50	4.2	87	610	11
MJVD-3-56	33.5	45	5.0	124	335	10
MJVD-3-57	25.5	30	5.2	121	370	8
MJVD-3-58	25.0	35	3.6	99	315	10
MJVD-3-59	33.0	25	4.8	125	500	10
MJVD-3-60	15.5	25	4.4	103	285	19
MJVD-3-61	32.0	40	4.3	95	310	24
MJVD-3-62	37.0	105	5.6	129	400	17
MJVD-3-63	38.5	65	5.2	143	375	21
MJVD-3-64	39.0	35	4.9	124	315	15

MJVD-3 (22/126)

Sample Name	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-3-65	17.5	30	3.6	96	265	12
MJVD-3-66	43.5	25	4.3	120	390	24
MJVD-3-67	26.0	40	3.1	85	325	16
MJVD-3-68	60.5	55	3.2	100	470	30
MJVD-3-69	34.0	80	3.2	82	585	20
MJVD-3-70	42.5	30	4.7	139	420	29
MJVD-3-71	39.5	30	5.4	136	280	21
MJVD-3-72	42.5	30	5.0	109	255	40
MJVD-3-73	52.0	60	7.1	166	250	16
MJVD-3-74	43.0	80	8.1	252	1,145	77
MJVD-3-75	43.5	45	3.8	92	355	9
MJVD-3-76	29.5	80	6.5	187	995	58
MJVD-3-77	29.0	15	4.4	101	215	12
MJVD-3-78	15.0	30	3.2	80	355	18
MJVD-3-79	35.5	100	6.0	137	440	34
MJVD-3-80	22.0	60	3.6	86	410	22

MJVD-4 (23/126)

Sample Name	F	Ba	Al	As	B	Be	Bi	Ca	Cd	Cr	Fe	Ga	Hg	K	Mg	Mn
	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%	ppm
MJVD-4-1	0.4	42.60	0.82	470	<10	<5.0	<10	0.12	1.0	26	3.11	<100	<1	0.04	0.02	7,230
MJVD-4-2	0.5	37.00	0.74	640	<10	<5.0	<10	0.07	1.0	27	3.04	<100	<1	0.08	0.02	>10,000
MJVD-4-3	0.6	45.40	0.29	880	<10	<5.0	<10	0.17	1.5	12	1.65	<100	2	0.03	<0.01	>10,000
MJVD-4-4	0.8	34.20	1.89	952	<10	<5.0	<10	0.15	3.5	40	2.52	<100	<1	0.07	0.02	7,100
MJVD-4-5	0.6	36.70	1.28	580	<10	<5.0	10	0.47	5.0	45	2.66	<100	1	0.09	0.03	>10,000
MJVD-4-6	1.8	38.50	0.95	390	10	5	<10	2.29	6.0	36	2.26	<100	1	0.17	0.04	>10,000
MJVD-4-7	2.3	28.80	0.39	704	350	<5.0	<10	8.83	3.0	9	0.82	<100	<1	0.10	0.04	5,350
MJVD-4-8	0.7	21.70	0.15	176	10	<5.0	<10	>15.00	3.5	4	0.55	<100	<1	0.04	0.07	5,810
MJVD-4-9	0.5	14.90	0.06	36	50	<5.0	<10	>15.00	3.0	1	0.25	<100	1	0.03	0.08	3,770
MJVD-4-10	1.1	14.05	0.38	284	<10	<5.0	<10	>15.00	2.0	6	1.03	<100	<1	0.07	0.09	3,570
MJVD-4-11	1.0	10.35	1.63	434	<10	<5.0	<10	7.51	1.0	69	2.84	<100	<1	0.41	0.19	2,130
MJVD-4-12	1.9	4.96	1.71	132	<10	<5.0	<10	>15.00	0.5	69	1.39	<100	<1	0.68	0.16	2,530
MJVD-4-13	1.5	4.06	0.27	258	160	<5.0	<10	>15.00	4.0	4	0.60	<100	<1	0.10	0.07	4,100
MJVD-4-14	13.2	18.55	0.21	210	1,510	<5.0	<10	13.75	1.0	1	0.10	<100	<1	0.12	0.03	2,590
MJVD-4-15	7.6	17.35	0.34	170	1,080	<5.0	<10	>15.00	1.5	3	0.27	<100	<1	0.14	0.06	2,610
MJVD-4-16	0.8	4.13	0.23	96	10	<5.0	<10	>15.00	2.5	3	0.48	<100	<1	0.06	0.09	3,950
MJVD-4-17	0.5	2.77	0.10	92	10	<5.0	<10	>15.00	2.5	1	0.66	<100	1	0.04	0.08	4,300
MJVD-4-18	1.5	8.70	0.11	426	380	<5.0	<10	>15.00	2.5	1	0.59	<100	<1	0.06	0.06	3,150
MJVD-4-19	1.4	7.23	0.10	142	340	<5.0	<10	>15.00	2.0	1	0.35	<100	<1	0.06	0.12	3,180
MJVD-4-20	1.4	10.35	0.11	58	400	<5.0	<10	>15.00	2.0	1	0.29	<100	<1	0.06	0.16	3,060
MJVD-4-21	1.3	15.05	0.18	130	250	<5.0	<10	>15.00	1.5	3	0.38	<100	<1	0.06	0.09	3,070
MJVD-4-22	0.6	19.90	0.23	108	<10	<5.0	<10	>15.00	1.5	4	0.49	<100	<1	0.03	0.16	4,140
MJVD-4-23	0.7	10.35	0.24	140	<10	<5.0	<10	>15.00	2.5	5	0.55	<100	<1	0.04	0.11	4,480
MJVD-4-24	1.5	3.96	0.18	78	230	<5.0	<10	>15.00	2.5	3	0.39	<100	<1	0.06	0.07	3,460
MJVD-4-25	0.8	13.40	0.18	190	30	<5.0	<10	>15.00	2.5	5	0.42	<100	<1	0.04	0.05	2,750
MJVD-4-26	0.5	12.35	0.08	208	90	<5.0	<10	>15.00	1.5	1	0.23	<100	<1	0.03	0.08	2,380
MJVD-4-27	0.5	6.38	0.07	20	60	<5.0	<10	>15.00	2.0	1	0.30	<100	<1	0.03	0.27	2,760
MJVD-4-28	0.3	6.05	0.04	38	30	<5.0	<10	>15.00	1.5	1	0.21	<100	<1	0.01	0.09	2,730
MJVD-4-29	0.3	12.95	0.05	74	20	<5.0	<10	>15.00	1.5	2	0.25	<100	<1	0.02	0.08	2,470
MJVD-4-30	0.7	15.60	0.12	120	10	<5.0	<10	>15.00	2.5	6	0.82	<100	<1	0.04	0.08	3,230
MJVD-4-31	0.2	7.39	0.03	38	20	<5.0	<10	>15.00	0.5	<1	0.24	<100	<1	0.01	0.09	3,000
MJVD-4-32	0.1	1.62	0.01	18	10	<5.0	<10	>15.00	0.5	<1	0.13	<100	<1	<0.01	0.12	2,070
MJVD-4-33	0.2	5.16	0.01	16	30	<5.0	<10	>15.00	<0.5	<1	0.14	<100	<1	0.01	0.11	1,975
MJVD-4-34	0.2	4.66	0.03	36	10	<5.0	<10	>15.00	<0.5	<1	0.13	<100	<1	0.01	0.11	2,010
MJVD-4-35	0.5	8.96	0.05	102	110	<5.0	<10	>15.00	0.5	<1	0.16	<100	<1	0.03	0.09	2,640
MJVD-4-36	0.8	12.65	0.10	98	170	<5.0	<10	>15.00	1.0	3	0.33	<100	<1	0.05	0.09	2,810
MJVD-4-37	0.6	7.55	0.06	88	100	<5.0	<10	>15.00	0.5	1	0.48	<100	<1	0.03	0.18	2,540
MJVD-4-38	0.3	2.52	0.02	48	10	<5.0	<10	>15.00	<0.5	<1	0.17	<100	<1	0.03	0.18	2,750
MJVD-4-39	0.4	5.55	0.03	12	<10	<5.0	<10	>15.00	<0.5	<1	0.14	<100	<1	0.05	0.19	2,430
MJVD-4-40	0.2	1.81	0.01	10	<10	<5.0	<10	>15.00	<0.5	<1	0.15	<100	<1	0.01	0.17	2,890
MJVD-4-41	0.4	10.25	0.10	164	10	<5.0	<10	>15.00	1.0	3	0.45	<100	<1	0.03	0.14	2,860
MJVD-4-42	0.8	10.50	0.07	304	210	<5.0	<10	>15.00	1.0	1	0.26	<100	<1	0.04	0.13	2,730
MJVD-4-43	0.7	2.75	0.06	58	120	<5.0	<10	>15.00	1.0	3	0.57	<100	<1	0.05	0.16	3,540
MJVD-4-44	1.4	13.05	0.10	90	290	<5.0	<10	>15.00	1.5	2	0.57	<100	<1	0.09	0.16	2,890
MJVD-4-45	0.4	4.08	0.04	44	40	<5.0	<10	>15.00	0.5	1	0.37	<100	<1	0.02	0.12	2,290
MJVD-4-46	1.0	20.10	0.08	164	310	<5.0	<10	>15.00	0.5	1	0.30	<100	<1	0.04	0.07	1,710
MJVD-4-47	0.9	8.21	0.06	134	60	<5.0	<10	>15.00	0.5	1	0.53	<100	<1	0.09	0.18	2,750
MJVD-4-48	0.6	5.82	0.05	86	<10	<5.0	<10	>15.00	2.0	1	0.59	<100	<1	0.09	0.21	2,640
MJVD-4-49	0.7	7.47	0.08	88	170	<5.0	<10	>15.00	2.5	1	0.47	<100	<1	0.04	0.10	2,640
MJVD-4-50	1.3	5.33	0.13	262	330	<5.0	<10	>15.00	1.0	<1	0.27	<100	<1	0.06	0.10	3,190
MJVD-4-51	0.5	5.01	0.37	124	<10	<5.0	<10	>15.00	1.0	7	0.56	<100	<1	0.05	0.16	2,990
MJVD-4-52	0.3	3.94	0.06	40	<10	<5.0	<10	>15.00	1.0	<1	0.16	<100	<1	0.01	0.14	4,110
MJVD-4-53	1.0	8.93	1.01	426	<10	<5.0	<10	>15.00	1.5	20	0.97	<100	<1	0.07	0.17	2,970
MJVD-4-54	0.5	16.85	0.23	236	<10	<5.0	<10	>15.00	1.5	4	0.36	<100	<1	0.03	0.06	2,920
MJVD-4-55	0.2	8.85	0.13	44	<10	<5.0	<10	>15.00	1.5	3	0.26	<100	<1	0.01	0.10	3,210
MJVD-4-56	0.3	5.82	0.12	50	<10	<5.0	<10	>15.00	1.5	3	0.30	<100	<1	0.04	0.15	3,360
MJVD-4-57	0.4	6.75	0.29	70	<10	<5.0	<10	>15.00	1.0	6	0.42	<100	<1	0.04	0.14	3,370

MJVD-4 (24/126)

Sample Name	F %	Ba %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm
MJVD-4-58	0.6	3.59	0.32	50	<10	<5.0	<10	>15.00	2.0	5	0.39	<100	<1	0.06	0.13	3,890
MJVD-4-59	0.2	2.42	0.05	8	<10	<5.0	<10	>15.00	0.5	1	0.13	<100	<1	0.02	0.12	2,080
MJVD-4-60	0.3	3.80	0.08	74	<10	<5.0	<10	>15.00	0.5	1	0.27	<100	<1	0.04	0.15	2,650
MJVD-4-61	0.7	3.32	0.13	<2	120	<5.0	<10	>15.00	1.0	4	0.33	<100	1	0.08	1.92	3,670
MJVD-4-62	0.6	8.32	0.06	58	100	<5.0	<10	>15.00	1.0	1	0.25	<100	<1	0.04	0.20	3,230
MJVD-4-63	0.7	5.02	0.06	26	100	<5.0	<10	>15.00	0.5	<1	0.21	<100	<1	0.04	0.62	2,900
MJVD-4-64	0.6	4.48	0.32	100	<10	<5.0	<10	>15.00	2.5	9	0.45	<100	1	0.06	0.19	3,810
MJVD-4-65	3.6	16.75	0.78	536	60	5	<10	13.20	1.0	14	0.79	<100	<1	0.33	0.13	5,850
MJVD-4-66	1.1	3.35	1.05	198	<10	5	<10	>15.00	1.5	15	0.81	<100	<1	0.13	0.24	7,080
MJVD-4-67	0.6	5.90	0.16	64	<10	<5.0	<10	>15.00	1.5	2	0.45	<100	<1	0.10	0.24	3,540
MJVD-4-68	0.5	6.40	0.09	34	<10	<5.0	<10	>15.00	1.5	<1	0.31	<100	<1	0.12	0.37	3,210
MJVD-4-69	0.9	4.95	0.14	18	80	<5.0	<10	>15.00	0.5	1	0.30	<100	<1	0.10	2.50	2,910
MJVD-4-70	0.4	3.41	0.10	10	<10	<5.0	<10	>15.00	0.5	1	0.28	<100	1	0.09	0.29	3,310
MJVD-4-71	1.4	19.55	0.85	184	<10	5	<10	13.30	1.0	18	1.24	<100	1	0.30	0.35	4,610
MJVD-4-72	1.1	3.90	0.74	62	<10	5	<10	>15.00	0.5	12	0.67	<100	1	0.17	3.00	3,370
MJVD-4-73	0.4	4.56	0.06	24	<10	<5.0	<10	>15.00	0.5	1	0.27	<100	<1	0.11	0.28	3,290
MJVD-4-74	0.7	8.46	0.06	42	<10	<5.0	<10	>15.00	1.0	3	0.60	<100	<1	0.12	0.25	2,970
MJVD-4-75	1.1	1.42	0.07	6	110	<5.0	<10	>15.00	<0.5	1	0.16	<100	<1	0.13	5.32	2,350
MJVD-4-76	2.0	3.66	0.13	230	390	5	<10	>15.00	0.5	1	0.22	<100	<1	0.15	1.43	3,140
MJVD-4-77	0.9	2.73	0.05	54	10	5	<10	>15.00	0.5	<1	0.16	<100	<1	0.24	1.26	3,090
MJVD-4-78	0.6	10.30	0.06	34	<10	5	<10	>15.00	1.0	2	0.31	<100	<1	0.18	1.53	2,870
MJVD-4-79	1.1	12.75	0.08	176	140	<5.0	<10	>15.00	2.0	3	0.55	<100	<1	0.08	0.16	3,380
MJVD-4-80	3.1	8.88	0.16	150	750	<5.0	<10	>15.00	2.5	3	0.56	<100	<1	0.10	0.17	3,360
MJVD-4-81	1.3	6.21	0.20	104	160	<5.0	<10	>15.00	2.5	6	0.42	<100	<1	0.08	0.14	2,820
MJVD-4-82	1.9	8.82	0.19	80	320	<5.0	<10	>15.00	2.5	3	0.26	<100	<1	0.09	0.13	3,540
MJVD-4-83	0.9	4.60	0.08	86	190	<5.0	<10	>15.00	0.5	2	0.26	<100	<1	0.05	2.27	2,810
MJVD-4-84	0.9	6.49	0.07	198	170	<5.0	<10	>15.00	3.5	1	0.32	<100	<1	0.04	0.10	3,870
MJVD-4-85	1.1	5.87	0.11	288	200	<5.0	<10	>15.00	2.5	1	0.24	<100	<1	0.06	0.11	3,520
MJVD-4-86	1.6	3.34	0.09	308	450	<5.0	<10	>15.00	0.5	1	0.17	<100	<1	0.06	2.82	2,110
MJVD-4-87	1.9	6.94	0.10	574	450	<5.0	<10	>15.00	0.5	2	0.26	<100	<1	0.08	0.36	2,380
MJVD-4-88	2.5	8.46	0.11	266	540	<5.0	<10	>15.00	1.5	<1	0.58	<100	<1	0.07	0.29	2,720
MJVD-4-89	0.8	11.00	0.06	42	140	<5.0	<10	>15.00	0.5	2	0.37	<100	<1	0.06	3.74	2,460
MJVD-4-90	1.0	1.62	0.07	8	200	<5.0	<10	>15.00	<0.5	<1	0.18	<100	1	0.06	0.51	3,480
MJVD-4-91	1.8	11.95	0.09	78	450	<5.0	<10	>15.00	1.0	7	0.27	<100	<1	0.06	0.18	2,760
MJVD-4-92	0.8	8.45	0.06	118	160	<5.0	<10	>15.00	1.5	<1	0.24	<100	<1	0.04	0.17	2,830
MJVD-4-93	0.8	6.38	0.06	130	150	<5.0	<10	>15.00	2.0	13	0.85	<100	1	0.04	0.10	3,330
MJVD-4-94	3.6	9.81	0.13	152	750	<5.0	<10	>15.00	2.5	3	0.66	<100	<1	0.09	0.09	3,480
MJVD-4-95	8.0	9.74	0.14	94	1,190	<5.0	<10	>15.00	1.0	1	0.35	<100	<1	0.17	0.15	2,730
MJVD-4-96	6.8	12.35	0.18	324	1,190	<5.0	<10	>15.00	2.5	3	0.77	<100	<1	0.11	0.05	2,420
MJVD-4-97	1.7	10.45	0.10	46	460	<5.0	<10	>15.00	1.5	1	0.38	<100	<1	0.06	0.10	2,680
MJVD-4-98	1.11	10.65	0	268	270	<5.0	<10	>15.00	2	1	0.42	<100	<1	0	0.07	3,000
MJVD-4-99	0.39	12.3	0	82	110	<5.0	<10	>15.00	0.5	1	0.28	<100	<1	0	0.11	2,150
MJVD-4-100	0.83	6.93	0	66	180	<5.0	<10	>15.00	0.5	1	0.36	<100	<1	0	0.58	1,505

MJVD-4 (25/126)

Sample Name	Mo ppm	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm	Ho ppm
MJVD-4-1	14	<0.01	1,460	0.04	32	<20	0.01	16,970	1	8.0	85	101.5	45.1	<450	330	1	13.6
MJVD-4-2	28	<0.01	1,730	0.03	34	<20	0.01	19,610	0.7	8.5	70	145.5	64.4	<400	464	1	19.7
MJVD-4-3	49	0.01	2,540	0.02	48	<20	0.01	16,830	0.2	6.5	70	236.0	96.6	<450	758	1	30.3
MJVD-4-4	22	<0.01	2,010	0.03	18	<20	0.02	40,000	1.3	9.5	50	129.5	72.7	<350	536	13	17.4
MJVD-4-5	19	<0.01	3,340	0.02	26	<20	0.01	19,640	2	10.0	75	158.5	73.1	<350	468	2	22.2
MJVD-4-6	12	0.01	1,920	0.03	30	<20	0.01	18,500	1.3	7.0	70	103.0	51.4	<400	297	1	15.2
MJVD-4-7	13	0.08	1,330	0.06	20	<20	<0.01	43,700	0.5	3.0	25	103.0	62.5	<300	463	<1	13.7
MJVD-4-8	18	0.03	1,030	0.09	18	<20	<0.01	10,510	0.4	2.0	40	57.3	28.6	<200	160	<1	8.7
MJVD-4-9	109	0.03	780	0.11	20	<20	<0.01	1,900	0.2	1.0	35	24.0	10.5	<150.0	53	<1	3.6
MJVD-4-10	29	0.03	1,590	0.11	30	<20	<0.01	12,540	0.6	4.5	40	45.8	25.5	<150.0	158	<1	6.4
MJVD-4-11	10	0.01	1,860	0.04	10	<20	0.01	20,000	5.7	18.0	35	35.5	23.4	<100.0	147	3	5.1
MJVD-4-12	5	0.01	1,420	0.07	4	<20	<0.01	6,220	5	10.5	10	24.3	13.0	<50.0	77	2	3.6
MJVD-4-13	3	0.05	720	0.12	10	<20	<0.01	14,160	0.3	2.0	5	48.3	25.9	40	144	<1	7.0
MJVD-4-14	3	0.23	250	0.06	<2	<20	<0.01	11,490	0.1	<0.5	<5	38.8	21.2	<200	140	2	5.5
MJVD-4-15	3	0.18	270	0.06	2	<20	<0.01	9,890	0.4	1.5	<5	34.4	18.8	<200	130	1	4.8
MJVD-4-16	26	0.03	730	0.12	8	<20	<0.01	5,070	0.4	1.5	25	30.8	16.4	<40.0	77	<1	4.8
MJVD-4-17	1	0.03	530	0.16	8	<20	<0.01	5,630	0.4	6.0	145	33.5	17.5	20	84	<1	4.9
MJVD-4-18	4	0.08	450	0.11	8	<20	<0.01	22,300	0.2	1.5	30	47.0	29.2	<90.0	196	<1	6.4
MJVD-4-19	3	0.08	770	0.09	8	<20	<0.01	8,160	0.2	1.0	35	32.3	18.4	<70.0	102	<1	4.7
MJVD-4-20	1	0.09	760	0.09	4	<20	<0.01	3,740	0.1	2.0	30	34.1	14.7	<100.0	85	<1	4.7
MJVD-4-21	1	0.06	750	0.08	6	<20	<0.01	7,000	0.3	1.0	10	32.3	16.7	<150.0	95	<1	4.3
MJVD-4-22	4	0.01	700	0.07	10	<20	<0.01	5,670	0.4	1.5	30	33.4	17.2	<200	91	<1	4.9
MJVD-4-23	4	0.01	670	0.05	18	<20	<0.01	6,850	0.5	2.5	190	29.6	16.1	<100.0	93	<1	4.5
MJVD-4-24	5	0.05	530	0.06	12	<20	<0.01	4,340	0.3	1.0	15	25.2	13.7	<40.0	69	<1	3.9
MJVD-4-25	2	0.02	670	0.04	20	<20	<0.01	10,950	0.4	1.0	20	30.4	18.2	<140.0	121	<1	4.3
MJVD-4-26	1	0.04	580	0.07	8	<20	<0.01	12,490	0.1	0.5	5	29.1	18.2	<130.0	125	<1	4.0
MJVD-4-27	1	0.03	440	0.06	6	<20	<0.01	1,565	0.1	0.5	5	18.0	8.5	<60.0	39	<1	2.8
MJVD-4-28	<1	0.02	310	0.04	4	<20	<0.01	2,270	0.2	0.5	10	15.3	8.1	<60.0	38	<1	2.3
MJVD-4-29	1	0.02	790	0.05	8	<20	<0.01	4,260	0.2	1.5	10	19.7	9.9	<140.0	59	<1	2.6
MJVD-4-30	4	0.02	1,070	0.06	18	<20	<0.01	5,670	0.4	2.5	55	30.5	15.2	<150.0	86	<1	4.3
MJVD-4-31	1	0.03	360	0.09	<2	<20	<0.01	2,330	0.2	1.0	10	22.3	10.9	<70.0	48	<1	3.1
MJVD-4-32	<1	0.03	150	0.07	<2	<20	<0.01	1,670	0.2	1.0	5	13.7	7.3	<20.0	31	<1	2.1
MJVD-4-33	<1	0.03	470	0.07	2	<20	<0.01	1,265	0.2	1.5	10	12.5	6.0	<50.0	28	<1	1.7
MJVD-4-34	<1	0.03	390	0.07	<2	<20	<0.01	2,490	0.2	0.5	5	13.5	6.5	<50.0	38	<1	2.0
MJVD-4-35	3	0.04	270	0.07	<2	<20	<0.01	6,010	0.2	0.5	10	20.1	11.1	<100.0	71	<1	3.0
MJVD-4-36	1	0.05	1,000	0.06	6	<20	<0.01	5,300	0.2	1.0	20	20.7	11.7	<150.0	66	<1	2.9
MJVD-4-37	3	0.04	290	0.09	10	<20	<0.01	5,100	0.2	3.0	35	21.4	12.1	<80.0	65	<1	3.1
MJVD-4-38	2	0.03	210	0.09	<2	<20	<0.01	3,370	0.4	0.5	5	22.5	11.3	<25.0	57	<1	3.6
MJVD-4-39	1	0.03	250	0.09	<2	<20	<0.01	1,390	0.3	0.5	<5	15.8	7.9	<50.0	35	<1	2.5
MJVD-4-40	1	0.03	280	0.11	<2	<20	<0.01	1,040	0.2	1.0	5	18.4	7.7	<20.0	32	<1	2.6
MJVD-4-41	1	0.03	410	0.1	8	<20	<0.01	8,060	0.2	2.0	25	27.2	14.8	<100.0	94	<1	3.6
MJVD-4-42	4	0.05	310	0.11	6	<20	<0.01	18,030	0.2	1.5	20	34.2	22.7	<100.0	166	<1	4.8
MJVD-4-43	3	0.05	1,520	0.12	6	<20	<0.01	3,470	0.2	1.0	25	26.2	13.1	20	65	<1	3.8
MJVD-4-44	3	0.07	710	0.09	12	<20	<0.01	5,170	0.2	2.5	35	25.4	13.2	<150.0	76	<1	3.6
MJVD-4-45	3	0.03	350	0.09	8	<20	<0.01	2,630	0.2	2.0	30	16.0	8.1	<40.0	42	<1	2.4
MJVD-4-46	3	0.07	620	0.06	8	<20	<0.01	8,480	0.1	1.0	20	16.8	11.2	<200	86	<1	2.3
MJVD-4-47	4	0.04	860	0.09	8	<20	<0.01	9,170	0.3	2.0	30	36.6	18.3	<100.0	134	<1	5.0
MJVD-4-48	3	0.03	780	0.09	12	<20	<0.01	5,130	0.4	4.0	40	24.5	13.0	<50.0	76	<1	3.4
MJVD-4-49	1	0.05	1,080	0.09	14	<20	<0.01	5,550	0.2	2.5	40	25.9	13.7	<80.0	82	<1	3.7
MJVD-4-50	2	0.08	420	0.13	2	<20	<0.01	15,820	0.4	1.0	15	36.1	22.2	50	159	<1	4.7
MJVD-4-51	5	0.03	850	0.12	6	<20	<0.01	6,290	0.8	1.0	20	62.0	29.8	40	138	<1	9.4
MJVD-4-52	3	0.03	2,200	0.14	2	<20	<0.01	2,460	0.3	1.0	15	24.6	11.8	<40.0	56	<1	3.9
MJVD-4-53	6	0.01	1,650	0.04	20	<20	0.01	23,400	2	5.5	45	49.8	31.1	<100.0	237	<1	6.5
MJVD-4-54	4	0.01	740	0.04	14	<20	<0.01	12,720	0.8	2.5	30	34.6	20.5	<150.0	134	<1	4.7
MJVD-4-55	2	0.02	850	0.05	8	<20	<0.01	2,820	0.5	1.0	35	20.1	10.4	<100.0	54	<1	3.3
MJVD-4-56	3	0.03	890	0.09	6	<20	<0.01	3,020	0.6	1.5	15	22.7	11.1	<50.0	58	<1	3.4
MJVD-4-57	1	0.02	970	0.06	8	<20	<0.01	3,640	0.9	2.0	25	21.9	11.9	<60.0	60	<1	3.2

MJVD-4 (26/126)

Sample Name	Mo ppm	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm	Ho ppm
MJVD-4-58	1	0.02	930	0.05	8	<20	<0.01	2,780	1.1	2.0	40	21.0	11.0	<30.0	57	<1	3.3
MJVD-4-59	<1	0.02	210	0.06	2	<20	<0.01	809	0.4	0.5	10	11.0	5.1	<20.0	22	<1	1.7
MJVD-4-60	4	0.03	930	0.08	2	<20	<0.01	4,210	0.5	0.5	10	20.7	11.5	<40.0	63	<1	3.0
MJVD-4-61	6	0.05	350	0.08	6	<20	<0.01	2,800	0.3	0.5	45	22.4	10.4	<30.0	56	<1	3.3
MJVD-4-62	4	0.04	460	0.06	4	<20	<0.01	3,600	0.2	1.5	30	23.9	13.5	<100.0	63	<1	3.8
MJVD-4-63	9	0.04	460	0.12	4	<20	<0.01	1,890	0.2	1.5	20	21.8	9.4	<50.0	47	<1	3.3
MJVD-4-64	4	0.02	1,100	0.09	8	<20	<0.01	6,120	0.7	3.0	45	34.1	16.8	<45.0	104	<1	5.2
MJVD-4-65	9	0.04	1,710	0.06	22	<20	0.01	31,200	1.1	3.5	70	83.2	47.8	<200	381	1	11.1
MJVD-4-66	7	0.02	820	0.07	20	<20	0.01	14,880	2.7	4.5	75	71.1	40.5	120	355	1	9.7
MJVD-4-67	5	0.03	470	0.11	6	<20	<0.01	4,000	0.6	1.5	35	28.3	13.7	<60.0	77	<1	4.1
MJVD-4-68	4	0.03	450	0.12	2	<20	<0.01	2,450	0.6	1.5	25	22.3	11.4	<60.0	53	<1	3.6
MJVD-4-69	7	0.03	170	0.07	2	<20	<0.01	1,435	0.5	0.5	15	18.2	8.0	<50.0	37	<1	2.7
MJVD-4-70	2	0.03	100	0.14	<2	<20	<0.01	1,130	0.8	0.5	10	20.4	9.5	<40.0	41	<1	3.4
MJVD-4-71	6	0.02	830	0.06	18	<20	0.01	9,640	3.3	5.0	60	36.2	19.6	<200	131	1	5.2
MJVD-4-72	5	0.02	390	0.06	8	<20	0.01	3,610	2.9	3.0	30	26.9	12.8	<40.0	68	<1	4.2
MJVD-4-73	9	0.03	620	0.13	2	<20	<0.01	1,780	0.9	1.0	20	23.5	9.6	<40.0	50	<1	3.6
MJVD-4-74	5	0.03	820	0.09	8	<20	<0.01	2,760	0.8	3.0	50	25.9	12.5	<100.0	59	<1	3.9
MJVD-4-75	4	0.04	40	0.07	<2	<20	<0.01	907	0.4	0.5	<5	14.0	6.0	<15.0	29	<1	2.0
MJVD-4-76	5	0.08	90	0.07	2	<20	<0.01	15,810	0.4	0.5	10	53.1	28.1	40	185	<1	7.4
MJVD-4-77	29	0.03	110	0.13	4	<20	<0.01	3,900	1.1	<0.5	15	30.0	13.7	30	79	<1	4.6
MJVD-4-78	7	0.02	260	0.11	6	<20	<0.01	2,190	1	1.5	25	19.2	9.7	<100.0	50	<1	2.9
MJVD-4-79	5	0.04	770	0.08	14	<20	<0.01	10,510	0.3	2.5	50	37.1	20.3	<150.0	129	<1	5.5
MJVD-4-80	4	0.13	1,080	0.08	10	<20	<0.01	9,440	0.3	1.5	55	36.8	19.5	<100.0	121	<1	5.1
MJVD-4-81	<1	0.04	260	0.06	12	<20	<0.01	5,620	0.5	2.0	50	34.4	16.6	<60.0	110	<1	5.1
MJVD-4-82	<1	0.07	260	0.08	14	<20	<0.01	4,930	0.3	1.0	65	28.2	14.8	<95.0	92	<1	4.1
MJVD-4-83	<1	0.05	120	0.09	4	<20	<0.01	5,260	0.2	1.0	20	28.7	14.5	<45.0	81	<1	4.3
MJVD-4-84	<1	0.05	1,070	0.1	10	<20	<0.01	12,890	0.3	1.5	45	46.8	26.7	60	169	4	7.0
MJVD-4-85	5	0.05	340	0.1	4	<20	<0.01	16,020	0.3	1.0	35	46.4	27.0	50	187	<1	6.6
MJVD-4-86	64	0.09	350	0.42	2	<20	<0.01	18,940	0.2	0.5	25	35.8	24.0	60	184	<1	4.8
MJVD-4-87	32	0.10	200	0.48	4	<20	<0.01	35,800	0.3	1.0	20	64.7	41.4	60	334	<1	8.0
MJVD-4-88	57	0.11	760	0.68	10	<20	<0.01	14,230	0.2	1.5	50	30.6	19.5	<90.0	139	<1	4.2
MJVD-4-89	18	0.04	240	0.25	6	<20	<0.01	2,320	0.3	1.5	25	16.9	8.0	<120.0	45	<1	2.6
MJVD-4-90	18	0.06	460	0.32	2	<20	<0.01	1,160	0.3	1.0	10	19.6	9.4	10	38	<1	3.0
MJVD-4-91	54	0.09	770	0.31	12	<20	<0.01	4,540	0.3	1.0	35	26.6	12.8	<150.0	79	<1	3.8
MJVD-4-92	61	0.05	380	0.4	8	<20	<0.01	6,940	0.4	1.5	85	31.1	15.6	<90.0	107	2	4.5
MJVD-4-93	39	0.05	1,050	0.14	20	<20	<0.01	6,080	0.3	2.5	105	26.6	13.1	<60.0	82	<1	4.1
MJVD-4-94	26	0.14	910	0.11	8	<20	<0.01	7,970	0.2	1.5	65	32.9	17.6	<100.0	114	3	5.0
MJVD-4-95	30	0.20	530	0.1	<2	<20	<0.01	5,310	0.3	1.0	25	26.9	14.9	<100.0	85	1	4.1
MJVD-4-96	5	0.19	640	0.09	12	<20	<0.01	16,250	0.3	1.5	45	31.9	21.3	<120.0	144	1	4.7
MJVD-4-97	1	0.09	670	0.11	6	<20	<0.01	3,010	0.2	1.0	30	22.9	10.9	<110.0	63	<1	3.6
MJVD-4-98	7	0.06	850	0.1	8	<20	<0.01	16,880	0.3	2	40	47.8	28.2	<120.0	193	<1	6.9
MJVD-4-99	28	0.04	400	0.53	2	<20	<0.01	5,180	0.2	1	20	24.4	12.1	<130.0	81	<1	3.4
MJVD-4-100	26	0.06	270	0.71	6	<20	<0.01	3,650	0.2	4	45	17.7	9.8	<70.0	62	<1	2.7

MJVD-4 (27/126)

Sample Name	La ppm	Pb ppm	Lu ppm	Nd ppm	Ni ppm	Nb ppm	Pr ppm	Rb ppm	Sm ppm	Ag ppm	Sr ppm	Ta ppm	Tb ppm	Tl ppm	Th ppm	Tm ppm	Sn ppm
MJVD-4-1	15,190	2,580	2.3	5,320	25	185	1,825	16.4	693	<1	4,540	<0.5	33.6	2.0	79	3.2	3
MJVD-4-2	21,600	3,310	3.0	7,270	20	237	2,460	20.2	912	<1	3,560	<0.5	47.7	2.5	92	4.5	<1
MJVD-4-3	30,300	4,500	4.6	10,510	5	313	3,400	5.8	1,370	<1	4,750	1.0	75.4	2.5	60	6.7	<1
MJVD-4-4	35,300	1,820	2.8	11,120	20	174	3,950	19.0	1,115	2	3,750	<0.5	55.3	2.0	94	4.0	1
MJVD-4-5	20,700	3,260	4.0	7,200	20	467	2,370	25.0	903	<1	4,470	2.0	48.4	1.5	46	5.6	3
MJVD-4-6	14,430	3,760	2.6	4,790	10	290	1,655	19.0	616	1	5,500	2.0	32.3	0.5	45	4.0	6
MJVD-4-7	34,800	1,800	2.0	10,200	5	205	3,690	7.4	953	1	6,460	<0.5	47.2	0.5	112	3.0	3
MJVD-4-8	7,500	1,840	1.6	2,560	<5	102	906	5.6	335	<1	10,920	<0.5	17.5	<0.5	20	2.4	2
MJVD-4-9	1,345	1,350	0.6	599	10	62	191	2.6	126	<1	12,130	<0.5	6.0	<0.5	8	0.9	5
MJVD-4-10	12,150	1,860	1.2	3,290	10	233	1,225	11.2	315	<1	8,800	<0.5	17.3	<0.5	18	1.6	1
MJVD-4-11	17,190	1,050	1.0	3,720	50	80	1,485	126.0	274	<1	2,880	<0.5	16.7	2.5	32	1.2	7
MJVD-4-12	5,100	720	0.7	1,455	25	33	529	95.0	148	<1	4,030	<0.5	8.4	1.5	17	0.9	2
MJVD-4-13	11,740	1,450	1.1	2,900	<5	47	1,105	7.4	250	<1	10,430	<0.5	16.8	<0.5	16	1.9	1
MJVD-4-14	8,010	290	0.9	2,640	5	10	955	2.4	292	<1	6,340	<0.5	14.7	<0.5	45	1.3	3
MJVD-4-15	6,800	450	0.8	2,400	10	46	852	6.8	287	<1	5,840	<0.5	13.5	<0.5	18	1.3	1
MJVD-4-16	3,990	910	0.8	1,205	5	80	442	7.4	133	<1	9,490	<0.5	9.1	<0.5	6	1.4	<1
MJVD-4-17	4,260	1,410	0.9	1,360	20	55	496	4.2	137	<1	12,790	<0.5	9.9	<0.5	6	1.3	4
MJVD-4-18	19,020	1,130	1.1	4,540	5	38	1,775	3.2	353	<1	8,260	<0.5	21.1	<0.5	29	1.6	<1
MJVD-4-19	6,430	870	0.9	1,915	5	33	709	3.2	186	<1	8,210	<0.5	11.3	<0.5	11	1.2	<1
MJVD-4-20	2,620	770	0.8	1,075	30	66	359	3.6	164	<1	7,350	<0.5	9.6	<0.5	113	1.1	1
MJVD-4-21	5,390	520	0.8	1,750	5	85	628	5.6	209	<1	7,680	<0.5	11.0	<0.5	15	1.2	<1
MJVD-4-22	4,230	580	0.9	1,455	5	93	516	6.6	213	<1	7,560	<0.5	10.4	<0.5	15	1.3	9
MJVD-4-23	5,240	1,610	0.9	1,695	10	82	613	7.0	190	<1	4,190	<0.5	10.3	0.5	13	1.2	<1
MJVD-4-24	3,230	1,330	0.6	1,115	<5	62	390	4.6	126	<1	3,870	<0.5	7.8	<0.5	6	1.1	<1
MJVD-4-25	7,740	1,830	0.9	2,460	<5	87	897	4.6	249	<1	3,600	<0.5	12.5	<0.5	14	1.3	<1
MJVD-4-26	9,830	830	0.7	2,730	<5	51	1,020	2.2	259	<1	7,770	<0.5	13.2	<0.5	13	1.1	<1
MJVD-4-27	1,055	1,140	0.5	445	5	70	146	3.0	80	<1	5,810	<0.5	4.5	<0.5	2	0.9	<1
MJVD-4-28	1,660	800	0.4	571	<5	39	202	2.6	83	<1	3,930	<0.5	4.5	<0.5	2	0.6	<1
MJVD-4-29	3,190	1,260	0.6	1,040	10	138	372	3.8	140	<1	5,460	<0.5	6.4	<0.5	5	0.8	<1
MJVD-4-30	4,250	1,550	0.9	1,440	10	158	514	7.2	195	1	6,450	<0.5	9.6	<0.5	8	1.1	<1
MJVD-4-31	1,680	630	0.7	629	<5	51	214	2.6	95	<1	8,540	<0.5	5.5	<0.5	2	0.9	<1
MJVD-4-32	1,185	470	0.4	429	5	37	149	1.8	54	<1	7,390	<0.5	3.7	<0.5	<1	0.6	<1
MJVD-4-33	880	370	0.4	355	5	73	118	2.4	60	<1	7,770	<0.5	3.3	<0.5	<1	0.5	<1
MJVD-4-34	1,840	340	0.4	625	5	38	224	3.6	78	<1	7,580	<0.5	4.2	<0.5	17	0.5	<1
MJVD-4-35	4,700	590	0.6	1,390	<5	69	520	3.4	149	<1	6,260	<0.5	7.8	<0.5	7	0.8	<1
MJVD-4-36	4,010	780	0.6	1,300	5	148	467	4.0	158	<1	5,530	<0.5	7.7	<0.5	6	0.8	<1
MJVD-4-37	3,960	670	0.6	1,215	5	59	445	2.8	138	<1	8,060	<0.5	7.6	<0.5	6	0.9	<1
MJVD-4-38	2,380	410	0.7	900	5	31	308	8.4	98	<1	7,490	<0.5	6.6	<0.5	3	0.9	<1
MJVD-4-39	959	260	0.4	393	5	80	130	12.4	69	<1	12,950	<0.5	4.1	<0.5	<1	0.7	<1
MJVD-4-40	660	420	0.5	330	10	45	103	7.2	53	<1	11,890	<0.5	3.8	<0.5	5	0.8	<1
MJVD-4-41	6,470	970	0.7	1,870	5	66	704	4.4	192	<1	8,260	<0.5	10.6	<0.5	14	0.9	<1
MJVD-4-42	14,640	770	0.8	3,800	5	78	1,435	3.0	332	<1	7,880	<0.5	17.8	<0.5	54	1.0	<1
MJVD-4-43	2,520	1,130	0.8	933	5	85	318	6.4	110	<1	9,810	<0.5	7.4	<0.5	18	1.0	<1
MJVD-4-44	3,980	720	0.8	1,305	<5	129	458	10.0	171	<1	7,640	<0.5	8.4	<0.5	17	0.9	<1
MJVD-4-45	2,020	370	0.4	640	5	53	232	3.2	80	<1	9,440	<0.5	4.7	<0.5	8	0.6	<1
MJVD-4-46	6,790	250	0.5	1,990	<5	94	747	3.4	230	<1	6,700	<0.5	9.1	<0.5	16	0.5	<1
MJVD-4-47	6,440	650	0.8	2,280	10	106	789	18.2	260	<1	9,810	<0.5	14.2	<0.5	211	1.0	<1
MJVD-4-48	3,690	960	0.6	1,335	<5	182	471	22.2	150	<1	10,570	<0.5	8.0	<0.5	19	0.9	<1
MJVD-4-49	4,030	1,190	0.8	1,480	<5	164	508	2.8	164	<1	7,550	<0.5	8.7	<0.5	16	1.0	<1
MJVD-4-50	12,780	770	0.8	3,360	5	91	1,270	4.4	296	<1	8,370	<0.5	16.6	<0.5	24	1.2	<1
MJVD-4-51	4,420	1,000	1.7	1,745	<5	466	590	8.0	240	<1	20,300	<0.5	16.1	<0.5	12	2.8	<1
MJVD-4-52	1,750	570	0.8	683	5	188	228	3.0	96	<1	8,040	<0.5	6.4	<0.5	4	1.1	<1
MJVD-4-53	18,400	1,410	1.1	5,150	25	185	1,890	17.0	455	<1	3,200	<0.5	25.0	1.0	36	1.6	<1
MJVD-4-54	9,810	670	0.8	2,820	20	140	1,035	6.2	292	<1	4,920	<0.5	14.2	1.0	18	1.2	<1
MJVD-4-55	1,975	700	0.6	771	10	201	262	6.2	114	<1	5,930	<0.5	5.9	1.0	5	0.8	<1
MJVD-4-56	2,140	800	0.6	841	5	119	282	16.6	113	<1	9,860	<0.5	6.3	0.5	5	0.9	<1
MJVD-4-57	2,730	770	0.6	934	15	137	327	16.0	120	<1	5,660	<0.5	6.5	1.0	8	0.8	<1

MJVD-4 (28/126)

Sample Name	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-4-58	1,880	960	0.6	784	20	129	257	17.4	102	<1	3,850	<0.5	6.2	1.0	7	0.8	<1
MJVD-4-59	544	360	0.3	234	<5	41	78	9.0	42	<1	3,980	<0.5	2.7	<0.5	1	0.5	<1
MJVD-4-60	3,240	430	0.5	1,060	5	74	373	14.0	116	<1	8,220	<0.5	6.9	<0.5	6	0.8	<1
MJVD-4-61	1,990	650	0.6	784	5	106	261	8.6	99	<1	4,840	<0.5	6.6	<0.5	6	0.9	<1
MJVD-4-62	2,660	690	0.7	948	10	159	326	7.4	131	<1	5,440	<0.5	7.1	<0.5	7	1.1	<1
MJVD-4-63	1,300	710	0.6	552	20	149	178	6.4	90	1	8,670	<0.5	5.5	<0.5	3	0.9	<1
MJVD-4-64	4,360	1,710	0.8	1,660	15	107	565	16.2	189	<1	5,970	<0.5	11.4	1.0	16	1.3	<1
MJVD-4-65	23,200	2,900	1.5	7,650	20	307	2,640	25.2	775	2	4,890	<0.5	38.4	3.0	49	2.4	<1
MJVD-4-66	7,670	2,900	1.5	5,620	30	183	1,600	30.4	774	1	5,590	<0.5	31.6	2.0	28	2.3	1
MJVD-4-67	2,790	910	0.8	1,130	10	157	378	17.0	148	<1	7,550	<0.5	8.7	<0.5	9	1.1	<1
MJVD-4-68	1,650	450	0.7	728	10	146	235	28.8	114	<1	8,080	<0.5	6.5	<0.5	8	1.1	<1
MJVD-4-69	971	990	0.6	432	5	127	138	15.6	75	<1	5,120	<0.5	4.3	<0.5	5	0.7	<1
MJVD-4-70	676	570	0.6	377	5	87	115	33.8	70	<1	10,220	<0.5	4.9	<0.5	1	0.8	<1
MJVD-4-71	6,550	2,200	1.0	2,310	15	227	808	83.2	290	1	5,420	<0.5	14.1	2.5	21	1.4	<1
MJVD-4-72	2,600	1,200	0.7	999	20	120	335	42.4	123	<1	5,870	<0.5	7.6	0.5	12	1.1	<1
MJVD-4-73	1,140	890	0.7	558	10	260	174	47.2	90	<1	10,490	<0.5	5.6	<0.5	3	1.0	<1
MJVD-4-74	1,925	1,090	0.8	783	20	384	258	46.0	124	1	9,150	<0.5	6.7	<0.5	18	1.2	<1
MJVD-4-75	553	270	0.3	296	5	59	91	26.4	48	<1	5,710	<0.5	3.6	<0.5	2	0.5	<1
MJVD-4-76	11,900	820	1.1	3,660	<5	135	1,315	17.6	334	<1	4,400	<0.5	20.2	<0.5	22	1.7	<1
MJVD-4-77	2,680	750	0.8	1,110	5	128	365	75.0	132	<1	9,410	<0.5	8.7	<0.5	8	1.1	<1
MJVD-4-78	1,500	560	0.5	641	5	129	208	61.6	112	<1	7,800	<0.5	5.8	<0.5	3	0.8	<1
MJVD-4-79	7,230	1,160	1.1	2,470	5	170	880	11.4	261	<1	6,380	<0.5	14.4	0.5	19	1.3	<1
MJVD-4-80	6,710	1,540	1.0	2,190	5	264	778	6.6	231	<1	5,540	<0.5	13.2	0.5	16	1.4	<1
MJVD-4-81	3,570	1,350	1.0	1,580	10	72	541	8.2	188	<1	3,080	1.0	10.4	0.5	11	1.4	<1
MJVD-4-82	3,080	1,330	0.8	1,375	10	61	473	6.2	178	<1	3,610	<0.5	8.2	1.5	19	1.2	<1
MJVD-4-83	3,470	730	0.8	1,280	10	91	477	5.6	130	<1	6,080	1.0	8.3	<0.5	10	1.1	<1
MJVD-4-84	8,440	1,430	1.0	2,950	15	124	1,100	3.8	279	<1	8,090	<0.5	15.6	<0.5	27	1.7	<1
MJVD-4-85	10,630	1,120	1.0	3,610	5	88	1,350	5.2	312	<1	9,870	<0.5	17.2	<0.5	26	1.5	<1
MJVD-4-86	13,100	630	0.8	3,980	20	70	1,535	5.4	312	<1	74,800	<0.5	16.6	<0.5	30	1.1	<1
MJVD-4-87	25,100	830	1.0	7,430	5	71	2,880	5.6	557	<1	58,100	<0.5	30.1	<0.5	138	1.7	<1
MJVD-4-88	10,070	1,270	0.7	2,910	5	111	1,145	3.0	238	<1	41,800	<0.5	13.1	<0.5	22	1.0	<1
MJVD-4-89	1,430	450	0.5	621	5	97	216	7.6	101	<1	21,500	<0.5	4.5	<0.5	4	0.8	<1
MJVD-4-90	642	610	0.6	366	10	244	117	6.2	55	<1	27,600	<0.5	4.2	<0.5	<1	0.9	<1
MJVD-4-91	2,870	600	0.7	1,180	<5	72	424	3.4	157	<1	32,500	<0.5	7.8	<0.5	6	0.9	1
MJVD-4-92	4,410	650	0.6	1,820	5	40	648	5.2	196	<1	39,800	<0.5	9.9	<0.5	11	1.0	<1
MJVD-4-93	4,200	1,010	0.7	1,405	15	257	537	3.8	140	<1	18,220	<0.5	8	<0.5	5	1.1	<1
MJVD-4-94	5,470	1,530	0.9	1,915	10	125	721	5.8	197	<1	13,330	<0.5	10.7	<0.5	11	1.2	<1
MJVD-4-95	3,600	730	0.7	1,325	5	60	481	14.6	165	<1	15,210	<0.5	8	<0.5	6	1.1	<1
MJVD-4-96	11,990	1,200	0.7	3,170	5	126	1,260	4.2	273	<1	8,310	<0.5	13.3	<0.5	17	1.2	<1
MJVD-4-97	1,900	610	0.6	807	10	94	280	5.6	117	<1	10,440	<0.5	6	<0.5	2	0.8	5
MJVD-4-98	11,370	1,050	1.2	3,730	5	81	1,390	6	341	<1	16,900	<0.5	18.2	<0.5	19	1.6	<1
MJVD-4-99	3,410	510	0.6	1,295	15	49	470	3	159	<1	39,500	<0.5	7.4	<0.5	6	0.9	<1
MJVD-4-100	2,670	540	0.5	977	15	36	327	4	114	<1	26,800	<0.5	5.9	<0.5	3	0.7	<1

MJVD-4 (29/126)

Sample Name	W ppm	U ppm	V ppm	Yb ppm	Y ppm	Zn ppm	Zr ppm
MJVD-4-1	44	74.5	150	18.9	390	690	59
MJVD-4-2	59	95.5	190	27.8	602	720	43
MJVD-4-3	89	127.5	110	41.2	933	500	47
MJVD-4-4	28	176.0	110	25.5	485	625	70
MJVD-4-5	39	209.0	150	31.7	621	1,245	104
MJVD-4-6	23	145.0	120	23.0	546	1,935	102
MJVD-4-7	25	159.0	70	18.2	461	895	33
MJVD-4-8	7	76.5	65	13.3	280	1,575	6
MJVD-4-9	3	30.0	25	5.9	102	895	2
MJVD-4-10	14	105.0	65	9.9	195	835	49
MJVD-4-11	35	75.5	145	7.2	157	1,410	160
MJVD-4-12	27	21.5	100	5.8	110	695	102
MJVD-4-13	6	38.5	55	10.2	211	730	33
MJVD-4-14	1	20.0	30	7.7	197	410	13
MJVD-4-15	3	39.0	45	7.0	204	515	16
MJVD-4-16	6	33.0	55	8.0	142	470	15
MJVD-4-17	191	23.5	90	8.6	147	550	7
MJVD-4-18	9	55.5	60	9.2	211	505	10
MJVD-4-19	5	25.5	40	8.0	152	555	10
MJVD-4-20	6	21.0	55	7.1	135	435	28
MJVD-4-21	6	36.0	55	6.6	138	385	25
MJVD-4-22	8	34.5	50	7.9	151	470	12
MJVD-4-23	64	36.0	65	7.8	129	530	8
MJVD-4-24	36	28.0	40	6.1	118	380	12
MJVD-4-25	46	52.0	30	7.1	129	490	12
MJVD-4-26	10	44.5	20	6.6	127	335	<0.5
MJVD-4-27	13	20.0	40	4.8	84	385	2
MJVD-4-28	17	15.5	30	4.4	74	225	<0.5
MJVD-4-29	11	43.5	30	4.4	83	300	<0.5
MJVD-4-30	18	47.5	100	7.2	130	670	5
MJVD-4-31	6	18.0	25	5.1	92	210	<0.5
MJVD-4-32	4	13.5	30	3.8	65	140	<0.5
MJVD-4-33	4	21.0	40	3.0	56	160	<0.5
MJVD-4-34	5	16.0	25	3.4	54	125	<0.5
MJVD-4-35	5	30.0	35	4.9	84	235	3
MJVD-4-36	5	51.5	45	5.3	89	425	9
MJVD-4-37	5	25.0	50	4.9	93	300	1
MJVD-4-38	2	16.5	25	5.2	103	155	<0.5
MJVD-4-39	3	26.0	10	4.0	73	85	<0.5
MJVD-4-40	2	16.0	15	4.8	78	175	<0.5
MJVD-4-41	3	29.0	25	5.7	106	330	1
MJVD-4-42	2	53.5	45	7.0	131	430	<0.5
MJVD-4-43	4	30.5	55	6.2	115	480	6
MJVD-4-44	5	46.0	55	6.4	108	505	1
MJVD-4-45	2	21.5	30	3.8	72	235	<0.5
MJVD-4-46	<1	39.0	35	3.9	72	250	<0.5
MJVD-4-47	5	44.5	45	6.8	125	445	4
MJVD-4-48	5	53.0	50	5.4	100	375	<0.5
MJVD-4-49	4	53.5	40	6.2	113	330	<0.5
MJVD-4-50	4	54.0	35	7.3	144	315	<0.5
MJVD-4-51	26	137.5	75	17.0	270	285	<0.5
MJVD-4-52	10	54.0	30	6.4	109	280	<0.5
MJVD-4-53	51	91.0	45	9.6	204	895	41
MJVD-4-54	19	51.5	50	7.4	140	410	6
MJVD-4-55	10	48.5	30	5.1	90	405	4
MJVD-4-56	11	34.0	35	5.1	98	355	<0.5
MJVD-4-57	16	36.5	25	5.3	96	555	9

MJVD-4 (30/126)

Sample Name	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-4-58	34	30.0	35	5.9	96	580	11
MJVD-4-59	5	10.5	25	3.2	50	185	<0.5
MJVD-4-60	5	31.0	25	4.6	88	175	<0.5
MJVD-4-61	10	32.5	40	5.2	96	290	5
MJVD-4-62	9	47.5	60	6.4	108	460	<0.5
MJVD-4-63	6	47.0	70	5.7	93	585	9
MJVD-4-64	27	39.0	60	8.0	148	575	22
MJVD-4-65	112	128.0	60	13.8	370	935	56
MJVD-4-66	118	84.0	80	15.0	278	1,095	54
MJVD-4-67	12	59.5	55	7.1	132	460	<0.5
MJVD-4-68	10	48.0	40	6.0	107	505	<0.5
MJVD-4-69	7	37.0	30	4.6	80	475	1
MJVD-4-70	7	26.0	25	5.5	94	230	<0.5
MJVD-4-71	69	72.0	45	8.2	159	1,030	44
MJVD-4-72	27	35.5	40	5.8	117	675	30
MJVD-4-73	10	82.5	30	5.8	102	275	<0.5
MJVD-4-74	15	110.0	25	6.5	108	460	40
MJVD-4-75	3	15.5	35	3.3	64	295	3
MJVD-4-76	9	76.5	45	10.3	233	510	<0.5
MJVD-4-77	7	49.5	45	7.1	133	335	<0.5
MJVD-4-78	6	40.5	40	4.8	86	315	<0.5
MJVD-4-79	8	68.5	35	8.2	161	725	1
MJVD-4-80	18	88.0	55	8.6	159	755	4
MJVD-4-81	14	37.5	40	7.4	172	435	6
MJVD-4-82	16	30.0	15	7.0	145	580	6
MJVD-4-83	5	40.0	25	5.9	130	380	<0.5
MJVD-4-84	9	68.5	60	10.1	205	560	227
MJVD-4-85	6	66.0	40	9.4	195	375	13
MJVD-4-86	4	79.5	45	6.4	143	380	<0.5
MJVD-4-87	8	116.0	25	9.2	225	505	4
MJVD-4-88	4	80.5	25	6.5	130	915	16
MJVD-4-89	2	50.5	25	4.0	74	545	<0.5
MJVD-4-90	7	92.5	30	4.5	87	290	6
MJVD-4-91	2	36.0	20	6.0	121	530	5
MJVD-4-92	4	38.5	15	6.2	137	485	132
MJVD-4-93	9	94.0	40	6.2	114	540	<0.5
MJVD-4-94	20	42.5	70	6.9	150	835	171
MJVD-4-95	9	23.0	20	5.6	141	420	21
MJVD-4-96	9	87.5	35	6.5	144	595	36
MJVD-4-97	6	36.5	45	5.5	101	360	4
MJVD-4-98	8	58.5	40.0	9.6	185.0	510	11
MJVD-4-99	2	38.5	15	5.1	107	415	<0.5
MJVD-4-100	4	28.5	40	4.2	88	250	6

MJVD-5 (31/126)

Sample Name	F %	Ba %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm
MJVD-5-1	0.9	35.60	0.22	1130	130	<5.0	<10	0.12	1.5	23	1.38	<100	<1	0.03	<0.01	>10,000
MJVD-5-2	2.2	22.00	0.29	2360	300	<5.0	<10	0.24	2.5	37	0.92	<100	<1	0.07	<0.01	2,310
MJVD-5-3	1.1	31.70	0.30	1330	70	<5.0	<10	0.11	1.0	22	2.06	<100	1	0.08	0.01	>10,000
MJVD-5-4	1.8	34.10	0.17	1780	310	<5.0	<10	0.16	2.5	19	0.63	<100	<1	0.05	<0.01	5,360
MJVD-5-5	1.2	25.20	0.29	1505	110	<5.0	<10	0.11	2.0	32	2.28	<100	1	0.06	<0.01	>10,000
MJVD-5-6	1.4	33.80	0.30	1520	180	<5.0	10	0.13	1.5	16	1.17	<100	<1	0.08	0.01	>10,000
MJVD-5-7	3.0	21.90	0.45	2250	220	<5.0	<10	0.15	0.5	21	1.05	<100	<1	0.16	0.02	4,460
MJVD-5-8	8.2	38.00	0.45	390	1,280	<5.0	<10	4.86	1.0	11	1.13	<100	<1	0.19	0.01	8,290
MJVD-5-9	1.4	38.10	0.30	1450	150	<5.0	10	0.19	1.0	20	1.05	<100	3	0.09	<0.01	>10,000
MJVD-5-10	0.5	44.40	0.22	472	<10	<5.0	<10	0.19	0.5	13	1.45	<100	2	0.07	<0.01	>10,000
MJVD-5-11	10.1	38.70	0.43	244	1,090	<5.0	<10	4.70	1.0	9	0.78	<100	1	0.18	0.01	7,680
MJVD-5-12	0.4	44.20	0.27	578	<10	<5.0	10	0.12	0.5	33	3.29	<100	1	0.08	0.04	>10,000
MJVD-5-13	6.1	37.80	0.51	524	670	<5.0	<10	3.38	2.5	14	1.04	<100	<1	0.19	0.02	>10,000
MJVD-5-14	4.7	37.20	0.39	590	660	<5.0	<10	2.76	1.5	13	1.12	<100	2	0.15	0.01	>10,000
MJVD-5-15	7.3	37.90	0.64	260	770	<5.0	<10	4.56	1.5	14	1.14	<100	1	0.22	0.03	8,220
MJVD-5-16	2.1	9.72	5.31	116	<10	5	<10	1.70	3.0	208	4.84	<100	1	0.42	0.43	4,090
MJVD-5-17	1.1	2.73	5.32	52	<10	5	<10	1.15	2.0	265	5.06	<100	<1	0.32	1.38	1,430
MJVD-5-18	1.8	1.29	3.99	48	<10	<5.0	<10	2.60	2.0	259	4.51	<100	<1	0.35	1.40	1,140
MJVD-5-19	6.0	19.00	2.47	306	20	<5.0	<10	5.17	6.5	114	2.11	<100	2	1.17	0.36	5,190
MJVD-5-20	8.0	12.25	0.37	812	1,090	<5.0	<10	12.80	3.0	7	0.51	<100	<1	0.17	0.04	3,470
MJVD-5-21	4.1	8.98	3.23	686	90	<5.0	<10	5.19	3.0	144	2.22	<100	<1	0.98	0.13	2,720
MJVD-5-22	5.1	10.80	0.37	502	710	5	<10	>15.00	1.5	10	0.76	<100	<1	0.16	0.06	2,740
MJVD-5-23	7.7	6.91	0.29	254	930	<5.0	<10	>15.00	2.0	4	0.43	<100	<1	0.14	0.06	3,600
MJVD-5-24	5.1	5.91	0.25	228	700	<5.0	<10	>15.00	2.5	4	0.42	<100	<1	0.12	0.06	4,540
MJVD-5-25	6.1	17.00	0.24	964	1,050	5	<10	9.94	2.5	7	0.75	<100	<1	0.12	0.02	1,635
MJVD-5-26	8.3	6.44	0.28	248	960	<5.0	<10	>15.00	2.0	3	0.41	<100	<1	0.13	0.06	3,610
MJVD-5-27	3.1	18.50	0.11	56	780	<5.0	<10	>15.00	1.0	1	0.19	<100	<1	0.06	0.04	3,360
MJVD-5-28	4.6	21.90	0.17	64	1,000	<5.0	<10	>15.00	0.5	2	0.19	<100	<1	0.10	0.04	2,710
MJVD-5-29	5.0	13.25	0.11	80	940	<5.0	<10	>15.00	1.5	1	0.23	<100	<1	0.07	0.05	2,990
MJVD-5-30	4.0	8.66	0.11	36	920	<5.0	<10	>15.00	1.0	2	0.54	<100	<1	0.08	0.06	3,360
MJVD-5-31	5.2	15.00	0.15	38	1,090	<5.0	<10	>15.00	0.5	<1	0.30	<100	<1	0.09	0.05	2,980
MJVD-5-32	5.2	18.60	0.13	174	1,010	<5.0	<10	>15.00	1.5	<1	0.20	<100	<1	0.08	0.03	2,790
MJVD-5-33	3.1	10.25	0.13	62	660	<5.0	<10	>15.00	1.5	<1	0.23	<100	1	0.07	0.07	4,110
MJVD-5-34	4.7	27.90	0.13	52	1,100	<5.0	<10	13.60	0.5	1	0.49	<100	<1	0.08	0.03	2,500
MJVD-5-35	4.2	11.20	0.10	34	860	<5.0	<10	>15.00	1.5	<1	0.40	<100	<1	0.07	0.05	3,990
MJVD-5-36	3.3	7.48	0.08	124	710	<5.0	<10	>15.00	2.5	<1	0.24	<100	<1	0.06	0.05	3,170
MJVD-5-37	4.1	13.00	0.10	118	850	<5.0	<10	>15.00	2.0	1	0.17	<100	<1	0.07	0.04	2,840
MJVD-5-38	2.2	6.20	0.15	110	550	<5.0	<10	>15.00	2.0	4	0.19	<100	<1	0.09	0.06	3,350
MJVD-5-39	0.9	8.96	0.05	30	240	<5.0	<10	>15.00	0.5	<1	0.24	<100	<1	0.03	0.08	3,630
MJVD-5-40	1.3	9.73	0.06	22	330	<5.0	<10	>15.00	0.5	1	0.23	<100	<1	0.04	0.07	2,890
MJVD-5-41	1.5	36.60	0.06	32	440	<5.0	<10	9.94	0.5	1	0.12	<100	<1	0.03	0.03	1,585
MJVD-5-42	1.0	33.00	0.04	18	280	<5.0	<10	13.40	0.5	1	0.11	<100	<1	0.02	0.03	1,965
MJVD-5-43	1.8	17.20	1.35	174	<10	<5.0	<10	10.90	1.5	76	1.74	<100	<1	0.47	0.23	1,605
MJVD-5-44	0.3	0.48	1.20	48	<10	<5.0	<10	7.19	<0.5	246	3.19	<100	<1	0.40	1.49	1,090
MJVD-5-45	0.2	0.46	0.95	42	<10	5	<10	7.24	<0.5	170	3.30	<100	<1	0.38	0.89	685
MJVD-5-46	0.3	0.33	1.17	26	<10	<5.0	<10	7.19	<0.5	195	3.38	<100	<1	0.47	1.14	735
MJVD-5-47	3.4	6.23	2.32	128	30	<5.0	<10	13.25	0.5	103	1.59	<100	<1	1.00	0.24	1,475
MJVD-5-48	2.9	7.92	0.10	94	600	<5.0	<10	>15.00	2.5	3	0.30	<100	<1	0.07	0.06	3,450
MJVD-5-49	3.9	9.52	0.13	114	750	<5.0	<10	>15.00	1.5	2	0.33	<100	<1	0.09	0.06	3,880
MJVD-5-50	5.8	8.12	0.14	132	840	<5.0	<10	>15.00	1.5	3	0.32	<100	<1	0.08	0.07	2,930
MJVD-5-51	3.4	14.00	0.14	142	670	<5.0	<10	>15.00	1.5	1	0.21	<100	1	0.10	0.05	2,970
MJVD-5-52	4.5	16.20	0.46	240	300	<5.0	<10	>15.00	1.5	15	0.62	<100	<1	0.21	0.09	4,340
MJVD-5-53	4.8	30.70	0.41	172	590	<5.0	<10	11.50	0.5	26	0.84	<100	1	0.23	0.04	4,480
MJVD-5-54	2.3	10.20	0.32	120	30	<5.0	<10	>15.00	1.5	1	0.17	<100	<1	0.38	0.05	3,430
MJVD-5-55	3.3	11.95	0.21	158	500	<5.0	<10	>15.00	1.5	6	0.29	<100	<1	0.12	0.05	3,140
MJVD-5-56	7.4	8.75	0.13	246	1,050	<5.0	<10	>15.00	1.5	1	0.13	<100	<1	0.08	0.04	3,020
MJVD-5-57	10.7	12.05	0.15	112	1,370	<5.0	<10	>15.00	0.5	<1	0.12	<100	<1	0.10	0.04	2,530

MJVD-5 (32/126)

Sample Name	F	Ba	Al	As	B	Be	Bi	Ca	Cd	Cr	Fe	Ga	Hg	K	Mg	Mn
	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%	ppm
MJVD-5-58	5.9	13.80	0.12	94	770	<5.0	<10	>15.00	0.5	<1	0.09	<100	<1	0.10	0.04	3,020
MJVD-5-59	9.8	14.50	0.15	180	1,150	<5.0	<10	>15.00	0.5	1	0.17	<100	<1	0.10	0.04	2,490
MJVD-5-60	5.1	11.35	0.12	70	650	<5.0	<10	>15.00	1.0	<1	0.16	<100	<1	0.09	0.05	2,650
MJVD-5-61	4.4	14.65	0.11	62	840	<5.0	<10	>15.00	0.5	1	0.34	<100	<1	0.07	0.05	2,760
MJVD-5-62	7.8	20.70	0.14	286	1,140	<5.0	<10	14.55	1.0	<1	0.10	<100	<1	0.09	0.03	2,190
MJVD-5-63	3.9	11.25	0.13	412	800	<5.0	<10	>15.00	1.0	3	0.51	<100	<1	0.07	0.05	2,980
MJVD-5-64	4.3	11.50	0.13	182	920	<5.0	<10	>15.00	1.0	1	0.47	<100	<1	0.08	0.06	2,980
MJVD-5-65	4.9	7.87	0.13	214	990	<5.0	<10	>15.00	1.0	<1	0.31	<100	<1	0.08	0.05	2,890
MJVD-5-66	4.0	9.90	0.14	258	840	<5.0	<10	>15.00	1.5	<1	0.31	<100	<1	0.08	0.05	3,290
MJVD-5-67	8.1	16.25	0.15	270	1,310	<5.0	<10	>15.00	1.0	1	0.22	<100	<1	0.10	0.04	1,960
MJVD-5-68	7.8	16.85	0.18	128	1,250	<5.0	<10	>15.00	1.5	2	0.25	<100	<1	0.11	0.04	2,250
MJVD-5-69	5.1	14.90	0.23	100	730	<5.0	<10	>15.00	1.0	2	0.31	<100	<1	0.24	0.05	2,750
MJVD-5-70	1.0	4.26	0.04	44	40	<5.0	<10	>15.00	1.5	1	0.59	<100	<1	0.14	0.18	4,440
MJVD-5-71	7.8	7.35	0.14	162	1,150	<5.0	<10	>15.00	1.5	2	0.63	<100	<1	0.11	0.08	3,680
MJVD-5-72	7.5	7.74	0.15	258	1,050	<5.0	<10	>15.00	1.5	<1	0.17	<100	<1	0.10	0.06	3,260
MJVD-5-73	8.9	10.60	0.17	240	1,300	<5.0	<10	>15.00	0.5	1	0.24	<100	<1	0.11	0.05	3,070
MJVD-5-74	11.2	16.25	0.28	168	1,260	<5.0	<10	>15.00	0.5	<1	0.17	<100	<1	0.14	0.05	2,240
MJVD-5-75	5.8	13.05	1.94	102	250	<5.0	<10	>15.00	1.0	3	0.77	<100	<1	0.11	0.05	2,140
MJVD-5-76	5.0	5.55	0.15	136	920	<5.0	<10	>15.00	2.0	<1	0.37	<100	<1	0.08	0.06	3,640
MJVD-5-77	3.3	7.49	0.15	76	730	<5.0	<10	>15.00	1.5	1	0.37	<100	<1	0.08	0.06	3,350
MJVD-5-78	5.2	10.40	0.33	126	780	<5.0	<10	>15.00	1.0	<1	0.43	<100	<1	0.11	0.06	2,900
MJVD-5-79	4.6	10.05	0.13	182	1,000	<5.0	<10	>15.00	1.0	<1	0.28	<100	<1	0.08	0.06	2,750
MJVD-5-80	3.8	7.60	0.13	190	780	<5.0	<10	>15.00	2.0	11	0.49	<100	<1	0.07	0.06	2,830
MJVD-5-81	3.3	9.08	0.23	188	610	<5.0	<10	>15.00	1.5	<1	0.34	<100	<1	0.09	0.05	2,890
MJVD-5-82	3.3	7.31	0.15	152	620	<5.0	<10	>15.00	1.0	<1	0.27	<100	<1	0.12	0.08	2,940
MJVD-5-83	5.5	19.10	0.15	568	1,200	<5.0	<10	13.80	0.5	<1	0.11	<100	<1	0.11	0.03	1,650
MJVD-5-84	5.1	23.20	0.16	406	1,090	<5.0	<10	13.35	0.5	<1	0.12	<100	<1	0.12	0.03	1,805
MJVD-5-85	2.5	4.92	0.08	116	590	<5.0	<10	>15.00	0.5	3	0.14	<100	<1	0.05	0.06	3,020
MJVD-5-86	6.1	6.09	0.12	276	950	<5.0	<10	>15.00	1.0	<1	0.20	<100	<1	0.08	0.05	2,920
MJVD-5-87	5.8	8.06	0.13	222	1,010	<5.0	<10	>15.00	2.0	1	0.23	<100	<1	0.08	0.05	2,890
MJVD-5-88	3.8	8.17	0.10	222	720	<5.0	<10	>15.00	1.0	<1	0.23	<100	1	0.06	0.05	3,110
MJVD-5-89	1.6	3.50	0.06	32	400	<5.0	<10	>15.00	1.5	<1	0.49	<100	<1	0.04	0.07	3,280
MJVD-5-90	2.0	4.03	0.08	52	480	<5.0	<10	>15.00	0.5	<1	0.19	<100	<1	0.05	0.08	3,250
MJVD-5-91	4.5	5.44	0.12	208	810	<5.0	<10	>15.00	0.5	<1	0.13	<100	<1	0.07	0.06	3,020
MJVD-5-92	5.2	7.39	0.12	24	950	<5.0	<10	>15.00	1.0	<1	0.30	<100	<1	0.08	0.05	3,100
MJVD-5-93	3.3	10.05	0.17	96	640	<5.0	<10	>15.00	0.5	<1	0.18	<100	<1	0.08	0.07	3,510
MJVD-5-94	2.8	7.89	0.67	326	180	<5.0	<10	>15.00	1.0	2	0.38	<100	<1	0.30	0.05	2,890
MJVD-5-95	5.0	12.65	0.34	116	700	<5.0	<10	>15.00	0.5	3	0.35	<100	<1	0.26	0.04	2,620
MJVD-5-96	1.3	4.31	0.18	86	100	<5.0	<10	>15.00	2.0	<1	0.15	<100	<1	0.17	0.05	3,480
MJVD-5-97	2.1	9.54	0.34	142	230	<5.0	<10	>15.00	2.0	1	0.26	<100	1	0.12	0.06	3,500
MJVD-5-98	1.86	10.5	0	536	290	<5.0	<10	>15.00	2	6	0.41	<100	<1	0	0.06	5,070
MJVD-5-99	5.09	12.05	0	368	1,040	<5.0	<10	>15.00	1	1	0.23	<100	<1	0	0.04	3,180
MJVD-5-100	5.44	10.2	0	634	980	<5.0	<10	>15.00	1.5	<1	0.18	<100	<1	0	0.04	2,300

MJVD-5 (33/126)

Sample Name	Mo ppm	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm
MJVD-5-1	17	0.03	2,450	0.04	32	<20	0.01	45,000	0.3	3.0	50	175.0	110.0	<350	749	1
MJVD-5-2	17	0.06	600	0.05	18	<20	0.01	123,900	0.3	2.0	25	299.0	215.0	500	1,730	1
MJVD-5-3	17	0.02	1,990	0.03	52	<20	0.02	52,800	0.4	6.0	85	171.5	109.0	<350	740	2
MJVD-5-4	16	0.06	420	0.05	22	<20	0.01	96,000	0.2	2.0	30	214.0	153.5	350	1,185	5
MJVD-5-5	19	0.03	2,010	0.03	62	<20	0.02	62,200	0.5	7.5	80	238.0	141.5	200	940	6
MJVD-5-6	18	0.04	1,150	0.03	36	<20	0.01	79,000	0.4	4.0	60	234.0	152.5	300	1,010	3
MJVD-5-7	14	0.05	920	0.06	30	<20	0.02	131,100	0.9	2.5	35	281.0	207.0	400	1,415	3
MJVD-5-8	6	0.19	2,910	0.05	20	<20	<0.01	20,000	0.6	2.5	50	112.0	58.3	<400	381	3
MJVD-5-9	14	0.04	3,230	0.03	48	<20	0.01	62,800	0.5	3.5	105	243.0	139.0	<400	928	1
MJVD-5-10	11	0.01	3,500	0.04	30	<20	<0.01	18,850	0.7	4.0	115	123.5	62.2	<500	407	3
MJVD-5-11	9	0.16	3,370	0.06	24	<20	<0.01	11,320	0.7	3.5	50	88.1	45.1	<400	284	3
MJVD-5-12	12	0.01	2,810	0.04	58	<20	0.01	22,200	0.8	7.5	100	93.7	51.4	<500	336	1
MJVD-5-13	9	0.11	2,560	0.05	16	<20	<0.01	33,500	0.9	2.0	55	158.0	88.2	<400	555	3
MJVD-5-14	16	0.11	1,640	0.04	24	<20	0.01	40,800	0.6	2.5	95	180.0	110.0	<400	685	3
MJVD-5-15	9	0.12	1,270	0.05	14	<20	<0.01	13,660	0.9	2.5	60	79.9	42.0	<400	266	2
MJVD-5-16	9	<0.01	3,520	0.02	8	<20	0.06	3,090	10.7	31.5	75	27.9	17.9	<100.0	72	6
MJVD-5-17	<1	0.01	3,350	0.02	2	<20	0.19	979	9.6	35.5	75	11.9	10.1	<20.0	25	6
MJVD-5-18	1	0.01	2,880	0.04	<2	<20	0.2	741	5.7	32.0	60	8.5	6.1	<10.0	18	4
MJVD-5-19	7	0.17	1,370	0.06	8	<20	0.06	13,160	2.5	9.5	30	56.3	29.0	<200	226	3
MJVD-5-20	5	0.19	730	0.07	2	<20	<0.01	48,600	0.5	2.0	25	96.5	67.6	100	542	2
MJVD-5-21	8	0.03	1,470	0.07	6	<20	0.02	33,300	3.5	14.0	40	54.2	42.0	100	355	3
MJVD-5-22	4	0.13	460	0.07	2	<20	<0.01	27,800	0.6	3.5	20	64.3	42.9	100	356	1
MJVD-5-23	4	0.16	550	0.08	2	<20	<0.01	16,060	0.5	2.5	15	55.3	33.3	60	245	2
MJVD-5-24	3	0.13	650	0.07	6	<20	<0.01	14,130	0.4	1.0	15	57.4	34.9	60	226	3
MJVD-5-25	6	0.18	590	0.06	10	<20	<0.01	59,700	0.3	2.0	35	101.5	82.9	200	686	5
MJVD-5-26	3	0.17	520	0.07	<2	<20	<0.01	16,160	0.3	2.0	30	60.8	35.0	60	269	2
MJVD-5-27	<1	0.13	780	0.08	<2	<20	<0.01	3,260	0	0.5	20	31.5	16.3	<200	81	1
MJVD-5-28	<1	0.16	1,220	0.08	2	<20	<0.01	3,530	0.2	1.0	20	30.8	16.2	<250	85	1
MJVD-5-29	<1	0.16	2,400	0.11	8	<20	<0.01	5,000	0.1	0.5	30	40.7	21.9	<150.0	118	2
MJVD-5-30	<1	0.16	1,500	0.12	6	<20	<0.01	2,460	0.2	0.5	15	35.9	17.1	<100.0	86	2
MJVD-5-31	<1	0.18	1,330	0.09	8	<20	<0.01	2,800	0.2	1.0	15	31.7	17.2	<150.0	86	2
MJVD-5-32	<1	0.17	1,680	0.08	2	<20	<0.01	8,420	0.1	1.0	10	34.4	19.4	<200	118	1
MJVD-5-33	<1	0.12	900	0.09	4	<20	<0.01	3,700	0.2	0.5	10	36.5	20.0	<100.0	98	<1
MJVD-5-34	1	0.17	470	0.08	<2	<20	<0.01	2,950	0.2	1.0	<5	25.7	14.3	<300	75	2
MJVD-5-35	<1	0.15	1,190	0.11	2	<20	<0.01	2,770	0.2	1.5	10	45.2	21.7	<125.0	98	1
MJVD-5-36	<1	0.13	1,670	0.1	8	<20	<0.01	6,740	0.2	1.0	15	39.8	22.2	<80.0	116	1
MJVD-5-37	<1	0.14	950	0.09	6	<20	<0.01	6,050	0.2	0.5	5	35.6	19.6	<150.0	112	<1
MJVD-5-38	<1	0.11	2,470	0.08	10	<20	<0.01	5,960	0.3	1.5	30	36.4	20.4	<60.0	115	<1
MJVD-5-39	<1	0.06	600	0.09	2	<20	<0.01	2,060	0.1	0.5	5	29.7	15.5	<100.0	66	<1
MJVD-5-40	<1	0.07	650	0.07	2	<20	<0.01	2,040	0.1	0.5	15	24.4	12.6	<100.0	59	<1
MJVD-5-41	<1	0.08	490	0.06	2	<20	<0.01	1,680	0.2	<0.5	10	13.5	7.7	<400	39	<1
MJVD-5-42	1	0.05	470	0.06	<2	<20	<0.01	1,245	0.1	<0.5	10	15.8	7.8	<350	39	<1
MJVD-5-43	2	0.01	1,380	0.05	8	<20	0.02	7,150	2.8	10.0	60	27.2	17.2	<200	110	2
MJVD-5-44	<1	0.01	2,330	0.04	<2	<20	0.12	293	13.5	28.5	40	4.2	2.5	3.3	9	3
MJVD-5-45	<1	0.01	2,390	0.04	2	<20	0.08	194	13.2	25.0	60	3.8	2.7	2.4	7	3
MJVD-5-46	<1	0.01	2,360	0.03	2	<20	0.1	156	15	24.0	55	3.8	2.5	2.1	7	3
MJVD-5-47	2	0.01	1,510	0.07	6	<20	0.01	4,900	4.7	11.5	55	19.6	11.8	<60.0	71	2
MJVD-5-48	<1	0.11	1,250	0.09	6	<20	<0.01	5,630	0.2	1.5	30	37.7	20.5	<90.0	115	<1
MJVD-5-49	<1	0.13	1,100	0.1	6	<20	<0.01	6,670	0.1	1.0	30	41.0	23.9	<100.0	133	<1
MJVD-5-50	<1	0.15	620	0.09	4	<20	<0.01	7,260	0.1	1.5	40	30.8	19.5	<90.0	114	<1
MJVD-5-51	<1	0.12	1,410	0.1	6	<20	<0.01	9,100	0.3	4.5	30	40.7	23.0	<150.0	148	<1
MJVD-5-52	<1	0.08	2,380	0.07	14	<20	<0.01	12,770	1	3.5	60	52.4	29.8	<150.0	196	1
MJVD-5-53	5	0.10	1,310	0.06	12	<20	<0.01	9,100	0.5	2.5	55	47.5	28.5	<350	157	1
MJVD-5-54	<1	0.03	1,920	0.1	2	<20	<0.01	6,980	0.2	0.5	40	43.7	22.5	<110.0	140	<1
MJVD-5-55	<1	0.10	2,000	0.09	8	<20	<0.01	9,140	0.3	2.5	30	41.1	23.7	<130.0	146	<1
MJVD-5-56	<1	0.17	410	0.08	2	<20	<0.01	13,880	0.1	<0.5	25	41.7	27.2	<100.0	174	1
MJVD-5-57	<1	0.22	690	0.1	<2	<20	<0.01	6,090	0.9	1.5	25	33.8	19.4	<150.0	107	1

MJVD-5 (34/126)

Sample Name	Mo ppm	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm
MJVD-5-58	<1	0.14	890	0.12	<2	<20	<0.01	5,880	0.2	<0.5	15	37.4	20.0	<150.0	116	<1
MJVD-5-59	<1	0.19	920	0.08	2	<20	<0.01	8,490	0	<0.5	15	29.0	18.4	<150.0	123	1
MJVD-5-60	<1	0.12	1,110	0.1	2	<20	<0.01	4,330	0.1	0.5	15	31.2	17.3	<120.0	94	1
MJVD-5-61	<1	0.15	1,580	0.11	4	<20	<0.01	3,890	0.2	1.5	20	32.5	17.7	<150.0	90	1
MJVD-5-62	<1	0.18	390	0.08	<2	<20	<0.01	15,970	0.1	0.5	25	38.4	25.2	<250	178	1
MJVD-5-63	<1	0.15	2,830	0.08	6	<20	<0.01	23,200	0.1	1.0	30	56.8	37.9	<130.0	270	2
MJVD-5-64	1	0.16	1,780	0.11	2	<20	<0.01	10,050	0.5	1.5	20	36.2	22.1	<130.0	144	1
MJVD-5-65	1	0.18	2,950	0.1	2	<20	<0.01	14,260	0.1	0.5	25	41.6	27.5	<100.0	189	1
MJVD-5-66	<1	0.14	810	0.09	2	<20	<0.01	14,070	0.1	0.5	20	50.9	29.0	<100.0	209	1
MJVD-5-67	2	0.21	1,470	0.07	4	<20	<0.01	18,810	0	1.5	20	48.6	31.5	<200	246	1
MJVD-5-68	<1	0.19	870	0.08	4	<20	<0.01	6,700	0.1	0.5	15	33.7	18.8	<200	116	1
MJVD-5-69	<1	0.13	890	0.11	<2	<20	<0.01	5,900	0.1	0.5	30	33.0	19.6	<150.0	113	1
MJVD-5-70	3	0.04	1,460	0.12	6	<20	<0.01	2,930	0.5	1.0	30	37.9	17.7	<40.0	87	<1
MJVD-5-71	5	0.19	780	0.1	2	<20	<0.01	9,060	0.2	1.0	25	37.5	22.5	<80.0	145	1
MJVD-5-72	<1	0.17	290	0.08	<2	<20	<0.01	13,470	0.2	0.5	20	43.3	27.6	<90.0	187	1
MJVD-5-73	1	0.21	370	0.08	2	<20	<0.01	12,250	0.1	1.0	20	38.7	24.6	<120.0	162	1
MJVD-5-74	3	0.19	180	0.09	2	<20	<0.01	9,030	0.3	2.0	15	31.8	20.3	<190.0	128	2
MJVD-5-75	5	0.05	480	0.09	8	<20	<0.01	4,860	0.3	3.5	50	30.4	16.6	<150.0	98	1
MJVD-5-76	7	0.16	1,800	0.12	6	<20	<0.01	6,770	0.1	2.5	35	37.2	21.0	<60.0	129	1
MJVD-5-77	20	0.13	1,180	0.13	6	<20	<0.01	4,440	0.2	1.5	25	32.4	17.4	<80.0	102	1
MJVD-5-78	7	0.13	630	0.11	8	<20	<0.01	6,610	0.2	1.0	15	38.9	20.8	<120.0	131	2
MJVD-5-79	1	0.17	1,050	0.18	6	<20	<0.01	9,900	0.2	1.0	5	31.6	20.8	<110.0	136	1
MJVD-5-80	<1	0.13	590	0.1	8	<20	<0.01	10,930	0.1	1.5	20	38.3	22.1	<80.0	155	1
MJVD-5-81	<1	0.11	530	0.1	6	<20	<0.01	11,760	0.3	2.0	20	44.0	26.0	<100.0	171	<1
MJVD-5-82	4	0.11	470	0.14	10	<20	<0.01	8,570	0.2	1.0	10	36.6	20.8	<80.0	132	<1
MJVD-5-83	5	0.19	190	0.09	<2	<20	<0.01	28,200	0.2	0.5	5	38.7	31.1	<220	283	1
MJVD-5-84	3	0.17	170	0.08	<2	<20	<0.01	21,800	0.2	0.5	<5	36.4	29.2	<280	239	<1
MJVD-5-85	<1	0.10	270	0.09	2	<20	<0.01	6,550	0	1.0	5	28.5	17.2	<50.0	109	<1
MJVD-5-86	<1	0.16	450	0.08	4	<20	<0.01	15,970	0.1	1.0	10	37.1	26.9	60	188	<1
MJVD-5-87	<1	0.16	440	0.09	6	<20	<0.01	13,600	0	1.5	10	34.9	24.6	<100.0	167	1
MJVD-5-88	1	0.13	260	0.08	6	<20	<0.01	13,160	0.2	0.5	5	37.9	25.0	<90.0	176	<1
MJVD-5-89	10	0.08	720	0.14	8	<20	<0.01	2,270	0.1	1.0	15	21.1	10.9	<40.0	57	<1
MJVD-5-90	27	0.10	510	0.18	6	<20	<0.01	3,780	0.2	0.5	<5	26.3	13.7	<40.0	77	1
MJVD-5-91	4	0.15	440	0.15	2	<20	<0.01	12,590	0.1	<0.5	<5	32.5	22.1	<60.0	148	<1
MJVD-5-92	<1	0.16	1,080	0.13	4	<20	<0.01	1,855	0.3	0.5	5	32.9	17.0	<90.0	69	1
MJVD-5-93	<1	0.12	1,060	0.14	2	<20	<0.01	6,220	0.3	0.5	20	41.4	23.3	<120.0	129	<1
MJVD-5-94	1	0.04	580	0.09	2	<20	<0.01	16,710	0.3	1.0	5	44.9	29.6	<100.0	209	1
MJVD-5-95	<1	0.12	600	0.1	6	<20	<0.01	6,000	0.2	0.5	10	35.5	20.0	<150.0	113	2
MJVD-5-96	<1	0.04	450	0.09	6	<20	<0.01	5,310	0.2	0.5	10	42.4	22.8	<50.0	123	1
MJVD-5-97	<1	0.05	600	0.08	6	<20	<0.01	9,190	0.2	1.0	10	44.4	24.1	<120.0	152	1
MJVD-5-98	6	0.06	580	0.06	18	<20	<0.01	29,600	0.6	3	15	68.9	48.3	120	364	<1
MJVD-5-99	2	0.17	630	0.06	8	<20	<0.01	19,540	0.2	1	5	40.5	29.1	<150.0	222	1
MJVD-5-100	3	0.17	400	0.07	2	<20	<0.01	36,500	0.2	1	5	48	43.5	120	358	1

MJVD-5 (35/126)

Sample Name	Ho	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-5-1	28.1	37,000	2,920	4.0	13,690	5	141	4,380	4.0	1,365	<1	3,600	<0.5	67.2	3.0	157
MJVD-5-2	43.8	114,800	1,370	5.7	35,600	5	38	12,850	3.8	3,010	<1	2,680	<0.5	150.5	0.5	365
MJVD-5-3	27.5	46,600	4,200	4.1	13,390	<5	319	4,580	6.4	1,225	1	3,170	1.0	69.0	5.0	133
MJVD-5-4	33.0	78,200	3,040	4.7	24,600	5	24	8,940	3.6	2,090	1	3,590	<0.5	105.0	1.5	242
MJVD-5-5	37.6	53,000	4,680	5.6	15,850	5	196	5,250	6.0	1,495	<1	3,200	<0.5	86.9	5.0	146
MJVD-5-6	37.2	59,400	5,000	5.5	19,070	5	78	6,810	5.4	1,760	1	3,590	<0.5	93.6	4.0	180
MJVD-5-7	45.2	112,300	3,780	6.2	29,700	<5	113	11,310	12.2	2,310	1	2,410	<0.5	131.5	1.5	281
MJVD-5-8	18.5	15,090	2,040	2.7	5,330	5	72	1,695	10.2	700	<1	5,670	1.0	35.9	<0.5	63
MJVD-5-9	39.1	54,300	5,450	6.3	14,920	5	223	4,930	6.4	1,495	1	4,260	<0.5	86.8	4.0	167
MJVD-5-10	19.8	14,990	3,310	3.1	5,530	5	173	1,765	8.8	740	1	5,170	1.0	38.8	2.5	80
MJVD-5-11	14.3	9,640	2,770	2.3	3,630	5	122	1,115	9.4	530	<1	5,660	1.0	26.6	0.5	38
MJVD-5-12	14.9	17,800	4,100	2.3	5,430	<5	424	1,860	15.4	640	<1	4,210	2.0	32.6	3.0	51
MJVD-5-13	26.5	25,200	3,160	3.5	8,470	<5	107	2,760	11.2	972	<1	4,600	<0.5	53.6	1.5	121
MJVD-5-14	29.4	29,100	3,030	4.9	10,960	5	357	3,470	7.4	1,225	1	4,220	1.0	63.0	2.5	158
MJVD-5-15	13.4	9,960	1,130	2.1	3,680	5	135	1,180	12.6	524	1	5,520	<0.5	25.1	1.0	47
MJVD-5-16	5.0	2,250	720	1.6	943	75	92	295	123.0	136	<1	1,680	<0.5	7.4	3.0	32
MJVD-5-17	2.6	758	210	1.0	305	70	24	96	176.5	42	<1	1,290	<0.5	2.6	3.0	22
MJVD-5-18	1.9	565	370	0.6	227	70	14	71	217.0	29	1	1,480	<0.5	1.8	2.5	18
MJVD-5-19	8.3	9,540	1,220	1.1	3,520	30	84	1,130	92.4	428	<1	3,090	<0.5	20.8	2.5	51
MJVD-5-20	14.6	38,500	1,620	2.1	11,110	15	166	3,790	6.2	966	2	5,180	1.0	49.4	<0.5	107
MJVD-5-21	7.7	25,700	790	1.1	7,720	25	66	2,640	70.0	647	1	2,680	<0.5	31.0	1.0	99
MJVD-5-22	9.3	21,400	1,210	1.3	6,760	15	118	2,260	7.0	634	3	4,860	<0.5	30.7	<0.5	72
MJVD-5-23	8.9	11,630	1,270	1.3	4,230	10	140	1,365	5.6	428	1	5,810	<0.5	21.6	<0.5	39
MJVD-5-24	9.8	10,410	1,230	1.7	3,680	10	175	1,195	4.8	390	<1	6,330	<0.5	21.1	<0.5	34
MJVD-5-25	14.8	45,200	1,070	2.3	14,720	5	94	4,810	4.2	1,300	1	4,570	<0.5	58.8	<0.5	119
MJVD-5-26	9.1	11,640	2,310	1.5	4,430	15	129	1,400	4.2	471	<1	5,950	<0.5	24.0	<0.5	159
MJVD-5-27	5.2	2,370	510	1.0	934	5	36	301	0.6	170	<1	6,170	<0.5	8.5	<0.5	8
MJVD-5-28	5.3	2,720	730	0.9	991	20	78	319	3.4	189	<1	12,700	<0.5	8.7	<0.5	15
MJVD-5-29	6.7	3,690	980	1.0	1,425	15	123	459	1.2	207	1	25,000	1.0	11.7	<0.5	60
MJVD-5-30	6.3	1,715	830	1.0	824	5	131	243	1.2	144	<1	16,230	<0.5	9.2	<0.5	10
MJVD-5-31	5.4	1,900	650	1.0	889	10	96	275	1.6	165	<1	9,930	<0.5	8.8	<0.5	6
MJVD-5-32	5.5	6,290	660	1.0	1,910	10	54	655	1.4	240	<1	7,000	<0.5	11.6	<0.5	16
MJVD-5-33	6.5	2,710	700	1.1	1,095	5	97	344	2.2	163	1	7,090	<0.5	9.7	<0.5	12
MJVD-5-34	4.5	2,080	440	0.8	902	<5	39	278	1.8	202	2	13,200	<0.5	7.5	<0.5	5
MJVD-5-35	8.0	1,900	1,040	1.5	899	15	80	271	1.6	167	<1	23,800	<0.5	10.7	<0.5	4
MJVD-5-36	6.6	5,420	870	1.2	1,695	10	44	582	1.8	187	<1	6,590	<0.5	11.8	<0.5	8
MJVD-5-37	6.4	4,640	670	1.1	1,620	5	34	538	1.2	204	<1	6,210	<0.5	11.2	<0.5	11
MJVD-5-38	6.2	4,600	1,300	1.2	1,570	10	58	528	2.4	185	<1	4,170	<0.5	11.2	<0.5	12
MJVD-5-39	5.0	1,445	690	0.9	648	10	99	197	1.2	116	<1	6,260	<0.5	7.1	<0.5	2
MJVD-5-40	3.9	1,415	370	0.7	632	10	52	193	1.2	118	<1	5,110	<0.5	6.2	<0.5	6
MJVD-5-41	2.1	1,225	130	0.5	492	<5	25	154	0.8	181	<1	7,870	<0.5	3.7	<0.5	<1
MJVD-5-42	2.9	885	310	0.6	382	<5	46	117	0.8	162	<1	7,340	<0.5	4.0	<0.5	<1
MJVD-5-43	4.4	5,530	970	0.7	1,905	25	83	643	60.8	230	<1	3,820	<0.5	10.7	0.5	21
MJVD-5-44	0.8	201	170	0.2	95	75	9	28	224.0	14	2	1,530	<0.5	0.9	3.5	12
MJVD-5-45	0.9	121	210	0.3	66	65	7	19	238.0	11	<1	1,475	<0.5	0.8	4.0	12
MJVD-5-46	0.9	99	200	0.3	58	60	6	16	215.0	9	<1	1,400	<0.5	0.8	4.0	12
MJVD-5-47	3.0	3,830	1,490	0.6	1,215	40	19	423	101.0	129	<1	2,990	<0.5	6.8	1.5	20
MJVD-5-48	6.5	4,060	3,130	1.2	1,630	15	82	526	2.8	191	<1	6,120	<0.5	11.2	<0.5	7
MJVD-5-49	6.8	4,890	1,520	1.1	1,920	10	81	632	2.6	223	<1	7,370	<0.5	12.7	<0.5	13
MJVD-5-50	5.1	5,710	1,590	0.8	1,865	10	54	641	2.2	199	<1	5,410	<0.5	11.0	<0.5	9
MJVD-5-51	6.7	6,260	810	1.1	2,270	10	30	761	4.8	266	<1	8,780	<0.5	13.7	<0.5	10
MJVD-5-52	8.3	9,900	1,330	1.4	3,120	20	69	1,055	12.8	344	<1	5,570	<0.5	18.7	1.0	20
MJVD-5-53	8.5	6,630	1,110	1.3	2,340	10	100	784	10.8	336	<1	6,250	1.0	15.2	1.0	20
MJVD-5-54	7.1	5,100	1,460	1.2	1,985	5	55	647	22.4	235	<1	6,660	<0.5	13.5	<0.5	12
MJVD-5-55	6.8	6,170	910	1.1	2,320	5	22	758	5.8	266	<1	5,690	<0.5	14.1	<0.5	13
MJVD-5-56	6.9	10,730	810	1.1	3,220	5	13	1,110	1.2	305	<1	5,550	<0.5	17.2	<0.5	19
MJVD-5-57	5.6	4,570	430	0.9	1,670	10	13	551	1.8	202	<1	8,700	<0.5	10.8	<0.5	16

MJVD-5 (36/126)

Sample Name	Ho ppm	La ppm	Pb ppm	Lu ppm	Nd ppm	Ni ppm	Nb ppm	Pr ppm	Rb ppm	Sm ppm	Ag ppm	Sr ppm	Ta ppm	Tb ppm	Tl ppm	Th ppm
MJVD-5-58	6.4	4,320	320	1.1	1,645	5	15	542	2.4	213	<1	9,460	<0.5	11.2	<0.5	5
MJVD-5-59	4.6	5,660	340	0.7	2,120	5	20	703	1.0	232	<1	5,850	<0.5	11.3	<0.5	16
MJVD-5-60	5.2	3,010	430	0.9	1,285	5	34	414	2.6	173	<1	7,660	<0.5	9.2	<0.5	9
MJVD-5-61	5.6	2,830	560	1.0	1,125	10	25	361	2.2	174	<1	8,410	<0.5	9.4	<0.5	37
MJVD-5-62	5.9	12,810	400	0.9	3,450	10	9	1,240	1.4	346	<1	7,450	<0.5	16.9	<0.5	38
MJVD-5-63	8.6	17,730	670	1.3	5,210	5	40	1,820	1.8	468	<1	5,560	<0.5	24.9	<0.5	50
MJVD-5-64	5.7	6,840	440	0.9	2,440	5	56	817	3.2	269	<1	7,550	<0.5	13.8	<0.5	23
MJVD-5-65	6.7	9,920	550	1.1	3,530	5	36	1,190	1.6	320	<1	8,210	<0.5	17.6	<0.5	86
MJVD-5-66	8.0	10,540	780	1.2	3,460	5	66	1,165	1.0	358	<1	6,040	<0.5	19.9	<0.5	145
MJVD-5-67	7.0	12,630	470	0.9	4,850	10	35	1,615	0.2	461	<1	5,560	<0.5	22.6	<0.5	70
MJVD-5-68	5.7	5,010	340	0.9	1,855	5	33	616	2.8	236	<1	6,450	<0.5	11.4	<0.5	12
MJVD-5-69	5.9	4,270	540	1.0	1,670	15	43	542	8.2	226	<1	10,110	<0.5	10.9	<0.5	8
MJVD-5-70	6.3	1,995	1,320	1.1	916	5	387	282	31.6	137	<1	14,540	1.0	9.4	<0.5	3
MJVD-5-71	6.1	6,020	1,070	0.9	2,330	5	123	761	4.2	251	<1	7,770	1.0	13.3	<0.5	11
MJVD-5-72	7.2	10,360	630	1.1	3,260	5	69	1,090	3.6	329	<1	7,210	<0.5	17.8	<0.5	63
MJVD-5-73	6.4	9,480	770	0.9	2,910	5	68	971	1.8	296	<1	6,710	<0.5	15.3	<0.5	16
MJVD-5-74	5.3	6,290	440	0.9	2,150	10	51	723	4.6	244	<1	7,800	1.0	12.3	<0.5	15
MJVD-5-75	4.9	3,560	770	0.7	1,380	10	102	449	7.0	187	1	6,370	<0.5	9.4	<0.5	13
MJVD-5-76	6.1	5,030	1,110	1.0	1,945	10	230	626	2.0	224	<1	7,700	<0.5	12.6	<0.5	14
MJVD-5-77	5.6	3,150	810	0.9	1,320	20	101	416	2.2	172	<1	10,380	<0.5	9.8	<0.5	8
MJVD-5-78	6.2	4,840	770	1.0	1,880	10	91	611	3.4	229	<1	8,430	1.0	12.4	<0.5	27
MJVD-5-79	5.0	6,670	650	0.8	2,370	10	43	805	1.4	244	<1	15,330	<0.5	12.5	<0.5	16
MJVD-5-80	6.1	7,490	1,500	0.9	2,630	15	88	888	1.8	275	1	26,800	<0.5	14.8	<0.5	39
MJVD-5-81	7.1	8,780	920	1.0	2,900	10	67	971	3.6	302	<1	15,640	<0.5	16.1	<0.5	29
MJVD-5-82	5.9	5,870	920	0.9	2,130	10	324	706	4.0	232	<1	31,100	<0.5	12.8	<0.5	22
MJVD-5-83	5.4	22,200	310	0.7	6,200	5	26	2,170	1.8	548	<1	9,830	<0.5	25.1	<0.5	40
MJVD-5-84	5.5	17,050	200	0.7	4,970	10	16	1,715	2.2	495	<1	7,010	<0.5	21.7	<0.5	30
MJVD-5-85	4.9	4,970	1,350	0.8	1,780	20	30	586	1.0	186	<1	6,740	<0.5	10.4	<0.5	14
MJVD-5-86	5.7	12,920	1,080	0.9	3,540	10	75	1,225	1.6	320	<1	5,380	<0.5	17.3	<0.5	29
MJVD-5-87	5.5	10,850	1,700	1.0	3,030	15	105	1,045	0.6	297	<1	6,230	<0.5	15	<0.5	14
MJVD-5-88	5.7	9,850	2,040	0.9	3,190	5	58	1,065	1.0	316	<1	3,510	<0.5	16.2	<0.5	34
MJVD-5-89	3.7	1,600	2,150	0.6	665	5	190	208	1.6	92	<1	10,930	<0.5	5.8	<0.5	3
MJVD-5-90	4.3	2,770	520	0.7	1,030	10	124	335	1.4	126	<1	12,820	1.0	7.8	<0.5	4
MJVD-5-91	5.5	10,230	780	0.8	2,720	10	71	957	1.4	244	<1	11,340	<0.5	13.8	<0.5	9
MJVD-5-92	5.9	1,245	760	1.0	594	5	70	176	1.4	114	<1	12,140	<0.5	7.5	<0.5	<1
MJVD-5-93	6.9	4,510	890	1.2	1,745	5	70	562	2.4	222	<1	10,580	<0.5	12.6	<0.5	4
MJVD-5-94	7.4	12,700	1,150	1.1	3,850	5	112	1,315	15.0	355	<1	5,320	<0.5	19.7	<0.5	23
MJVD-5-95	5.9	4,510	820	1.0	1,625	5	79	531	8.6	213	<1	8,770	<0.5	11.5	<0.5	4
MJVD-5-96	7.3	3,850	1,920	1.2	1,505	5	53	481	10.6	182	<1	8,980	<0.5	12.1	<0.5	2
MJVD-5-97	7.2	6,370	1,580	1.2	2,160	10	135	728	6.2	253	<1	5,870	<0.5	14.9	0.5	8
MJVD-5-98	10.1	22,700	1,860	1.7	6,830	10	51	2,320	5	637	<1	4,600	<0.5	32.3	1.5	59
MJVD-5-99	6.2	15,210	1,040	1.0	4,450	5	115	1,515	2	410	<1	4,080	<0.5	20.3	0.5	32
MJVD-5-100	6.7	29,000	1,240	1.1	7,950	5	61	2,760	2	641	<1	5,090	<0.5	31.9	<0.5	39

MJVD-5 (37/126)

Sample Name	Tm	Sn	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-5-1	6.1	<1	68	168.0	100	36.3	1055	455	88
MJVD-5-2	9.5	1	36	273.0	65	45.6	1420	275	32
MJVD-5-3	6.5	<1	89	178.5	80	37.6	895	735	108
MJVD-5-4	7.2	<1	86	168.5	70	42.3	1160	370	248
MJVD-5-5	9.0	<1	229	167.5	110	48.8	1225	775	327
MJVD-5-6	9.0	<1	150	154.5	85	41.0	1175	650	144
MJVD-5-7	10.1	<1	41	254.0	50	42.3	1660	375	128
MJVD-5-8	3.9	<1	14	51.0	75	22.5	602	380	103
MJVD-5-9	9.4	<1	117	199.5	65	42.8	1260	640	51
MJVD-5-10	4.7	2	33	111.5	80	26.7	550	515	198
MJVD-5-11	3.5	<1	18	53.0	75	19.8	475	370	118
MJVD-5-12	3.2	<1	72	127.5	160	20.8	416	875	35
MJVD-5-13	5.6	<1	30	72.0	50	31.9	900	630	102
MJVD-5-14	7.7	<1	39	133.0	80	42.5	972	600	169
MJVD-5-15	3.3	<1	16	66.0	50	19.3	422	445	87
MJVD-5-16	1.7	2	38	65.0	180	11.3	166	5,700	256
MJVD-5-17	1.2	2	17	28.5	155	7.7	109	6,520	258
MJVD-5-18	0.7	1	11	13.0	135	4.3	83	1,295	207
MJVD-5-19	1.7	1	20	59.0	70	10.2	259	1,460	160
MJVD-5-20	3.3	1	16	157.5	115	18.8	443	1,055	109
MJVD-5-21	1.8	2	31	107.5	100	10.2	253	1,545	139
MJVD-5-22	2.0	2	10	106.5	65	11.7	279	480	102
MJVD-5-23	2.0	3	12	83.0	35	13.0	281	580	96
MJVD-5-24	2.4	4	10	76.5	45	15.3	285	575	218
MJVD-5-25	3.3	4	9	235.0	50	21.3	450	690	341
MJVD-5-26	2.1	1	9	80.5	40	12.5	297	535	96
MJVD-5-27	1.6	1	<1	15.0	10	8.4	152	240	20
MJVD-5-28	1.4	2	1	18.5	20	8.1	156	475	74
MJVD-5-29	1.8	5	6	41.5	15	9.8	191	630	78
MJVD-5-30	1.5	2	6	40.0	15	8.5	170	475	113
MJVD-5-31	1.4	2	3	25.0	20	8.7	163	335	78
MJVD-5-32	1.4	1	1	33.0	10	8.1	172	315	42
MJVD-5-33	1.9	<1	4	40.0	25	9.8	185	365	48
MJVD-5-34	1.3	1	<1	11.5	<5	7.8	137	460	122
MJVD-5-35	2.1	1	4	25.5	25	11.8	217	535	49
MJVD-5-36	1.7	1	3	50.5	40	10.7	191	425	42
MJVD-5-37	1.6	2	2	33.0	30	8.9	180	335	21
MJVD-5-38	1.6	<1	7	40.0	85	9.8	179	680	19
MJVD-5-39	1.3	<1	4	39.0	30	8.2	144	290	30
MJVD-5-40	1.1	<1	3	28.5	25	6.3	118	250	51
MJVD-5-41	0.7	<1	<1	15.0	10	4.0	65	225	14
MJVD-5-42	0.9	<1	2	19.5	15	4.5	77	195	18
MJVD-5-43	1.1	<1	29	44.5	90	6.3	130	775	132
MJVD-5-44	0.3	21	25	8.5	120	1.9	23	675	163
MJVD-5-45	0.3	5	19	7.5	115	1.8	22	475	165
MJVD-5-46	0.3	1	10	7.0	105	2.0	22	750	176
MJVD-5-47	0.9	1	42	25.5	95	5.0	97	625	131
MJVD-5-48	1.6	<1	23	40.5	55	9.9	173	280	42
MJVD-5-49	1.8	<1	15	47.0	45	9.8	197	335	22
MJVD-5-50	1.3	<1	18	36.5	30	7.6	157	355	29
MJVD-5-51	1.6	2	11	30.5	10	9.7	193	385	31
MJVD-5-52	2.0	<1	36	48.5	20	11.9	250	800	49
MJVD-5-53	2.1	4	31	42.5	30	11.7	261	565	52
MJVD-5-54	1.8	<1	11	35.0	20	10.8	193	290	28
MJVD-5-55	1.7	<1	12	33.0	15	9.2	194	410	11
MJVD-5-56	1.7	1	16	37.0	20	9.8	209	400	52
MJVD-5-57	1.5	1	5	19.5	10	9.0	186	285	37

MJVD-5 (38/126)

Sample Name	Tm	Sn	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-5-58	1.7	<1	6	20.0	5	8.5	183	245	38
MJVD-5-59	1.0	<1	3	22.0	5	6.8	148	290	32
MJVD-5-60	1.4	<1	4	20.5	10	7.3	154	255	29
MJVD-5-61	1.4	<1	5	24.0	25	8.1	171	360	21
MJVD-5-62	1.5	<1	3	40.0	<5	8.9	221	365	30
MJVD-5-63	1.9	<1	10	59.0	10	10.0	256	450	115
MJVD-5-64	1.4	<1	5	37.5	10	8.1	168	360	58
MJVD-5-65	1.5	<1	7	41.5	20	9.3	196	305	86
MJVD-5-66	1.7	<1	6	60.0	20	9.8	232	480	39
MJVD-5-67	1.5	1	18	50.0	35	8.8	225	275	43
MJVD-5-68	1.3	1	21	23.0	<5	8.1	197	290	48
MJVD-5-69	1.4	1	9	23.5	5	8.1	180	305	90
MJVD-5-70	1.7	<1	14	104.0	25	8.9	171	495	13
MJVD-5-71	1.5	<1	17	39.5	30	9.1	210	540	28
MJVD-5-72	1.7	2	15	40.5	10	9.4	230	270	28
MJVD-5-73	1.5	2	14	43.5	<5	9.1	231	340	25
MJVD-5-74	1.3	2	8	32.5	10	7.1	208	365	76
MJVD-5-75	1.2	1	9	28.0	30	6.8	199	675	82
MJVD-5-76	1.5	2	12	92.5	25	8.4	208	635	36
MJVD-5-77	1.4	<1	5	41.0	35	7.7	171	430	36
MJVD-5-78	1.5	3	10	46.5	25	7.8	211	360	56
MJVD-5-79	1.2	<1	6	42.5	15	7.3	155	260	43
MJVD-5-80	1.4	<1	7	91.5	30	8.1	197	585	94
MJVD-5-81	1.7	<1	6	64.5	20	9.1	217	485	46
MJVD-5-82	1.6	<1	14	148.0	25	7.8	193	450	37
MJVD-5-83	1.1	1	1	72.0	15	7.4	167	315	44
MJVD-5-84	1.2	<1	2	71.0	<5	7.4	189	495	11
MJVD-5-85	1.3	<1	5	33.0	40	7.1	141	360	13
MJVD-5-86	1.3	1	12	51.5	<5	8.2	186	460	19
MJVD-5-87	1.5	<1	15	59.0	10	8.3	167	460	45
MJVD-5-88	1.4	<1	10	57.5	5	8.5	184	555	25
MJVD-5-89	0.9	<1	11	79.0	10	5.6	95	530	74
MJVD-5-90	1.1	2	10	61.0	20	5.9	119	305	81
MJVD-5-91	1.2	<1	6	45.5	10	7.1	151	270	112
MJVD-5-92	1.6	<1	12	16.0	5	8.8	161	230	54
MJVD-5-93	1.8	<1	7	34.5	5	10.2	196	325	24
MJVD-5-94	1.8	<1	19	58.5	15	9.2	209	370	56
MJVD-5-95	1.5	1	13	30.5	<5	8.1	199	255	128
MJVD-5-96	1.8	<1	11	34.0	10	10.2	193	400	110
MJVD-5-97	1.8	<1	18	46.5	10	10.0	188	420	70
MJVD-5-98	2.4	<1	94	83.5	15.0	14.4	278.0	275	42
MJVD-5-99	1.4	<1	25	55.5	<5	8.7	176	255	36
MJVD-5-100	1.6	1	15	0.9	<5	9.9	198	345	38

MJVD-6 (39/126)

Sample Name	Ba	F	Al	As	B	Be	Bi	Ca	Cd	Cr	Fe	Ga	Hg	K	Mg	Mn
	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%	ppm
MJVD-6- 1	31.8	0.10	2.03	132	<10	<5.0	<10	0.05	0.5	46	4.62	<100	1	0.03	0.01	2,270
MJVD-6- 2	40.8	0.08	1.00	116	<10	<5.0	<10	0.04	0.5	35	4.64	<100	<1	0.02	0.01	1,250
MJVD-6- 3	39.8	0.06	0.79	90	<10	<5.0	<10	0.03	<0.5	34	3.21	<100	<1	0.01	0.01	1,545
MJVD-6- 4	40.2	0.05	0.96	106	<10	<5.0	<10	0.03	0.5	35	3.06	<100	<1	0.02	0.01	1,115
MJVD-6- 5	44.1	0.05	0.63	84	<10	<5.0	<10	0.04	0.5	29	2.71	<100	<1	0.02	<0.01	>10,000
MJVD-6- 6	29.9	0.08	1.97	144	<10	<5.0	<10	0.04	<0.5	43	3.82	<100	<1	0.03	<0.01	>10,000
MJVD-6- 7	23.0	0.10	1.92	146	<10	<5.0	<10	0.05	<0.5	40	4.39	<100	<1	0.03	0.01	1,490
MJVD-6- 8	33.3	0.07	0.88	132	<10	<5.0	<10	0.03	0.5	34	4.98	<100	<1	0.03	0.01	5,420
MJVD-6- 9	33.8	0.09	0.66	100	<10	5	<10	0.01	0.5	35	6.14	<100	<1	0.04	0.02	9,150
MJVD-6- 10	42.2	0.05	0.54	128	<10	<5.0	<10	0.04	0.5	32	4.20	<100	<1	0.03	0.01	3,740
MJVD-6- 11	45.1	0.05	0.42	86	<10	<5.0	<10	0.01	0.5	27	4.14	<100	<1	0.03	0.01	2,930
MJVD-6- 12	43.7	0.05	0.41	80	<10	<5.0	<10	0.05	0.5	27	4.58	<100	<1	0.03	0.02	5,260
MJVD-6- 13	29.6	0.08	0.45	230	<10	5	30	0.03	1.0	67	7.28	<100	<1	0.04	0.03	3,730
MJVD-6- 14	35.0	0.07	0.35	224	<10	5	20	0.10	1.0	59	6.87	<100	<1	0.03	0.04	2,950
MJVD-6- 15	31.2	0.10	0.50	152	<10	10	<10	0.05	1.0	46	7.46	<100	<1	0.05	0.03	>10,000
MJVD-6- 16	45.0	0.03	0.19	66	<10	<5.0	<10	0.01	0.5	37	4.45	<100	<1	0.02	0.01	1,715
MJVD-6- 17	37.2	0.06	0.37	182	<10	<5.0	<10	0.04	1.5	46	7.59	<100	<1	0.03	0.03	4,110
MJVD-6- 18	38.5	0.07	0.44	198	<10	<5.0	30	0.03	1.0	43	5.49	<100	<1	0.03	0.02	2,600
MJVD-6- 19	28.0	0.12	1.00	190	<10	<5.0	40	0.03	0.5	42	6.36	<100	<1	0.03	0.03	4,210
MJVD-6- 20	14.3	0.15	3.41	148	<10	<5.0	<10	0.03	<0.5	34	4.35	<100	<1	0.04	0.01	3,350
MJVD-6- 21	16.9	0.13	3.11	124	<10	<5.0	<10	0.01	0.5	34	3.54	<100	<1	0.04	0.01	705
MJVD-6- 22	18.6	0.10	1.88	116	<10	<5.0	<10	0.02	0.5	33	4.08	<100	<1	0.04	0.01	2,730
MJVD-6- 23	38.0	0.07	0.47	104	<10	<5.0	<10	0.01	0.5	36	4.99	<100	<1	0.04	0.01	4,380
MJVD-6- 24	30.9	0.09	0.56	294	<10	<5.0	<10	0.04	1.0	59	10.90	<100	<1	0.04	0.05	5,280
MJVD-6- 25	34.6	0.12	0.51	224	<10	5	<10	0.07	0.5	48	8.99	<100	2	0.03	0.04	2,110
MJVD-6- 26	20.7	0.12	0.79	258	<10	15	20	0.05	2.0	57	11.30	<100	<1	0.05	0.04	>10,000
MJVD-6- 27	31.1	0.13	0.74	278	<10	15	10	0.08	1.5	52	7.95	<100	<1	0.05	0.03	7,780
MJVD-6- 28	36.5	0.08	0.73	236	<10	15	<10	0.07	2.0	43	6.21	<100	<1	0.03	0.02	5,680
MJVD-6- 29	35.6	0.08	0.72	280	<10	15	10	0.08	2.0	56	8.07	<100	<1	0.03	0.03	5,480
MJVD-6- 30	33.9	0.07	0.93	224	<10	10	<10	0.06	1.5	47	6.21	<100	<1	0.04	0.02	4,430
MJVD-6- 31	34.3	0.09	1.11	428	<10	<5.0	<10	0.04	0.5	33	5.23	<100	<1	0.05	0.02	>10,000
MJVD-6- 32	31.3	0.19	1.43	244	<10	10	<10	0.05	2.0	36	5.53	<100	<1	0.05	0.03	8,450
MJVD-6- 33	21.1	0.13	0.90	210	<10	5	<10	0.05	0.5	42	6.25	<100	<1	0.06	0.03	9,100
MJVD-6- 34	23.8	0.27	1.09	400	<10	5	<10	0.05	1.5	36	5.93	<100	<1	0.08	0.03	>10,000
MJVD-6- 35	14.2	0.11	0.76	220	<10	<5.0	<10	0.08	<0.5	34	4.30	<100	<1	0.05	0.03	4,260
MJVD-6- 36	28.7	0.16	0.91	244	<10	5	<10	0.04	2.0	36	5.65	<100	<1	0.05	0.02	>10,000
MJVD-6- 37	42.5	0.09	0.93	234	<10	<5.0	<10	0.03	0.5	25	3.48	<100	<1	0.03	0.01	9,300
MJVD-6- 38	25.0	0.16	1.76	312	<10	<5.0	<10	0.03	0.5	25	3.75	<100	<1	0.04	0.01	5,820
MJVD-6- 39	34.2	0.19	1.07	260	<10	<5.0	<10	0.02	0.5	24	3.49	<100	<1	0.06	0.02	7,390
MJVD-6- 40	32.2	0.26	1.06	480	<10	<5.0	<10	0.04	1.5	16	3.90	<100	<1	0.07	0.04	8,700
MJVD-6- 41	38.0	0.23	0.66	286	<10	<5.0	<10	0.04	2.0	12	2.66	<100	<1	0.08	0.06	6,630
MJVD-6- 42	32.0	0.41	1.00	242	<10	<5.0	<10	0.08	5.0	28	4.61	<100	<1	0.18	0.20	>10,000
MJVD-6- 43	19.8	0.61	2.32	190	<10	5	<10	0.08	6.5	63	6.71	<100	<1	0.26	0.30	>10,000
MJVD-6- 44	27.0	0.63	2.17	240	<10	<5.0	<10	0.54	3.5	26	2.97	<100	<1	0.23	0.07	5,840
MJVD-6- 45	15.4	0.12	0.91	200	<10	<5.0	<10	0.10	3.5	29	2.59	<100	<1	0.02	0.01	5,730
MJVD-6- 46	14.2	0.17	1.43	198	<10	<5.0	<10	0.16	2.0	15	2.66	<100	<1	0.06	0.01	3,500
MJVD-6- 47	9.0	0.74	6.85	212	<10	<5.0	<10	0.05	2.5	12	2.37	<100	<1	0.04	<0.01	4,170
MJVD-6- 48	35.2	0.71	1.70	772	<10	<5.0	<10	0.09	2.5	15	2.14	<100	<1	0.09	0.05	5,450
MJVD-6- 49	33.0	0.29	1.34	180	<10	<5.0	<10	0.05	1.5	34	3.40	<100	<1	0.10	0.07	5,880
MJVD-6- 50	20.7	0.78	3.00	430	<10	5	<10	0.06	4.5	29	4.74	<100	<1	0.31	0.37	>10,000
MJVD-6- 51	11.3	0.51	5.51	382	<10	<5.0	10	0.04	1.5	27	3.73	<100	<1	0.06	0.01	4,490
MJVD-6- 52	33.4	0.36	1.60	438	<10	<5.0	<10	0.05	2.0	21	2.82	<100	<1	0.07	0.07	6,290
MJVD-6- 53	38.8	0.23	0.93	212	<10	<5.0	<10	0.04	1.5	19	2.38	<100	<1	0.06	0.05	5,550
MJVD-6- 54	30.8	0.19	3.65	284	<10	<5.0	<10	0.05	4.5	18	2.90	<100	<1	0.16	0.12	>10,000
MJVD-6- 55	28.5	0.65	1.72	254	<10	5	<10	0.08	2.0	30	3.34	<100	<1	0.11	0.07	7,710
MJVD-6- 56	27.4	0.30	1.35	178	<10	10	<10	0.06	4.0	26	3.48	<100	<1	0.41	0.43	>10,000
MJVD-6- 57	31.9	0.59	1.17	162	<10	5	<10	0.05	2.5	25	3.23	<100	<1	0.34	0.39	8,640

MJVD-6 (40/126)

Sample Name	Ba %	F %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm
MJVD-6-58	37.6	0.34	0.89	196	<10	<5.0	<10	0.05	1.5	29	3.11	<100	<1	0.15	0.15	6,400
MJVD-6-59	40.8	0.65	0.85	138	<10	5	<10	0.03	1.5	21	2.30	<100	<1	0.28	0.32	6,760
MJVD-6-60	32.5	0.40	2.46	218	<10	5	<10	0.05	3.0	52	3.78	<100	<1	0.14	0.15	>10,000
MJVD-6-61	13.0	0.19	1.29	300	<10	10	<10	0.08	2.0	67	5.07	<100	<1	0.09	0.09	5,830
MJVD-6-62	27.6	0.18	0.74	338	<10	10	<10	0.09	2.5	65	4.75	<100	<1	0.09	0.06	8,970
MJVD-6-63	29.8	0.25	0.41	212	<10	<5.0	<10	0.11	1.5	41	0.90	<100	<1	0.10	0.02	2,300
MJVD-6-64	17.2	0.70	0.48	356	30	<5.0	<10	0.69	1.0	71	0.69	<100	<1	0.14	0.03	1,820
MJVD-6-65	23.5	3.85	0.42	324	730	<5.0	<10	3.11	1.0	46	0.86	<100	<1	0.16	0.03	2,060
MJVD-6-66	32.4	7.32	0.47	436	1,270	<5.0	<10	4.24	2.0	14	0.82	<100	<1	0.18	0.03	5,510
MJVD-6-67	33.9	8.88	0.66	428	1,230	<5.0	<10	5.18	2.5	13	0.75	<100	<1	0.24	0.04	7,830
MJVD-6-68	40.9	1.32	0.21	282	190	<5.0	<10	1.07	4.0	19	1.40	<100	<1	0.05	0.01	>10,000
MJVD-6-69	42.6	0.35	0.08	308	60	<5.0	<10	0.18	0.5	26	0.98	<100	<1	0.01	<0.01	5,030
MJVD-6-70	24.9	7.39	0.25	708	1,130	<5.0	<10	4.28	2.0	15	0.86	<100	<1	0.12	0.01	3,200
MJVD-6-71	24.9	8.61	0.32	410	1,700	<5.0	<10	4.93	0.5	37	1.18	<100	<1	0.15	0.01	1,040
MJVD-6-72	25.9	15.55	0.35	454	1,880	<5.0	<10	6.02	1.5	12	0.65	<100	<1	0.17	0.01	4,490
MJVD-6-73	21.9	8.38	0.49	558	1,290	<5.0	<10	4.32	1.5	49	2.45	<100	<1	0.19	0.03	2,230
MJVD-6-74	22.4	7.49	0.38	942	700	<5.0	<10	3.62	3.5	26	2.70	<100	<1	0.14	0.03	1,150
MJVD-6-75	30.3	8.77	0.52	366	1,300	<5.0	<10	4.56	2.0	32	1.02	<100	<1	0.19	0.03	8,510
MJVD-6-76	19.7	4.54	1.64	550	120	<5.0	<10	3.53	6.0	117	3.47	<100	<1	0.47	0.10	>10,000
MJVD-6-77	16.1	5.63	1.28	1395	350	<5.0	<10	2.35	7.5	40	1.45	<100	<1	0.37	0.06	7,490
MJVD-6-78	13.1	10.40	0.54	1100	560	<5.0	<10	4.72	5.0	16	0.64	<100	<1	0.19	0.02	3,590
MJVD-6-79	15.0	10.65	0.49	932	710	<5.0	<10	4.56	6.5	9	0.56	<100	<1	0.17	0.01	>10,000
MJVD-6-80	19.4	11.00	0.78	940	880	<5.0	<10	4.02	5.0	11	0.63	<100	<1	0.28	0.03	>10,000
MJVD-6-81	16.1	8.03	0.45	890	860	<5.0	<10	3.55	5.5	20	1.46	<100	<1	0.15	0.03	>10,000
MJVD-6-82	16.3	6.17	0.43	1550	370	<5.0	<10	2.56	5.5	10	0.72	<100	<1	0.13	0.01	5,330
MJVD-6-83	28.4	8.76	0.92	366	960	<5.0	<10	5.47	3.0	24	1.64	<100	<1	0.30	0.05	>10,000
MJVD-6-84	22.5	16.55	0.65	148	2,150	<5.0	<10	7.43	2.0	15	0.89	<100	<1	0.24	0.03	5,560
MJVD-6-85	28.2	14.40	0.64	290	1,790	<5.0	<10	6.38	2.5	15	0.62	<100	<1	0.23	0.03	7,080
MJVD-6-86	21.9	12.15	0.97	658	1,220	<5.0	<10	5.05	10.0	17	1.03	<100	<1	0.29	0.04	>10,000
MJVD-6-87	23.1	7.46	0.93	334	1,020	<5.0	<10	5.37	15.5	20	1.00	<100	<1	0.28	0.04	>10,000
MJVD-6-89	17.7	4.24	3.20	352	150	5	<10	5.12	15.0	42	2.64	<100	<1	0.93	0.15	>10,000
MJVD-6-90	22.9	7.33	1.71	276	400	<5.0	<10	6.14	14.0	31	2.11	<100	<1	0.52	0.09	>10,000
MJVD-6-91	27.9	12.45	1.11	126	1,190	<5.0	<10	7.25	10.5	20	1.44	<100	<1	0.37	0.06	>10,000
MJVD-6-92	21.7	6.05	2.39	172	280	<5.0	<10	6.65	7.0	36	3.17	<100	<1	0.75	0.12	>10,000
MJVD-6-93	19.2	13.95	2.31	126	430	<5.0	<10	8.38	2.0	33	2.12	<100	<1	0.68	0.10	2,830
MJVD-6-94	14.8	22.40	1.11	96	1,710	<5.0	<10	9.03	0.5	18	0.85	<100	<1	0.41	0.05	905
MJVD-6-95	12.1	29.90	0.76	122	2,420	<5.0	<10	8.65	0.5	11	0.55	<100	<1	0.29	0.03	810
MJVD-6-96	22.1	19.15	1.37	126	1,150	<5.0	<10	8.14	0.5	20	1.21	<100	<1	0.50	0.07	1,550
MJVD-6-97	14.4	29.30	0.41	72	2,640	<5.0	<10	8.13	<0.5	8	0.26	<100	<1	0.21	0.01	500
MJVD-6-98	16.7	28.00	0.55	110	2,410	<5.0	<10	8.08	0.5	8	0.31	<100	<1	0.23	0.02	1,005
MJVD-6-99	7.45	31.9	1	50	2,400	<5.0	<10	9.76	0.5	14	0.72	<100	<1	0	0.04	965
MJVD-6-100	17.7	23.8	1	160	2,080	<5.0	<10	8.09	0.5	9	0.5	<100	<1	0	0.03	1,455

MJVD-6 (41/126)

Sample Name	Mo ppm	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm
MJVD-6- 1	35	<0.01	1,750	0.06	32	<20	<0.01	9,660	2.1	9.0	40	20.4	12.5	<300	67	3
MJVD-6- 2	113	<0.01	1,340	0.06	30	<20	<0.01	10,840	1.2	4.5	35	10.0	7.4	<400	37	2
MJVD-6- 3	40	<0.01	980	0.06	20	<20	<0.01	12,170	1.5	3.0	30	13.4	8.8	<400	39	2
MJVD-6- 4	45	<0.01	670	0.06	24	<20	<0.01	10,370	2.2	2.0	35	8.9	5.9	<400	27	2
MJVD-6- 5	32	<0.01	750	0.05	20	<20	<0.01	10,050	2	56.5	35	10.3	6.4	<400	29	1
MJVD-6- 6	76	<0.01	920	0.06	26	<20	<0.01	10,180	3.4	8.0	55	11.5	8.0	<300	40	4
MJVD-6- 7	83	<0.01	1,340	0.06	18	<20	<0.01	8,040	3.5	10.0	45	21.7	14.4	<200	73	3
MJVD-6- 8	38	<0.01	1,630	0.06	24	<20	<0.01	7,880	2	35.0	50	31.1	18.5	<350	94	1
MJVD-6- 9	38	<0.01	790	0.06	32	<20	0.01	6,890	1.7	62.5	60	24.5	15.1	<350	55	1
MJVD-6- 10	38	<0.01	1,380	0.06	30	<20	0.01	9,000	1.5	13.0	40	27.6	15.4	<450	82	2
MJVD-6- 11	27	<0.01	890	0.05	24	<20	<0.01	13,470	1.1	8.0	35	13.6	9.9	<450	49	2
MJVD-6- 12	22	<0.01	930	0.06	24	<20	<0.01	11,470	0.9	18.0	35	19.2	11.2	<450	49	1
MJVD-6- 13	33	<0.01	2,610	0.05	68	<20	0.01	12,920	1.6	14.0	75	47.9	29.3	<300	150	1
MJVD-6- 14	32	<0.01	2,320	0.06	56	<20	0.01	12,010	0.9	16.5	60	46.1	29.7	<300	141	1
MJVD-6- 15	6	<0.01	1,820	0.05	42	<20	0.01	7,950	1.5	45.0	105	54.1	29.8	<300	139	1
MJVD-6- 16	3	<0.01	800	0.06	18	<20	<0.01	10,520	0.6	8.0	35	14.3	8.7	<450	38	2
MJVD-6- 17	15	<0.01	2,750	0.06	36	<20	0.01	12,510	0.9	19.0	75	50.2	31.3	<400	151	1
MJVD-6- 18	31	<0.01	2,220	0.05	48	<20	0.01	11,960	0.8	7.0	40	38.8	23.5	<400	131	1
MJVD-6- 19	43	<0.01	2,800	0.05	40	<20	0.01	11,050	1.5	13.0	40	44.6	26.0	<300	151	1
MJVD-6- 20	81	<0.01	1,110	0.07	24	<20	<0.01	7,080	5.8	23.5	45	17.1	11.5	<100.0	53	5
MJVD-6- 21	61	<0.01	930	0.07	20	<20	<0.01	8,240	4.8	4.0	40	16.6	10.3	<150.0	47	6
MJVD-6- 22	39	<0.01	910	0.06	26	<20	<0.01	8,120	3.9	11.0	40	17.3	11.2	<200	56	4
MJVD-6- 23	7	<0.01	1,090	0.06	30	<20	0.01	9,850	1.2	12.0	45	22.5	14.2	<400	61	2
MJVD-6- 24	5	<0.01	4,390	0.06	36	<20	0.01	12,710	1.3	37.5	105	74.6	51.2	<300	233	1
MJVD-6- 25	3	<0.01	5,030	0.05	22	<20	<0.01	9,340	0.7	18.5	100	54.7	35.3	<300	200	2
MJVD-6- 26	9	<0.01	3,440	0.05	90	<20	0.01	6,950	2.2	95.0	105	63.8	39.0	<200	186	1
MJVD-6- 27	7	<0.01	5,900	0.04	64	<20	0.01	9,570	2.1	57.5	80	71.1	48.4	<300	225	2
MJVD-6- 28	7	<0.01	5,760	0.03	54	<20	0.01	10,020	1	30.0	90	62.4	39.5	<400	222	2
MJVD-6- 29	7	<0.01	5,800	0.03	74	<20	0.01	9,190	1.1	24.5	115	60.0	41.4	<350	199	3
MJVD-6- 30	17	<0.01	3,730	0.05	60	<20	0.01	9,560	1.7	17.5	70	46.0	29.0	<350	157	3
MJVD-6- 31	9	<0.01	4,880	0.05	30	<20	<0.01	18,200	0.9	15.5	195	104.0	68.6	<350	309	5
MJVD-6- 32	7	<0.01	6,080	0.02	42	<20	0.01	8,250	1.7	13.5	120	74.7	49.7	<300	217	3
MJVD-6- 33	9	0.01	2,880	0.04	42	<20	0.01	6,210	1.7	17.0	90	73.9	47.0	<200	198	3
MJVD-6- 34	12	<0.01	5,100	0.04	30	<20	<0.01	14,560	1.7	13.5	90	118.5	81.4	<250	360	3
MJVD-6- 35	7	<0.01	2,260	0.04	34	<20	0.01	4,530	1.3	7.5	65	46.1	30.7	<150.0	131	7
MJVD-6- 36	16	<0.01	3,830	0.04	40	<20	<0.01	7,820	1.4	11.0	130	81.1	53.2	<300	245	3
MJVD-6- 37	26	<0.01	2,750	0.05	18	<20	<0.01	5,290	1.1	11.5	65	54.1	36.3	<400	184	2
MJVD-6- 38	23	0.01	1,950	0.05	20	<20	<0.01	4,750	1.8	9.0	95	91.2	54.9	<250	262	5
MJVD-6- 39	58	<0.01	1,460	0.05	24	<20	<0.01	6,420	1.4	6.5	130	87.4	57.5	<300	251	3
MJVD-6- 40	54	0.01	2,680	0.05	42	<20	<0.01	9,920	1.1	7.0	260	166.5	100.0	<350	458	5
MJVD-6- 41	40	0.01	2,230	0.05	22	<20	<0.01	6,500	1	4.5	140	98.8	63.1	<350	261	5
MJVD-6- 42	48	<0.01	2,830	0.04	40	<20	0.01	7,340	2.2	17.5	165	98.0	56.6	<300	242	5
MJVD-6- 43	45	<0.01	5,290	0.02	40	<20	0.02	5,310	3.5	39.0	145	82.9	51.8	<200	184	1
MJVD-6- 44	43	0.01	2,410	0.05	22	<20	<0.01	8,600	1.2	5.0	125	74.2	55.6	<250	172	4
MJVD-6- 45	34	<0.01	1,730	0.05	24	<20	<0.01	5,320	0.9	5.5	90	72.2	60.2	<150.0	158	11
MJVD-6- 46	23	0.01	1,450	0.05	18	<20	<0.01	2,820	2.6	5.5	80	71.2	56.4	<150.0	150	6
MJVD-6- 47	23	0.01	1,510	0.05	14	<20	<0.01	2,820	1.1	4.0	75	67.5	49.5	<80.0	177	11
MJVD-6- 48	34	<0.01	1,490	0.05	18	<20	<0.01	21,700	0.9	4.5	100	190.0	126.5	<350	644	4
MJVD-6- 49	17	<0.01	1,540	0.04	26	<20	0.02	6,920	3.6	12.5	115	59.7	43.6	<350	152	5
MJVD-6- 50	38	0.01	2,820	0.05	28	<20	0.02	7,930	3.4	13.5	190	175.5	117.5	<200	435	8
MJVD-6- 51	22	0.01	2,030	0.05	30	<20	<0.01	4,690	1.2	6.0	95	109.0	65.7	100	317	12
MJVD-6- 52	31	<0.01	1,720	0.05	28	<20	<0.01	7,330	0.9	6.0	150	154.5	91.9	<350	446	5
MJVD-6- 53	25	<0.01	1,540	0.05	22	<20	<0.01	5,650	0.8	5.5	110	68.8	44.1	<400	173	5
MJVD-6- 54	30	<0.01	1,300	0.04	26	<20	<0.01	9,980	1.6	7.0	215	115.0	78.9	<300	285	2
MJVD-6- 55	25	<0.01	1,790	0.04	28	<20	0.02	9,430	3.7	15.0	155	86.3	68.4	<300	218	4
MJVD-6- 56	13	<0.01	1,440	0.04	36	<20	0.01	7,620	3.8	8.0	140	102.0	64.6	<300	265	1
MJVD-6- 57	15	<0.01	1,140	0.05	30	<20	<0.01	7,670	2.8	9.0	125	76.8	47.6	<300	221	2

MJVD-6 (42/126)

Sample Name	Mo ppm	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm
MJVD-6-58	28	<0.01	1,370	0.05	32	<20	<0.01	8,250	1.5	6.0	125	62.2	42.8	<300	194	3
MJVD-6-59	13	<0.01	1,160	0.05	24	<20	<0.01	5,980	1.8	5.0	85	42.7	27.6	<400	147	2
MJVD-6-60	18	<0.01	2,180	0.03	36	<20	0.01	7,930	2	8.5	115	101.0	65.7	<400	274	2
MJVD-6-61	12	<0.01	1,820	0.03	42	<20	0.03	3,010	8.9	20.5	85	55.5	42.5	<100.0	138	5
MJVD-6-62	18	<0.01	2,260	0.03	76	<20	0.02	5,720	3.1	13.0	115	63.1	40.8	<200	202	2
MJVD-6-63	10	0.01	480	0.06	14	<20	<0.01	12,200	0.8	1.0	20	64.2	40.2	<300	331	2
MJVD-6-64	11	0.01	1,110	0.06	20	<20	<0.01	23,500	0.9	2.0	15	97.2	66.7	150	451	2
MJVD-6-65	11	0.11	810	0.05	18	<20	<0.01	21,000	0.6	1.5	15	64.9	44.1	<200	361	3
MJVD-6-66	8	0.17	810	0.04	14	<20	<0.01	27,600	0.6	1.0	40	77.0	56.3	<300	357	4
MJVD-6-67	12	0.18	1,500	0.04	26	<20	<0.01	26,200	0.6	2.5	50	83.2	61.0	<300	316	3
MJVD-6-68	10	0.03	2,800	0.01	22	<20	0.01	17,540	0.1	4.5	65	105.5	74.6	<400	342	5
MJVD-6-69	11	0.01	820	0.04	26	<20	<0.01	17,130	0.4	1.5	30	78.9	57.8	<400	303	3
MJVD-6-70	14	0.17	1,040	0.03	28	<20	<0.01	84,200	0.3	2.0	35	120.5	122.0	200	822	3
MJVD-6-71	8	0.23	570	0.05	22	<20	<0.01	34,000	0.4	1.0	30	86.3	71.2	<200	528	2
MJVD-6-72	5	0.27	810	0.04	14	<20	<0.01	45,100	0.4	1.5	35	71.6	66.7	<200	519	5
MJVD-6-73	8	0.19	850	0.05	16	<20	<0.01	40,400	1.2	2.5	35	85.8	77.9	<200	484	3
MJVD-6-74	10	0.12	160	0.03	28	<20	<0.01	112,000	0.6	6.0	30	110.0	136.5	200	963	2
MJVD-6-75	10	0.17	1,590	0.03	14	<20	<0.01	24,500	0.7	3.0	65	67.0	47.8	<300	314	3
MJVD-6-76	14	0.04	3,390	0.04	40	<20	0.05	30,700	4.6	12.0	80	120.0	83.8	<200	468	8
MJVD-6-77	12	0.07	1,530	0.05	20	<20	0.01	104,600	1.9	3.5	55	126.0	128.5	300	830	7
MJVD-6-78	9	0.10	350	0.01	12	<20	<0.01	134,600	1	2.0	30	124.0	151.0	400	1,030	3
MJVD-6-79	12	0.12	550	0.01	16	<20	<0.01	126,500	0.6	1.5	60	190.5	199.0	450	1,200	3
MJVD-6-80	12	0.14	510	0.03	8	<20	<0.01	92,900	1	3.0	60	149.0	148.5	200	885	3
MJVD-6-81	11	0.14	1,700	0.01	18	<20	<0.01	88,800	0.5	2.5	65	132.0	119.0	300	775	9
MJVD-6-82	12	0.07	450	0.02	6	<20	<0.01	171,700	0.5	2.5	45	145.0	168.5	450	1,040	6
MJVD-6-83	11	0.14	2,290	0.03	38	<20	<0.01	17,900	0.7	5.0	65	56.1	38.7	<200	211	5
MJVD-6-84	8	0.27	1,690	0.04	24	<20	<0.01	8,810	0.7	4.0	45	54.4	33.0	<200	156	4
MJVD-6-85	8	0.24	1,150	0.05	12	<20	<0.01	17,910	0.9	2.5	50	63.5	43.4	<300	200	5
MJVD-6-86	8	0.19	2,190	0.04	16	<20	<0.01	46,300	0.9	3.5	75	163.0	104.0	<300	505	3
MJVD-6-87	7	0.14	2,990	0.04	20	<20	<0.01	20,200	0.9	4.0	75	132.0	82.1	<300	329	3
MJVD-6-89	14	0.06	4,330	0.03	30	<20	0.01	19,880	3.6	10.0	85	131.5	79.1	150	346	3
MJVD-6-90	11	0.08	3,460	0.04	50	<20	0.01	15,530	2.1	10.0	100	122.0	74.1	<200	322	5
MJVD-6-91	6	0.16	2,370	0.04	24	<20	<0.01	7,010	1.2	7.0	65	80.8	46.7	<300	178	4
MJVD-6-92	12	0.06	2,930	0.04	24	<20	0.01	8,840	2.6	11.0	75	85.8	50.7	<200	203	4
MJVD-6-93	7	0.08	1,950	0.05	14	<20	0.01	6,410	2.4	8.0	85	43.5	26.0	<200	122	4
MJVD-6-94	4	0.25	1,060	0.05	2	<20	<0.01	6,100	1.2	4.0	70	35.6	24.5	<150.0	111	3
MJVD-6-95	3	0.30	520	0.06	4	<20	<0.01	10,530	0.8	4.0	35	41.8	27.2	<150.0	148	5
MJVD-6-96	6	0.17	600	0.06	6	<20	<0.01	7,230	2	7.5	40	31.3	20.3	<200	98	4
MJVD-6-97	1	0.34	190	0.06	6	<20	<0.01	4,240	0.2	2.0	20	26.0	15.1	<150.0	71	3
MJVD-6-98	3	0.32	250	0.06	2	<20	<0.01	6,720	0.4	2.0	30	26.7	17.8	<150.0	93	4
MJVD-6-99	1	0.3	250	0.07	2	<20	<0.01	2,700	0.9	3	20	22	12.6	<75.0	62	3
MJVD-6-100	4	0.27	390	0.06	6	<20	<0.01	8,900	0.6	3	20	29.5	20.1	<200	108	3

MJVD-6 (43/126)

Sample Name	Ho	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-6-1	3.7	2,900	1,935	0.4	1,030	<5	237	367	29.6	214	<1	4,590	<0.5	7.7	2.5	129
MJVD-6-2	1.7	2,270	1,765	0.3	686	<5	115	261	18.6	197	<1	5,230	<0.5	5.0	1.5	95
MJVD-6-3	2.3	1,810	1,625	0.4	656	<5	126	229	20.8	204	<1	4,760	<0.5	5.4	2.0	146
MJVD-6-4	1.3	1,345	1,370	0.3	456	<5	66	167	24.2	184	<1	3,690	<0.5	4.1	1.5	126
MJVD-6-5	1.6	1,415	1,210	0.4	494	<5	67	182	22.0	210	<1	3,780	<0.5	4.1	1.0	114
MJVD-6-6	2.1	1,980	1,545	0.3	697	<5	67	252	40.8	177	<1	3,300	<0.5	5.3	2.0	128
MJVD-6-7	4.0	2,760	1,480	0.5	1,070	<5	103	378	51.4	190	<1	3,190	<0.5	7.9	3.5	94
MJVD-6-8	5.6	3,060	3,630	0.6	1,310	10	208	444	39.6	264	<1	3,670	<0.5	10.3	6.5	123
MJVD-6-9	4.8	1,485	4,200	0.7	646	20	237	224	52.0	208	<1	3,810	<0.5	6.9	10.0	177
MJVD-6-10	4.9	2,820	3,250	0.6	1,170	<5	196	406	26.4	278	<1	4,590	<0.5	9.0	4.5	108
MJVD-6-11	2.5	1,995	2,550	0.5	754	<5	198	273	19.6	234	<1	4,400	<0.5	6.5	3.0	105
MJVD-6-12	3.2	1,625	3,810	0.5	708	10	308	248	23.0	229	<1	4,530	<0.5	6.7	5.0	106
MJVD-6-13	8.3	4,870	3,790	1.0	2,180	10	473	742	37.6	348	<1	4,270	<0.5	15.4	5.0	97
MJVD-6-14	8.5	4,380	2,980	0.9	1,935	15	302	672	30.4	338	<1	4,380	<0.5	15.3	4.0	144
MJVD-6-15	9.8	3,520	4,320	1.2	1,595	30	302	532	59.4	301	<1	3,280	<0.5	15.1	6.5	150
MJVD-6-16	2.5	1,215	1,645	0.4	506	<5	197	177	12.0	217	<1	4,130	<0.5	5.2	1.5	172
MJVD-6-17	8.8	4,970	3,410	1.1	2,130	10	533	726	27.4	380	<1	3,600	<0.5	16.8	4.0	158
MJVD-6-18	6.7	5,060	4,020	0.7	2,080	5	446	721	15.4	345	<1	3,630	1.0	13.7	3.0	127
MJVD-6-19	7.5	4,880	4,440	1.0	2,150	5	578	731	31.6	336	<1	3,970	<0.5	15.6	5.0	136
MJVD-6-20	3.0	2,320	2,110	0.4	859	<5	152	303	69.2	135	<1	2,210	<0.5	6.2	4.5	131
MJVD-6-21	2.9	2,240	1,160	0.4	815	<5	128	301	64.2	140	<1	2,490	<0.5	5.4	2.5	149
MJVD-6-22	3.3	2,240	1,935	0.5	819	5	136	292	49.0	153	<1	3,290	<0.5	6.5	4.5	158
MJVD-6-23	4.0	2,220	3,130	0.5	845	10	298	303	29.6	232	<1	3,470	<0.5	7.2	3.0	154
MJVD-6-24	13.1	8,860	2,580	1.7	3,390	10	401	1,220	37.8	463	<1	2,680	<0.5	24.0	4.5	125
MJVD-6-25	9.4	7,870	2,230	1.2	2,930	5	256	1,060	24.0	436	<1	4,120	<0.5	19.5	2.0	154
MJVD-6-26	11.5	5,410	5,110	1.7	2,540	20	348	856	69.6	373	<1	2,110	<0.5	19.5	4.5	174
MJVD-6-27	14.2	8,340	4,940	1.9	3,140	15	343	1,105	51.2	447	<1	3,690	<0.5	23.6	4.0	193
MJVD-6-28	11.5	8,020	3,080	1.5	3,190	20	322	1,095	22.4	496	<1	4,500	0.5	22.4	3.0	269
MJVD-6-29	10.9	7,540	3,460	1.3	3,030	25	250	1,055	26.0	465	<1	4,380	<0.5	20.4	3.0	167
MJVD-6-30	7.9	5,760	2,190	1.1	2,330	20	283	814	34.8	364	<1	3,730	<0.5	15.6	2.5	162
MJVD-6-31	19.2	13,280	5,080	2.7	4,480	10	232	1,655	33.0	584	<1	3,170	<0.5	33.2	3.5	163
MJVD-6-32	14.8	8,630	3,000	1.9	2,830	40	175	976	36.2	426	<1	4,230	<0.5	22.4	4.0	121
MJVD-6-33	14.6	5,770	3,960	1.6	2,250	20	210	768	44.6	342	<1	3,210	<0.5	21.5	4.5	190
MJVD-6-34	22.5	16,910	3,560	3.2	4,950	30	240	1,790	50.0	588	<1	3,050	<0.5	35.7	5.5	177
MJVD-6-35	8.6	5,040	2,630	1.4	1,855	5	137	648	33.8	261	<1	2,320	<0.5	13.5	3.0	148
MJVD-6-36	15.1	8,410	2,280	1.8	3,320	40	177	1,175	47.0	466	<1	3,480	<0.5	24.6	4.5	123
MJVD-6-37	9.7	7,520	1,585	1.3	2,940	15	100	1,045	26.2	441	<1	4,280	<0.5	18.1	2.5	59
MJVD-6-38	16.4	8,970	2,080	2.0	3,440	15	146	1,115	43.6	457	<1	3,040	<0.5	25.6	2.0	133
MJVD-6-39	16.2	8,470	3,370	2.1	3,110	25	224	1,040	43.4	469	<1	4,220	<0.5	25.1	3.0	153
MJVD-6-40	30.2	14,120	5,040	4.0	5,090	10	350	1,645	81.0	686	<1	3,760	<0.5	46.4	5.5	108
MJVD-6-41	19.7	7,680	3,110	2.9	2,680	10	155	870	77.2	437	<1	4,590	<0.5	25.7	3.0	100
MJVD-6-42	18.6	6,110	4,100	2.9	2,170	60	247	748	127.0	406	<1	3,400	<0.5	24.8	9.5	139
MJVD-6-43	16.7	4,390	4,230	2.7	1,565	95	319	518	197.0	297	<1	2,490	<0.5	20.5	8.5	78
MJVD-6-44	15.8	7,100	2,630	2.7	2,130	10	145	755	104.5	307	<1	3,150	<0.5	19.5	3.0	124
MJVD-6-45	17.0	5,530	3,770	2.9	1,775	15	175	615	14.0	245	<1	2,990	<0.5	16.6	3.0	200
MJVD-6-46	16.1	4,750	2,120	3.1	1,410	10	105	450	161.5	196	<1	2,120	<0.5	15.3	2.0	123
MJVD-6-47	14.4	6,130	1,590	2.5	1,965	5	93	655	133.0	251	<1	1,165	<0.5	17.3	2.0	143
MJVD-6-48	34.6	32,900	2,410	4.6	9,320	5	99	3,250	28.8	1,005	<1	3,530	<0.5	61.2	3.0	99
MJVD-6-49	13.0	5,790	1,525	2.5	1,695	55	91	599	71.6	297	<1	3,700	<0.5	15.8	8.0	78
MJVD-6-50	35.7	15,920	4,330	5.6	4,290	65	339	1,445	182.5	569	<1	1,975	<0.5	44.4	9.0	122
MJVD-6-51	20.0	11,530	2,120	2.8	3,770	<5	171	1,250	106.5	449	<1	2,060	<0.5	31.1	3.0	200
MJVD-6-52	28.5	16,850	3,330	3.9	4,850	15	190	1,590	49.6	645	<1	3,890	<0.5	44.1	5.0	168
MJVD-6-53	13.5	6,580	2,650	2.1	1,945	15	131	647	53.2	352	<1	6,380	<0.5	17.8	3.5	98
MJVD-6-54	25.6	10,070	2,340	4.3	2,840	105	136	954	91.2	414	<1	2,740	<0.5	29.6	6.5	116
MJVD-6-55	17.2	8,950	2,370	3.0	2,560	65	133	939	73.6	395	<1	2,980	<0.5	22.7	5.0	105
MJVD-6-56	19.4	5,730	1,730	3.1	2,430	45	300	788	206.0	473	<1	2,830	<0.5	27.6	7.0	139
MJVD-6-57	14.4	5,340	2,420	2.3	2,250	25	254	730	167.0	451	<1	3,340	<0.5	22.1	4.5	130

MJVD-6 (44/126)

Sample Name	Ho ppm	La ppm	Pb ppm	Lu ppm	Nd ppm	Ni ppm	Nb ppm	Pr ppm	Rb ppm	Sm ppm	Ag ppm	Sr ppm	Ta ppm	Tb ppm	Tl ppm	Th ppm
MJVD-6-58	12.0	6,360	2,550	2.0	2,260	25	208	769	76.6	426	<1	4,310	<0.5	18.9	2.0	147
MJVD-6-59	8.1	4,660	1,275	1.3	1,730	20	190	580	110.0	352	<1	4,290	<0.5	14.1	5.0	105
MJVD-6-60	19.2	6,260	2,280	2.9	2,830	50	330	884	70.4	516	<1	3,420	<0.5	26.6	6.5	73
MJVD-6-61	11.8	3,620	1,535	2.3	1,275	70	141	402	63.4	217	<1	1,945	<0.5	13.8	3.0	40
MJVD-6-62	12.4	4,560	2,540	2.0	2,120	80	341	653	49.2	402	<1	5,080	<0.5	18.8	4.5	50
MJVD-6-63	10.4	7,680	810	0.8	4,700	<5	30	1,375	14.0	775	<1	4,580	<0.5	27.6	0.5	72
MJVD-6-64	16.8	15,880	955	1.5	6,950	<5	41	2,270	11.0	887	<1	2,360	<0.5	40.7	<0.5	107
MJVD-6-65	10.5	15,560	1,300	1.0	5,900	<5	100	1,915	9.4	768	<1	3,190	<0.5	30.7	<0.5	80
MJVD-6-66	12.9	23,000	1,870	1.6	6,200	<5	172	2,280	6.8	740	<1	5,570	0.5	32.0	<0.5	59
MJVD-6-67	15.2	22,000	1,885	1.7	5,340	<5	51	2,040	10.8	617	<1	5,860	0.5	31.9	1.0	145
MJVD-6-68	19.6	12,230	2,590	3.0	4,490	<5	529	1,555	4.0	708	<1	4,410	<0.5	33.9	1.0	47
MJVD-6-69	13.8	10,920	2,800	2.3	4,760	<5	48	1,590	2.2	703	<1	5,070	<0.5	28.8	<0.5	59
MJVD-6-70	21.2	64,500	1,540	2.0	18,800	<5	62	6,900	3.6	1,570	<1	4,050	<0.5	77.0	<0.5	88
MJVD-6-71	14.2	22,800	1,115	1.3	9,870	<5	35	3,200	4.2	1,130	<1	4,230	<0.5	45.6	<0.5	106
MJVD-6-72	11.6	32,900	1,480	1.3	10,980	<5	104	3,890	4.4	1,075	<1	6,070	2.0	46.5	<0.5	101
MJVD-6-73	15.0	30,200	1,405	1.5	9,950	<5	66	3,530	8.8	987	<1	3,480	<0.5	45.9	<0.5	77
MJVD-6-74	17.7	88,700	970	1.6	24,700	<5	12	9,220	7.2	1,790	<1	3,350	<0.5	88.7	0.5	90
MJVD-6-75	11.6	18,920	2,450	1.4	5,490	<5	145	2,010	8.4	623	<1	4,570	1.0	30.0	2.0	33
MJVD-6-76	21.2	26,400	4,150	2.7	7,710	35	399	2,780	38.4	834	<1	2,790	<0.5	45.8	6.0	59
MJVD-6-77	21.3	90,300	2,410	2.3	20,300	10	104	7,940	22.0	1,495	<1	2,380	<0.5	83.8	3.0	79
MJVD-6-78	20.4	116,900	1,065	2.3	26,500	<5	22	10,210	10.6	1,785	<1	3,050	<0.5	103.0	1.0	105
MJVD-6-79	35.7	102,900	2,790	3.3	27,500	<5	36	10,070	8.2	2,110	<1	3,700	<0.5	115.0	2.5	73
MJVD-6-80	26.5	73,400	3,560	2.6	20,200	<5	34	7,600	14.4	1,680	<1	4,430	<0.5	84.5	2.0	50
MJVD-6-81	23.0	66,000	2,910	2.8	19,480	<5	303	6,430	6.2	1,495	<1	3,240	2.0	78.9	0.5	68
MJVD-6-82	23.1	134,800	1,765	2.6	33,400	<5	99	11,650	7.4	2,100	<1	2,540	0.5	123.5	0.5	129
MJVD-6-83	10.1	11,530	2,450	1.1	4,110	<5	310	1,325	13.0	467	<1	4,070	0.5	24.1	0.5	25
MJVD-6-84	10.0	5,890	1,400	1.3	2,410	<5	189	729	8.4	363	<1	6,920	2.0	17.3	<0.5	20
MJVD-6-85	12.0	12,170	2,090	1.5	3,790	<5	107	1,260	9.0	441	<1	5,870	1.5	22.7	<0.5	19
MJVD-6-86	30.0	35,500	3,930	3.4	9,640	5	285	3,240	15.0	946	<1	4,280	1.0	61.8	1.0	48
MJVD-6-87	26.1	13,420	4,630	3.1	4,820	10	266	1,515	15.8	627	<1	3,270	<0.5	40	2.0	34
MJVD-6-89	24.8	12,730	4,150	3.6	4,740	15	357	1,480	60.6	621	<1	2,540	<0.5	40.8	2.5	38
MJVD-6-90	22.8	10,940	5,200	3.3	4,300	15	518	1,315	34.6	604	<1	3,640	1.0	37.5	3.0	38
MJVD-6-91	15.1	4,700	2,330	2.2	2,000	5	355	594	20.6	370	<1	5,130	2.0	22.1	0.5	19
MJVD-6-92	16.1	5,930	1,815	2.1	2,580	20	226	759	50.8	400	<1	4,110	1.0	24.1	0.5	35
MJVD-6-93	8.3	4,330	640	1.1	1,930	10	74	575	42.4	280	<1	4,580	0.5	13.8	<0.5	41
MJVD-6-94	6.3	3,910	580	0.8	1,830	<5	29	534	21.2	252	<1	6,050	0.5	11.7	<0.5	23
MJVD-6-95	6.9	7,420	585	0.9	2,730	<5	89	858	13.2	327	<1	9,070	1.5	16.3	<0.5	21
MJVD-6-96	6.0	5,090	885	0.8	1,830	<5	20	586	30.2	236	<1	6,560	1.5	10.9	<0.5	18
MJVD-6-97	4.4	2,810	240	0.4	1,190	<5	10	352	3.8	177	<1	7,610	0.5	7.9	<0.5	10
MJVD-6-98	4.5	4,610	385	0.6	1,845	<5	13	566	9.0	234	<1	8,440	1.0	10.1	<0.5	10
MJVD-6-99	4.4	1,815	365	0.5	803	<5	23	234	18	122	<1	9,230	1	6.3	<0.5	10
MJVD-6-100	5.6	6,440	555	0.5	2,230	<5	13	720	13	252	<1	8,090	2	11.9	<0.5	14

MJVD-6 (45/126)

Sample Name	Tm	Sn	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-6- 1	0.8	<1	61	65.0	245	4.7	92.3	550	115
MJVD-6- 2	0.4	<1	36	46.5	140	2.9	46.4	525	51
MJVD-6- 3	0.6	<1	30	50.0	190	3.1	56.7	400	65
MJVD-6- 4	0.4	<1	29	37.0	165	2.0	36	350	88
MJVD-6- 5	0.5	4	615	37.5	170	2.2	40.5	425	58
MJVD-6- 6	0.7	<1	52	47.5	210	3.1	52.2	400	218
MJVD-6- 7	0.8	<1	38	60.5	175	4.8	112	360	161
MJVD-6- 8	1.1	<1	53	62.0	250	5.7	131	715	64
MJVD-6- 9	1.3	<1	66	49.0	315	5.5	98.6	905	39
MJVD-6- 10	1.0	<1	56	58.0	200	4.7	113	770	39
MJVD-6- 11	0.6	<1	31	60.5	205	3.0	56.7	600	35
MJVD-6- 12	0.8	<1	37	77.0	235	3.8	81.5	700	28
MJVD-6- 13	1.9	<1	121	140.0	305	9.0	216	1,215	12
MJVD-6- 14	1.7	<1	87	96.0	320	8.7	202	910	5
MJVD-6- 15	2.3	<1	77	74.0	400	10.4	244	1,045	27
MJVD-6- 16	0.8	<1	29	60.5	145	3.7	54	550	19
MJVD-6- 17	2.1	<1	68	134.0	300	10.8	222	920	18
MJVD-6- 18	1.4	<1	70	124.5	320	6.8	172.5	910	3
MJVD-6- 19	1.5	2	59	143.5	315	8.3	180	900	39
MJVD-6- 20	0.8	2	42	61.5	220	4.5	79.7	310	220
MJVD-6- 21	0.7	2	41	56.0	230	3.5	74.3	245	300
MJVD-6- 22	0.8	1	51	53.5	235	4.2	85.5	420	215
MJVD-6- 23	1.0	<1	57	68.0	255	5.3	91.8	735	48
MJVD-6- 24	3.4	<1	56	174.0	320	15.2	351	895	69
MJVD-6- 25	1.8	1	43	111.0	195	10.2	262	640	39
MJVD-6- 26	2.8	3	127	107.0	345	15.1	320	1,635	48
MJVD-6- 27	3.1	5	97	115.0	245	15.9	375	1,240	78
MJVD-6- 28	2.5	4	84	100.5	190	12.9	333	825	47
MJVD-6- 29	2.4	3	115	95.5	205	11.3	298	1,100	77
MJVD-6- 30	1.9	1	112	87.0	240	9.3	200	775	106
MJVD-6- 31	4.6	1	41	147.0	340	21.5	517	1,005	232
MJVD-6- 32	3.5	<1	66	85.0	235	16.6	395	885	92
MJVD-6- 33	3.1	5	77	81.5	355	15.4	419	1,055	151
MJVD-6- 34	5.7	7	71	102.0	375	26.6	714	1,105	167
MJVD-6- 35	2.2	3	83	53.0	245	12.4	247	480	371
MJVD-6- 36	3.6	<1	55	94.0	315	18.6	481	1,065	123
MJVD-6- 37	2.1	<1	30	90.0	130	10.7	235	640	45
MJVD-6- 38	3.9	4	42	71.0	150	17.2	440	745	264
MJVD-6- 39	3.8	2	36	103.5	130	18.4	460	550	173
MJVD-6- 40	7.1	2	44	181.5	155	34.8	793	855	246
MJVD-6- 41	4.9	<1	27	92.0	95	22.3	547	570	176
MJVD-6- 42	4.4	<1	98	99.5	155	20.0	584	1,485	208
MJVD-6- 43	4.0	2	125	77.5	390	20.0	485	2,110	37
MJVD-6- 44	4.3	3	26	79.0	175	19.6	552	795	164
MJVD-6- 45	4.9	2	30	70.5	140	23.0	549	900	519
MJVD-6- 46	4.9	2	25	45.5	125	21.3	608	530	304
MJVD-6- 47	3.7	<1	25	62.0	65	17.3	481	525	512
MJVD-6- 48	8.1	<1	34	91.5	130	41.1	975	480	107
MJVD-6- 49	3.7	7	57	58.0	190	18.2	416	730	187
MJVD-6- 50	8.8	<1	62	144.0	240	42.9	1080	1,070	401
MJVD-6- 51	4.6	1	44	111.5	130	23.2	519	415	577
MJVD-6- 52	6.5	<1	30	100.5	125	34.6	756	755	231
MJVD-6- 53	3.6	<1	30	74.0	95	16.4	378	540	140
MJVD-6- 54	6.7	<1	40	94.0	160	32.2	769	1,065	48
MJVD-6- 55	5.0	14	70	85.0	195	24.5	581	1,140	152
MJVD-6- 56	5.0	<1	37	83.5	220	24.6	560	1,680	43
MJVD-6- 57	3.6	<1	27	97.0	195	17.1	427	1,160	46

MJVD-6 (46/126)

Sample Name	Tm	Sn	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-6- 58	3.3	<1	31	101.0	165	15.4	419	960	99
MJVD-6- 59	2.1	<1	28	71.0	90	9.5	221	620	13
MJVD-6- 60	4.7	<1	67	138.0	175	23.5	585	1,405	33
MJVD-6- 61	3.5	<1	91	51.5	140	16.5	470	905	207
MJVD-6- 62	3.2	<1	185	71.0	120	15.6	411	920	62
MJVD-6- 63	1.8	<1	31	61.0	30	8.5	380	255	18
MJVD-6- 64	2.9	<1	34	71.0	45	13.8	628	140	33
MJVD-6- 65	1.9	4	21	72.5	85	9.5	406	295	43
MJVD-6- 66	2.9	5	17	83.5	70	14.0	392	300	60
MJVD-6- 67	3.1	7	28	62.5	50	16.0	405	355	30
MJVD-6- 68	5.5	8	41	127.5	125	25.2	551	530	214
MJVD-6- 69	3.5	5	28	59.0	75	18.5	509	400	25
MJVD-6- 70	3.9	1	61	198.5	45	18.5	764	310	118
MJVD-6- 71	2.6	3	24	87.0	40	13.3	601	430	39
MJVD-6- 72	1.9	4	25	101.5	35	11.0	393	360	83
MJVD-6- 73	2.9	4	17	120.0	175	14.7	549	545	102
MJVD-6- 74	2.7	4	50	196.5	55	16.0	509	585	21
MJVD-6- 75	2.3	5	36	61.5	60	9.9	361	415	111
MJVD-6- 76	4.7	3	115	143.0	125	24.0	546	1,445	333
MJVD-6- 77	4.0	<1	37	190.0	85	20.4	514	1,060	333
MJVD-6- 78	3.9	1	30	241.0	45	19.6	538	325	111
MJVD-6- 79	6.8	2	27	257.0	85	32.1	806	255	67
MJVD-6- 80	5.4	1	17	190.5	80	24.7	639	280	90
MJVD-6- 81	5.0	8	31	178.5	120	24.0	511	630	436
MJVD-6- 82	5.6	4	22	307.0	110	25.5	581	365	237
MJVD-6- 83	2.1	3	27	108.5	90	10.4	246	565	165
MJVD-6- 84	2.2	4	23	51.0	60	11.3	351	355	153
MJVD-6- 85	2.7	18	20	47.0	65	13.2	374	420	102
MJVD-6- 86	6.9	2	37	132.5	120	32.5	775	1,345	79
MJVD-6- 87	6.1	1	33	100.0	160	27.8	592	1,975	124
MJVD-6- 89	5.7	1	42	124.5	150	28.8	568	2,390	138
MJVD-6- 90	5.4	3	52	149.0	160	26.7	589	2,310	232
MJVD-6- 91	3.8	5	34	101.0	110	16.6	410	1,825	95
MJVD-6- 92	3.6	4	32	88.5	160	17.0	367	1,070	96
MJVD-6- 93	1.9	2	37	35.0	95	10.2	292	615	97
MJVD-6- 94	1.5	1	9	25.5	45	7.9	306	355	70
MJVD-6- 95	1.5	3	14	42.5	50	6.1	332	240	86
MJVD-6- 96	1.2	3	10	21.5	50	5.0	268	130	68
MJVD-6- 97	0.9	2	5	11.5	40	4.5	293	100	42
MJVD-6- 98	0.9	5	7	17.5	30	4.8	268	135	42
MJVD-6- 99	0.8	5	8	11.5	30.0	3.7	287.0	135	63
MJVD-6- 100	0.9	3	9	20.5	40	5.2	277	80	43

MJVD-7 (47/126)

Sample Name	Ba %	F %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm	Mo ppm
MJVD-7- 1	7.5	0.19	5.63	134	<10	<5.0	<10	0.11	0.5	117	8.32	<100	<1	0.07	0.07	6,320	28
MJVD-7- 2	8.5	0.16	5.28	146	<10	<5.0	<10	0.06	0.5	112	8.17	<100	<1	0.06	0.07	6,660	32
MJVD-7- 3	32.9	0.12	2.75	138	<10	<5.0	<10	0.09	0.5	70	5.65	<100	<1	0.04	0.04	6,650	20
MJVD-7- 4	38.5	0.14	1.17	254	<10	<5.0	<10	0.05	1.5	41	4.84	<100	<1	0.04	0.02	>10,000	17
MJVD-7- 5	25.4	0.25	1.51	194	<10	<5.0	<10	0.04	0.5	74	5.04	<100	<1	0.15	0.05	>10,000	52
MJVD-7- 6	1.3	0.30	1.65	146	<10	<5.0	<10	0.05	0.5	101	4.98	<100	<1	0.26	0.08	>10,000	5
MJVD-7- 7	2.2	0.32	1.42	254	<10	<5.0	<10	0.05	0.5	107	4.76	<100	<1	0.29	0.07	2,850	6
MJVD-7- 8	2.6	0.26	2.11	172	<10	<5.0	<10	0.04	1.0	105	4.49	<100	<1	0.18	0.06	2,520	4
MJVD-7- 9	37.3	0.32	0.78	400	<10	<5.0	<10	0.07	1.5	53	2.38	<100	<1	0.08	0.03	9,450	14
MJVD-7- 10	27.8	0.75	1.69	752	<10	5	<10	0.79	6.5	89	2.09	<100	<1	0.47	0.08	8,440	15
MJVD-7- 11	8.4	0.49	2.00	164	<10	10	<10	10.80	2.5	80	2.56	<100	<1	0.35	0.16	3,380	5
MJVD-7- 12	25.9	1.57	2.13	250	<10	10	<10	6.60	1.0	52	1.93	<100	<1	0.26	0.22	4,630	8
MJVD-7- 13	32.1	2.48	0.94	232	50	5	<10	6.26	1.0	35	1.35	<100	<1	0.21	0.09	4,580	8
MJVD-7- 14	21.9	5.04	1.94	348	60	10	<10	5.98	2.0	38	2.09	<100	<1	0.28	0.15	>10,000	13
MJVD-7- 15	33.7	2.55	0.52	460	360	5	<10	4.21	2.0	18	1.03	<100	<1	0.10	0.04	7,400	10
MJVD-7- 16	24.4	3.15	1.22	654	70	10	<10	5.07	2.0	29	1.79	<100	<1	0.20	0.10	8,970	15
MJVD-7- 17	40.2	1.33	0.24	150	160	<5.0	<10	5.97	1.5	15	0.71	<100	<1	0.05	0.02	2,800	6
MJVD-7- 18	27.1	2.56	0.74	526	60	<5.0	<10	8.40	1.5	22	1.19	<100	<1	0.16	0.07	4,500	9
MJVD-7- 19	23.4	5.38	0.97	740	460	5	<10	6.33	1.5	27	1.51	<100	<1	0.20	0.07	6,430	13
MJVD-7- 20	22.8	4.13	0.55	838	650	5	<10	5.28	2.5	21	1.40	<100	<1	0.17	0.05	5,880	13
MJVD-7- 21	27.0	8.50	0.69	302	1,310	<5.0	<10	9.76	2.0	20	0.79	<100	<1	0.20	0.04	4,210	6
MJVD-7- 22	26.3	4.57	1.47	330	160	5	<10	6.37	2.0	44	1.49	<100	<1	0.18	0.13	5,760	11
MJVD-7- 23	16.7	3.84	1.09	588	130	5	<10	10.95	2.5	27	1.08	<100	<1	0.13	0.11	6,020	10
MJVD-7- 24	5.7	1.63	0.10	368	440	<5.0	<10	>15.00	4.5	4	0.23	<100	<1	0.04	0.04	3,350	11
MJVD-7- 25	6.5	1.01	0.11	192	180	<5.0	<10	>15.00	4.0	6	0.50	<100	<1	0.04	0.05	3,770	12
MJVD-7- 26	10.3	2.80	0.12	296	710	<5.0	<10	>15.00	4.0	2	0.16	<100	<1	0.06	0.03	2,940	10
MJVD-7- 27	25.1	8.32	0.50	218	1,400	<5.0	<10	10.20	1.5	14	0.64	<100	<1	0.17	0.03	1,870	4
MJVD-7- 28	30.8	10.25	0.43	190	1,710	<5.0	<10	8.58	0.5	20	0.76	<100	<1	0.16	0.02	1,545	4
MJVD-7- 29	36.4	4.45	0.54	336	850	<5.0	<10	7.20	1.5	16	0.82	<100	<1	0.15	0.03	2,380	5
MJVD-7- 30	22.4	4.93	0.56	366	760	<5.0	<10	11.70	3.0	21	0.99	<100	<1	0.15	0.04	5,140	9
MJVD-7- 31	23.6	5.71	0.37	352	1,120	<5.0	<10	10.40	3.5	18	0.98	<100	<1	0.13	0.03	6,200	9
MJVD-7- 32	25.4	5.66	0.39	304	1,080	<5.0	<10	10.10	3.0	25	0.82	<100	<1	0.12	0.03	5,050	8
MJVD-7- 33	29.3	5.94	0.33	362	1,280	<5.0	<10	10.40	2.0	15	0.68	<100	<1	0.12	0.02	3,730	6
MJVD-7- 34	28.2	6.91	0.28	310	1,310	<5.0	<10	9.99	1.5	11	0.45	<100	<1	0.11	0.02	2,750	5
MJVD-7- 35	24.9	4.45	0.41	504	820	<5.0	<10	10.15	2.0	16	0.91	<100	<1	0.10	0.04	4,460	9
MJVD-7- 36	18.6	4.58	0.38	172	1,010	<5.0	<10	>15.00	1.5	16	0.86	<100	<1	0.13	0.06	1,750	12
MJVD-7- 37	8.9	2.43	0.16	86	640	<5.0	<10	>15.00	2.0	7	0.57	<100	1	0.08	0.06	2,340	10
MJVD-7- 38	2.8	0.79	0.10	34	120	<5.0	<10	>15.00	2.0	4	0.23	<100	<1	0.05	0.09	2,670	9
MJVD-7- 39	1.7	0.48	0.05	18	60	<5.0	<10	>15.00	0.5	7	0.18	<100	3	0.02	0.13	1,860	9
MJVD-7- 40	25.8	6.75	0.51	832	1,140	<5.0	<10	5.22	6.5	18	1.20	<100	<1	0.13	0.03	6,550	14
MJVD-7- 41	25.5	7.59	0.46	776	1,300	<5.0	<10	5.63	4.5	16	1.22	<100	<1	0.12	0.03	5,780	15
MJVD-7- 42	32.3	1.53	0.37	806	300	5	<10	1.41	10.5	20	1.20	<100	<1	0.06	0.03	7,710	16
MJVD-7- 43	33.9	1.12	0.57	760	20	10	<10	0.94	11.5	19	1.68	<100	<1	0.05	0.04	9,990	21
MJVD-7- 44	28.2	1.12	0.56	1110	<10	10	<10	0.52	21.5	26	1.52	<100	<1	0.05	0.03	7,640	23
MJVD-7- 45	24.4	1.37	0.67	1310	<10	15	<10	0.57	31.5	33	1.50	<100	<1	0.07	0.04	>10,000	24
MJVD-7- 46	25.0	1.69	1.34	1140	<10	10	<10	2.09	20.0	26	1.68	<100	<1	0.08	0.06	7,150	19
MJVD-7- 47	28.2	2.07	1.24	726	40	5	<10	3.66	13.5	77	1.81	<100	<1	0.23	0.09	9,980	20
MJVD-7- 48	6.4	1.40	3.88	346	<10	15	<10	2.71	2.5	617	3.52	<100	<1	0.71	0.19	2,430	7
MJVD-7- 49	21.8	6.98	1.63	548	290	5	<10	6.37	5.0	132	1.39	<100	<1	0.31	0.07	4,690	12
MJVD-7- 50	28.3	12.60	0.53	312	1,820	<5.0	<10	7.05	1.5	26	0.92	<100	<1	0.19	0.03	1,915	8
MJVD-7- 51	26.1	8.83	0.56	398	1,430	<5.0	<10	6.51	3.0	25	1.15	<100	<1	0.18	0.03	6,080	12
MJVD-7- 52	22.4	6.49	0.27	564	1,550	5	<10	7.06	7.5	23	1.49	<100	<1	0.14	0.03	>10,000	19
MJVD-7- 53	20.1	7.98	0.65	308	1,130	10	<10	6.62	19.0	46	2.54	<100	<1	0.28	0.15	>10,000	13
MJVD-7- 54	18.2	8.64	0.68	596	1,000	10	<10	6.87	16.5	40	2.00	<100	<1	0.31	0.20	>10,000	14
MJVD-7- 55	20.8	10.40	0.65	360	1,220	5	<10	8.99	10.0	39	1.51	<100	<1	0.25	0.12	8,470	9
MJVD-7- 56	23.6	2.50	0.31	96	370	<5.0	<10	14.90	3.0	19	0.53	<100	<1	0.10	0.12	4,210	1
MJVD-7- 62	18.6	5.12	0.44	150	800	<5.0	<10	>15.00	5.0	29	1.26	<100	<1	0.13	0.09	6,540	12

MJVD-7 (48/126)

Sample Name	Ba	F	Al	As	B	Be	Bi	Ca	Cd	Cr	Fe	Ga	Hg	K	Mg	Mn	Mo
	%	%	%	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	%	ppm	ppm
MJVD-7-63	4.7	1.14	0.18	170	120	5	<10	>15.00	2.5	4	0.37	<100	1	0.03	2.15	2,500	9
MJVD-7-64	11.7	2.49	1.12	230	50	5	<10	>15.00	2.5	25	1.13	<100	<1	0.21	0.16	5,490	11
MJVD-7-65	8.7	0.85	2.00	242	<10	10	<10	>15.00	2.5	50	2.34	<100	<1	0.15	0.39	9,440	15
MJVD-7-66	3.0	0.36	0.11	46	20	<5.0	<10	>15.00	1.5	1	0.19	<100	<1	0.03	0.91	2,010	9
MJVD-7-67	7.0	0.34	0.12	94	<10	<5.0	<10	>15.00	3.0	15	0.82	<100	<1	0.02	0.08	3,090	9
MJVD-7-68	15.1	3.49	0.68	162	30	<5.0	<10	>15.00	2.5	25	1.15	<100	<1	0.13	0.11	5,390	11
MJVD-7-69	10.1	0.72	0.08	64	30	<5.0	<10	>15.00	2.5	8	0.56	<100	<1	0.02	0.08	3,690	10
MJVD-7-70	4.0	0.44	0.13	118	<10	<5.0	<10	>15.00	2.0	4	0.39	<100	<1	0.04	0.10	3,100	10
MJVD-7-71	12.9	0.97	0.28	256	20	<5.0	<10	>15.00	2.0	10	0.46	<100	<1	0.07	0.08	3,080	9
MJVD-7-72	13.0	3.05	0.67	352	40	<5.0	<10	>15.00	2.0	21	0.85	<100	<1	0.14	0.22	2,860	12
MJVD-7-73	4.5	0.96	0.32	242	10	<5.0	<10	>15.00	1.5	13	0.37	<100	1	0.06	0.12	2,980	10
MJVD-7-74	7.0	0.31	0.21	88	<10	<5.0	<10	>15.00	1.5	9	0.26	<100	<1	0.04	0.10	3,140	7
MJVD-7-75	6.2	0.41	0.13	192	10	<5.0	<10	>15.00	1.5	9	0.20	<100	<1	0.04	0.06	3,100	7
MJVD-7-76	7.5	0.72	0.16	82	110	<5.0	<10	>15.00	1.5	6	0.31	<100	<1	0.04	0.09	3,230	7
MJVD-7-77	6.5	0.34	0.08	108	30	<5.0	<10	>15.00	2.0	9	0.31	<100	<1	0.02	0.08	2,610	9
MJVD-7-78	11.2	0.90	0.17	248	210	<5.0	<10	>15.00	1.5	8	0.36	<100	<1	0.05	0.06	2,420	9
MJVD-7-79	7.8	0.34	0.06	52	70	<5.0	<10	>15.00	1.0	4	0.17	<100	<1	0.01	0.10	2,730	9
MJVD-7-80	15.7	0.39	0.11	108	20	<5.0	<10	>15.00	1.5	7	0.58	<100	<1	0.03	0.07	2,590	9
MJVD-7-81	3.6	0.36	0.08	56	90	<5.0	<10	>15.00	1.5	2	0.21	<100	<1	0.03	0.11	3,840	30
MJVD-7-82	14.2	0.46	0.09	88	60	<5.0	<10	>15.00	1.0	3	0.59	<100	<1	0.04	0.11	2,860	21
MJVD-7-83	16.7	2.52	0.41	136	250	<5.0	<10	>15.00	2.5	18	0.41	<100	<1	0.10	0.10	2,730	9
MJVD-7-84	11.1	1.62	0.37	180	70	<5.0	<10	>15.00	1.5	14	0.58	<100	<1	0.11	0.15	2,960	10
MJVD-7-85	19.7	3.64	0.83	640	190	<5.0	<10	10.90	2.5	21	0.76	<100	<1	0.24	0.08	3,950	9
MJVD-7-86	13.9	3.17	0.75	330	100	<5.0	<10	>15.00	2.5	22	0.80	<100	<1	0.21	0.13	4,740	12
MJVD-7-87	7.0	0.69	0.12	56	150	<5.0	<10	>15.00	1.0	5	0.27	<100	1	0.04	0.14	2,860	7
MJVD-7-88	16.2	2.65	0.41	190	310	<5.0	<10	>15.00	2.0	17	0.84	<100	<1	0.11	0.07	2,580	9
MJVD-7-89	9.9	0.86	0.08	172	160	<5.0	<10	>15.00	0.5	11	0.42	<100	<1	0.03	0.08	2,380	8
MJVD-7-90	11.3	0.68	0.09	290	190	<5.0	<10	>15.00	3.5	12	0.66	<100	<1	0.03	0.08	2,690	10
MJVD-7-91	5.7	2.93	0.17	104	560	<5.0	<10	>15.00	2.0	13	1.15	<100	<1	0.07	0.07	3,980	10
MJVD-7-92	5.4	5.29	0.16	138	920	<5.0	<10	>15.00	2.0	10	0.76	<100	<1	0.08	0.05	2,770	11
MJVD-7-93	6.7	5.78	0.23	370	960	<5.0	<10	>15.00	2.5	7	0.53	<100	<1	0.11	0.05	1,995	5
MJVD-7-94	9.3	1.66	0.55	386	70	<5.0	<10	>15.00	1.0	13	0.66	<100	<1	0.16	0.15	2,530	11
MJVD-7-95	19.4	2.69	0.63	228	120	<5.0	<10	14.40	2.5	19	1.01	<100	1	0.16	0.08	2,570	5
MJVD-7-96	12.6	1.21	0.68	282	50	<5.0	<10	>15.00	2.5	16	0.94	<100	<1	0.17	0.08	3,060	4
MJVD-7-97	6.2	1.41	0.25	174	310	<5.0	<10	>15.00	1.5	7	0.35	<100	<1	0.09	0.14	2,600	12
MJVD-7-98	14.5	2.86	0.57	250	230	<5.0	<10	14.75	1.5	10	0.59	<100	<1	0.20	1.92	2,310	1
MJVD-7-99	27.7	6.25	0.97	382	670	<5.0	<10	8.56	1.5	23	1.16	<100	<1	0.26	0.05	2,280	6
MJVD-7-100	7.9	1.42	0.30	134	310	<5.0	<10	>15.00	1.5	9	0.55	<100	<1	0.10	0.14	2,710	14

MJVD-7 (49/126)

Sample Name	Na	P	S	Sb	Sc	Ti	Ce	Cs	Co	Cu	Dy	Er	Eu	Gd	Hf	Ho
	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-7- 1	<0.01	1,860	0.08	40	<20	0.02	13,770	6.9	24.5	105	18.2	12.9	<75.0	42	6	3.8
MJVD-7- 2	<0.01	2,040	0.07	40	<20	0.01	13,890	6.1	22.0	95	22.3	14.5	<80.0	53	5	4.1
MJVD-7- 3	<0.01	2,060	0.06	36	<20	0.01	11,190	3.1	14.0	100	24.6	16.0	<350	77	4	4.1
MJVD-7- 4	<0.01	4,000	0.05	36	<20	0.01	10,160	1.5	9.5	205	68.0	39.9	<450	212	3	11.6
MJVD-7- 5	<0.01	2,660	0.03	16	<20	<0.01	5,270	5.9	18.0	140	51.6	30.7	<250	152	3	8.9
MJVD-7- 6	<0.01	1,350	0.05	6	20	<0.01	1,780	9.7	26.5	120	45.9	27.2	60	146	5	7.8
MJVD-7- 7	<0.01	1,610	0.05	12	20	<0.01	1,040	8.4	34.5	115	32.6	19.1	40	94	6	5.9
MJVD-7- 8	<0.01	3,430	0.03	4	20	0.01	855	7	25.0	100	27.1	17.1	40	86	6	5.3
MJVD-7- 9	<0.01	1,890	0.04	52	<20	0.01	19,890	1	9.0	120	89.5	55.1	<450	322	3	15.1
MJVD-7- 10	0.01	1,970	0.04	36	<20	<0.01	50,800	2.8	11.5	160	107.5	81.0	<350	533	3	17.8
MJVD-7- 11	<0.01	1,640	0.04	26	<20	0.01	5,880	6	14.5	75	24.2	17.1	<80.0	90	2	4.3
MJVD-7- 12	0.01	1,050	0.03	30	<20	0.03	12,720	3.8	9.0	65	34.6	26.1	<250	150	3	5.7
MJVD-7- 13	0.03	1,210	0.05	16	<20	0.01	12,490	1.1	4.0	60	33.6	24.3	<300	159	2	5.6
MJVD-7- 14	0.03	1,520	0.05	44	<20	0.03	20,300	2.9	11.0	95	52.3	35.1	<250	227	2	8.6
MJVD-7- 15	0.06	980	0.04	28	<20	<0.01	28,900	0.9	4.0	80	55.8	43.3	<400	300	4	8.9
MJVD-7- 16	0.04	1,550	0.04	44	<20	0.01	43,600	2.1	6.5	130	84.8	63.7	<300	443	3	12.9
MJVD-7- 17	0.03	620	0.05	18	<20	<0.01	7,320	0.5	2.0	40	21.5	15.2	<400	96	3	3.4
MJVD-7- 18	0.03	940	0.06	38	<20	0.01	36,000	1.6	4.0	75	54.4	45.8	<300	322	3	8.1
MJVD-7- 19	0.09	1,230	0.04	46	<20	0.01	53,000	1.8	5.0	90	84.8	69.7	<250	471	2	14.0
MJVD-7- 20	0.11	880	0.05	42	<20	<0.01	56,300	0.6	3.5	75	87.1	71.8	<250	497	2	13.6
MJVD-7- 21	0.19	400	0.05	28	<20	<0.01	18,460	0.5	3.0	60	49.6	30.5	<250	192	3	8.5
MJVD-7- 22	0.04	1,130	0.06	54	<20	0.01	20,000	1.7	7.5	85	62.4	39.5	<250	257	2	10.0
MJVD-7- 23	0.04	1,100	0.04	42	<20	0.01	39,800	1.4	6.5	85	73.2	57.3	150	387	1	11.8
MJVD-7- 24	0.08	580	0.04	8	<20	<0.01	25,200	0.1	2.0	45	41.2	34.1	50	210	<1	6.9
MJVD-7- 25	0.04	1,220	0.05	16	<20	<0.01	10,550	0.3	1.5	45	34.6	24.1	<75.0	127	<1	6.4
MJVD-7- 26	0.11	600	0.06	10	<20	<0.01	20,500	0.2	1.0	40	39.1	29.6	<100.0	184	1	6.4
MJVD-7- 27	0.19	490	0.06	20	<20	<0.01	11,830	0.4	2.0	45	30.6	22.3	<350	128	3	4.8
MJVD-7- 28	0.24	780	0.06	18	<20	<0.01	9,700	0.4	2.0	40	24.9	17.0	<350	114	3	3.7
MJVD-7- 29	0.12	580	0.06	20	<20	<0.01	19,650	0.5	2.5	40	33.4	28.7	<350	190	2	5.6
MJVD-7- 30	0.12	1,290	0.04	42	<20	<0.01	24,800	0.5	3.5	90	55.3	41.8	<250	264	2	8.8
MJVD-7- 31	0.16	1,340	0.05	54	<20	<0.01	22,400	0.4	4.0	90	53.9	41.6	<250	256	2	9.4
MJVD-7- 32	0.16	1,540	0.05	42	<20	<0.01	20,200	0.3	2.5	75	51.5	35.6	<250	232	1	8.1
MJVD-7- 33	0.18	850	0.05	30	<20	<0.01	24,800	0.3	2.5	70	48.9	36.7	<300	254	4	7.6
MJVD-7- 34	0.19	700	0.05	18	<20	<0.01	21,000	0.3	2.0	50	41.7	32.7	<300	216	2	6.6
MJVD-7- 35	0.12	1,420	0.06	30	<20	<0.01	33,100	0.6	4.0	60	61.2	45.8	<250	314	2	10.1
MJVD-7- 36	0.14	970	0.06	18	<20	<0.01	9,820	0.5	2.5	45	29.7	18.9	<200	136	1	4.7
MJVD-7- 37	0.10	420	0.06	20	<20	<0.01	5,790	0.2	1.5	40	21.0	14.2	<80.0	84	<1	3.7
MJVD-7- 38	0.03	2,530	0.05	10	<20	<0.01	2,440	0.3	1.0	35	18.8	11.0	20	55	<1	3.5
MJVD-7- 39	0.02	190	0.06	2	<20	<0.01	781	0.2	1.0	20	10.3	5.9	10	21	<1	2.1
MJVD-7- 40	0.18	1,660	0.04	40	<20	<0.01	64,100	0.3	3.5	80	93.7	81.9	275	589	2	14.0
MJVD-7- 41	0.18	1,640	0.04	38	<20	<0.01	65,400	0.5	2.5	85	94.4	83.7	275	595	2	14.4
MJVD-7- 42	0.05	1,980	0.03	44	<20	<0.01	56,900	0.3	3.5	85	91.1	77.8	<300	509	2	14.2
MJVD-7- 43	0.01	2,710	0.03	56	<20	0.01	47,300	0.5	4.5	105	86.5	72.1	<300	468	2	14.3
MJVD-7- 44	<0.01	2,570	0.03	52	<20	0.01	80,600	0.7	4.0	80	133.0	107.5	300	772	2	21.3
MJVD-7- 45	<0.01	2,840	0.01	64	<20	0.01	99,000	0.7	6.0	105	150.5	130.0	400	926	2	23.0
MJVD-7- 46	0.01	2,500	0.04	54	<20	0.01	84,400	0.7	7.0	115	113.0	102.0	300	717	2	16.9
MJVD-7- 47	0.01	2,510	0.03	60	<20	0.01	47,100	2.2	6.5	140	87.6	69.9	<350	462	3	14.0
MJVD-7- 48	<0.01	3,570	0.06	42	<20	0.01	8,860	15.1	45.0	145	25.1	18.2	<60.0	102	5	4.0
MJVD-7- 49	0.06	1,500	0.06	38	<20	0.01	35,700	2.5	11.5	115	67.0	54.2	<350	346	2	10.8
MJVD-7- 50	0.25	370	0.05	20	<20	<0.01	19,990	0.5	1.5	35	46.3	34.6	<300	236	2	7.8
MJVD-7- 51	0.21	1,540	0.04	36	<20	<0.01	26,100	0.7	3.0	65	70.5	49.9	<300	302	2	11.7
MJVD-7- 52	0.22	3,760	0.03	54	<20	0.01	46,000	0.2	4.5	95	139.0	89.1	250	527	1	23.0
MJVD-7- 53	0.15	3,870	0.03	46	<20	0.01	14,730	0.7	4.5	75	75.6	48.0	<200	237	2	13.2
MJVD-7- 54	0.15	3,470	0.03	58	<20	0.01	41,200	0.9	5.5	85	102.5	73.7	200	454	2	17.1
MJVD-7- 55	0.17	2,500	0.04	40	<20	<0.01	24,100	0.7	4.5	75	75.7	52.4	<200	293	3	12.7
MJVD-7- 56	0.06	1,310	0.07	20	<20	<0.01	5,290	0.4	1.5	45	27.0	15.9	<250	88	1	4.7
MJVD-7- 62	0.12	1,410	0.06	30	<20	<0.01	8,920	0.9	3.5	85	43.7	29.6	<250	152	1	7.6

MJVD-7 (50/126)

Sample Name	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm	Ho ppm
MJVD-7-63	0.03	550	0.06	8	<20	<0.01	11,260	0.2	1.5	30	24.9	22.1	40	119	<1	4.2
MJVD-7-64	0.03	1,100	0.07	30	<20	0.01	14,000	2.6	6.5	75	45.1	32.0	<100.0	178	1	7.9
MJVD-7-65	0.01	1,900	0.03	48	<20	0.04	5,570	3.7	15.0	80	22.6	16.1	<60.0	75	2	4.4
MJVD-7-66	0.02	260	0.06	4	<20	<0.01	2,920	0.3	1.0	20	18.4	10.7	<30.0	52	<1	3.1
MJVD-7-67	0.01	410	0.02	24	<20	<0.01	4,410	0.3	1.5	70	22.9	14.8	<60.0	71	<1	4.4
MJVD-7-68	0.03	860	0.02	30	<20	<0.01	8,230	0.9	9.0	70	28.7	19.7	<150.0	103	2	5.1
MJVD-7-69	0.01	870	0.02	16	<20	<0.01	3,440	0.1	1.0	55	22.0	13.4	<200	62	1	4.1
MJVD-7-70	0.01	1,090	0.03	16	<20	<0.01	7,160	0.4	1.5	35	26.3	19.7	30	94	<1	4.6
MJVD-7-71	0.02	1,000	0.03	14	<20	<0.01	15,160	0.4	1.5	45	30.4	25.2	<125.0	156	<1	5.1
MJVD-7-72	0.03	640	0.03	16	<20	<0.01	27,500	0.7	3.0	50	38.6	34.2	<125.0	232	1	6.0
MJVD-7-73	0.02	450	0.06	14	<20	<0.01	18,080	0.4	2.0	35	30.1	25.8	40	156	<1	5.1
MJVD-7-74	0.01	750	0.05	10	<20	<0.01	5,400	0.5	1.5	50	26.1	16.8	<60.0	82	<1	4.5
MJVD-7-75	0.01	790	0.05	12	<20	<0.01	13,210	0.4	1.0	50	38.8	29.2	60	167	<1	6.8
MJVD-7-76	0.03	1,250	0.06	12	<20	<0.01	5,470	0.4	1.0	40	25.7	16.2	<70.0	83	<1	4.6
MJVD-7-77	0.01	1,010	0.06	14	<20	<0.01	6,990	<0.1	2.0	50	25.9	18.2	<60.0	97	<1	5.0
MJVD-7-78	0.04	950	0.06	10	<20	<0.01	18,560	0.2	1.0	40	29.5	25.7	<100.0	174	<1	4.9
MJVD-7-79	0.03	2,270	0.07	10	<20	<0.01	3,070	0.2	1.0	35	20.7	12.8	<70.0	57	<1	3.6
MJVD-7-80	0.01	990	0.06	24	<20	<0.01	6,660	0.3	2.5	70	27.5	18.0	<150.0	99	<1	4.8
MJVD-7-81	0.03	1,610	0.1	14	<20	<0.01	3,840	0.1	0.5	45	35.0	20.3	30	101	<1	6.9
MJVD-7-82	0.03	2,480	0.08	28	<20	<0.01	4,780	0.1	1.5	65	19.4	12.8	<150.0	68	<1	3.5
MJVD-7-83	0.05	610	0.09	16	<20	<0.01	8,280	0.6	2.0	45	30.1	21.0	<150.0	114	1	5.3
MJVD-7-84	0.03	780	0.07	16	<20	<0.01	10,590	0.8	3.0	60	26.7	21.3	<100.0	121	<1	4.3
MJVD-7-85	0.05	870	0.07	22	<20	<0.01	46,200	1.2	4.0	75	60.1	57.6	<200	382	2	9.3
MJVD-7-86	0.04	1,790	0.08	26	<20	<0.01	22,700	1.5	3.0	75	42.1	36.0	<150.0	218	1	7.3
MJVD-7-87	0.05	2,610	0.07	10	<20	<0.01	3,420	0.2	0.5	55	19.7	12.0	<60.0	60	<1	3.7
MJVD-7-88	0.06	1,320	0.07	16	<20	<0.01	11,490	0.4	2.5	45	27.6	21.9	<150.0	133	1	5.0
MJVD-7-89	0.04	1,090	0.06	12	<20	<0.01	11,350	<0.1	1.5	35	35.3	23.9	<100.0	142	<1	5.7
MJVD-7-90	0.05	2,820	0.07	16	<20	<0.01	19,690	0.1	1.0	40	39.8	31.4	<100.0	191	<1	7.2
MJVD-7-91	0.10	1,820	0.08	22	<20	<0.01	6,470	0.2	2.0	55	33.7	21.3	50	107	<1	6.4
MJVD-7-92	0.16	1,140	0.07	18	<20	<0.01	8,890	<0.1	1.5	60	28.8	21.3	50	108	<1	5.3
MJVD-7-93	0.17	520	0.06	22	<20	<0.01	30,200	0.3	1.5	30	54.2	42.7	120	277	<1	8.6
MJVD-7-94	0.03	430	0.06	10	<20	<0.01	30,000	1.5	2.0	45	43.8	41.6	80	269	<1	7.4
MJVD-7-95	0.03	570	0.07	16	<20	<0.01	14,530	0.7	2.5	50	29.5	25.6	<200	157	1	5.2
MJVD-7-96	0.03	850	0.04	14	<20	<0.01	22,700	0.9	2.5	20	43.3	35.1	<150.0	218	1	6.8
MJVD-7-97	0.06	790	0.06	14	<20	<0.01	24,300	1.1	5.0	30	62.8	47.6	<150.0	280	3	11.1
MJVD-7-98	0.06	660	0.07	8	<20	<0.01	14,640	0.8	1.5	40	32.2	24.2	<150.0	145	1	5.7
MJVD-7-99	0.11	720	0.05	16	<20	<0.01	21,000	0.7	3.5	45	39.0	31.2	<300	198	3	6.6
MJVD-7-100	0.06	700	0.08	20	<20	<0.01	7,790	0.4	1.5	35	28.7	19.6	<70.0	105	<1	5.0

MJVD-7 (51/126)

Sample Name	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-7- 1	2,190	2,560	0.6	695	10	370	234	42.6	103	<1	1,550	1.0	6.7	3.5	165	1.1	3
MJVD-7- 2	2,530	2,390	0.7	863	15	372	285	42.8	124	<1	1,605	1.0	8.2	4.0	164	1.1	2
MJVD-7- 3	3,490	3,020	0.7	1,340	10	294	439	26.6	261	<1	3,060	1.0	9.3	2.5	98	1.1	3
MJVD-7- 4	7,900	3,900	1.8	3,470	50	475	1,095	28.2	539	<1	3,570	4.0	23.4	2.0	103	2.3	1
MJVD-7- 5	5,480	2,870	1.3	2,510	20	165	754	82.8	372	<1	2,550	<0.5	16.6	2.5	62	2.2	1
MJVD-7- 6	4,850	665	1.3	2,370	45	36	678	170.0	269	<1	530	<0.5	15.2	5.0	175	2.1	2
MJVD-7- 7	3,860	815	1.0	1,525	45	53	456	174.0	166	<1	806	<0.5	10.0	5.5	31	1.5	3
MJVD-7- 8	3,320	410	0.8	1,370	45	30	407	110.0	151	<1	522	<0.5	8.6	3.5	31	1.3	2
MJVD-7- 9	16,130	4,000	1.9	5,880	10	163	1,810	15.2	743	<1	4,190	<0.5	34.1	1.5	58	3.3	<1
MJVD-7- 10	36,100	3,400	1.9	12,010	15	174	3,880	54.0	1,140	<1	2,700	0.5	56.0	2.0	112	3.1	<1
MJVD-7- 11	4,020	1,645	0.6	1,545	10	90	488	78.4	189	<1	1,945	<0.5	9.4	2.5	46	1.1	1
MJVD-7- 12	8,980	955	1.0	3,260	10	85	1,055	36.6	384	<1	3,790	<0.5	16.1	1.5	51	1.4	<1
MJVD-7- 13	8,760	870	0.5	3,270	10	113	1,045	18.8	423	<1	4,700	0.5	16.5	1.5	48	1.2	<1
MJVD-7- 14	12,850	3,110	1.2	4,820	10	161	1,515	28.4	513	<1	4,240	<0.5	23.2	5.0	60	1.7	<1
MJVD-7- 15	20,500	1,405	1.0	6,680	5	171	2,150	9.4	740	<1	5,690	2.5	31.3	2.5	53	1.8	<1
MJVD-7- 16	31,100	3,100	1.4	9,870	5	157	3,240	19.2	971	<1	4,640	1.0	47.3	3.5	88	2.6	1
MJVD-7- 17	5,060	855	0.5	1,855	5	73	597	6.0	319	<1	5,180	<0.5	9.7	0.5	21	0.7	1
MJVD-7- 18	26,300	1,780	0.9	8,020	5	198	2,610	14.4	723	<1	4,660	<0.5	32.8	2.5	60	1.7	<1
MJVD-7- 19	38,300	2,500	1.3	11,420	5	163	3,770	15.2	978	<1	4,740	<0.5	50.9	2.5	138	2.6	<1
MJVD-7- 20	41,700	3,170	1.2	12,050	<5	167	4,010	10.2	1,035	<1	4,820	<0.5	53.9	1.5	119	2.5	<1
MJVD-7- 21	12,230	2,460	0.8	3,940	<5	39	1,320	9.0	441	<1	5,020	0.5	21.2	0.5	49	1.6	2
MJVD-7- 22	12,430	3,920	1.1	4,880	5	111	1,525	16.4	584	<1	4,610	<0.5	27.0	1.0	80	1.9	2
MJVD-7- 23	28,600	4,380	1.1	8,750	5	84	2,870	12.6	796	<1	3,430	<0.5	40.4	2.0	88	2.2	1
MJVD-7- 24	18,410	1,235	0.8	5,470	<5	30	1,795	1.8	436	<1	1,735	<0.5	23.5	0.5	34	1.5	1
MJVD-7- 25	7,960	2,040	0.8	2,480	<5	82	833	3.4	242	<1	2,000	<0.5	13.9	0.5	19	1.3	<1
MJVD-7- 26	13,720	1,500	0.8	4,370	<5	31	1,470	2.6	388	<1	2,670	<0.5	20.8	<0.5	29	1.6	<1
MJVD-7- 27	8,430	930	0.6	2,860	<5	41	932	8.8	368	<1	4,710	0.5	13.6	<0.5	34	0.9	6
MJVD-7- 28	6,950	910	0.5	2,460	<5	58	791	6.0	344	<1	5,130	0.5	11.3	<0.5	33	0.7	3
MJVD-7- 29	12,720	1,505	0.6	4,340	<5	51	1,415	9.8	515	<1	4,630	1.0	19.4	<0.5	40	1.0	44
MJVD-7- 30	17,250	2,710	0.9	5,680	<5	169	1,825	9.4	598	<1	3,950	<0.5	28.5	1.0	66	2.0	<1
MJVD-7- 31	13,860	3,160	0.9	5,290	<5	193	1,660	4.6	592	<1	3,900	<0.5	27.3	1.0	69	1.9	<1
MJVD-7- 32	12,430	2,430	0.8	4,730	<5	250	1,500	5.2	538	<1	4,170	1.0	23.8	1.0	62	1.7	1
MJVD-7- 33	17,350	1,995	0.8	5,710	<5	92	1,830	4.4	614	<1	4,430	1.0	26.7	0.5	60	1.7	<1
MJVD-7- 34	13,030	1,875	0.8	4,790	<5	66	1,550	3.2	526	<1	4,460	1.0	22.6	0.5	49	1.2	2
MJVD-7- 35	23,500	1,900	1.0	7,330	<5	167	2,360	5.2	715	<1	4,160	<0.5	33.7	0.5	61	1.8	<1
MJVD-7- 36	6,550	685	0.6	2,650	<5	183	812	7.2	339	<1	3,400	<0.5	13.5	<0.5	46	1.0	<1
MJVD-7- 37	3,600	910	0.5	1,655	<5	118	501	4.4	191	<1	2,410	<0.5	8.5	<0.5	17	1.1	<1
MJVD-7- 38	1,475	655	0.5	757	<5	65	222	5.8	103	<1	2,450	<0.5	5.5	<0.5	8	0.8	1
MJVD-7- 39	456	290	0.3	240	5	5	68	2.8	39	<1	2,710	<0.5	2.7	<0.5	1	0.5	2
MJVD-7- 40	45,100	2,300	1.2	14,590	<5	181	4,750	5.6	1,270	<1	4,260	0.5	60.7	2.0	95	2.6	2
MJVD-7- 41	46,500	2,620	1.3	14,990	<5	161	4,890	3.8	1,310	<1	4,460	0.5	61.3	1.5	95	2.8	1
MJVD-7- 42	40,700	2,760	1.4	12,650	<5	281	4,150	6.0	1,140	<1	3,700	1.5	54.5	2.0	85	2.9	2
MJVD-7- 43	34,000	3,110	1.5	10,740	<5	455	3,510	6.8	1,030	<1	3,840	2.5	48.7	2.5	70	3.0	1
MJVD-7- 44	56,700	3,000	1.8	18,290	5	265	5,940	5.4	1,655	<1	3,450	1.0	81.8	2.5	158	3.4	2
MJVD-7- 45	70,400	3,510	2.2	22,200	10	318	7,170	6.2	1,940	<1	2,840	1.0	96.1	4.0	274	4.1	1
MJVD-7- 46	59,600	2,850	1.6	18,500	5	216	6,040	8.0	1,525	<1	3,550	1.0	77.0	2.5	113	3.2	1
MJVD-7- 47	32,900	3,520	1.3	10,730	30	268	3,490	18.2	1,035	<1	4,890	2.0	49.7	3.0	71	2.6	2
MJVD-7- 48	6,200	1,620	0.7	2,210	145	132	713	119.0	213	<1	2,380	<0.5	11.0	2.5	36	0.9	5
MJVD-7- 49	24,800	1,655	1.1	7,980	35	141	2,580	24.2	781	<1	4,850	0.5	35.8	1.5	62	2.3	3
MJVD-7- 50	11,950	960	0.6	5,010	5	38	1,545	6.4	603	<1	5,340	0.5	24.2	0.5	59	1.7	3
MJVD-7- 51	17,550	2,210	1.2	6,340	<5	187	1,960	11.2	696	<1	5,270	<0.5	31.8	1.0	61	2.5	3
MJVD-7- 52	32,500	4,050	2.4	10,600	5	424	3,410	6.6	1,065	<1	4,440	1.5	56.6	2.5	96	5.1	3
MJVD-7- 53	9,900	2,620	1.6	4,070	<5	213	1,255	17.6	497	<1	4,540	2.5	25.6	1.5	52	3.1	4
MJVD-7- 54	28,500	2,180	1.8	9,580	5	260	3,040	20.2	909	<1	4,290	1.0	48.8	2.0	105	3.7	2
MJVD-7- 55	16,410	1,950	1.4	5,700	<5	238	1,760	16.4	635	<1	4,650	0.5	32.0	1.5	72	3.0	4
MJVD-7- 56	3,440	605	0.5	1,470	5	152	442	6.4	244	<1	4,200	<0.5	9.4	<0.5	18	1.0	2
MJVD-7- 62	5,710	1,175	1.0	2,540	5	228	772	9.4	365	<1	4,400	<0.5	16.8	0.5	31	1.8	2

MJVD-7 (52/126)

Sample Name	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th	Tm	Sn
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-7-63	7,990	725	0.6	2,820	<5	55	904	4.4	246	<1	3,900	<0.5	13.0	<0.5	17	1.0	1
MJVD-7-64	9,710	1,660	0.9	3,560	10	128	1,145	25.2	368	<1	3,430	<0.5	19.0	1.5	39	1.7	2
MJVD-7-65	3,800	3,180	0.6	1,375	25	48	447	23.4	158	<1	2,430	<0.5	8.5	1.0	18	1.1	2
MJVD-7-66	1,825	605	0.4	819	<5	15	244	3.6	104	<1	4,460	<0.5	6.4	<0.5	14	0.7	3
MJVD-7-67	3,040	1,295	0.6	1,170	<5	26	367	2.6	146	<1	3,190	<0.5	8.1	<0.5	9	1.1	1
MJVD-7-68	5,610	1,345	0.5	2,150	5	81	683	13.0	261	<1	3,850	<0.5	11.5	1.0	25	1.1	1
MJVD-7-69	2,130	1,175	0.6	1,005	<5	73	299	3.4	186	<1	3,130	<0.5	7.0	0.5	3	1.1	2
MJVD-7-70	4,970	1,705	0.5	1,835	<5	192	592	4.6	181	<1	3,710	<0.5	10.9	<0.5	8	1.0	1
MJVD-7-71	10,890	910	0.6	3,660	<5	119	1,235	8.2	338	<1	4,460	<0.5	17.9	<0.5	18	1.2	<1
MJVD-7-72	19,420	1,055	0.5	6,080	<5	58	1,990	14.0	495	<1	4,250	<0.5	25.0	<0.5	34	1.1	<1
MJVD-7-73	11,610	1,040	0.6	3,940	<5	47	1,325	6.8	326	<1	5,200	<0.5	17.2	<0.5	21	1.1	<1
MJVD-7-74	3,630	990	0.6	1,435	<5	41	449	7.0	172	<1	3,980	<0.5	9.0	<0.5	9	1.1	<1
MJVD-7-75	9,090	1,285	0.7	3,510	<5	45	1,130	5.4	342	<1	3,110	<0.5	18.4	<0.5	27	1.4	<1
MJVD-7-76	3,620	860	0.6	1,480	<5	136	464	4.4	183	<1	4,620	<0.5	9.4	0.5	10	1.1	<1
MJVD-7-77	4,800	1,685	0.6	1,800	<5	67	580	2.0	194	<1	4,100	<0.5	10.9	<0.5	9	1.3	<1
MJVD-7-78	11,890	665	0.5	4,200	<5	121	1,385	3.4	378	<1	4,260	<0.5	18.8	<0.5	25	1.0	<1
MJVD-7-79	2,000	520	0.5	843	<5	216	258	2.2	127	<1	4,840	<0.5	6.4	<0.5	1	1.0	<1
MJVD-7-80	4,520	1,055	0.5	1,760	<5	115	558	3.4	240	<1	4,990	<0.5	10.4	<0.5	10	1.2	<1
MJVD-7-81	2,400	1,670	0.7	1,170	<5	31	344	2.8	153	<1	10,290	<0.5	10.2	<0.5	6	1.8	<1
MJVD-7-82	3,280	1,415	0.5	1,245	<5	277	392	5.0	179	<1	11,300	<0.5	7.8	<0.5	5	0.8	<1
MJVD-7-83	5,610	885	0.6	2,170	<5	34	687	8.8	278	<1	9,900	<0.5	12.4	<0.5	13	1.2	<1
MJVD-7-84	7,450	1,450	0.5	2,690	<5	55	868	10.4	280	<1	6,220	<0.5	13.4	<0.5	13	1.0	<1
MJVD-7-85	32,900	1,875	0.8	10,120	<5	63	3,390	18.6	820	<1	5,500	<0.5	42.0	<0.5	51	1.6	<1
MJVD-7-86	16,040	2,730	0.8	5,100	<5	133	1,660	20.4	470	<1	6,620	<0.5	24.9	0.5	27	1.5	<1
MJVD-7-87	2,180	1,720	0.4	955	<5	9	293	4.4	130	<1	10,320	<0.5	6.4	<0.5	2	0.9	1
MJVD-7-88	7,970	970	0.6	2,940	<5	50	958	8.0	311	<1	4,350	<0.5	13.7	<0.5	18	1.2	3
MJVD-7-89	7,890	1,040	0.7	3,010	<5	75	958	2.0	306	<1	3,880	<0.5	16.3	<0.5	159	1.2	2
MJVD-7-90	12,360	2,230	0.8	4,540	<5	75	1,485	1.6	409	<1	7,370	<0.5	21.2	<0.5	28	1.5	<1
MJVD-7-91	4,300	1,755	0.7	1,785	<5	154	555	2.6	211	<1	5,450	<0.5	12.7	<0.5	13	1.5	<1
MJVD-7-92	6,410	1,900	0.6	2,190	<5	60	724	1.8	213	<1	4,190	<0.5	12.3	<0.5	11	1.3	<1
MJVD-7-93	21,500	2,190	0.8	6,670	<5	52	2,250	4.0	548	<1	3,360	<0.5	32	<0.5	34	1.6	2
MJVD-7-94	21,900	1,780	0.7	6,620	<5	43	2,200	14.4	546	<1	4,000	<0.5	30.5	<0.5	44	1.3	4
MJVD-7-95	10,300	895	0.7	3,610	<5	81	1,185	14.6	394	<1	4,440	<0.5	17.3	0.5	23	1.0	2
MJVD-7-96	16,030	1,295	0.8	5,200	<5	64	1,695	18.4	467	<1	3,530	<0.5	24.5	0.5	40	1.2	9
MJVD-7-97	17,320	1,165	1.2	6,040	20	102	2,010	15.6	563	<1	6,590	<0.5	31.4	1.0	45	1.9	21
MJVD-7-98	12,620	700	0.5	3,150	<5	67	1,105	12.0	303	<1	4,630	<0.5	16.3	<0.5	23	1.2	4
MJVD-7-99	18,360	930	0.7	4,470	<5	68	1,515	17.6	482	<1	5,350	1.0	22	<0.5	37	1.4	6
MJVD-7-100	5,850	1,075	0.6	1,925	<5	98	628	8.0	218	<1	3,730	<0.5	11.8	<0.5	13	1.1	3

MJVD-7 (53/126)

Sample Name	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-7- 1	102	67.5	395	6.1	98.1	770	282
MJVD-7- 2	97	71.5	390	6.4	110.5	790	277
MJVD-7- 3	58	66.5	275	5.9	115	795	138
MJVD-7- 4	41	125.5	255	12.3	329	1,455	96
MJVD-7- 5	33	71.5	170	10.5	244	680	138
MJVD-7- 6	55	37.0	215	9.9	223	485	230
MJVD-7- 7	100	36.0	180	7.5	158	645	229
MJVD-7- 8	59	16.5	210	5.9	145.5	425	252
MJVD-7- 9	46	72.0	160	18.7	360	700	46
MJVD-7- 10	58	143.0	220	16.8	511	1,290	64
MJVD-7- 11	77	34.5	100	5.6	137	1,730	114
MJVD-7- 12	68	41.5	100	7.7	182.5	1,810	83
MJVD-7- 13	49	46.0	60	6.2	164	1,200	37
MJVD-7- 14	183	63.5	90	9.9	242	2,230	83
MJVD-7- 15	90	74.5	65	9.3	241	1,445	38
MJVD-7- 16	157	95.5	125	13.4	348	2,080	79
MJVD-7- 17	24	30.0	35	3.8	95.4	595	22
MJVD-7- 18	78	103.0	40	9.4	222	1,145	37
MJVD-7- 19	106	131.5	45	13.5	367	1,620	61
MJVD-7- 20	59	136.0	65	12.7	368	1,455	33
MJVD-7- 21	40	40.0	50	8.6	274	825	27
MJVD-7- 22	106	63.0	65	11.3	334	1,625	85
MJVD-7- 23	96	79.5	40	10.8	335	1,225	47
MJVD-7- 24	37	43.0	20	9.2	168.5	225	7
MJVD-7- 25	20	33.5	40	7.1	146	450	43
MJVD-7- 26	27	42.5	35	7.4	175.5	230	8
MJVD-7- 27	38	30.0	80	5.3	191	450	25
MJVD-7- 28	22	29.5	45	3.4	180.5	345	23
MJVD-7- 29	29	41.5	35	5.3	171.5	580	62
MJVD-7- 30	59	71.5	40	9.7	280	1,005	30
MJVD-7- 31	69	69.5	35	9.6	289	1,070	31
MJVD-7- 32	58	82.0	25	7.6	263	1,000	19
MJVD-7- 33	41	55.5	30	7.5	250	835	48
MJVD-7- 34	33	45.0	25	6.5	208	685	31
MJVD-7- 35	49	88.0	25	8.2	260	980	16
MJVD-7- 36	23	50.5	35	4.8	158.5	480	15
MJVD-7- 37	17	35.0	25	4.0	107.5	475	9
MJVD-7- 38	9	24.0	15	4.1	90	285	<0.5
MJVD-7- 39	6	6.5	<5	2.1	53.1	105	12
MJVD-7- 40	77	126.5	60	14.3	379	1,425	229
MJVD-7- 41	78	117.0	60	16.0	387	1,305	25
MJVD-7- 42	78	126.5	55	14.3	401	1,675	30
MJVD-7- 43	75	143.5	60	14.7	392	1,835	35
MJVD-7- 44	84	166.5	55	20.4	585	1,565	35
MJVD-7- 45	116	197.5	90	22.5	590	2,270	56
MJVD-7- 46	129	150.5	130	16.1	481	2,320	28
MJVD-7- 47	142	110.0	60	12.9	357	3,530	53
MJVD-7- 48	117	39.5	130	5.6	122	2,100	206
MJVD-7- 49	89	76.5	60	12.2	325	1,345	59
MJVD-7- 50	27	41.0	5	7.0	336	550	29
MJVD-7- 51	55	90.0	50	11.9	359	1,250	21
MJVD-7- 52	87	179.0	60	25.9	587	2,750	30
MJVD-7- 53	53	88.0	75	16.4	332	5,170	37
MJVD-7- 54	56	134.5	65	18.1	469	4,530	37
MJVD-7- 55	50	98.5	55	14.9	407	3,010	40
MJVD-7- 56	24	48.0	30	5.5	132.5	1,025	7
MJVD-7- 62	46	75.5	65	9.3	235	1,860	17

MJVD-7 (54/126)

Sample Name	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-7-63	11	36.5	30	4.7	108.5	620	5
MJVD-7-64	58	59.5	50	9.9	213	1,595	53
MJVD-7-65	80	23.0	60	5.9	115	1,540	77
MJVD-7-66	5	12.5	35	4.4	90.9	185	8
MJVD-7-67	12	17.5	30	4.6	111.5	425	<0.5
MJVD-7-68	62	31.5	50	4.4	145.5	885	26
MJVD-7-69	23	20.5	40	4.4	95	560	<0.5
MJVD-7-70	11	59.0	10	4.7	117.5	375	<0.5
MJVD-7-71	17	46.0	5	4.8	129	450	8
MJVD-7-72	22	37.0	35	5.5	156.5	645	19
MJVD-7-73	13	34.5	20	4.6	121.5	385	2
MJVD-7-74	13	20.5	20	5.2	108.5	380	3
MJVD-7-75	16	32.5	25	6.8	162.5	365	2
MJVD-7-76	14	47.0	15	4.7	115	385	7
MJVD-7-77	7	36.0	85	5.1	114	300	7
MJVD-7-78	13	45.0	10	4.5	109.5	285	1
MJVD-7-79	9	63.0	15	4.1	85.5	295	12
MJVD-7-80	9	61.5	25	4.9	114.5	630	<0.5
MJVD-7-81	4	17.5	25	6.6	162	480	<0.5
MJVD-7-82	11	90.0	10	3.7	88.7	445	15
MJVD-7-83	13	33.5	25	5.4	149	430	11
MJVD-7-84	12	39.5	55	5.3	118	570	6
MJVD-7-85	31	105.0	35	8.1	231	845	21
MJVD-7-86	27	70.5	45	7.3	186.5	940	20
MJVD-7-87	7	12.5	25	3.8	90.5	335	4
MJVD-7-88	19	41.5	15	6.0	138	440	11
MJVD-7-89	7	58.0	35	5.9	134.5	230	<0.5
MJVD-7-90	12	53.5	25	6.6	168.5	505	<0.5
MJVD-7-91	14	45.0	30	6.9	150	730	7
MJVD-7-92	15	35.0	30	5.2	138.5	475	63
MJVD-7-93	10	64.5	65	6.6	212	545	16
MJVD-7-94	14	58.0	50	6.8	175	585	15
MJVD-7-95	27	48.0	60	4.6	137.5	735	11
MJVD-7-96	41	54.5	55	6.6	176.5	840	24
MJVD-7-97	42	75.0	115	9.6	253	690	33
MJVD-7-98	17	54.5	30	5.3	146.5	400	13
MJVD-7-99	31	58.5	45	5.6	197.5	565	33
MJVD-7-100	23	50.5	40	5.1	128	265	6

MJVD-8 (55/126)

Sample Name	F %	Ba %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm
MJVD-8-01	0.2	14.90	2.79	208	<10	5	10	0.32	0.5	91	10.25	<100	<1	0.03	0.06	8,430
MJVD-8-02	0.1	29.60	1.30	234	<10	10	10	0.13	0.5	75	9.06	<100	<1	0.02	0.04	8,100
MJVD-8-03	0.1	27.20	1.04	150	<10	5	10	0.12	0.5	69	9.11	<100	<1	0.03	0.04	>10,000
MJVD-8-04	0.1	27.20	0.96	244	<10	10	10	0.16	0.5	81	10.30	<100	<1	0.03	0.05	>10,000
MJVD-8-05	0.1	32.00	0.69	158	<10	5	10	0.12	0.5	57	6.82	<100	<1	0.03	0.03	>10,000
MJVD-8-06	0.1	30.30	0.73	172	<10	10	<10	0.08	1.5	63	7.36	<100	<1	0.03	0.04	>10,000
MJVD-8-07	0.1	32.20	0.62	220	<10	10	<10	0.08	1.5	45	6.71	<100	<1	0.03	0.03	>10,000
MJVD-8-08	0.1	32.60	0.43	240	<10	10	<10	0.09	2.5	27	6.12	<100	<1	0.03	0.03	>10,000
MJVD-8-09	0.1	30.10	0.59	236	<10	10	10	0.09	2.0	32	6.67	<100	<1	0.03	0.03	>10,000
MJVD-8-10	0.2	22.30	1.47	232	<10	15	<10	0.10	3.5	49	6.85	<100	<1	0.05	0.03	>10,000
MJVD-8-11	0.1	25.30	0.79	266	<10	10	<10	0.08	1.5	69	8.79	<100	<1	0.03	0.04	>10,000
MJVD-8-12	0.1	29.80	0.55	236	<10	10	10	0.08	1.5	56	10.35	<100	<1	0.03	0.05	>10,000
MJVD-8-13	0.5	35.60	0.32	646	<10	<5.0	<10	0.10	1.0	31	3.01	<100	<1	0.05	0.03	>10,000
MJVD-8-14	0.1	41.70	0.54	92	<10	<5.0	<10	0.05	0.5	25	4.01	<100	<1	0.04	0.01	9,760
MJVD-8-15	0.3	41.40	0.34	86	<10	<5.0	<10	0.08	0.5	12	2.38	<100	<1	0.04	0.02	7,550
MJVD-8-16	0.3	38.10	0.62	226	<10	<5.0	<10	0.08	2.5	17	3.31	<100	<1	0.08	0.04	>10,000
MJVD-8-17	0.1	46.50	0.26	48	<10	<5.0	<10	0.09	<0.5	8	1.45	<100	<1	0.03	0.03	4,380
MJVD-8-19	0.0	47.70	0.14	30	<10	<5.0	<10	0.10	<0.5	6	1.06	<100	<1	0.01	<0.01	2,060
MJVD-8-20	0.4	50.50	0.22	68	10	<5.0	<10	0.62	<0.5	8	1.15	<100	<1	0.04	0.01	4,360
MJVD-8-21	6.7	36.30	0.76	96	1,590	<5.0	<10	7.69	0.5	22	1.19	<100	<1	0.22	0.04	2,320
MJVD-8-22	2.6	41.50	0.75	150	340	<5.0	<10	3.60	<0.5	30	2.00	<100	<1	0.15	0.03	6,320
MJVD-8-23	0.1	44.60	0.22	152	10	<5.0	<10	0.10	<0.5	25	1.73	<100	<1	0.03	0.01	6,630
MJVD-8-24	0.3	36.60	0.49	410	<10	5	<10	0.09	1.0	65	8.21	<100	<1	0.06	0.04	9,980
MJVD-8-25	0.3	25.80	0.61	474	<10	5	<10	0.11	2.0	77	13.80	<100	<1	0.06	0.06	>10,000
MJVD-8-26	0.3	37.00	0.51	442	<10	<5.0	<10	0.06	1.5	29	6.45	<100	<1	0.10	0.04	>10,000
MJVD-8-27	0.4	41.80	0.26	358	<10	<5.0	<10	0.05	<0.5	13	2.21	<100	<1	0.04	0.01	3,500
MJVD-8-28	0.4	39.50	0.30	412	<10	<5.0	<10	0.08	0.5	13	1.92	<100	<1	0.05	0.01	3,450
MJVD-8-29	0.4	41.20	0.29	380	10	<5.0	<10	0.10	1.0	14	1.82	<100	1	0.03	0.01	8,310
MJVD-8-30	0.3	44.90	0.24	346	<10	<5.0	<10	0.06	0.5	16	2.45	<100	1	0.04	0.01	6,670
MJVD-8-31	0.3	44.80	0.25	324	<10	<5.0	<10	0.05	0.5	15	2.64	<100	1	0.04	<0.01	9,610
MJVD-8-32	0.0	43.20	0.16	110	<10	<5.0	<10	0.03	0.5	14	1.98	<100	1	0.01	<0.01	9,460
MJVD-8-33	0.0	45.40	0.20	116	<10	<5.0	<10	0.04	0.5	9	1.42	<100	2	0.01	<0.01	6,900
MJVD-8-34	0.0	40.90	0.18	110	<10	<5.0	<10	0.03	1.0	12	2.09	<100	4	0.01	<0.01	>10,000
MJVD-8-35	0.2	42.60	0.40	186	<10	<5.0	<10	0.05	0.5	12	1.09	<100	1	0.05	0.01	5,750
MJVD-8-36	0.7	39.80	0.41	442	<10	<5.0	<10	0.09	0.5	17	0.82	100	1	0.07	0.01	7,530
MJVD-8-37	0.0	42.30	0.16	66	<10	<5.0	<10	0.04	0.5	19	2.50	<100	2	0.01	<0.01	>10,000
MJVD-8-38	0.1	42.30	0.12	116	<10	<5.0	<10	0.04	1.0	17	1.29	<100	1	<0.01	<0.01	>10,000
MJVD-8-39	0.5	38.10	0.25	472	<10	<5.0	<10	0.06	<0.5	31	3.58	<100	<1	0.03	0.01	6,070
MJVD-8-40	0.1	38.70	0.67	80	<10	<5.0	<10	0.04	0.5	27	3.91	<100	5	0.04	0.01	>10,000
MJVD-8-41	0.6	37.80	0.29	548	30	<5.0	10	0.11	0.5	21	1.64	<100	4	0.05	<0.01	>10,000
MJVD-8-42	0.7	27.30	0.30	674	80	<5.0	20	0.08	0.5	23	3.35	<100	5	0.04	<0.01	>10,000
MJVD-8-43	0.5	31.60	0.43	484	<10	<5.0	30	0.08	1.0	27	5.31	<100	9	0.05	<0.01	>10,000
MJVD-8-44	0.5	30.90	0.26	564	<10	<5.0	30	0.07	1.0	21	5.11	<100	8	0.03	<0.01	>10,000
MJVD-8-45	0.4	35.90	0.18	416	10	<5.0	20	0.06	1.5	16	2.71	<100	4	0.03	<0.01	>10,000
MJVD-8-46	1.4	33.60	0.34	394	230	<5.0	<10	1.30	1.0	13	2.26	<100	3	0.08	<0.01	>10,000
MJVD-8-47	6.9	28.80	0.88	242	980	<5.0	10	5.14	0.5	19	1.96	<100	1	0.24	0.03	>10,000
MJVD-8-48	2.1	38.90	0.17	226	610	<5.0	<10	2.01	1.0	14	2.15	<100	2	0.06	<0.01	>10,000
MJVD-8-49	0.6	39.70	0.27	246	10	<5.0	<10	0.37	0.5	18	1.89	<100	3	0.06	0.01	>10,000
MJVD-8-50	0.6	33.50	0.61	390	<10	<5.0	10	0.27	1.0	29	3.10	<100	2	0.10	0.04	>10,000
MJVD-8-51	0.5	33.90	0.54	304	<10	<5.0	<10	0.18	1.0	26	2.53	<100	3	0.09	0.01	>10,000
MJVD-8-52	0.2	33.60	0.16	278	<10	<5.0	10	0.06	1.0	26	3.17	<100	3	0.02	<0.01	>10,000
MJVD-8-53	0.4	31.30	0.27	400	<10	<5.0	10	0.06	1.0	27	3.69	<100	4	0.04	<0.01	>10,000
MJVD-8-54	0.7	35.30	0.32	598	<10	<5.0	<10	0.08	1.0	16	1.78	<100	<1	0.06	<0.01	>10,000
MJVD-8-55	0.6	29.70	0.34	500	<10	<5.0	<10	0.08	1.5	31	3.04	<100	3	0.05	0.01	>10,000
MJVD-8-56	0.8	36.20	0.23	576	70	<5.0	<10	0.10	1.5	16	1.37	100	<1	0.05	<0.01	7,870
MJVD-8-57	4.0	24.50	1.67	458	90	<5.0	10	4.12	3.5	68	2.42	<100	2	0.47	0.11	9,760
MJVD-8-58	4.6	29.30	1.27	384	70	<5.0	10	2.99	3.0	30	2.54	<100	<1	0.34	0.05	>10,000

MJVD-8 (56/126)

Sample Name	F %	Ba %	Al %	As ppm	B ppm	Be ppm	Bi ppm	Ca %	Cd ppm	Cr ppm	Fe %	Ga ppm	Hg ppm	K %	Mg %	Mn ppm
MJVD-8-59	3.2	14.05	3.56	272	<10	5	<10	4.57	2.0	179	3.13	<100	1	1.52	0.73	4,720
MJVD-8-60	0.1	1.08	1.77	34	<10	5	<10	5.32	0.5	326	3.88	<100	<1	0.28	1.75	1,280
MJVD-8-61	0.3	1.54	1.65	40	<10	5	<10	3.03	<0.5	307	4.05	<100	<1	0.28	1.48	1,375
MJVD-8-62	0.2	0.73	1.84	18	<10	5	<10	2.18	<0.5	347	4.11	<100	<1	0.26	1.84	1,040
MJVD-8-63	0.2	1.23	2.03	24	<10	5	<10	1.36	<0.5	369	4.47	<100	<1	0.26	1.84	1,120
MJVD-8-64	0.2	0.83	1.85	22	<10	5	<10	1.71	0.5	324	4.18	<100	<1	0.24	1.70	1,005
MJVD-8-65	0.4	1.13	0.69	18	<10	<5.0	<10	9.77	2.0	59	2.70	<100	<1	0.20	0.14	1,070
MJVD-8-66	0.3	2.31	0.55	50	<10	<5.0	<10	9.15	<0.5	64	2.17	<100	<1	0.18	0.08	900
MJVD-8-67	0.4	5.25	0.74	34	<10	<5.0	<10	14.60	0.5	51	1.36	<100	<1	0.22	3.01	1,775
MJVD-8-68	0.4	3.52	0.12	10	<10	<5.0	<10	>15.00	0.5	4	0.32	<100	<1	0.05	4.93	1,680
MJVD-8-69	2.6	12.00	0.16	54	530	<5.0	<10	>15.00	1.5	6	0.60	<100	<1	0.08	0.21	2,670
MJVD-8-70	1.8	8.61	0.14	138	590	<5.0	<10	>15.00	3.0	3	0.29	<100	<1	0.07	0.11	2,300
MJVD-8-71	3.0	7.41	0.14	86	570	<5.0	<10	>15.00	2.0	3	0.48	<100	<1	0.07	0.09	3,210
MJVD-8-72	1.4	6.90	0.11	80	300	<5.0	<10	>15.00	1.5	6	0.55	<100	<1	0.06	0.08	3,000
MJVD-8-73	0.2	2.01	0.12	24	<10	<5.0	<10	>15.00	0.5	<1	0.24	<100	<1	0.01	0.10	2,280
MJVD-8-74	0.7	8.23	0.36	80	<10	<5.0	<10	>15.00	1.0	8	0.61	<100	<1	0.07	0.09	3,500
MJVD-8-75	0.4	5.15	0.15	40	<10	<5.0	<10	>15.00	0.5	3	0.37	<100	<1	0.04	0.10	2,580
MJVD-8-76	0.8	7.50	0.11	78	210	<5.0	<10	>15.00	1.5	<1	0.37	<100	<1	0.05	0.08	2,800
MJVD-8-77	0.5	5.32	0.09	44	70	<5.0	<10	>15.00	1.5	2	0.37	<100	<1	0.04	0.11	3,080
MJVD-8-78	1.0	9.61	0.10	56	210	<5.0	<10	>15.00	1.5	1	0.27	<100	<1	0.05	0.10	3,140
MJVD-8-79	0.6	14.80	0.12	68	50	<5.0	<10	>15.00	0.5	13	1.32	<100	<1	0.05	0.12	3,380
MJVD-8-80	0.7	6.82	0.10	124	180	<5.0	<10	>15.00	1.0	1	0.39	<100	<1	0.04	0.56	2,720
MJVD-8-81	0.6	5.10	0.19	58	90	<5.0	<10	>15.00	1.5	3	0.34	<100	<1	0.06	0.65	3,270
MJVD-8-82	0.6	5.56	0.14	80	130	<5.0	<10	>15.00	2.0	1	0.42	<100	<1	0.06	0.50	3,280
MJVD-8-83	0.3	7.23	0.04	30	60	<5.0	<10	>15.00	2.0	<1	0.32	<100	<1	0.02	0.12	3,260
MJVD-8-84	0.4	11.25	0.05	50	70	<5.0	<10	>15.00	1.5	1	0.41	<100	<1	0.02	0.10	2,590
MJVD-8-85	0.2	5.76	0.04	38	10	<5.0	<10	>15.00	2.0	<1	0.34	<100	<1	0.01	0.13	3,070
MJVD-8-86	0.9	36.60	0.49	70	<10	<5.0	<10	7.16	0.5	22	2.13	<100	<1	0.10	0.05	3,100
MJVD-8-87	1.0	36.70	0.41	66	<10	<5.0	<10	7.80	0.5	18	1.92	<100	<1	0.08	0.05	2,810
MJVD-8-88	0.4	8.17	0.64	48	<10	<5.0	<10	>15.00	3.0	36	0.91	<100	<1	0.08	0.24	3,850
MJVD-8-90	0.2	18.80	0.04	32	20	<5.0	<10	>15.00	4.0	2	0.35	<100	<1	0.01	0.04	2,340
MJVD-8-91	0.3	5.75	0.03	10	50	<5.0	<10	>15.00	0.5	<1	0.14	<100	<1	0.01	0.08	1,750
MJVD-8-92	0.3	4.06	0.05	20	120	<5.0	<10	>15.00	1.0	<1	0.30	<100	1	0.02	0.07	2,620
MJVD-8-93	0.4	7.31	0.13	58	<10	<5.0	<10	>15.00	1.0	2	0.44	<100	<1	0.03	0.07	3,240
MJVD-8-94	0.8	4.26	0.08	200	310	<5.0	<10	>15.00	1.5	<1	0.19	<100	<1	0.04	0.07	3,100
MJVD-8-95	0.2	9.56	0.04	38	30	<5.0	<10	>15.00	3.5	3	0.43	<100	<1	0.01	0.06	3,720
MJVD-8-96	1.0	16.20	0.32	396	130	<5.0	<10	>15.00	2.5	5	0.54	<100	1	0.11	0.05	3,430
MJVD-8-97	0.9	33.70	0.35	132	40	<5.0	<10	9.87	0.5	17	1.39	<100	1	0.10	0.05	2,770
MJVD-8-98	0.7	8.82	0.14	164	160	<5.0	<10	>15.00	1.5	<1	0.22	<100	<1	0.05	0.06	3,180
MJVD-8-99	0.6	6.47	0.13	146	60	<5.0	<10	>15.00	1.5	3	0.42	<100	<1	0.04	0.07	3,140
MJVD-8-100	0.72	10.55	0	276	250	<5.0	<10	>15.00	1.5	<1	0.18	<100	<1	0	0.04	3,180

MJVD-8 (57/126)

Sample Name	Mo	Na	P	S	Sb	Sc	Ti	Ce	Cs	Co	Cu	Dy	Er	Eu	Gd	Hf
	ppm	%	ppm	%	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-8-01	17	<0.01	1,940	0.05	34	<20	0.01	9,510	3.9	26.5	140	24.5	14.7	<200	50	5
MJVD-8-02	11	<0.01	1,500	0.04	52	<20	0.01	7,920	1.6	19.5	120	23.2	14.3	<300	53	2
MJVD-8-03	10	<0.01	930	0.04	54	<20	0.01	8,160	1.8	14.0	100	21.4	14.4	<300	35	3
MJVD-8-04	12	<0.01	1,680	0.04	70	<20	0.02	8,020	1.4	22.0	155	34.7	21.7	<300	82	2
MJVD-8-05	9	<0.01	1,410	0.04	44	<20	0.01	6,480	1.2	17.0	75	29.4	18.2	<300	73	2
MJVD-8-06	11	<0.01	1,710	0.03	40	<20	0.01	8,160	1.2	14.5	80	39.0	23.7	<400	97	2
MJVD-8-07	11	<0.01	3,690	0.03	34	<20	0.01	7,640	1.3	11.0	75	70.3	40.2	<350	190	2
MJVD-8-08	8	<0.01	4,520	0.03	30	<20	<0.01	10,180	1.2	12.0	120	85.9	54.5	<350	262	2
MJVD-8-09	10	<0.01	4,060	0.02	68	<20	0.01	9,200	1.7	15.5	225	86.3	51.6	<350	238	2
MJVD-8-10	21	<0.01	3,870	0.03	32	<20	0.01	8,590	3.4	18.5	190	96.3	61.3	<250	251	2
MJVD-8-11	12	<0.01	2,560	0.03	56	<20	0.03	7,760	2	25.5	135	57.7	37.4	<300	165	2
MJVD-8-12	8	<0.01	3,500	0.04	34	<20	0.01	8,580	1.6	32.0	115	84.7	54.7	<400	215	2
MJVD-8-13	32	<0.01	1,630	0.02	42	<20	0.01	26,700	0.4	6.5	85	115.0	75.2	<400	428	2
MJVD-8-14	11	<0.01	1,320	0.04	22	<20	<0.01	3,820	1.2	10.0	70	30.1	17.8	<400	83	2
MJVD-8-15	8	<0.01	1,130	0.04	20	<20	<0.01	6,620	1.1	5.5	110	29.6	18.0	<400	87	1
MJVD-8-16	27	<0.01	1,820	0.04	32	<20	<0.01	20,500	1.1	7.5	165	67.9	39.4	<400	223	2
MJVD-8-17	8	<0.01	390	0.04	16	<20	<0.01	3,450	0.7	3.0	60	13.8	9.1	<400	42	2
MJVD-8-19	4	<0.01	270	0.05	14	<20	<0.01	1,520	0.3	2.5	45	7.8	5.1	<400	25	4
MJVD-8-20	6	<0.01	590	0.04	28	<20	<0.01	2,000	0.3	2.5	50	20.4	11.1	<400	63	4
MJVD-8-21	5	0.22	520	0.06	16	<20	0.01	3,890	0.8	3.0	25	17.8	11.3	<400	60	3
MJVD-8-22	11	0.05	1,030	0.04	50	<20	0.02	4,610	0.7	9.0	55	27.5	16.4	<400	85	4
MJVD-8-23	9	<0.01	780	0.04	50	<20	0.01	4,290	1.1	5.0	55	24.1	14.0	<400	71	2
MJVD-8-24	18	<0.01	1,910	0.04	84	<20	<0.01	15,020	0.9	12.5	210	76.6	47.4	<400	290	2
MJVD-8-25	33	<0.01	3,020	0.03	134	<20	<0.01	15,130	1.3	15.5	360	126.0	82.8	<300	423	1
MJVD-8-26	15	<0.01	1,830	0.04	48	<20	<0.01	12,500	1.3	12.5	155	106.5	64.0	<300	337	2
MJVD-8-27	8	0.01	1,060	0.05	28	<20	<0.01	12,840	0.2	4.0	120	74.2	46.7	<300	287	3
MJVD-8-28	7	0.01	1,040	0.05	24	<20	<0.01	17,780	0.3	4.5	80	88.0	56.8	<300	368	3
MJVD-8-29	9	0.01	990	0.05	16	<20	<0.01	22,300	0.2	2.0	110	72.0	49.9	<300	378	2
MJVD-8-30	7	0.01	1,830	0.05	32	<20	<0.01	22,600	0.3	3.5	70	67.7	49.4	<300	354	3
MJVD-8-31	9	0.01	2,330	0.04	32	<20	<0.01	24,900	0.1	3.0	100	59.2	44.7	<300	303	3
MJVD-8-32	6	0.01	2,380	0.04	24	<20	<0.01	25,100	0.1	2.5	60	38.3	23.0	<300	121	2
MJVD-8-33	4	0.01	2,450	0.05	26	<20	<0.01	20,800	0.3	2.5	65	34.7	22.4	<300	119	2
MJVD-8-34	6	<0.01	2,860	0.04	30	<20	<0.01	31,900	0.2	2.5	110	35.4	21.5	<300	123	2
MJVD-8-35	8	0.01	980	0.05	14	<20	<0.01	27,500	0.5	2.0	35	33.8	26.9	<300	167	2
MJVD-8-36	8	0.01	590	0.05	12	<20	<0.01	54,900	0.2	1.0	50	73.5	60.0	<300	398	2
MJVD-8-37	10	<0.01	1,000	0.04	38	<20	0.01	31,700	0.2	4.5	85	24.9	14.7	<300	62	2
MJVD-8-38	17	<0.01	810	0.04	34	<20	0.01	31,400	0.2	1.5	50	28.3	18.8	<300	100	2
MJVD-8-39	12	<0.01	1,720	0.05	54	<20	0.02	23,000	0.3	4.5	75	119.5	71.8	<300	469	4
MJVD-8-40	10	0.01	1,110	0.05	26	<20	<0.01	6,910	1.3	46.5	55	28.1	16.9	<300	76	2
MJVD-8-41	58	0.01	1,670	0.03	34	<20	0.01	26,300	0.4	4.0	90	143.0	86.1	<300	590	3
MJVD-8-42	65	0.03	1,650	0.03	78	<20	0.01	35,200	0.2	8.5	160	144.5	99.2	<300	627	3
MJVD-8-43	213	0.01	3,340	0.03	102	<20	0.01	29,300	0.4	9.0	230	131.0	83.5	<300	523	3
MJVD-8-44	445	0.01	5,270	0.02	142	<20	0.01	30,700	0.3	10.0	350	229.0	124.0	350	767	6
MJVD-8-45	214	0.01	2,940	0.03	88	<20	0.01	20,700	0.3	7.0	175	155.5	91.9	<400	598	4
MJVD-8-46	137	0.04	2,530	0.03	80	<20	0.01	18,040	0.3	6.5	165	170.0	93.6	<400	646	3
MJVD-8-47	110	0.15	2,060	0.04	44	<20	0.01	15,600	0.5	5.0	135	118.5	71.2	<400	413	3
MJVD-8-48	149	0.09	3,960	0.04	66	<20	0.01	20,400	0.2	5.0	135	193.0	115.5	<400	479	3
MJVD-8-49	140	0.01	2,270	0.03	48	<20	0.01	14,070	0.4	5.5	105	138.5	82.0	<400	378	4
MJVD-8-50	116	0.01	2,390	0.02	58	<20	0.01	18,870	0.7	8.5	120	187.5	115.0	<400	581	3
MJVD-8-51	78	0.01	1,730	0.03	42	<20	0.01	18,520	0.8	6.5	85	115.5	71.6	<400	394	3
MJVD-8-52	45	0.01	2,610	0.03	58	<20	0.01	13,150	0.3	6.5	110	115.5	64.9	<400	398	3
MJVD-8-53	44	0.01	2,870	0.03	54	<20	0.01	18,360	0.4	8.5	125	168.0	93.8	<400	602	3
MJVD-8-54	40	0.01	2,290	0.03	38	<20	0.01	15,670	0.3	5.5	85	256.0	139.0	400	1,010	4
MJVD-8-55	39	0.01	2,110	0.02	44	<20	0.01	26,800	0.3	10.5	110	195.5	112.5	300	726	3
MJVD-8-56	22	0.02	1,180	0.03	18	<20	<0.01	44,900	0.2	3.5	40	174.5	117.0	<400	690	2
MJVD-8-57	18	0.04	2,810	0.05	48	<20	0.02	38,300	2.3	9.0	190	120.5	87.5	<400	503	5
MJVD-8-58	21	0.04	2,750	0.04	34	<20	0.01	34,000	1.2	8.5	120	140.0	92.0	<400	500	3

MJVD-8 (58/126)

Sample Name	Mo ppm	Na %	P ppm	S %	Sb ppm	Sc ppm	Ti %	Ce ppm	Cs ppm	Co ppm	Cu ppm	Dy ppm	Er ppm	Eu ppm	Gd ppm	Hf ppm
MJVD-8-59	12	0.17	2,490	0.05	20	<20	0.08	22,500	5.4	16.5	90	61.2	46.3	<150.0	264	4
MJVD-8-60	2	0.01	2,570	0.05	<2	<20	0.18	878	5	25.0	45	8.2	5.3	<10.0	20	4
MJVD-8-61	5	0.01	2,680	0.04	2	<20	0.14	1,030	6.7	26.5	40	7.6	6.2	<10.0	22	4
MJVD-8-62	<1	0.01	2,740	0.04	<2	<20	0.18	486	4.9	26.0	40	4.5	3.5	4.8	12	4
MJVD-8-63	3	0.01	2,950	0.05	2	<20	0.2	628	5.9	29.0	45	5.2	4.2	<10.0	12	4
MJVD-8-64	<1	0.01	2,820	0.04	<2	<20	0.19	415	5.7	27.0	50	4.7	3.5	4.4	9	4
MJVD-8-65	<1	0.01	2,270	0.06	4	<20	<0.01	433	8.5	21.5	45	4.9	4.0	<10.0	12	4
MJVD-8-66	<1	<0.01	2,220	0.06	<2	<20	<0.01	312	9.1	21.5	30	3.2	2.6	<10.0	8	3
MJVD-8-67	<1	<0.01	1,110	0.05	2	<20	<0.01	1,805	4.4	13.0	30	9.2	6.2	<50.0	28	2
MJVD-8-68	<1	0.01	650	0.05	4	<20	<0.01	910	0.3	1.5	10	8.9	6.2	<50.0	23	<1
MJVD-8-69	<1	0.10	1,060	0.06	16	<20	<0.01	4,140	0.1	2.0	30	19.0	11.8	<100.0	65	<1
MJVD-8-70	<1	0.11	290	0.07	10	<20	<0.01	10,740	0.1	1.0	25	29.6	22.0	<100.0	123	2
MJVD-8-71	<1	0.10	680	0.07	10	<20	<0.01	7,460	0.1	2.0	30	33.1	21.0	<100.0	114	1
MJVD-8-72	<1	0.07	760	0.06	12	<20	<0.01	6,340	0.3	2.5	35	23.9	16.2	<100.0	86	<1
MJVD-8-73	<1	0.01	390	0.05	4	<20	<0.01	1,925	0.2	1.0	15	12.9	8.0	<100.0	34	<1
MJVD-8-74	6	0.02	420	0.04	18	<20	<0.01	6,930	0.5	3.5	30	27.8	18.5	<100.0	101	1
MJVD-8-75	<1	0.01	550	0.05	12	<20	<0.01	3,610	0.5	2.0	30	18.7	12.2	<100.0	61	<1
MJVD-8-76	<1	0.05	1,420	0.04	20	<20	<0.01	7,210	0.1	2.0	45	27.5	18.5	<100.0	97	<1
MJVD-8-77	<1	0.03	1,130	0.05	14	<20	<0.01	3,830	0.1	1.5	30	26.0	17.0	<100.0	76	<1
MJVD-8-78	<1	0.05	1,500	0.05	12	<20	<0.01	5,680	0.1	2.5	35	30.9	18.9	<100.0	93	<1
MJVD-8-79	<1	0.01	310	0.04	34	<20	<0.01	3,330	0.1	3.5	50	29.2	17.1	<100.0	84	1
MJVD-8-80	1	0.04	880	0.04	12	<20	<0.01	11,040	0.2	3.0	20	32.9	24.7	<100.0	141	<1
MJVD-8-81	<1	0.03	240	0.05	14	<20	<0.01	3,710	0.2	2.5	45	28.0	17.1	<50.0	79	<1
MJVD-8-82	<1	0.04	210	0.05	14	<20	<0.01	6,330	0.2	1.5	40	33.7	22.4	<50.0	104	<1
MJVD-8-83	<1	0.02	460	0.05	12	<20	<0.01	2,020	0.1	1.0	40	20.6	12.5	<50.0	53	<1
MJVD-8-84	<1	0.03	1,140	0.05	6	<20	<0.01	3,260	0.1	1.0	35	18.7	13.6	100	59	<1
MJVD-8-85	<1	0.01	970	0.05	10	<20	<0.01	2,930	<0.1	1.0	45	24.7	14.2	<50.0	67	<1
MJVD-8-86	13	0.01	720	0.04	16	<20	<0.01	3,600	0.5	5.0	55	21.3	14.0	<400	72	2
MJVD-8-87	11	0.01	660	0.04	16	<20	<0.01	3,550	0.5	5.5	50	19.5	12.8	<400	66	2
MJVD-8-88	<1	0.01	1,160	0.05	12	<20	0.02	3,120	1.2	5.0	55	22.8	15.1	<80.0	67	<1
MJVD-8-90	<1	0.01	970	0.05	26	<20	<0.01	2,010	<0.1	3.0	70	16.6	10.3	<200	45	<1
MJVD-8-91	<1	0.02	230	0.04	6	<20	<0.01	828	<0.1	1.0	20	10.3	6.6	<50.0	24	<1
MJVD-8-92	<1	0.04	590	0.05	8	<20	<0.01	1,325	0.1	1.5	5	16.5	9.4	<50.0	43	<1
MJVD-8-93	<1	0.01	510	0.04	8	<20	<0.01	4,800	0.2	1.5	35	28.6	18.9	<50.0	88	5
MJVD-8-94	<1	0.07	830	0.05	10	<20	<0.01	17,960	<0.1	1.5	35	38.3	31.0	80	216	<1
MJVD-8-95	<1	0.02	1,350	0.05	26	<20	<0.01	2,400	<0.1	1.0	55	27.2	16.1	<100.0	67	<1
MJVD-8-96	8	0.04	600	0.04	14	<20	<0.01	37,700	0.3	1.5	45	63.8	59.1	150	418	1
MJVD-8-97	11	0.02	760	0.04	22	<20	<0.01	9,110	0.4	4.0	55	26.8	21.2	<350	127	1
MJVD-8-98	<1	0.04	360	0.04	8	<20	<0.01	14,380	0.2	3.0	30	31.5	26.2	<100.0	162	<1
MJVD-8-99	1	0.03	1,300	0.05	12	<20	<0.01	13,650	0.2	1.0	55	32.9	27.4	50	164	1
MJVD-8-100	1	0.05	280	0.04	6	<20	<0.01	25,100	0.1	1	30	43.4	41	100	269	<1

MJVD-8 (59/126)

Sample Name	Ho	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-8-01	4.7	2,340	2,030	0.7	690	20	335	233	41.0	156	<1	1,995	1.0	7.5	5.5	150
MJVD-8-02	4.4	2,160	2,680	0.7	811	20	243	259	23.4	218	<1	2,570	0.5	7.3	4.0	133
MJVD-8-03	4.1	1,215	3,150	0.8	474	25	344	153	42.0	183	<1	2,750	1.0	5.9	6.5	150
MJVD-8-04	6.6	2,930	3,460	0.9	1,245	20	421	395	32.2	271	<1	2,680	1.5	10.7	5.0	115
MJVD-8-05	5.4	2,520	2,440	0.8	1,095	25	218	348	35.0	283	<1	3,200	0.5	9.4	4.0	96
MJVD-8-06	6.9	2,620	2,800	1.0	1,445	40	244	427	37.0	337	<1	2,980	1.0	12.1	5.5	152
MJVD-8-07	13.1	6,310	2,140	1.4	2,730	40	160	845	33.8	465	<1	3,130	<0.5	21.1	4.5	100
MJVD-8-08	16.5	7,030	2,140	2.0	4,110	20	266	1,165	27.4	624	<1	3,770	1.5	28.4	6.0	102
MJVD-8-09	15.4	6,940	2,950	2.0	3,390	20	316	1,000	33.2	551	<1	3,950	2.5	26.8	6.0	64
MJVD-8-10	19.1	6,690	2,430	2.6	3,470	90	214	1,045	65.6	542	<1	2,670	<0.5	29.1	9.5	71
MJVD-8-11	11.6	5,620	3,160	1.4	2,510	45	243	791	40.0	414	<1	2,790	0.5	19.0	5.5	109
MJVD-8-12	16.8	6,210	2,770	2.2	3,010	30	183	902	33.0	538	<1	2,800	0.5	26.7	5.5	80
MJVD-8-13	19.5	25,500	3,370	2.1	8,320	10	176	2,650	9.0	956	<1	3,510	0.5	47.8	3.5	67
MJVD-8-14	5.5	2,390	1,550	0.9	1,375	20	221	432	37.8	358	<1	4,580	1.0	9.7	3.0	41
MJVD-8-15	4.9	2,450	2,230	0.7	1,280	10	104	393	55.4	361	<1	5,850	<0.5	10.4	2.5	98
MJVD-8-16	11.2	7,340	3,300	1.5	3,820	50	391	1,155	54.0	626	<1	3,570	0.5	26.2	6.0	275
MJVD-8-17	2.7	1,410	675	0.5	747	20	51	228	17.8	317	<1	4,790	2.0	5.1	1.0	47
MJVD-8-19	1.6	737	675	0.3	383	<5	13	116	8.8	280	<1	8,230	1.0	2.9	<0.5	15
MJVD-8-20	3.7	1,640	480	0.6	939	<5	27	270	7.2	347	<1	8,820	2.0	6.9	0.5	11
MJVD-8-21	3.0	2,560	650	0.3	1,040	<5	36	323	11.4	258	<1	7,780	0.5	7.0	<0.5	21
MJVD-8-22	4.6	3,090	2,780	0.7	1,350	10	74	420	13.6	317	<1	7,430	1.0	9.4	1.5	26
MJVD-8-23	4.1	2,440	2,010	0.7	1,100	10	50	327	9.4	303	<1	7,950	0.5	8.0	1.5	27
MJVD-8-24	12.6	10,950	4,160	1.4	5,290	35	269	1,555	19.4	725	<1	4,860	0.5	31.6	5.0	74
MJVD-8-25	22.1	11,430	5,590	2.7	7,130	40	364	1,950	31.0	952	<1	3,830	<0.5	45.8	11.0	90
MJVD-8-26	19.5	12,970	2,610	2.3	5,690	35	236	1,705	27.2	813	<1	4,850	2.0	37.3	6.0	71
MJVD-8-27	11.5	17,720	2,750	1.2	5,760	<5	31	1,830	6.8	787	<1	5,510	2.0	31.3	2.5	59
MJVD-8-28	13.9	20,700	2,350	1.3	7,150	<5	44	2,220	6.4	910	<1	4,570	1.0	38.7	1.5	56
MJVD-8-29	10.4	19,680	2,740	1.1	7,900	5	51	2,460	3.6	1,020	<1	3,920	1.0	38.8	4.5	64
MJVD-8-30	10.0	17,940	3,330	1.1	7,320	<5	142	2,300	6.0	914	<1	4,410	2.5	36.9	1.5	294
MJVD-8-31	9.5	16,730	4,180	0.9	6,670	<5	294	2,120	6.6	861	<1	3,910	4.0	33.1	3.0	83
MJVD-8-32	6.6	4,170	3,270	0.9	2,070	<5	157	632	4.2	423	<1	4,110	1.5	17.2	3.5	91
MJVD-8-33	6.3	4,980	3,420	0.8	1,990	5	192	625	6.6	425	<1	3,490	3.5	15.8	2.0	68
MJVD-8-34	5.9	4,470	3,950	0.9	2,130	<5	258	661	4.4	473	<1	3,790	3.5	17.2	3.0	101
MJVD-8-35	5.6	9,430	2,340	0.7	3,940	<5	71	1,290	13.6	536	<1	4,860	0.5	19.2	1.0	87
MJVD-8-36	11.7	26,200	4,650	1.2	10,320	<5	43	3,330	8.0	1,085	<1	4,170	0.5	49.0	1.5	117
MJVD-8-37	4.7	1,770	4,800	0.7	944	5	232	288	4.4	322	<1	4,710	<0.5	12.3	2.0	72
MJVD-8-38	4.9	5,480	3,870	0.6	2,030	<5	179	673	2.2	382	<1	5,200	<0.5	14.9	1.0	48
MJVD-8-39	19.3	24,400	3,750	2.0	8,330	<5	251	2,590	3.6	975	<1	3,760	0.5	49.4	1.0	63
MJVD-8-40	5.2	2,300	2,650	0.8	1,150	15	212	370	27.8	334	<1	4,190	0.5	9.9	3.5	51
MJVD-8-41	22.4	30,300	6,130	2.1	10,950	<5	191	3,430	4.0	1,290	1	4,210	1.5	60.2	3.5	50
MJVD-8-42	22.7	38,300	>10,000	2.4	12,660	10	434	3,970	2.6	1,365	1	3,810	1.5	65.8	4.5	56
MJVD-8-43	22.2	25,900	>10,000	2.3	9,350	5	484	2,900	6.2	1,120	1	3,040	2.0	55.3	6.0	59
MJVD-8-44	37.9	30,800	>10,000	3.9	11,850	<5	535	3,600	2.8	1,510	1	3,110	2.0	80.4	6.0	103
MJVD-8-45	25.1	23,900	>10,000	2.5	9,710	<5	325	2,810	2.8	1,315	2	4,010	1.5	61.3	2.5	86
MJVD-8-46	27.1	24,500	6,020	2.6	10,220	<5	333	2,990	6.0	1,355	1	4,650	1.5	65.6	2.0	68
MJVD-8-47	21.0	13,520	3,440	2.3	6,570	<5	236	1,920	13.4	882	1	4,540	1.0	43.3	2.5	67
MJVD-8-48	38.8	12,090	3,580	4.4	6,210	5	282	1,785	1.8	925	1	4,660	1.5	55.7	2.0	81
MJVD-8-49	27.3	12,120	4,260	3.0	5,030	<5	212	1,505	5.8	739	2	4,240	<0.5	42.4	1.5	55
MJVD-8-50	36.5	21,700	5,490	3.8	7,790	5	312	2,300	13.8	1,030	1	3,650	0.5	62.2	2.0	69
MJVD-8-51	21.7	16,400	3,980	2.6	5,910	<5	262	1,765	16.8	798	<1	3,580	1.0	41.2	1.5	64
MJVD-8-52	20.6	12,640	4,830	2.1	5,590	<5	268	1,605	3.2	787	<1	3,840	1.5	41.2	1.5	49
MJVD-8-53	27.9	23,200	5,200	2.7	8,780	<5	333	2,560	6.0	1,130	1	3,360	2.0	61.9	2.5	60
MJVD-8-54	40.9	40,000	5,170	3.4	14,850	<5	366	4,380	6.6	1,850	<1	3,750	2.5	98.7	1.5	69
MJVD-8-55	31.8	29,000	4,790	3.2	10,870	5	366	3,160	6.8	1,345	<1	3,640	2.0	71.9	2.5	70
MJVD-8-56	32.0	36,200	2,700	3.5	11,500	<5	162	3,560	5.0	1,315	<1	3,870	1.5	69.9	1.0	78
MJVD-8-57	22.0	27,200	4,130	2.2	9,420	10	236	2,970	34.4	1,065	1	3,690	3.0	52.5	3.0	69
MJVD-8-58	26.3	24,200	3,660	3.0	8,580	5	365	2,640	31.0	1,005	<1	3,730	2.5	54.0	2.0	57

MJVD-8 (60/126)

Sample Name	Ho	La	Pb	Lu	Nd	Ni	Nb	Pr	Rb	Sm	Ag	Sr	Ta	Tb	Tl	Th
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-8-59	11.0	13,360	1,970	1.1	5,440	20	104	1,725	123.0	549	<1	2,680	<0.5	29.0	2.5	52
MJVD-8-60	1.5	658	185	0.4	288	30	11	84	203.0	39	<1	1,170	<0.5	2.2	3.0	16
MJVD-8-61	1.5	696	240	0.4	301	30	19	92	261.0	43	<1	1,220	<0.5	2.2	5.0	21
MJVD-8-62	1.1	299	110	0.2	145	40	5	43	261.0	20	<1	1,000	<0.5	1.3	4.0	17
MJVD-8-63	1.1	302	85	0.2	146	45	8	42	247.0	25	<1	1,190	<0.5	1.3	3.5	22
MJVD-8-64	1.0	215	55	0.2	110	45	13	31	240.0	19	<1	1,160	<0.5	1.2	3.0	18
MJVD-8-65	1.3	296	75	0.3	142	25	18	42	133.0	23	<1	1,060	<0.5	1.4	2.5	19
MJVD-8-66	0.6	169	130	0.2	94	35	36	25	122.5	22	<1	648	<0.5	0.9	3.5	16
MJVD-8-67	1.7	1,160	505	0.2	481	20	50	151	59.6	70	<1	2,780	<0.5	3.1	1.5	14
MJVD-8-68	1.6	492	295	0.2	282	<5	50	78	6.0	51	<1	3,700	<0.5	2.7	<0.5	1
MJVD-8-69	3.8	2,780	925	0.5	1,115	<5	161	347	3.0	167	<1	3,890	<0.5	7.4	0.5	6
MJVD-8-70	5.2	7,970	1,225	0.5	2,480	<5	26	847	2.0	253	<1	3,060	<0.5	13.7	<0.5	25
MJVD-8-71	6.2	5,160	1,145	0.5	1,915	<5	64	613	2.8	238	<1	3,820	<0.5	12.5	0.5	29
MJVD-8-72	4.3	4,490	1,230	0.6	1,510	<5	150	495	3.2	168	<1	3,560	<0.5	9.6	<0.5	13
MJVD-8-73	2.8	1,245	475	0.3	483	<5	18	152	2.8	63	<1	2,960	<0.5	3.6	<0.5	3
MJVD-8-74	4.8	4,990	1,200	0.7	1,845	<5	40	578	10.6	207	<1	3,160	<0.5	11.3	<0.5	12
MJVD-8-75	3.4	2,570	880	0.5	979	<5	21	311	6.4	125	<1	3,380	<0.5	6.7	<0.5	4
MJVD-8-76	4.9	4,970	890	0.5	1,860	<5	106	600	2.2	203	<1	4,690	<0.5	10.9	<0.5	11
MJVD-8-77	5.1	2,380	860	0.7	1,090	<5	118	328	3.4	154	<1	4,060	<0.5	8.7	0.5	5
MJVD-8-78	5.3	3,670	825	0.7	1,520	<5	244	482	2.8	208	<1	4,490	<0.5	10.5	0.5	6
MJVD-8-79	5.5	2,050	1,665	0.6	1,015	<5	169	294	5.4	200	<1	4,060	<0.5	8.7	1.0	5
MJVD-8-80	5.7	7,840	1,340	0.7	2,850	<5	78	920	3.4	295	<1	2,580	<0.5	15.3	0.5	20
MJVD-8-81	5.1	2,640	1,155	0.6	1,050	<5	113	354	5.8	151	<1	2,810	<0.5	9.0	<0.5	13
MJVD-8-82	6.1	4,700	1,145	0.8	1,720	<5	107	574	6.0	205	<1	3,800	<0.5	11.9	<0.5	13
MJVD-8-83	4.1	1,400	1,010	0.5	610	<5	86	191	1.6	114	<1	3,530	<0.5	6.2	<0.5	6
MJVD-8-84	3.3	2,390	770	0.5	916	<5	206	303	1.8	154	<1	4,530	<0.5	6.8	<0.5	6
MJVD-8-85	4.5	2,120	1,055	0.5	847	<5	81	272	1.8	137	<1	4,110	<0.5	7.7	<0.5	5
MJVD-8-86	3.9	3,150	750	0.6	1,105	<5	57	369	13.8	295	<1	5,310	1.0	8	<0.5	15
MJVD-8-87	3.5	3,030	450	0.6	1,060	<5	57	356	10.2	296	<1	5,390	1.5	7.4	<0.5	14
MJVD-8-88	4.3	2,170	860	0.5	926	5	52	297	32.2	150	<1	3,760	<0.5	7.5	0.5	10
MJVD-8-90	3.3	1,460	1,410	0.5	598	<5	67	193	1.4	162	<1	4,860	0.5	5.3	<0.5	3
MJVD-8-91	2.0	542	330	0.2	278	<5	24	84	1.0	65	<1	3,040	<0.5	2.6	<0.5	1
MJVD-8-92	3.2	814	780	0.4	461	<5	116	135	1.8	82	<1	3,080	<0.5	5	0.5	4
MJVD-8-93	5.1	3,530	725	0.6	1,400	<5	67	457	4.0	190	<1	3,100	<0.5	10.2	0.5	13
MJVD-8-94	6.4	13,380	1,120	0.6	4,450	<5	275	1,560	1.6	410	<1	3,950	<0.5	23.5	<0.5	124
MJVD-8-95	5.4	1,680	2,340	0.7	742	<5	197	236	1.2	150	<1	3,740	<0.5	7.9	0.5	6
MJVD-8-96	10.1	28,500	1,215	0.9	9,180	<5	61	3,200	8.0	833	<1	3,360	<0.5	44.1	0.5	56
MJVD-8-97	5.0	7,260	970	0.6	2,440	<5	65	856	10.0	383	<1	5,330	1.0	14.4	0.5	22
MJVD-8-98	5.4	10,010	885	0.6	3,440	<5	21	1,215	4.4	338	<1	3,420	<0.5	18	<0.5	20
MJVD-8-99	5.6	9,260	805	0.7	3,460	<5	46	1,165	4.0	333	<1	3,390	<0.5	18.2	<0.5	21
MJVD-8-100	7.1	18,670	420	0.9	6,140	<5	41	2,140	1	572	<1	3,180	<0.5	28.8	<0.5	33

MJVD-8 (61/126)

Sample Name	Tm	Sn	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-8-01	1.3	15	198	58.0	355	5.5	115	860	214
MJVD-8-02	1.1	6	138	53.5	255	5.0	108.5	925	70
MJVD-8-03	1.2	4	116	63.5	255	5.7	87.8	1,195	78
MJVD-8-04	1.6	2	173	80.5	255	7.0	152	1,225	65
MJVD-8-05	1.3	2	105	60.5	210	5.3	135	900	52
MJVD-8-06	1.8	6	141	69.5	250	7.3	159	1,165	50
MJVD-8-07	2.8	4	68	65.5	200	12.9	363	935	44
MJVD-8-08	3.6	5	47	80.5	280	14.9	473	1,070	28
MJVD-8-09	4.0	10	92	86.5	330	16.8	429	1,310	46
MJVD-8-10	4.8	3	97	91.0	305	21.8	548	1,350	71
MJVD-8-11	2.6	1	186	69.0	295	10.8	279	1,105	101
MJVD-8-12	3.9	2	119	77.0	390	18.2	607	1,165	42
MJVD-8-13	3.9	4	32	87.5	205	17.4	461	490	19
MJVD-8-14	1.1	1	33	70.5	140	6.3	129	660	13
MJVD-8-15	1.1	1	29	38.0	110	6.7	107	355	19
MJVD-8-16	2.5	22	58	96.5	280	11.6	221	815	16
MJVD-8-17	0.6	<1	24	19.0	120	3.2	53.1	360	2
MJVD-8-19	0.4	<1	10	9.5	90	2.3	42.3	205	<0.5
MJVD-8-20	0.9	<1	22	11.5	45	4.2	89.6	235	18
MJVD-8-21	0.7	2	39	17.0	30	3.5	128.5	360	51
MJVD-8-22	1.2	<1	164	28.5	80	5.0	136	415	55
MJVD-8-23	1.1	<1	116	21.0	30	4.8	113	295	19
MJVD-8-24	2.7	<1	57	110.5	235	14.0	268	1,290	11
MJVD-8-25	5.6	<1	59	176.0	350	25.7	502	2,080	13
MJVD-8-26	4.2	1	40	95.5	245	18.6	393	935	14
MJVD-8-27	2.2	<1	17	65.5	180	10.2	262	510	1
MJVD-8-28	2.3	5	16	72.0	155	12.1	296	425	6
MJVD-8-29	1.7	<1	21	64.0	70	9.4	207	450	2
MJVD-8-30	1.9	<1	19	70.0	85	8.8	203	410	11
MJVD-8-31	2.0	<1	40	86.0	100	9.4	204	480	20
MJVD-8-32	1.6	<1	6	71.5	30	7.4	140.5	420	4
MJVD-8-33	1.5	1	23	70.5	45	6.1	134	350	6
MJVD-8-34	1.2	3	27	94.5	75	6.6	128.5	440	8
MJVD-8-35	1.0	1	4	61.0	25	6.1	112	220	12
MJVD-8-36	2.1	<1	12	134.5	45	11.0	226	210	19
MJVD-8-37	1.2	<1	50	81.5	180	6.3	82.4	420	15
MJVD-8-38	1.2	<1	33	67.0	75	5.5	112	285	9
MJVD-8-39	3.6	1	72	79.0	100	18.5	470	555	58
MJVD-8-40	1.2	2	55	63.5	130	6.6	107.5	575	16
MJVD-8-41	4.1	<1	24	96.0	190	20.8	527	335	40
MJVD-8-42	4.4	1	42	135.5	255	21.2	520	730	101
MJVD-8-43	4.7	<1	40	185.5	285	21.5	509	895	88
MJVD-8-44	7.6	3	43	280.0	250	32.7	817	955	243
MJVD-8-45	4.8	2	30	133.0	200	22.2	553	565	110
MJVD-8-46	5.4	2	34	129.5	170	25.0	635	570	42
MJVD-8-47	4.3	<1	25	105.5	120	20.8	547	405	58
MJVD-8-48	9.1	<1	23	159.0	135	40.0	963	410	19
MJVD-8-49	5.9	1	28	128.0	90	24.7	745	410	40
MJVD-8-50	7.4	3	31	97.5	130	32.4	968	590	42
MJVD-8-51	4.9	2	35	92.0	105	20.4	561	500	44
MJVD-8-52	3.9	1	34	96.5	95	18.5	438	800	48
MJVD-8-53	5.6	<1	37	125.5	90	24.4	608	905	73
MJVD-8-54	6.7	<1	40	117.5	80	33.6	893	445	27
MJVD-8-55	6.8	<1	47	165.0	125	29.8	767	750	59
MJVD-8-56	6.7	2	23	152.5	45	32.3	877	335	13
MJVD-8-57	4.6	2	64	135.0	245	18.9	568	1,220	115
MJVD-8-58	5.8	1	36	127.5	140	24.5	619	640	73

MJVD-8 (62/126)

Sample Name	Tm	Sn	W	U	V	Yb	Y	Zn	Zr
	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm
MJVD-8-59	2.2	1	33	72.0	200	10.6	314	1,735	139
MJVD-8-60	0.4	1	16	11.0	115	2.7	45.5	330	150
MJVD-8-61	0.5	1	27	12.0	145	1.9	41.4	345	166
MJVD-8-62	0.3	1	10	7.5	175	0.9	26.6	55	167
MJVD-8-63	0.4	2	19	8.0	140	2.2	27.5	140	180
MJVD-8-64	0.4	1	21	7.0	145	2.1	28.4	275	189
MJVD-8-65	0.2	1	74	11.5	150	1.6	29.7	535	167
MJVD-8-66	0.2	1	71	18.0	125	1.4	21.2	255	169
MJVD-8-67	0.3	<1	34	19.5	80	2.1	41	350	66
MJVD-8-68	0.5	<1	8	19.0	15	2.0	46.8	245	6
MJVD-8-69	0.8	<1	19	46.0	20	3.9	97.2	440	16
MJVD-8-70	1.1	<1	17	37.5	45	5.2	154	235	71
MJVD-8-71	1.3	<1	19	36.0	25	5.6	158	325	16
MJVD-8-72	1.1	<1	13	56.5	20	5.1	115	350	18
MJVD-8-73	0.6	<1	8	11.0	15	2.7	64.4	75	25
MJVD-8-74	1.2	<1	19	28.0	35	5.2	128.5	185	19
MJVD-8-75	0.8	<1	10	17.0	25	3.5	85.1	135	23
MJVD-8-76	1.1	<1	10	44.5	20	5.3	120	220	9
MJVD-8-77	1.2	<1	9	40.0	35	5.8	123	270	8
MJVD-8-78	1.2	<1	14	66.5	15	6.3	138.5	250	7
MJVD-8-79	1.2	<1	31	43.0	15	6.7	128	440	5
MJVD-8-80	1.3	<1	33	44.0	5	5.2	142	265	15
MJVD-8-81	1.2	1	30	31.5	15	5.5	133	235	<0.5
MJVD-8-82	1.5	<1	25	37.5	<5	6.6	151	195	<0.5
MJVD-8-83	0.9	<1	17	21.0	<5	4.1	95.4	155	<0.5
MJVD-8-84	0.8	<1	19	51.5	15	3.8	88.7	170	<0.5
MJVD-8-85	1.1	<1	16	22.0	<5	4.9	113.5	125	<0.5
MJVD-8-86	0.9	3	16	24.0	40	4.3	108.5	255	4
MJVD-8-87	0.9	2	21	23.0	50	4.2	96.3	310	1
MJVD-8-88	1.1	<1	33	18.0	35	4.1	113.5	435	22
MJVD-8-90	0.9	<1	20	21.0	50	3.5	79.2	215	6
MJVD-8-91	0.5	<1	7	7.5	<5	2.4	54	45	<0.5
MJVD-8-92	0.8	2	11	25.0	10	3.2	85.5	230	21
MJVD-8-93	1.3	<1	13	25.5	45	5.1	126	195	251
MJVD-8-94	1.2	<1	13	99.0	40	6.0	141	150	<0.5
MJVD-8-95	1.3	<1	20	50.5	20	6.0	132	295	5
MJVD-8-96	1.9	<1	25	65.5	15	8.4	232	270	7
MJVD-8-97	1.0	<1	18	32.5	30	4.7	125	305	4
MJVD-8-98	1.2	<1	14	27.0	5	5.7	131	155	<0.5
MJVD-8-99	1.4	<1	16	32.0	35	5.2	138.5	205	93
MJVD-8-100	1.5	<1	14	44.0	20.0	6.7	165.0	115	4